

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
17 July 2003 (17.07.2003)

PCT

(10) International Publication Number
WO 03/057445 A1

(51) International Patent Classification⁷: B29C 43/22,
59/02, 37/00, B41M 5/00

GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ,
LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN,
MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD,
SE, SG, SI, SK (utility model), SK, SL, TJ, TM, TN, TR,
TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW.

(21) International Application Number: PCT/US02/35345

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK,
TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

(22) International Filing Date:
4 November 2002 (04.11.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/028,617 21 December 2001 (21.12.2001) US

(71) Applicant: 3M INNOVATIVE PROPERTIES COMPANY [US/US]; 3M Center, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(72) Inventors: BERG, Brandon, T.; Post Office Box 33427, Saint Paul, MN 55133-3427 (US). HOLLOBAUGH, Tony, B.; Post Office Box 33427, Saint Paul, MN 55133-3427 (US). NGUYEN, David, D.; Post Office Box 33427, Saint Paul, MN 55133-3427 (US). KOEHLER, Bruce, H.; Post Office Box 33427, Saint Paul, MN 55133-3427 (US). NERAD, Bruce, A.; Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(74) Agents: LITTLE, Douglas B., et al.; Office of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, MN 55133-3427 (US).

(81) Designated States (national): AE, AG, AL, AM, AT (utility model), AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ (utility model), CZ, DE (utility model), DE, DK (utility model), DK, DM, DZ, EC, EE (utility model), EE, ES, FI (utility model), FI, GB, GD, GE,

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii)) for the following designations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW, ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG)
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations

Published:

- with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 03/057445 A1

(54) Title: CONTINUOUS PROCESS FOR INDIRECT PRINTING OF POLYMERIC FILMS HAVING TEXTURE

(57) Abstract: Described is a method of indirect printing on a thermoplastic film having texture, wherein said method comprises: a) providing a heated thermoplastic melt; b) providing a tool having a molding portion that comprises a texture having a surface and a plurality of cavities in said surface, and that comprises a material having a surface energy sufficient to release ink; c) applying ink to said texture; d) substantially drying or curing said ink; e) contacting said thermoplastic melt with said molding portion having ink applied to it; f) forming a texture in said thermoplastic melt, wherein said texture comprises a plurality of protrusions and an area between said protrusions, that is the inverse of the texture of said molding surface; g) transferring said ink from said molding portion to said thermoplastic melt; h) quenching said thermoplastic melt to form a thermoplastic film; and i) removing said thermoplastic film from said molding portion.

**CONTINUOUS PROCESS FOR INDIRECT PRINTING
OF POLYMERIC FILMS HAVING TEXTURE**

Field of the Invention

5 The present invention relates generally to printing. More particularly, the present invention relates to a continuous process for indirect printing of polymeric films having texture during the formation of the films.

Background of the Invention

10 Image graphics are omnipresent in modern life. Images that are used for product identification, marketing purposes, etc., are applied to a variety of surfaces.

15 The use of ink jet printing to apply such image graphics is desirable. In fact, the use of thermal and piezo ink jet inks has greatly increased in recent years with accelerated development of inexpensive and efficient ink jet printers, ink delivery systems, and the like.

20 Articles having replicated texture, for example, are used for a variety of purposes. A few examples of such articles, having microreplicated texture in particular, are stemmed webs, and hook and loop fasteners, etc. (See, for examples, U.S. Patent Numbers 4,959,265 (Wood et al.), 5,845,375 (Miller et al.), which may be used for a multitude of purposes. It may be desirable to apply image graphics to these articles.

25 Currently, images are typically applied to the non-textured side of the articles. The problem with applying graphics to the non-textured side is that the material of the article may not be transparent, which will not allow the graphics to be seen from the textured side of the article. Another problem with printing on the non-textured side is that the ink may not be compatible with the non-textured side or with another coating that is applied to the non-textured side, such as an adhesive.

30 Images may also be applied to the textured side. The current processes that are known for applying images to the textured side, however, are by using lamination or printing on the surface of a completely formed article. One problem with using the known processes is the lack of durability or abrasion resistance of the image. The image may be

easily worn off because the image is printed on the tops of the protrusions that provide the texture.

Summary of the Invention

5 The inventors recognized that if an image could be printed substantially on the area between protrusions making up the textured side of a thermoplastic film, it would have good abrasion resistance. They also recognized that printing on the area between protrusions on a textured side would provide good resolution of the image. As a result, the inventors, invented a continuous method for indirect printing of an image on a textured side(s) of a thermoplastic film, having texture on at least one side, during the formation of said films.

10 The inventive method is a method of indirect printing on a thermoplastic film having texture, wherein said method comprises: a) providing a heated thermoplastic melt; b) providing a tool having a molding portion that comprises a texture having a surface and a plurality of cavities in said surface, and that comprises a material having a surface energy sufficient to release ink; c) applying ink to said texture; d) substantially drying or curing said ink; e) contacting said thermoplastic melt with said molding portion having ink applied to it; f) forming a texture in said thermoplastic melt, wherein said texture comprises a plurality of protrusions and an area between said protrusions, that is the inverse of the texture of said molding surface; g) transferring said ink from said molding portion to said thermoplastic melt; h) quenching said thermoplastic melt to form a thermoplastic film; and i) removing said thermoplastic film from said molding portion.

15 The invention also includes an article, which comprises: a) a thermoplastic film having a texture on at least one side wherein said texture comprises protrusions and an area between said protrusions; and b) ink appearing on at least a portion of said textured side wherein said ink is on less than 10% of the surface area of said protrusions.

20 An advantage of the present inventive method is that the image, which is different than the pattern of protrusions, appears substantially in the area between the protrusions on the textured side. Therefore, the printed images have good wear resistance. In addition, the printed images also have good resolution.

25 In the present invention:

“Surface energy” means energy being equal to the surface tension of the highest surface tension liquid (real or imaginary) that will completely wet a solid with a contact angle of 0 degrees, which may be determined by measuring the critical surface tension from static contact angles of pure liquids using the methods of W.A. Zisman described in 5 “Relation of Equilibrium Contact Angle to Liquid and Solid Constitution”, ACS Advances in Chemistry #43, American Chemical Society, 1961, pages 1-51.

Brief Description of the Drawings

Figure 1 is a side schematic view of one embodiment of the present inventive 10 method;

Figure 2 is a digital image showing the samples from Example 1 (bottom of digital image) and Comparative Example 1 (top of digital image);

Figure 3a is a digital image of a top view and close up view of the sample from Comparative Example 1;

15 Figure 3b is a digital image of a top view and close up view of the sample from Example 1;

Figure 3c is a digital image of an angled view and close up view of the sample from Comparative Example 1;

20 Figure 3d is a digital image of an angled view and close up view of the sample from Example 1;

Figure 4a is a digital image of a top view and close up view of the sample from Example 1 before Abrasion Test;

Figure 4b is a digital image of a top view and close up view of the sample from Comparative Example 1 after Abrasion Test;

25 Figure 4c is a digital image of a top view and close up view of the sample from Example 1 after Abrasion Test;

Figure 4d is a digital image of a top view and close up view of the sample from Comparative Example 1 before Abrasion Test;

Figure 5a is a digital image of a top view and close up view of the sample from Comparative Example 2 before Abrasion Test;

Figure 5b is a digital image of a top view and close up view of the sample from Example 2 before Abrasion Test;

5 Figure 5c is a digital image of a top view and close up view of the sample from Comparative Example 2 after Abrasion Test;

Figure 5d is a digital image of a top view and close up view of the sample from Example 2 after Abrasion Test;

Figure 6 is a digital image of the sample from Example 3; and

10 Figure 7 is a digital image of the sample from Example 4.

Detailed Description of the Invention

METHOD

Figure 1 shows an embodiment of the present inventive method. A heated thermoplastic melt **10** is continuously extruded from a molten-resin extrusion means **12**, which may be a die (as shown). The heated thermoplastic melt is then compressed against a tool **14** having a molding portion **16** that comprises a continuous surface and a plurality of cavities in the continuous surface that are suitable for forming texture on the thermoplastic melt **10**, with the molding portion **16** being the inverse of the texture that is desired to be formed on the resultant article (thermoplastic film **24**). The ink is applied to the molding portion **16**, before it contacts the thermoplastic melt **10**, by an ink jet printer head **20**, as shown in the Figure. It is also dried or cured before the thermoplastic melt **10** is applied. A drying or curing means is shown in the Figure as **22**. The drying or curing means **22** is, however, optional. For example, the ambient temperature may be warm enough to dry the ink without the need for a drying means. The printer head **20** is located above the tool **14**, and applies ink on the molding portion **16** of the tool **14** in a desired pattern. The ink is substantially coated on the continuous surface of the molding portion **16**. However, some may, and will probably, be applied in the cavities as well. The Figure exemplifies one possible way to contact the thermoplastic melt **10** with the molding portion **16** of a tool. This method uses a nip roll **18** to bring the thermoplastic melt **10** into

contact with the molding portion **16**. The ink that is coated on the molding portion **16** is transferred to the thermoplastic melt **10** as they are contacted together. Since the melt **10** is in the melt state, the ink may be substantially incorporated into the thermoplastic material. The thermoplastic melt **10** with ink is then quenched to form a thermoplastic film **24** having a texture, comprising a plurality of protrusions and an area between said protrusions, which is the inverse of the texture of the molding surface. The ink substantially appears on the area between protrusions on the thermoplastic film. The thermoplastic film **24** is then removed from the molding portion **16**.

The thermoplastic melt of the present inventive method comprises at least one melt processable polymer that is able to flow at an elevated temperature and cool to hold a shape at a use temperature. A "melt processable polymer" is a polymer that flows while heated to a molten state and becomes a solid when cooled. Melt processable polymers include materials that are melted in a polymeric state or are polymerized from monomers or oligomers into polymers while at elevated temperatures.

Examples of melt processable polymers that may be used in the present inventive method to form the thermoplastic melt include, but are not limited to, polyesters, polyamides, polyolefins, poly(vinyl chloride), polypropylene, copolymers of ethylene with vinyl acetate or vinyl alcohol, polycarbonate, norborene copolymers, fluorinated thermoplastics such as copolymers and terpolymers of hexafluoropropylene, poly(ethylene terephthalate), and copolymers thereof, polyurethanes, polyimides, acrylics, plasticized polyvinyl alcohols, blends of polyvinylpyrrolidone and ethylene acrylic acid copolymer and filled versions of the above using fillers such as silicates, aluminates, feldspar, talc calcium carbonate, titanium dioxide, and the like. The thermoplastic melt may also include stabilizers, such as antioxidants, UV absorbers, etc.

The thermoplastic melt may be formed by a molten-resin extrusion means. For example, a feed stream of thermoplastic resin (or a melt processable polymer) is fed into an extruder, the resin is then heated and extruded, and then the molten resin is fed through a neck tube (that may also be heated) and into a die (that may also be heated) that forms a film-like thermoplastic melt.

Non-limiting examples of equipment useful for the extrusion include single screw extruders such as a 1 ¼ inch KILLION™ extruder (available from Killion Extruders, Inc. of Cedar Grove, NJ) equipped with a gear pump such as a ZENITH™ gear pump to

control flow rate, co-rotating twin screw extruders such as a 25mm BERSTORFF™ extruder (available from Berstorff Corporation of Charlotte, NC) and counter-rotating twin screw extruders such as a 30mm LEISTRITZ™ extruder (available from American Leistritz Extruder Corporation of Somerville, NJ). Flow rate in the twin screw extruder 5 can be controlled using weight loss feeders such as a K-TRON™ weight loss feeder (available from K-tron America of Pitman, NJ) to feed raw material into the extruder. A film die with adjustable slot is used to form a uniform film out of the extruder.

Conditions for extrusion are chosen to meet the general requirements of forming 10 textured articles, which are understood to the skilled artisan.

The die used to form the thermoplastic melt may be any suitable film-forming die.

The die is located at a position such that the thermoplastic melt extruded from the die can be contacted with the molding portion of the tool while in a substantially molten state.

15 The tool of the present inventive method has a molding portion that comprises a texture that is suitable for forming texture on the thermoplastic film, with the texture on the molding portion being the inverse of the texture that is desired to be formed on the resultant article.

There are alternative embodiments of for the tool used in the present inventive 20 method. For example, one preferred tool comprises a molding portion on a powered, rotating roll or cylinder. The molding portion, with the texture, is on the outer part of the roll and may be made by patterning the roll surface or patterning a sleeve that is then placed over the roll surface. The melt is then contacted with the molding portion on the cylindrical tool using a nip roll. (As shown in Figure 1).

25 Alternatively, the molding portion may be an independent surface that is conveyed around a portion of the roll both before and after a nip point.

Another alternative is a configuration that would allow for texture on both sides (of 30 the two sides) of the thermoplastic melt. This configuration would be much like that shown in Figure 1, except the nip roll would be textured as well as the molding portion on the cylindrical tool. In addition, printing could be done on both textured sides by applying ink to the nip roll also.

The molding portion of the tool (or both the tool and nip roll, if a dual-sided textured thermoplastic film is desired) must be made of a material, or at least have a coating of a material, that allows the molding portion to receive and transfer ink. The material that allows for receipt and transfer of ink is a low surface energy material. A 5 preferred level of surface energy of the ink release coating, or the molding portion itself, is up to about 40 dynes per centimeter (dynes/cm) (0.04 Newtons/meter (N/m)). The particular preferred range is from about 14 (0.014 N/m) to about 32 dynes/cm (0.032 N/m). If the surface energy of the material that makes up the molding portion is within a required range, then the ink beads up and does not wet the surface. The beading allows for 10 better transfer of the ink to the thermoplastic melt.

The low surface energy material may make up the molding portion of the tool or may be an outer layer of the molding portion. The low energy surface has a surface energy lower than the polymer material and ink in contact with the molding portion to permit easy removal of the imaged article (thermoplastic film) from the molding portion.

15 The molding portion material may comprise, for example: fluorochemicals, and polymers thereof, like that sold under the brand name TEFLON™ (available from E. I. DuPont de Nemours, Wilmington, DE); elastomeric materials; urethanes; silicones; and other polymers, such as polypropylene and polyethylene.

20 The bulk of the cylindrical tool, besides the molding portion, may be made of metals, such as aluminum, stainless steel and copper, for example.

25 The molding portion of the tool of the present inventive method comprises a texture that is suitable for forming a texture in the resulting thermoplastic film. The molding portion comprises a surface and a plurality of cavities. The term "surface" includes both a continuous surface and a plurality of discontinuous surfaces (there will be more than one if surface is discontinuous). An example of a surface that comprises discontinuous surfaces is when the tool comprises a plurality of cavities that are channels that stretch the width of the molding portion.

30 The texture of the molding portion is the inverse of the texture that is desired to be formed in a resultant article. The surface of the molding portion may include structures of various types that will produce a desired structure in a resultant article. For example, the

shape of the opening of the plurality of cavities (or the cross-section of the cavities) may, independently, be circular, oval, triangular, polygonal, etc.

An example of a molding portion that has a discontinuous surface with cavities is found in U.S. Patent No. 6,190,594 (Gorman et al.). Further examples of possible molding portion are described in the following patents, U.S. Patent Nos. 4,775,310 (Fischer), 5,077,870 (Melbye et al.), 5,792,411 (Morris et al.), and 6,287,665 (Hammer).

Preferably, the surface is about 50% to about 99% of the projected surface area (the surface area that the surface of the molding portion would have if it was void of cavities) of the molding portion. Most preferably, the surface is about 80% to about 99% of the projected surface area of the molding portion.

Using an ink jet printer head to apply the ink is preferred in the invention. However, other printers or printing means may be used. An ink jet printer is preferred because it is efficient for use in a continuous process.

Suitable inks for the present invention include water-based inks, as well as solvent-based inks. In addition, curable inks may be used in the present invention. If curable inks are used, a curing source, such as an ultraviolet (UV) light, is used to cure the ink on the molding surface prior to contact with the thermoplastic melt. Another ink that could be used is a black-light ink (visible using a black light or light in the non-visible wavelength range). Ink jet inks can be wholly or partially water-based, such as those disclosed in U.S. Pat. No. 5,271,765 (Ma).

An ink jet printer applies the ink by deposition of ink droplets. The ink droplets may be deposited in a pattern that forms an image, such as a figure, word or logo, etc.

At least one ink is applied to at least one portion of the molding portion of the tool. The ink is applied preferably in an image, which is the mirror image of the image that is desired to appear on the textured side of the resulting thermoplastic film.

Ink jet printers generally comprise the printer itself, a computer, and software. The ink jet printer system controls the size, number and placement of the ink drops that form image graphics.

Non-limiting commercially available examples of ink jet printers include thermal ink jet printers such as DESKJET™ brand, PAINTJET™ brand, DESKWRITER™ brand,

DESIGNJET™ brand, and other printers commercially available from Hewlett Packard Corporation of Palo Alto, CA, and the NovaJet brand wide format printers commercially available from Encad, Inc., San Diego, CA. Also included are piezo type ink jet printers such as those from Seiko-Epson, Raster Graphics, and Xerox, spray jet printers, and 5 continuous ink jet printers. Any of these commercially available printing techniques introduce the ink in a jet spray of a specific image. Another example of a printer is the BUD-JET IV 128 ULTRA-MARK™ from Fas-Co Coders, Inc., Chandler, Arizona. Any of the above printers can be attached to a computer to print computer-generated images.

Depending upon the image that is desired on the resultant article, combinations of 10 different colors of inks may be applied to the tool.

A variety of ink jet inks may be used and are obtainable from many commercial sources. It should be understood that each of these inks has a different formulation, even for different colors within the same ink family. Non-limiting sources of inks include 3M Company, (St. Paul, MN), Encad Corporation, Hewlett Packard Corporation, and the like. 15 These inks are preferably designed to work with the ink jet printers described above.

After the ink is applied to the molding portion (or a portion thereof) it is dried and/or cured. The curing source depends upon the ink that is used. Inks that are cured by ultraviolet light, for example, will be exposed to ultraviolet light. The ink is substantially dried and/or cured prior to being contacted with the thermoplastic melt.

20 The molding portion with the dried and/or cured ink on it is then contacted with the thermoplastic melt. The ink is then transferred from the molding portion of the tool to the film. The molding portion of the tool has a texture the inverse of which is imprinted into the thermoplastic film upon contact of the thermoplastic melt with the molding portion.

25 The nip roll 18 in Figure 1 is one alternative in the present inventive method for pressing the film 10 against the molding surface 16 of the tool, which shapes or provides structure to the film. However, alternative configurations are also contemplated by the present application.

30 After the ink has been transferred, the thermoplastic melt is quenched. This solidifies the thermoplastic melt into a thermoplastic film. Quenching may be done by using, for example, a fluid-cooled tool or an air-cooled tool.

The next step is removal of the molding portion from the thermoplastic film.

5 The thermoplastic film will comprise a plurality of protrusions and an area between said protrusions. The aspect ratio (the ratio of the height of the protrusion to the width of the protrusion at the widest portion of the cross-section of the protrusion) of the plurality of protrusions is preferably greater than about 1:1. Most preferably it is greater than about 2:1.

ARTICLE

10 The invention also includes an article, which comprises: a) a thermoplastic film having a texture on at least one side wherein said texture comprises protrusions and an area between said protrusions; and b) ink appearing on said on at least a portion of said textured side wherein said ink is on less than 10% of the surface area of said protrusions. More preferably, the ink is on less than 5% of the surface area of said protrusions, which are surrounded by an inked areas between said protrusions.

15 **EXAMPLES**

20 This invention is further illustrated by the following examples that are not intended to limit the scope of the invention. In the examples, all parts, ratios and percentages are by weight unless otherwise indicated. The following test methods were used to characterize the stemmed web compositions in the following examples:

Test Methods

Abrasion Test

25 An abrasion tester (Model CS-39 available from Standard Scientific Supply Company, Bethlehem, Pennsylvania) was used to determine the abrasion resistance of an image on the textured side of the samples. Two circular sections with a diameter of about 114 mm (4.5 in) were cut from the sample. The smooth side of one section was adhered with double-coated pressure-sensitive adhesive tape to the surface of the upper disc of the tester, while the other was adhered the same way to the lower disc. The discs were brought in contact with a weight of about 1.4 kg (3 lb) and the tester was operated for 500 cycles. Pictures were taken of the resulting image.

Tape Snap Test

Ink adhesion was evaluated using the Tape Snap Test (ASTM # 3359). The Tape Snap Test consists of scoring an ink layer with the corner of a single edge razor blade without damaging the underlying print surface, making lines approximately 1 cm apart in a cross-hatched pattern. A piece of Scotch™ 610 tape (3M) approximately 10 cm long was applied to the cross-hatched area using a PA1 applicator (3M), bonding approximately 8 cm of the tape to the ink, leaving one end free. The tape was peeled back at approximately 180° as rapidly as possible. An excellent result was when no ink was removed by the tape; a good result was when about 5% or less was removed; a poor result was when about 5%-25% of the ink was removed; a failure was when nearly all the ink was removed.

Image Quality Test

The quality of the image was subjectively determined by observation. The quality was considered "excellent" if the appearance of the resulting image, to the human eye, closely approximated the image that was programmed into the print head. Typically this also meant that the image looked crisp. By contrast, image quality was considered "poor" if the lines of the image were significantly wider than that of the image programmed into the print head. Typically this resulted in the appearance of a blurred image.

The following process was used in the Examples:

Process Description

Two rolls (a tool and a nip roll) formed a nip point having a nip pressure of 345 kPa (50 psi). The first roll (tool) presented a molding portion that was heated to 38°C and contained one of two patterns of cavities. The second roll (nip roll) had a chrome-plated surface that was also heated to 38°C.

Two different molding portions (with different patterns of cavities, and each with a continuous surface between cavities) were used in the process. Molding Portion A contained cavities with diameters of about 380 microns (15 mils), depths in excess of about 2.5 mm (100 mils) and spacing of about 940 microns (37 mils), resulting in an article having a protrusion array with a protrusion density of nominally about 62

protrusion/cm² (400 protrusion /in²) and a projected protrusion area of about 7%. Molding Portion B contained cavities with diameters of about 216 microns (8.5 mils), depths in excess of about 1.0 mm (30 mils) and spacing of about 457 microns (18 mils), resulting in and article having a protrusion array with a protrusion density of nominally about 390 protrusion /cm² (3000 protrusion /in²) and projected protrusion area of about 17%.

Two types of ink were used, a solvent-based ink or an ultraviolet (UV) light curable ink. The ink was image-wise applied with an ink jet print head (Model XJ128-200 with 128 ink jet nozzles, available from Xaar Americas, Schaumburg, Illinois). It was applied to the surface of the molding portion about 356 mm before the nip point to permit the ink to either air dry or cure upon exposure to UV radiation. UV-curable ink was cured at a line speed of 30.5 mm/sec (1.2 in/sec) by exposure to 370 mW/cm² of UV-A radiation, 330 mW/cm² of UV-B radiation, 29 mW/cm² of UV-C radiation and 150 mW/cm² of UV-V radiation from a UV radiation source, Portable 2 UV Curing Unit, available from UV Process Supply Inc., Chicago, Illinois. Ink was delivered at about 36 dots per cm (92.5 dots per in) utilizing a firing frequency of 185 Hz.

A melt processable polymer, one of the polymers listed in Table 1, was melted and conveyed with a single screw extruder (Model KTS125, available from Killion Extruders, Inc. of Cedar Grove, NJ) in a similar manner for each polymer. The extruder had a diameter of about 63 mm (2.5 in), a length : diameter ratio (L/D) of 30/1, a screw speed of 10 rpm and a rising temperature profile up to approximately 216°C. The polymer was passed through the extruder and continuously discharged at a pressure of at least about 0.69 MPa (100 psi) through a heated neck tube (custom-made) and into a 356 mm (14 in) wide die (EBR III Internal Deckled extrusion die Model JO9601501, available from Cloeren Company, Orange, Texas). The die was set at approximately 216°C and the die gap was 0.76 mm (30 mils). The thermoplastic melt was discharged from the die and drop fed onto the molding portion near the nip point. As the thermoplastic melt was passed between the tool and the nip roll, the thermoplastic melt was pressed into the cavities to form a thermoplastic melt having a texture on the side of the melt that was in contact with the molding portion. As the thermoplastic melt left the nip point, the thermoplastic melt was quenched to form a textured thermoplastic film (having a textured side and a non-textured side) and the resulting thermoplastic film was removed from the molding portion at a rate of about 3.0 m/min (10 fpm). A textured thermoplastic film was formed with an

image on the textured side. The textured side comprised a plurality of protrusions and an area between the protrusions. The diameter and height of the protrusions made with Molding Portion A were approximately 381 and 1016 microns (μm), respectively. The diameter and height of the protrusions made with Molding Portion B were approximately 5 216 and 559 μm , respectively.

Materials Used

A variety of polymeric materials and inks were used in the preparation of the samples of the examples. These materials are summarized in Table 1.

10

Table 1

Material	Description
REXENE™ W101	Significantly atactic polypropylene available from Huntsman Polypropylene Corp., Woodbury, New Jersey.
KRATON™ D1117	A styrene-isoprene block copolymer available from Shell Chemical Company, Houston Texas.
Polypropylene 3155	Isotactic polypropylene available from Exxon Chemical Co., Houston, Texas.
ESTANE™ 58238	Polyurethane available from Noveon, Inc., Cleveland, Ohio.
Solvent-based ink	Ink available as SCOTCHCAL™ 3795 Black from 3M Company, St. Paul Minnesota.
UV-curable ink	Ink available as XAARJET™ XUV Black from Xaar Americas, Schaumburg, Illinois.

Example 1 and Comparative Example 1

These examples illustrate the effect of application of an image to a film before or 15 during formation, and the image's adhesion to the thermoplastic film.

In Example 1, the polymer was REXENE™ W101, the ink was solvent-based and the molding portion was Molding Portion A resulting in a protrusion density of 62 protrusion/cm² (400 protrusion/in²). The sample was observed for image quality and presence of ink on the protrusions, and tested with the Abrasion Test. In addition, ink was 20 applied to the smooth back-side (non-textured side) of the sample to determine the tendency for this ink to adhere to the thermoplastic film with the Tape Snap Test.

Comparative Example 1 was made as Example 1 with the same image, except ink was applied directly onto the textured side of a textured thermoplastic film after the film was already formed.

Image quality for Example 1 was excellent. Figure 2 shows the textured side with the image of Example 1 (bottom portion of digital image) and Comparative Example 1 (top portion of digital image). As seen, the image is excellent (crisp) for Example 1 but poor (blurred) for Comparative Example 1. Figures 3a-3d are magnified views of the textured side with the image of Example 1 and Comparative Example 1 from either a top-down perspective (3a and 3b) or an angled-viewing perspective (3c and 3d). As seen, little ink appears on the protrusions of Example 1 (3b and 3d). In addition, distinct droplets of ink appear on the area between protrusions. In contrast, the tops and much of the sides of the protrusions of Comparative Example 1 (3a and 3c) are coated with ink and the area between protrusions does not show distinct droplets but rather a continuous coating of ink. The appearance of drops provide a better or sharper image.

In addition, the durability of the images of Example 1 and Comparative Example 1 was evaluated with the Abrasion Test. Figures 4a-4d show the magnified views of the textured side with the image of Example 1 (4a and 4b) and Comparative Example 1 (4c and 4d) before and after the test was performed. As seen, more ink remains (after the Abrasion Test) on the image with Example 1 (4b) than with Comparative Example 1 (4d). The same ink used on the textured side was applied to the smooth polymer side of Example 1 and evaluated with the Tape Snap Test. The ink adhesion by this test was a failure because nearly all of the ink was removed.

Example 2 and Comparative Example 2

This example illustrates the image durability with a different polymer.

Example 2 and Comparative Example 2 were made as Example 1 and Comparative Example 1, respectively, except the polymer was KRATON™ D1117. The durability of the images of Example 2 and Comparative Example 2 was evaluated with the Abrasion Test. Figures 5a-5d show the magnified views of the textured side having an image of Example 2 (5b and 5d) and Comparative Example 2 (5a and 5c) before and after the test was performed. As seen, more ink remains on the textured surface of the image in

Example 2 (5d) than Comparative Example 2 (5c). Also, dots of ink were visible with both Example 2 and Comparative Example 2.

Example 3

5 This example illustrates the image quality of the invention with a different polymer and ink.

Example 3 was made as Example 1 except the polymer was Polypropylene 3115 and the ink was UV-curable. Figure 6 shows the imaged surface of Example 3. As seen the image quality is excellent and comparable to that seen in Figure 2 for Example 1.

10

Example 4

This example illustrates the effect of protrusion density on an imaged surface made with the invention.

15 Example 4 was made as Example 1 except the polymer was ESTANE™ 58238 and the protrusions were made with Molding Portion B resulting in a protrusion density of 390 protrusion/cm² (3000 protrusion/in²). Figure 7 shows the imaged surface of Example 4. As seen the image quality is excellent and comparable to that seen in Figure 2 for Example 1. In either case (different protrusion densities), a good image resulted.

What is Claimed is:

1. A method of indirect printing on a thermoplastic film having texture, wherein said method comprises:
 - a. providing a heated thermoplastic melt;
 - 5 b. providing a tool having a molding portion that comprises a texture having a surface and a plurality of cavities in said surface, and that comprises a material having a surface energy sufficient to release ink;
 - c. applying ink to said texture;
 - d. substantially drying or curing said ink;
 - 10 e. contacting said thermoplastic melt with said molding portion having ink applied to it;
 - f. forming a texture in said thermoplastic melt, wherein said texture comprises a plurality of protrusions and an area between said protrusions, that is the inverse of the texture of said molding surface;
 - 15 g. transferring said ink from said molding portion to said thermoplastic melt;
 - h. quenching said thermoplastic melt to form a thermoplastic film; and
 - i. removing said thermoplastic film from said molding portion.
- 20 2. The method of claim 1 wherein said heated thermoplastic melt is formed by a molten-resin extrusion means.
3. The method of claim 1 wherein said molding portion material has a surface energy of from less than about 14 to about 32 dynes per centimeter.
- 25 4. The method of claim 1 wherein said ink is applied to said molding portion in a pattern and said ink on said thermoplastic film then appears in an image having the mirror-image of said pattern.
5. The method of claim 1 wherein said ink appears substantially on said area of said thermoplastic film between the protrusions.

6. The method of claim 1 wherein said protrusions of said film have an aspect ratio of greater than about 1:1.

5 7. The method of claim 1 wherein said protrusions of said film have an aspect ratio of greater than about 2:1.

8. The method of claim 1 wherein said ink is applied to said molding portion in a pattern to form an image on said film.

10 9. The method of claim 1 wherein said ink is applied to the molding portion using an ink jet printer.

10. The method of claim 1 wherein said surface is about 50% to about 99% of the projected surface area of the molding portion.

15 11. The method of claim 1 wherein said surface is about 80% to about 99% of the projected surface area of the molding portion.

20 12. The method of claim 1 wherein the surface comprises a plurality of discontinuous surfaces.

13. An article comprising:

a. a thermoplastic film having a texture on at least one side wherein said texture comprises protrusions and an area between said protrusions; and

25 b. ink appearing on at least a portion of said textured side wherein said ink is on less than 10% of the surface area of said protrusions.

14. The article of claim 13 wherein the ink is on less than 5% of the surface area of said protrusions.

30

1/9




Fig. 1




Fig. 2

2/9




Fig. 3a




Fig. 3b

3/9




Fig. 3c




Fig. 3d

4/9




Fig. 4a




Fig. 4b

5/9




Fig. 4c




Fig. 4d

6/9




Fig. 5a




Fig. 5b

7/9




Fig. 5c




Fig. 5d

8/9




Fig. 6

9/9



Fig. 7

INTERNATIONAL SEARCH REPORT

Internat Application No

PCT/US 02/35345

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B29C43/22 B29C59/02 B29C37/00 B41M5/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B29C B41M B41F B44C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 836 927 A (IDEMITSU PETROCHEMICAL CO) 22 April 1998 (1998-04-22) figures 2,3 page 2, line 1 - line 6 page 2, line 45 -page 4, line 26 page 5, line 12 - line 18 claim 3 ---	1-14
X	EP 0 825 038 A (YUGENGAISYA TOWA) 25 February 1998 (1998-02-25) figures 3,4 column 1, line 41 -column 5, line 28 --- -/-	1-12

 Further documents are listed in the continuation of box C. Patent family members are listed in annex.

° Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

- *&* document member of the same patent family

Date of the actual completion of the international search

Date of mailing of the international search report

5 February 2003

17/02/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Whelan, N

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 02/35345

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DATABASE WPI Section Ch, Week 199644 Derwent Publications Ltd., London, GB; Class A32, AN 1996-438184 XP002230029 & JP 08 216250 A (KASAMATSU KAKO KENKYUSHO KK), 27 August 1996 (1996-08-27) abstract; figures ----	1-12
X	DATABASE WPI Section Ch, Week 199832 Derwent Publications Ltd., London, GB; Class A32, AN 1998-370528 XP002230030 & JP 10 146940 A (AICA KOGYO CO LTD), 2 June 1998 (1998-06-02) abstract -----	1-14

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 02/35345

Patent document cited in search report		Publication date		Patent family member(s)		Publication date
EP 0836927	A	22-04-1998	AT CN DE DE EP JP US	215439 T 1180610 A ,B 69711538 D1 69711538 T2 0836927 A1 10175282 A 6296731 B1		15-04-2002 06-05-1998 08-05-2002 24-10-2002 22-04-1998 30-06-1998 02-10-2001
EP 0825038	A	25-02-1998	JP JP DE DE DE EP ES KR TW	3312850 B2 10058816 A 69707074 D1 69707074 T2 825038 T1 0825038 A2 2114518 T1 243988 B1 442405 B		12-08-2002 03-03-1998 08-11-2001 06-06-2002 03-09-1998 25-02-1998 01-06-1998 01-02-2000 23-06-2001
JP 8216250	A	27-08-1996		NONE		
JP 10146940	A	02-06-1998		NONE		