



(86) Date de dépôt PCT/PCT Filing Date: 2004/05/19
(87) Date publication PCT/PCT Publication Date: 2004/12/02
(85) Entrée phase nationale/National Entry: 2005/11/03
(86) N° demande PCT/PCT Application No.: EP 2004/050850
(87) N° publication PCT/PCT Publication No.: 2004/103336
(30) Priorités/Priorities: 2003/05/23 (60/473,055) US;
2003/05/23 (03101490.5) EP

(51) Cl.Int./Int.Cl. *A61K 9/00* (2006.01),
A61P 31/18 (2006.01), *A61P 15/18* (2006.01),
A61K 31/565 (2006.01), *A61K 9/24* (2006.01)
(71) Demandeur/Applicant:
AKZO NOBEL N.V., NL
(72) Inventeurs/Inventors:
GROENEWEGEN, RUDOLF JOHANNES JOSEPH, NL;
DE GRAAFF, WOUTER, NL;
OUT, HENK JAN, NL
(74) Agent: FETHERSTONHAUGH & CO.

(54) Titre : SYSTEME D'ADMINISTRATION DE MEDICAMENTS
(54) Title: DRUG DELIVERY SYSTEM

(57) **Abrégé/Abstract:**

The subject invention provides a drug delivery system comprising at least one compartment consisting of (i) a drug-loaded thermoplastic polymer core, (ii) a drug-loaded thermoplastic polymer intermediate layer and (iii) a non-medicated thermoplastic polymer skin covering the intermediate layer, wherein said intermediate layer is loaded with (a) crystals of a first pharmaceutically active compound and with (b) a second pharmaceutically active compound in dissolved form and wherein said core is loaded with said second compound in dissolved form.



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
2 December 2004 (02.12.2004)

PCT

(10) International Publication Number
WO 2004/103336 A3

- (51) International Patent Classification⁷: A61K 9/00, 9/24, 31/565, A61P 15/18, 31/18
- (21) International Application Number: PCT/EP2004/050850
- (22) International Filing Date: 19 May 2004 (19.05.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
03101490.5 23 May 2003 (23.05.2003) EP
60/473,055 23 May 2003 (23.05.2003) US
- (71) Applicant (for all designated States except US): **AKZO NOBEL N.V.** [NL/NL]; Velperweg 76, NL-6824 BM Arnhem (NL).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **GROENEWEGEN, Rudolf, Johannes, Joseph** [NL/NL]; N.V. Organon, P.O. Box 20, NL-5340 BH Oss (NL). **DE GRAAFF, Wouter** [NL/NL]; N.V. Organon, P.O. Box 20, NL-5340 BH Oss (NL). **OUT, Henk, Jan** [NL/NL]; N.V. Organon, P.O. Box 20, NL-5340 BH Oss (NL).
- (74) Agent: **VAN DEN BROEK, Ludovicus, A.G.M.**; P.O. Box 20, NL-5340 BH Oss (NL).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
- with international search report
 - before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- (88) Date of publication of the international search report: 6 January 2005
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: DRUG DELIVERY SYSTEM

(57) Abstract: The subject invention provides a drug delivery system comprising at least one compartment consisting of (i) a drug-loaded thermoplastic polymer core, (ii) a drug-loaded thermoplastic polymer intermediate layer and (iii) a non-medicated thermoplastic polymer skin covering the intermediate layer, wherein said intermediate layer is loaded with (a) crystals of a first pharmaceutically active compound and with (b) a second pharmaceutically active compound in dissolved form and wherein said core is loaded with said second compound in dissolved form.



WO 2004/103336 A3

Drug delivery system

FIELD OF THE INVENTION

5

The present invention relates to the field of female contraception and hormone replacement therapy.

10 The present invention relates to a drug delivery system (device) for the simultaneous release of two or more active substances and more particularly to a ring shaped vaginal drug delivery system, which system releases the active substances in a substantially constant ratio over a prolonged period of time. Since the invention pertains to a drug delivery article for intra-vaginal use, its use is focussed on typically female medical indications, such as contraception and hormone-replacement. The article according to the invention is
15 particularly in the form of a ring, and will hereinafter be referred to as a vaginal ring.

BACKGROUND OF THE INVENTION

20 Vaginal rings are known. Background art in this respect includes the following patent documents.

U.S. Patents Nos. 3,995,633 and 3,995,634, describe separate, preferably spherical or cylindrical, reservoirs containing different active substances which are assembled in specially constructed holders.

25

U.S. Patent No. 4,237,885 describes a tube or coil of polymeric material which is divided into portions by means of a plurality of "spacers" provided in the tube, after which each of the separate tube portions is filled with a different active substance in a silicone fluid and the two ends of the tube are subsequently connected to one another. In this release system,
30 however, transport (diffusion) of active material from one reservoir to the other takes place through the wall of the tube, especially upon prolonged storage, so that the pre-set fixed release ratio between the active substances in question will change over a period of time.

European patent publication 0,050,867 discloses a two-layered vaginal ring which comprises a pharmacologically acceptable supporting ring covered by two layers preferably of silicone elastomers whereby the inner layer is a silicone elastomer loaded with an active substance.

5 US Patent No. 4,292,965 describes a ring shaped vaginal delivery system of three layers made of silicone elastomers.

US Patent 4,596,576 describes a two-compartment vaginal ring wherein each compartment contains a different active substance. To achieve a suitable ring with a constant release ratio
10 between the various active substances, the end portions of the compartments are joined by glass stoppers.

Patent Publication WO 97/02015 describes a two-compartments device, a first compartment consisting of a core, a medicated middle layer and a non medicated outer layer, and a second
15 compartment consisting of a medicated core and a non medicated outer layer.

EP 876 815 discloses a vaginal ring (Nuvaring®) which is designed for the simultaneous release of a progestogenic steroid compound and an estrogenic steroid compound in a fixed physiological ratio over a prolonged period of time. The drug delivery system comprises one
20 compartment comprising a thermoplastic polymer core containing the mixture of the progestogenic and estrogenic compounds and a thermoplastic polymer skin, the progestogenic compound being initially dissolved in the polymer core material in a relatively low degree of supersaturation.

25 From the above disclosures, it is clear that e.g. the material, the layers and the compartments are all aspects of a ring device which play a role in the designs that have been developed.

All choices are usually made with a view to obtain a constant release pattern, which is
30 complicated when two or more active substances are involved. The latter is of particular importance in the field of contraception, as for this purpose often a combination of a

progesterone and an estrogen is used. Also in hormone replacement, however, it is desired to have rings which deliver combinations of drugs.

5 Among the above disclosures, EP 876 815 clearly sets a standard; it involves a one-compartment design, it obviates the need for silastic polymer by using EVA combinations, and it releases two or more active substances in a substantially constant ratio to one another over a prolonged period in time.

10 As any product of technology at all times however, also the latter can still be improved upon. The drug delivery device disclosed in EP 876815 is physically stable only when stored below room temperature. It requires storage and transport below room temperature which is expensive and requires a lot of attention. Moreover, if not stored below room temperature, steroid eventually crystallizes out onto the skin of the device which may lead to uncontrollable and high burst release.

15 The subject improved drug delivery system solves this problem since it is physically stable under room temperature conditions and thus does not need special storage and transportation conditions.

20 Moreover, in the subject improved drug delivery system, it is possible to adjust the release rate of more than one pharmaceutically active compound independently from one another, while maintaining the physical stability of the system.

SUMMARY OF THE INVENTION

25 The subject invention provides a three-layer design vaginal ring, physically stable at room temperature, from which at least two pharmaceutically active compounds can be released independently from one another.

30 The ring comprises at least one compartment comprising (i) a medicated thermoplastic polymer core, (ii) a medicated thermoplastic polymer intermediate layer and (iii) a non-medicated thermoplastic polymer skin covering the intermediate layer. The intermediate layer is medicated (loaded) with (a) crystals of a first active substance and with (b) a second active

substance in dissolved form. The core is loaded with the second active substance as well, optionally in the same concentration as in the intermediate layer.

FIGURES

5 Figure 1:

In vitro release rates of etonogestrel (ENG) for all 4.0 mm batches.

Figure 2:

In vitro release rates of etonogestrel for all 3.5 mm batches.

10

Figure 3:

In vitro release rates of ethinyl estradiol (EE) for all 4.0 mm batches.

Figure 4:

15 In vitro release rates of ethinyl estradiol for all 3.5 mm batches.

Figure 5:

Schematic description of a vaginal ring of the subject invention.

20 Figure 6:

In vitro-release rates of etonogestrel and ethinyl estradiol from one A1 ring.

Figure 7:

In vitro-release rates of etonogestrel and ethinyl estradiol from one A2 ring.

25

Figure 8:

In vitro-release rates of etonogestrel and ethinyl estradiol from one A3 ring.

Figure 9:

30 In vitro-release rates of etonogestrel and ethinyl estradiol from one A4 ring.

Figure 10:

In vitro-release rates of etonogestrel and ethinyl estradiol from one B1 ring.

Figure 11:

In vitro-release rates of etonogestrel and ethinyl estradiol from one B2 ring.

5

Figure 12:

In vitro-release rates of etonogestrel and ethinyl estradiol from one B3 ring.

Figure 13:

10 **In vitro-release rates of etonogestrel and ethinyl estradiol from one B4 ring.**

Figure 14:

In vitro release rates of etonogestrel for fibre variants E, F, G, H and I.

15 **Figure 15:**

In vitro release rates of etonogestrel for fibre variants J, K, L, W and X.

Figure 16:

In vitro release rates of etonogestrel for fibre variants M, N, O, P and Q.

20

Figure 17:

In vitro release rates of etonogestrel for fibre variants R, S, T, U and V.

Figure 18:

25 **In vitro release rates of ethinyl estradiol for fibre variants E, F, G, H and I.**

Figure 19:

In vitro release rates of ethinyl estradiol for fibre variants J, K, L, W and X.

30 **Figure 20:**

In vitro release rates of ethinyl estradiol for fibre variants M, N, O, P and Q.

Figure 21:

In vitro release rates of ethinyl estradiol for fibre variants R, S, T, U and V.

DETAILED DESCRIPTION OF THE INVENTION

5

Fick's law of diffusion governs the release of compounds, such as contraceptive steroids from a ring. According to this law, the amount of mass transferred over the boundary is an inverse function of the distance across the boundary. In a two-layer design, the steroid nearest to the outer layer (the skin) will diffuse first and this results in depletion of the outer core and hence the diffusion distance will increase. The depletion of the outer core layer and the resulting increase of the diffusion distance will result in a decrease of the release rate. When speaking about the release rate of one drug substance, the problem of depletion and increase of the diffusion distance can be overcome by concentrating the drug substance in an intermediate layer between a placebo skin and a placebo core. Since the drug substance is then concentrated in a relatively thin layer, lengthening of the diffusion distance during release is minimal, resulting in a more constant release rate over time.

15

The release rate of a cylindrical reservoir/membrane design is:

$$20 \quad \frac{dM}{dt} = \frac{2\pi L D_p K_{p/s} \Delta C}{\ln(r_0 / r_1)}$$

- L = the length of the cylinder
- D_p = the diffusion co-efficient of the compound in a skin polymer
- $K_{p/s}$ = partition coefficient of the steroid between the skin and core polymer
- 25 ΔC = the difference in concentration between the core (or intermediate layer) and the sink
- r_0 = is the overall radius, i.e. the radius of the cylinder including the skin
- r_1 = is the radius of the core

The equation shows that zero order release is obtained when the term on the right hand side of the equation is constant, i.e. not a function of time. Lengthening of the diffusion distance due to depletion of the core is insignificant in a three-layer design containing one drug

30

substance and hence the term (r_0 / r_1) may be considered almost constant. In case the steroid in the intermediate layer is present in the dissolved state, the concentration gradient (ΔC) will steadily decrease in time and consequently the release rate dM/dt will decrease (deviate from zero order release kinetics).

5

The subject invention provides a drug delivery system comprising at least two active drug substances.

The subject invention provides a drug delivery system, typically a substantially ring-shaped form intended for vaginal administration, which comprises at least one compartment consisting of (i) a thermoplastic polymer core, (ii) a thermoplastic polymer intermediate layer and (iii) a thermoplastic polymer skin covering the intermediate layer, wherein said intermediate layer comprises (a) crystals of a first pharmaceutically active compound and (b) a second pharmaceutically active compound in dissolved state and wherein said core comprises said second compound as well, optionally in the same concentration as in the intermediate layer.

10
15

The essence of this novel three-layered ring of the subject invention lies in the provision of the possibility to adjust the release rates of more than one pharmaceutically active compound independently from each other while maintaining the physical stability of the ring at room temperature.

20

This is accomplished by (1) incorporating crystalline reservoirs of the (first) compound in the intermediate layer of the ring, (2) loading both the intermediate layer and the core of the ring with the second compound in dissolved form, thereby enlarging the compound reservoir, and (3) defining the thickness of the skin of the ring.

In a specific embodiment of the subject invention, the compounds are steroids. For the sake of ease, we hereinafter refer to steroids, although also non-steroidal compounds are contemplated by the subject invention as well.

25

The steroid molecules incorporated in the crystalline lattice are in dynamic equilibrium with the steroid dissolved in the polymer of the intermediate layer. When no diffusion occurs, the

steroid concentration in the polymer will equal or come close to the equilibrium concentration. After the ring has been put in a sink, steroid will start to diffuse out of the ring and the concentration of the steroid dissolved in the polymeric intermediate layer will drop slightly. As a consequence thereof, the steroid crystals will start to dissolve. Thus, the decrease of the concentration gradient due to diffusive transport out of the ring is counterbalanced by the steroid in the crystalline reservoir. Figures 1 and 2 illustrate this stabilizing effect of crystals in the intermediate layer. In the beginning, the slope of the release curve is very flat, i.e. indicates that the release is almost zero order up to day 10. Then, after day 10, the release curve suddenly becomes much steeper, i.e. the release rate becomes more time dependent (less zero order). Apparently this moment coincides with the moment that the size and amount of crystals in the polymer matrix has decreased beyond a certain point and from this point on the loss of steroid due to diffusion outside the ring can no longer be adequately counterbalanced by crystals going into dissolution. When the majority of crystals are dissolved the concentration gradient is no longer stabilized and hence a steeper curve is seen. The stabilization of the concentration gradient by this mechanism functions when the dissolving of the steroid crystals proceeds fast compared to the loss of steroid due to diffusion. So, the concentration drop is counter balanced to a certain extent, and the net effect will be zero provided the crystals dissolve relatively fast in the polymer.

In other words, the subject three-layer design is a three-layered ring comprising at least one compartment consisting of (i) an intermediate layer loaded with two steroids, one (steroid A) partly present in the crystalline phase and partly dissolved in the polymer and the other (steroid B) entirely dissolved in the polymer, (ii) a core loaded with steroid B (entirely dissolved and optionally in the same concentration as in the intermediate layer) and (iii) a placebo skin.

In the subject three-layered ring, steroid B is not only accommodated in the intermediate layer, but also in the core. In one embodiment of the subject invention, the concentration of steroid B is the same in the core and in the intermediate layer.

By loading both core and intermediate layer with steroid B, the reservoir for steroid B is largely increased, allowing a fairly constant release rate of this steroid over a prolonged

period (see figures 3 and 4). As a result of this design, the release rate of steroid A and the release rate of steroid B can be adjusted independently from each other. Moreover, by loading the core with steroid B, also back-diffusion of steroid B from the intermediate layer back to the core is prevented. Back-diffusion of steroid B would lead to a steadily decreasing concentration in the intermediate layer and thus a decreasing release profile upon storage (until even distribution of steroid B in core and intermediate layer). Also steroid A may back-diffuse into the core. This is however less critical since the concentration of steroid A in the intermediate layer is stabilized because of its presence in crystalline form. In a special embodiment of the subject invention, steroid A, in dissolved form, can however also be loaded into the core. This will reduce (or eliminate) internal diffusion effects.

Thus, the concept of this three-layer vaginal ring is to concentrate steroid in a relatively thin intermediate layer wherein part thereof will be present in the form of crystals dispersed in the thin intermediate layer. The desired release rate of steroid A is obtained by adjusting the skin thickness. Therefore, steroid A is incorporated in crystalline form and steroid B in dissolved form thereby making it possible to adjust the concentration of steroid B to the already pre-set skin thickness. Since the volume of the intermediate layer may be relatively small, this approach may lead to a relatively small content and may become depleted relatively fast. A possible too fast depletion of the three-layered ring is prevented by loading the core with the second steroid (B) as well.

In a different embodiment of the subject invention, the drug delivery system is a three-layered vaginal ring comprising at least one compartment consisting of (i) an intermediate layer loaded with steroid A partly present in the crystalline phase and partly dissolved in the polymer and (ii) a core loaded with steroid B which is entirely dissolved in the polymer and (iii) a placebo skin. This ring design, although containing only one steroid in the intermediate layer (as opposed to two steroids in the ring design described above), will, after some time, turn into the same design as the ring described above wherein there are two steroids in the intermediate layer. This is because over a period of time, steroid B will diffuse into the intermediate layer and at a particular point in time will contain (i) an intermediate layer medicated with two steroids, one (steroid A) partly present in the crystalline phase and partly dissolved in the polymer and the other (steroid B) entirely

dissolved in the polymer, (ii) a core loaded with steroid B (entirely dissolved) and (iii) a placebo skin.

5 The vaginal ring of the subject invention can be manufactured by the known process of extrusion, such as co-extrusion and/or blend-extrusion. The drug-loaded core, the drug-loaded intermediate layer and the non-medicated outer layer are all co-extruded. The fibres thus obtained are cut into pieces of the required length and each piece is assembled to a ring-shaped device in any suitable manner. The rings are then packed for example in a suitable sachet, optionally after being sterilized or disinfected.

10

The thermoplastic polymer that can be used in practising the invention, may in principle be any thermoplastic polymer or elastomer material suitable for pharmaceutical use, such as low density polyethylene, ethylene-vinylacetate copolymers and styrene-butadiene-styrene copolymers. In a specific embodiment, ethylene-vinylacetate copolymer (poly-EVA) is used
15 due to its excellent mechanical and physical properties (e.g. solubility of the steroids in the material). The poly-EVA material may be used for the core, the intermediate layer as well as the skin and can be any commercially available ethylene-vinylacetate copolymer, such as the products available under the trade names: Elvax, Evatane, Lupolen, Movriton, Ultrathene, Ateva and Vestypar.

20

In one embodiment both core and intermediate layer are made out of the same polymer grade. In another embodiment, the core and the intermediate layer are not made out of the same polymer grade in order to allow for further flexibility of the ring. By electing different polymer grades for the core and the intermediate layer, fine-tuning of the flexibility of the
25 ring is possible.

The vaginal ring according to the invention can be manufactured in any size as required. In one embodiment, the ring has an outer diameter (outer circumference) of between 50 and 60 mm and in another embodiment between 52 and 56 mm; the cross sectional diameter is
30 between about 2.5 and 5 mm, in a specific embodiment between about 3.0 and 4.5 mm, and in another embodiment between about 3.5 and 4.0 mm and in yet another embodiment is 4.0 mm.

It is also an object of the subject invention to provide an improved vaginal ring in which the intermediate layer and/or the core, in addition to steroids for contraception or hormone replacement, also comprises anti-microbials, e.g. to concomitantly treat and/or prevent sexually-transmitted diseases (STD's) such as HIV, herpes, chlamydia and gonorrhoea.

In the subject invention, the surface of the core body is more than 800 mm², and in another embodiment more than 1000 mm² and will typically be in the order of 1700-2200 mm², though significantly larger surfaces are possible, provided that the design (physical dimensions) of the vaginal ring prevents inconvenience for the subject. It may sometimes be required to add a second compartment which is a placebo compartment or a compartment loaded with one or more other drugs. Such an extra compartment may be necessary for example in practising hormonal replacement therapy, where the ratio between progestogen and estrogen is different from the ratio suitable for contraception. Such an extra compartment can also be necessary to administer, in addition to the steroids, anti-microbial drugs to treat and/or prevent STD's such as AIDS, chlamydia, herpes and gonorrhoea.

Any anti-microbial drug can be incorporated into a vaginal ring of the subject invention (in the intermediate layer and/or in the core and/or in an additional compartment). The anti-microbial drug can be any anti-bacterial drug such as any antibiotic, any anti-viral agent, any anti-fungal agent or any anti-protozoal agent. An example of an anti-microbial drug contemplated to be incorporated into the vaginal ring of the subject invention is mandelic acid condensation polymer (*Zanefeld et al. (2002), Fertility and Sterility 78(5): 1107-1115*). Another example is dapivirine (4-[[4-[2,4,6-trimethylphenyl]amino-2-pyrimidinyl]amino]benzotrile).

Figure 5 shows a schematic description of the vaginal ring of the subject invention. R_1 is the diameter of the three-layered fibre. R_2 is the radius of the core together with the intermediate layer and R_3 is the radius of the core. The ratios of R_1/R_2 and R_2/R_3 described in that figure are defined as follows:

Ranges	R_1/R_2	R_2/R_3
--------	-----------	-----------

Embodiment 1	1.0075-2.0000	1.0075-2.0000
Embodiment 2	1.0100-1.5000	1.0200-1.5000
Embodiment 3	1.0300-1.3000	1.0200-1.5000
Embodiment 4	1.0400-1.1800	1.0200-1.0500
Embodiment 5	1.0300-1.2000	1.0100-1.0900

As used herein, "room temperature" lies anywhere between about 18°C and about 30°C.

As used herein, a physically stable drug delivery system (ring) is a system which can be
 5 stored at about 18°C-30°C for at least about one and a half (1.5) year without steroid crystal
 formation on the surface of the skin of the vaginal ring.

The vaginal ring according to the invention is primarily designed for contraceptive use, but
 -as said above- may also be used under certain conditions in HRT (hormonal replacement
 10 therapy).

The vaginal ring of the subject invention may –as said above - also be used to concomitantly
 provide contraception and combat microbial disease. The microbial infection to be treated
 and/or prevented can be any bacterial, viral, fungal or protozoal infection. Specifically,
 15 sexually transmitted diseases such as HIV, chlamydia, gonorrhoea, or herpes may be treated
 by incorporation of an anti-microbial agent into the ring of the subject invention.

It is a further object of the invention to provide a method of contraception which comprises
 the steps of positioning a drug delivery system of the subject invention within the female
 20 vaginal tract and retaining the system within the vaginal tract for at least approximately 21
 days.

It is another object of the subject invention to provide a method of concomitantly providing
 contraception and treating or preventing a sexually transmitted disease which comprises the
 25 steps of positioning a drug delivery system of the subject invention within the female vaginal
 tract and retaining the system within the vaginal tract for at least approximately 21 days.

In one embodiment, the drug delivery system is removed after about 21 days for an approximate one week period to permit menstruation. In other embodiments, the drug delivery system is removed after about 42, 63, 84, 105, 126, 147, 186, 189, 210, 231, 252, 273, 294, 315, 336 or 357 days for an approximate one week period to permit menstruation.

After the approximate week to allow for menstruation, a new drug delivery system of the subject invention is inserted into the female vagina to provide contraception in the next female cyclus or cyclusses.

The subject invention further envisions a use of a drug delivery system of the subject invention for the manufacture of a contraceptive kit.

The subject invention further encompasses a use of a drug delivery system of the subject invention for the manufacture of a medicament for hormone replacement therapy.

The subject invention also provides a use of a drug delivery system of the subject invention for the manufacture of a combination preparation to provide contraception and to treat and/or prevent a sexually transmitted disease such as for example AIDS, herpes, chlamydia and gonorrhoea.

The progestogenic steroidal compound of the subject invention can be any suitable progestogen, such as desogestrel, etonogestrel, levonorgestrel, norgestimate, gestodene or any other steroidal compound with progestogenic activity. The estrogenic steroidal compound can be any suitable estrogen, such as estradiol, estriol, mestranol and ethinyl-estradiol. In a specific embodiment of the subject invention, the progestogen is etonogestrel. In a specific embodiment of the subject invention the estrogen for contraceptive use is ethinylestradiol. In another embodiment, estradiol is the estrogen used for HRT.

In one embodiment of the subject invention, ethinyl estradiol is present in the intermediate layer and in the core at about 0.05-1.5% by weight. In other embodiments, ethinyl estradiol is present in the intermediate layer and in the core at about 0.08-0.5% by weight, at about 0.09-0.20% by weight, at about 0.09-0.18% by weight or at about 0.09-0.15% by weight.

In one embodiment of the subject invention, etonogestrel is present in the intermediate layer at about 6-80% by weight. In other embodiments, etonogestrel is present in the intermediate layer at about 6-70% by weight, at about 10-53% by weight, at about 10-30% by weight, at
5 about 10-15% by weight, or at about 10-12% by weight.

The subject invention also provides a method of manufacturing the three-layered drug delivery system of the subject invention by:

- 10 (i) Producing a loaded (medicated) homogenous polymer core granulate and a loaded (medicated) homogenous polymer intermediate layer granulate;
- (ii) Co-extruding the core granulate and the intermediate layer granulate with a polymer skin granulate to form the three-layered drug delivery system.

The production of the loaded (medicated) homogenous polymer core granulate and loaded
15 (medicated) homogenous polymer intermediate layer granulate comprises:

- (a) grounding the polymer;
- (b) dry powder mixing the grounded polymer with the active compounds to be loaded in the intermediate layer;
- (c) dry powder mixing the grounded polymer with the active compound to be
20 loaded in the core;
- (d) blend extruding the resulting powder mixtures of steps (b) and (c);
- (e) cutting the resulting loaded polymer strands into granules, thereby obtaining a core granulate and an intermediate layer granulate;
- (f) lubricating both core granulate and intermediate granulate with a lubricant;
25 wherein steps (b) and (c) are interexchangeable.

The present invention is further described in the following examples which are not in any way intended to limit the scope of the invention as claimed.

30 EXAMPLES

EXAMPLE 1 – Preparation of the three-layered ring

Eight (8) three-layer fibres were prepared (A1-A4 and B1-B4). The fibres were stretched to 3.5 mm (Bx) and 4.0 mm (Ax) from a single capillary (4.1 mm).

5 In order to mix the active ingredients etonogestrel (steroid A) and ethinyl estradiol (steroid B) homogeneously through the polymer, two subsequent mixing steps were performed. In the first step, dry powder mixing was performed with the micronized active compounds and polymer powder. These micronized compounds were mixed with polymer powder in a stainless steel drum using a Rhönrad (Barrel-hoop principle) with a fixed rotation speed of
 10 approximately 26 rpm for 60 minutes. This first powder mixing step was performed to mix polymer and active compounds for both the core (polymer powder and micronized ethinyl estradiol) as well as for the intermediate layer (polymer powder, micronized ethinyl estradiol and micronized etonogestrel). Subsequently the homogenized powder mixture was blend
 15 extruded using a 25 mm co-rotating double screw blend extruder (Berztorff ZE25) and the resulting medicated polymer strands were cut into granules using an Scheer granulator. According to this process a batch core granulate and a batch intermediate layer granulate were manufactured. After granulation these batches were lubricated with magnesium stearate in order to facilitate the next processing step (co-extrusion). The composition of the granulate batches that was used to manufacture the tri-layer fibre, using a co-extrusion
 20 process, are described in Table 1 below.

Table 1:

Material	Composition	
	Core granulate	Intermediate layer granulate
Etonogestrel	-	10.3%
Ethinyl estradiol	0.095%	0.092%
Evatane 28-25	99.8%	89.5%
Magnesium Stearate	0.1%	0.1%
Total	100.0%	100.0%

Tri-layer co-extrusion

25 A Plastic Maschinenbau co-extruder (15/18 mm) in combination with an EX10, Fourné (10 mm) extruder was used for trico-extrusion. The 18 mm and the 15 mm Plastic Maschinenbau extruders processed the core and the intermediate layer respectively and the 10 mm Fourné extruder was used to process the skin (outer layer). The three extruders were connected with

a 3-compartment spinning block (Ankotec, Germany) with 3 separate spinning pumps (to control the volume flow rate (melt flow) of each layer). The three melt flows were combined in a spinneret resulting in a fibre with 3 layers. A capillary of 4.1 mm was used. All fibres were extruded at an extrusion temperature of 110°C.

5

The spinning rate was tuned to obtain the desired fibre diameter, either 3.5 mm or 4.0 mm, and the desired layer thickness for skin and intermediate layer was obtained by adjustment of the spinning pumps. Each of the tri-layer fibre variants was produced by using the appropriate spinning rate and spinning pump settings (totally 2 x 4 variants, A1-A4 and B1-B4). After approximately 20 minutes tri-layer co-extrusion of each variant, the tri-layer fibre was collected on a stainless steel reel for 30 minutes. The outer diameter of the fibre was measured on-line continuously using a laser micrometer and recorded. At the start and at the end of these 30 minutes, the diameter of the fibre, thickness of the middle layer, thickness of the skin was measured and recorded.

15

The loaded fibres were processed at an extrusion speed of 3 m/min for variants A and 3.9 m/min for variants B. Except variant 3 which was processed at 1.0 m/min for the fibre A3 and 1.3 m/min for the fibre B3.

20 *Fibre dimensions*

The fibre dimensions (outer diameter, intermediate layer thickness and skin thickness) were determined directly after processing and on 10 assembled rings. The outer diameter was determined by means of laser thickness gauge (Mitutoyo). The intermediate layer and skin thickness were determined using a microscope (Jena). The results for the loaded batches are shown in Tables 2a and 2b.

25

Table 2a: Fibre dimensions of 4.0 mm loaded fibres processed at an extrusion speed of 3 m/min (except variant A3, which was processed at 1 m/min)

Variant	Fibre diameter [mm]	Intermediate layer [µm]	Skin [µm]	Skin polymer	R1/R2	R2/R3
A1	4.00	67	66	Evatane 1020 VN3	1.0341	1.0359

A2	4.00	61	81	Evatane 1020 VN3	1.0422	1.0328
A3	3.99	67	294	Evatane 1040 VN4	1.1728	1.0410
A4	4.00	51	80	Evatane 1020 VN3	1.0417	1.0273

Table 2b: Fibre dimensions of 3.5 mm loaded fibres processed at an extrusion speed of 3.9 m/min (except variant B3, which was processed at 1.3 m/min)

variant	Fibre diameter [mm]	Intermediate layer [μm]	Skin [μm]	Skin polymer	R1/R2	R2/R3
B1	3.49	54	58	Evatane 1020 VN3	1.0344	1.0331
B2	3.51	52	73	Evatane 1020 VN3	1.0434	1.0319
B3	3.50	59	261	Evatane 1040 VN4	1.1753	1.0413
B4	3.50	48	70	Evatane 1020 VN3	1.0417	1.0294

5

The concentration of the active constituents in core and intermediate layer was identical for all rings (10.3% ENG, 0.092% EE in intermediate layer and 0.095 % EE in core). The concentration of 0.092 and 0.095% for the intermediate layer and core respectively, was considered (practically) identical.

10 *In-vitro release rates*

Results for in-vitro release are shown in Table 3, Figures 1 to 4 and Figures 6 to 13.

Figures 1 and 2 show the release rate of etonogestrel from one sample of each kind of ring tested. Figures 3 and 4 show the release rate of ethinyl estradiol from one sample of each kind of ring tested. Figures 6 to 13 also show release rates of etonogestrel and ethinyl

15 estradiol from one sample of each kind of ring tested (A1-A4 and B1-B4). In Table 3, the release rates are calculated from six (6) samples of each kind of ring tested.

Table 3: In vitro release rates for all produced batches at t=0.

Batch	In-vitro release rate of etonogestrel ($\mu\text{g/day/ring}$)				In-vitro release rate of EE ($\mu\text{g/day/ring}$)			
	Day 1	Average day (2-21)	Rsd (%)	Day 21	Day 1	Average day (2-21)	Rsd (%)	Day 21
A1	258-264	194	1	177-180	22-22	14	1	11-12

A2	216-225	162	1	149-152	19-20	12	1	10-10
A3	179-184	119	0	113-114	25-25	11	0	8-9
A4	213-221	156	1	130-132	19-20	12	1	10-10
B1	223-232	188	1	157-163	19-21	13	2	10-11
B2	191-197	158	1	139-143	18-19	11	1	9-10
B3	168-172	117	1	110-112	26-26	10	1	8-8
B4	182-196	145	2	104-111	17-19	11	2	9-9

The day 1 and day 21 release rate is presented as the range of the individual results of 6 rings (minimum and maximum value are given).

The average day 2-21 release represents the average release rate over the day 2 up to and including day 21. The presented value is the mean of 6 rings.

Assembly

The 4 mm batches (Ax) were cut to pieces of 157 mm and welded with a welding temperature of 130°C and a welding time of 15 second, on the TWI mono welding unit.

The 3.5 mm fibres were cut into pieces of 157 mm and the ends were glued together (Loctite, type 406 and 770; cat nr. 40621 and 77012).

Thus, a novel three layered ring design, with layers varying from 50 to 300 µm, was processed with limited variations in skin thickness and intermediate layer thickness.

EXAMPLE 2 – PHYSICAL STABILITY

The storage stability of NuvaRing® at normal storage temperature (up to 30°C) is limited
5 due to the formation of steroid crystals on the surface of the skin of the vaginal ring, which
leads to an increased on-set release, the so-called burst release and thus to a decreased
physical stability. The burst release (day 1 release) of 8 batches of a ring of the subject
invention was tested at time zero and after 12, 18 and 24 months storage at 30°C/75% R.H.
in a closed aluminum foil laminate sachet (WO 99/30976). The burst release of 3
10 representative NuvaRing® batches was also tested at time zero and after 12, 18 and 24
months storage at 30°C/75% R.H. in said closed aluminum foil laminate sachet. The release
rate at time zero was determined by analyzing 12 rings per batch and the release rate after
12, 18 and 24 months was determined by analyzing 6 rings per batch. The results of these
analyses are described in Tables 4, 5 and 6. It is apparent that the burst release of all three
15 NuvaRing® batches increases upon storage already after 12 months at 30°C. With exception
of variant A3, all seven batches of a ring of the subject invention show a constant or a lower
burst release after storage at 30°C. Visual examination of rings from batch A3, revealed that
the increase of the burst release is not due to the formation of steroid crystals on the surface
of the ring. The fact that the increase of the burst release of batch A3 is not due to crystal
20 formation on the ring surface is also shown by the small differences observed between
individual test result as indicated by the low RSD (relative standard deviation) value.

Table 4: day 1 release rate at time zero and after 12 months storage at 30°C/75%R.H.

NuvaRing®	On-Set release			
	Individual results t=0	RSD (%)	Individual results t=12 months	RSD (%)
N1	186.4, 193.2, 186.6, 185.5, 189.9, 188.5, 187.8, 187.6, 189.6, 184.4, 188.3, 190.2	1.3	210.6, 191.0, 179.5, 178.6, 171.8, 205.9	8.3
N2	197.4, 199.0, 199.3, 198.2, 199.7, 198.3, 205.1, 200.5, 200.4, 200.1, 200.3, 198.3	1.0	188.5, 190.5, 194.4, 195.4, 215.3, 200.1	4.9
N3	194.6, 197.5, 197.0, 193.8 198.3, 197.5, 198.3, 199.4, 198.7, 204.5, 211.6, 201.8	2.4	255.1, 325.3, 276.3, 215.0 505.9, 222.5	36.6
Ring of the subject invention				
A1	260.7, 264.9, 263.7, 260.3, 263.6, 261.6, 265.2, 264.7, 263.7, 261.7, 265.5, 258.4	0.9	210.2, 207.1, 220.7, 217.2, 209.3, 209.2	2.5
A2	219.5, 221.6, 219.5, 219.2, 219.4, 225.0, 222.5, 221.7, 215.8, 223.6, 218.0, 221.2	1.1	184.2, 181.1, 176.9, 179.9, 177.3, 177.0	1.6
A3	181.0, 180.8, 180.0, 182.2, 179.3, 180.7, 180.5, 181.5, 181.2, 182.1, 180.7, 193.6	0.6	198.7, 194.0, 197.7, 202.5, 199.0, 199.5	1.4
A4	217.9, 213.4, 216.3, 216.9, 215.1, 219.2, 220.1, 220.6, 221.1, 218.0, 217.9, 219.2,	1.1	169.1, 171.1, 176.6, 176.6, 175.0, 169.3	2.0

B1	222.9, 230.0, 225.5, 227.8, 230.5, 229.4, 229.5, 226.8, 226.4, 231.9, 232.3, 226.6	1.2	181.6, 178.4, 180.8, 181.8, 178.1, 179.0	0.9
B2	194.8, 194.5, 194.3, 197.4, 190.9, 195.2, 194.9, 192.8, 191.5, 192.6, 194.2, 194.0,	0.9	154.1, 152.5, 151.0, 154.3, 154.1, 153.7	0.8
B3	171.3, 171.3, 170.1, 171.4, 168.8, 172.0, 171.5, 171.5, 169.7, 169.7, 167.5, 167.9	0.9	179.0, 177.8, 176.6, 183.2, 179.1, 178.9	1.2
B4	188.2, 189.9, 195.8, 185.9, 189.9, 181.7, 194.3, 192.2, 191.5, 182.5, 189.7, 193.6	2.3	155.1, 150.6, 148.8, 150.4, 151.6, 148.3	1.6

Table 5: day 1 release rate at time zero and after 18 months storage at 30°C/75%R.H.

NuvaRing®	On-Set release			
	Individual results t=0	RSD (%)	Individual results t=18 months	RSD (%)
N1	186.4, 193.2, 186.6, 185.5, 189.9, 188.5, 187.8, 187.6, 189.6, 184.4, 188.3, 190.2	1.3	188.6, 237.0, 301.8, 252.6, 234.0, 186.4	18.5
N2	197.4, 199.0, 199.3, 198.2, 199.7, 198.3, 205.1, 200.5, 200.4, 200.1, 200.3, 198.3	1.0	210.8, 183.0, 261.6, 202.1, 241.8, 249.4	13.7
N3	194.6, 197.5, 197.0, 193.8 198.3, 197.5, 198.3, 199.4, 198.7, 204.5, 211.6, 201.8	2.4	479.6, 560.2, 510.2, 483.0, 579.4, 477.9	8.6
Ring of the subject invention				
A1	260.7, 264.9, 263.7, 260.3, 263.6, 261.6, 265.2, 264.7, 263.7, 261.7, 265.5, 258.4	0.9	205.5, 209.1, 201.9, 207.5, 199.0, 198.3	2.2
A2	219.5, 221.6, 219.5, 219.2, 219.4, 225.0, 222.5, 221.7, 215.8, 223.6, 218.0, 221.2	1.1	172.5, 174.0, 174.0, 180.5, 177.0, 174.5	1.7
A3	181.0, 180.8, 180.0, 182.2, 179.3, 180.7, 180.5, 181.5, 181.2, 182.1, 180.7, 193.6	0.6	194.0, 203.4, 197.9, 201.5, 190.2, 197.9	2.5
A4	217.9, 213.4, 216.3, 216.9, 215.1, 219.2, 220.1, 220.6, 221.1, 218.0, 217.9, 219.2,	1.1	166.9, 163.2, 165.7, 168.1, 159.4, 166.4	1.9

B1	222.9, 230.0, 225.5, 227.8, 230.5, 229.4, 229.5, 226.8, 226.4, 231.9, 232.3, 226.6	1.2	171.8, 169.7, 167.6, 173.7, 171.6, 169.4	1.3
B2	194.8, 194.5, 194.3, 197.4, 190.9, 195.2, 194.9, 192.8, 191.5, 192.6, 194.2, 194.0,	0.9	147.6, 146.1, 146.0, 146.8, 142.9, 143.7	1.3
B3	171.3, 171.3, 170.1, 171.4, 168.8, 172.0, 171.5, 171.5, 169.7, 169.7, 167.5, 167.9	0.9	172.3, 170.9, 171.7, 172.0, 169.5, 177.1	1.5
B4	188.2, 189.9, 195.8, 185.9, 189.9, 181.7, 194.3, 192.2, 191.5, 182.5, 189.7, 193.6	2.3	147.5, 146.5, 142.4, 127.3, 145.6, 145.5	5.4

Table 6: day 1 release rate at time zero and after 24 months storage at 30°C/75%R.H.

NuvaRing®	On-Set release			
	Individual results t=0	RSD (%)	Individual results t=24 months	RSD (%)
N1	186.4, 193.2, 186.6, 185.5, 189.9, 188.5, 187.8, 187.6, 189.6, 184.4, 188.3, 190.2	1.3	199.0, 175.9, 219.9, 188.9, 206.9, 184.8	8.2
N2	197.4, 199.0, 199.3, 198.2, 199.7, 198.3, 205.1, 200.5, 200.4, 200.1, 200.3, 198.3	1.0	247.0, 275.7, 297.3, 371.9, 215.6, 269.0	19.0
N3	194.6, 197.5, 197.0, 193.8 198.3, 197.5, 198.3, 199.4, 198.7, 204.5, 211.6, 201.8	2.4	271.3, 262.2, 268.1, 247.2, 436.6, 329.4	23.6
Ring of the subject invention				
A1	260.7, 264.9, 263.7, 260.3, 263.6, 261.6, 265.2, 264.7, 263.7, 261.7, 265.5, 258.4	0.9	206.4, 208.6, 201.8, 203.7, 209.9, 213.7	2.1
A2	219.5, 221.6, 219.5, 219.2, 219.4, 225.0, 222.5, 221.7, 215.8, 223.6, 218.0, 221.2	1.1	179.1, 172.1, 173.4, 179.8, 179.8, 172.8	2.0
A3	181.0, 180.8, 180.0, 182.2, 179.3, 180.7, 180.5, 181.5, 181.2, 182.1, 180.7, 193.6	0.6	197.7, 195.8, 196.8, 197.8, 197.7, 204.9	1.6
A4	217.9, 213.4, 216.3, 216.9, 215.1, 219.2, 220.1, 220.6, 221.1, 218.0, 217.9, 219.2,	1.1	170.1, 163.6, 163.5, 168.2, 164.6, 166.9	1.6

B1	222.9, 230.0, 225.5, 227.8, 230.5, 229.4, 229.5, 226.8, 226.4, 231.9, 232.3, 226.6	1.2	171.3, 170.3, 172.1, 175.9, 168.2, 171.8	1.5
B2	194.8, 194.5, 194.3, 197.4, 190.9, 195.2, 194.9, 192.8, 191.5, 192.6, 194.2, 194.0,	0.9	143.5, 145.8, 146.8, 148.0, 150.0, 148.8	1.6
B3	171.3, 171.3, 170.1, 171.4, 168.8, 172.0, 171.5, 171.5, 169.7, 169.7, 167.5, 167.9	0.9	173.9, 173.0, 173.9, 177.4, 175.4, 175.9	0.9
B4	188.2, 189.9, 195.8, 185.9, 189.9, 181.7, 194.3, 192.2, 191.5, 182.5, 189.7, 193.6	2.3	145.0, 145.6, 144.9, 143.9, 142.6, 143.4	0.8

EXAMPLE 3- improved three-layered ring versus ring described in US 4,292,965

5 This example illustrates the benefits of the subject improved three-layered ring relative to the three-layered ring described in US 4,292,965.

In US 4,292,965 two steroids are accommodated in the intermediate layer; no steroid is present in the core.

10 The essence of the improved three-layer ring is that the release rate of two or more steroids can be adjusted independently from one another and that the ring is able to sustain this release rate for a more prolonged period of time while maintaining physical stability at room temperature conditions. This example demonstrates the advantage of the improved three-layered ring which also has a loaded core over a ring design with a non-medicated core as
15 described in US 4,292,965.

It is not possible to load more than one steroid in the intermediate layer in the crystalline form and have independent release. In order to adjust the release rate of two (or more) steroids from one compartment, only one steroid can be present in the crystalline phase and
20 the other(s) has to be present in the dissolved phase. In case steroid A is partly present in the crystalline phase, the steroid in the crystalline lattice will be in dynamic equilibrium with dissolved steroid. Since the concentration of steroid A is pre-determined, the release rate of steroid A can be adjusted by choosing the right skin thickness. Considering the fact that the skin thickness is already used as a means to adjust the release rate of steroid A, the release
25 rate of the second component, steroid B can only be tuned by choosing the appropriate concentration. Since steroid B is only present in the dissolved form, more steroid can be incorporated into the ring (while maintaining the same concentration gradient over the membrane) by increasing the volume of the reservoir (the core). Thus, the volume of the reservoir determines the amount of dissolved steroid B that can be loaded in the ring.

30

For ring A2 of the subject invention (see example 1) the volume of the intermediate layer and core reservoir can be calculated as follows. The fibre dimensions of ring A2 are

approximately; length 15.7 cm, diameter 4.0 mm, thickness intermediate layer about 60 μ m and skin about 80 μ m and the volume of the intermediate layer and the core of approximately $V_{\text{int}} = 0.11$ ml and $V_{\text{core}} = 1.71$ ml. The densities of both core and intermediate layer are relatively close to 1 g/ml and consequently the mass of the core and intermediate layer are approximately 1.71 g and 0.11 g respectively. The concentration EE in the core and intermediate layer is approximately 0.095% m/m. and hence the core contains approximately 1620 μ g EE and the intermediate layer contains approximately 106 μ g of EE. Thus, in this particular case (A2) more than approximately 15 times more EE can be loaded in the improved three-layered design compared to a ring with a non-medicated core.

The release of EE from ring A2 as function of time is presented in figure 3 and can be used to illustrate the advantage of loading the core with EE. The semi-steady state release (release day 2 -21) is between 15 and 10 μ g/day and the content of the intermediate layer alone (106 μ g) would be insufficient to sustain a fairly constant release rate over a period longer than a few days. After less than 7 days the intermediate layer would be almost completely depleted and the release rate would drop already dramatically after a few days.

Moreover, in a ring design such as that of US 4,292,965, due to internal diffusion into the core, a non-equilibrium situation is obtained and consequently the concentration EE in the intermediate layer will decrease, which results in a pharmaceutical product with an unstable release profile. However, when the core is loaded with the same concentration EE as in the intermediate layer the desired equilibrium situation is obtained.

This non-steady state behaviour due to internal diffusion (also called back diffusion) is inherent to the three-layer design according to US 4,292,965 while the improved three layer design eliminates also these undesired effects.

EXAMPLE 4 – Preparation of additional three-layered rings

Twenty (20) additional three-layer fibres were prepared (E-X). The fibre variants had a dimension of 4 mm (E-V), 3 mm (variant W) and 5 mm (variant X). All fibres were spun
5 from a single capillary (3.6 mm).

Several core and intermediate granulates (C1-C4 and D1-D2 respectively) were prepared using essentially the same method as described in Example 1 with the following minor changes:

10 Granulates C4, D1 and D2 were mixed in a stainless steel drum using a Rhönrad (Barrel-hoop principle) with a fixed speed of approximately of 47 rpm for 60 minutes.

Table 7: Composition core granulates

Variant	Etonogestrel	Ethinyl estradiol	Ateva 2820A	Magnesium stearate	Total
C1	--	0.16%	99.7%	0.1%	100.0%
C2	--	0.13%	99.8%	0.1%	100.0%
C3	--	0.20%	99.7%	0.1%	100.0%
C4	0.33 %	0.16%	99.4%	0.1%	100.0%

15 Table 8: Composition intermediate layer granulates

Variant	Etonogestrel	Ethinyl estradiol	Ateva 2820A	Magnesium stearate	Total
D1	10.5%	0.16%	89.2%	0.1%	100.0%
D2	52.5%	0.16%	47.2%	0.1%	100.0%

Tri-layer co-extrusion

A Fourné trico-extruder (25/18/18 mm) was used for the production of the three-layered
20 fibres. The 25 mm extruder processed the core layer, whereas the two 18 mm extruders processed the intermediate layer and the skin (outer layer) respectively. The three extruders

were connected with a 3-compartment spinning block with 3 separate spinning pumps (to control the volume flow rate (melt flow) of each layer). The three melt flows were combined in a spinneret resulting in a fibre with 3 layers. A capillary of 3.6 mm was used. All fibres were extruded at an extrusion temperature of 110°C.

5

The spinning rate was adjusted to obtain the desired fibre diameter of 3, 4 or 5 mm. The desired layer thickness for skin and intermediate layer was obtained by adjustment of the spinning pumps. Each of the tri-layer fibre variants was produced by using the appropriate spinning rate and spinning pump settings (totally 20 variants, E-X). After approximately 20 minutes tri-layer co-extrusion of each variant, the tri-layer fibre was collected on a stainless steel reel for 120 minutes. The outer diameter of the fibre was measured on-line continuously using a laser micrometer and recorded. At the start and at the end of these 120 minutes, the diameter of the fibre, thickness of the middle layer, and the thickness of the skin was measured and recorded. The variants W and X were collected for only 30 minutes.

10

The loaded fibres were processed at an extrusion speed of 2.00 m/min for variants E-V, at 3.59 m/min for variant W, and at 1.28 m/min for variant X.

15

Fibre dimensions

The intermediate layer thickness and skin thickness were determined for each fibre variant from fibre pieces of 4 samples during the trico-extrusion . The outer diameter was determined for each fibre variant from fibre pieces of 6 samples during processing on trico-extruded fibres . The outer diameter was determined by means of a laser thickness gauge (Zumbach). The intermediate layer and skin thickness were determined using a microscope (Jena). The results for the loaded batches are shown in Tables 9a, 9b and 9c.

20

25

Table 9a: Fibre dimensions of 4 mm loaded fibres processed at an extrusion speed of 2.00 m/min

Variant	Fibre diameter [mm]	Composition core	Intermediate layer [μm]	Composition intermediate layer	Skin [μm]	R1/R2	R2/R3	Skin polymer
E	4.01	C1	61	D1	110	1.0580	1.0333	Ateva 1070
F	4.01	C3	60	D1	100	1.0525	1.0325	Ateva 1070
G	4.02	C3	63	D1	126	1.0669	1.0346	Ateva 1070
H	4.02	C2	53	D1	94	1.0491	1.0284	Ateva 1070
I	4.04	C2	62	D1	123	1.0648	1.0338	Ateva 1070
J	4.02	C1	148	D1	110	1.0579	1.0845	Ateva 1070
K	4.00	C1	28	D2	111	1.0588	1.0150	Ateva 1070
L	4.03	C4	67	D1	112	1.0589	1.0365	Ateva 1070
M	4.01	C1	61	D1	146	1.0780	1.0339	Ateva 1231
N	4.03	C2	60	D1	133	1.0701	1.0329	Ateva 1231
O	4.01	C2	63	D1	167	1.0909	1.0355	Ateva 1231
P	4.02	C3	63	D1	132	1.0703	1.0347	Ateva 1231
Q	4.02	C3	60	D1	161	1.0871	1.0335	Ateva 1231
R	4.04	C1	70	D1	315	1.1848	1.0428	Ateva 1525
S	4.05	C2	69	D1	277	1.1585	1.0411	Ateva 1525
T	4.02	C2	68	D1	335	1.2000	1.0423	Ateva 1525
U	4.04	C3	67	D1	298	1.1731	1.0405	Ateva 1525
V	4.04	C3	65	D1	334	1.1981	1.0401	Ateva 1525

5

Table 9b: Fibre dimensions of 3 mm loaded fibres processed at an extrusion speed of 3.59 m/min

Variant	Fibre diameter [mm]	Composition core	Intermediate layer [μm]	Composition intermediate layer	Skin [μm]	R1/R2	R2/R3	Skin polymer
W	3.03	C1	45	D1	83	1.0580	1.0324	Ateva 1070

10

Table 9c: Fibre dimensions of 5 mm loaded fibres processed at an extrusion speed of 1.28 m/min

Variant	Fibre diameter [mm]	Composition core	Intermediate layer [μm]	Composition intermediate layer	Skin [μm]	R1/R2	R2/R3	Skin polymer
X	5.00	C1	74	D1	138	1.0584	1.0323	Ateva 1070

5 *In-vitro release rates*

Results for in-vitro release are shown in Table 10 and Figures 14 to 21 which show release rates of etonogestrel and ethinyl estradiol of all fibres (E-W). In Table 10 and also in Figures 14-21, the release rates are calculated from six (6) samples of each kind of ring tested.

10 **Table 10:** In vitro release rates for all produced batches at $t=0$

Batch	In-vitro release rate of etonogestrel ($\mu\text{g/day/ring}$)				In-vitro release rate of EE ($\mu\text{g/day/ring}$)			
	Day 1	Average day (2-21)	Rsd (%)	Day 21	Day 1	Average day (2-21)	Rsd (%)	Day 21
E	140-153	94	1	89-90	23-24	14	3	12-13
F	153-162	108	2	99-104	29-30	19	2	17-18
G	125-131	82	1	76-79	24-25	15	2	12-14
H	148-157	106	2	97-101	20-21	13	3	10-12
I	122-127	82	1	76-79	17-18	10	4	8-9
J	208-214	101	1	91-93	23-24	14	2	12-13
K	123-135	95	2	88-93	21-23	13	3	11-12
L	178-187	98	2	87-91	21-23	13	3	11-11
M	187-197	123	1	113-117	34-35	19	2	16-17
N	193-198	133	1	121-125	30-31	17	2	14-15
O	165-171	106	1	98-101	26-28	14	2	11-12
P	182-208	138	1	127-131	39-44	25	2	22-23
Q	170-180	112	1	103-107	38-40	21	2	19-19

Batch	In-vitro release rate of etonogestrel (µg/day/ring)				In-vitro release rate of EE (µg/day/ring)			
	Day 1	Average day (2-21)	Rsd (%)	Day 21	Day 1	Average day (2-21)	Rsd (%)	Day 21
R	186-203	118	1	109-113	26-29	19	2	15-17
S	226-236	131	1	123-126	36-38	18	2	14-15
T	190-197	110	1	102-105	27-29	15	2	12-12
U	218-224	125	1	116-119	41-44	24	2	20-22
V	181-193	111	1	103-107	30-32	22	2	19-19
W	120-122	96	1	83-85	21-21	13	2	11-12
X	134-144	84	3	77-84	21-22	12	3	10-12

The day 1 and day 21 release rate is presented as the range of the individual results of 6 rings (minimum and maximum value are given)

The average day 2-21 release represents the average release rate over the day 2 up to and including day 21. The presented value is the mean of 6 rings.

Assembly

The 4 mm fibres (E-V) were cut to pieces of 157 mm and welded with a welding temperature of 130°C and a welding time of 17 seconds, on a CCM (Centrum voor Constructie en Mechatronica, The Netherlands) assembly unit. Fibres W and X were manually cut to 157 mm and the fibre ends were glued together using Loctite adhesive (type 406 and 770; cat nr. 40621 and 77012).

CLAIMS

1. A drug delivery system comprising at least one compartment consisting of (i) a drug-
5 loaded thermoplastic polymer core, (ii) a drug-loaded thermoplastic polymer intermediate
layer and (iii) a non-medicated thermoplastic polymer skin covering the intermediate
layer, wherein said intermediate layer is loaded with (a) crystals of a first
pharmaceutically active compound and with (b) a second pharmaceutically active
10 compound in dissolved form and wherein said core is loaded with said second compound
in dissolved form.
2. A drug delivery system according to claim 1 which is physically stable at about 18-30°C.
3. A drug delivery system according to claim 1 wherein said second compound in the core
15 is present in the same concentration as in the intermediate layer.
4. A drug delivery system according to claim 1, characterised in that the delivery system has
a substantially ring-shaped form and is intended for vaginal administration.
- 20 5. A drug delivery system according to claim 1, wherein said first active compound is a
steroid and said second active compound is a steroid.
6. A drug delivery system according to claim 5, wherein said first active steroid is a
progestogen.
- 25 7. A drug delivery system according to claim 5, wherein said second active steroid is an
estrogen.
8. A drug delivery system according to claim 7, wherein the estrogen is ethinyl estradiol.
- 30 9. A drug delivery system according to claim 6, wherein the progestogen is etonogestrel.

10. A drug delivery system according to claim 1, wherein the first active compound is etonogestrel and the second active compound is ethinyl estradiol.
11. A drug delivery system according to claim 1, characterised in that at least the skin but
5 optionally also the core and the intermediate layer comprise ethylene-vinylacetate copolymer as the thermoplastic polymer .
12. A drug delivery system according to claim 11, characterised in that the core and the
10 intermediate layer comprise the same grade of ethylene-vinylacetate copolymer as the thermoplastic polymer.
13. A drug delivery system according to claim 11, characterised in that the core and the
intermediate layer comprise a different grade of ethylene-vinylacetate copolymer as the
15 thermoplastic polymer .
14. A drug delivery system according to claim 1 characterised in that the core is additionally
loaded with the first compound.
15. A drug delivery system according to claim 8 wherein ethinyl estradiol is present in the
20 intermediate layer and in the core at about 0.05-1.5% by weight .
16. A drug delivery system according to claim 15 wherein ethinyl estradiol is present in the
intermediate layer and in the core at about 0.08-0.5% by weight .
- 25 17. A drug delivery system according to claim 16 wherein ethinyl estradiol is present in the
intermediate layer and in the core at about 0.09-0.18% by weight.
18. A drug delivery system according to claim 17 wherein ethinyl estradiol is present in the
intermediate layer and in the core at about 0.09-0.15% by weight.
30
19. A drug delivery system according to claim 16 wherein ethinyl estradiol is present in the
intermediate layer and in the core at about 0.09-0.20% by weight.

20. A drug delivery system according to claim 9 wherein etonogestrel is present in the intermediate layer at about 6-80% by weight.
- 5 21. A drug delivery system according to claim 20 wherein etonogestrel is present in the intermediate layer at about 6-70% by weight.
22. A drug delivery system according to claim 21 wherein etonogestrel is present in the intermediate layer at about 10-53% by weight.
- 10 23. A drug delivery system according to claim 22 wherein etonogestrel is present in the intermediate layer at about 10-30% by weight.
24. A drug delivery system according to claim 23 wherein etonogestrel is present in the intermediate layer at about 10-15% by weight.
- 15 25. A drug delivery system according to claim 24 wherein etonogestrel is present in the intermediate layer at about 10-12% by weight.
- 20 26. A drug delivery system according to claim 1 wherein the ratio R_1/R_2 as described in Figure 5 is between about 1.0075-2.0000 and the ratio R_2/R_3 is between about 1.0075-2.0000.
- 25 27. A drug delivery system according to claim 26 wherein the ratio R_1/R_2 as described in Figure 5 is between about 1.0100-1.5000 and the ratio R_2/R_3 is between about 1.0200-1.5000.
- 30 28. A drug delivery system according to claim 27 wherein the ratio R_1/R_2 as described in Figure 5 is between about 1.0300-1.3000 and the ratio R_2/R_3 is between about 1.0200-1.5000.

29. A drug delivery system according to claim 28 wherein the ratio R_1/R_2 as described in Figure 5 is between about 1.0400-1.1800 and the ratio R_2/R_3 is between about 1.0200-1.0500.
- 5 30. A drug delivery system according to claim 1 wherein the ratio R_1/R_2 as described in Figure 5 is between about 1.0300-1.2000 and the ratio R_2/R_3 is between about 1.0100-1.0900.
- 10 31. A drug delivery system according to claims 5-30 characterised in that the intermediate layer additionally contains an anti-microbial agent.
32. A drug delivery system according to claims 5-30 characterised in that the core additionally contains an anti-microbial agent.
- 15 33. A drug delivery system according to any one of the preceding claims characterised in that the device contains two compartments.
34. A drug delivery system according to claim 33 wherein the second compartment contains an anti-microbial agent.
- 20 35. A drug delivery system according to claims 31-34 wherein the anti-microbial agent is mandelic acid condensation polymer.
- 25 36. A method of contraception which comprises the steps of (i) positioning the drug delivery system of claims 1-30 within the female vaginal tract and (ii) retaining the system within the vaginal tract for at least about 21 days.
- 30 37. A method of contraception which comprises the steps of (i) positioning the drug delivery system of claims 1-30 within the female vaginal tract (ii) retaining the system within the vaginal tract for at least about 21 days and (iii) removing the system for an approximate one week period to permit menstruation.

38. A method of concomitantly providing contraception and treating or preventing a sexually transmitted disease which comprises the steps of (i) positioning the drug delivery system of claims 31-35 within the female vaginal tract and (ii) retaining the system within the vaginal tract for at least about 21 days.
- 5
39. A method of concomitantly providing contraception and treating or preventing a sexually transmitted disease which comprises the steps of (i) positioning the drug delivery system of claims 31-35 within the female vaginal tract (ii) retaining the system within the vaginal tract for at least about 21 days and (iii) removing the system for an approximate one
- 10 week period to permit menstruation.
40. A use of the drug delivery system of claims 1-30 for the manufacture of a contraceptive kit.
- 15 41. A use of the drug delivery system of claims 1-30 for the manufacture of a medicament for hormone replacement therapy.
42. A use of the drug delivery system of claims 31-35 for the manufacture of a combination preparation to provide contraception and to treat and/or prevent a sexually transmitted
- 20 disease.
43. The use of claim 42 wherein the disease is AIDS.
44. The use of claim 42 wherein the disease is herpes.
- 25 45. The use of claim 42 wherein the disease is chlamydia.
46. The use of claim 42 wherein the disease is gonorrhoea.
- 30 47. A method of manufacturing the three-layered drug delivery system of claim 1 comprising:
- (iii) Producing a loaded homogenous polymer core granulate and a loaded homogenous polymer intermediate layer granulate;

- (iv) Co-extruding the core granulate and the intermediate layer granulate with a polymer skin granulate to form the three-layered drug delivery system.

48. A method according to claim 47 wherein step (i) comprises:

- 5 (a) grounding the polymer;
- (b) dry powder mixing the grounded polymer with the active compounds to be loaded in the intermediate layer;
- (c) dry powder mixing the grounded polymer with the active compound to be loaded in the core;
- 10 (d) blend extruding the resulting powder mixtures of steps (b) and (c);
- (e) cutting the resulting loaded polymer strands into granules, thereby obtaining a core granulate and an intermediate layer granulate;
- (f) lubricating both core granulate and intermediate granulate with a lubricant;
- wherein steps (b) and (c) are interexchangeable.

15

49. A drug delivery system comprising at least one compartment consisting of (i) a drug-loaded thermoplastic polymer core, (ii) a drug-loaded thermoplastic polymer intermediate layer and (iii) a non-medicated thermoplastic polymer skin covering the intermediate layer, wherein said intermediate layer is loaded with crystals of a first pharmaceutically active compound and wherein said core is loaded with a second pharmaceutically active compound in dissolved form.
- 20




Figure 1




Figure 2




Figure 3

4/21




Figure 4




Figure 5




Figure 6




Figure 7




Figure 8




Figure 9

10/21




Figure 10

11/21




Figure 11

12/21




Figure 12




Figure 13




Figure 14




Figure 15




Figure 16




Figure 17




Figure 18




Figure 19




Figure 20




Figure 21