

(12) UK Patent

(19) GB

(11) 2526758

(13) B

(45) Date of B Publication

26.08.2020

(54) Title of the Invention: Methods for artificially aging aluminum-zinc-magnesium alloys, and products based on the same

(51) INT CL: C22F 1/053 (2006.01)

(21) Application No: 1517864.3

(22) Date of Filing: 12.03.2014

Date Lodged: 09.10.2015

(30) Priority Data:  
(31) 13827918 (32) 14.03.2013 (33) US

(86) International Application Data:  
PCT/US2014/024576 En 12.03.2014

(87) International Publication Data:  
WO2014/159647 En 02.10.2014

(43) Date of Reproduction by UK Office 02.12.2015

(72) Inventor(s):

Xinyan Yan  
Wenping Zhang  
Dana Clark  
James Daniel Bryant  
Jen Lin

(73) Proprietor(s):

Alcoa USA Corp  
201 Isabella Street, Pittsburgh, PA 15212-5858,  
United States of America

(74) Agent and/or Address for Service:

Forresters IP LLP  
Skygarden, Erika-Mann-Str. 11, Munich 80636,  
Germany

(56) Documents Cited:

WO 1995/024514 A1 US 3305410 A  
US 20090269608 A1 US 20080173378 A1  
US 20060289093 A1 US 20030213537 A1

(58) Field of Search:

As for published application 2526758 A viz:

INT CL B32B, C22C, C22F

Other: eKOMPASS  
updated as appropriate


Additional Fields  
Other: None

GB

2526758

B

FIG. 1



# METHODS FOR ARTIFICIALLY AGING ALUMINUM-ZINC-MAGNESIUM ALLOYS, AND PRODUCTS BASED ON THE SAME

## BACKGROUND

[001] Aluminum alloys are useful in a variety of applications. However, improving one property of an aluminum alloy without degrading another property is elusive. For example, it is difficult to increase the strength of an alloy without decreasing the toughness of an alloy. Other properties of interest for aluminum alloys include corrosion resistance and fatigue crack growth resistance, to name two.

## SUMMARY OF THE DISCLOSURE

[002] Broadly, the present patent application relates to improved methods of artificially aging aluminum alloys having zinc and magnesium, and products based on the same. As used herein, aluminum alloys having zinc and magnesium are aluminum alloys where at least one of the zinc and the magnesium is the predominate alloying ingredient other than aluminum, and whether such aluminum alloys are casting alloys (i.e., 5xx.x or 7xx.x alloys) or wrought alloys (i.e., 5xxx or 7xxx alloy). The aluminum alloys having zinc generally comprise from 2.5 to 12 wt. % Zn, from 1.0 to 5.0 wt. % Mg and may include up to 3.0 wt. % Cu. In one embodiment, the aluminum alloy comprises 4.0 - 5.0 wt. % Zn and 1.0 - 2.5 wt. % Mg.

[003] The method generally includes:

- (a) casting an aluminum alloy having from 2.5 - 12 wt. % Zn and from 1.0 to 5.0 wt. % Mg, then;
- (b) optionally hot working or cold working the aluminum alloy;
- (c) after the casting step (a) and the optional step (b), solution heat treating and then quenching the aluminum alloy;
- (d) after step (c), optionally working the aluminum alloy; and
- (e) after step (c) and the optional step (d), artificially aging the aluminum alloy, wherein the artificial aging step (e) comprises:
  - (i) first aging the aluminum alloy at a first temperature of from about 154°C (310°F) (or about 166°C (330°F)) to 277°C (530°F) and for a first aging time of from 5 minutes to 45 minutes;
  - (ii) second aging the aluminum alloy at a second temperature for a second aging time of at least 30 minutes, wherein the second temperature is lower than the

first temperature.

The methods may realize an improved combination of properties and/or improved throughput relative to conventional aging processes.

[004] The casting step (a) may be any suitable casting step for a wrought aluminum alloy or a casting aluminum alloy. Wrought aluminum alloys may be cast, for example, by direct chill casting and/or continuous casting (e.g., via twin belt casting), among other methods. Casting aluminum alloys are shape cast, and may be cast via any suitable shape casting method, including permanent mold casting, high pressure die casting, sand mold casting, investment casting, squeeze casting and semi-solid casting, among others.

[005] After the casting step (a), the method may include (b) optionally hot working and/or cold working the cast aluminum alloy. When the aluminum alloy is a wrought aluminum alloy, it is generally hot worked and may be cold worked after the casting step. This optional hot working step may include rolling, extruding and/or forging. The optional cold working step may include flow-forming, drawing and other cold working techniques. This optional step (b) is not completed when the aluminum alloy is a shape cast aluminum alloy. A homogenization step may occur before any hot working step (e.g., for wrought aluminum alloys).

[006] After the optional hot working and/or cold working step (b), the method includes (c) solution heat treating and then quenching the aluminum alloy. Solution heat treating and then quenching, and the like, means heating an aluminum alloy to a suitable temperature, generally above the solvus temperature, holding at that temperature long enough to allow soluble elements to enter into solid solution, and cooling rapidly enough to hold the elements in solid solution. The solution heat treating may include placing the aluminum alloy in a suitable heating apparatus for a suitable period of time. The quenching (cooling) may be accomplished in any suitable manner, and via any suitable cooling medium. In one embodiment, the quenching comprises contacting the aluminum alloy with a gas (e.g., air cooling). In another embodiment, the quenching comprises contacting the aluminum alloy sheet with a liquid. In one embodiment, the liquid is aqueous based, such as water or another aqueous based cooling solution. In one embodiment, the liquid is water and the water temperature is at about ambient temperature. In another embodiment, the liquid is water, and the water temperature is at about boiling temperature. In another embodiment, the liquid is an oil. In one embodiment, the oil is hydrocarbon based. In another embodiment, the oil is silicone based.

[007] After the solution heat treating and then quenching the aluminum alloy step (c), the method may optionally include (d) working the aluminum alloy body, such as by stretching 1-10% (e.g., for flatness and/or stress relief) and/or inducing a high amount of cold work (e.g., 25-90%), as taught by commonly-owned U.S. Patent Application Publication No. 2012/0055888. This optional step (d) may include hot working and/or cold working.

[008] After the solution heat treating and then quenching the aluminum alloy step (c) and the optional working step (d), the method includes artificially aging the aluminum alloy (e). The artificial aging step (e) may include (i) first aging the aluminum alloy at a first temperature of from about 166°C to 277°C (330°F to 530°F) and for a first aging time of from 5 minutes to 45 minutes, and (ii) second aging the aluminum alloy at a second temperature for a second aging time of at least 30 minutes, wherein the second temperature is lower than the first temperature. One or more additional aging steps after the first and second aging steps may be completed. No artificial aging steps before the first aging step are completed.

[009] As noted above, the first aging step generally occurs at a first aging temperature and this first aging temperature is generally from 154°C (310°F) (or 166°C (330°F)) to 277°C (530°F). Lower temperatures may be more useful with higher levels of zinc, and higher temperatures may be more useful with lower levels of zinc. In one embodiment, the first aging temperature is at least 177°C (350°F). In another embodiment, the first aging temperature is at least 188°C (370°F). In yet another embodiment, the first aging temperature is at least 199°C (390°F). In one embodiment, the first aging temperature is not greater than 238°C (460°F). In one embodiment, the first aging temperature is not greater than 216°C (420°F).

[0010] The duration of the first aging step is generally from 5 minutes to 45 minutes, and may be related to the first aging temperature. For example, longer first aging steps may be useful at lower temperatures, and shorter first aging steps may be useful at higher temperatures. In an embodiment, the first aging time is not greater than 30 minutes. In another embodiment, the first aging time is not greater than 20 minutes.

[0012] As noted above, the second aging step generally occurs at a second temperature for a second aging time of at least 30 minutes, and the second temperature is lower than the first temperature. In one embodiment, the second aging temperature is from 2.8°C to 83°C (5°F to 150°F) lower than the first aging temperature. In another embodiment, the second aging temperature is from 5.6°C to 56°C (10°F to 100°F) lower than the first aging temperature. In yet another embodiment, the second aging temperature is from 5.6°C to 42°C (10°F to 75°F) lower than the first aging temperature. In another embodiment, the second aging temperature is from 11.1°C to 28°C (20°F to 50°F) lower than the first aging temperature.

[0013] As noted above, the duration of the second aging step is at least 30 minutes. In one embodiment, the duration of the second aging step is at least 1 hour. In another embodiment, the duration of the second aging step is at least 2 hours. In yet another embodiment, the duration of the second aging step is at least 3 hours. In one embodiment, the duration of the second aging step is not greater than 30 hours. In another embodiment, the duration of the second aging step is not greater than 20 hours. In another embodiment, the duration of the second aging step is not greater than 12 hours. In another embodiment, the duration of the second aging step is not greater than 10 hours. In another embodiment, the duration of the second aging step is not greater than 8 hours.

[0014] In one embodiment, the second aging step is conducted for "2 to 8 hours at a temperature of about 182°C (360°F)", or a substantially equivalent aging condition. As appreciated by those skilled in the art, aging temperatures and/or times may be adjusted based on well-known aging principles and/or formulas. Thus, those skilled in the art could increase the aging temperature but decrease the aging time, or vice-versa, or only slightly change only one of these parameters, and still achieve the same result as "2 to 8 hours of aging at a temperature of about 182°C (360°F)". The amount of artificial aging practices that could achieve the same result as "2 to 8 hours of aging at a temperature of about 182°C (360°F)" is numerous, and therefore all such substitute aging practices are not listed herein, even though they are within the scope of the present invention. The phrases "or a substantially equivalent artificial aging

temperature and duration" and "or a substantially equivalent practice" are used to capture all such substitute aging practices.

[0015] The method may optionally include forming the aluminum alloy into a predetermined shaped product during or after the aging step (e). As used herein, a "predetermined shaped product" and the like means a product that is formed into a shape via a shape forming operation (e.g., drawing, ironing, warm forming, flow forming, shear forming, spin forming, doming, necking, flanging, threading, beading, bending, seaming, stamping, hydroforming, and curling, among others), and which shape is determined in advance of the shape forming operation (step). Examples of predetermined shaped products include automotive components (e.g., hoods, fenders, doors, roofs, and trunk lids, among others) and containers (e.g., food cans, bottles, among others), consumer electronic components (e.g., as laptops, cell phones, cameras, mobile music players, handheld devices, computers, televisions, among others), among other aluminum alloy products. In one embodiment, the predetermined shaped product is in its final product form after the forming step. The forming step utilized to produce "predetermined shaped products" may occur concomitant to or after the artificial aging step (e.g., concomitant to or after the first aging step, and/or before, after or concomitant to the second aging step).

[0016] In one embodiment, the forming step is completed concomitant to the aging step (e), and thus may occur at elevated temperature. Such elevated temperature forming steps are referred to herein as "warm forming" operations. In one embodiment, a warm forming operation occurs at a temperature of from 93°C to 277°C (200°F to 530°F). In another embodiment, a warm forming operation occurs at a temperature of from 121°C to 232°C (250°F to 450°F). Thus, in some embodiments, warm forming may be used to produce predetermined shaped products. Warm forming may facilitate production of defect-free predetermined shaped products. Defect-free means that the components are suitable for use as a commercial product, and thus may have little (insubstantial) or no cracks, wrinkles, Ludering, thinning and/or orange peel, to name a few. In other embodiments, room temperature forming may be used to produce defect-free predetermined shaped products.

[0017] In one approach, the method comprises (a) shape casting an aluminum alloy, wherein the aluminum alloy comprises 4.0 - 5.0 wt. % Zn and 1.0 - 2.5 wt. % Mg, then (b) solution heat treating and then quenching the aluminum alloy body, and then (c) artificially aging the aluminum alloy, wherein the artificial aging includes first aging the aluminum alloy at a first temperature of from about 199°C to 216°C (390°F to 420°F) and for a first aging time of from 5 minutes to 45 minutes, and (ii) second aging the aluminum alloy at a second temperature

for

a

second

aging time of at least 30 minutes, wherein the second temperature is lower than the first temperature. In one embodiment of this approach, the second aging temperature is from 149°C to 193°C (300°F to 380°F), and the aging time is from 1 to 36 hours. In another embodiment, the second aging temperature is from 166°C to 188°C (330°F to 370°F), and the aging time is from 1 to 8 hours. One or more additional aging steps after the first and second aging steps may be completed. No aging steps before the first aging step are completed.

[0018] In one approach, the method comprises (a) shape casting an aluminum alloy, wherein the aluminum alloy is one of aluminum casting alloy 707.X, 712.X, 713.X or 771.X, and then (b) solution heat treating and then quenching the aluminum alloy body, and then (c) artificially aging the aluminum alloy, wherein the artificial aging includes first aging the aluminum alloy, such as using any of the first aging conditions described above, and (ii) second aging the aluminum alloy at a second temperature for a second aging time of at least 30 minutes, wherein the second temperature is lower than the first temperature. One or more additional aging steps after the first and second aging steps may be completed. No artificial aging steps before the first aging step are completed. Aluminum shape casting alloys 707.X, 712.X, 713.X or 771.X, are known casting alloys, and their compositions are defined in, for example, The Aluminum Association document "*Designation and Chemical Compositions Limits for Aluminum Alloys in the Form of Castings and Ingots*," April 2002. As known, the "X" may be replaced with a "0", "1", etc., to define the specific casting alloy composition (known or future). In a general sense, for this document, the "0" generally refers to the composition of a shape cast product, whereas a "1" or "2" generally refers to a composition of an ingot. For instance, 707.0 includes 1.8 - 2.4 wt. % Mg for a shape cast product made from the 707 alloy, whereas 707.1 includes 1.9 - 2.4 wt. % Mg for an ingot made from the 707 alloy.

[0019] In one embodiment, the alloy is a wrought 7xxx aluminum alloy product, meaning that the alloy has been hot worked at some point after casting. Examples of wrought products include rolled products (sheet and plate), extrusions and forgings. In one embodiment, a method includes (a) preparing a wrought 7xxx aluminum alloy for solution heat treating, wherein the wrought 7xxx aluminum alloy comprises 4.0 - 9.5 wt. % Zn, from 1.2 to 3.0 wt. % Mg, and up to 2.6 wt. % Cu, (b) after step (a), solution heat treating and then quenching the wrought 7xxx aluminum alloy, and (c) after step (b), artificially aging the wrought 7xxx aluminum alloy, wherein the artificial aging step (c) comprises, (i) first aging the wrought 7xxx aluminum alloy at a first temperature in the range of from 154°C to 221°C (310°F to 430°F) for from 5 minutes to 45 minutes, (ii) second aging the wrought 7xxx aluminum alloy at

temperature for at least 0.5 hour, wherein the second temperature is lower than the first temperature. One or more additional aging steps after the first and second aging steps may be completed. No aging artificial steps before the first aging step are completed. In one embodiment, the artificial aging step consists of the first aging step and the second aging step (i.e., only two aging steps are used). The first and second artificial aging steps generally comprise heating or cooling to the stated temperature(s), as the case may be, and then holding for the stated amount of time. For instance, a first artificial aging step of "188°C (370°F) for 10 minutes" would include heating the aluminum alloy until it reaches the target temperature of 188°C (370°F), and then holding for 10 minutes within a tolerable and controllable temperature range centered around 188°C (370°F) ((e.g., +/- 5.6°C (10°F), or +/- 2.8°C (5°F), for instance). Age integration may be used to facilitate proper aging.

[0020] In one embodiment, the method includes stress-relieving the wrought 7xxx aluminum alloy, wherein the stress-relieving occurs after the solution heat treating and then quenching step (b) and prior to the artificial aging step (c). In one embodiment, the stress-relieving comprises at least one of stretching by 0.5 to 8% and compressing by 0.5 to 12%.

[0021] As noted above, the method includes artificially aging the wrought 7xxx aluminum alloy, wherein the artificial aging step (c) comprises, (i) first aging the wrought 7xxx aluminum alloy at a first temperature in the range of from 154°C to 221°C (310°F to 430°F) for from 5 minutes to 45 minutes, (ii) second aging the wrought 7xxx aluminum alloy at a second temperature for at least 0.5 hour, wherein the second temperature is lower than the first temperature. In one embodiment, the second temperature is at least 5.6°C (10°F) lower than the first temperature. In another embodiment, the second temperature is at least 11°C (20°F) lower than the first temperature. In yet another embodiment, the second temperature is at least 17°C (30°F) lower than the first temperature. In another embodiment, the second temperature is at least 22°C (40°F) lower than the first temperature. In yet another embodiment, the second temperature is at least 28°C (50°F) lower than the first temperature. In another embodiment, the second temperature is at least 33°C (60°F) lower than the first temperature. In yet another embodiment, the second temperature is at least 39°C (70°F) lower than the first temperature. In another embodiment, the first aging step is not greater than 120 minutes. In another embodiment, the first aging step is not greater than 90 minutes. In yet another embodiment, the first aging step is not greater than 60 minutes. In another embodiment, the first aging step is not greater than 45 minutes. In yet another embodiment, the first aging step is not greater than 30 minutes. In another embodiment, the first aging step is not greater than 20 minutes. In one embodiment, the first aging step is at least 5 minutes. In another embodiment, the first aging step is at least 10

minutes. In one embodiment, the first aging step is for from 5 to 20 minutes. In one embodiment, the second aging step is for from 1 to 12 hours. In another embodiment, the second aging step is for from 2 to 8 hours. In yet another embodiment, the second aging step is for from 3 to 8 hours.

[0022] In one approach, the wrought 7xxx aluminum alloy includes 4.0 - 9.5 wt. % Zn, from 1.2 to 3.0 wt. % Mg, and from 1.0 to 2.6 wt. % Cu. In an embodiment, the first temperature is from 171°C to 193°C (340°F to 380°F), and the first aging step is not greater than 30 minutes. In one embodiment, the second aging temperature is from 121°C to 177°C (250°F to 350°F), and the second aging step is from 0.5 to 12 hours. In another embodiment, the second aging temperature is from 132°C to 171°C (270°F to 340°F), and the second aging step is from 1 to 12 hours. In yet another embodiment, the second aging temperature is from 138°C to 168°C (280°F to 335°F), and the second aging step is from 2 to 8 hours. In another embodiment, the second aging temperature is from 143°C to 166°C (290°F to 330°F), and wherein the second aging step is from 2 to 8 hours. In yet another embodiment, the second aging temperature is from 149°C to 163°C (300°F to 325°F), and wherein the second aging step is from 2 to 8 hours. In some of these embodiments, the second aging step is at least 3 hours. In some of these embodiments, the second aging step is at least 4 hours. In one embodiment, the wrought 7xxx aluminum alloy includes from 5.7 - 8.4 wt. % Zn, from 1.3 to 2.3 wt. % Mg, and from 1.3 to 2.6 wt. % Cu. In one embodiment, the wrought 7xxx aluminum alloy includes from 7.0 to 8.4 wt. % Zn. In one embodiment, the wrought 7xxx aluminum alloy is selected from the group consisting of 7x85, 7x55, 7x50, 7x40, 7x99, 7x65, 7x78, 7x36, 7x37, 7x49, and 7x75, among others, as defined by The Aluminum Association document "International Alloy Designations and Chemical Composition Limits for Wrought Aluminum and Wrought Aluminum Alloys" February 2009, and its corresponding Addendum of February 2014, collectively the "Teal Sheets". As known, the "x" may be replaced with a "0", "1", etc., as appropriate, to define the specific wrought 7xxx aluminum alloy composition (known or future). For instance, 7040 includes 1.5 - 2.3 wt. % Cu, 1.7 - 2.4 wt. % Mg, and 5.7 - 6.7 wt. % Zn, whereas 7140 includes 1.3 - 2.3 wt. % Cu, 1.5 - 2.4 wt. % Mg, and 6.2 - 7.0 wt. % Zn, as shown by the Teal Sheets. In one embodiment, the wrought 7xxx aluminum alloy is a 7x85 alloy. In another embodiment, the wrought 7xxx aluminum

alloy is a 7x55 alloy. In yet another embodiment, the wrought 7xxx aluminum alloy is a 7x40 alloy. In another embodiment, the 7xxx aluminum alloy is a 7x65 alloy. In another embodiment, the alloy is a 7x50 alloy. In yet another embodiment, the 7xxx aluminum alloy is a 7x75 alloy.

[0023] In another approach, the wrought 7xxx aluminum alloy includes 4.0 - 9.5 wt. % Zn, from 1.2 to 3.0 wt. % Mg, and from 0.25 to less than 1.0 wt. % Cu. In an embodiment, the first temperature is from 182°C to 213°C (360°F to 415°F), and the first aging step is not greater than 30 minutes. In one embodiment, the second aging temperature is from 121°C to 188°C (250°F to 370°F), and the second aging step is from 0.5 to 12 hours. In another embodiment, the second aging temperature is from 132°C to 182°C (270°F to 360°F), and the second aging step is from 1 to 12 hours. In yet another embodiment, the second aging temperature is from 138°C to 179°C (280°F to 355°F), and the second aging step is from 2 to 8 hours. In another embodiment, the second aging temperature is from 143°C to 177°C (290°F to 350°F), and the second aging step is from 2 to 8 hours. In yet another embodiment, the second aging temperature is from 149°C to 174°C (300°F to 345°F), and the second aging step is from 2 to 8 hours. In some of these embodiments, the second aging step is at least 3 hours. In some of these embodiments, the second aging step is at least 4 hours. In one embodiment, the wrought 7xxx aluminum alloy is a 7x41 alloy, as defined by the Teal Sheets. In one embodiment, the wrought 7xxx aluminum alloy is Russian alloy RU1953.

[0024] In yet another approach, the wrought 7xxx aluminum alloy includes 4.0 - 9.5 wt. % Zn, from 1.2 to 3.0 wt. % Mg, and less than 0.25 wt. % Cu. In an embodiment, the first temperature is from 171°C to 193°C (340° to 380°F), and the first aging step is not greater than 30 minutes. In one embodiment, the second aging temperature is from 121°C to 177°C (250°F to 350°F), and the second aging step is from 0.5 to 12 hours. In another embodiment, the second aging temperature is from 132°C to 171°C (270°F to 340°F), and the second aging step is from 1 to 12 hours. In yet another embodiment, the second aging temperature is from 138°C to 168°C (280°F to 335°F), and the second aging step is from 0.5 to 12 hours.

the second aging step is from 2 to 8 hours. In another embodiment, the second aging temperature is from 143°C to 166°C (290°F to 330°F), and the second aging step is from 2 to 8 hours. In yet another embodiment, the second aging temperature is from 149°C to 163°C (300°F to 325°F), and the second aging step is from 2 to 8 hours. In some of these embodiments, the second aging step is at least 3 hours. In some of these embodiments, the second aging step is at least 4 hours. In one embodiment, the wrought 7xxx aluminum alloy is selected from the group consisting of 7x05, 7x39, and 7x47, as defined by the Teal Sheets, or Russian alloy RU1980. In one embodiment, the wrought 7xxx aluminum alloy is a 7x39 alloy. In one embodiment, the wrought 7xxx aluminum alloy is Russian alloy RU1980.

[0025] The new aluminum alloys having zinc and magnesium described herein may be used in a variety of applications, such as in automotive and/or aerospace applications, among others. In one embodiment, the new aluminum alloys are used in an aerospace application, such as wing skins (upper and lower) or stringers / stiffeners, fuselage skin or stringers, ribs, frames, spars, seat tracks, bulkheads, circumferential frames, empennage (such as horizontal and vertical stabilizers), floor beams, seat tracks, doors, and control surface components (e.g., rudders, ailerons) among others. In another embodiment, the new aluminum alloys are used in an automotive application, such as closure panels (e.g., hoods, fenders, doors, roofs, and trunk lids, among others), wheels, and critical strength applications, such as in body-in-white (e.g., pillars, reinforcements) applications, among others. In another embodiment, the new aluminum alloys are used in a munitions / ballistics / military application, such as in ammunition cartridges and armor, among others. Ammunition cartridges may include those used in small arms and cannons or for artillery or tank rounds. Other possible ammunition components would include sabots and fins. Artillery, fuse components are another possible application as are fins and control surfaces for precision guided bombs and missiles. Armor components could include armor plates or structural components for military vehicles. In another embodiment, the new aluminum alloys are used in an oil and gas application, such as for risers, auxiliary lines, drill pipe, choke-and-kill lines, production piping, and fall pipe, among others.

#### **BRIEF DESCRIPTION OF THE DRAWINGS**

[0026] FIG. 1 is a graph illustrating the electrical conductivity versus SCC performance for the Example 1 alloys.

#### **DETAILED DESCRIPTION**

##### **Example 1**

[0027] A 7xx casting aluminum alloy having the composition shown in Table 1, below, was cast via directional solidification.

Table 1 - Composition of Ex. 1 Alloy (in wt. %)

Alloy	Zn	Mg	Cu
1	4.24	1.52	0.80

[0028] After casting, Alloy 1 was solution heat treated, and then quenched in boiling water. Alloy 1 was then stabilized by naturally aging for about 12-24 hours at room temperature. Next Alloy 1 was artificially aged at various times and temperatures, as shown in Table 2, below. For Alloys 1-A through 1-D, the alloys were heated from ambient to the first aging temperature in about 40 minutes, and then held at the first aging temperature for the stated duration; after the first aging step was completed, Alloys 1-A through 1-D were heated to the second aging temperature in about 45 minutes, and then held at the second aging temperature for the stated duration. Alloy 1-E was heated from ambient to the first aging temperature in about 50 minutes, and then held at the first aging temperature for the stated duration; after the first aging step was completed, power to the furnace was turned-off and the furnace was open to the air until the furnace reached the second target temperature (about 10 minutes), and after which Alloy 1-E was held at the second aging temperature for the stated duration.

Table 2 - Artificial Aging Practices

Alloy	1 <sup>st</sup> Step	2 <sup>nd</sup> Step	Note
1-A	250°F for 3 hours	360°F for 16 hours	Non-Invention
1-B	250°F for 3 hours	360°F for 3 hours	Non-Invention
1-C	250°F for 3 hours	360°F for 4 hours	Non-Invention
1-D	250°F for 3 hours	360°F for 5 hours	Non-Invention
1-E	400°F for 10 mins.	360°F for 4 hours	Invention

250°F is 121°C, 360°F is 182°C and 400°F is 204°C.

[0029] Various mechanical properties and the SCC (stress corrosion cracking) resistance of the alloys were then measured, the results of which are shown in Tables 3-5, below. Strength and elongation were measured in accordance with ASTM E8 and B557 (average of triplicate specimens). Fatigue performance was tested in accordance with ASTM E466 (Kt = 1, R= -1, Stress = 160 MPa (23.2 ksi), 25 Hz, in lab air) (average of triplicate specimens). SCC resistance was measured in accordance with ASTM G103 (stress = 240 MPa (34.8 ksi)).

Table 3 - Strength and Elongation Properties of Ex. 1 Alloys

Alloy	TYS (MPa)	UTS (MPa)	Total El (%)
1-A	327 (47.4 ksi)	382 (55.4 ksi)	9.3
1-B	344 (49.9 ksi)	390 (56.5 ksi)	6.7
1-C	334 (48.5 ksi)	388 (56.3 ksi)	9.3
1-D	327 (47.4 ksi)	372 (53.9 ksi)	6.3
1-E	323 (46.8 ksi)	377 (54.7 ksi)	8.7

Table 4 - Fatigue Properties of Ex. 1 Alloys

Alloy	Average Cycles to Fail	Standard Deviation
1-A	105,421	27,715
1-B	109,519	58,674
1-C	142,187	105,362
1-D	90,002	22,694
1-E	144,611	35,256

Table 5 - SCC resistance of Ex. 1 Alloys

Alloy	Specimen	Hours to Failure	Average hours to Failure
1-A	1	45	111
	2	96	
	3	96	
	4	150	
	5	168	
1-B	1	21	60.2
	2	45	
	3	45	
	4	72	
	5	118	
1-C	1	24	47.8
	2	30	
	3	45	
	4	68	
	5	72	
1-D	1	68	80.4
	2	72	
	3	72	
	4	72	
	5	118	

1-E	1	142	154
	2	142	
	3	150	
	4	168	
	5	168	

[0030] As shown above, the invention alloy (1-E) achieves about the same strength but better fatigue resistance as compared to the non-invention alloys. The invention alloy also achieves much better stress corrosion cracking resistance as compared to the non-invention alloys. Furthermore, the invention alloy achieves its improved properties with only about 4 hours, 10 minutes of artificial aging time, whereas the non-invention alloys all required at least 6 or more hours of artificial aging time.

[0031] The electrical conductivity of the alloys was also measured using a HOCKING electric conductivity meter (AutoSigma 3000DL), the results of which are shown in Table 6, below (average of quadruplicate specimens). As shown in FIG. 1, the invention alloy unexpectedly achieves better SCC performance at lower electrical conductivity. The lower electrical conductivity of the invention alloy indicates that it has not been overly aged, but yet still improved SCC performance is achieved.

Table 6 - Electrical conductivity of Ex. 1 Alloys

Alloy	Average EC (% IACS)	StdDev
1-A	42.0	0.05
1-B	40.9	0.15
1-C	41.4	0.05
1-D	41.6	0.01
1-E	41.2	0.06

## Example 2

[0032] Alloy 1 from Example 1 was processed similar to Example 1, but was artificially aged for various times as shown in Table 7, below.

Table 7 - Artificial Aging Practices

Alloy	1 <sup>st</sup> Step	2 <sup>nd</sup> Step	Note
1-F	400°F for 10 mins.	360°F for 3 hours	Invention
1-G	400°F for 10 mins.	360°F for 4 hours	Invention
1-H	400°F for 10 mins.	360°F for 6 hours	Invention
1-I	400°F for 5 mins.	360°F for 4 hours	Invention
1-J	400°F for 20 mins.	360°F for 4 hours	Invention

400°F is 204°C and 360°F is 182°C.

[0033] Various mechanical properties and the SCC (stress corrosion cracking) resistance of the alloys were then measured, the results of which are shown in Tables 8-10, below. Strength and elongation were measured in accordance with ASTM E8 and B557 (average of triplicate specimens). Fatigue performance was tested in accordance with ASTM E466 (Kt = 1, R= -1, Stress = 160 MPa (23.2 ksi), 25 Hz, in lab air) (average of triplicate specimens). SCC resistance was measured in accordance with ASTM G103 (stress = 240 MPa (34.8 ksi)).

Table 8 - Strength and Elongation Properties of Ex. 2 Alloys

Alloy	TYS (MPa)	UTS (MPa)	Total El (%)
1-F	336 (48.7 ksi)	383 (55.5 ksi)	7.3
1-G	331 (48.0 ksi)	380 (55.1 ksi)	7.3
1-H	331 (48.0 ksi)	377 (54.7 ksi)	7.0
1-I	323 (46.9 ksi)	370 (53.6 ksi)	6.3
1-J	328 (47.5 ksi)	376 (54.5 ksi)	8.0

Table 9 - Fatigue Properties of Ex. 2 Alloys

Alloy	Average Cycles to Fail	Standard Deviation
1-F	112,269	48,630
1-G	144,611	35,256
1-H	94,599	49,852
1-I	103,367	31,106
1-J	107,605	16,369

Table 10 - SCC resistance of Ex. 2 Alloys

Alloy	Specimen	Hours to Failure	Average hours to Failure
1-F	1	72	102.3
	2	72	
	3	96	
	4	124.08	
	5	147.6	
1-G	1	96	142.8
	2	113.76	
	3	168	
	4	168	
	5	168	

1-H	1	96	124.8
	2	96	
	3	96	
	4	168	
	5	168	
1-I	1	42	118.8
	2	96	
	3	120	
	4	168	
	5	168	
1-J	1	96	138.0
	2	114	
	3	144	
	4	168	
	5	168	

[0034] Similar to Example 1, the invention alloys achieve a good combination of strength, fatigue resistance and stress corrosion cracking resistance.

### Example 3

[0035] Alloy 1 from Example 1 was processed similar to Example 1, but was artificially aged for various times as shown in Table 11, below.

Table 11 - Artificial Aging Practices

Alloy	1 <sup>st</sup> Step	2 <sup>nd</sup> Step	Note
1-K	390°F for 10 mins.	360°F for 4 hours	Invention
1-L	400°F for 10 mins.	360°F for 4 hours	Invention
1-M	420°F for 10 mins.	360°F for 4 hours	Invention

360°F is 182°C ,390°F is 199°C, 400°F is 204°C and 420°F is 216°C.

[0036] Various mechanical properties and the SCC (stress corrosion cracking) resistance of the alloys were then measured, the results of which are shown in Tables 12-14, below. Strength and elongation were measured in accordance with ASTM E8 and B557 (average of triplicate specimens, except Alloy 1-K, which was the average of duplicate specimens). Fatigue performance was tested in accordance with ASTM E466 (Kt = 1, R= -1, Stress = 160 MPa (23.2 ksi), 25 Hz, in lab air) (average of triplicate specimens). SCC resistance was measured in accordance with ASTM G103 (stress = 240 MPa (34.8 ksi)).

Table 12 - Strength and Elongation Properties of Ex. 3 Alloys

Alloy	TYS (MPa)	UTS (MPa)	Total El (%)
1-K	332 (48.2 ksi)	370 (53.6 ksi)	5.5
1-L	331 (48.0 ksi)	373 (54.1 ksi)	5.7
1-M	323 (46.9 ksi)	363 (52.6 ksi)	5.3

Table 13 - Fatigue Properties of Ex. 3 Alloys

Alloy	Average Cycles to Fail	Standard Deviation
1-K	110423	41955
1-L	110362	36083
1-M	103406	23128

Table 14 - SCC resistance of Ex. 3 Alloys

Alloy	Specimen	Hours to Failure	Average hours to Failure
1-K	1	46	104
	2	94	
	3	94	
	4	118	
	5	168	
1-L	1	48	117.4
	2	79	
	3	146	
	4	146	
	5	168	
1-M	1	94	153.2
	2	168	
	3	168	
	4	168	
	5	168	

[0037] Similar to Examples 1-2, the invention alloys achieve a good combination of strength, fatigue resistance and stress corrosion cracking resistance.

#### Example 4 - Aging of Wrought Aluminum Alloy 7085

[0038] Aluminum alloy 7085 having the composition shown in Table 15 was produced as a conventional plate product (e.g., homogenized, rolled to final gauge, solution heat treated and cold water quenched, stress relieved by stretching (2%)) having a thickness of 5.1 cm (2 inches).

After about four days of natural aging, the 7085 plate was multi-step aged for various times at various temperatures, as shown in Table 16. After aging, mechanical properties were measured in accordance with ASTM E8 and B557, the results of which are shown in Table 17. Stress corrosion cracking (SCC) resistance was also measured in accordance with ASTM G44, 3.5% NaCl, Alternate Immersion, the results of which are shown in Table 18 (stress in the ST direction).

Table 15 - Composition of the 7085 Alloy (in wt. %)\*

Alloy	Zn	Mg	Cu	Zr	Si	Fe	Mn	Cr	Ti
7085	7.39	1.54	1.66	0.11	0.02	0.03	<0.01	< 0.01	0.02

\* The balance of the alloy is aluminum and other elements, with the aluminum alloy containing not more than 0.05 wt. % each of any other element, and with the aluminum alloy containing not more than 0.15 wt. % in total of the other elements.

Table 16 - Artificial Aging Practices

Alloy	1 <sup>st</sup> Step	2 <sup>nd</sup> Step
7085-1	N/A - Conventional 3-step aging practice of 250°F for 6 hours, then 310 °F for 18 hours, and then 250 °F for 24 hours	
7085-2	400°F for 10 mins.	310°F for 4 hours
7085-3	400°F for 10 mins.	310°F for 6 hours
7085-4	400°F for 10 mins.	310°F for 8 hours
7085-5	460°F for 5 mins.	310°F for 8 hours
7085-6	430°F for 7.5 mins.	310°F for 8 hours
7085-7	400°F for 5 mins.	310°F for 8 hours
7085-8	400°F for 15 mins.	310°F for 8 hours
7085-9	460°F for 5 mins.	310°F for 4 hours
7085-10	460°F for 5 mins.	310°F for 6 hours
7085-11	375°F for 10 mins.	310°F for 4 hours
7085-12	375°F for 20 mins.	310°F for 4 hours
7085-13	375°F for 30 mins.	310°F for 4 hours
7085-14	345°F for 15 mins.	310°F for 6 hours
7085-15	345°F for 30 mins.	310°F for 6 hours

250°F is 121°C, 310°F is 154°C, 345°F is 174°C, 375°F is 191°C, 400°F is 204°C, 430°F is 221°C and 460°F is 238°C.

For the artificial aging, the samples were heated to the first temperature in about 50 minutes and then held at the stated temperature for the stated amount of time. The samples were then

cooled to the second temperature by changing the furnace set-point and opening the furnace door until the second temperature was reached. The specimens were then held at the second temperature for the stated amount of time, after which the samples were removed from the furnace and allowed to air cool to room temperature.

Table 17 - Mechanical Properties

Alloy	Tensile Yield Strength (TYS), MPa (ST)	Ultimate Tensile Strength (UTS), MPa (ST)	Elongation, % (ST)
7085-1	467 (67.7 ksi)	526 (76.3 ksi)	10.9
7085-2	423 (61.3 ksi)	488 (70.8 ksi)	10.9
7085-3	416 (60.3 ksi)	486 (70.5 ksi)	10.9
7085-4	422 (61.2 ksi)	492 (71.3 ksi)	11.4
7085-5	318 (46.1 ksi)	407 (59.1 ksi)	14.1
7085-6	357 (51.8 ksi)	439 (63.7 ksi)	14.1
7085-7	417 (60.5 ksi)	486 (70.5 ksi)	11.4
7085-8	399 (57.8 ksi)	472 (68.4 ksi)	10.4
7085-9	323 (46.9 ksi)	412 (59.8 ksi)	15.1
7085-10	319 (46.3 ksi)	407 (59.1 ksi)	14.6
7085-11	452 (65.5 ksi)	512 (74.2 ksi)	12.0
7085-12	450 (65.2 ksi)	509 (73.8 ksi)	10.9
7085-13	443 (64.2 ksi)	503 (73.0 ksi)	10.9
7085-14	464 (67.3 ksi)	521 (75.5 ksi)	9.4
7085-15	456 (66.2 ksi)	514 (74.6 ksi)	10.4

Table 18 - SCC Results

Alloy	Stress (ksi)	Days to Failure				
		Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
7085-1	45	DNF	50	42	86	89
7085-1	55	DNF	89	44	33	29
7085-2	45	DNF	DNF	DNF	DNF	N/A
7085-2	55	DNF	DNF	90	DNF	N/A
7085-3	45	DNF	DNF	DNF	77	N/A
7085-3	55	DNF	DNF	DNF	DNF	N/A
7085-4	45	DNF	DNF	DNF	DNF	N/A
7085-4	55	DNF	DNF	DNF	DNF	N/A
7085-5	45	DNF	DNF	DNF	DNF	N/A
7085-5	55	DNF	DNF	DNF	DNF	N/A
7085-6	45	DNF	DNF	DNF	DNF	N/A
7085-6	55	DNF	DNF	DNF	DNF	N/A
7085-7	45	DNF	DNF	DNF	DNF	N/A
7085-7	55	DNF	DNF	DNF	DNF	N/A

Alloy	Stress (ksi)	Days to Failure				
		Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
7085-8	45	DNF	DNF	DNF	DNF	N/A
7085-8	55	DNF	DNF	DNF	DNF	N/A
7085-9	45	DNF	DNF	DNF	DNF	N/A
7085-9	55	DNF	DNF	DNF	DNF	N/A
7085-10	45	DNF	DNF	DNF	DNF	N/A
7085-10	55	DNF	DNF	DNF	DNF	N/A
7085-11	45	DNF(66)	51	59	50	N/A
7085-11	55	DNF(66)	DNF(66)	43	DNF(66)	N/A
7085-14	45	50	50	59	40	N/A
7085-14	55	40	DNF(66)	44	44	43
7085-12	55	DNF(66)	58	DNF(66)	48	54
7085-13	55	58	57	DNF(66)	DNF(66)	65
7085-15	55	54	47	DNF(66)	DNF(66)	DNF(66)

\* DNF = did not fail after 90 days

\*\* DNF(66) = did not fail after 66 days

45 ksi is 310 MPa and 55 ksi is 380 MPa.

[0039] As shown, the new aging practice yields significant improvement in throughput via decreased total aging time, and with similar strength and corrosion resistance. Indeed, alloy 7085-14 realizes about the same strength as conventionally aged 7085-1, but with only 6.25 hours of total aging time (not including ramp-up time and cool down time) as compared to the total aging time of 48 hours (not including ramp-up time and cool down time) for alloy 7085-1.

#### Example 5 - Aging of Alloy 7255

[0040] Aluminum alloy 7255 having the composition shown in Table 19 was produced as a conventional plate product (e.g., homogenized, rolled to final gauge, solution heat treated and cold water quenched, stress relieved by stretching (2%)) having a thickness of 3.8 cm (1.5 inches). After about four days of natural aging, the 7255 plate was multi-step aged for various times at various temperatures, as shown in Table 20. After aging, mechanical properties were measured in accordance with ASTM E8 and B557, the results of which are shown in Table 21. Stress corrosion cracking (SCC) resistance was also measured in accordance with ASTM G44, 3.5% NaCl, Alternate Immersion, the results of which are shown in Table 22 (stress in the ST direction and with a stress of 241 MPa (35 ksi)). For some of the alloys, electrical conductivity

(% IACS) was measured in accordance with ASTM E1004-09, *Standard Test Method for Determining Electrical Conductivity Using the Electromagnetic (Eddy-Current) Method*, using a 2.5 cm by 3.8 cm by 10.2 cm (1 inch by 1.5 inch by 4 inch) block, the results of which are shown in Table 23, below.

Table 19 - Composition of the 7255 Alloy (in wt. %)\*

Alloy	Zn	Mg	Cu	Zr	Si	Fe	Mn	Cr	Ti
7255	7.98	1.91	2.18	0.11	0.02	0.03	<0.01	<0.01	0.02

\* The balance of the alloy is aluminum and other elements, with the aluminum alloy containing not more than 0.05 wt. % each of any other element, and with the aluminum alloy containing not more than 0.15 wt. % in total of the other elements.

Table 20 - Artificial Aging Practices

Alloy	1 <sup>st</sup> Step	2 <sup>nd</sup> Step
7255-1	N/A - Conventional 3-step aging practice of 250°F for 6 hours, then 400 °F for 3 minutes ( $\approx$ 30 minute ramp to 400°F), and then 250°F for 24 hours	
7255-2	400°F for 10 mins.	310°F for 4 hours
7255-3	400°F for 10 mins.	310°F for 6 hours
7255-4	400°F for 10 mins.	310°F for 8 hours
7255-5	480°F for 5 mins.	310°F for 8 hours
7255-6	440°F for 10 mins.	310°F for 8 hours
7255-7	400°F for 5 mins.	310°F for 8 hours
7255-8	400°F for 15 mins.	310°F for 8 hours
7255-9	480°F for 5 mins.	310°F for 4 hours
7255-10	480°F for 5 mins.	310°F for 6 hours
7255-11	370°F for 5 mins.	310°F for 4 hours
7255-12	370°F for 10 mins.	310°F for 4 hours
7255-13	370°F for 20 mins.	310°F for 4 hours
7255-14	345°F for 15 mins.	310°F for 4 hours
7255-15	345°F for 30 mins.	310°F for 4 hours

250°F is 121°C, 310°F is 154°C, 345°F is 174°C, 370°F is 188°C, 400°F is 204°C, 440°F is 227°C and 480°F is 249°C.

For the artificial aging, unless otherwise stated, the samples were heated to the first temperature in about 50 minutes and then held at the stated temperature for the stated amount of time. The samples were then cooled to the second temperature by changing the furnace set-point and opening the furnace door until the second temperature was reached. The specimens were then held at the second temperature for the stated amount of time, after which the samples were removed from the furnace and allowed to air cool to room temperature.

Table 21 - Mechanical Properties

Alloy	Tensile Yield Strength (TYS), MPa (ST)	Ultimate Tensile Strength (UTS), MPa (ST)	Elongation, %
7255-1	537 (77.9 ksi)	613 (88.9 ksi)	4.7
7255-2	474 (68.8 ksi)	549 (79.6 ksi)	9.4
7255-3	467 (67.7 ksi)	542 (78.7 ksi)	9.4
7255-4	466 (67.6 ksi)	545 (79.0 ksi)	9.4
7255-5	303 (44.0 ksi)	409 (59.3 ksi)	13.6
7255-6	374 (54.2 ksi)	471 (68.3 ksi)	12.5
7255-7	483 (70.0 ksi)	560 (81.2 ksi)	7.8
7255-8	448 (65.0 ksi)	530 (76.9 ksi)	9.4
7255-9	300 (43.5 ksi)	407 (59.1 ksi)	12.5
7255-10	302 (43.8 ksi)	410 (59.5 ksi)	12.5
7255-11	522 (75.7 ksi)	592 (85.8 ksi)	7.8
7255-12	518 (75.1 ksi)	582 (84.4 ksi)	6.7
7255-13	518 (75.2 ksi)	582 (84.4 ksi)	5.7
7255-14	525 (76.1 ksi)	588 (85.3 ksi)	6.2
7255-15	523 (75.8 ksi)	586 (85.0 ksi)	6.2

Table 22 - SCC Results

Alloy	Days to Failure				
	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
7255-1	5	71	6	8	5
7255-2	88	42	88	74	43
7255-3	63	70	74	54	53
7255-4	49	88	88	88	88
7255-5	DNF	DNF	DNF	DNF	DNF
7255-6	DNF	DNF	DNF	DNF	DNF
7255-7	60	63	88	47	46
7255-8	88	71	DNF	90	90
7255-9	DNF	DNF	DNF	DNF	DNF
7255-10	DNF	DNF	DNF	DNF	DNF
7255-11	48	32	26	25	22
7255-12	45	41	51	52	52
7255-13	51	DNF(66)	53	53	57
7255-14	8	8	8	32	24
7255-15	24	43	48	8	32

\* DNF = did not fail after 90 days

\*\* DNF(66) = did not fail after 66 days

[0041] As shown, the new aging practice yields significant improvement in throughput via decreased total aging time, and with similar strength and corrosion resistance. Indeed, alloy 7255-14 realizes about the same strength as conventionally aged 7255-1, but with only 4.25 hours of total aging time (not including ramp-up time and cool down time) as compared to the total aging time of about 30 hours (not including ramp-up time and cool down time) for alloy 7255-1. The 7255-14 alloy also realizes comparable corrosion resistance to alloy 7255-1. Improved corrosion resistance is realized by alloy 7255-15 over alloy 7255-1, with comparable strength, and with only 4.5 - 5.0 hours of total aging time (not including ramp-up time and cool down time).

Table 23 - Electrical Conductivity + SCC Results

Alloy	Ave. SCC (days to failure)	EC (% IACS)
7255-1	19	37.5
7255-11	30.6	37.2
7255-12	48.2	37.6
7255-13	56	38.8
7255-14	16	37.0
7255-15	31	37.1

**Example 6 - Aging of Alloy 1980**

[0042] Russian alloy 1980 having the composition shown in Table 24 was produced as a conventional rod product (e.g., homogenized, extruded to rod, solution heat treated and cold water quenched) having an outer diameter of about 17.8 cm (7.0 inches) and a thickness of about 3.3 cm (1.3 inches). After about 0.5 - 1 days of natural aging, the 1980 alloy rod was multi-step aged for various times at various temperatures, as shown in Table 25. After aging, mechanical properties were measured in accordance with ASTM E8 and B557, the results of which are shown in Table 26. Stress corrosion cracking (SCC) resistance for some of the alloys was also measured in accordance with ASTM G103, Boiling Salt Test, the results of which are shown in Table 27 (stress in the ST direction and with a stress of 112 MPa (16.2 ksi)).

Table 24 - Composition of the 1980 Alloy (in wt. %)\*

Alloy	Zn	Mg	Cu	Zr	Si	Fe	Mn	Cr	Ti
1980	4.25	2.00	0.07	0.12	0.12	0.20	0.38	0.13	<0.01

\* The balance of the alloy is aluminum and other elements, with the aluminum alloy containing not more than 0.05 wt. % each of any other element, and with the aluminum alloy containing not more than 0.15 wt. % in total of the other elements.

Table 25 - Artificial Aging Practices

Alloy	1 <sup>st</sup> Step	2 <sup>nd</sup> Step
1980-2	400°F for 10 mins.	350°F for 2 hours
1980-3	400°F for 10 mins.	350°F for 4 hours
1980-4	400°F for 10 mins.	350°F for 6 hours
1980-5	420°F for 7.5 mins.	350°F for 4 hours
1980-6	380°F for 10 mins.	350°F for 4 hours
1980-7	400°F for 5 mins.	350°F for 4 hours
1980-8	400°F for 15 mins.	350°F for 4 hours
1980-9	420°F for 7.5 mins.	350°F for 2 hours
1980-10	420°F for 7.5 mins.	350°F for 6 hours
1980-12	370°F for 10 mins.	310°F for 2 hours
1980-13	360°F for 10 mins.	310°F for 2 hours
1980-14	350°F for 10 mins.	310°F for 2 hours
1980-15	350°F for 10 mins.	310°F for 4 hours
1980-16	350°F for 30 mins.	310°F for 2 hours
1980-17	350°F for 30 mins.	310°F for 4 hours
1980-18	330°F for 20 mins.	310°F for 2 hours
1980-19	330°F for 20 mins.	310°F for 4 hours

310°F is 154°C, 330°F is 166°C, 350°F is 177°C, 360°F is 182°C, 370°F is 188°C, 380°F is 193°C, 400°F is 204°C and 420°F is 216°C.

For the artificial aging, unless otherwise stated, the samples were heated to the first temperature in about 50 minutes and then held at the stated temperature for the stated amount of time. The samples were then cooled to the second temperature by changing the furnace set-point and opening the furnace door until the second temperature was reached. The specimens were then held at the second temperature for the stated amount of time, after which the samples were removed from the furnace and allowed to air cool to room temperature.

Table 26 - Mechanical Properties

Alloy	Tensile Yield Strength (TYS), MPa	Ultimate Tensile Strength (UTS), MPa	Elongation, %
1980-2	245 (35.5 ksi)	337 (48.9 ksi)	14.0

Alloy	Tensile Yield Strength (TYS), MPa	Ultimate Tensile Strength (UTS), MPa	Elongation, %
1980-3	248 (35.9 ksi)	338 (49.0 ksi)	14.0
1980-4	245 (35.5 ksi)	334 (48.4 ksi)	12.0
1980-5	230 (33.4 ksi)	322 (46.7 ksi)	12.0
1980-6	252 (36.6 ksi)	340 (49.3 ksi)	12.0
1980-7	243 (35.2 ksi)	333 (48.3 ksi)	12.0
1980-8	241 (35.0 ksi)	331 (48.0 ksi)	12.7
1980-9	236 (34.3 ksi)	328 (47.6 ksi)	12.7
1980-10	235 (34.1 ksi)	327 (47.4 ksi)	12.0
1980-12	308 (44.7 ksi)	389 (56.4 ksi)	10.7
1980-13	319 (46.2 ksi)	392 (56.8 ksi)	10.7
1980-14	308 (44.7 ksi)	388 (56.3 ksi)	10.7
1980-15	325 (47.2 ksi)	399 (57.9 ksi)	10.0
1980-16	320 (46.4 ksi)	394 (57.2 ksi)	10.0
1980-17	332 (48.1 ksi)	405 (58.7 ksi)	10.0
1980-18	315 (45.7 ksi)	392 (56.8 ksi)	9.3
1980-19	334 (48.5 ksi)	404 (58.6 ksi)	10.7

Table 27 - SCC Results

Alloy	Hours to Failure					
	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5	Specimen 6
1980-3	1.5	1.5	1.5	1.5	2.5	2.5
1980-6	1.5	2	2	2.5	3	3.5
1980-8	1.5	1.5	1.5	2	2	N/A
1980-10	1.5	1.5	2	2	3.5	8
1980-12	1	1	0.5	1	N/A	N/A
1980-13	1	0.5	0.5	1	N/A	N/A
1980-14	0.5	0.5	0.5	0.5	N/A	N/A
1980-15	20.5	1	0.5	0.5	N/A	N/A
1980-16	1.5	20.5	0.5	0.5	N/A	N/A
1980-17	0.5	1	0.5	1	N/A	N/A
1980-18	0.5	20.5	1	1	N/A	N/A
1980-19	0.5	0.5	0.5	2.5	N/A	N/A

[0043] As shown, the new aging practice yields significant improvement in throughput via decreased total aging time, and with similar strength and corrosion resistance.

### Example 6 - Aging of Alloy 1953

[0044] Russian alloy 1953 having the composition shown in Table 28 was produced as a conventional rod product (e.g., homogenized, extruded to rod, solution heat treated and cold water quenched) having an outer diameter of about 17.8 cm (7.0 inches) and a thickness of about 3.3 cm (1.3 inches). After about 0.5 - 1 days of natural aging, the 1953 alloy rod was multi-step aged for various times at various temperatures, as shown in Table 29. After aging, mechanical properties were measured in accordance with ASTM E8 and B557, the results of which are shown in Table 30. Stress corrosion cracking (SCC) resistance was also measured in accordance with ASTM G103, Boiling Salt Test, the results of which are shown in Table 31 (stress in the ST direction and with a stress of 138 MPa (20 ksi)), and in accordance with ASTM G44, 3.5% NaCl, Alternate Immersion, the results of which are shown in Table 32 (stress in the ST direction and with a stress of 241 MPa (35 ksi)).

Table 28 - Composition of the 1953 Alloy (in wt. %)\*

Alloy	Zn	Mg	Cu	Zr	Si	Fe	Mn	Cr	Ti
1953	5.76	2.65	0.55	0.02	0.04	0.08	0.17	0.20	<0.01

\* The balance of the alloy is aluminum and other elements, with the aluminum alloy containing not more than 0.05 wt. % each of any other element, and with the aluminum alloy containing not more than 0.15 wt. % in total of the other elements.

Table 29 - Artificial Aging Practices

Alloy	1 <sup>st</sup> Step	2 <sup>nd</sup> Step
1953-1	230°F for 5 hours	330°F for 5 hours
1953-2	400°F for 10 mins.	330°F for 2 hours
1953-3	400°F for 10 mins.	330°F for 4 hours
1953-4	400°F for 10 mins.	330°F for 6 hours
1953-5	460°F for 5 mins.	330°F for 4 hours
1953-6	430°F for 7.5 mins.	330°F for 4 hours
1953-7	400°F for 5 mins.	330°F for 4 hours
1953-8	400°F for 15 mins.	330°F for 4 hours
1953-9	460°F for 5 mins.	330°F for 2 hours
1953-10	460°F for 7.5 mins.	330°F for 6 hours

230°F is 110°C, 330°F is 166°C, 400°F is 204°C, 430°F is 221°C and 460°F is 238°C.

For the artificial aging, unless otherwise stated, the samples were heated to the first temperature in about 50 minutes and then held at the stated temperature for the stated amount

of time. The samples were then cooled to the second temperature by changing the furnace set-point and opening the furnace door until the second temperature was reached. The specimens were then held at the second temperature for the stated amount of time, after which the samples were removed from the furnace and allowed to air cool to room temperature.

Table 30 - Mechanical Properties

Alloy	Tensile Yield Strength (TYS), MPa	Ultimate Tensile Strength (UTS), MPa	Elongation, %
1953-1	476 (69.0 ksi)	538 (78.0 ksi)	12.0
1953-2	462 (67.0 ksi)	522 (75.7 ksi)	12.0
1953-3	455 (66.0 ksi)	520 (75.4 ksi)	12.0
1953-4	449 (65.1 ksi)	512 (74.3 ksi)	12.0
1953-5	365 (53.0 ksi)	454 (65.8 ksi)	12.0
1953-6	412 (59.7 ksi)	489 (70.9 ksi)	12.0
1953-7	447 (64.9 ksi)	517 (75.0 ksi)	12.0
1953-8	434 (63.0 ksi)	507 (73.6 ksi)	12.0
1953-9	361 (52.3 ksi)	456 (66.1 ksi)	13.3
1953-10	352 (51.1 ksi)	449 (65.1 ksi)	12.0

Table 31 - SCC Results - ASTM G103

Alloy	Days to Failure		
	Specimen 1	Specimen 2	Specimen 3
1953-1	0.08	0.17	0.17
1953-2	0.17	0.17	0.17
1953-3	0.17	0.17	0.17
1953-4	0.17	0.08	0.08

Table 32 - SCC Results - ASTM G44

Alloy	Days to Failure					
	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5	Specimen 6
1953-1	DNF	90	90	N/A	N/A	N/A
1953-2	DNF	90	90	N/A	N/A	N/A
1953-3	90	DNF	DNF	N/A	N/A	N/A
1953-4	90	DNF	N/A	N/A	N/A	N/A
1953-5	DNF	99	DNF	DNF	DNF	DNF
1953-6	DNF	DNF	DNF	90	90	N/A
1953-7	90	DNF	90	90	DNF	DNF
1953-8	75	90	DNF	90	DNF	90
1953-9	DNF	DNF	DNF	DNF	DNF	DNF
1953-10	DNF	DNF	DNF	DNF	DNF	DNF

\* DNF = did not fail after 140 days

07 05 20

[0045] As shown, the new aging practice yields significant improvement in throughput via decreased total aging time, and with similar strength and corrosion resistance. Indeed, alloy 1953-2 realizes about the same strength as conventionally aged 1953-1, but with only about 2.17 hours of total aging time (not including ramp-up time and cool down time) as compared to the total aging time of 10 hours (not including ramp-up time and cool down time) for alloy 1953-1.

[0046] While various embodiments of the present disclosure have been described in detail, it is apparent that modifications and adaptations of those embodiments will occur to those skilled in the art. However, it is to be expressly understood that such modifications and adaptations are within the spirit and scope of the present disclosure.

## Claims

1. A method comprising:
  - (a) casting an aluminum alloy having from 2.5 - 12.0 wt. % Zn and from 1.0 to 5.0 wt. % Mg, where at least one of the zinc and the magnesium is the predominate alloying ingredient other than aluminum;
  - (b) optionally hot working or cold working the aluminum alloy;
  - (c) after the casting step (a) and the optional step (b), solution heat treating and then quenching the aluminum alloy;
  - (d) after step (c), optionally working the aluminum alloy;
  - (e) after step (c) and the optional step (d), artificially aging the aluminum alloy, wherein the artificial aging step (e) comprises:
    - (i) first aging the aluminum alloy at a first temperature of from 166°C to 277°C (330°F to 530°F) and for a first aging time of from 5 minutes to 45 minutes;
    - (ii) second aging the aluminum alloy at a second temperature for a second aging time of at least 30 minutes, wherein the second temperature is lower than the first temperature.
2. The method of claim 1, wherein the first temperature is from 177°C to 238°C (350°F to 460°F).
3. The method of claim 1, wherein the first temperature is from 199°C to 216°C (390°F to 420°F).
4. The method of any of the preceding claims, wherein the first aging time is not greater than 30 minutes.
5. The method of any of the preceding claims, wherein the first aging time is at least 5 minutes.
6. The method of any of the preceding claims, wherein the second aging temperature is from 2.8 to 83.3 K (5 to 150°F) lower than the first aging temperature.
7. The method of any of the preceding claims, wherein the second aging temperature is from 5.6 to 55.6 K (10 to 100°F) lower than the first aging temperature.
8. The method of any of the preceding claims, wherein the second aging temperature is from 5.6 to 41.7 K (10 to 75°F) lower than the first aging temperature.

9. The method of any of the preceding claims, wherein the second aging temperature is from 11.1 to 27.8 K (20 to 50°F) lower than the first aging temperature.
10. The method of any of the preceding claims, wherein the first aging temperature is about 204°C (400°F) and wherein the second aging temperature is about 182°C (360°F).
11. The method of any of the preceding claims, wherein the method consists of steps (a), (c) and (e), optionally with step (d).
12. The method of any of the preceding claims, wherein the aluminum alloy comprises  
4.0 - 5.0 wt. % Zn and 1.0 - 2.5 wt. % Mg, optionally with up to 3.0 wt. % Cu.