



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification⁵ : D01F 2/00, 11/02, D06M 13/224 D06M 13/41, 13/358, D06P 1/382 D06P 1/642</p>	<p>A1</p>	<p>(11) International Publication Number: WO 94/09191</p> <p>(43) International Publication Date: 28 April 1994 (28.04.94)</p>
<p>(21) International Application Number: PCT/GB93/02155</p> <p>(22) International Filing Date: 19 October 1993 (19.10.93)</p> <p>(30) Priority data: 9222059.9 21 October 1992 (21.10.92) GB</p> <p>(71) Applicant (for all designated States except US): COUR- TAULDS FIBRES LIMITED [GB/GB]; 50 George Street, London W1A 2BB (GB).</p> <p>(72) Inventor; and (75) Inventor/Applicant (for US only) : POTTER, Christopher, David [GB/GB]; 27 Crabtree Hill, Little Eaton, Derby DE2 5DL (GB).</p> <p>(74) Agent: HALE, Stephen, Geoffrey; J.Y. & G.W. Johnson, Furnival House, 14-18 High Holborn, London WC1V 6DE (GB).</p>	<p>(81) Designated States: AT, AU, BB, BG, BR, BY, CA, CH, CZ, DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, LV, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>	
<p>(54) Title: FIBRE TREATMENT</p> <p>(57) Abstract</p> <p>The fibrillation tendency of solvent-spun cellulose fibre is reduced by treating the previously dried fibre with a chemical reagent containing at least two functional groups which are reactive with cellulose and which are electrophilic carbon-carbon double bonds, particularly vinyl sulphone groups, or precursors thereof or electrophilic three-membered heterocyclic rings or precursors thereof. The chemical reagent is preferably colourless and is preferably applied to the fibre from aqueous solution. The fibre may be contained in a woven or knitted fabric.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NE	Niger
BE	Belgium	GN	Guinea	NL	Netherlands
BF	Burkina Faso	GR	Greece	NO	Norway
BG	Bulgaria	HU	Hungary	NZ	New Zealand
BJ	Benin	IE	Ireland	PL	Poland
BR	Brazil	IT	Italy	PT	Portugal
BY	Belarus	JP	Japan	RO	Romania
CA	Canada	KP	Democratic People's Republic of Korea	RU	Russian Federation
CF	Central African Republic	KR	Republic of Korea	SD	Sudan
CG	Congo	KZ	Kazakhstan	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovak Republic
CM	Cameroon	LU	Luxembourg	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	MC	Monaco	TG	Togo
CZ	Czech Republic	MG	Madagascar	UA	Ukraine
DE	Germany	ML	Mali	US	United States of America
DK	Denmark	MN	Mongolia	UZ	Uzbekistan
ES	Spain			VN	Viet Nam
FI	Finland				

- 1 -

FIBRE TREATMENTTechnical Field

This invention is concerned with improvements in methods of reducing the fibrillation tendency of solvent-spun cellulose fibre.

It is known that cellulose fibre can be made by extrusion of a solution of cellulose in a suitable solvent into a coagulating bath. One example of such a process is described in US-A-4,246,221, the contents of which are incorporated herein by way of reference. Cellulose is dissolved in a solvent such as a tertiary amine N-oxide, for example N-methylmorpholine N-oxide. The resulting solution is then extruded through a suitable die into an aqueous bath to produce an assembly of filaments which is washed in water to remove the solvent and is subsequently dried. This process is referred to as "solvent-spinning", and the cellulose fibre produced thereby is referred to as "solvent-spun" cellulose fibre. Solvent-spun cellulose fibre is to be distinguished from cellulose fibre made by other known processes which rely on the formation of a soluble chemical derivative of cellulose and its subsequent decomposition to regenerate the cellulose, for example the viscose process.

Fibre may exhibit a tendency to fibrillate, particularly when subjected to mechanical stress in the wet state. Fibrillation occurs when fibre structure breaks down in the longitudinal direction so that fine fibrils become partially detached from the fibre, giving a hairy appearance to the fibre and to fabric containing it, for example woven or knitted fabric. Dyed fabric containing fibrillated fibre tends to have a "frosted" appearance, which may be aesthetically undesirable. Such fibrillation is believed to be caused by mechanical abrasion of the fibres during treatment in a wet and swollen state. Wet treatment processes such as dyeing processes inevitably subject fibres to mechanical abrasion. Higher temperatures and longer times of treatment generally tend to produce greater degrees

- 2 -

of fibrillation. Solvent-spun cellulose fibre appears to be particularly sensitive to such abrasion and is consequently often found to be more susceptible to fibrillation than other types of cellulose fibre. The present invention is
5 concerned with the treatment of solvent-spun cellulose fibre so as to reduce or inhibit its tendency to fibrillate. It has however been found that some such treatments may have detrimental effects on the mechanical properties of the fibre such as its tenacity and extensibility, for example by
10 embrittling the fibre, or on the processability of the fibre and fabric, in particular its dyeability. It can be difficult to identify a method of treatment which provides a satisfactory reduction in fibrillation tendency while avoiding such detrimental effects.

15 Background Art

EP-A-538,977 describes a process for providing a solvent-spun cellulose fibre with a reduced fibrillation tendency, in which process the fibre is treated with a chemical reagent having two to six functional groups
20 reactive with cellulose. It states that the untreated fibre and the treated fibre are preferably of substantially the same colour and that the functional groups reactive with cellulose are those generally used in fibre-reactive dyes for cellulose, for example as described in an article
25 entitled "Dyes, Reactive" in Kirk-Othmer, Encyclopaedia of Chemical Technology, 3rd edition, Volume 8 (1979, Wiley-Interscience) at pages 374-392. Preferred examples of such functional groups are said to be reactive halogen atoms attached to a polyazine ring, for example fluorine,
30 chlorine or bromine atoms attached to a pyridazine, pyrimidine or sym-triazine ring. Other examples of such functional groups are said to include vinyl sulphones and precursors thereof. The great majority of the chemical reagents utilised in the Examples in EP-A-538,977 contain
35 halogen atoms attached to a polyazine ring as the only functional groups reactive with cellulose, but one commercial dyestuff which is used in the Examples contains as the functional groups one chlorine atom and one vinyl

- 3 -

sulphone group attached to a triazine ring.

FR-A-2273091 describes a method of manufacturing polynosic viscose rayon fibre with reduced tendency to fibrillation. In that method the fibre is treated in the primary gel state characteristic of polynosic viscose rayon manufacture with a crosslinking agent containing at least two acrylamido groups and an alkaline catalyst. This primary polynosic gel is a highly swollen gel having a water imbibition of 190-200%, which is found only in polynosic viscose rayon that has never been dried. Water imbibition is defined as the weight of water retained per unit weight of bone-dry material. By way of comparison, never-dried conventional viscose rayon fibre is known generally to have a water imbibition in the range 120-150%. Triacryloyl-hexahydro-1,3,5-triazine and N,N'-methylenebisacrylamide are mentioned in FR-A-2273091 as preferred examples of crosslinking agent.

Disclosure of Invention

The present invention provides in one aspect a process for the manufacture of solvent-spun cellulose fibre with a reduced tendency to fibrillation wherein the fibre is treated with a chemical reagent containing two or more functional groups reactive with cellulose, characterised in that the fibre has previously been dried and in that the reagent contains as functional groups reactive with cellulose at least two groups selected from the class consisting of electrophilic carbon-carbon double bonds and precursors thereof and electrophilic three-membered heterocyclic rings and precursors thereof.

It has surprisingly been found that the selection in combination of the characterising features of the present invention offers advantages in reducing fibrillation tendency over any treatment previously disclosed. These features are the selection of previously-dried fibre and the selection of electrophilic carbon-carbon double bonds or electrophilic three-membered heterocyclic rings as the

- 4 -

functional groups.

The present invention provides in another aspect a process for the manufacture of solvent-spun cellulose fibre with a reduced tendency to fibrillation wherein the fibre is
5 treated with a chemical reagent containing two or more functional groups reactive with cellulose, characterised in that the fibre has previously been dried and in that the reagent reacts with the cellulose with the formation of at least two aliphatic ether groups. These aliphatic ether
10 groups are derived from cellulose hydroxyl groups.

The chemical reagent preferably contains electrophilic carbon-carbon double bonds as the functional groups reactive with cellulose. The electrophilic carbon-carbon double bonds are activated towards addition of a nucleophile and
15 are polarised by substitution with at least one electron-withdrawing group. Cellulose contains hydroxyl groups which react with the electrophilic carbon-carbon double bonds in the chemical reagent by Michael addition to form ether groups. Electrophilic carbon-carbon double bonds
20 substituted with a single electron-withdrawing group are generally preferred. Examples of suitable electron-withdrawing groups include carbonyl groups, for example amide or ester groups, and sulphone groups. Preferred examples of such functional groups include acrylamido and
25 acrylate ester groups. Precursors of electrophilic carbon-carbon double bonds include beta-sulphatoethyl sulphone and beta-chloroethyl sulphone groups. The carbon-carbon double bond is preferably the double bond in a vinyl group. A preferred example of such a functional group is the vinyl
30 sulphone group. Additional substitution on the double bond generally reduces the reactivity of the bond towards addition of a nucleophile. The hydroxyl groups in cellulose react with such reagents to form $-XCH_2CH_2O-$ groups, wherein X represents an electron-withdrawing group
35 such as $-CO-$ or $-SO_2-$ and the oxygen atom is derived from a cellulose hydroxyl group.

- 5 -

The chemical reagent may alternatively contain electrophilic three-membered heterocyclic rings as the functional groups reactive with cellulose. Examples of such rings are aziridine rings, in which the carbon atoms are preferably unsubstituted and the nitrogen atom is a tertiary nitrogen atom. The hydroxyl groups in cellulose react with the aziridine rings in such reagents to open the ring with the formation of an $-NHCH_2CH_2O-$ group, wherein the cellulose is linked to the reagent by an ether group. Examples of precursors of aziridine rings include 2-chloroethylamino, 2-sulphatoethylamino, 2-chloroethylamido and 2-chloroethyl-sulphonamido groups.

The bonds in the chemical reagent are preferably resistant to chemical hydrolysis under the conditions normally experienced in fabric processing and laundering, and chemical reagents in which the functional groups are vinyl sulphone groups or particularly acrylamido groups may therefore be preferred. The functional groups in the reagent may be the same or different. The chemical reagent may additionally contain one or more functional groups of types other than electrophilic carbon-carbon double bonds, for example reactive halogen atoms attached to a polyazine ring.

The method of treatment of the invention has the advantage that the bonds formed between the reagent and cellulose resist chemical hydrolysis under the conditions normally experienced in fabric processing and laundering, in particular chemical hydrolysis by mild alkali. These bonds are aliphatic ether groups. It has been found that when solvent-spun cellulose fibre is treated instead with a reagent of the halogenated polyazine type, as described in EP-A-538,977, the reduction in fibrillation tendency so obtained tends to be lost when fabric containing the treated fibre is scoured and laundered. Such reagents react with cellulose to form a multiplicity of aromatic/aliphatic ether groups which are believed to be prone to chemical hydrolysis

- 6 -

during fabric processing and laundering.

It is known that fibre-reactive dyestuffs containing vinyl sulphone and in particular acryloylamino (acrylamido) groups are less reactive towards cellulose than dyestuffs which are reactive acid chlorides (imide chlorides), in particular dichlorotriazine and dichloropyrimidine reactive dyes. It was therefore surprising to find that such less reactive groups are highly effective in a treatment to reduce fibrillation tendency.

10 The chemical reagent generally contains as functional groups reactive with cellulose two to six, preferably three to six, often three or four, commonly three, electrophilic carbon-carbon double bonds or three-membered heterocyclic rings or precursors of either of these. The chemical reagent preferably contains at least one ring with at least three, in particular three, cellulose-reactive functional groups attached thereto. Examples of such rings are polyazine rings, for example diazine or triazine rings, which may be hydrogenated. A preferred example of the reagent is triacryloylhexahydrotriazine (1,3,5-tri-
15 propenoylperhydro-1,3,5-triazine, abbreviated as TAHT), which has previously been suggested as a dye fixative. Other examples of the reagent include the reaction product of two molecules of TAHT with one molecule of a
20 bifunctional reagent capable of reacting with TAHT, for example an aliphatic diol. Another example of the reagent is 2,4,6-tris(1-aziridinyl)-1,3,5-triazine. A further example of the reagent is N,N'-methylenabisacrylamide.

Solvent-spun fibre which has been treated by the process of the invention is preferably of substantially the same colour as the untreated fibre. This can be achieved by the use of a chemical reagent which is substantially colourless and so does not substantially alter the colour of the fibre by the treatment, for example TAHT. Such treated
35 fibre is thereafter suitable for dyeing in any manner known

- 7 -

for cellulose fibres, yarns or fabrics.

The chemical reagent is preferably applied to the fibre in the form of an aqueous solution. The chemical reagent may contain one or more solubilising groups to
5 enhance its solubility in water. A solubilising group may be an ionic species, for example a sulphonic acid group, or a nonionic species, for example an oligomeric poly(ethylene glycol) or poly(propylene glycol) chain. Nonionic species
10 generally have less effect on the essential dyeing characteristics of the cellulose fibre than ionic species and may be preferred for this reason. The solubilising group may be attached to the chemical reagent by a labile bond, for example a bond which is susceptible to hydrolysis after the chemical reagent has reacted with the cellulose
15 fibre.

The known processes for the manufacture of solvent-spun cellulose fibre include the steps of:

- (i) dissolving cellulose in a solvent, in particular a tertiary amine N-oxide, to form a solution,
20 the solvent being miscible with water;
- (ii) extruding the solution through a die to form a fibre precursor;
- (iii) passing the fibre precursor through at least one aqueous bath to remove the solvent and form the
25 fibre and wash the fibre; and
- (iv) drying the fibre.

The wet fibre at the end of step (iii) is never-dried fibre and typically has a water imbibition in the range
30 120-150%. The dried fibre after step (iv) typically has a water imbibition of around 60-80%. Solvent-spun cellulose fibre is treated according to the process of the invention

- 8 -

after it has been dried, that is to say subsequent to step (iv).

The process of the invention may be carried out using conventional techniques for fibre-reactive dyeing of cellulose, in which the chemical reagent is used in the same manner as or a similar manner to a reactive dyestuff. The process may be carried out on tow or staple fibre, yarn or woven or knitted fabric. It is preferably carried out on fabric prior to any dyeing process and further preferably during a scouring treatment, although it may alternatively be carried out concurrently with or subsequently to a dyeing process or in both a scouring process and a dyeing process. Conventional dyestuffs for cellulose, for example direct or reactive dyestuffs, may be used in such dyeing processes. The process of the invention may be carried out using a dye bath which contains both a conventional reactive dyestuff and the chemical reagent. The functional groups in any such dyestuffs and reagents may be the same or different chemical species.

The fibrillation tendency of cellulose fibre can be reduced by use of the process of the invention without markedly reducing the dyeability of the fibre. It has been found possible to strip dye from dyed fibre or fabric treated according to the invention and subsequently to re-dye it without excessive fibrillation. The fibre or fabric continues to exhibit a low fibrillation tendency after the relatively severe type of chemical treatment required to strip dye from a fibre or fabric.

The electrophilic carbon-carbon double bonds in the chemical reagent used in the process of the invention may react most rapidly with cellulose under alkaline conditions. It may therefore be preferred to treat the solvent-spun fibre with a mildly alkaline aqueous solution of the chemical reagent, for example from an aqueous solution made alkaline by the addition of sodium carbonate (soda ash) or

- 9 -

sodium hydroxide. When TAHT is used as the chemical reagent the pH of the solution is preferably in the range 10 to 13, more preferably 10.5 to 11.5. Alternatively, the fibre may be treated using a two-stage technique, in which the fibre 5 is treated firstly with mild aqueous alkali and secondly with the solution of the chemical reagent, although this may generally be less preferred. Such initial treatment of a fibre or fabric with alkali is known in the dyeing trade as presharpening. The solution of the chemical reagent used in 10 the second step of the two-stage technique may or may not contain added alkali.

The electrophilic groups in the chemical reagent may react with cellulose at room temperature, but it is generally preferable to apply heat to induce a substantial 15 extent of reaction. For example, the reagent may be applied using a hot solution, or the fibre wetted with the reagent may be heated or steamed, or the wetted fibre may be heated to dry it. If the fibre or fabric is steamed, then low-pressure steam is preferably used, for example at a 20 temperature of 100 to 110°C, and the steaming time may be for example 5 to 20 minutes.

The fibre may be rinsed with a mildly acidic aqueous solution, for example a weak solution of acetic acid, after reaction of the chemical reagent with the cellulose in order 25 to neutralise any added alkali.

The fibre may be treated so as to react with 0.1 to 10%, preferably 0.2 to 5%, more preferably 0.5 to 3%, further preferably 1 to 2%, by weight of the chemical reagent, based on the weight of fibre. The chemical reagent 30 may be reacted with the cellulose fibre so that less than 10% and preferably less than 5% of the dye sites on the cellulose fibre are occupied, so as to permit subsequent dyeing of the fibre with coloured dyes, which may or may not be reactive dyes.

- 10 -

The process of the invention is applicable to the treatment of fibre contained in a knitted or woven fabric. Knitted fabric has been generally found to be more susceptible to fibrillation than woven fabric. Fabric 5 treated by the process of the invention may subsequently be processed, in particular dyed, in open width or by methods which tend to subject the fabric to more severe abrasion, for example in rope form, including jet treatment. Knitted fabric is only rarely processed in open width and is 10 preferably treated in rope form. Woven fabric is commonly processed in open width rather than in rope form to avoid the generation of unsightly marks and creases.

It is an advantage of the invention that fibre or fabric can be treated during a conventional wet processing 15 stage and that therefore no additional processing time or step is needed. The cost of machine time is a significant element of the cost of fibre or fabric processing and may outweigh the cost of the chemicals used.

Cellulose fibre, particularly in the form of fabrics 20 made from such fibre, may be treated with a cellulase enzyme to remove surface fibrils. The cellulase enzyme may be in the form of an aqueous solution, and the concentration may be in the range 0.5% to 5%, preferably 1% to 3%, by weight. The pH of the solution may be in the range 4 to 6. There 25 may be a nonionic detergent in the solution. The fabric may be treated at a temperature in the range 20°C to 70°C, preferably 40°C to 65°C, further preferably 50°C to 60°C, for a period in the range 15 minutes to 4 hours. This cellulase treatment may be utilised to remove fibrils from 30 solvent-spun fibres, yarns and fabrics which have been treated with a chemical reagent according to the method of the invention.

The invention is illustrated by the following Examples. Solvent-spun cellulose fibre commercially 35 available from Courtaulds Fibres Limited under the Trade

- 11 -

Mark 'Tencel' was used in all cases. Materials were assessed for degree of fibrillation using the method described below as Test Method 1 and assessed for fibrillation tendency using the techniques described below 5 as Test Methods 2-4.

Test Method 1 (Assessment of Fibrillation)

There is no universally accepted standard for assessment of fibrillation, and the following method was used to assess Fibrillation Index (F.I.). A series of 10 samples of fibre having nil and increasing amounts of fibrillation was identified. A standard length of fibre from each sample was then measured and the number of fibrils (fine hairy spurs extending from the main body of the fibre) along the standard length was counted. The length of each 15 fibril was measured, and an arbitrary number, being the product of the number of fibrils multiplied by the average length of each fibril, was determined for each fibre. The fibre exhibiting the highest value of this product was identified as being the most fibrillated fibre and was 20 assigned an arbitrary Fibrillation Index of 10. The wholly unfibrillated fibre was assigned a Fibrillation Index of zero, and the remaining fibres were evenly ranged from 0 to 10 based on the microscopically measured arbitrary numbers.

The measured fibres were then used to form a standard 25 graded scale. To determine the Fibrillation Index for any other sample of fibre, five or ten fibres were visually compared under the microscope with the standard graded fibres. The visually determined numbers for each fibre were then averaged to give a Fibrillation Index for the sample 30 under test. It will be appreciated that visual determination and averaging is many times quicker than measurement, and it has been found that skilled fibre technologists are consistent in their rating of fibres.

Fibrillation Index of fabrics was assessed on fibres

- 12 -

drawn from the surface of the fabric. Woven fabrics having an F.I. of more than about 2.0 to 2.5 exhibited an unsightly appearance.

Test Method 2 (Scour, Bleach, Dye)

5 (i) Scour

1 g fibre was placed in a stainless steel cylinder approximately 25 cm long by 4 cm diameter and having a capacity of approximately 250 ml. 50 ml conventional scouring solution containing 2 g/l Detergyl FS955 (an
10 anionic detergent available from ICI plc) (Detergyl is a Trade Mark) and 2 g/l sodium carbonate was added, a screw cap fitted and the capped cylinder tumbled end-over-end at 60 tumbles per minute for 60 minutes at 95°C. The scoured fibre was then rinsed with hot and cold water.

15 (ii) Bleach

50 ml bleaching solution containing 15 ml/l 35% hydrogen peroxide, 1 g/l sodium hydroxide, 2 g/l Prestogen PC (a bleach stabiliser available from BASF AG) (Prestogen is a Trade Mark) and 0.5 ml/l Irgalon PA (a sequestrant
20 available from Ciba-Geigy AG) (Irgalon is a Trade Mark) was added to the fibre and a screw cap fitted to the cylinder. The cylinder was then tumbled as before for 90 minutes at 95°C. The bleached fibre was then rinsed with hot and cold water.

25 (iii) Dye

50 ml dyeing solution containing 8% on weight of fibre Procion Navy HER 150 (a reactive dye) (Procion is a Trade Mark of ICI plc) and 55 g/l Glauber's salt was added, and the cylinder was capped and tumbled as before for 10 minutes
30 at 40°C. The temperature was raised to 80°C and sufficient sodium carbonate added to give a concentration of 20 g/l.

- 13 -

The cylinder was then capped once more and tumbled for 60 minutes. The fibre was rinsed with water. 50 ml solution containing 2 ml/l Sandopur SR (a detergent available from Sandoz AG) (Sandopur is a Trade Mark) was then added and the cylinder capped. The cylinder was then tumbled as before for 20 minutes at 100°C. The dyed fibre was then rinsed and dried. It was then assessed for fibrillation using Test Method 1.

Test Method 3 (Wash and Tumble-dry)

10 Fabrics were subjected to wet abrasive conditions utilising a typical domestic wash and tumble-dry cycle (W/T cycle). The fabric was washed in a solution of Daz (a domestic detergent available from Procter & Gamble Limited) (Daz is a Trade Mark) for 45 minutes at 60°C.

15 Test Method 4 (Blender)

If the sample of fibre to be tested had not previously been scoured, it was scoured using Test Method 2(i).

0.5 g fibre cut into 5-6 mm lengths and dispersed in 500 ml water at ambient temperature was placed in a household blender (liquidiser) and the blender run for 2 minutes at about 12000 rpm. The fibre was then collected and dried and assessed for degree of fibrillation using Test Method 1. Test Method 4 provides more severe fibrillating conditions than Test Method 2.

25 Comparative Example 1

Never-dried solvent-spun cellulose fibre (1.7 dtex tow, 30 cm length) was padded with an aqueous alkaline solution (100 ml) containing N,N'-methylenebisacrylamide (10 g/l) and sodium sulphate (100 g/l) under various conditions, rinsed with 0.1% by volume acetic acid, and dried. F.I. was assessed by Test Method 4. Details of each treatment and of

- 14 -

the F.I. results are set out below:

Alkali	Treatment	F.I.
-	None	5.6 (average of 4)
Na ₂ CO ₃ (20 g/l)	Pad 3 x 5 min	3.4
5 Na ₂ CO ₃ (20 g/l)	Steam for 10 min	4.8
Na ₂ CO ₃ (20 g/l)	Steam for 20 min	2.9
NaOH (20 g/l)	Steam for 20 min	4.4
Na ₂ CO ₃ (20 g/l)	70°C for 8 min	3.5

Steaming was carried out at 100°C and 98% R.H. The 10 fibre was discoloured when NaOH was used as the alkali. A moderate improvement in F.I. was observed in all cases.

Comparative Example 2

Never-dried solvent-spun cellulose fibre (1.7 dtex, 30 cm length) was padded with an aqueous alkaline solution (100 ml) containing TAHT (20 g/l) under various conditions, rinsed with 0.1% by volume acetic acid, and dried. F.I. was assessed by Test Method 4. Details of each treatment and of the F.I. results are set out below:

	Alkali	Na ₂ SO ₄	Treatment	F.I.
20	-	-	None	5.0
	Na ₂ CO ₃ (20 g/l)	-	Steam for 20 min	0.3
	Na ₂ CO ₃ (20 g/l)	-	Dry 2 min at 120°C, steam 1 min	0.3
	NaOH (20 g/l)	-	Pad at 40°C	0.7
	Na ₂ CO ₃ (10 g/l)	75 g/l	Steam for 20 min	0.2
25	Na ₂ CO ₃ (10 g/l)	75 g/l	Dry 2 min at 120°C, steam 1 min	0.6
	Na ₂ CO ₃ (10 g/l)	50 g/l	Steam for 20 min	0.2
	Na ₂ CO ₃ (10 g/l)	50 g/l	Dry 2 min at 120°C, steam 1 min	1.2
	Na ₂ CO ₃ (10 g/l)	-	Not heated	3.2
	Na ₂ CO ₃ (10 g/l)	-	Steam for 20 min	0.1
30	Na ₂ CO ₃ (10 g/l)	-	Dry 2 min at 120°C, steam 1 min	0.3

- 15 -

A marked improvement in F.I. was observed in almost all cases. However, the heating times required in these treatments would be unacceptable on a continuous production line for the manufacture of solvent-spun fibre.

5

Comparative Example 3

Three samples of never-dried solvent-spun cellulose fibre were treated with solutions of TAHT in various ways as described below. They were then scoured, bleached and dyed according to Test Method 2, with F.I. being measured after 10 each step by Test Method 4.

Sample 1 was padded with a solution containing TAHT (20 g/l), Na_3PO_4 (10 g/l) and Na_2SO_4 (25 g/l) and then heated at 70°C for 6 minutes.

Sample 2 was padded with a solution containing TAHT (30 g/l), urea (100 g/l) and Na_2CO_3 (10 g/l) and then steamed at 100°C for 20 minutes.

Sample 3 was first padded with a solution containing Na_2CO_3 (2 g/l) at 70°C and then padded with a solution containing TAHT (20 g/l), Na_2CO_3 (8 g/l) and Na_2SO_4 (25 g/l) at 70°C.

The following average results for F.I. were obtained, the number of replicate experiments in each case being shown in parentheses:

	After scour	After bleach	After dyeing
25 Sample 1	0.1 (2)	0.5 (3)	0.2 (3)
Sample 2	0.5 (3)	1.7 (3)	2.2 (3)
Sample 3	2.4 (3)	2.4 (3)	2.6 (3)

Although good results were obtained on Sample 1, the heating time required would be unacceptable on a continuous

- 16 -

production line for the manufacture of solvent-spun fibre.

Example 1

Woven fabric of solvent-spun cellulose fibre (123 gm-2 standard weave of 20 tex ring-spun yarn of 1.7 dtex fibre) 5 was padded with an aqueous solution of TAHT (20 g/l), Na_2CO_3 (10 g/l) and Na_2SO_4 (25 g/l) and heated for 15 minutes at 70°C (Sample 1). A control sample was treated in the same way except that the TAHT was omitted. Another sample of fabric was padded with an aqueous solution of TAHT (20 g/l) 10 and NaOH (20 g/l) and heated for 30 minutes at 40°C (Sample 2). The samples of fabric were then dyed under the following conditions. The sample was immersed in a bath containing Procion Navy H4R (4% by weight on fabric) (a monochloro-triazine reactive dye available from ICI plc) 15 (Procion is a Trade Mark), Matexil PAL (3 g/l) (a mild oxidising agent-nitrobenzenesulphonic acid-available from ICI plc) (Matexil is a Trade Mark) and Depsolube ACA (1 g/l) (an alkali-stable lubricant supplied for use in jet dyeing by ICI plc) (Depsolube is a Trade Mark) at 25°C. The 20 temperature was raised to 80°C while sufficient NaCl was added in three portions to give 70 g/l. The temperature was maintained for 20 minutes, sufficient Na_2CO_3 was added over 10 minutes to give 20 g/l and the temperature maintained for a further 60 minutes. The fabric was then 25 rinsed and soaped off in a solution of soap flakes (2 g/l) for 20 minutes at the boil. The dyed and dried fabrics were washed and tumble-dried five times and assessed for F.I., with the following results (averages of two experiments):

30	Control	3.7
	Sample 1	0.8
	Sample 2	1.8

A knitted fabric of solvent-spun cellulose fibre (193 gm-2 tubular knit of 20 tex rotor-spun yarn of 1.7 dtex

- 17 -

fibre) was treated and dyed in the same manner and F.I. assessed after two and four wash and tumble-dry cycles with the following results:

		2 cycles	4 cycles
5	Control	3.6	4.8
	Sample 1	0.0	0.1
	Sample 2	1.3	2.6

Example 2

A woven fabric of solvent-spun cellulose as used in Example 1 was scoured in open width with a solution containing Detergyl (2 g/l), alkali (2 g/l), TAHT (20 g/l) and Na_2SO_4 (25 g/l) and heated at 95°C for 1 hour. The nitrogen content of the scoured and dried fibre was measured by the Kjeldahl technique, and the results were expressed in terms of TAHT content by weight of the fabric. A sample of fabric treated in the same way but with the omission of TAHT was used as control. The samples of fabric were then dyed with the direct dye Solophenyl Red 3BL (available from Ciba-Geigy AG) (Solophenyl is a Trade Mark) in rope form on a winch, as follows. The fibre was immersed in a bath containing the dye (4% by weight of fabric) at 50°C, the temperature was raised to 100°C over 30 minutes and held there for 15 minutes, sufficient Na_2SO_4 was added to give 20 g/l, and the temperature was maintained for a further 45 minutes, after which the fabric was washed and dried. The samples of fabric were then repeatedly washed and tumble-dried, with F.I. being assessed after each cycle, and the following results were obtained:

30		Alkali	TAHT %	Wash and tumble-dry cycles					
				0	1	2	3	4	5
	Control	-	-	3.3	3.9	5.4	4.9	5.6	6.5
	Sample 1	Na_2CO_3	2.88	0.0	0.2	0.1	0.0	0.0	0.0
	Sample 2	Na_2CO_3	2.40	0.2	0.0	0.0	0.0	0.0	0.2
	Sample 3	NaOH	5.28	0.1	0.0	0.0	0.0	0.0	0.0

- 18 -

Sample 3 dyed to a paler shade than the other samples, and it is thought that this sample may have been overloaded with TAHT.

Example 3

5 A woven fabric of solvent-spun cellulose staple fibre as used in Example 1 was scoured in open width using a solution of Detergyl (2 g/l) and Na_2CO_3 (2 g/l) for 1 hour at 95°C. The fabric was then subjected to a series of treatments on a winch dyeing machine in rope form. The
10 first treatment was with a solution containing TAHT (20 g/l), Na_2CO_3 (2 g/l) and Na_2SO_4 (30 g/l) at 20°C for 10 minutes. Sufficient Drimarene Orange K3R (a dichloro-fluoropyrimidine reactive dye available from Sandoz AG) (Drimarene is a Trade Mark) was then added to give 4% by
15 weight on fibre. After 10 minutes, the temperature of the bath was raised to 50°C over 30 minutes and maintained at 50°C for a further 20 minutes. Na_2CO_3 (18 g/l) was then added and treatment continued for a further 60 minutes at 50°C. The fabric was then soaped off and dried. A control
20 sample was treated in the same way except that the TAHT was omitted. The samples of fabric were then subjected to repeated wash and tumble-dry cycles, and the following results for F.I. were obtained:

	Wash and tumble-dry cycles					
25	0	1	2	3	4	5
Control	1.5	3.7	3.5	3.7	4.8	5.0
Sample	3.1	1.2	0.5	0.4	0.6	0.4

Example 4

Fabric samples of solvent-spun cellulose fibre as used
30 in Example 1 were scoured using a solution of TAHT (20 g/l), Detergyl (2 g/l), Na_2CO_3 (2 g/l) and Na_2SO_4 (20 g/l) at 95°C for 1 hour. Control samples were scoured in the same

- 19 -

way except that the TAHT was omitted. Scouring was performed either in open form on a jig or in rope form on a winch. The samples were then dyed in rope form on a winch in the following manner. The fabric was treated with a bath containing Procion Green H4G (a monofunctional reactive dye available from ICI plc) (4% by weight on fabric), Depsolube ACA (1 g/l) (an alkali-stable lubricant supplied for use in jet dyeing by ICI plc) (Depsolube is a Trade Mark) and Matexil PAL (a mild oxidising agent - nitrobenzenesulphonic acid - used as a textile auxiliary to prevent dye reduction) (Matexil is a Trade Mark of ICI plc) (3 g/l). The fabric was run through the bath for 10 minutes at 20°C; the temperature was then raised to 80°C while NaCl (70 g/l) was added in portions; the temperature was maintained at 80°C for 20 minutes; Na₂CO₃ (20 g/l) was added over 10 minutes; and the temperature was maintained at 80°C for 60 minutes. The fabric was then rinsed and soaped off in a bath containing Sandopur SR (2 g/l) (a detergent available from Sandoz AG) (Sandopur is a Trade Mark) for 20 minutes at 95°C. The fabrics were then subjected to repeated wash and tumble-dry cycles and the following results for F.I. were obtained:

Fabric	Scour	TAHT	Wash and tumble-dry cycles					
			0	1	2	3	4	5
25 Woven	Jig	No	2.7	2.1	3.6	4.3	5.3	4.8
Woven	Jig	Yes	0.0	0.0	0.0	0.0	0.0	0.0
Woven	Winch	No	1.5	3.0	3.1	3.8	4.6	5.3
Woven	Winch	Yes	0.4	0.0	0.0	0.0	0.0	2.5
Knitted	Winch	No	1.4	3.9	4.2	4.9	4.2	5.1
30 Knitted	Winch	Yes	0.0	0.0	0.0	0.0	0.0	0.0

(It is thought that the result obtained with woven fabric, winch scouring using TAHT after 5 wash and tumble-dry cycles was anomalous.)

- 20 -

Example 5

A single-jersey knitted fabric of solvent-spun cellulose fibre was fully processed on a jet-dyeing machine. This type of machine provides the harshest of all 5 common processing conditions and is therefore the most likely to cause severe abrasion. The fabric was first scoured with a bath containing TAHT (20 g/l), Na_2SO_4 (25 g/l), Depsolube ACA (1 g/l), Na_2CO_3 (2 g/l) and Sandopur SR (2 g/l) at 50°C for 10 minutes. The temperature was 10 raised to 95°C and maintained at that value for 60 minutes. The fabric was then rinsed with hot water. It was then treated with a bath containing Na_2SO_4 (70 g/l) and Tebolan UF (3 g/l) (a nonionic lubricant available from Dr. Th Böhme KG, Germany) (Tebolan is a Trade Mark) at 25°C for 15 15 minutes, after which Procion Red HE-7B (4% on weight of fabric) (a bismonochlorotriazine reactive dye available from ICI plc) was added over 10 minutes. The temperature was raised to 80°C and maintained at that value for 20 minutes. Na_2CO_3 (2 g/l) was added over 10 minutes and the 20 fabric run through the machine for 1 hour, after which it was rinsed and soaped off. The fabric contained 5.16% by weight TAHT calculated from its nitrogen content (assessed by the Kjeldahl method). The side of the fabric exposed to the jet had F.I. 0.2, and this value remained unchanged 25 through 35 wash and tumble-dry cycles. The side of the fabric exposed to the jet undergoes the most severe treatment and garments are normally made up with this side facing inwards.

Example 6

30 A woven fabric of solvent-spun cellulose fibre (115 gm-2 standard weave of 20 tex ring-spun yarn of 1.7 dtex fibre) was scoured with a solution containing TAHT (20 g/l), Detergyl (2 g/l), Na_2CO_3 (2 g/l) and Na_2SO_4 (25 g/l) for 1 hour at 95°C. A control sample was scoured in the same 35 way but with the omission of TAHT. The samples of fabric

- 21 -

were then dyed with Procion Brown H3R (4% by weight on fabric) (a monochlorotriazine reactive dye available from ICI plc) (Procion is a Trade Mark) in the following manner. The fabric was treated with a solution containing the dye, 5 Matexil PAL (3 g/l) and Depsolube ACA (1 g/l) at 25°C. The temperature was then raised to 80°C while NaCl was added in three portions to give a concentration of 70 g/l. The temperature was maintained at 80°C for 20 minutes, after which Na₂CO₃ was added over 10 minutes to give a total 10 concentration of 22 g/l. Dyeing was continued for a further 60 minutes, during which time samples of dyebath and fabric were taken for analysis. The total amount of dye on each of the two fabrics was assessed by Q-value. Comparison of the treated fabric against the control gave Q = 100.2% (standard 15 = 100%).

	Time (minutes)	Standard		Treated	
		Dye in Bath	Dye on Fibre	Dye in Bath	Dye on Fibre
	0	100	-	100	-
20	15	15.4	87.3	22.7	84.8
	30	12.6	92.7	16.8	95.7
	45	11.1	95.8	13.9	95.3
	60	13.0	100	10.1	100

The figures in the columns headed "dye in bath" are 25 expressed as a percentage of the amount present in the bath initially. The figures in the columns headed "dye on fibre" are the percentage of the Q value developed after the arbitrary time of 60 minutes.

It can be seen that the treated fabric dyed at a 30 satisfactory rate.

Example 7

A woven fabric of solvent-spun cellulose fibre was

- 22 -

scoured with a solution of TAHT (20 g/l), Detergyl (2 g/l), Na_2CO_3 (2 g/l) Na_2SO_4 (25 g/l) for 1 hour at 95°C. A control sample was scoured in the same way, except that the TAHT was omitted. The treated and control samples were then dyed with either a direct or a reactive dye; treated to strip the dye from the fabric; redyed with the same dye as before; and subjected to a number of wash and tumble-dry (W/T) cycles. Fibrillation Index was assessed at each stage.

The following two methods were used to dye the fabric:

10 Direct dye, neutral bath method: Immerse the fabric in a solution of Sirius Super Violet F2BLL (4% by weight on fabric) (available from Bayer AG) (Sirius is a Trade Mark) and Na_2SO_4 (18 g/l) at room temperature; raise the temperature to 97°C over 45 minutes; maintain temperature for 1 hour; rinse and dry.

Reactive dye, standard method: Immerse the fabric in a solution of Procion Red MX-8B (4% by weight on fabric) (available from ICI plc) (Procion is a Trade Mark) at 40°C; maintain temperature for 10 minutes; add sufficient NaCl to give 60 g/l; maintain temperature for 30 minutes; add sufficient Na_2CO_3 to give 5 g/l; maintain temperature for 30 minutes; rinse; soap off using a solution of soap flakes (2 g/l) for 15 minutes at 100°C; dry.

The following three methods were used to strip the dye from the fabric; in each case, the fabric was rinsed and dried on conclusion of the stripping treatment:

Method A: Treat fabric with a solution of Na_2CO_3 (6 g/l) and sodium hydrosulphite (6 g/l) for 1 hour at 100°C.

- 23 -

Method B: Treat fabric with a solution of sodium hypochlorite (10 g/l) for 20 minutes in the cold followed by addition of a sufficient amount of a solution of sodium bisulphite or thiosulphate (2.5 g/l) to destroy the residual hypochlorite.

Method C: Method A followed by Method B.

The results obtained for F.I. are shown in the following Tables:

10 Direct Dye:

	Scoured	Dyed	Method	Stripped	Redyed	1 W/T	5 W/T
Control	2.2	1.8	A	1.0	2.4	7.2	9.2
			B	2.8	3.8	6.0	8.8
			C	1.6	3.2	6.2	8.8
15 Treated	1.2	0.6	A	2.2	0.4	0.4	0.6
			B	2.2	1.8	0.2	0.4
			C	2.4	0.4	0.4	0.4

Reactive Dye:

	Scoured	Dyed	Method	Stripped	Redyed	1 W/T	5 W/T
20 Control	2.2	2.0	A	2.0	1.6	2.8	7.6
			B	1.0	2.6	3.0	7.0
			C	0.4	0.8	2.8	8.2
25 Treated	1.2	0.4	A	0.4	0.8	0.4	0.2
			B	0.2	1.6	0.6	0.2
			C	0.8	0.4	0.2	0.2

It can be seen that the redyed fabric exhibited a considerably reduced tendency to fibrillation compared with the control in each case.

- 24 -

Example 8

Woven solvent-spun cellulose fabric as used in Example 1 was scoured at different values of pH using a solution of TAHT (10 g/l), Detergyl FS955 (2 g/l), Na₂SO₄ (5 g/l) and 5 alkali at 95°C for 1 hour. A control sample was scoured using a solution of Detergyl (2 g/l) and Na₂CO₃ (2 g/l) at 95°C for 1 hour. The liquor to fabric ratio was 10:1. The samples were then treated with a solution of Procion Red HE-7B (4% by weight on fibre) (available from ICI plc), Matexil 10 PAL (3 g/l) and Depsolube ACA (1 g/l) at 25°C; the temperature was raised to 80°C over 30 minutes while sufficient NaCl was added to give 70 g/l; the temperature was maintained for 20 minutes; sufficient Na₂CO₃ was added to give 20 g/l; the temperature was maintained for 60 15 minutes; then the fabric was rinsed and soaped off using a solution of Sandopur SR (2 g/l) for 20 minutes at 95°C. The liquor to fabric ratio was 70:1. The dried fabric was subjected to five wash and tumble-dry cycles. The Fibrillation Index of the samples was assessed, and the 20 TAHT content of the samples estimated from their nitrogen content determined by Kjeldahl analysis. The following results were obtained:

Alkali	pH	TAHT %	F.I.
-	-	-	7.2
25 NaHCO ₃ (3 g/l)	8.3	0.14	6.2
NaHCO ₃ (10 g/l)	8.45	0.17	6.3
NaHCO ₃ (10 g/l) + Na ₂ CO ₃ (1.02 g/l)	9.0	0.39	5.5
Na ₂ CO ₃ (0.5 g/l)	10.25	0.92	1.2
Na ₂ CO ₃ (2 g/l)	10.77	2.23	0.1
30 Na ₂ CO ₃ (10 g/l)	11.19	2.87	0.1
Na ₃ PO ₄ (1 g/l)	11.53	1.85	0.3
Na ₃ PO ₄ (10 g/l)	12.03	2.74	1.9
NaOH (3 g/l)	12.53	1.70	0.8

It can be seen that the level of fixation of TAHT was 35 greater and the tendency to fibrillation was less when the

- 25 -

pH of the scour bath was greater than 10, and that the best F.I. results were obtained at a pH in the range 10.5 to 11.5.

Example 9

5 Woven or knitted solvent-spun cellulose fabric as used in Example 1 was treated on a winch with a solution containing TAHT (various amounts), Detergyl (2 g/l), Na₂CO₃ (10 g/l) and Na₂SO₄ (5 g/l) for 1 hour at 95°C. A control sample was scoured using a solution of Detergyl (2 g/l) and
 10 Na₂CO₃ (2 g/l) for 1 hour at 95°C. The liquor to fabric ratio was 15:1. The samples were then dyed with Procion Red HE-7B in the manner described in Example 8 and subjected to a single wash and tumble-dry cycle. The following F.I. results were obtained:

15 TAHT g/l	Woven Fabric		Knitted Fabric	
	F.I. as dyed	F.I. after W/T	F.I. as dyed	F.I. after W/T
-	2.2	3.4	3.0	3.0
1	1.4	2.0	1.8	2.2
20 2	1.0	1.2	1.4	1.8
5	1.0	1.0	0.2	0.6

It can be seen that fibrillation tendency was significantly reduced even at the lowest concentrations of TAHT.

25

Example 10

Woven solvent-spun cellulose fabric as used in Example 1 was scoured using a solution of TAHT (20 g/l), Detergyl (2 g/l), Na₂CO₃ (2 g/l) and Na₂SO₄ (25 g/l) at 95°C for 1 hour. A control sample was scoured in the same way except
 30 that the TAHT was omitted. The fabric samples were then bleached by immersion in a solution of hydrogen peroxide (15 ml of 35% solution per litre), Prestogen PC (1 g/l) (a

- 26 -

bleach stabiliser available from BASF AG) (Prestogen is a Trade Mark), Trilon C (0.5 g/l) (Trilon is a Trade Mark of BASF AG) and NaOH (1 g/l) at 50°C, after which the temperature was raised to 85°C and maintained there for 60 5 minutes, following which the samples were rinsed. The samples were then dyed with Procion Brown H3R in the manner described in Example 6. The following results were obtained for F.I. after various numbers of wash and tumble-dry cycles:

10	W/T cycles					
	0	1	2	3	4	5
Control	4.5	4.5	4.7	5.1	6.5	4.9
Treated	0.5	0.0	0.0	0.3	0.4	0.0

It can be seen that the reduction in fibrillation tendency 15 obtained by treatment with TAHT was not removed by the bleaching treatment.

Example 11

Woven solvent-spun cellulose fabric as used in Example 1 was loaded into a dyeing machine containing a bath which 20 was an aqueous solution at 50°C containing an anionic or nonionic lubricant. The fabric was passed through the bath to wet it and TAHT (4 g/l) was then added to the bath followed by Na₂CO₃ (10 g/l) and Na₂SO₄ (5 g/l) to give pH 10.5-11.5. The temperature of the bath was raised to 95°C 25 while the fabric continued to be passed through the bath, and this temperature was maintained for 1 hour. These treatment conditions have been found to give good fixation and resistance to fibrillation. The target fixation level for the TAHT was more than 1%, preferably 1.2-1.5%, by 30 weight on fabric. The fabric was then soaped off and dried to provide a fabric with a low fibrillation tendency.

- 27 -

CLAIMS

1. A process for the manufacture of solvent-spun cellulose fibre with a reduced tendency to fibrillation wherein solvent-spun cellulose fibre is treated with a
5 chemical reagent containing two or more functional groups reactive with cellulose, characterised in that the fibre subjected to treatment has previously been dried and in that the chemical reagent contains as functional groups reactive
10 consisting of electrophilic carbon-carbon double bonds and precursors thereof and electrophilic three-membered heterocyclic rings and precursors thereof.

2. A process for the manufacture of solvent-spun cellulose fibre with a reduced tendency to fibrillation
15 wherein solvent-spun cellulose fibre is treated with a chemical reagent containing two or more functional groups reactive with cellulose, characterised in that the fibre subjected to treatment has previously been dried and in that the chemical reagent reacts with the cellulose with the
20 formation of at least two aliphatic ether groups.

3. A process according to claim 1 or claim 2, characterised in that the chemical reagent contains at least one acrylamido or acrylic ester group as a functional group reactive with cellulose.

25 4. A process according to claim 1 or claim 2, characterised in that the chemical reagent contains at least one vinyl sulphone group as a functional group reactive with cellulose.

5. A process according to any preceding claim,
30 characterised in that the chemical reagent contains two to six functional groups reactive with cellulose.

- 28 -

6. A process according to any preceding claim, characterised in that the chemical reagent contains at least one ring having attached thereto at least three functional groups reactive with cellulose .

5 7. A process according to claim 6, characterised in that the chemical reagent is triacryloylhexahydrotriazine.

8. A process according to claim 3, characterised in that the chemical reagent is N,N'-methylenebisacrylamide.

9. A process according to any preceding claim,
10 characterised in that the fibre is treated with an aqueous solution of the chemical reagent.

10. A process according to claim 9, characterised in that the aqueous solution is mildly alkaline.

11. A process according to any preceding claim,
15 characterised in that the fibre is treated so as to react with the fibre 0.2 to 5 percent by weight of the chemical reagent, based on the weight of fibre.

12. A process according to claim 11, characterised in that the fibre is treated so as to react with the fibre 1 to
20 2 percent by weight of the chemical reagent, based on the weight of fibre.

13. A process according to any preceding claim, characterised in that the fibre subjected to treatment is present in a woven fabric.

25 14. A process according to any one of claims 1 to 12, characterised in that the fibre subjected to treatment is present in a knitted fabric.

15. A process according to claim 14, characterised in that the knitted fabric is treated in rope form with the

- 29 -

chemical reagent.

16. A process according to any preceding claim, characterised in that the treated fibre is subsequently dyed.

5 17. A process according to any preceding claim, characterised in that the chemical reagent is substantially colourless.

18. A process according to any preceding claim, characterised in that the fibre is of substantially the same
10 colour before and after the treatment with the chemical reagent.

19. A process according to any preceding claim, characterised in that the fibre has been prepared by extrusion of a solution of cellulose in a tertiary amine N-
15 oxide into an aqueous bath, followed by washing and drying.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 93/02155

A. CLASSIFICATION OF SUBJECT MATTER
IPC 5 D01F2/00 D01F11/02 D06M13/224 D06M13/41 D06M13/358
D06P1/382 D06P1/642

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 5 D01F D06M D06P

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,Y	EP,A,0 538 977 (COURTAULDS PLC.) 28 April 1993 cited in the application see page 3, line 32 - line 49; claims ---	1,2,6,7, 9-19
Y	US,A,3 400 127 (GIULIANA C. TESORO) 3 September 1968 see column 6, line 13 - line 21; example VIII ---	1,2,6,7, 9-19
A	GB,A,936 399 (FARBENFABRIKEN BAYER AG) 11 September 1963 see page 1, line 32 - page 2, line 2; claims ---	1-19
A	GB,A,953 171 (FARBWERKE HOECHST AG.) 25 March 1964 see the whole document ---	1-3,5-19
	-/--	

Further documents are listed in the continuation of box C. Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search 1 February 1994	Date of mailing of the international search report 18.02.94
---	---

Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax (+31-70) 340-3016	Authorized officer Blas, V
---	--

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 93/02155

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US,A,3 574 522 (STANLEY P. ROLAND ET AL.) 13 April 1971 see claims ---	1-5,9-19
A	WO,A,92 07124 (COURTAULDS PLC.) 30 April 1992 see claims ---	1
A	WO,A,92 14871 (COURTAULDS PLC.) 3 September 1992 -----	

1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/GB 93/02155

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0538977	28-04-93	JP-A- 5117970	14-05-93

US-A-3400127		NONE	

GB-A-936399		CH-A- 384523	
		DE-B- 1123283	
		FR-A- 1263749	
		US-A- 3056695	

GB-A-953171		BE-A- 591132	
		DE-B- 1109135	
		FR-A- 1258556	
		NL-A- 251910	

US-A-3574522	13-04-71	NONE	

WO-A-9207124	30-04-92	EP-A- 0552270	28-07-93

WO-A-9214871	03-09-92	AU-A- 1241092	15-09-92
		EP-A- 0571460	01-12-93
