



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2711005 A1 2011/02/03

(21) **2 711 005**

(12) **DEMANDE DE BREVET CANADIEN
CANADIAN PATENT APPLICATION**

(13) **A1**

(22) Date de dépôt/Filing Date: 2010/07/29

(41) Mise à la disp. pub./Open to Public Insp.: 2011/02/03

(30) Priorité/Priority: 2009/08/03 (US12/534,682)

(51) Cl.Int./Int.Cl. *A61K 8/362* (2006.01),
A61K 8/19 (2006.01), *A61Q 11/00* (2006.01)

(71) Demandeur/Applicant:
MCNEIL-PPC, INC., US

(72) Inventeur/Inventor:
SHARMA, DEEPAK, US

(74) Agent: SMART & BIGGAR

(54) Titre : COMPOSES POUR LE TRAITEMENT DES DENTS SENSIBLES

(54) Title: TOOTH SENSITIVITY TREATMENT COMPOSITIONS

(57) **Abrégé/Abstract:**

A tooth sensitivity treatment composition is disclosed. The composition includes a compound of formula I $M^1-A-M^2-B-M^1$ (1) wherein: M^1 is a monovalent or divalent metal; M^2 is a polyvalent metal or metal oxide; and A and B are, independently, selected from the group consisting of $C_2 - C_6$ diacids, triacids, and tetraacids. Methods for treating tooth sensitivity are also disclosed.



51507-171

Abstract

A tooth sensitivity treatment composition is disclosed. The composition includes a compound of formula I

5



wherein: M^1 is a monovalent or divalent metal; M^2 is a polyvalent metal or metal oxide; and A and B are, independently, selected from the group consisting of $C_2 - C_6$ diacids, triacids, and tetraacids. Methods for treating tooth sensitivity are also disclosed.

10

51507-171

TOOTH SENSITIVITY TREATMENT COMPOSITIONS

Field of the Invention

5

The present invention relates to tooth sensitivity treatment compositions, which have an affinity for dentin and effectively occlude open dentinal tubules.

Background of the Invention

10

15

20

25

30

Many people suffer from sensitive teeth, and this condition is often referred as dentinal hypersensitivity, which is a common problem in adult population. It is defined as a transient pain arising from exposed dentin, typically in response to chemical, thermal, tactile or osmotic stimuli that cannot be explained by any other dental defect or pathology. Erosion of the outer surface (enamel) of the tooth and/or gum recession often results in exposure of dentinal tubules providing pathways between oral cavity and nerve fibers in the pulp. It has been shown in-vivo that a pressure gradient exists across dentin, which causes outward flow of fluid. This fluid flow is disturbed or increases in response to tactile, thermal (heat, or cold), and osmotic stimuli (high levels of sugar etc.), which is thought to result in a mechano-receptor response in the nerve fibers of the pulp, which is detected as pain. Nerve desensitizers and dentin tubule occluding agents have been used to treat teeth sensitivity. Special toothpastes, which contain potassium nitrate and/or bio-glass, amorphous calcium phosphate etc. are regularly used by consumers suffering from dentinal sensitivity. Another occluding agent that is also used to treat tooth sensitivity is potassium oxalate. However, none of these occluding agents are completely effective in mitigating the dentinal sensitivity, as effective occlusion on dentinal tubules is dependent on different variables. There is, therefore, a continuing need for tooth sensitivity treatment compositions, which have an improved affinity for dentin and effectively occlude dentinal tubules.

51507-171

Summary of the Invention

It has been discovered that the aforementioned objective can be achieved by selecting specific compounds which provide a protective barrier for teeth and/or effectively occlude exposed dentinal tubules and thereby decrease tooth sensitivity. In certain embodiments, the present invention provides an oral composition comprising:

- a) at least one compound of Formula I



wherein: M^1 and M^3 are, independently, a monovalent or divalent metal; M^2 is a polyvalent metal or metal oxide; and A and B are, independently, selected from the group consisting of $C_2 - C_6$ diacids, triacids, and tetraacids;

- b) optionally, a flavor;
c) optionally, a sweetener;
d) optionally, a pH buffer; and
e) at least one orally acceptable solvent,

wherein the oral composition has a pH of greater than (or at least) 2.0 (or about 2).

In other embodiments, the compositions of the present invention relate to an oral composition, comprising:

- a) at least one compound of Formula I



wherein: M^1 and M^3 are, independently, a monovalent or divalent metal; M^2 is a polyvalent metal or metal oxide; and A and B are, independently, selected from the group consisting of $C_2 - C_6$ diacids, triacids, and tetraacids; and

- b) at least one orally acceptable solvent

wherein the composition is substantially free of water.

In still other embodiments, the compositions of the present invention relate to oral compositions comprising:

51507-171

a) at least one compound of Formula I



wherein: M^1 and M^3 are, independently, a monovalent or divalent metal; M^2 is a polyvalent metal or metal oxide; and
 A and B are, independently, selected from the group
 consisting of $C_2 - C_6$ diacids, triacids, and tetraacids;

b) at least one additional desensitizing agent; and

c) at least one orally acceptable solvent.

In another embodiment, the compositions of the present invention
 relate to a method of treating sensitive teeth comprising the steps of applying
 to the sensitive teeth, for at least two consecutive applications, a
 composition comprising:

a) at least one compound of Formula I



wherein: M^1 and M^3 are, independently, a monovalent or divalent metal; M^2 is a polyvalent metal or metal oxide; and
 A and B are, independently, selected from the group
 consisting of $C_2 - C_6$ diacids, triacids, and tetraacids; and

b) at least one orally acceptable solvent

wherein the applications are spaced no more than (or less than) 12
 (or about 12) hours apart.

In still other embodiments, the compositions of the present invention
 relate to a method of occluding dentinal tubules of teeth comprising the
 steps of applying to the teeth, for at least two consecutive applications, a
 composition comprising:

a) at least one compound of Formula I



wherein: M^1 and M^3 are, independently, a monovalent or divalent metal; M^2 is a polyvalent metal or metal oxide; and

51507-171

A and B are, independently, selected from the group consisting of C₂ – C₆ diacids, triacids, and tetraacids; and
 b) contacting the teeth with the composition for at least (or greater than) 10 (or about 10) seconds

5 wherein the tubules are at least (or greater than) about 5% occluded.

In yet other embodiments, the compositions of the present invention relates to a method of occluding dentinal tubules of the teeth comprising the steps of applying to the teeth, for at least two consecutive applications, a
 10 composition comprising:

a) at least one compound of Formula I



wherein: M¹ and M³ are, independently, a monovalent or divalent metal; M² is a polyvalent metal or metal oxide; and A and B are, independently, selected from the group consisting
 15 of C₂ – C₆ diacids, triacids, and tetraacids; and

b) contacting the teeth with the composition in the presence of calcium for at least 20 seconds

wherein the compound forms a precipitate with the calcium on or in the vicinity of the teeth such that at least (or greater than) 30% (or about 30%)
 20 of the formed precipitate remains on the teeth after sonicating for 2 (or about 2) minutes.

In other embodiments, the compositions of the present invention relates to a method of depositing a precipitate on teeth and/or dentinal
 25 tubules of teeth comprising the steps of applying to the teeth, for at least two consecutive applications, a composition comprising:

a) at least one compound of Formula I



wherein: M¹ and M³ are, independently, a monovalent or divalent metal; M² is a polyvalent metal or metal oxide; and A
 30

51507-171

and B are, independently, selected from the group consisting of C₂ – C₆ diacids, triacids, and tetraacids; and

b) contacting the teeth with the composition in the presence of calcium for at least (or greater than) 20 (or about 20) seconds

wherein M² is present in the precipitate at a concentration of at least (or greater than) 5% (or about 5%) of the deposited precipitate.

Brief Description of the Figures

Figure 1 is a scanning electron microscope image of an etched dentin chip taken after 7 treatments with 0.5% potassium oxalate formulation and showing minimal oxalate precipitation on dentin chip surface and/or dentin tubule occlusion after treatment.

Figure 2 is a scanning electron microscope image of an etched dentin chip taken after 14 treatments with 0.5% potassium oxalate formulation and showing minimal oxalate precipitation on dentin chip surface and/or dentin tubule occlusion after treatment.

Figure 3 is a scanning electron microscope image of an etched dentin chip taken after 21 treatments with 0.5% potassium oxalate formulation and showing minimal oxalate precipitation on dentin chip surface and/or dentin tubule occlusion after treatment.

Figure 4 is a scanning electron microscope image of an etched dentin chip taken after 28 treatments with 0.5% potassium oxalate formulation and showing minimal oxalate precipitation on dentin chip surface and/or dentin tubule occlusion after treatment.

Figure 5 is a scanning electron microscope image of an etched dentin chip taken after 7 treatments with 0.5% potassium titanium oxide oxalate formulation and showing substantial titanium oxide oxalate precipitation on

51507-171

dentin chip surface and/or virtually complete dentin tubule occlusion after treatment.

Figure 6 is a scanning electron microscope image of an etched dentin chip taken after 14 treatments with 0.5% potassium titanium oxide oxalate formulation and showing substantial titanium oxide oxalate precipitation on dentin chip surface and/or virtually complete dentin tubule occlusion after treatment.

Figure 7 is a scanning electron microscope image of an etched dentin chip taken after 21 treatments with 0.5% potassium titanium oxide oxalate formulation and showing substantial titanium oxide oxalate precipitation on dentin chip surface and/or virtually complete dentin tubule occlusion after treatment.

Figure 8 is a scanning electron microscope image of an etched dentin chip taken after 28 treatments with 0.5% potassium titanium oxide oxalate formulation and showing substantial titanium oxide oxalate precipitation on dentin chip surface and/or virtually complete dentin tubule occlusion after treatment.

Figure 9 is a scanning electron microscope image of an etched dentin chip taken before treatment with a formulation having the same ingredients as that used to treat the dentin chips of **Figures 1** through **8**, but containing no potassium oxalate or potassium titanium oxide oxalate and showing no change in precipitation on dentin chip surface and/or dentin tubule occlusion prior to treatment and after treatment.

Figure 10 is a scanning electron microscope image of an etched dentin chip taken after 28 treatment with a formulation having the same ingredients as that used to treat the dentin chips of **Figures 1** through **8**, but containing no potassium oxalate or potassium titanium oxide oxalate and

51507-171

showing no change in precipitation on dentin chip surface and/or dentin tubule occlusion prior to treatment and after treatment.

Figure 11 is a scanning electron microscope image of an etched dentin chip having undergone 28 treatments with a formulation containing 0.5% potassium oxalate (Formulation B) and then sonicated for 2 minutes using a sonicator at normal pulse.

Figure 12 is a scanning electron microscope image of an etched dentin chip having undergone 28 treatments with a formulation containing 0.5% potassium titanium oxide oxalate (Formulation D) and then sonicated for 2 minutes using a sonicator at normal pulse. Comparison of these dentin chips images in **Figures 11** and **12** with their respective 28 day treatment image as depicted in **Figures 4** and **8** illustrate the increased stability of the precipitates generated by potassium titanium oxide oxalate formulation versus the potassium oxalate formulation.

Detailed Description of the Invention

The compositions of the present invention can comprise, consist of, or consist essentially of the essential elements and limitations of the invention described herein, as well any of the additional or optional ingredients, components, or limitations described herein.

All percentages, parts and ratios are based upon the total weight of the composition of the present invention, unless otherwise specified. All such weights as they pertain to the listed ingredients are based on the active level and, therefore, do not include carriers or by-products that may be included in commercially available materials, unless otherwise specified.

The term "safe and effective amount" as used herein means an amount of a compound or composition such as a topical or system active sufficient to significantly induce a positive benefit, for example, tooth desensitization, but low enough to avoid serious side effects, i.e., to provide

51507-171

a reasonable benefit to risk ratio, within the scope of sound judgment of the skilled artisan.

The term "occluded" or "occlusion" as used herein, means that the exposed openings of or into the dentin tubules are partially, substantially or completely obstructed.

The compositions of the present invention comprise at least one compound of Formula I



wherein: M^1 and M^3 are, independently, a monovalent or divalent metal; M^2 is a polyvalent metal or metal oxides thereof; and A and B are, independently, selected from the group consisting of $C_2 - C_6$ diacids, triacids, and tetraacids., optionally C_2-C_4 diacids or triacids, optionally C_2-C_3 diacids or triacids, or optionally, C_2 diacids .

Examples of suitable monovalent metals include, but are not limited to Na, K and Li, optionally, Na or K, or optionally, K.

Examples of suitable divalent metals, include, but are not limited to, Mg, Ca, Sr, Ba, and Zn, optionally, Mg, Ba, and Zn,, or optionally, Mg.

Examples of suitable polyvalent metals include, but are not limited to Ti, V, Cr, Mn, Fe, Co, Ni, Cu, Tc, Re, Os, Ir, Hg, Ce, Sn, Eu, Yb, Pa, and U, optionally, Ti, Sn, Mn, and Fe, or optionally Ti.

Examples of suitable metal oxides include, but are not limited to, the corresponding oxides of Ba, Ti, V, Cr, Mn, Fe, Co, Ni, Cu, Tc, Re, Os, Ir, Hg, Ce, Sm, Eu, Yb, Pa, and U, optionally, the corresponding oxides of Ba, Ti, Sr, Sn, Zr, Mn, and Fe, optionally, the corresponding oxides of Ba, Ti, Sr, Sn, Zr, or optionally , the corresponding oxide of Ti.

51507-171

In certain embodiments, M^1 and/or M^3 are, independently, selected from the group consisting of Na, K, and Li. Optionally, both M^1 and M^3 are K.

5 In certain embodiments, M^2 is selected from the group consisting of Ti, Sr, Sn, Mg, Ca, Mn, and Zr. Optionally, M^2 is selected from the group consisting of oxides of Ti, Sr, Sn, Mg, Ca, Mn, and Zr. In other embodiments, M^2 is selected from the group consisting of Ti or oxide of Ti.

10 Examples of suitable diacids include, but are not limited to, oxalic acid, succinic acid, methylsuccinic acid, diglycolic acid, glutaric (i.e. pentanedioic) acid, 3,5,5-trimethylpentanedioic acid, hexanedioic acid, 3, 5,5-trimethylhexanedioic acid, 2,4,4-trimethylhexanedioic acid, decanedioic acid, undecanedioic acid, dodecanedioic acid, 1,4-cyclohexanedicarboxylic acid,
15 cyclohexane-1,4-diacetic acid, maleic acid, citraconic acid, itaconic acid, fumaric acid, oxalic acid, terephthalic acid, phthalic acid, and isophthalic acid, hydroxysuccinic acid, malonic acid, adipic acid, sebacic acid, and tartaric acid, optionally, oxalic acid, succinic acid, or optionally, oxalic acid.

Examples of suitable triacids include, but are not limited to, citric acid.

20 Examples of suitable tetraacids include, but are not limited to, 1,1,2,2-ethanetetracarboxylic acid; 1,1,2,3-propanetetracarboxylic acid; 1,1,4,4-butanetetracarboxylic acid; 1,2,4, 5-benzenetricarboxylic acid and ethylenediaminetetraacetic acid, or optionally, 1,1,2,2-ethanetetracarboxylic acid.

25 In certain embodiments, the compound of Formula I is selected from the group consisting of potassium titanium oxide oxalate ("KTO") (also referred to as potassium titanium oxalate), potassium titanium oxide citrate, calcium titanium oxalate, and potassium calcium titanium oxalate, optionally, potassium titanium oxide oxalate ("KTO"), potassium titanium oxide citrate or
30 optionally, potassium titanium oxide oxalate ("KTO").

51507-171

The compositions of the present invention include, based upon the total weight of the composition, from 0.01% (or about 0.01%) to 10.0% (or about 10.0%), optionally, from 0.1% (or about 0.1%) to 7.0% (or about 7.0%), or optionally, from 1% (or about 1%) to 5.0% (or about 5.0%) of at least one compound of Formula I.

In certain embodiments, the compositions of the invention include an orally acceptable solvent. Orally acceptable solvents include, but are not limited to, water; ethanol; n-propanol; or polyhydric alcohols such as glycerin, sorbitol, and polyethylene glycol; and any mixtures thereof and may be present at concentrations of from about 0.1% to about 99.9%, optionally, from about 1% to about 90%, or optionally, from about 10% to about 75% of the orally acceptable solvent.

In certain other embodiments, the compositions of the present invention are substantially free of water. By "substantially free", as used herein means less than 5% (or about 5%), optionally, less than 3% (or about 3%), optionally, less than 1% (or about 1%), optionally, less than 0.5% (or about 0.5%), optionally zero (or anhydrous).

In certain embodiments, the compositions of the present invention have a pH of at least 2 (or about 2), optionally, from 2.5 (or about 2.5) to 7.0 (or about 7.0), optionally, from 3.5 (or about 3.5) to 6.0 (or about 6.0)., or optionally, from 3.2 (or about 3.2) to 4.5(or about 4.5).

In certain embodiments, the pH of the compositions of the present invention may be buffered using conventional acid /salt systems. Common buffer systems include phosphoric acid and sodium phosphate salts, or citric acid and sodium citrate. Suitable acid/acid salt buffer combinations for use in this invention include citric acid-sodium citrate, phosphoric acid-sodium phosphate, sodium monobasic phosphate, sodium dibasic phosphate, acetic acid-sodium acetate, succinic acid-sodium succinate, aconitic acid-sodium aconitate and benzoic acid-sodium benzoate in amounts up to about

51507-171

1% w/w, optionally from about 0.05% w/w to about 0.75% w/w of the composition, and or optionally from about 0.1% w/w to about 0.5% w/w of the composition.

5

Optional Components

10

15

In certain embodiments, the compositions of the present invention further include other tooth desensitizing agents. Examples of additional tooth desensitizing agents include, but are not limited to, potassium citrate, potassium chloride, potassium nitrate, citric acid, citric acid salts, strontium chloride, and mixtures thereof. Also, useful herein are the bioactive glass materials as described in US patents 5735942; 5891233; 6086374; 6244871; 6338751; and 6365132, and phosphopeptides as described in US patents 5015628; 5981475; 6448374; and 6780844.

20

In certain embodiments, the additional tooth desensitizing agent is potassium nitrate. In certain embodiments, the concentration of the additional tooth desensitizing agent is from 0.1% (or about 0.01%) to 10% (or about 10%), optionally, from 0.1% (or about 0.1%) to 8% (or about 8%), or optionally, from 1% (or about 1%) to 7% (or about 7%) by weight of the composition.

25

Fluoride ion sources are well known for use in oral care compositions as anticaries actives and may also be incorporated into the compositions of the present invention. Fluoride ions are contained in a number of oral care compositions for this purpose, particularly toothpastes. Patents disclosing such toothpastes include U.S. Patents 3538230; 3689637; 3711604; 3911104; 3935306; and 4040858.

30

Application of fluoride ions to dental enamel serves to protect teeth against decay. A wide variety of fluoride ion-yielding materials can be employed as sources of soluble fluoride in the instant compositions. Examples

51507-171

of suitable fluoride ion-yielding materials are found in Briner et al; U.S. Pat. No. 3,535,421; issued Oct. 20, 1970 and Widder et al; U. S. Pat. No. 3,678,154; issued July 18, 1972. In certain embodiments, fluoride ion sources for use herein include stannous fluoride, monofluorophosphate, sodium fluoride, potassium fluoride and ammonium fluoride. In other embodiments sodium fluoride is incorporated. In certain embodiments, the compositions of the present invention provide from about 50 ppm to 10,000 ppm, optionally from about 100 to 3000 ppm, of fluoride ions in the aqueous solutions that contact dental surfaces.

Also useful in the compositions of the present invention are phosphates. Phosphates include pyrophosphates, polyphosphates, polyphosphonates and mixtures thereof. Pyrophosphates are among the best known for use in dental care products. Pyrophosphate ions are delivered to the teeth derive from pyrophosphate salts. The pyrophosphate salts useful in the present compositions include the dialkali metal pyrophosphate salts, tetra-alkali metal pyrophosphate salts, and mixtures thereof. Disodium dihydrogen pyrophosphate ($\text{Na}_2\text{H}_2\text{P}_2\text{O}_7$), tetrasodium pyrophosphate ($\text{Na}_4\text{P}_2\text{O}_7$), and tetrapotassium pyrophosphate ($\text{K}_4\text{P}_2\text{O}_7$) in their unhydrated as well as hydrated forms are the preferred species. In certain embodiments, tetrasodium pyrophosphate salt is the pyrophosphate.

The pyrophosphate salts are described in more detail in Kirk & Othmer, Encyclopedia of Clinical Technology Third Edition, Volume 17, Wiley-Interscience Publishers (1982). Additional anticalculus agents include pyrophosphates or polyphosphates disclosed in U.S. Patent 4590066; polyacrylates and other polycarboxylates such as those disclosed in U.S. Patents 3429963; 4304766; and 4661341; polyepoxysuccinates such as those disclosed in U.S. Patent 4846650; ethylenediaminetetraacetic acid as disclosed in British Patent No. 490, 384 dated Feb. 15, 1937; nitrilotriacetic acid and related compounds as disclosed in U.S. Patent 3678154;

51507-171

polyphosphonates as disclosed in U.S. Patents 3737533; 3988443; and 4877 603. In certain embodiments, phosphates include potassium and sodium pyrophosphates; sodium tripolyphosphate; diphosphonates, such as ethane-1-hydroxy-1,1-diphosphonate, 1-azacycloheptane-1,1-diphosphonate, and linear alkyl diphosphonates; tricalcium phosphates, linear carboxylic acids; sodium zinc citrate and mixtures of any of the above phosphates. In certain embodiments, the phosphate is tricalcium phosphate plus sodium lauryl sulfate as described in US 20080187500 A1, published Aug. 7, 2008 to Karlinsey, Robert L.

When incorporated into the compositions of the present invention, the phosphates can be present at concentrations of from about 0.01% to about 10%, optionally, from about 0.1% to about 7%, and, optionally, from about 0.5% to about 5%.

In certain embodiments, the compositions of the present invention also include essential oils. Essential oils are volatile aromatic oils that are synthetic or are derived from plants by distillation, expression or extraction. Essential oils usually carry the odor or flavor of the plant from which they are obtained. If used in the dentifrice compositions of this invention, essential oils provide anti-gingivitis activity. Some of these essential oils also act as flavoring agents. The essential oils of this invention include, but are not limited to, thymol, menthol, methyl salicylate (wintergreen oil) and eucalyptol.

Thymol, also known by the chemical formula 5-methyl 2-(1-methylethyl) phenol, is obtained from the essential oil of *Thymus vulgaris* Labiatae and *Monarda punctata* Labiatae. Thymol is a white crystalline powder with an aromatic odor and taste. Thymol is soluble in organic solvents but only slightly soluble in deionized water.

Menthol is isolated principally from the oil of *Mentha arvensis*. In its commercial form, menthol is available as L-menthol crystals obtained from a process involving cooling of the oil. Fractional distillation of peppermint oil

51507-171

that usually contains from about 40% to about 65% menthol represents another important source of menthol. Synthetic sources of L-menthol are also available.

Eucalyptol is derived from the eucalyptus tree. Having a camphoraceous odor and cooling taste, this essential oil is often combined with other essential oils such as menthol in confection formulations to impart medicinal effect. Combinations of menthol and eucalyptol are widely used. Particularly preferred uses of the menthol-eucalyptol combination include, according to the present invention, dentifrices such as toothpastes or dental gels.

Methyl salicylate is the main ingredient in many essential oils, constituting about 99% of oil of wintergreen (*Gaultheria procumbens*) and sweet birch (*Betula lenta*). Methyl salicylate, which has a distinctive refreshing aroma, is used widely in mouthwashes, chewing gums and other oral and pharmaceutical preparations.

The amounts of essential oils that can be used in the compositions of the present invention are from 0.001 (or about 0.001) to 1% (or about 1%) thymol, 0.001 (or about 0.001) to 1% (or about 1%) methyl salicylate, 0.001 (or about 0.001) to 15% (or about 15%) menthol and 0.001 (or about 0.001) to 1% (or about 1%) eucalyptol, wherein said amounts are clinically effective in inhibiting gingivitis. Optionally, a composition according to the present invention contains about 0.064% thymol, about 0.060% methyl salicylate, about 0.042% menthol and about 0.092% eucalyptol, wherein said amounts are clinically effective in inhibiting gingivitis.

Alternatively or in addition to the essential oils, the compositions of the present invention can also include an antimicrobially effective amount of an antimicrobial agent selected from the group consisting of polyphenols (e.g. triclosan) zinc salts, stannous fluoride, chlorhexidine, hexetidine, sanguinarine, benzalkonium chloride, salicylanilide, domiphen bromide, cetylpyridinium chloride, tetradecylpyridinium chloride (TPC), N-tetradecyl-4-

51507-171

ethylpyridinium chloride (TDEPC), octenidine, delmopinol, octapinol, and other piperidine derivatives, nicin preparations, zinc/stannous ion agents, antibiotics such as augmentin, amoxicillin, tetracycline, doxycycline, minocycline, and metronidazole, and analogs and salts of the above, essential oils including eugenol, geraniol, carvacrol, citral, hinokitiol, catechol, hydrogen peroxide, metal salts of chlorite, or any combination(s) of all of the above.

Mixtures of any of the above mentioned agents may also be used.

The compositions of the invention may also contain a surfactant selected from anionic, nonionic, amphoteric, betaine, cationic, and mixtures thereof. Suitable anionic surfactants include alkyl sulfates, alkyl ether sulfates, sulfosuccinates, isethionates, acyl amides, alkyl ether carboxylates and alkyl phosphates, wherein the alkyl group has from about 6 carbon atoms to about 30 carbon atoms. Suitable cationic surfactants include cetyl pyridinium chloride. The total amount of surfactant(s) that are suitable for use in the composition of the present invention may range from, based upon the total weight of the total composition, from about 1% to about 50%, optionally, from about 5% to about 40% or, optionally, from about 8% to about 25%.

Types of nonionic surfactants that are suitable for use in this invention include the fatty alcohol acid or amide ethoxylates, monoglyceride ethoxylates, sorbitan ester ethoxylates and alkyl polyglycosides. These nonionic surfactants can be employed in composition of the present invention in an amount, based upon the total weight of the composition, from about 0.0% to about 30%, e.g. from about 0.1% to about 20% and from about 0.1% to about 15%.

Classes of amphoteric surfactants that are suitable for use in this invention include alkylimino-dipropionates, alkylamphoglycinates (mono or di), alkylamphopropionates (mono or di), alkylamphoacetates (mono or di), N-alkyl β -aminopropionic acids, alkylpolyamino carboxylates, and

51507-171

phosphorylated imidazolines. These amphoteric surfactants can be employed in composition of the present invention in an amount, based upon the total weight of the composition, from about 0.1% to about 20%, e.g. from about 0.1% to about 15% and from about 0.1% to about 10%.

5 Types of betaines that are suitable for use in this invention include alkyl betaines, alkylamido betaines, alkyl sultaines and alkylamido sultaines, wherein the alkyl group has from about 6 carbon atoms to about 30 carbon atoms, with about 10 to about 14 carbon atoms being preferred. These betaine surfactants can be employed in the composition of the present
10 invention in an amount, based upon the total weight of the cleansing composition, from about 0.1% to about 15%, e.g. from about 0.1% to about 10% and from about 0.1% to about 8%.

 Classes of cationic surfactants that are suitable for use in this invention include alkyl quaternaries (mono, di, or tri), benzyl quaternaries
15 (e.g. cetyl pyridinium chloride), ester quaternaries, ethoxylated quaternaries, alkyl amines, and mixtures thereof, wherein the alkyl group has from about 6 carbon atoms to about 30 carbon atoms, with about 8 to about 22 carbon atoms being preferred. These cationic surfactants can be employed in composition of the present invention in an amount, based upon the total
20 weight of the composition, from about 0.01% to about 20%, optionally from about 0.05% to about 15% and or optionally from about 0.1% to about 10%.

 The compositions of the present invention may also include one or more optional ingredients nonexclusively including a thickening agent, humectants, chelating agents and additives such as flavorants,
25 preservatives, and the like.

 Commercially available thickening agents, which are capable of imparting the appropriate viscosity to the compositions, are suitable for use in this invention. Examples of suitable thickening agents nonexclusively include: mono or diesters of 1) polyethylene glycol of formula: $\text{HO}-(\text{CH}_2\text{CH}_2\text{O})_z\text{H}$,

51507-171

wherein z is an integer from about 3 to about 200; and 2) fatty acids containing from about 16 to about 22 carbon atoms; fatty acid esters of ethoxylated polyols; ethoxylated derivatives of mono and diesters of fatty acids and glycerine; hydroxyalkyl cellulose; alkyl cellulose; hydroxyalkyl alkyl cellulose; and mixtures thereof. Preferred thickeners include polyethylene glycol ester, and more preferably PEG-150 distearate which is available from the Stepan Company of Northfield, Illinois or from Comiel, S.p.A. of Bologna, Italy under the tradename, "PEG 6000 DS".

In certain embodiments, thickening agents can be included in the compositions of the present invention at concentrations of from about 0.01% to about 10%, optionally, from about 0.1 to about 5%, or optionally, from about 0.2% to about 2.0%.

Commercially available humectants are suitable for use in the present invention for their humectant properties in addition to their use as a potential solvents as detailed above. The humectant may be present in an amount of from about 0 % to about 10 %, preferably from about 0.5 % to about 5 %, and more preferably from about 0.5 % to about 3 %, based on the overall weight of the composition. Examples of suitable humectants nonexclusively include: 1) water soluble liquid polyols selected from the group comprising glycerine, propylene glycol, hexylene glycol, butylene glycol, dipropylene glycol, and mixtures thereof; 2) polyalkylene glycol of the formula: $\text{HO}-(\text{R}''\text{O})_b\text{-H}$, wherein R'' is an alkylene group having from about 2 to about 3 carbon atoms and b is an integer of from about 2 to about 10; 3) polyethylene glycol ether of methyl glucose of formula $\text{CH}_3\text{-C}_6\text{H}_{10}\text{O}_5\text{-(OCH}_2\text{CH}_2)_c\text{-OH}$, wherein c is an integer from about 5 to about 25; 4) urea; and 5) mixtures thereof, with glycerine being the preferred humectant.

In certain embodiments, humectants can be incorporated into the compositions of the present invention at concentrations of from about 0.1% to about 40%, optionally, from about 1.0% to about 30%, or optionally, from about 5% to about 25%.

51507-171

In certain embodiments, chelating agents can be incorporated into the compositions of the present invention. Examples of suitable chelating agents include those which are capable of protecting and preserving the compositions of this invention. Optionally, in addition to its potential use as a tetraacid in the compound(s) of Formula I, ethylenediamine tetracetic acid ("EDTA") may be used as the chelating agent. In certain embodiments, the chelating agent is tetrasodium EDTA, available commercially from Dow Chemical Company of Midland, Michigan under the tradename, "Versene 100XL" and may be present in an amount, based upon the total weight of the composition, of from about 0 to about 0.5%, and optionally from about 0.05% to about 0.25%.

Suitable preservatives include, sodium benzoate, and polysorbate and are present in the composition in an amount, based upon the total weight of the composition, from about 0 to about 0.2 %, and preferably from about 0.05 % to about 0.10 %.

The compositions of the present invention may be in the form of mouthwashes, mouthrinses, dentifrices, pastes such as toothpastes, powders such as toothpowders, gels, tablets, lozenges, microcapsules, sprays, varnishes or strips (such as remineralization strips as disclosed in US patent publication 20070128130 to Kropt et al. published June 7, 2007 or, peroxide or non-peroxide tooth whitening strips as disclosed in US patent publication 20080003248 to Georgiades et al. published January 3, 2008 and US patent 6949240 to Sagel et al. issued Sept. 27, 2005), coatings for such strips and the like. As alluded to above, the compositions of the present invention can also be applied by conventional oral care devices, including toothbrushes, dental pics, dental floss, dental sprayers or misters and dental pens as described in US patent publication 20080044363 to Montgomery, published Feb. 21, 2008.

The compositions of the present invention can also be useful as a coating for or as an impregnant for impregnation into dental devices selected from the group consisting of toothbrushes (manual or mechanical), toothbrush bristles, dental floss, dental pics and the like. The compositions

51507-171

of the present invention can also be useful as coatings or impregnants for dental composite materials, dental fillings and the like.

Method of Using the Compositions of the Present Invention

The invention illustratively disclosed herein may be practiced in the absence of any component, ingredient, or step which is not specifically disclosed herein.

In certain embodiments, the compositions of the present invention are applied to sensitive teeth, for at least two consecutive applications, optionally, at least (or greater than) 7 (or about 7) consecutive applications, or optionally, 14 (or about 14) consecutive applications, or optionally, 21 (or about 21) consecutive applications, or optionally, 28 (or about 28) consecutive applications.

When applied to a sensitive tooth (or teeth), in certain embodiments, the composition is allowed to remain in contact with the sensitive teeth for at least (or greater than) 10 (or about 10) seconds, optionally 20 (or about 20) seconds, optionally 30 (or about 30) seconds, optionally 50 (or about 50) seconds, or optionally 60 (or about 60) seconds.

In certain embodiments, the time between consecutive applications should be no more than (or less than) 12 (or about 12) hours apart, optionally, 8 (or about 8) hours apart, optionally, 4 (or about 4) hours apart, optionally, 2 (or about 2) hours apart, or optionally, one (or about one) hour apart.

In certain embodiments, the compositions of the present invention are applied to the sensitive teeth such that the compounds of Formula I form precipitate deposits with available calcium on the teeth such that at least (or greater than) 5% (or about 5%) of the teeth's dentin tubules are occluded, optionally 25% (or about 25%) of the dentin tubules are occluded, optionally 40% (or about 40%) of the dentin tubules are occluded, optionally 60% (or about 60%) of the dentin tubules are occluded, optionally 75% (or about 75%) of the dentin tubules are occluded, optionally 85% (or about 85%) of

51507-171

the dentin tubules are occluded, or optionally 95% (or about 95%) of the dentin tubules are occluded.

In certain embodiments, the M^2 of Formula I is present in the precipitate deposit formed by the compound(s) of Formula I and calcium at a concentration of at least (or greater than) 5% (or about 5%), optionally 10% (or about 10%), optionally 20% (or about 20%), or optionally 35% (or about 35%).

Once formed on the teeth, the stability of precipitate deposit(s) comprising the compounds Formula I and calcium provide is such that at least (or greater than) 5% (or about 5%), optionally 30% (or about 30%), optionally 35% (or about 35%), optionally 50% (or about 50%), optionally 75% (or about 75%), or optionally 90% (or about 90%) remain on the teeth after sonication for 2 (or about 2) minutes using an ultra sonicator CD-4800 (Digital Professional Ultrasonic Cleaner [CD-4800], manufactured by Best And More Electronics [Shenzhen] Co., Ltd., China) at normal pulse of about 42 KHz. At this pulse, the sonicator generally provides a force greater than that typically used in sonic or manual tooth brushing. The phrase "precipitate deposit(s)", as used herein means the deposit formed on the teeth and/or which occludes the tubules of the teeth by precipitation of the compound(s) of Formula I with calcium present in the fluids of the oral cavity after application of compositions comprising the compound(s) of Formula I as disclosed in the present application. Formation of the precipitate deposit(s) with the compound(s) of Formula I may also be generated or facilitated by separately adding calcium to the oral cavity in the form of water-soluble calcium salts before or after addition of the compositions of the present invention comprising the compound(s) of Formula I. Examples of suitable water-soluble calcium salts include, but are not limited to calcium chloride, calcium nitrate, calcium bromide, and calcium dihydrogenphosphate and mixtures thereof. The amount of the water-soluble calcium salt should exceed, on a molar basis, the amount of the

51507-171

compound(s) of Formula I provided by the compositions of the present invention.

Several examples are set forth below to further illustrate the nature of the invention and the manner of carrying it out.

5

Examples

The compositions of the present invention as described in following examples illustrate specific embodiments of compositions of the present invention, but are not intended to be limiting thereof. Other modifications can be undertaken by the skilled artisan without departing from the spirit and scope of this invention.

10

Preparation of Mouthrinse Formulations

Liquid mouth rinse formulations were prepared and the dentin occluding efficacy of potassium titanium oxide oxalate (KTO) formulations was evaluated. The method of preparation is described as follows:

15

In a formulation vessel, water, KTO, benzoic acid, and poloxamer was added and mixed until dissolved. Once poloxamer was dissolved, the alcohol, n-propanol, sorbitol and water were added, followed by sodium benzoate and then mixed until dissolved. The pH was checked and determined to be about 4.2.

20

To the above formulation mixture, menthol, thymol, eucalyptol, methyl salicylate were added and mixed until homogenous. Once a homogenous solution is formed, sodium saccharin and FDC green #3 (1% solution, purity adjusted) were added. The formulation was mixed until homogeneous. The final pH of the formulation was 4.2.

25

The composition of the liquid mouthrinse formulations are described in Table 1.

51507-171

Table 1

Ingredient	A	B	C	D	E
	% wt	% wt	% wt	% wt	% wt
Alcohol USP	22.653	22.653	22.653	22.653	22.653
Menthol USP	0.032	0.032	0.032	0.032	0.032
Thymol NF	0.064	0.064	0.064	0.064	0.064
Methyl Salicylate NF	0.066	0.066	0.066	0.066	0.066
Eucalyptol USP	0.092	0.092	0.092	0.092	0.092
n-Propanol	0.500	0.500	0.500	0.500	0.500
Mint Flavor N & A	0.085	0.085	0.085	0.085	0.085
Poloxamer 407	0.250	0.250	0.250	0.250	0.250
Benzoic Acid, USP	0.120	0.120	0.120	0.120	0.120
Sodium Benzoate	0.035	0.035	0.035	0.035	0.035
Potassium oxalate (KO)	0.100	0.5	0.000	0.000	0.000
Potassium Titanium oxide Oxalate(KTO)	0.000	0.000	0.100	0.500	0.000
Saccharin Sodium USP	0.117	0.117	0.117	0.117	0.117
FD&C Green #3	0.001	0.001	0.001	0.001	0.001
Sorbitol Solution USP	20.000	20.000	20.000	20.000	20.000
Purified Water, USP	55.885	55.485	55.885	55.485	55.985
TOTAL	100.00 0	100.00 0	100.00 0	100.00 0	100.00 0
pH	4.2	4.2	4.2	4.2	4.2

Preparation of Dentin Samples and Artificial Saliva

5

Dentin occlusion efficacy of the KTO compounds and formulations of the present invention was demonstrated as follows:

10

Dentin chips (polished and unetched) were obtained from Dental product testing, Division of Thermametric technologies Inc., Indianapolis, Indiana, USA. The dentin chips were etched to completely remove the smear layer (or, debris layer caused by cutting the dentin or enamel) by soaking the dentin chips in 6% citric acid for up to 2 minutes followed by rinsing and sonication in deionized water.

15

Potassium oxalate (KO) was obtained from Fluka, St. Louis, MO, (lot#: 430462/1). Potassium titanium oxide oxalate (KTO) dihydrate was obtained from Sigma, St. Louis MO (lot# 51740).

51507-171

Artificial saliva was prepared using conventional equipment and protocols routinely used in laboratory protocols and having the composition as shown in Table 2:

5

Table 2

Ingredient	Concentration
Sodium Chloride	0.381 g/L
Calcium Chloride di-hydrate	0.213 g/L
Potassium dihydrogen phosphate	0.738 g/L
Potassium Chloride	1.114 g/L
Gastric Mucin	2.20 g/L

pH = 7.0

Comparison Testing and Analysis

10

All the etched dentin chip samples (10 in total) were randomized and divided into five treatment groups. Scanning electron microscopy (SEM) and surface chemical analysis using Electron dispersive spectroscopy (EDS) were performed to monitor tubule occlusion and surface deposition generated by the KTO formulations. The five treatment groups were as follows:

15

Group 1: Treated with formulation AGroup 2: Treated with formulation BGroup 3: Treated with formulation CGroup 4: Treated with formulation D

20

Group 5: Treated with formulation E (i.e., no KTO nor KO)

The treatment regimen for the Groups 1-5 consisted of the following:

1. Treating the chip samples in each group with 20 mls of respective treatment formulation, with shaking, for 30 seconds.
2. Rinsing the chip samples in each group with deionized H₂O for 1 minute.

25

51507-171

3. Immersing the chip samples in the artificial saliva composition between treatments, and no more than two treatments were carried per day.
4. Repeating steps 1-3 for a total 28 treatments.
5. Dentin specimens were analyzed by SEM and/or EDS after 7, 14, 21 and 28 treatments. Before analysis the chips were rinsed with deionized H₂O for 3 minutes and air dried for SEM analysis.

The data obtained from EDS analysis of the 2 chip samples per group (Chip 1 and Chip 2) is summarized in Tables 3 and 4 below.

Table 3

EDS after 7 Treatments						
<u>Formulation</u>		<u>S (%)</u>	<u>K (%)</u>	<u>P (%)</u>	<u>Ca (%)</u>	<u>Ti (%)</u>
A	Chip 1	39.0	5.4	12.5	43.1	X
	Chip 2	37.9	6.2	13.5	42.4	X
B	Chip 1	16.9	9.3	17.2	56.6	X
	Chip 2	17.7	9.7	18.0	54.6	X
C	Chip 1	5.7	12.0	21.7	34.6	26.0
	Chip 2	4.6	12.4	19.6	35.2	28.2
D	Chip 1	X	11.6	28.0	28.3	32.1
	Chip 2	X	12.5	25.7	33.3	28.5
E	Chip 1	48.2	X	13.0	38.8	X
	Chip 2	47.7	X	13.2	39.1	X

Table 4

EDS after 14 Treatments						
<u>Formulation</u>		<u>S (%)</u>	<u>K (%)</u>	<u>P (%)</u>	<u>Ca (%)</u>	<u>Ti (%)</u>
A	Chip 1	30.6	8.4	12.5	48.5	X
	Chip 2	29.5	9.0	11.3	50.2	X
B	Chip 1	6.8	13.5	16.0	60.5	X
	Chip 2	8.7	15.4	18.4	57.5	X
C	Chip 1	1.8	10.2	27.4	26.3	26.7
	Chip 2	2.1	11.7	29.4	25.8	28.4
D	Chip 1	X	18.7	22.1	26.4	32.8
	Chip 2	X	20.9	17.7	30.0	31.4
E	Chip 1	47.5	X	13.6	38.9	X
	Chip 2	48.1	X	12.7	39.2	X

51507-171

After 7 treatments, 0.5 % KTO (Formulation D) treated samples show the highest affinity for etched dentin surface as is evident from the reduction of the percent sulfur detected in the EDS reading (EDS spectra of etched dentin surface typically shows about 45-50% Sulfur). The percent sulfur detected is reduced as the sulfur on the dentin chip surface becomes covered or masked by the surface deposition generated by the KTO formulation treatments. While not completely absent, the percent sulfur detected is dramatically reduced in the 0.1% KTO (Formulation C) treated sample. After 14 treatments, the percent sulfur detected remained low in the 0.5% KTO (Formulation D) treated sample and more significantly reduced in the 0.1% KTO (formulation C) treated sample.

Scanning electron microscopy carried out on these samples suggests the initiation or formation of surface precipitation on the dentin surface for Formulation D samples, and the degree of tubule occlusion increases with number of treatments.

SEM analysis, image grading, and calculation of percent tubule occlusion was carried out to obtain a semi-quantitative comparison of dentin tubule occlusion efficacy of different formulations. The methods and calculations for analyzing SEM data, grading images and obtaining percent tubule occlusion were carried out in accordance with methods described in West NX, Addy, M, Hughes, J. (1998) J. Oral Rehabil, 25, 885 and confirm by the methods describes in Lee SY, Kwon HK, Kim BI (2008) J. Oral Rehabil, 35, 847. Based on the above described analysis of the SEM data, the percent tubule occlusion was determined for Formulations A- E at treatments 7, 14, 21 and 28 is summarized in Table 5.

51507-171

Table 5

Percentage tubule occlusion

<u>Formulation</u>	7 treatment	14 treatment	21 treatment	28 treatment
A	5%	15%	25%	40%
B	20%	35%	45%	60%
C	25%	35%	55%	75%
D	40%	65%	85%	>99%
E	0%	5%	5%	5%

A comparison analyzed data for pre- (prior to treatments) and post treatment scanning electron micrographs at different times in treatment cycle and different KTO concentrations (as illustrated in Table 5 and **Figures 1** through **4** (KO treatment), **5** through **8** (KTO treatment) and **9** and **10** (no oxalate treatment) clearly demonstrate increased surface precipitation leading to enhanced and effective increase in tubule occlusion.

Substantivity Determination for Formed Precipitate Deposits

The following was performed to determine the substantivity (or, ability of the precipitate to remain on the dental surface) of the KTO precipitate deposited on dentin chip samples during the treatment cycle. The dentin chips treated with Formulation B (0.5% KO) and Formulation D (0.5% KTO) for 28 treatments were sonicated for 2 minutes (about 2 minutes can also be used) using an ultra sonicator CD-4800 at normal pulse (about 42 KHz). Comparison of the images of the sonicated chips (**Figures 11** and **12**) with their respective 28 day treatment images as depicted in **Figures 4** and **8** demonstrate that the KTO generated precipitate deposits were more resistant to the sonication (about 92% of KTO generated precipitate remained on chip sample) than the KO generated precipitates (about 38% of KO generated precipitate remained on chip sample) indicating that the KTO generated precipitate deposits provide increased stability versus the KO generated precipitate deposits. Without being limited by theory, it is believed

51507-171

that this improved stability of the precipitate deposits generated by the compounds of Formula I, not only provide a greater degree of tooth desensitization, but longer lasting tooth desensitization as well.

5

Tables 6 and 7 provide Examples F-O illustrating additional mouthwash examples of compositions of the present invention. Examples F-O can be prepared in the manner outlined for Examples A-E above.

10

Table 6

	F	G	H	I	J
	% wt	% wt	% wt	% wt	% wt
Alcohol USP	22.653	22.653	22.653	22.653	22.653
Menthol USP	0.032	0.032	0.032	0.032	0.032
Thymol NF	0.064	0.064	0.064	0.064	0.064
Methyl Salicylate NF	0.066	0.066	0.066	0.066	0.066
Eucalyptol USP	0.092	0.092	0.092	0.092	0.092
n-Propanol	0.500	0.500	0.500	0.500	0.500
Mint Flavor N & A	0.085	0.085	0.085	0.085	0.085
Poloxamer 407	0.250	0.250	0.250	0.250	0.250
Benzoic Acid, USP	0.120	0.120	0.120	0.120	0.120
Sodium Benzoate	0.035	0.035	0.035	0.035	0.035
Potassium Titanium Oxide Citrate	0.100	0.5	-	-	-
Calcium Titanium Oxalate	-	-	0.100	0.500	-
Potassium Titanium Oxide Oxalate					2.00
Saccharin Sodium USP	0.117	0.117	0.117	0.117	0.117
FD&C Green #3	0.001	0.001	0.001	0.001	0.001
Sorbitol Solution USP	20.000	20.000	20.000	20.000	20.000
Purified Water, USP	55.885	55.485	55.885	55.485	53.485
TOTAL	100.00	100.00	100.00	100.00	100.000
pH	4.2	4.2	4.2	4.2	4.2

51507-171

Table 7

	K	L	M	N	O
	% wt	% wt	% wt	% wt	% wt
Alcohol USP	22.653	22.653	22.653	22.653	22.653
Menthol USP	0.032	0.032	0.032	0.032	0.032
Thymol NF	0.064	0.064	0.064	0.064	0.064
Methyl Salicylate NF	0.066	0.066	0.066	0.066	0.066
Eucalyptol USP	0.092	0.092	0.092	0.092	0.092
Mint Flavor N & A	0.085	0.085	0.085	0.085	0.085
Poloxamer 407	0.250	0.250	0.250	0.250	0.250
Benzoic Acid, USP	0.120	0.120	0.120	0.120	0.120
Sodium Benzoate	0.035	0.035	0.035	0.035	0.035
Potassium Titanium Oxide Oxalate	0.100	0.500	0.5	1.0	2.0
Potassium Nitrate	2.4	2.4	3.0	3.0	3.0
Saccharin Sodium USP	0.117	0.117	0.117	0.117	0.117
FD&C Green #3	0.001	0.001	0.001	0.001	0.001
Sorbitol Solution USP	20.000	20.000	20.000	20.000	20.000
Purified Water, USP	53.210	52.810	52.210	52.710	51.710
TOTAL	100.00	100.00	100.00	100.00	100.000
pH	4.2	4.2	4.2	4.2	4.2

Table 8 provides Examples P-S illustrating dentifrice examples of compositions of the present invention. Examples P-S can be prepared using conventional dentifrice mixing technology. Example S illustrates an anhydrous dentifrice embodiment of the present invention.

5

51507-171

Table 8

Ingredients	P (% w/w)	Q (% w/w)	R (% w/w)	S (% w/w)
Water	15.00	12.50	10.00	---
Glycerin 99.7%, USP	23.00	23.00	23.00	28.00
Sodium Carboxymethylcellulose	0.60	0.60	0.60	0.60
Sorbitol (70%)	24.96	24.96	24.96	29.96
Sodium Saccharin	0.20	0.20	0.20	0.20
Sucralose	0.80	0.80	0.80	0.80
Sodium Fluoride	0.24	0.24	0.24	0.24
Hydrated Silica	20.00	20.00	20.00	20.00
Potassium Nitrate	0.00	5.00	5.00	5.00
potassium titanium oxalate (KTO)	5.00	2.50	5.00	5.00
Synthetic Amorphous Silica	6.50	6.50	6.50	6.50
Sodium Lauroyl Sarcosinate	1.00	1.00	1.00	1.00
Lauryl Glucoside	1.00	1.00	1.00	1.00
Cocamidopropyl betaine	0.50	0.50	0.50	0.50
Flavor	1.20	1.20	1.20	1.20
Total	100.00	100.00	100.00	100.00

51507-171

CLAIMS:

1. A use of a composition for treating sensitive teeth, the composition comprising:

a) at least one compound of Formula I



wherein: M^1 and M^3 are, independently, a monovalent or divalent metal; M^2 is a polyvalent metal or metal oxide; and A and B are, independently, selected from the group consisting of $C_2 - C_6$ diacids, triacids, and tetraacids; and

b) at least one orally acceptable solvent

wherein the composition is used for at least two consecutive applications at an interval of no more than 12 hours apart.

2. The use according to claim 1, wherein the composition is used for at least about 7 consecutive applications.

3. The use according to claim 1, wherein the composition is in contact with the teeth for at least about 10 seconds during each application.

4. The use according to claim 3, wherein the composition is in contact with the teeth for at least about 30 seconds during each application.

5. The use according to claim 1, wherein the compound of Formula I is selected from the group consisting of potassium titanium oxide oxalate and potassium titanium oxide citrate and mixtures thereof.

6. A use of a composition for occluding dentinal tubules of teeth, the composition comprising:

51507-171

at least one compound of Formula I



wherein: M^1 and M^3 are, independently, a monovalent or divalent metal; M^2 is a polyvalent metal or metal oxide; and A and B are, independently, selected from the group consisting of $C_2 - C_6$ diacids, triacids, and tetraacids; and

wherein the composition is used for at least two consecutive applications and the composition is in contact with the teeth for at least 20 seconds such that the tubules are at least about 5% occluded.

7. The use according to claim 6, wherein the tubules are at least 25% occluded.

8. A use of a composition for occluding dentinal tubules of the teeth, the composition comprising:

at least one compound of Formula I



wherein: M^1 and M^3 are, independently, a monovalent or divalent metal; M^2 is a polyvalent metal or metal oxide; and A and B are, independently, selected from the group consisting of $C_2 - C_6$ diacids, triacids, and tetraacids; and

wherein the composition is used for at least two consecutive applications and the composition is in contact with the teeth in the presence of calcium for at least 10 seconds to allow the compound to form a precipitate with the calcium on the teeth such that at least about 30% of the formed precipitate remains on the teeth after sonication of the teeth for 2 minutes using ultra sonicator CD-4800 at normal pulse.

51507-171

9 The use of claim 8, wherein the compound forms a precipitate with the calcium on the teeth such that at least about 25% of the formed precipitate remains on the teeth after sonication.

5

10. The use of claim 9, wherein the compound forms a precipitate with the calcium on the teeth such that at least about 50% of the formed precipitate remains on the teeth after sonicating.

10

11. A use of a composition for depositing a precipitate on teeth or dentinal tubules of teeth, the composition comprising:

a) at least one compound of Formula I



15

wherein: M^1 and M^3 are, independently, a monovalent or divalent metal; M^2 is a polyvalent metal or metal oxide; and A and B are, independently, selected from the group consisting of $C_2 - C_6$ diacids, triacids, and tetraacids; and

20

wherein the composition is used for at least two consecutive applications and the composition is in contact with the teeth in the presence of calcium for at least 10 seconds to form a precipitate in which M^2 is present in the precipitate at a concentration of at least about 5%.

Application number / numéro de demande: 2711005

Figures: 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12,

Pages: _____

Unscannable items
received with this application
(Request original documents in File Prep. Section on the 10th floor)

Documents reçu avec cette demande ne pouvant être balayés
(Commander les documents originaux dans la section de préparation des dossiers au
10^{ème} étage)