PCT WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 5 :		(11) International Publication Number:
B05D 1/04, H01B 1/20	A1	WO 94/07612
		(43) International Publication Date: 14 April 1994 (14.04.94)

(21) International Application Number: PCT/US93/08470

(22) International Filing Date: 9 September 1993 (09.09.93)

(30) Priority data:
07/954,628 30 September 1992 (30.09.92) US

(71) Applicant: THE DOW CHEMICAL COMPANY [US/US]; 2030 Dow Center, Abbott Road, Midland, MI 48640 (US).

(72) Inventors: CARSWELL, Robert ; 306 Narcissus, Lake Jackson, TX 77566 (US). CORNELL, Martin, C. ; 240 Petunia Street, Lake Jackson, TX 77566 (US). GROSETH, Cynthia, K. ; Route 6, P.O. Box 6537 A, Brazoria, TX 77422 (US). PORTER, James, R. ; 103 Spruce, Lake Jackson, TX 77566 (US). PRIESTER, Ralph, D., Jr. ; 428 Huckleberry, Lake Jackson, TX 77566 (US). TABOR, Ricky, L. ; 420 Garland Drive, Apartment 1408, Lake Jackson, TX 77566 (US). ZAWISZA, Melissa, J. ; 2562 Pine Oak Court, Midland, MI 48640 (US).

(74) Agent: TYLER, Gene, L.; The Dow Chemical Company, Patent Department, B-1211, 2301 Brazosport Blvd., Freeport, TX 77541 (US).

(81) Designated States: BR, CA, JP, KR, RU, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

Published
With international search report.

(54) Title: ELECTROSTATICALLY PAINTED POLYMERS AND A PROCESS FOR MAKING SAME

(57) Abstract

Polyurethane/polyurea polymers can be electrostatically painted without first being coated with a conductive primer. Disclosed is an improvement in a process for electrostatically painting polyurethane/polyurea polymers, the improvement being to prepare the polymer from a formulation including a non-volatile metal salt conductivity inducing material. The polymers painted by the process of the present invention can have physical properties and aesthetic properties substantially similar to those of otherwise identical polymers prepared without the non-volatile metal salt conductivity inducing materials of the present invention. The increased conductivity of the polymers can allow them to be charged with sufficient charge density to permit efficient paint transfer to the polymer surface. Also disclosed is a composition of at least two layers, one layer being an outer layer of electrostatically applied paint, and the other an inner layer of polyurethane/polyurea polymer.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	**FR**	France	**MR**	Mauritania
AU	Australia	**GA**	Gabon	**MW**	Malawi
BB	Barbados	**GB**	United Kingdom	**NE**	Niger
BE	Belgium	**GN**	Guinea	**NL**	Netherlands
BF	Burkina Faso	**GR**	Greece	**NO**	Norway
BG	Bulgaria	**HU**	Hungary	**NZ**	New Zealand
BJ	Benin	**IE**	Ireland	**PL**	Poland
BR	Brazil	**IT**	Italy	**PT**	Portugal
BY	Belarus	**JP**	Japan	**RO**	Romania
CA	Canada	**KP**	Democratic People's Republic of Korea	**RU**	Russian Federation
CF	Central African Republic			**SD**	Sudan
CG	Congo	**KR**	Republic of Korea	**SE**	Sweden
CH	Switzerland	**KZ**	Kazakhstan	**SI**	Slovenia
CI	Côte d'Ivoire	**LI**	Liechtenstein	**SK**	Slovak Republic
CM	Cameroon	**LK**	Sri Lanka	**SN**	Senegal
CN	China	**LU**	Luxembourg	**TD**	Chad
CS	Czechoslovakia	**LV**	Latvia	**TG**	Togo
CZ	Czech Republic	**MC**	Monaco	**UA**	Ukraine
DE	Germany	**MG**	Madagascar	**US**	United States of America
DK	Denmark	**ML**	Mali	**UZ**	Uzbekistan
ES	Spain	**MN**	Mongolia	**VN**	Viet Nam
FI	Finland				

ELECTROSTATICALLY PAINTED POLYMERS AND A PROCESS FOR MAKING SAME

This invention relates to a process for electrostatically painting polymers. This invention particularly relates to electrostatically painting polymers having urethane or urea groups.

It is well known that most painting processes are unlikely to be 100 percent efficient. For example, when paint is applied to an object as a spray, some fraction of the paint directed at the object may not be deposited on the object. In even more inefficient circumstances, the paint and the object can acquire a static charge of the same polarity resulting in the paint being partially repelled from the object. Another painting inefficiency commonly observed is that the paint layer on a painted object can be of inconsistent thickness. Yet another painting inefficiency commonly observed, particularly in spray painting objects having complex shapes, is that paint can tend to travel from a spraying apparatus to the object to be painted in a relatively straight line and may not cover surfaces not directly accessible to the spraying apparatus.

In painting applications requiring a very high quality paint finish, such as in the painting of automobile body parts, it is generally desirable to completely and evenly coat an object to be painted with a minimum expenditure of paint. This is desirable for several reasons. First, paint for such applications is often very expensive. Therefore, reducing paint consumption offers the immediate benefit of reduced paint cost. Second, paint which is not deposited upon the object to be painted can be lost to the environment and this loss can be environmentally undesirable. Therefore, reducing the quantity of paint lost to the environment in a painting process reduces the costs of disposing of the lost paint solids and reduces emissions of paint solvents. Third, while the layer of paint being slightly too thick on an object can sometimes be tolerated, the paint layer being too thin more often cannot. Besides improving the appearance of an object, modern paints often play a vital role in protecting a painted object from its environment. For example, paint can protect a metal object from corrosion or protect a plastic object from degradation by ultraviolet radiation. Therefore, failures of painted objects due to areas of too thin paint on the objects can be avoided by applying paint to objects wherein the layer of paint is of a consistent and sufficient thickness.

In order to minimize problems with inefficient painting, it is common practice in painting some materials to apply paint electrostatically. In electrostatic painting, a static electric potential is generated between paint and an object to be painted causing the paint to be attracted to the object. As a result of the electrostatic attraction, less paint can be lost to the environment and the paint can be more evenly applied to the object without the entire surface being directly accessible to the paint spraying apparatus.

But electrostatically painting objects is not always trouble free. In order to electrostatically paint an object, an electric charge potential must be generated between the object to be painted and a paint to be applied to the object. If an object is either not conductive or of very low conductivity, it cannot be efficiently electrostatically charged and cannot, therefore, be efficiently electrostatically painted.

One means of electrostatically painting polymers is to first make them more conductive by preparing the polymers from formulations including conductive fillers. European Patent Application 0 363 103 to Suzuki, et al., discloses preparing a thermoplastic polymer having 2 to 50 percent by weight of a fibrous conductive filler such as carbon fibers, metallic fibers, metalized glass fibers, metal coated carbon fibers and conductive potassium titanate whiskers. The polymer is etched and then electrostatically painted. However, adding such large amounts of fibrous fillers to a polymer can adversely affect both the polymer's physical properties and paint finish. A separate etching step can also be undesirable.

JP II 2-180960 assigned to Kanto Auto Works discloses preparing polyurethane substrates having improved conductivity. The polyurethanes of this reference are prepared with ammonium salts such as n-alkyldimethyl ammonium sulphates. One problem with such additives are that they promote conductivity only when humidified. This could be a problem in a painting application located in a region wherein the ambient humidity is not constant. Alternatively, deliberately humidifying articles prior to electrostatically painting them could be time consuming and expensive.

Another means of electrostatically painting polymers is to first make them more conductive by applying thereto conductive agents called "prepcoats". These prepcoats are conductive agents which adhere to

the surface of the polymer. Such agents can include materials such as quaternary amines. One problem with such compounds is that they are often hydrophilic. In reaction injection molding (RIM) polyurethanes, the adsorbed water can cause blemishes on the surfaces of the polymer. Hydrophilic coatings can aggravate the tendency of objects to adsorb water prior to painting, thus promoting the formation of blemishes and thereby be undesirable in applications requiring high quality finishes.

Yet another solution to the problem of electrostatically painting plastics is to first coat a plastic object with a conductive coating, and then to electrostatically paint the coated object. For example, U.S. Patent 5,071,593 to Takahashi, et. al., discloses coating problematic plastics such as polyacetal and polyesters with a conductive agent prior to electrostatic painting. However, coating an object with a conductive agent can be inefficient. It requires a capital expenditure for additional painting equipment, additional processing time to apply the conductive agent, additional processing time to allow the conductive agent to cure and expenditures for the cost of the conductive agent.

It is known in the art that polymers, particularly reaction injection molded polyurethane/polyurea polymers, are useful materials for preparing automobile parts such as, for example, fascia and interior and exterior panels. In order to paint articles prepared from such polymers and produce a high quality paint finish, as is required in modern automobile manufacturing practices, it is known to electrostatically paint these articles after first applying a conductive primer thereto. Known processes for electrostatically painting polymer articles include at least the steps of: (1) preparing an object to be painted from a polyurethane/polyurea polymer formulation; (2) coating the object with a conductive agent (or conductive primer); (3) applying an electric charge of a first polarity to a paint; (4) applying an electric charge of second and opposite polarity to the object (or merely charging either the paint or the article relative to ground while leaving the other neutral to ground); and (5) discharging the paint from a painting apparatus onto the object.

It would be desirable in the art to efficiently electrostatically paint polymers without having to pretreat the polymer by priming or prep-coating the polymer with a conductive material. It would also be desirable in the art to more efficiently

electrostatically paint a polymer which has been primed or prepcoated with a conductive substance. It would be desirable in the art to prepare a polymer with sufficient native conductivity to efficiently electrostatically paint the polymer. It would be desirable in the art that the polymer to be painted not require special treatment such as humidification. And it would also be desirable in the art that the painted polymer have a sufficiently high quality painted surface and sufficiently strong physical properties such that the polymer could be used in very demanding applications such as the manufacture of automobiles. Finally, it would be desirable in the art if objects of dissimilar composition, for example, metal and plastic, can be painted as a unit rather than painted separately and then joined together.

In one aspect, the present invention is a process for electrostatically painting cured urea and/or urethane group containing polymers comprising the steps of: (A) preparing a cured polymer from a polymer formulation including (1) materials which include or form urea groups, urethane groups or mixtures thereof, and (2) a non-volatile metal salt conductivity inducing material, and (B) electrostatically painting the polymer, wherein (a) the polymer can be efficiently electrostatically painted, and (b) the polymer would not be conductive but for the inclusion of the non-volatile metal salt conductivity inducing materials in the polymer.

Another aspect of the present invention is in a process for electrostatically painting a cured urea and/or urethane group containing polymer wherein the polymer is formed into a shaped article, coated with a conductive preparatory substance and then electrostatically painted, the improvement comprising preparing the polymer from a polymer formulation including (1) materials which include or form urea groups, urethane groups or mixtures thereof, and (2) a non-volatile metal salt conductivity inducing material.

Still another aspect of the present invention is an electrostatically painted object comprising at least two layers, a first layer being a layer of polymer prepared from a polymer formulation including (1) materials which include or form urea groups, urethane groups or mixtures thereof, and (2) a non-volatile metal salt conductivity inducing material, and a second layer, the second layer being a layer of electrostatically applied paint, wherein (a) the polymer can be efficiently electrostatically painted, and (b) the polymer would not be conductive but for the inclusion of the non-volatile metal salt conductivity inducing materials in the polymer.

The present invention is an improvement to known processes for electrostatically painting polymers. This improvement includes preparing an object to be painted from a from a polymer formulation including (1) materials which include or form urea and/or urethane groups and (2) a non-volatile metal salt conductivity inducing material. The resultant polymers can be electrostatically painted without the use of a conductive primer or other preparatory coating.

In the process of the present invention, a cured polymer is painted. For the purposes of the present invention, a cured polymer is one wherein the reaction to produce the polymer is substantially complete and the polymer is in a solid and preferably fixed shape. Even more preferably, the polymer is in a shape appropriate for painting. For example, the polymer can be in the shape of an automobile body panel, side cladding or fascia.

The conductivity inducing materials of the present invention are non-volatile metal salts. As a salt, the conductivity inducing materials of the present invention will have both a cation and an anion. The cation of the salts can be a cation of any metal which forms an ionizable salt with one or more anions, including Li, Be, Na, Mg, Al, K, Ca, Ga, Ge, Cu, Zn, Sc, Ti, V, Cr, Mn, Fe, Co, Ni, Rb, Sr, In, Sn, Sb, Y, Zr, Nb, Mo, Tc, Ru, Rh, Pd, Ag, Cd, Cs, Ba, Tl, Pb, Bi, Po, Hf, Ta, W, Re, Os, Ir, Pt, Au, Hg, Fr, Ra and the Lanthanide series of the Periodic Table of the Elements. Preferably, the cation is a cation of an alkali metal (Li, Na, K, Rb, Cs, Fr), an alkaline earth metal (Ca, Ba, Sr, Ra), Co, Ni, Fe, Cu, Cd, Zn, Sn, Al or Ag; more preferably the cation is a cation of an alkaline earth or alkali metal; even more preferably the cation is a monovalent cation, especially an alkali metal cation; and most preferably the cation is a cation of Li, Na, K or mixtures thereof. The non-volatile metal salt cations of the present invention can be selected from the group consisting of cations of Li, Na, K and mixtures thereof.

The non-volatile metal salt conductivity inducing materials of the present invention are salts of certain anions with the cations described above. One group of preferred non-volatile metal salts are fluoroalkyl sulfonic acid salts. The fluoroalkyl sulfonic acid anion (fluoroalkyl sulfonate) is suitably any fluoroalkyl sulfonic acid anion compatible with a specific composition in which it is used. Advantageously, preferred fluoroalkyl sulfonates have from one to twenty carbon atoms and are either straight chained, branched or cyclic. Fluoroalkyl sulfonates are sulfonate anions having an alkyl

group having fluorine substitution, that is, fluorine atoms bonded to the carbon atoms of the alkyl groups. The alkyl groups, optionally, also have hydrogen atoms and/or other halogen atoms bonded to the carbon atoms. Preferably, at least 25 percent, more preferably 75 percent, (by number) of the atoms other than carbon which are bonded to carbon atoms of the fluoroalkyl groups are halogen, preferably fluorine. More preferably, the fluoroalkyl groups are perhaloalkyl groups, that is, alkyl groups having only halogen substitution. Suitable halogens include fluorine, chlorine, bromine and iodine, preferably fluorine and chlorine. Suitable perhaloalkyl sulfonic acid anions include, for instance, $C_2H_2F_3SO_3^-$(tresylate), $C_2HF_4SO_3^-$, $C_2HClF_3SO_3^-$, $C_3H_2F_5SO_3^-$, $C_4H_2F_7SO_3^-$, $C_5H_2F_9SO_3^-$, $C_7ClF_{14}SO_3^-$, $C_8Cl_2H_2F_{13}SO_3^-$, $C_{20}ClHF_{39}SO_3^-$.

The fluoroalkyl groups are most preferably perfluoroalkyl groups. Exemplary perfluoroalkyl sulfonic acid anions include, for example $CF_3SO_3^-$(triflate), $C_2F_5SO_3^-$, $C_3F_7SO_3^-$, $C_4F_9SO_3^-$(nonaflate), $C_5F_{11}SO_3^-$, $C_6F_{13}SO_3^-$, $C_7F_{15}SO_3^-$, $C_8F_{17}SO_3^-$, $C_9F_{19}SO_3^-$, $C_{20}F_{41}SO_3^-$, isomers thereof and mixtures thereof. The salts of perfluoroalkyl sulfonates preferably have from 1 to 20, more preferably from 1 to 10, carbon atoms for reasons of availability and compatibility with polymers.

Other non-volatile metal salts can be used as conductivity inducing materials to prepare the formulations of the present invention also. The anion of such salts is recognizable by those skilled in the art by such characteristics as pi bonding, electron withdrawing groups such as halogen atoms and the possibility of resonance structures. The anion is preferably a relatively large, multiatomic anion having substituents like phenyl groups, sulfur atoms, and phosphorus atoms that can accept and delocalize an electron charge; more preferably the anion has more than one, more preferably at least 4, most preferably at least 5, non-metallic atoms.

Non-metallic atoms are generally considered to be selected from the group consisting of boron, carbon, silicon, phosphorus, arsenic, oxygen, sulfur, selenium, tellurium, fluorine, chlorine, bromine, iodine and astatine. Preferred non-metallic atoms are boron, phosphorus, sulfur, fluorine and carbon in aromatic groups; sulfur and carbon in aromatic groups are more preferred. The anion is preferably monovalent. The anion is more preferably the conjugate base of an inorganic acid having one or more delocalizable electrons, for example, a fluoroalkyl sulfonate or a tetraorganoboron ion. Such anions include, for example, NO_3^-, SCN^-, SO_4^{2-}, HSO_4^-, SO_3^{2-}, PX_6^-, HSO_3^-, $CNSO_3^-$, XSO_3^- wherein X is a halogen, $SXSO_3^-$ wherein X is a hydrogen or

an anion, ClO_4^-, PO_4^{3-}, $H_2PO_4^-$, HPO_4^{2-}, PO_3^{3-}, HPO_3^{2-}, $H_2PO_3^-$, particularly tetraalkyl and tetraarylboron ions and non-alkyl or non-aryl substituted sulfonic ions.

For the purposes of the present invention, the term non-volatile metal salt is further defined to exclude those salts which are incompatible with or undesirable in formulations for polymers having urethane and/or urea groups. For example, the anion of a non-volatile metal salt of the present invention is not an SCN^- anion because the salts of these anions can cause handling problems due to viscosity growth in polyurea formulations. SCN^- anions are also known to be water extractable in some polyurethane formulations. This property can cause handling problems in some painting applications. In contrast, non-volatile metal salts having good compatibility with formulations for polymers having urethane and/or urea groups are included and are preferred. For example, tetraphenylboron and hexfluorophosphate anions are particularly preferred as conductivity inducing materials for the present invention because of their good compatibility and handling properties. Mixtures of the non-volatile metal salts of the present invention can also be used to practice the present invention. Most preferably, the non-volatile metal salts of the present invention are salts wherein the non-volatile metal salt anion is selected from the group consisting of a perfluoroalkyl sulfonate, a tetraphenylboron anion, a hexafluorophosphate anion, or mixtures thereof.

The amount of conductivity inducing material which will be included in the polyurethane/polyurea formulations of the present invention will vary with the polymer. In the practice of the present invention, sufficient conductivity enhancing material is included in the formulation to render the material sufficiently conductive to allow efficient electrostatic painting. A polymer which is comparatively nonconductive can require more conductivity inducing material than a polymer which is comparatively more conductive. However, generally, the amount of conductivity inducing material added to a polymer formulation useful for preparing polyurethane/polyurea polymers to be electrostatically painted is preferably from 0.02 percent to 1.5 percent, more preferably from 0.05 percent to 1.0 percent and even more preferably from 0.10 to 0.75 percent.

The non-volatile metal salt conductivity inducing materials of the present invention are preferably those which, when included in a polymer formulation, result in a polymer which has physical

properties substantially similar to those of otherwise identical polymers prepared without the non-volatile metal salt conductivity inducing materials. The physical properties relevant to this are those properties which determine if the polymer is useful in the application for which it is intended. For example, one such property is aesthetic appearance. If a non-volatile metal salt produces an undesirable appearance in a polymer at the minimum concentration necessary to efficiently paint the polymer, it is not a preferred conductivity inducing material of the present invention. Other physical properties often useful in determining if a polymer is useful in applications wherein electrostatic painting is often done include: flex modulus, tear strength and tensile strength. For the purpose of the present invention, two polymers have substantially similar physical properties if the values for those properties are within 15 percent, preferably within 12 percent, and most preferably within 10 percent of each other. In some cases, the non-volatile metal salts of the present invention can interact with the polymers they are incorporated into to actually improve some polymer physical properties.

The polymers of the present invention can be electrostatically painted with the same efficiency as a steel control painted under similar conditions. The efficiency of the painting process is determined by measuring the amount of paint deposited onto the object during the electrostatic painting process. For the purposes of the present invention, the term "efficiently electrostatically painted" is defined as the condition wherein the same thickness of paint is deposited upon a polymer object as is deposited upon a steel object when electrostatically painted under the same or substantially similar conditions.

The process of the present invention can be used with polymers that would not be conductive but for the inclusion of the non-volatile metal salt conductivity inducing materials of the present invention. For the purposes of the present invention, the term "conductive" is defined as having sufficient electrical conductivity to be efficiently electrostatically painted. The term "efficiently electrostatically painted" is used as defined in the paragraph immediately above.

The polymers of the present invention have urea groups, urethane groups and mixtures thereof. That is the polymers can be prepared from materials which include or react to form only

polyurethane or polyurea groups, or the polymers of the present invention can be prepared from materials which include or react to form both polyurethane and polyurea groups. Other polymer linkages can be formed in the practice of the present invention too. For example, a polymer having polyurethane, polyurea and isocyanurate groups can be prepared.

The polymers of the present invention can also be polymer blends and polymer interpenetrating network polymers. For example, a polyurethane of the present invention can be blended with another polymer such as, for example, an acrylonitrile-butadiene-styrene polymer and then be electrostatically painted. Other blendable polymers useful with the present invention include but are not limited to nylon, polyethyl terephthalate and polyacrylate. Interpenetrating network polymers can be prepared with polymers of the present invention with materials such as epoxy resins and polycarbonate resins. The network polymers can be prepared by including one or more monomers in the formulations of the present invention such that the materials form a co-continuous or phase segregated in-situ polymer network. Preferably, the urea/urethane group containing polymers are the predominant component of multipolymer compositions of the present invention.

The polymers of the present invention can be either thermoplastic or thermoset. Polyurethanes are prepared from formulations including both polyisocyanate and a polyalcohol. Polyureas are prepared from formulations including both a polyisocyanate and a polyamine. The polyurethane/polyurea polymers are often prepared from formulations including a polyisocyanate and both a polyalcohol and a polyamine.

In the practice of the present invention, the polyisocyanate formulation component can be advantageously selected from organic polyisocyanates, modified polyisocyanates, isocyanate-based prepolymers, and mixtures thereof. These can include aliphatic and cycloaliphatic isocyanates, but aromatic and especially multifunctional aromatic isocyanates are preferred. Preferred are 2,4- and 2,6-toluenediisocyanate and the corresponding isomeric mixtures; 4,4'-, 2,4'- and 2,2'- diphenylmethanediisocyanate and the corresponding isomeric mixtures; mixtures of 4,4'-, 2,4'- and 2,2'-diphenylmethanediisocyanates and polyphenyl polymethylene polyisocyanates (PMDI); and mixtures of PMDI and toluene diisocyanates. Also useful with the present invention are aliphatic and cycloaliphatic

isocyanate compounds such as 1,6-hexamethylenediisocyanate; 1-isocyanato-3,5,5-trimethyl-1-3- isocyanatomethyl-cyclohexane; 2,4- and 2,6- hexahydrotoluenediisocyanate, as well as the corresponding isomeric mixtures; 4,4'-, 2,2'- and 2,4'- dicyclohexylmethane-diisocyanate, as well as the corresponding isomeric mixtures.

Also advantageously used for the polyisocyanate component are the so-called modified multifunctional isocyanates, that is products which are obtained through chemical reactions of the above diisocyanates and/or polyisocyanates. Exemplary are polyisocyanates containing esters, ureas, biurets, allophanates and preferably carbodiimides and/or uretone imines; isocyanurate and/or urethane group containing diisocyanates or polyisocyanates. Liquid polyisocyanates containing carbodiimide groups, uretonimine groups and/or isocyanurate rings, having isocyanate groups (NCO) contents of from 10 to 40 weight percent, more preferably from 20 to 35 weight percent, can also be used. These include, for example, polyisocyanates based on 4,4'-, 2,4'- and/or 2,2'- diphenylmethane diisocyanate and the corresponding isomeric mixtures, 2,4- and/or 2,6-toluenediisocyanate and the corresponding isomeric mixtures, 4,4'-, 2,4'- and 2,2'-diphenylmethanediisocyanate and the corresponding isomeric mixtures; mixtures of diphenylmethane diisocyanates and PMDI and mixtures of toluene diisocyanates and PMDI and/or diphenylmethane diisocyanates.

Suitable also are prepolymers having NCO contents of from 5 to 40 weight percent, more preferably from 15 to 30 weight percent. These prepolymers are prepared by reaction of the di- and/or poly-isocyanates with materials including diols, triols, but also they can be prepared with multivalent active hydrogen compounds such as di- and tri-amines and di- and tri-thiols. Individual examples are aromatic polyisocyanates containing urethane groups, preferably having NCO contents of from 5 to 40 weight percent, more preferably 20 to 35 weight percent, obtained by reaction of diisocyanates and/or polyisocyanates with, for example, lower molecular weight diols, triols, oxyalkylene glycols, dioxyalkylene glycols or polyoxyalkylene glycols having molecular weights up to 800. These polyols can be employed individually or in mixtures as di- and/or polyoxyalkylene glycols. For example, diethylene glycols, dipropylene glycols, polyoxyethylene glycols, polyoxypropylene glycols and polyoxypropylenepolyoxyethylene glycols can be used.

Particularly useful in the present invention are: (i) polyisocyanates having an NCO content of from 8 to 40 weight percent containing carbodiimide groups and/or urethane groups, from 4,4'-diphenylmethane diisocyanate or a mixture of 4,4'- and 2,4'-diphenylmethane diisocyanates; (ii) prepolymers containing NCO groups, having an NCO content of from 20 to 35 weight percent, based on the weight of the prepolymer, prepared by the reaction of polyoxyalkylene polyols, having a functionality of preferably from 2 to 4 and a molecular weight of from 800 to 15,000 with 4,4'-diphenylmethane diisocyanate or with a mixture of 4,4'- and 2,4'-diphenylmethane diisocyanates and mixtures of (i) and (ii); and (iii) 2,4- and 2,6-toluenediisocyanate and the corresponding isomeric mixtures. PMDI in any of its forms can also be used and is preferred. In this case it preferably has an equivalent weight between 125 and 300, more preferably from 130 to 175, and an average functionality of greater than 2. More preferred is an average functionality of from 2.5 to 3.5. The viscosity of the polyisocyanate component is preferably from 25 to 5,000 centipoise (cps) (0.025 to 5 Pa·s), but values from 100 to 1,000 cps (0.1 to 1 Pa·s)at 25°C are preferred for ease of processing. Similar viscosities are preferred where alternative polyisocyanate components are selected.

In the practice of the present invention, a polyalcohol formulation component can be advantageously selected from the following classes of compositions, alone or in admixture: (a) alkylene oxide adducts of polyhydroxyalkanes; (b) alkylene oxide adducts of non-reducing sugars and sugar derivatives; (c) alkylene oxide adducts of phosphorus and polyphosphorus acids; and (d) alkylene oxide adducts of polyphenols. Polyols of these types are referred to herein as "base polyols". Examples of alkylene oxide adducts of polyhydroxyalkanes useful herein are adducts of ethylene glycol, propylene glycol, 1,3-dihydroxypropane, 1,4- dihydroxybutane, and 1,6-dihydroxyhexane, glycerol, 1,2,4-trihydroxybutane, 1,2,6-trihydroxyhexane, 1,1,1- trimethylolethane, 1,1,1-trimethylolpropane, pentaerythritol, polycaprolactone, xylitol, arabitol, sorbitol, and mannitol. Preferred herein as alkylene oxide adducts of polyhydroxyalkanes are the ethylene oxide adducts of trihydroxyalkanes. Other useful adducts include ethylene diamine, glycerin, ammonia, 1,2,3,4-tetrahydroxy butane, fructose, and sucrose.

Also preferred are poly(oxypropylene) glycols, triols, tetrols, pentols and hexols and any of these that are capped with ethylene oxide. These polyols also include poly(oxypropyleneoxy-

ethylene)polyols. The oxyethylene content should preferably comprise less than 80 weight percent of the total and more preferably less than 40 weight percent. The ethylene oxide, when used, can be incorporated in any way along the polymer chain, for example, as internal blocks, terminal blocks, or randomly distributed blocks, or any combination thereof.

Another preferred class of polyols are "copolymer polyols", which are base polyols containing stably dispersed polymers such as acrylonitrile-styrene copolymers. Production of these copolymer polyols can be from reaction mixtures comprising a variety of other materials, including, for example, catalysts such as azobisisobutyronitrile; copolymer polyol stabilizers; and chain transfer agents such as isopropanol.

Polyisocyanate polyaddition active hydrogen containing compounds (PIPA) are also useful for preparing formulations of the present invention. PIPA compounds are typically the reaction products of TDI and triethanolamine. A process for preparing PIPA compounds can be found in, for example, United States Patent 4,374,209, issued to Rowlands.

Polyester polyols can be used for preparing the polymers of the present invention. For example, polyols prepared from caprolactone are useful. Polyols prepared from butanediol and adipic acid can also be used. Any polyester known to one skilled in the art of preparing polyurethanes and polyureas to be useful can be used with the present invention.

Low molecular weight diols and triols can also be used in preparing the polymers of the present invention. Ethylene glycol is particularly useful but other, similar compounds can also be used. Propylene glycol, diethylene glycol, are also suitable for use in the present invention.

In the practice of the present invention, the polyamine formulation component can be selected from the group including polyamines, and amine terminated polyols. Polyamines are preferred for preparing the polyurethane/polyurea formulations of the present invention include the known low molecular isocyanate-reactive compounds such as aromatic polyamines, especially diamines, having molecular weights of less than 800, preferably less than 500.

Preferred amine group containing compounds include the sterically hindered aromatic diamines which contain at least one linear or branched alkyl substituent in the ortho position to the first amino group and at least one, preferably two, linear or branched alkyl substituents containing at least one, preferably one to three carbon atoms in the ortho position to the second amino group. These aromatic diamines include 1-methyl-3,5-diethyl-2,4-diaminobenzene, 1-methyl-3,5-diethyl-2,6-diaminobenzene, 1,3,5-trimethyl-2,4-diaminobenzene, 1-methyl5-t-butyl-2,4-diaminobenzene, 1-methyl-5-t-butyl-2,6-diaminobenzene, 1,3,5-triethyl-2,4-diaminobenzene, 1-methyl-5-t-butyl-2,4-diaminobenzene, 1-methyl-5-t-butyl-2,6-diaminobenzene, 1,3,5-triethyl-2,4- diaminobenzene, 3,5,3', 5'-tetraethyl-4,4'- diaminodiphenylmethane, 3,5,3',5'-tetraisopropyl-4,4'- diaminodiphenylmethane, 3,5-diethyl-3', 5'-diisopropyl- 4,4'-diaminodiphenylmethane, 3,3'-diethyl-5,5'-diisopropyl-4,4'-diaminodiphenylmethane, 1-methyl-2,6- diamino-4-isopropylbenzene and mixtures of the above diamines. Most preferred are mixtures of 1-methyl-3,5- diethyl-2,4-diaminobenzene and 1-methyl-3,5-diethyl-2,6- diaminobenzene in a weight ratio between 50:50 to 85:15, preferably 65:35 to 80:20.

Unhindered aromatic polyamines can be used with the sterically hindered chain extenders and include 2,4- and/or 2,6-diaminotoluene, 2,4' and/or 4,4'- diaminodiphenylmethane, 1,2'- and 1,4-phenylene diamine, naphthalene-1,5-diamine and triphenyl methane-4,4', 4"- triamine. The difunctional and polyfunctional aromatic amine compounds may also exclusively or partly contain secondary amino groups such as 4,4'-di- (methylamino)-diphenylmethane or 1-methyl-2-methylamino-4-aminobenzene. Liquid mixtures of polyphenyl polymethylene polyamines of the type obtained by condensing aniline with formaldehyde are also suitable.

Generally the nonsterically hindered aromatic diamines and polyamines are too reactive to provide sufficient processing time in preparing polymers such as RIM polyurethanes and polyureas. Accordingly, these diamines and polyamines should be used in combination with one or more of the previously mentioned sterically hindered diamines. One exception to this is the case of methylene diorthochloroaniline. This particular diamine, though not sterically hindered, is a suitable material for preparing RIM polyurethane/polyureas.

Polyurethane catalysts are also suitably used with the present invention. The catalyst is preferably incorporated in the formulation in an amount suitable to increase the rate of reaction between the isocyanate groups of the composition of the present invention and a hydroxyl-reacting species. Although a wide variety of materials is known to be useful for this purpose, the most widely used and preferred catalysts are the tertiary amine catalysts and the organotin catalysts.

Examples of the tertiary amine catalysts include, for example, triethylenediamine, N-methyl morpholine, N-ethyl morpholine, diethyl ethanolamine, N-coco morpholine, 1-methyl-4-dimethyl-aminoethyl piperazine, 3-methoxy-N-dimethylpropylamine, N,N-diethyl-3-diethyl aminopropylamine, and dimethylbenzyl amine. Tertiary amine catalysts are advantageously employed in an amount from 0.01 to 2 percent by weight of the polyol formulation.

Examples of organotin catalysts include dimethyltin dilaurate, dibutyltin dilaurate, dioctyltin dilaurate, and stannous octoate. Other examples of effective catalysts include those taught in, for example, U.S. Patent No. 2,846,408. Preferably the organotin catalyst is employed in an amount from 0.001 to 0.5 percent by weight of the polyol formulation.

Catalysts which promote the formation of isocyanurate groups can also be used with the present invention. Suitable catalysts for use with the present invention include such as those mentioned in Saunders and Frisch, Polyurethanes, Chemistry and Technology in 1 High Polymers Vol. XVI, pp. 94-97 (1962). Such catalysts are referred to herein as trimerization catalysts. Examples of these catalysts include aliphatic and aromatic tertiary amine compounds, organometallic compounds, alkali metal salts of carboxylic acids, phenols and symmetrical triazine derivatives. Preferred trimerization catalysts are potassium salts of carboxylic acids such as potassium octoate and tertiary amines such as, for instance, 2,4,6-tris(dimethyl aminomethyl) phenol.

The process of the present invention can include an additional step wherein the polymer is formed into an article prior to painting it. RIM as already discussed above is a preferred method of preparing an article. Injection molding of thermoplastics is also a preferred means of preparing an article. Polymer casting can also be practiced with the process of the present invention as well as blow

molding, extrusion and compression molding. One advantage of the present invention is that articles so formed can be attached to metal articles and the two painted together as a unit.

In addition to the above formulations components, the polyurethane/polyurea formulations of the present invention can also include materials known to be useful in preparing polyurethane/polyurea polymers by those skilled in the art. Included in these materials are additives such as fillers, mold release agents, pigments, blowing agents, surfactants, and flame retardants. Specifically excluded are other conductive fillers. The polymers of the present invention are not sufficiently conductive in the absence of the non-volatile metal salt conductivity inducing materials of the present invention to be efficiently electrostatically painted.

The formulation components of the formulations of the present invention can be brought together to form a polymer in any way known to be useful to those skilled in the art of preparing polyurethane/polyurea polymers. One preferred means of forming the polyurethane/polyurea polymers of the present invention is by means of reaction injection molding (RIM). Preparing RIM polymers is well known in the art, but generally includes the steps of introducing at least two streams of mutually reactive materials through a mixer into a mold wherein the materials polymerize to produce a molded polymer article.

In addition to the advantage of being paintable without the use of a conductive primer, the polymers of the present invention can be molded with fewer defects due to flash imperfections. Small particles of polymer which remain in the mold after a molded article has been removed from the mold are known as flash. Since the polymers of the present invention are comparatively more conductive than otherwise identical polymers prepared without conductivity inducing materials, they can be less subject to a static-attraction to the mold and can be more easily removed. Therefore, the flash particles are less likely to remain behind and be an imperfection on the surface of the next article to be molded.

In the practice of the present invention, cured polymers are electrostatically painted. For the purposes of the present invention, electrostatic painting includes at least the steps of: (1) charging an object to be painted with an electrical charge, (2) charging a paint with an electrical charge of opposite polarity to that of the object

or at least grounding the paint relative to the charged article and (3) dispensing the paint from an electrostatic painting apparatus onto the object. It is also possible and even more routine, in some industries, to charge the paint and ground the object to be painted. Any means and apparatus known to be useful for electrostatic painting to those skilled in the art can be used with the process of the present invention. For example, an apparatus such as a BINKS MODEL 85* can be used to electrostatically paint the cured polymers of the present invention (*BINKS MODEL 85 is a trade designation of Binks Manufacturing Company).

While the present invention can be used with liquid paints, it is not intended that the term "paint" be so narrowly construed. For purposes of the present invention, the material which can be "painted" onto an object by the method the present invention includes any material which can be electrostatically deposited onto an object. These materials include but are not limited to liquid pigment paints, liquid transparent paints (also known as clear coats), powder pigments, powder coatings, conductive coatings such as primers and prepcoats. The materials can be neat or solvent born, water born or both solvent and water born. As with the case of powders, for example, the materials can also be applied as a solid. The process of electrostatic painting includes the process of electrodeposition as well wherein rather than applying the material onto the article in an aerosol, the article is dipped into the material while an electrostatic potential is maintained between the article and the material being applied thereto.

A preferred embodiment of the present invention is an electrostatically painted object comprising at least two layers, a first layer being a layer of polymer prepared from a polymer formulation including (1) materials which include or form urea groups, urethane groups or mixtures thereof, and (2) a non-volatile metal salt conductivity inducing material, and a second layer, the second layer being a layer of electrostatically applied paint, wherein (a) the polymer can be efficiently electrostatically painted, and (b) the polymer would not be conductive but for the inclusion of the non-volatile metal salt conductivity inducing materials in the polymer. While the present invention is useful for electrostatically painting articles not primed or coated with a conductive material, that is the two layers being adjacent, the present invention can also be used advantageously to prepare articles having a third layer interposed between the electrostatically applied paint and the polymer. The

third layer can be a non-conductive or a conductive coating. The non-volatile metal salts of the present invention increase the bulk conductivity of polymers prepared therewith. Surface coating of a polymer with a conductive material increases surface conductivity but has little effect on bulk conductivity. It is believed that surface conductivity alone is inefficient in charging an article to be electrostatically painted. Therefore, the method of the present invention can be employed to more efficiently paint a polymer coated with a non-conductive layer or even a polymer having a preparatory conductive coating such as a conductive primer or prep-coat.

The method of the present invention can be advantageous compared to conventional methods of electrostatically painting polymers for several reasons. One of these reason is that a very small amount of material is added to a polymer which both imparts sufficient conductivity to permit efficient electrostatic painting but does not substantially degrade polymer physical properties. The non-volatile metallic salts of the present invention can be selected such that they are compatible with the polymer formulation in which they will be included. Alternatively, the salt can be mixed with a compatibilizer. If a compatibilizer is used, it should be selected such that it does not impart undesirable properties to the polymer and that it does not degrade the physical properties of the polymer. For example, n-methyl-2-pyrrolidone can be used to compatibilize a non-volatile salt of the present invention and yet not cause a substantial degradation of polymer physical properties prepared therewith.

The following examples and comparative examples are meant to be illustrative of the present invention. These examples and comparative examples are not intended to limit the claims of the present inventions and they should not be so interpreted.

EXAMPLE 1

A polyurethane/polyurea polymer was prepared by reacting an isocyanate prepolymer (A side) and a polyol diamine mixture (B side) by means of a reaction injection molding apparatus to produce elastomer plaques measuring 17.5 in. (44.4 cm) x 10.0 in. (25.4 cm) x 0.063 in. (0.16 cm). The parameters of the reaction injection molding apparatus are displayed below in Table 1. The polyurethane/polyurea polymer formulation was of two components. The first component was a methylene diphenyl diisocyanate based soft segment prepolymer, the prepolymer being prepared with a polyether polyol sold commercially as SPECTRIM 50A* (*SPECTRIM 50A is a trade designation of The Dow

Chemical Company). The second component was a blended active hydrogen containing component based on a polyether polyol and diethyltoluenediamine sold commercially as SPECTRIM 50B* (*SPECTRIM 50B is a trade designation of The Dow Chemical Company). 0.164 percent of total polymer weight of a sodium perfluroalkyl sulfonic acid salt was included in the SPECTRIM 50B component, the SPECTRIM 50B component and sodium perfluroalkyl sulfonic acid salt, FLUORAD FC-98*, were mixed and placed into a reservoir of the RIM apparatus (*FLUORAD FC-98 is a trade designation of 3M and is a mixture of potassium perfluoro cyclohexyl alkylsulfonates). The SPECTRIM 50A was also placed in a reservoir of the RIM apparatus. Plaques were prepared by molding and postcuring.

The plaques were washed using a five step process including the steps of a 60 second rinse in ISW 32*, a 30 second deionized water rinse, a 30 second rinse in ISW 33**, a 30 second deionized water rinse, a 15 second deionized water rinse (*ISW-32 is a trade designation of DuBois Chemicals Corp. and is a phosphoric acid based detergent; **ISW-33 is a trade designation of DuBois Chemicals Corp. and is a phosphoric acid based painting conditioning agent). The plaques were then dried.

The plaques were painted by first weighing the plaques on an analytical balance (Original Plaque Weight (OP Wt)) and then mounting the plaques on a curved metal support having an 8.6 inch (21.8 cm) radius. The support was then mounted on a conveyor travelling 320 inches/minute (8.13 m/minute). The distance through which the plaques were moved during painting was 20 inches (50.8 cm). The plaques were painted with a BINKS MODEL 85* gun having a 0.046 inch (1.24 mm) orifice equipped with a an E63PB* air cap and a D63B* fluid tip (*BINKS MODEL 85, E63PB and D63B are trade designations of Binks Manufacturing Company). The optimum conditions to paint a metal coupon to 1.4 mil (0.036 mm) were 50 psi (345 mPa) air atomization pressure and 8 psi (55.2 mPa) cup pressure. The gun was indexed downward 3 inches (7.62 cm) for each of 6 passes per coat of paint. The applied voltage was 70 to 75 kilovolts at a current of 40 to 45 microamps. The paint used was PPG CBC8554* which was diluted with isobutyl acetate to produce a spray viscosity of 22 seconds using a Fisher #2 cup (*PPG CBC8554 is a trade designation of PPG Industries, Inc.). After a first coat of paint was applied, the paint was allowed to flash for 1.5 minutes and then a second coat of paint was applied.

After the plaques were painted, the paint transfer efficiency was measured by allowing the painted plaques to flash for five minutes and then curing the plaques in a ventilated oven at 260°F (127°C) for 45 minutes. The plaques were allowed to cool for 30 minutes at ambient temperature and then reweighed on an analytical balance (Final Plaque Weight (FP Wt)). Throughput of the spray gun (TP) was determined by disabling the air stream and weighing the amount of paint collected in one minute. Weight percent solids in the paint (WT Solids) was determined by flashing the solvent from 5-10 grams of paint, curing at 120°C for one hour and determining the difference in weight with a balance. Paint spray time (PST) was 44.4 seconds. Paint transfer efficiency was determined with the following formula:

$$\text{Paint Transfer Efficiency} = \frac{(\text{FP Wt}) - (\text{OP Wt})}{\text{TP} \times \text{PST} \times \text{Wt Solids}}$$

and displayed in Table 2 below.

COMPARATIVE EXAMPLE 2

A polyurethane/polyurea polymer was prepared, painted and tested substantially identically to Example 1 except that instead of 0.164 percent FLUORAD FC-98, the formulation includes no FLUORAD FC-98. The result is displayed in Table 2 below.

TABLE 1

Reaction Injection Molding Parameters

Head Pressure (psi)/(mPa)	1,900/13,100
Throughput (g/sec.)	400
Reservoirs Temperature (°C)	38
Mold Temperature (°C)	63
Injection Time (sec.)	0.85
Demold Time (sec.)	40

TABLE 2

Example Number	FC-98* Concentration	Paint Transfer Efficiency
1	0.164	13.47
Comparative 2	0.000	9.47

*FC-98 is a trade designation of 3M and is a mixture of potassium perfluoro cyclohexyl alkylsulfonates.

EXAMPLE 3

A polyurethane/polyurea polymer was prepared substantially identically to Example 1 except that instead of 0.164 percent FLUORAD FC-98, the formulation includes 0.761 percent FLUORAD FC-98. The plaques were tested for physical properties. The results are displayed in Table 3 below.

EXAMPLE 4

A polyurethane/polyurea polymer was prepared and tested substantially identically to Example 3 except that instead of 0.761 percent FLUORAD FC-98, the formulation includes 0.200 percent FLUORAD FC-98. The results are displayed in Table 3.

COMPARATIVE EXAMPLE 5

A polyurethane/polyurea polymer was prepared and tested substantially identically to Example 3 except that instead of 0.761 percent FLUORAD FC-98, the formulation includes no FLUORAD FC-98. The results are displayed in Table 3.

TABLE 3

Example Number	3	4	Comp. 5
FC-98* Concentration (percent)	0.761	0.200	0.000
Tensile Strength (psi)/mPa)[1]	3,740/ 25,787	4,780/ 32,959	3,970/ 27,373
Elongation (percent)[1]	298	338	307
Young's Modulus (psi)/(mPa)[2]	8,590/ 59,090	no data	7,680/ 52,594
Flexural Modulus (psi)/(mPa)[2]	60,620/ 417,975	55,600/ 383,362	58,400/ 402,668
Tear Strength (pli)/(kg/cm)[3]	688/791	658/760	676/876
Heat Sag 6in (15.2 cm)[4]	37.67	44.67	37.67
Notched Izod (in-lbs)/g/cm)[5]			
ambient	99.8/ 114,982	107.1/ 123,393	98.8/ 113,830
-20°F (-29°C)	23.7/ 27,305	95.2/ 4,558	94.8/ 4,539
Hardness A ((psi)/mPa)[6]	94.6/ 4,529	95.2/ 4,558	94.8/ 4,539
Water Absorption[7]			
24 hours	2.28	no data	2.51
240 hours	4.17	no data	3.84

*FC-98 is a trade designation of 3M and is a mixture of potassium perfluoro cyclohexyl alkylsulfonates.

1 ASTM-D-638-89, Test Method for Tensile Properties of Plastics

2 ASTM-D-790-86, Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics And Electrical Insulating Materials

3 ASTM-D-624-86, Test Method for Rubber Property -- Tear Resistance

4 ASTM-D-3796-85, Method of Testing Microcellular Urethanes -- High Temperature Sag

5 ASTM-D-256-88, Test Methods for Impact Resistance of Plastics and Electrical Insulating Materials

6 ASTM-D-2240--86, Test Method for Rubber Property -- Durometer Hardness

7 ASTM-D-570-81, Test Method for Water Absorption of Plastics

EXAMPLES 6-18 AND COMPARATIVE EXAMPLES 19-24

Polymers were prepared with the non-volatile metal salts of the present invention. The additives detailed below in Table 4A-4C were admixed into the polymer formulations and then injection molded or reaction injection molded into articles suitable for painting. A white basecoat (CBC9753) was applied with a SPRAYMATION MODEL 310160* automatic panel sprayer. The fixed conditions for the panel spraying system are:

--850"/minute (2.16 m/minute) gun traverse speed;
--2" (5.1 cm) spray gun index with 50% fan overlap ;
--40 psig (276 kPa) air atomization pressure
--BINKS MODEL 80A* electrostatic spray gun including a 63B fluid tip, N63 air cap, and a 111-1271 fluid needle;
--BINKS MODEL 111-3800*, 0-100 kilovolt power supply;
--Gun to part distance 10" (25.4 cm);
--Number of coats = 2;
--Number of gun passes per coat = 8 ; and
--80 kilovolts.

(*BINKS MODEL 80A and BINKS MODEL 111-3800 are trade designations of Binks Manufacturing Company, SPRAYMATION MODEL 310160 is a trade designation of Spraymation Equipment company)

The process conditions used during the application and the specific paint preparation conditions are shown below. Painted panels were cured after paint application in an electric air circulation oven. The paints used were Pittsburgh Paint and Glass (PPG)* paints. The paints had the following properties:

Designation	CBC9753*
Type	WHITE
---	---
LOT NUMBER	64233C
UNREDUCED VISCOSITY	60
SPRAY VISCOSITY	21
REDUCER	IBA
% REDUCER	25
NUMBER OF COATS	2
FLASH:COATS, MINUTES	0.5
FLASH BEFORE CURE - MINUTES	5
CURE TIME - MINUTES 30	40
CURE TEMPERATURE	260°F (127°C)

*PPG and CBC9753 are trade designations of Pittsburgh Paint and Glass

CALIBRATION :

Calibration was done on bare steel panels which were 0.032 x 4 x 12 inches (0.81mm x 10.2 cm x 30.48 cm) in size. The panels were painted without the electrostatics on for the calibration. The target film thickness for the steel calibration panel was 0.8 mils +/- 0.1 mils (0.02 +/- 0.0025 mm). With few exceptions, the target film thickness was reached using a pot pressure of 6 PSIG.

PANEL HOLDER AND GROUNDING:

The standard metal panel support rods on the SPRAYMATION were replaced with fiberglass rods of the same dimensions. The rack cross-members were replaced with oak which was glued on with epoxy. Aluminum plates (2) that were 4 x 6 x 1/4 inches (10.2 x 15.2 x 0.64 cm) in size were mounted 1 inch (2.54 cm) apart on the top oak cross-bar with wood screws. A metal bolt was flush mounted to the face of the metal plates. The bolt was centered on the plate and it protruded on the back where it serves as a grounding point. A grounding wire was attached with a nut and a washer. The ground had a resistivity of 0.15 ohms.

GROUND TESTING:

Ground testing was done with a WOODHEAD MODEL 7040* ground loop impedance tester (*WOODHEAD MODEL 7040 is a trade designation of Daniel Woodhead Company).

SAMPLE MOUNTING:

Test samples were mounted in such a way that half of the sample was backed by the grounded aluminum plate and half was unbacked. The test samples were held in place by clamping them on the outside edge (left handed part on the left side, right handed part on the right side) onto the aluminum plate with a conductive metal clip ($\geq$ 0.15 ohms resistivity). This ensures that the plastic articles were grounded.

Since the aluminum plates were 4 inches (10.2 cm) wide by 6 inches (15.2 cm) long, the optimum part size was 4 (10.2 cm) inches wide by 12 inches (30.5 cm) long so that half of the part would be backed and half would not be backed. Some of the parts were 10 inches (25.4 cm) long, in which case, 5 inches (12.7 cm) of the parts were backed with the aluminum and 5 inches (12.7 cm) were not.

Many of the parts were only 5 inches (12.7 cm) long. In this case, 2 parts that were 5 inches (12.7 cm) long were clipped together

to do the experiment. A 4 inch (10.2 cm) wide by 2.5 inch (6.4 cm) long by 1/4 inch (0.64 cm) thick, non-conductively modified polyurethane plaque was taped, from the back, onto the aluminum plate. The metal clip used to hold the parts in place was centered over the interface between the aluminum plate and the polyurethane. Half of the clip was on each of the 5 inch (12.7 cm) long parts. Masking tape was used to cover any exposed aluminum.

FILM THICKNESS:

Film thickness was measured on the steel panels using an ELCOMETER 245* portable film thickness meter (*ELCOMETER 245 is a trade designation of Elcometer Instruments Ltd.). Film thickness was measured visually on the plastic panels. A piece of the painted substrate was dug out of the painted plastic substrate with a razor knife. The chip was placed painted side down on a flat cutting surface. A cross-section was cut through the plastic and paint layers. The cross sectional piece was placed on a microscope slide. The paint thickness was measured at a magnification of 200 times with a graduated ocular. On the 12 inch (30.5 cm) long panels, film thickness measurements were made at 2 (5.1 cm) and 4 (12.7) inches from the top of the aluminum backed half of the test panels. On the 5 inch (12.7 cm) long panels that were clipped together, and the 10 inch (25.4 cm) long panels, film thickness measurements were made at 1.5 (3.81 cm) inches from the top of the aluminum backed half of the test panel. They were measured at 3.5 inches (8.9 cm) below the metal backing on all samples.

PAINT WRAP:

Also measured was the extent to which the paint wraps around the part rather than just travelling in a straight line from the sprayer to the part being painted. This is a subjective measurement, known as paint wrap, made by comparing a sample to both an electrostatically painted steel control and a steel control similarly painted except that the electrostatic power supply was turned off during the painting. These parts have paint wrap values of excellent and none respectively. The hierarchy of paint wrap values are:

excellent > good > fair >> slight > none.

Results are recorded below in Tables 4A-4C.

TABLE 4A

Example #	Polymer	Additive Type	Additive Amount	Film Build Backed	Film Build Unbacked	Paint Wrap
6	SPECTRIM 50S[A]	FC-98[B]	0.10	1.3 mil 0.033 mm	1.1 mil 0.027 mm	fair
7	SPECTRIM 50S[A]	FC-98[B]	0.20	1.2 mil 0.030 mm	1.0 mil 0.025 mm	good
8	SPECTRIM 50S[A]	FC-98[B]	0.50	1.3 mil 0.033 mm	1.2 mil 0.030 mm	excellent
9	SPECTRIM 50S[A]	FC-98[B]	0.05	1.4 mil 0.036 mm	0.9 mil 0.023 mm	slight
10	SPECTRIM 50S[A]	KPF_6	0.025	1.4 mil 0.036 mm	0.9 mil 0.023 mm	slight
11	SPECTRIM 50S[A]	KPF_6	0.05	1.4 mil 0.036 mm	1.1 mil 0.027 mm	slight
12	SPECTRIM 50S[A]	KPF_6	0.10	1.3 mil 0.033 mm	1.1 mil 0.027 mm	good

TABLE 4B

Example #	Polymer	Additive Type	Additive Amount	Film Build Backed	Film Build Unbacked	Paint Wrap
13	SPECTRIM 50S[A]	KPF_6	0.13	1.4 mil 0.036 mm	1.4 mil 0.036 mm	good
14	SPECTRIM 25[C]	FC-98[B]	0.20	1.3 mil 0.033 mm	1.2 mil 0.030 mm	good
15	SPECTRIM 25[C]	Sodium Tetraphenyl Boron	0.20	1.2 mil 0.030 mm	1.2 mil 0.030 mm	excellent
16	SPECTRIM 25[C]	Lithium trifluoro-methane-sulfonate	0.20	1.2 mil 0.030 mm	1.2 mil 0.030 mm	excellent
17	SPECTRIM HF85[D]	KPF_6	0.10	1.35 mil 0.034 mm	0.95 mil 0.024 mm	good
18	TPU[E]	FC-98[B]	1.0	1.5 mil 0.038 mm	1.2 mil 0.030 mm	good

TABLE 4C

Example #	Polymer	Additive Type	Additive Amount	Film Build Backed	Film Build Unbacked	Paint Wrap
Comparative 19	SPECTRIM 50S[A]	DEHYQUAT C[F]	0.5	1.4 mil 0.036 mm	0.60 mil 0.015 mm	slight
Comparative 20	SPECTRIM HF85[D]	control	--	1.2 mil 0.030 mm	0.35 mil 0.009 mm	slight
Comparative 21	SPECTRIM 25[C]	control	--	1.1 mil 0.027 mm	0.5 mil 0.013 mm	none
Comparative 22	SPECTRIM 50S[A]	control	--	1.0 mil 0.025 mm	0.5 mil 0.013 mm	none
Comparative 23	Steel	control	--	1.3 mil 0.033 mm	1.3 mil 0.033 mm	excellent
Comparative 24	TPU[E]	control	--	1.2 mil 0.030 mm	0.5 mil 0.013 mm	slight

[A] SPECTRIM 50S is a polyurethane/polyurea polymer prepared by admixing two commercially available components (SPECTRIM 50S is a trade designation of The Dow Chemical Company). The first component was a methylene diphenyl diisocyanate based soft segment prepolymer, the prepolymer being the prepared with a polyether polyol sold commercially as SPECTRIM 50A* (*SPECTRIM 50A is a trade designation of The Dow Chemical Company). The second component was a blended active hydrogen containing component based on a polyether polyol and diethyltoluenediamine sold commercially as SPECTRIM 50B* (*SPECTRIM 50B is a trade designation of The Dow Chemical Company). The articles were prepared by reaction injection molding.

[B] FC-98 is a mixture of potassium perfluoro cyclohexyl alkylsulfonates available from 3M. FC-98 is a trade designation of 3M.

[C] SPECTRIM 25 is a polyurethane/polyurea polymer prepared by admixing two commercially available components (SPECTRIM 25 is a trade designation of The Dow Chemical Company). The first component was a methylene diphenyl diisocyanate based soft segment prepolymer, the prepolymer being the prepared with a polyether polyol sold commercially as SPECTRIM 25A* (*SPECTRIM 25A is a trade designation of The Dow Chemical Company). The second component was a blended active hydrogen containing component based on a polyether polyol and diethyltoluenediamine sold commercially as SPECTRIM 25B* (*SPECTRIM 25B is a trade designation of The Dow Chemical Company). The articles were prepared by reaction injection molding.

[D] SPECTRIM HF85 is a polyurethane/polyurea polymer prepared by admixing two commercially available components (SPECTRIM HF85 is a trade designation of The Dow Chemical Company). The first component was a methylene diphenyl diisocyanate based soft segment prepolymer, the prepolymer being the prepared with a polyether polyol sold commercially as SPECTRIM HF85A* (*SPECTRIM HF85A is a trade designation of The Dow Chemical Company). The second component was a blended active hydrogen containing component based on an aminated polyether polyol sold commercially as SPECTRIM HF85B* (*SPECTRIM HF85B is a trade designation of The Dow Chemical Company). The articles were prepared by reaction injection molding.

[E] TPU is a thermoplastic urethane based on methylene diphenyl diisocyanate and a polyester polyol sold commercially as PELLETHANE 2354-65D by The Dow chemical Company. PELLETHANE 2354-65D is a trade designation of The Dow Chemical Company. The additive was admixed into the liquid precursors used to prepare the TPU. The articles were prepared by injection molding.

[F] DEHYQUAT C is lauryl pyridinium chloride and is a trade designation of Henkel Corporation.

EXAMPLES 25, 27-29 AND COMPARATIVE EXAMPLE 26&30

Sample polyurethane/polyurea plaques were prepared using the polymers and non-volatile metal salts as shown in Table 5 (*SPECTRIM 50S is a trade designation of The Dow Chemical Company). The plaques were prepared by admixing the non-volatile metal salts with the B side of the formulation and the reaction injection molding the plaques. The samples were tested for physical properties and the results are displayed below in Table 6.

TABLE 6

Example Number	25	Comparative 26	27	28	29	Comparative 30
Additive	Li-TF[4]	Control	FC-98[3]	FC-98[3]	KPF_6	Control
Amount	0.2	--	0.20	0.50	0.05	--
Polymer	Spectrim 25[1]	Spectrim 25[1]	Spectrim 50S[2]	Spectrim 50S[2]	Spectrim 50S[2]	Spectrim 50S[2]
Flexural Modulus[A] psi/mPa	26,470 182,504	27,400 188,916	60,860 419,615	59,450 409,893	62,760 432,715	58,670 404,515
Specific Gravity[B]	1.094	1.089	1.078	1.070	1.030	1.053
Tear[C] pli/(kg/cm)	475 546	451 518	607 698	605 695	591 679	585 672
Tensile[D] Strength psi/mPa	1,974 13,610	1,892 13,045	4,003 27,600	3,673 25,324	3,705 25,545	3,321 22,897
Elongation percent	288	292	235	242	219	213

[1] SPECTRIM 50S is a polyurethane/polyurea polymer prepared by admixing two commercially available components (SPECTRIM 50S is a trade designation of The Dow Chemical Company). The first component was a methylene diphenyl diisocyanate based soft segment prepolymer, the prepolymer being the prepared with a polyether polyol sold commercially as SPECTRIM 50A* (*SPECTRIM 50A is a trade designation of The Dow Chemical Company). The second component was a blended active hydrogen containing component based on a polyether polyol and diethyltoluenediamine sold commercially as SPECTRIM 50B* (*SPECTRIM 50B is a trade designation of The Dow Chemical Company). The articles were prepared by reaction injection molding.

[2] SPECTRIM 25 is a polyurethane/polyurea polymer prepared by admixing two commercially available components (SPECTRIM 25 is a trade designation of The Dow Chemical Company). The first component was a methylene diphenyl diisocyanate based soft segment prepolymer, the prepolymer being the prepared with a polyether polyol sold commercially as SPECTRIM 25A* (*SPECTRIM 25A is a trade designation of The Dow Chemical Company). The second component was a blended active hydrogen containing component based on a polyether polyol and diethyltoluenediamine sold commercially as SPECTRIM 25B* (*SPECTRIM 25B is a trade designation of The Dow Chemical Company). The articles were prepared by reaction injection molding.

[3] FC-98 is a mixture of potassium perfluoro cyclohexyl alkylsulfonates available from 3M. FC-98 is a trade designation of 3M.

[4] Lithium trifluoromethanesulfonate.

[A] ASTM D-790-86, Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics And Electrical Insulating Materials.

[B] ASTM D-792-86 Test Methods for Specific Gravity (Relative Density) and Density of Plastics by Displacement.

[C] ASTM-D-624-86, Test Method for Rubber Property -- Tear Resistance.

[D] ASTM-D-638-89, Test Method for Tensile Properties of Plastics.

EXAMPLE 31 AND COMPARATIVE EXAMPLES 32-36

Sample plaques were prepared with the polymers and additives indicated in Table 7 below. The plaques were powder coated using the following procedure:

POWDER COATING APPLICATION EQUIPMENT

A clear powder coating was applied electrostatically to test panels using a Nordson NPE CC8 Model 246152H* electrostatic Powder coating applicator. The applicator gun was mounted on an ECLIPSE MODEL 50-6528 panel sprayer using a rack speed of 300 inches/minute (762 cm/minute), a 10 inch (25.4 cm) gun to part distance, and a 3 inch (7.6 cm) gun index. The following conditions were keep constant on the powder applicator:

--Atomizing air = 20 PSIG (138 kPa)
--Fluidizing 0.2 PSIG (1.4 kPa) input
--Flow rate 30 PSIG (207 kPa)
--90 kilovolt electrostatic potential.

SAMPLE MOUNTING AND GROUNDING

The samples were mounted with a grounding clamp onto a corrugated cardboard holder which was made by taping 4, 12.5" L X

1.75" W X 0.125" inch (31.75 cm L x 4.45 cm W x 3.18 mm) pieces together. The holder was screwed onto the Eclipse support rod. The ground wire was attached at the top of the test parts.

POWDER COATING APPLICATION AND FORMULATION

The powder coating was applied in one coat and then cured for 15 minutes at 325°F (163°C).

The Powder coating formulation was composed of the following components by weight: DER 662UH* 100 parts, EPON P-108** 4 parts, RESIFLOW P-67*** 1 part. (* DER 662UH is a trade designation of The Dow Chemical Company, ** EPON P-108 is a trade designation of Shell Chemical Company, ***RESIFLOW P-108 is a trade designation of Esrton Chemical Company).

The melt was mixed on a Buss Condux PLK-46 extruder with a kneader rate of 200 revolutions per minute at 70°F (21°C). The extrudate was ground into powder with a Mikropul Bantam grinder using a 0.013 inch herringbone screen. The powder was sieved through a 150 mesh screen.

TABLE 7

Example Number	31	Comp. 32	Comp. 33	Comp. 34	Comp. 35	Comp. 36
Additive	KPF_6	control	FC-98[C]	FC-98[C]	FC-98[C]	control
Amount	0.1	--	1.00	0.50	0.25	--
Polymer	HF-85[A]	HF-85[A]	GTX[B]	GTX[B]	GTX[B]	GTX[B]
Powder Build grams	5.63	2.51	0.93	1.02	0.91	1.15

[A] SPECTRIM HF85 is a polyurethane/polyurea polymer prepared by admixing two commercially available components (SPECTRIM HF85 is a trade designation of The Dow Chemical Company). The first component was a methylene diphenyl diisocyanate based soft segment prepolymer, the prepolymer being the prepared with a polyether polyol sold commercially as SPECTRIM HF85A* (*SPECTRIM HF85A is a trade designation of The Dow Chemical Company). The second component was a blended active hydrogen containing component based on an aminated polyether polyol sold commercially as SPECTRIM HF85B* (*SPECTRIM HF85B is a trade designation of The Dow Chemical Company). The articles were prepared by reaction injection molding.

B GTX is NORYL GTX 910-A*, an engineering thermoplastic based on a polydimethylphenylene oxide and nylon blend available from General Electric Company (*NORYL GTX 910-A is a trade designation of General Electric Company). The additive is first admixed in high concentration with the plastic to form a concentrate. This concentrate is then admixed with virgin plastic in a ratio to achieve the indicated concentration. Articles were formed by injection molding.

[C] FC-98 is a mixture of potassium perfluoro cyclohexyl alkylsulfonates available from 3M. FC-98 is a trade designation of 3M.

WHAT IS CLAIMED IS:

1. A process for electrostatically painting cured urea and/or urethane group containing polymers comprising the steps of:

(A) preparing a cured polymer from a polymer formulation including

(1) materials which include or form urea groups, urethane groups or mixtures thereof, and

(2) a non-volatile metal salt conductivity inducing material, and

(B) electrostatically painting the polymer, wherein

(a) the polymer can be efficiently electrostatically painted, and

(b) the polymer would not be conductive but for the inclusion of the non-volatile metal salt conductivity inducing materials in the polymer.

2. The process of Claim 1 wherein the polymer has physical properties substantially similar to those of otherwise identical polymers prepared without the non-volatile metal salt conductivity inducing material of the present invention.

3. The process of Claim 1 additionally comprising a step of forming the polymer into a shaped article prior to painting it.

4. The process of Claim 3 wherein the polymer is formed into a shaped article by injection molding or reaction injection molding.

5. The process of Claim 4 wherein the polymer is formed into a shaped article by reaction injection molding.

6. The process of Claim 1 wherein the non-volatile metal salt contains a cation selected from the group consisting of cations of Li, Na, K and mixtures thereof.

7. The process of Claim 6 wherein the non-volatile metal salt contains an anion selected from the group consisting of a perfluoroalkyl sulfonate, a tetraphenylboron anion, a hexafluorophosphate anion, and mixtures thereof.

8. The process of Claim 1 wherein the non-volatile metal salt is present in the polymer formulation at from 0.02 to 1.5 percent.

9. In a process for electrostatically painting a cured urea and/or urethane group containing polymer wherein the polymer is formed into a shaped article, coated with a conductive preparatory substance and then electrostatically painted, the improvement comprising preparing the polymer from a polymer formulation including

(1) materials which include or form urea groups, urethane groups or mixtures thereof, and

(2) a non-volatile metal salt conductivity inducing material.

10. An electrostatically painted object comprising at least two layers, a first layer being a layer of polymer prepared from a polymer formulation including

(1) materials which include or form urea groups, urethane groups or mixtures thereof, and

(2) a non-volatile metal salt conductivity inducing material, and a second layer, the second layer being a layer of electrostatically applied paint, wherein

(a) the polymer can be efficiently electrostatically painted, and

(b) the polymer would not be conductive but for the inclusion of the non-volatile metal salt conductivity inducing materials in the polymer.

11. The electrostatically painted object of Claim 10 wherein the polymer has physical properties substantially similar to those of otherwise identical polymers prepared without the non-volatile metal salt conductivity inducing material of the present invention.

12. The electrostatically painted object of Claim 10 wherein the non-volatile metal salt contains a cation selected from the group consisting of cations of Li, Na, K and mixtures thereof.

13. The electrostatically painted object of Claim 12 wherein the non-volatile metal salt contains an anion selected from the group consisting of a perfluoroalkyl sulfonate, a tetraphenylboron anion, a hexafluorophosphate anion, and mixtures thereof.

14. The electrostatically painted object of Claim 10 wherein the non-volatile metal salt is present in the polymer at from 0.02 to 1.5 percent.

15. The electrostatically painted object of Claim 10 wherein the electrostatically applied paint layer and the polymer layer are adjacent.

16. The electrostatically painted object of Claim 10 wherein the object includes an additional layer interposed between the electrostatically applied paint layer and the polymer layer.

17. The electrostatically painted object of Claim 16 wherein the additional layer is a conductive primer or conductive preparatory coating.

18. The electrostatically painted object of Claim 10 wherein the polymer is an object formed by injection molding or reaction injection molding.

19. The electrostatically painted object of Claim 18 wherein the polymer is an object formed by reaction injection molding.

INTERNATIONAL SEARCH REPORT

Inte. ional Application No
PCT/US 93/08470

A. CLASSIFICATION OF SUBJECT MATTER
IPC 5 B05D1/04 H01B1/20

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 5 H01B B05D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 443 767 (HUGHES AIRCRAFT CO.) 28 August 1991 see page 3, column 4, line 11 - line 14 see page 4, column 5, line 23 - line 30 see page 5, column 7, line 7 - line 15 ---	1-7, 10-13,15
Y	US,A,3 535 294 (H. MARUMO) 20 October 1970 see the whole document ---	1-3, 8-11,14, 15
Y	EP,A,0 309 286 (POLYPLASTIC CO.LTD.) 29 March 1989 see the whole document --- -/--	1-3, 8-11,14, 15

[X] Further documents are listed in the continuation of box C.

[X] Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

2

Date of the actual completion of the international search	Date of mailing of the international search report
6 December 1993	17. 12. 93

Name and mailing address of the ISA	Authorized officer
European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax (+31-70) 340-3016	Brothier, J-A

Form PCT/ISA/210 (second sheet) (July 1992)

INTERNATIONAL SEARCH REPORT

Int...tional Application No
PCT/US 93/08470

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 475 360 (DAI-ICHI KOGYO SEIYAKU CO.) 18 March 1992 see the whole document -----	8,14

2

INTERNATIONAL SEARCH REPORT

Information on patent family members

Inter. .onal Application No
PCT/US 93/08470

Patent document cited in search report	Publication date	Patent family member(s)		Publication date
EP-A-0443767	28-08-91	US-A-	5188783	23-02-93
		JP-T-	4505636	01-10-92
		WO-A-	9113444	05-09-91
US-A-3535294	20-10-70	NONE		
EP-A-0309286	29-03-89	JP-A-	1085263	30-03-89
		US-A-	5071593	10-12-91
EP-A-0475360	18-03-92	JP-A-	4122775	23-04-92
		US-A-	5204397	20-04-93