



AU9223406

(12) PATENT ABRIDGMENT (11) Document No. AU-B-23406/92
(19) AUSTRALIAN PATENT OFFICE (10) Acceptance No. 657992

- (54) Title
IMPROVED ALUMINUM ALLOY
- (51)⁵ International Patent Classification(s)
C22C 021/16 B62D 029/00 C22C 021/08 C22F 001/047
C22F 001/057
- (21) Application No. : **23406/92** (22) Application Date : **22.07.92**
- (87) PCT Publication Number : **WO93/02220**
- (30) Priority Data
- (31) Number (32) Date (33) Country
734619 23.07.91 US UNITED STATES OF AMERICA
- (43) Publication Date : **23.02.93**
- (44) Publication Date of Accepted Application : **30.03.95**
- (71) Applicant(s)
ALCAN INTERNATIONAL LIMITED
- (72) Inventor(s)
ALOCK KUMAR GUPTA; DAVID JAMES LLOYD; PIERRE HENRI MAROIS
- (74) Attorney or Agent
DAVIES COLLISON CAVE , 1 Little Collins Street, MELBOURNE VIC 3000
- (56) Prior Art Documents
AU 84075/91 C22F 1/057 1/047 C22C 21/10
AU 75440/91 C22F 1/57
US 4589932
- (57) Claim

1. An aluminum alloy material consisting of, by weight percent, 1% to 1.8% Cu, 0.8% to 1.9% Mg, 0.2% to 0.4% Si, 0.05% to 0.4% Fe, 0.05% to 0.40% Mn, with the balance being aluminum including normal impurities, wherein the percentage of Mg by weight ($\pm 0.2\%$) is equal to $\% \text{Cu} / 2.2 + 1.73 \times \% \text{Si}$.

7. A method of making an improved aluminum alloy, comprising:

forming an aluminum alloy consisting of, by weight percent, 1% to 1.8% Cu, 0.8% to 1.9% Mg, 0.2% to 0.4% Si, 0.05% to 0.4% Fe, 0.05% to 0.40% Mn, with the balance aluminum with normal impurities;

forming aluminum alloy sheets from said aluminum alloy;
stamping said aluminum alloy sheets into workpieces;
and heat treating and age hardening said workpieces to form precipitate phases including a metastable beta phase of Mg_2Si and an S' phase of Al_2CuMg .

15. An automobile panel when made by the method of any one of claims 7 to 12 and 14.

OPI DATE 23/02/93 APPLN. ID 23406/92
AQJP DATE 29/04/93 PCT NUMBER PCT/CA92/00316



AU9223406

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C22C 21/16, C22F 1/057	A1	(11) International Publication Number: WO 93/02220 (43) International Publication Date: 4 February 1993 (04.02.93)
(21) International Application Number: PCT/CA92/00316 (22) International Filing Date: 22 July 1992 (22.07.92) (30) Priority data: 734,619 23 July 1991 (23.07.91) US (71) Applicant: ALCAN INTERNATIONAL LIMITED [CA/CA]; 1188 Sherbrooke Street, West, Montreal, Quebec H3A 3G2 (CA). (72) Inventors: GUPTA, Alock, Kumar ; 19 Macpherson Avenue, Unit 30, Kingston, Ontario K7M 6W4 (CA). LLOYD, David, James ; 865 Berwick Place, Kingston, Ontario K7M 6B7 (CA). MAROIS, Pierre, Henri ; 38B Crescent Drive, Kingston, Ontario K7M 4J5 (CA).		(74) Agents: EADES, Norris, M. et al.; Kirby, Eades, Gale, Baker & Potvin, Box 3432, Station D, Ottawa, Ontario K1P 6N9 (CA). (81) Designated States: AU, BR, CA, JP, KR, NO, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IT, LU, MC, NL, SE). Published <i>With international search report.</i> 657992
(54) Title: IMPROVED ALUMINUM ALLOY (57) Abstract The invention provides an aluminum alloy material consisting essentially of, by weight percent, 1 % to 1.8 % Cu, 0.8 % to 1.9 % Mg, 0.2 % to 0.6 % Si, 0.5 % to 0.4 % Fe, 0.05 % to 0.30 % Mn, with the balance aluminum with normal impurities. The alloy forms two precipitation phases during heat treatment and age hardening: a beta phase of Mg ₂ Si and an S' phase of Al ₂ CuMg. The alloy has improved formability without significant sacrifice of strength, and is particularly suited to be formed into automobile sheet metal parts such as hood lids, trunks lids, and fenders.		

IMPROVED ALUMINUM ALLOYTECHNICAL FIELD

This invention relates to improved aluminum alloys and products made therefrom, particularly aluminum alloys including magnesium, copper, and silicon having improved strength and formability properties. The present invention also relates to processes for producing such alloys, as well as aluminum alloy sheets and articles fabricated therefrom and to the products of such processes.

10 BACKGROUND ART

Aluminum alloys are enjoying growing use as automobile parts and are rolled into sheets which may be stamped into hoods, trunk lids, doors, and fenders, and the like from the aluminum alloy sheet. At present, however, none of the existing aluminum alloys suitable for use in forming automobile panels and parts appears to satisfy the specifications of the various automotive companies, as the standards tend to differ from one company to the other. For example, one company's requirements may emphasize alloy strength (e.g., a yield strength in excess of 25 ksi or 1757.5 kg/cm²), while other companies may prefer a softer alloy (e.g., a 15-18 ksi or 1054.5-1265.4 kg/cm² yield strength in the as delivered state), which has superior formability properties. Often, improvements in an alloy's formability decreases the ability of heat treatment of the alloy to improve its strength. As such, there exists a need for an alloy which may be formed easily into automotive body panels, but which has good age hardening properties so that when the alloy panels are heat treated, such as during the paint baking cycle, the strength of the alloy increases.

Various studies and previous attempts have been made to develop improved aluminum alloys which may be suitable for use in manufacturing automobile body panels, for



example, and which have a composition displaying good age hardening properties.

For example, U.S. Patent No. 4,589,932 (Park) appears to pertain to an alloy composition containing 0.4% to 1.2% Si, 0.5% to 1.3% Mg, 0.6% to 1.1% Cu, and 0.1% to 1% Mn. The patentee states that the alloy is responsive to high temperature artificial aging treatments.

In U.S. Patent No. 4,637,842 (Jeffrey et al.), the patentees discuss a method for producing Al-Mg-Si alloy sheets and articles. The patentees, however, do not attempt to create phases in an effort to improve the age hardening properties of the alloy.

Similarly, in U.S. Patent No. 3,881,966 (Staley et al.), the patentees state that the alloy they have developed, which contains 4.5% to 8% Zn, along with Cu and Mg, has very high strength when thermally treated.

However, the foregoing alloys require very close control over the natural and artificial aging cycle if appropriate combinations of strength and formability are to be achieved. In practice it is important that the T4 strength be relatively low, and the natural aging rate be slow, so that good formability can be maintained over a long period of time. Subsequently the alloy needs to show a high precipitation hardening response during the paint bake cycle so that a high final strength in the formed, painted part can be achieved.

DISCLOSURE OF THE INVENTION

The invention provides an aluminum alloy material consisting essentially of, by weight percent, 1% to 1.8% Cu, 0.8% to 1.9% Mg, 0.2% to 0.4% Si, 0.05% to 0.4% Fe, 0.05% to 0.40% Mn, with the balance aluminum with normal impurities, wherein the percentage of Mg by weight is approximately equal to $\% \text{Cu} / 2.2 + 1.73 \times \% \text{Si}$. The foregoing alloy appears to achieve a desirable balance between formability and strength, particularly when age hardened during the paint bake cycle after forming desired sheets or panels.



The invention also provides a process of making an improved aluminum alloy, comprising the steps of forming the above aluminum alloy. The aluminum alloy may be formed into sheets or other workpieces which are then heat
 5 treated and age hardened at a temperature and for a time period effective to form precipitate phases within the alloy, e.g. a metastable betaphase of Mg_2Si and an S' phase of Al_2CuMg . These precipitates strengthen the alloy.

The invention further embraces aluminum alloy sheets,
 10 articles and automobile body parts produced by the foregoing process and possessing the advantageous combination of mechanical properties achieved thereby.

Further features and advantages of the invention will be apparent from the detailed description hereinbelow set
 15 forth, together with the accompanying drawings.

BEST MODES FOR CARRYING OUT INVENTION

The invention provides an aluminum alloy material having improved formability without sacrificing strength. In particular, the improved alloys of the present
 20 invention display good strength properties, particularly after heat treatment and age hardening during the paint bake cycle. The inventive alloy consists essentially of, by weight percent, 1% to 1.8% Cu, 0.8% to 1.9% Mg, 0.2% to 0.4% Si, 0.05% to 0.4% Fe, 0.05% to 0.40% Mn, with the
 25 balance being aluminium with normal impurities, wherein the percentage of Mg by weight is approximately equal to $\% Cu/2.2 + 1.73 \times \% Si$. In this alloy the precipitation rate at room temperature is slow, but at higher
 30 temperatures the age hardening rate is high due to the precipitation of multiple metastable phases.

The invention further provides an aluminum alloy material consisting essentially of, by weight percent, 1.3% to 1.6% Cu, 1.0% to 1.4% Mg, 0.25% to 0.4% Si, 0.1% to 0.3% Fe, 0.05% to 0.2% Mn, with the balance being
 35 aluminum including normal impurities, wherein the percentage of Mg by weight is approximately equal to $\% Cu/2.2 + 1.73 \times \% Si$.




The aluminum alloy material is preferably and advantageously strengthened by heat treatment and age hardening cycles. It may be heat treated, for example, in a paint baking cycle after application of paint, enamel or
5 lacquer. Following solution heat treatment and quenching, the alloy is preferably allowed to stabilize at room temperature for about a week. Subsequent age hardening occurs during the paint baking after forming the final shape, and the metastable phases are precipitated.

10 The invention also provides a method of making an improved aluminum alloy, comprising the steps of forming an aluminum alloy consisting essentially of, by weight percent, 1% to 1.8% Cu, 0.8% to 1.9% Mg, 0.2% to 0.4% Si, 0.05% to 0.4% Fe, 0.05% to 0.40% Mn, with the balance
15 being aluminium with normal impurities, wherein the percentage of Mg by weight is approximately equal to $\% \text{Cu}/2.2 + 1.73 \times \% \text{Si}$. The DC ingot may then be homogenized at between 500 and 580°C for between 2 and 8 hours using a heating rate of about 30°C per hour. The
20 ingot is then rolled to final sheet gauge and solution heat treated at between 480 and 575°C and rapidly cooled to room temperature using an appropriate quenching method. The sheet is then preferably allowed to stabilize for about one week at room temperature, followed by forming to
25 final shape.

Advantageously, if the aluminum alloy sheet after stamping the sheet into a desired shape is primed and painted on one or both sides, the baking cycle can cure the paint and harden the alloy at the same time, providing
30 a desirable strength to the final shape.

The composition limits for the inventive aluminum alloy material were established as follows. Copper contributes to the increased strength of the present aluminum alloy. Preferably, the total copper content
35 should range from about 1% to about 1.8% by weight, with 1.3% to 1.6% being most preferred at present. The copper combines with aluminum and magnesium to form an S' phase



of Al_2CuMg precipitate after heat treatment.

Silicon, although present as an impurity in some aluminum alloys, increases strength in the alloys of the present invention. The silicon content is maintained in the range of about 0.2% to 0.4%, with about 0.25% to 0.4% being preferred. It is preferable for the composition of the alloy to have Cu below 1.8% and Si below 0.4% to avoid the formation of insoluble Q phase which degrades mechanical properties.

Also, from 0.8% to about 1.9% magnesium (Mg) is added to the alloys of the present invention, although 1.0% to 1.4% Mg appears preferable. The magnesium concentration (Mg) should be adjusted to provide a sufficient concentration of magnesium to form the precursors for both the metastable beta Mg_2Si precipitate, and the S' phase, which is an Al_2CuMg precipitate. The Mg concentration actually desired can be expressed mathematically as a function of copper and silicon concentrations:

$$\% \text{Mg} \pm 0.2\% = \% \text{Cu} / 2.2 + 1.73 \times \% \text{Si}$$

This relationship, if reached in the alloy helps assure that the Mg_2Si phase will be present in an alloy in which the Mg/Si ratio (by weight) is about 1.73. The concentration of Mg provides sufficient additional Mg to form the Al_2CuMg phase.

The iron (Fe) content of the alloy of the present invention ranges from about 0.05 to about 0.4% Fe, and preferably is 0.1% to 0.3% Fe. These concentrations correspond to the iron impurity levels in most commercial aluminum. Higher concentrations are undesirable, and may degrade the alloy.

The alloy also includes Manganese (Mn). Its concentration in the alloy is preferably maintained at 0.05% to 0.4%, although the most desired range appears to be 0.05% to 0.2%.

The present invention thus provides precursors of two or more strengthening precipitates which are formed during age hardening of the workpieces made from the alloy. At

the same time, the alloy may be rather easily formed into work pieces prior to heat treatment and age hardening. As mentioned above, during the heat treatment and age hardening process, two precipitate phases are formed. The most likely phases are metastable beta Mg_2Si and S' Al_2CuMg . The kinetics of the formation of these two precipitated phases are different, and thus make it possible for one alloy composition to provide strength upon heat treatment under a variety of conditions.

Previously, each of the alloys used in the manufacture of automobile panels, such as hoods, trunks, doors, fenders, and the like, had distinct and unique requirements for age hardening, which resulted in a different alloy being required whenever the heat treatment specification was altered. The composition of the present invention, on the other hand, may be used in a wider variety of applications and specifications. It provides high formability which facilitates stamping of automobile door panels, hood lids and trunk lids, for example. Once formed, the panels may be heat treated and age hardened according to a variety of techniques, but preferably this tempering step is combined with the paint baking cycle. That is, the requisite primer and paint layers are applied to the panel which has already been formed into the desired shape. The panel is passed through an oven or furnace to cure the paint and increase the strength of the final part.

The following example is intended to illustrate the practices of the invention and is not to be construed as limiting.

EXAMPLE I

Four alloys were cast in 75 x 230 x 500 mm DC ingot. Their chemical composition is listed in Table 1:



TABLE 1
CHEMICAL COMPOSITION OF ALLOYS

Alloy	Cu	Mg	Si	Fe	Mn	Others +
KSE	1.10	0.88	0.26	0.14	0.08	Al
KSF	1.12	1.08	0.34	0.15	0.08	Al
KSG	1.52	1.22	0.33	0.15	0.08	Al
KSH	1.62	1.54	0.50	0.16	0.08	Al

The alloys were scalped, homogenized (at heating rate of 30°C/h) at 530°C for 6 hours, hot rolled to -4.0 mm and cold rolled to the final gauge of 1.0 mm. They were solution heat treated in a fluidized sand bed at 530°C for 30 seconds, water quenched and aged at room temperature for a period of about one week (T4 temper). The alloys were optically examined and tested to determine mechanical properties of interest in T4 temper.

The following standard tests were performed on the alloys and samples of commercially available alloys:

Yield strength at T4 (ksi or kg/cm²), is the measurement of yield strength at T4 temper, as determined by ASTM METHOD E 8M-89, paragraph 7.3.1, "Offset Method". The yield strength, expressed in units of thousands of pounds per square inch (ksi) or kg/cm² is a criterion which determines if the material can be used for specific applications.

Elongation, expressed in terms of percentage elongation before failure, is another measure of the formability, and was determined by ASTM METHOD E 8M-89, paragraph 7.6.

Bendability, expressed in as r/t, where r is the radius of the bend and t is the thickness of the sheet prior to failure, is another measure of the formability of



the alloy, and was determined by ASTM METHOD E 290 87.

Erichsen Cup, or the Ball Punch Deformation Test is another test regarding formability, and is expressed in the height in inches or millimeters, of a dome attained by pressing a sphere into the sheet, until the sheet ruptures. It was carried out by ASTM METHOD E643 - 84.

Grain size is the measurement under the optical microscope of the grain size of the metal structure. The grain size, should be less than $70\mu\text{m}$ so that the sheet will be easily deformable, without defects.

Tensile tests were also conducted in T8X temper (2% stretch + 177°C for 1/2 hour), which is a test designed to replicate the forming and baking operation used in the U.S. auto-industry. The T8X test involves the following steps:

- prepare a specimen to T4 temper as outlined above.
- apply a 2% deformation to the specimen, and age at 177°C for 1/2 hour.
- measure the Yield Strength in ksi according to the ASTM METHOD E8 - 89.

The average tensile properties of KSE, KSF, KSG, and KSH alloys are summarized below in Table 2, which also includes the results of the Erichsen cup height, minimum bend radius and grain size measurements. It can be seen that tensile properties in T4 condition vary between 17.9 to 24 ksi (1258.4 to 1687.2 kg/cm^2) Y.S., between 38.3 to 47.1 ksi (2692.5 to 3311.1 kg/cm^2) U.T.S., and between 28 to 28.2% elongation. The KSE alloys represent the lower end and KSH alloy the upper end of tensile properties. In T8X temper, the KSE, KSF, KSG, and KSH alloys show significant increase in tensile properties giving values between 25.9 and 33.4 ksi (1820.8 to 2348 kg/cm^2) Y.S. and 40.4 and 47.1 ksi (2048 to 3311 kg/cm^2) U.T.S. along with a slight decrease in elongation (27 to 26%).




TABLE 2
MECHANICAL PROPERTIES OF THE
EXPERIMENTAL LABORATORY MADE ALLOYS

	Properties	Alloys			
		KSE	KSF	KSG	KSH
5	Yield Strength at T4 (ksi) (kg/cm ²)	17.9 1258.4	20.3 1427.1	23.9 1680.2	24.0 1687.2
	Elongation (%)	28.0	28.5	28.3	28.2
	Bendability, r/t	0.205	0.305	0.41	0.68
10	Erichsen (inches) (mm)	0.34 8.6	0.33 8.4	0.32 8.1	0.32 8.1
	Grain Size (μm)	27.0	20.0	18.0	20.0
15	Yield Strength at T4 + 2% Stretch + P.B.* (177°C, 1/2h) (ksi) (kg/cm ²)	25.9 1820.8	29.3 2059.8	32.9 2312.9	33.4 2348

* Paint Bake cycle.

The bendability of the alloys vary between 0.21 and 0.68, with the KSE alloy, being the best at 0.2, and the KSH, the worst, providing 0.6. All of the alloys provide Erichsen cup height close to one another (with a range of 0.34 to 0.32 weber or 8.6 to 8.1 mm).

The above mentioned results show that the alloys of the present invention compare favorably with sheet alloys currently used for making auto body panels. Table 3 lists mechanical properties of a few of the existing X611, X613, 6111 and 6009 alloys for comparison. It appears that the KSE, KSF and KSG compare favorably to commercially produced 6009, X613 and 6111 alloys respectively.

TABLE 3**NOMINAL COMPOSITION OF COMMERCIALY
AVAILABLE ALLOYS (WT.%)**

Alloy	Cu	Mg	Si	Fe	Mn	Ti
6111	0.75	0.72	0.85	0.2	0.2	0.02
6009	0.33	0.50	0.80	0.25	--	0.02
X611	--	0.77	0.92	0.15	--	0.06
X613	0.77	0.75	0.65	0.12	0.15	0.06

TABLE 4**MECHANICAL PROPERTIES OF COMMERCIALY
MADE ALLOYS**

Properties	Alloys			
	X611	X613	6111	6009
Yield Strength at T4 (ksi) (kg/cm ²)	21.3 1497.4	21.6 1518.5	25.0 1757.5	18.4 1293.5
Elongation (%)	26.5	27.5	26.9	24.8
Bendability, r/t	0.41	0.41	0.65	0.26
Erichsen (inches) (mm)	0.33 8.4	0.32 8.1	0.35 8.9	0.35 8.9
Yield Strength at T4 + 2% Stretch + P.B.* (177°C, 1/2h) (ksi) (kg/cm ²)	29.5 2073.8	29.9 2102	32.5 2284.7	27.0 1898.1

25 * Paint Bake cycle.

Table 4 compares the properties of the commercially available alloys, using the same tests used for the results in Table 2.

THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:-

1. An aluminum alloy material consisting of, by weight percent, 1% to 1.8% Cu, 0.8% to 1.9% Mg, 0.2% to 0.4% Si, 5 0.05% to 0.4% Fe, 0.05% to 0.40% Mn, with the balance being aluminum including normal impurities, wherein the percentage of Mg by weight ($\pm 0.2\%$) is equal to $\% \text{ Cu} / 2.2 + 1.73 \times \% \text{ Si}$.

2. An aluminum alloy material consisting of, by weight percent, 1.3% to 1.6% Cu, 1.0% to 1.4% Mg, 0.25% to 0.4% Si, 10 0.1% to 0.3% Fe, 0.05% to 0.2% Mn, with the balance being aluminum including normal impurities, wherein the percentage of Mg by weight ($\pm 0.2\%$) is equal to $\% \text{ Cu} / 2.2 + 1.73 \times \% \text{ Si}$.

3. An aluminum alloy material in accordance with claim 1 or 2, which has been heat treated and age hardened at a 15 temperature and for a time period effective to form precipitate phases.

4. An aluminum alloy material in accordance with claim 3, wherein said precipitate phases formed during heat treatment and age hardening include a metastable beta phase 20 of Mg_2Si and an S' phase of Al_2CuMg .

5. An aluminum alloy material in accordance with claim 4, in the form of a sheet having a paint coating on at least one side thereof, said paint coating having been cured during the heat treatment.

25 6. An aluminum alloy material in accordance with claim 5, in the form of an automobile body panel.

7. A method of making an improved aluminum alloy, comprising:

forming an aluminum alloy consisting of, by weight 30 percent, 1% to 1.8% Cu, 0.8% to 1.9% Mg, 0.2% to 0.4% Si, 0.05% to 0.4% Fe, 0.05% to 0.40% Mn, with the balance aluminum with normal impurities;

forming aluminum alloy sheets from said aluminum alloy;
stamping said aluminum alloy sheets into workpieces;
35 and heat treating and age hardening said workpieces

to form precipitate phases including a metastable beta phase of Mg_2Si and an S' phase of Al_2CuMg .

8. A method in accordance with claim 7 which includes the steps of forming the alloy into an ingot,
5 homogenizing the ingot at a temperature between 500 and 580°C for between 2 and 8 hours and rolling said ingot to form said alloy sheets.

9. A method in accordance with claim 8 wherein the ingot is heated to the temperature between 500 and 580°C
10 at a rate of 30°C per hour.

10. A method in accordance with claim 8 which includes the steps of solution heat treating the workpieces at a temperature between 480 and 575°C, and then quenched.

11. A method in accordance with claim 10 which includes the step of painting the workpieces prior to solution heat treatment.

12. A method in accordance with claim 10 or 11 which includes the step of stabilizing the workpieces at room
20 temperature for about one week.

13. An aluminum alloy material according to claim 1 and substantially as herein described with reference to the Examples.

14. A method of making an improved aluminum alloy according to claim 7 and substantially as herein described with reference to the Examples.

15. An automobile panel when made by the method of any one of claims 7 to 12 and 14.

DATED this 13th day of January, 1994.

ALCAN INTERNATIONAL LIMITED
By its Patent Attorneys
DAVIES COLLISON CAVE

INTERNATIONAL SEARCH REPORT

International Application No

PCT/CA 92/00316

I. CLASSIFICATION OF SUBJECT MATTER (if several classification symbols apply, indicate all) ⁶		
According to International Patent Classification (IPC) or to both National Classification and IPC		
Int.Cl. 5 C22C21/16; C22F1/057		
II. FIELDS SEARCHED		
Minimum Documentation Searched ⁷		
Classification System	Classification Symbols	
Int.Cl. 5	C22C ; C22F	
Documentation Searched other than Minimum Documentation to the Extent that such Documents are Included in the Fields Searched ⁸		
III. DOCUMENTS CONSIDERED TO BE RELEVANT⁹		
Category ¹⁰	Citation of Document, ¹¹ with indication, where appropriate, of the relevant passages ¹²	Relevant to Claim No. ¹³
Y	US,A,4 424 084 (M.F. CHISHOLM) 3 January 1984 see claim 1; example 2; table 1 ---	1-5
Y	J.E. HATCH 'ALUMINIUM' 1984 , AMERICAN SOCIETY FOR METALS , OHIO, US "ALUMINUM-COPPER-MAGNESIUM (SILICON)." see page 49 - page 50 "ALUMINUM-COOPER-MAGNESIUM ALLOYS." see page 144 - page 145 ---	1-5
A	US,A,4 113 472 (J.C. FISTER JR ET AL) 12 September 1978 see claims 1,12 ----- -/--	1,7,12
¹⁰ Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family		
IV. CERTIFICATION		
Date of the Actual Completion of the International Search 28 SEPTEMBER 1992		Date of Mailing of this International Search Report 20.10.92
International Searching Authority EUROPEAN PATENT OFFICE		Signature of Authorized Officer GREGG N.R. <i>Nicholas R. Gregg</i>

III. DOCUMENTS CONSIDERED TO BE RELEVANT (CONTINUED FROM THE SECOND SHEET)		
Category *	Citation of Document, with indication, where appropriate, of the relevant passages	Relevant to Claim No.
A	US,A,4 589 932 (B.K. PARK) 20 May 1986 cited in the application see claim 1 ---	1,2,7-9, 12,14,15
A	WO,A,8 702 712 (ALUMINIUM COMPANY OF AMERICA) 7 May 1987 see claim 1; example 1 ---	1,26-9, 12,14, 17-21
A	US,A,4 000 007 (R. DEVELEY ET AL) 28 December 1976 see claim 1 ---	1
A	FR,A,2 292 048 (SUMITOMO LIGHT METAL INDUSTRIES, LTD) 18 June 1976 see claim 1 ---	1,7,12
A	EP,A,0 090 583 (ALCAN INTERNATIONAL LIMITED) 5 October 1983 see claims 1,2 ---	12,14-16
A	W. HUFNAGEL 'ALUMINIUM-TASCHENBUCH' 1983, ALUMINIUM VERLAG, DUESSELDORF, DE "14.7 WEKKSTOFFE FUER DEN AUTOMOBILBAU" see page 1043 -----	

**ANNEX TO THE INTERNATIONAL SEARCH REPORT
ON INTERNATIONAL PATENT APPLICATION NO. CA. 9200316
SA 62435**

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. 28/09/92

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-4424084	03-01-84	CA-A- 1179530	18-12-84
US-A-4113472	12-09-78	DE-A- 2813810	12-10-78
		FR-A- 2386615	03-11-78
		GB-A- 1601680	04-11-81
US-A-4589932	20-05-86	CA-A- 1204654	20-05-86
WO-A-8702712	07-05-87	DE-A- 3682059	28-11-91
		EP-A, B 0245464	19-11-87
		JP-T- 63501581	16-06-88
		US-A- 4784921	15-11-88
		US-A- 4840852	20-06-89
US-A-4000007	28-12-76	FR-A- 2217429	06-09-74
		BE-A- 810974	13-08-74
		CA-A- 1026970	28-02-78
		CH-A- 585272	28-02-77
		DE-A, B 2334280	29-08-74
		GB-A- 1383895	12-02-74
		JP-C- 991680	27-03-80
		JP-A- 49113708	30-10-74
		JP-B- 54019363	14-07-79
		LU-A- 69151	08-04-74
		NL-A- 7306122	15-08-74
		SE-B- 397109	17-10-77
FR-A-2292048	18-06-76	None	
EP-A-0090583	05-10-83	CA-A- 1204987	27-05-86
		GB-A, B 2121822	04-01-84
		JP-A- 58181852	24-10-83
		US-A- 4526630	02-07-85