

**(12) STANDARD PATENT**  
**(19) AUSTRALIAN PATENT OFFICE**

(11) Application No. **AU 2007331538 B2**

(54) Title  
**Method for bleaching chemical paper pulps by final ozone treatment at high temperature**

(51) International Patent Classification(s)  
**D21C 9/153** (2006.01)

(21) Application No: **2007331538** (22) Date of Filing: **2007.12.11**

(87) WIPO No: **WO08/071718**

(30) Priority Data

(31) Number (32) Date (33) Country  
**0655467** **2006.12.13** **FR**

(43) Publication Date: **2008.06.19**

(44) Accepted Journal Date: **2011.01.27**

(71) Applicant(s)  
**ITT Manufacturing Enterprises, Inc.**

(72) Inventor(s)  
**Chirat, Christine;Hostachy, Jean-Christophe;Lachenal, Dominique;Ried, Achim;Pipon, Guillaume**

(74) Agent / Attorney  
**Davies Collison Cave, 255 Elizabeth Street, Sydney, NSW, 2000**

(56) Related Art  
**US 5571377**  
**WO 1997/015713**  
**WO 1996/001920**  
**WO 1996/034142**  
**US 5755925**  
**WO 2005/059241**

(19) World Intellectual Property Organization  
International Bureau




(43) International Publication Date  
19 June 2008 (19.06.2008)

PCT

(10) International Publication Number  
**WO 2008/071718 A1**

- (51) International Patent Classification:  
*D21C 9/153* (2006.01)
- (21) International Application Number:  
PCT/EP2007/063743
- (22) International Filing Date:  
11 December 2007 (11.12.2007)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
0655467 13 December 2006 (13.12.2006) FR
- (71) Applicant (for all designated States except US): **ITT MANUFACTURING ENTERPRISES, INC.** [US/US]; 1105 North Market Street, Suite 1217, Wilmington, Delaware 19801 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **PIPON, Guillaume** [FR/FR]; 24 Place Alfred de Vigny, F-38400 Saint Martin d'Hères (FR). **LACHENAL, Dominique** [FR/FR]; 1 Place de la Commune, F-38130 Echirolles (FR). **CHIRAT, Christine** [FR/FR]; 12 Avenue Rochambeau, F-38100 Grenoble (FR). **HOSTACHY, Jean-Christophe** [FR/FR]; 99 Rue du Prieuré, F-69440 Taluyers (FR). **RIED, Achim** [DE/DE]; Weizenacker 3, 32549 Bad Oyenhausen (DE).
- (74) Agents: **VUILLERMOZ, Bruno** et al.; Cabinet LAURENT & CHARRAS, 20 rue Louis Chirpaz, BP 32, F-69131 Ecully (FR).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:  
— with international search report  
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(54) Title: METHOD FOR BLEACHING CHEMICAL PAPER PULPS BY FINAL OZONE TREATMENT AT HIGH TEMPERATURE



(57) Abstract: Method for treating a prebleached chemical pulp comprising a step of ozone treatment of the said pulp, carried out at a temperature above 60°C, advantageously above 65°C and even more advantageously above or equal to 70°C.

WO 2008/071718 A1

**METHOD FOR BLEACHING CHEMICAL PAPER PULPS BY FINAL OZONE TREATMENT AT HIGH TEMPERATURE**

**TECHNICAL FIELD**

5

The invention relates to the bleaching of chemical paper pulps, in particular kraft or sulphite pulps.

10

In the context of the present invention, it has been demonstrated that the implementation of an ozone treatment, carried out at high temperature at the end of the bleaching sequence, served in particular to increase the brightness of the pulp, without reducing its quality.

**PRIOR ART**

15

In the method for producing bleached chemical paper pulps, a first phase called delignification consists in removing most of the lignin present in the pulp. This operation, conventionally carried out by chemical treatment with oxygen (O), is inherently accompanied by a bleaching of the pulp, due to the depletion of brown lignin.

20

The next phase, called bleaching, consists in removing the residual lignin completely, so as to retain only the perfectly white "carbon hydrates" fraction (cellulose and hemicellulose).

25

In general, chemical paper pulps are bleached using a succession of treatments, called a bleaching sequence, employing reagents such as chlorine dioxide (D), hydrogen peroxide (P), caustic soda (E) and again oxygen (O).

30

For example, a modern and simple method for producing bleached chemical pulp may comprise all of the four ODED stages.

35

Bleaching performance can be improved either by adding further stages, or by reinforcing the E stages by adding oxygen (O) or hydrogen peroxide (P). Thus, methods for producing bleached chemical pulp of the type OD(EO)D, OD(EP)D, OD(EO)DED, OD(EO)DP, D(EO)D(EP)D etc. are also found in the industry.

Since 1992, ozone (Z) has been added to the list of reagents used in chemical pulp bleaching. Ozone is a highly effective oxidizing agent for lignin. However, it is a reagent

- 2 -

that decomposes rapidly in aqueous medium, and which may partially oxidize the cellulose, requiring very accurate control of the operating conditions of its use.

5 This has been done in the thirty plants in the world which have introduced ozone stages into their bleaching sequence. Various sequences are implemented, in which the ozone stage is always positioned at the start of the bleaching, that is in general after the delignification with oxygen as, for example, in the OZED, OZDED, OZDED methods. In other words, the ozone treatment takes place before alkaline extraction (E) which may assume the E or EOP or EO or EP form.

10

Several investigations have been conducted to identify the operating conditions promoting the bleaching action by ozone in this type of method.

15 Thus, in the review TAPPI JOURNAL of January 1992, an article entitled "*A survey of the use of ozone in bleaching pulps*" by N. Liebergott *et al.* summarizes the conditions in which ozone must be used for bleaching pulps. It is described therein in particular that to obtain the best bleaching, the pH of the medium must be acidic, preferably about 2, and above all, that the temperature must also be as low as possible, close to 20°C, to prevent excessive decomposition of the ozone, thereby achieving a better degradation of the lignin. According to this teaching, the ozone treatment is therefore carried out in the early  
20 bleaching steps, called prebleaching, at a low temperature.

In more recent articles, like the one published in the review TAPPI JOURNAL of September 1997 (Vol. 80, No. 9, pp 209-14), it has been proposed to use ozone at the end  
25 of bleaching. The application of an ozone stage on an incompletely bleached pulp, and therefore containing residual lignin, causes the virtually instantaneous disappearance of this lignin, resulting in a rapid increase in the brightness of the pulp. Although the method described is spectacular, it only serves to gain 2 to 3 percentage points of brightness in most cases, if one wishes to avoid applying too much ozone and degrading  
30 the quality of the cellulose. In light of the prior teachings, the experiments reported have been performed taking care to avoid raising the temperature excessively.

Document WO 2005/059241 also reports an ozone treatment carried out between 20 and 60°C, but before the alkaline extraction, and necessarily associated with a prior  
35 acidification step at very high temperature. It also discourages exceeding these temperatures, because above this level, a degradation of the pulp is reported (loss of viscosity) and a decrease in efficiency.

## SUMMARY OF THE INVENTION

The present invention seeks to propose a more efficient ozone treatment, without increasing the quantity of ozone to be introduced nor damaging the material treated.

5

Thus, according to one aspect the present invention relates to a method for treating a prebleached chemical pulp, comprising a step of ozone treatment of the said pulp, carried out at high temperature.

10 In fact, it has been found surprisingly that if the temperature of the ozone treatment is raised above 20°C, the action of the ozone is more effective, contrary to the teachings of the prior art, which indicated that the higher the temperature, the lower the ozone activity.

According to another aspect of the present invention, this step is advantageously carried out at a temperature above 60°C, advantageously above 65°C and even more advantageously above or equal to 70°C.

15 According to a preferred embodiment, the ozone treatment is carried out at a temperature of between 80 and 90°C. In practice, a temperature of about 80°C is preferable, in order to take advantage of the invention without compromising the energy balances of the plant and without having to work under pressure.

Preferably, the ozone treatment is carried out at a temperature not exceeding 100°C.

25 According to another aspect the present invention provides a method for treating a prebleached chemical pulp comprising a step of ozone treatment of the said pulp, carried out at a temperature above 60°C.

30 Chemical paper pulps which are intended for treatment using the method according to the invention, are hardwood and softwood pulps, and also non-wood pulps such as annual plants. The method of the invention also serves to treat pulps after kraft, sulphite and soda

cooking.

The method according to the invention is carried out after the delignification phase and after the first conventional steps of the bleaching sequence. It is therefore carried out on a  
5 pulp called a prebleached pulp.

More precisely, the fact that a chemical pulp is prebleached can be evaluated according to its level of brightness and/or its residual lignin content.

10 Thus, the inventive method is advantageously carried out on a pulp of which the brightness level is above 70%, advantageously above 80%, and preferably close to 85%. The brightness level is determined according to standard NF ISO 3688.

5 A second criterion concerning the choice of prebleached pulps to be treated with the inventive method is the residual lignin content. Advantageously, the inventive method is carried out on a pulp of which the kappa number, correlated with the residual lignin content of the pulp, is lower than 2.5, advantageously lower than 2, and preferably lower than 1. These values should be compared with the kappa number of unbleached pulps which is generally between 20 and 30. The standard used for the kappa number is standard NF ISO 302.

10 The inventive method is advantageously carried out on pulps meeting at least one of these two criteria (brightness and kappa number), or even both.

15 According to one embodiment, the ozone treatment is the only step of the inventive method and therefore the final step of the treatment of the pulp. The ozone treatment is accordingly part of a more complex production method, of the type of those mentioned previously, containing stages with oxygen, with chlorine dioxide, with caustic soda, with hydrogen peroxide and optionally with ozone. For example, a complete sequence integrating the inventive method is of the type ODEDZ\*, ODEDPZ\*, OZEDZ\*, where Z\*

20 is the treatment according to the invention. It clearly appears that the inventive method advantageously implementing on pulps at the end of treatment, and having in particular undergone an upstream alkaline extraction (E).

25 Contrary to the prior art, no requirement exists concerning a prior treatment of the pulp, particularly a prior high temperature acidification.

30 Alternatively, the inventive method comprises an ozone treatment step as described and at least one subsequent bleaching step. It then concerns a new ozone treatment (Z\*) or a treatment with hydrogen peroxide (P), with chlorine dioxide (D), with caustic soda (E) and/or with oxygen combined with hydrogen peroxide (OP). The final bleaching treatments, which are the subject matter of the inventive method, may therefore be varied.

35 Due to the small quantity of residual lignin in the chemical pulp to be treated, the ozone treatment of the invention is only carried out with small quantities of ozone: less than 5 kg of ozone per tonne of dry pulp (or 0.5% by weight), preferably less than 2 kg of ozone per tonne (or 0.2% by weight). These moderate quantities reduce the risk of oxidizing the cellulose in a manner detrimental to its quality.

- 5 -

Advantageously, the minimum proportion of ozone introduced is 0.01% or 0.05% by weight of dry pulp (0.1 kg and 0.5 kg of ozone per tonne of pulp, respectively).

5 In the context of the invention, the pH of the pulp to be treated is not a problem because the ozone treatment step can take place at a pH of between 2 and 10. In particular, it has been demonstrated that the invention was equally advantageous at neutral pH, close to 7. Insofar as a prior acidification is not required, the inventive method may take place at a pH equal to or higher than 4. Due to the considerable advantage of being able to work at neutral pH (no addition of sulphuric acid, less corrosive liquor), the ozone treatment is  
10 advantageously carried out at a pH of between 4 (natural pH of the pulp after treatment with chlorine dioxide) and 8 (pH close to that of pure water).

Particularly due to the wide range of acceptable pH, the ozone treatment of the invention can be carried out directly after the final step of the sequence used for the prior bleaching  
15 (prebleaching), and therefore without intermediate washing. This may be the case, for example, when the final stage is a treatment with chlorine dioxide.

The method according to the invention, particularly the ozone treatment step, can be carried out on pulps having a wide range of consistency, corresponding to the mass ratio  
20 between the pulp and the mixture (pulp + water). Advantageously, the ozone treatment is carried out on a pulp with a consistency of between 1 and 45%, and more precisely between 2 and 3% when the low consistency technology is used, between 3 and 12% when the medium consistency technology is used, and between 35 and 40% when the high consistency technology is used.

25 The ozone treatment method according to the present invention is particularly suitable for kraft pulps or sulphite pulps.

30 As already stated, a more efficient ozone treatment is observed in the conditions of the invention, without increasing the quantity of ozone to be introduced nor damaging the treated material.

35 Characteristically, it has been observed that for certain types of hardwood pulps (deciduous), this treatment further served to remove the residual compounds of the "pitch" type, and thereby to improve the cleanliness of the bleached pulp.

**EMBODIMENTS**

The invention and its advantages will appear more clearly from the following exemplary embodiments, in conjunction with the appended figures. However, these are non-limiting.

5 Figure 1 shows the effect of temperature on the bleaching by ozone applied at the end of the bleaching sequence on a mixed hardwood kraft pulp.

Figure 2 shows the effect of the temperature of the final bleaching treatment by ozone on the degree of polymerization of the cellulose in the case of a mixed hardwood kraft pulp.

10 Figure 3 shows the effect of temperature on the bleaching by ozone applied at the end of a bleaching sequence on a softwood kraft pulp.

**EXAMPLE 1**

15 A softwood kraft pulp is treated in a known manner, having a residual lignin content corresponding to a kappa number close to 20, using a prebleaching D(EP)D sequence. The brightness obtained is 83.7% ISO.

20 This pulp, after washing with water and acidification with sulphuric acid up to pH 2.7, is subjected to an ozone treatment, with a consistency of 35%, in a conventional laboratory device consisting of a rotating glass reactor in a water bath having a variable temperature between 20 and 80°C.

A quantity of ozone close to 0.2% was progressively added to the pulp.

25 After this treatment, the pulp was washed and its brightness measured by the usual standard methods.

30 The results obtained are shown by the curve in Figure 1. They clearly show that the increase in the temperature of the Z stage improves the result of the bleaching, contrary to the teaching of the prior art, according to which, for example, the result at 80°C should be poorer than that at 20°C. However, it was observed that increasing the temperature above 80°C was not advantageous.

35 It is also interesting to observe in this example that the increase in efficiency of the ozone stage is not accompanied by a significant drop in the quality of the cellulose, of which the

- 7 -

degree of polymerization (measured according to standard NF ISO 5351 after reduction with sodium borohydride) remains at very good levels. This is illustrated in Figure 2.

**EXAMPLE 2**

5

A softwood wood kraft pulp is treated in a known manner, having a residual lignin content corresponding to a kappa number close to 27, with a DEDED bleaching sequence. The brightness obtained is 81.9% ISO.

10 This pulp, after washing with water, had a pH close to 7. It was then subjected to an ozone treatment, with a consistency of 35%, in the same device as in example 1.

A quantity of ozone of 0.19% was progressively added to the pulp. After this treatment, the pulp was washed and its brightness measured by the usual standard methods.

15

The results of the bleaching by this final ozone stage are shown in Figure 3. They are similar to those obtained in example 1. This is particularly remarkable because the pH of the treatment is 7, and this, according to the teaching of the prior art, should lead to a rapid decomposition of the ozone and hence its loss of efficiency.

20

In this example, it appears that the ozone treatment performance should be even better at a temperature above 80°C. However, the application of a temperature above 80°C may penalize the heat balance of the pulp plant.

**EXAMPLE 3**

25

The same pulp as in the previous example was partially bleached by the DEDED sequence, in order to obtain a brightness of 81.9.

30 Contrary to example 2, the pulp was not washed after the final D stage, but directly thickened to a consistency of 35%. Its pH was then close to 4.

The ozone treatment according to the invention at a temperature of 80°C was applied to this pulp up to an ozone consumption of 0.19%.

35

A brightness of 89% ISO was obtained, representing the same result as in example 2, in which washing had been carried out after the D stage.

Throughout this specification and the claims which follow, unless the context requires otherwise, the word "comprise", and variations such as "comprises" or "comprising", will be understood to imply the inclusion of a stated integer or step or group of integers or steps but not the exclusion of any other integer or step or group of integers or steps.

5

The reference in this specification to any prior publication (or information derived from it), or to any matter which is known, is not, and should not be taken as, an acknowledgement or admission or any form of suggestion that that prior publication (or information derived from it) or known matter forms part of the common general knowledge in the field of endeavour to which this specification relates.

10

**The claims defining the invention are as follows:**

1. Method for treating a prebleached chemical pulp comprising a step of ozone treatment of the said pulp, carried out at a temperature above 60°C.  
5
2. Method for treating a prebleached chemical pulp according to claim 1 wherein the ozone treatment step is carried out at a temperature of above 65°C.
3. Method for treating a prebleached chemical pulp according to claim 1 wherein the ozone treatment step is carried out at a temperature of above or equal to 70°C.  
10
4. Method for treating a prebleached chemical pulp according to Claim 1, wherein the ozone treatment step is carried out at a temperature of between 80 and 90°C, advantageously close to 80°C.  
15
5. Method for treating a prebleached chemical pulp according to any one of the preceding claims, wherein the prebleached chemical pulp has a brightness level above 70%, advantageously above 80%, and preferably close to 85%.
- 20 6. Method for treating a prebleached chemical pulp according to any one of the preceding claims, wherein the prebleached chemical pulp has a residual lignin content corresponding to a kappa number lower than 2.5, advantageously lower than 2, and preferably lower than 1.
- 25 7. Method for treating a prebleached chemical pulp according to any one of the preceding claims, wherein the quantity of ozone used in the ozone treatment step is between 0.01 and 0.5% by weight, advantageously between 0.05 and 0.2% by weight of dry pulp.
- 30 8. Method for treating a prebleached chemical pulp according to any one of the preceding claims, wherein the ozone treatment step is carried out at a pH of

between 2 and 10, advantageously between 4 and 8.

- 5
9. Method for treating a prebleached chemical pulp according to any one of the preceding claims, wherein the ozone treatment step is carried out on a pulp with a consistency of between 1 and 45%.
- 10
10. Method for treating a prebleached chemical pulp according to any one of the preceding claims, wherein the ozone treatment step is carried out directly after the final prebleaching step, without intermediate washing.
- 10
11. Method for treating a prebleached chemical pulp according to any one of the preceding claims, wherein the chemical pulp is a kraft or sulphite pulp.
- 15
12. A method for treating a prebleached chemical pulp substantially as hereinbefore described with reference to the examples.




Figure 1




Figure 2




Figure 3