

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
1 March 2007 (01.03.2007)

PCT

(10) International Publication Number
WO 2007/023009 A2

(51) International Patent Classification:
C08L 1/02 (2006.01) *C08K 3/36* (2006.01)
C08L 97/02 (2006.01)

(74) Common Representative: **DEGUSSA AG**; Intellectual
Property Management, Patente & Marken, Bau 1042 - PB
15, 45764 Marl (DE).

(21) International Application Number:
PCT/EP2006/063206

(22) International Filing Date: 14 June 2006 (14.06.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10 2005 040 683.1 26 August 2005 (26.08.2005) DE
10 2006 006 655.3
14 February 2006 (14.02.2006) DE

(71) Applicant (for all designated States except US): **DE-
GUSSA AG** [DE/DE]; Bennigsenplatz 1, 40474 Düssel-
dorf (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **JENKNER, Peter**
[AT/DE]; Ritterstrasse 16 a, 79618 Rheinfelden (DE).
STANDKE, Burkhard [DE/DE]; Chrschonastrasse
25, 79540 Lörrach (DE). **MONKIEWICZ, Jaroslaw**
[PL/DE]; Burstelstrasse 2 a, 79618 Rheinfelden (DE).
EDELMANN, Roland [DE/DE]; Hallwilstrasse 12,
79618 Rheinfelden (DE). **KHARAZIPOUR, Alireza**
[DE/DE]; In der Straut 10 b, 37079 Göttingen (DE).
KLOESER, Lars [DE/DE]; Valentinsbreite 5, 37077
Göttingen (DE).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU,
LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG,
NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD,
SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA,
UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT,
RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA,
GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished
upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: CELLULOSE- OR LIGNOCELLULOSE-CONTAINING COMPOSITE MATERIALS BASED ON A
SILANE-BASED COMPOSITE AS A BINDER

(57) Abstract: The present invention relates to a composite material based on (a) a cellulose- or lignocellulose-containing material and (b) a composite as a binder, the composite resulting from the reaction of at least the components (i) a glycidylxypropylalkoxysilane, (ii) an aqueous silica sol having a solids content of > 20% by weight, (iii) an organic acid as a hydrolysis catalyst and (iv) n-propyl zirconate, butyl titanate or titanium acetylacetonate as a crosslinking agent. The present invention furthermore relates to a process for the production of said composite materials and the use of a composite (b) as a binder for the production of wood-based materials.



WO 2007/023009 A2

Cellulose- or lignocellulose-containing composite materials based on a silane-based composite as a binder

The present invention relates to composite materials based on cellulose- or lignocellulose-containing materials and organosilicon compounds as a binder, a process for the production thereof and the use of special organosilicon compounds or a solution thereof.

Organosilicon compounds are used in the form of various silanes, their reaction products or corresponding formulations in the production of composite materials in particular those based on natural or near-natural fibers, i.e. cellulose- or lignocellulose-containing materials.

Wood-based materials comprise up to about 20% of binder and other additives. The most frequently used binder worldwide for wood-based materials is urea-formaldehyde resin (UF resin).

However, formaldehyde resin-bound wood-based materials have a continuous formaldehyde emission which, in spite of compliance with guidelines (EN 120 and DIBt guideline 100, class E1 = 0.1 ppm), appears problematic from the point of view of consumer protection since many studies have shown that formaldehyde not only affects the central nervous system but can also cause carcinomas. Very recently, there have been increased demands for a further reduction in the permissible formaldehyde concentrations.

Furthermore, wood-based materials glued with UF resin have a comparatively low heat and moisture resistance which prevents use for most special areas, for example for load-bearing and high-strength purposes and for the outdoor sector.

In addition to UF resins, about 10% of phenol-formaldehyde resin (PF resin) is also used for the production of wood-based materials.

Organic isocyanates are used in a small proportion in the wood-based materials industry for materials having good mechanical and water-resistant properties. Diphenylmethane diisocyanate (PMDI) is mainly used. In contrast to the systems described before, the isocyanates form chemical compounds with the wood,
5 demonstrably with lignin and cellulose.

However, the use of PMDI as a binder has a large number of disadvantages. In its regard to application technology, the affinity to metal is a cause for complaint since PMDI-glued particles and fibers can adhere to the press belts during the hot-
10 pressing. For this reason, it is necessary to work with expensive, specially coated press belts.

Moreover, stringent work safety measures have to be provided and complied with when handling PMDI.

15 Binders or binder systems for natural or near-natural wood-based materials, such as, for example, potato pulp (EP 0 613 906 A1, DE 43 06 441 A1, DE 43 40 517 A1, DE 434 518 A1), do not ensure an effect in compliance with standards for every application (in this context, cf. also "Enzyme von Weißfäulepilzen als Grundlage für
20 die Herstellung von Bindemitteln für Holzwerkstoffe [Enzymes of white-rot fungi as a basis for the preparation of binders for wood-based materials]" by A. R. Kharazipour, vol. 121, JD. Sauerländers Verlag, Frankfurt am Main, ISBN 3-7939-5124-3).

DE 100 37 724 A1 discloses a process for the production of composite materials
25 from organic substances using a binder based on hydrogen-, alkyl-, alkenyl-, phenyl-, glycidylalkyl-, acryloyloxyalkyl- and methacryloyloxyalkyl-functional siloxanes.

DE 196 47 369 A1 relates to composite materials based on glass fibers, mineral fibers or wood-based materials, the binder used being a so-called nanocomposite
30 which is prepared by the sol-gel process and is based, inter alia, on colloidal inorganic particles and one or more hydrolyzable organosilanes. The silanes used

may carry chloride, alkoxy, acetoxy, alkyl, alkenyl, aryl, glycidyoxyalkyl and methacryloyloxyalkyl groups as functional groups.

Furthermore, WO 98/22536 discloses composite materials based on plant materials, where, over and above the recommendation of DE 196 47 369 A1 for the polysiloxane of the sol-gel system, alkynyl, alkacryloyl and arylalkylene groups which optionally may also have one or more substituents, such as halogen, alkoxy, hydroxyl, amino or epoxide groups, are mentioned as possible radicals which cannot be hydrolytically eliminated, in addition to alkyl and alkenyl groups. Furthermore, according to WO 98/22536, pure methyltriethoxysilane or a mixture of methyltriethoxysilane and tetraethoxysilane can be used as a binder for the production of a composite material.

A substantial disadvantage of the abovementioned system is that hydrolyzable alkoxides are also used. These have a vapor pressure which is not negligible and moreover eliminate alcohol as a hydrolysis product. This leads in practice on the processing machines customary in particle board work to a considerable odor and to a hazard due to explosive vapors.

EP 0 716 127 B1 and EP 0 716 128 B1 disclose water-based aminoalkyl-/alkyl/hydroxyl- or alkoxysiloxane containing compositions which are used, inter alia, for imparting water repellency to textiles, leather, cellulose products and starch products. Such aminoalkylorganohydroxysiloxanes soluble in water or water/alcohol mixtures are also referred to as hydrosil systems. Fluoroalkyl-functional hydrosil systems are disclosed, for example, in EP 0 846 716 B1, EP 0 846 717 B1 and EP 1 101 787 A2.

The German patent application 10 2004 037 045.1 relates to aqueous silane nanocomposites, these being used in the coating of substrate surfaces, such as those of paper, board, wood, pressboard, plastic, lacquer coats, stone, ceramic, metal or metal alloys.

The object of the present invention was to provide cellulose- or lignocellulose-containing composite materials which are based on a further binder.

5 The object is achieved, according to the invention, in accordance with the information of the patent claims.

Thus, it was surprisingly found that novel composite materials having substantially improved properties, based on (a) at least one cellulose- or lignocellulose-containing material and (b) a composite as a binder, the composite (also referred to below as
10 nanocomposite or as binder for short) resulting from the reaction of at least the components

- (i) a glycidyloxypropylalkoxysilane,
- (ii) an aqueous silica sol having a solids content of > 20% by weight,
- (iii) an organic acid as a hydrolysis catalyst and
- 15 (iv) n-propyl zirconate, butyl titanate or titanium acetylacetonate as a crosslinking agent,

are obtainable in a simple and economical manner by

- treating dried or moist cellulose-or lignocellulose-containing material with
- 20 - a composite according to (b),
- bringing the cellulose or lignocellulose material treated in this manner into a desired form and then hot-pressing it.

The present results showed that a composite according to (b) can now also be used
25 as a binder for the production of composite materials.

Moreover, composite materials according to the invention can advantageously contain at least one further component (c), such as, for example, paraffin- or wax-based water repellants, flameproofing agents, e.g. polyphosphates, and biocidal
30 substances and fragrances – to mention but a few.

Composite materials according to the invention are as a rule advantageously distinguished by a substantially improved transverse tensile strength compared with other comparable composite materials.

- 5 Moreover, in contrast to UF-, PF- or MF-glued composite materials, composite materials according to the invention emit no harmful formaldehyde vapors.

Furthermore, the production of composite materials glued according to the invention, in particular wood-based materials is possible with a substantially reduced
10 processing risk and drastically reduced health-relevant risks compared with the PMDI-bound wood-based materials, properties of the products produced being identical or better.

The present invention therefore relates to composite materials based on (a) at least
15 one cellulose- or lignocellulose-containing material and (b) a composite as a binder, the composite resulting from the reaction of at least the components

- (i) a glycidyloxypropylalkoxysilane,
- (ii) an aqueous silica sol having a solids content of > 20% by weight,
- (iii) an organic acid as a hydrolysis catalyst and
- 20 (iv) n-propyl zirconate, butyl titanate or titanium acetylacetonate as a crosslinking agent.

Composite materials according to the invention are advantageously characterized by a solids content of the composite (b) of from 0.04 to 15% by weight, preferably from
25 3 to 12% by weight, in particular from 4 to 9% by weight, based on the absolutely dry cellulose or lignocellulose material.

Composite materials according to the invention are preferably characterized by (a) at least one natural or near-natural cellulose- or lignocellulose-containing material from
30 the series consisting of industrial wood, forestry industry timber, used or recycled wood, wood particles, woodchips, wood fibers, wood wool, wood dust, sawdust,

planing chips, cutting chips, slabs, veneer wastes, splinters, particle materials from annual plants, e.g. cereal straw, rice straw, hemp shavings or cotton straw, or a mixture of at least two of the above mentioned materials.

- 5 Cellulose- or lignocellulose-containing fiber material advantageously originates from hardwood and softwood, palm fibers, e.g. coconut fibers, and annual plants, such as cereal straw, rice straw, cotton, jute and hemp – to list but a few.

Composites (b) used in the present invention are described in detail in German
10 patent application 10 2004 037 045.1. The total content of the German patent application is hereby incorporated in the disclosure of the present application.

Thus, a composite (b) can be obtained by mixing at least (i) a
glycidyoxypropylalkoxysilane, (ii) a colloidal, aqueous silica sol having a solids
15 content of > 20% by weight, preferably > 30% by weight, (iii) an organic acid as a hydrolysis catalyst, in particular acetic acid, propionic acid or maleic acid, and (iv) zirconium tetrapropylate [also referred to as n-propyl zirconate: $\text{Zr}(\text{O}-\text{C}_3\text{H}_7)_4$], butyl titanate, in particular n-butyl titanate [$\text{Ti}(\text{O}-\text{C}_4\text{H}_9)_4$] or titanium acetylacetonate as a crosslinking agent. In addition, the alcohol hydrolysis product can be removed
20 substantially, i.e. to an extent of from < 5% by weight down to residual amounts in the region of the limit of detection, from such a hydrolysis product, in particular in the case of toxic methanol, and, if required, can be quantitatively replaced by water.

A composite (b) comprising a component (i) from the series consisting of 3-
25 glycidyoxypropyltrimethoxysilane, 3-glycidyoxypropyltriethoxysilane, 3-glycidyoxypropylmethyldimethoxysilane, 3-glycidyoxypropylmethyldiethoxysilane or a mixture of at least two of the abovementioned silanes is preferably selected for composite materials according to the invention.

30 A generally cationic colloidal silica sol having a solids content of from > 20 to 50% by weight, particularly preferably from 30 to 50% by weight, in particular from 40 to

- 50% by weight, i.e. about 45% by weight, is preferred as component (ii), the solids content being determined according to DIN EN ISO 3251. In particular, preferred aqueous silica sols have a pH of from 3 to 5, in particular from 3.5 to 4. However, it is also possible to use alkali-stabilized silica sol. The determination of the particle size distribution can be effected in the manner known per se by means of laser diffraction (Coulter LS particle size meter). Furthermore, in addition to amorphous, aqueous SiO₂ particles, silica sols used according to the invention may also contain further sol-gel-forming, aqueous element oxides, such as aluminum oxides or silicon/aluminum oxides. In addition, preferred silica sols contain as a rule amorphous, aqueous oxide particles having an average particle size of from 40 to 400 nm, for example – but not exclusively – Levasil 200S/30% and Levasil 100S/45%. The pH can be determined in a manner known per se, for example by means of pH paper or pH sticks.
- 15 Furthermore, an organic acid from the series consisting of acetic acid, propionic acid and maleic acid is preferred as component (iii). Thus, a composite (b) preferably contains from 0.01 to 3% by weight of component (iii), particularly preferably from 0.5 to 2% by weight, in particular from 1 to 2% by weight based on the composite.
- 20 The crosslinking agent according to component (iv) can be used as a powder or in alcoholic solution in the production of the composite. Composites used according to the invention are preferably based on a content of component (iv) of from 0.5 to 8% by weight, based on the composite (b).
- 25 A tetraalkoxysilane, in particular tetraethoxysilane, at least one alkylsilane, suitably an alkylalkoxysilane, in particular dimethyldiethoxysilane or methyltrimethoxysilane, and/or a phenyltrialkoxysilane, in particular phenyltriethoxysilane or phenyltrimethoxysilane, can also advantageously be used as further component (v) for binders (b) used according to the invention. Thus, a composite may contain component (v) in an amount of from 1 to 10% by weight, based on the composite. A
- 30

proportion of component (ii) is suitably and correspondingly replaced by component (v).

Composites (b) used according to the invention are as a rule slightly turbid to opalescent liquids and may contain sol particles having a mean diameter of from 40 to 200 nm, preferably from 50 to 100 nm. The determination of the diameter of the sol particles can be effected in a manner known per se, for example by use of laser diffraction.

Said composites (b) have, as a rule, a solids content of from > 40 to < 60% by weight, preferably from 45 to 55% by weight, in particular from 45 to 50% by weight, based on the total composition. The solids content of binders present is suitably determined on the basis of DIN ISO 3251. Furthermore, the solids content and the viscosity of composites present can be adjusted by adding water. Advantageously, the addition of water is advantageously such that a solids content of about 50% by weight is present.

In addition, binders used according to the invention are distinguished by a comparatively low content of alcohol hydrolysis product of < 5% by weight, preferably < 3% by weight, based on the composite. The alcohol content in a composite can be determined, for example, by gas chromatography in a manner known per se.

The composite (b) may also contain a particularly suitable organic solvent, preferably $\leq 10\%$ by weight of 1-methoxypropan-2-ol, in addition to or instead of water.

Thus, binders (b) present can also advantageously contain $\leq 10\%$ by weight, preferably from 5 to 10% by weight, based on the composite, of 1-methoxypropan-2-ol. Such systems are also distinguished as a rule by a high flashpoint.

Binders used according to the invention have, as a calculation parameter, preferably a water content of from about 70 to 30% by weight, particularly preferably from 65 to 50% by weight, based on the composite. At a proportion of about 50% or more of water as solvent, as a rule the content of "nonvolatile fractions" is determined in such a binder. The determination is usually effected by evaporating the water and alcohol according to DIN EN ISO 3251 – "Determination of the content of nonvolatile fractions". For this purpose, the binder is as a rule conditioned in a disposable aluminum dish for 1 hour at 125°C and the content of nonvolatile fractions is determined by differential weighing. Relative values are determined by this method. Thus, in the case of a composite (b), a content of nonvolatile fractions of from 45 to 50% by weight is particularly preferred.

Furthermore, so-called hydrosil systems can be added to a nanocomposite (b) used according to the invention.

Here, hydrosil systems are understood as meaning substantially water-based, chloride-free, predominantly slightly acidic, aqueous system which contain a mixture of water-soluble, virtually completely hydrolyzed (fluoro)alkyl-/aminoalkyl-/hydroxyl- (or alkoxy-) siloxanes, as disclosed, for example, in EP 0 716 127 A, EP 0 716 128 A, EP 0 846 717 A, EP 1 031 593 A and EP 1 101 787 A. An addition of DYNASYLAN® F 8815 to a binder (b) present in the weight ratio of from 1:0.01 to 0.01:1, particularly preferably from about 1:0.1 to 0.1:1, is particularly advantageous, the aqueous DYNASYLAN® F 8815 used here preferably having an active substance content of < 40% by weight, particularly preferably from 0.1 to 20% by weight, in particular from about 13 to 15% by weight, based on the composite and determined according to DIN EN ISO 3251, as described above. Composites obtained in this manner are advantageously distinguished on application by strongly hydrophobic and oleophobic properties (also referred to as "easy to clean") of the coating.

Water, methanol, ethanol and/or 1-methoxypropan-2-ol may be used as diluents in composites present.

Furthermore, a hydrosil, preferably one comprising a fluoro-functional active substance can be added to the binder or composite (b) present. In particular, a hydrosil concentrate in an amount of from 13 to 15% by weight, calculated as active substance and based on the subsequent binder composition, is added with thorough
5 mixing.

The present invention furthermore relates to a composite material which is obtainable by

- bringing dried or moist cellulose- or lignocellulose-containing material (a)
- 10 - into contact with a composite (b),
- bringing the cellulose or lignocellulose material treated in this manner into a desired form and then hot-pressing it.

The so-called "absolutely dry wood mass" is determined as a rule by treating the
15 cellulose- or lignocellulose-containing material at 103°C to constant weight, cf. in this context DIN 53 183 and EN 322.

Moist cellulose- or lignocellulose-containing material, for example in the form of wood fibers, can have a wood moisture content (also referred to below as moisture
20 content for short) of more than 100%, based on absolutely dry wood mass, after the industrial process of defibrating in the so-called refiner. For example, freshly felled trunks have a moisture content of from 120 to 160%, depending on the tree species.

In the production of medium density fiber boards (MDF) by the so-called "blow line"
25 process, the fiber material used is as a rule not dried prior to application of glue but passes from the upstream defibration process in the still moist state directly into the blow line, in which the binder is added to the fibers. Only thereafter are the fibers dried in this state after application of glue. A moisture content from about 10 to 14% is preferably established and further processing to MDF is subsequently effected.

However, it is also possible to use already dried cellulose- or lignocellulose-containing material for production of composite materials.

Thus, for example in the production of MDF by the blender process, dried fibers, preferably those having a moisture content of from about 10 to 12%, are used. This material is as a rule subjected to application of glue in a mixer and then further processed to MDF. Here too the glue application step can be followed by an additional drying step, for example in a tubular dryer line.

In particle board production, the use of ready-dried particles, in particular those having a moisture content of from 2 to 5%, is furthermore preferred. The drying on this material used is predominantly effected in a tube-bundle or rotary dryer.

The present invention therefore also relates to a process for the production of a composite material according to the invention by

- treating dried or moist cellulose- or lignocellulose-containing material (a) with
- a composite according to (b),
- bringing the material treated in this manner into a desired form and then hot-pressing it.

When carrying out the process according to the invention, the cellulose- or lignocellulose-containing material (a) is preferably sprayed uniformly with the composite (b), preferably in a pneumatically or hydraulically initiated glue application apparatus.

Advantageously up to 15% by weight, preferably from 0.1 to 14% by weight, particularly preferably from 3 to 13% by weight, very particularly preferably from 5 to 12% by weight, of composite (b), based on absolutely dry cellulose or lignocellulose material, can be used.

Moreover, in addition to the components (a) and (b), at least one from the series consisting of the paraffins, waxes, flameproofing agents, dyes, pigments, biocidal substance and fragrances can be used as further component (c). A component (c) is advantageously used in an amount of up to 8% by weight, preferably from 0.01 to 5 7% by weight, based on absolutely dry cellulose or lignocellulose material.

For carrying out the process according to the invention, the apparatuses or plants known per se for the production of composite materials, in particular wood-based materials, can be used, such as, for example, continuously operating Controll plants 10 from Siempelkamp, Binos, Dieffenbacher or Metso – to mention but a few examples.

Suitable methods for the treatment of cellulose- or lignocellulose-containing material with a binder are, for example, brushing, roll-coating, spraying, dipping, flooding, spraying, application of glue by the blowline method or application of glue in a mixer 15 (blender method using apparatuses from, for example, Lödige, Drais or Binos).

The cellulose- or lignocellulose-containing material can particularly advantageously be sprayed with a component (b) as a binder in a rotating drum (circulation process) preferably carried out at room temperature or with cooling at about 10°C) by means 20 of a glue application apparatus operated with compressed air, for example a glue application gun, which suitably has an operating pressure of from 0 to 4 bar abs. As a rule a material to which glue has been substantially uniformly applied is obtained in this manner.

25 In the process according to the invention the glue application can moreover advantageously be carried out on a pilot or industrial scale, but also in a trough mixer, plowshare mixer or blender mixer or by the blowline process.

Furthermore, in the process according to the invention, the cellulose or 30 lignocellulose material treated in this manner at ambient temperature can advantageously be scattered to give a cake, i.e. in particular a particle cake or matt,

combed, and pressed at a temperature of up to 250°C, preferably from 150 to 210°C, and a pressure of up to 9 N/mm², preferably from 4 to 7 N/mm², and for a time of up to 300 s per mm of the desired board thickness, preferably from 5 to 60 s/mm, particularly preferably from 8 to 40 s/mm.

5

However, other shaped articles, for example extrudates or cuboid parts or special shaped articles, can be produced from such a cake or from cellulose or lignocellulose material to which glue has been applied according to the invention.

- 10 However, it is furthermore possible for an existing cake or material to which glue has been applied first to be prepressed or precompacted, for example with a preliminary pressure of from 0.2 to 0.6 N/mm². In addition, material to which glue has been applied, in particular a cake, can be preheated before, during or after the prepressing, i.e. before the actual pressing, for example to 60 to 80°. Such a
- 15 thermal and/or mechanical pretreatment of the cake or of the material to which glue has been applied before the actual pressing step can advantageously contribute toward a substantial improvement in the subsequent product quality.

- In addition, the shaped articles obtained in the shaping or pressing step can
- 20 advantageously be subjected to a postconditioning or ageing. Thus, for example, boards can be subjected to storage in a stack. Frequency heating, for example by means of microwave technology, can additionally be carried out.

- However, cooling is also possible, for example for from 20 to 30 minutes in a star
- 25 cooling turner.

The postconditioning can additionally contribute to standardization or uniformity in the composite materials.

- 30 Thus, composite materials according to the invention are obtained after the cooling, in particular particle boards, fiberboards, ultralight fiberboards (ULF), light

fiberboards (LBF), medium density fiberboards (MDF), high density fiberboards (HDF), OSB boards (oriented strand board = OSB), veneer boards, plywood boards, wood pellets, wood briquettes and industrial construction material comprising wood, so-called "engineered wood", such as laminated strand lumber (LSL), parallel strand
5 lumber (PSL) and laminated veneer lumbar (LVL). Abovementioned composite materials suitably have a bulk density of from 150 to 1200 kg/m³. The bulk density can be determined, for example, according to EN 323.

For obtaining the particle (cf. component (a)) three raw material varieties are used
10 nowadays in different proportions. About 57% of the required timber raw material are provided by industrial wood residues. Timber wastes from the wood treatment and processing industry are referred to as industrial timber residues. These include sawdusts, planing chips, cutting chips and slabs, but also residual rolls from the veneer industry. About a further 23% of the timber raw materials are obtained from
15 forestry industry timber. This is the classical raw material in the form of harvested trunks, which are processed in the particle board works to give woodchips or directly by means of long wood chippers to give particles. The third group of raw materials comprising used or recycled wood is about 20%. These are used products comprising solid wood, wood-based materials or composite materials having a
20 predominant wood content of more than 50% by mass. In the works, particles having defined dimensions are produced from the various raw material varieties by means of knife ring chippers, long wood chippers and hammer mills. After the particle material is present, it is dried as a rule to a moisture content of from 1.5 to 3% in tube-bundles or tubular drum dryers. Screening and classification are then
25 effected, the particle material being separated into top and middle layer particles and possible coarse particle material being separated off. The particles of the top and middle layer fraction can then be fed for glue application and pressed, for example, to give particle boards.

30 In industrial fiber production, industrial wood residues are generally also used as raw material, in addition to forestry timber. The previously debarked forestry timber

is comminuted together with the industrial wood residues in a chipper to give woodchips. These woodchips are as a rule digested by the "Asplund process" in steam at from 160 to 180°C under a pressure of from 8 to 12 bar. After this operation, the so-called plastification, the material enters a refiner. This consists of
5 two counter rotating grinding discs between which the material is defibrated. A constant pressure of about 11 bar prevails in the refiner. Owing to the mild digestion conditions, the wood is subject to few chemical changes. This leads to a light color of the fiber thus provided and a high efficiency.

10 Lignocellulose is generally understood as meaning the matrix component which is formed by the three major chemical wood ingredients, cellulose, hemicellulose and lignin. The incorporation of lignin (incrustation with lignin) leads as a rule to lignification of the cell wall and hence to improved mechanical stability and strength of terrestrial plants. Lignocellulose for use in the wood-based materials industry is
15 obtained predominantly in the form of fibers or particles. For example, lignocellulose fibers can be obtained from hardwoods and softwoods. Furthermore, some annual plants, such as cereal, flax or hemp, are also a suitable source for lignocellulose fibers.

20 Fibers can be obtained – as described above – by the Asplund process. There, the wood is first comminuted into woodchip and then digested at high temperatures and pressure and finally defibrated using a refiner (which consists of two counterrotating grinding discs) for obtaining the particles, as a rule wood in the form of woodchips is fed to so-called knife ring chippers and chipped therein to give particles having
25 defined dimensions.

In the process according to the invention, at least one natural or near-natural cellulose or lignocellulose-containing material from the series consisting of industrial wood, forestry industry timber, used or recycled wood, wood particles, woodchips,
30 wood fibers, for example from pinewood, wood wool, wood dust, particles, such as sawdusts, planing chips or cutting chips, slabs, veneer wastes, splinters, particle

material from annual plants, e.g. cereal straw, rice straw, hemp shavings or cotton straw, or a mixture of at least two of the abovementioned materials can advantageously be used according to component (a).

- 5 In the process according to the invention, a cellulose- or lignocellulose-containing material from plants from the series consisting of hardwood, softwood, coconut, in particular coconut fibers, cotton, flax scrapings, hemp scrapings, bargasse, jute, sisal, reed, rice straw or sealed straw is particular preferably used.
- 10 In general, the present invention is carried out as follows:
Cellulose or lignocellulose-containing material (a) is treated with a composite according to (b). If appropriate, further components are added to the material thus obtained, and the latter is introduced into a mold and cured in a manner known per se. For example, the material thus obtained can be scattered on the surface of a hot
15 press, combed and hot-pressed. During this procedure, the cellulose- or lignocellulose-containing material reacts with the binder present and water evaporates.

- Composite materials according to the invention, in particular wood-based materials,
20 comprising cellulose- or lignocellulose-containing material (a), can thus advantageously be produced using a composite (b) as a binder.

The present invention therefore also relates to the use of a composite (b) as a binder for the production of wood-based materials.

25

- In particular, the present binders are used for the production of particle boards, fiberboards, ultralight fiberboards, light fiberboards, medium density fiberboards, high density fiberboards, OSB boards, veneer boards, plywood boards, wood pellets, wood briquettes, "engineered wood", insulating materials, plant pots, for example
30 from red-rotting spruce wood, moldings, for example – but not exclusively – moldings for automotive interior trim.

The present invention shows that composites (b) are particularly suitable also as binders in the production of composite materials, in particular wood-based materials having good mechanical-technological properties. The production and use of these wood-based materials is moreover advantageously free of emissions which are harmful to health.

Examples

DYNASYLAN® VPS 4112 – bound one-layer particle boards

The particles used for the production of the particle boards were taken from the belt weigher in an industrial particle board work after drying and immediately before application of glue. They are divided into top layer fraction and middle layer fraction as a result of the process. The binder was finely atomized by means of a glue application gun from WALTHER PILOT in a rotating glue application drum by means of compressed air (from 0.2 to 1.2 bar) and added to the particles.

Thereafter, the particles were scattered to give a particle board cake and were hot-pressed. In the case of 3-layer particle boards, 40% of top layer material were used for the outer layers and 60% of middle layer material for the inner layer. One-layer particle boards produced consisted of 100% of middle layer material.

6 mm thick one-layer particle board having a required bulk density of 750 kg/m³ were produced from middle layer particles using the nanocomposite DYNASYLAN® VPS 4112 as a binder. In each case, 8.5% of DYNASYLAN® VPS 4112, based on absolutely dry particles, were applied as glue to the particle material. The particle boards were pressed at 210°C and for a pressing time of 40 s/mm. The results of the material test are summarized in table 1.

Table 1

Designation	Transverse tensile strength (N/mm ²)	Change of transverse tensile strength compared with EN 312-4 (0,45 N/mm ²) in %
VPS 4112	0.53	+18

The particle boards of all test series were able to fulfill EN 312-4 (0.45 N/mm²) and EN 312-5 (0.5 N/mm²). Thus, it was shown that the composite DYNASYLAN[®] VPS 4112 according to component (b) is also advantageously suitable as the sole binder

5 for particle boards.

Patent claims:

1. A composite material based on (a) at least one cellulose- or lignocellulose-
containing material and (b) a composite as a binder, the composite resulting
5 from the reaction of at least the components
 - (i) a glycidyloxypropylalkoxysilane,
 - (ii) an aqueous silica sol having a solids content of > 20% by weight,
 - (iii) an organic acid as a hydrolysis catalyst and
 - (iv) n-propyl zirconate, butyl titanate or titanium acetylacetonate as a
10 crosslinking agent.
2. A composite material according to claim 1, comprising a solids content of the
composite (b) of from 0.04 to 9% by weight, based on absolutely dry cellulose
or lignocellulose material.
15
3. A composite material according to claim 1 or 2, comprising a component (i) for
composite (b) from the series consisting of 3-glycidyloxypropyltrimethoxysilane,
3-glycidyloxypropyltriethoxysilane, 3-glycidyloxypropylmethyldimethoxysilane,
3-glycidyloxypropylmethyldiethoxysilane or a mixture of at least two of the
20 abovementioned silanes.
4. A composite material according to any of claims 1 to 3, comprising a colloidal
silica sol having a solids content of from > 20 to 50% by weight as component
(ii) for composite (b).
25
5. A composite material according to any of claims 1 to 4, comprising an organic
acid from the series consisting of acetic acid, propionic acid and maleic acid as
component (iii) for composite (b).
- 30 6. A composite material according to any of claims 1 to 5, comprising a content of
component (iv) for composite (b) of from 0.5 to 8% by weight, based on the
composition of the composite.

7. A composite material according to any of claims 1 to 6, comprising at least one tetraalkoxysilane, at least one alkylsilane and/or a phenyltrialkoxysilane as further component (v) for composite (b).
- 5 8. A composite material according to any of claims 1 to 7, comprising sol particles in the component (ii) for composite (b) which have a mean diameter of from 40 to 200 nm.
- 10 9. A composite material according to any of claims 1 to 8, comprising a solids content of from > 40 to $< 60\%$ by weight in the component (ii) for composite (b), based on the total composition of the composite.
- 15 10. A composite material according to any of claims 1 to 9, comprising a content of alcohol hydrolysis product in the composite (b) of $< 5\%$ by weight, based on the total composition of the composite.
- 20 11. A composite material according to any of claims 1 to 10, comprising a content of 1-methoxypropan-2-ol in the composite (b) of $\leq 10\%$ by weight, based on the total composition of the composite.
12. A composite material according to any of claims 1 to 11, comprising a water content in the composite (b) of from about 70 to 30% by weight, based on the total composition of the composite.
- 25 13. A composite material according to any of claims 1 to 12, comprising a content of at least one surfactant in the composite (b).
14. A composite material according to any of claims 1 to 14, comprising an addition of a hydrosil system to the composite (b) in the weight ratio of from 1:0.01 to 0.01:1, the hydrosil system used here preferably having an active substance content of $< 40\%$ by weight of said siloxanes.
- 30

15. A composite material according to any of claims 1 to 13, comprising
(a) at least one natural or near-natural cellulose- or lignocellulose-containing material from the series consisting of industrial wood, forestry industry timber, used or recycled wood, wood particles, woodchips, wood fibers, wood wool, wood dust, sawdusts, planing chips, cutting chips, slabs, veneer wastes, splinters, particle material from annual plant or a mixture of at least two of the abovementioned materials.
16. A composite material according to either of claims 1 and 15, a cellulose- or lignocellulose-containing fiber material originating from hardwood, softwood, palm fibers and annual plants.
17. A composite material according to any of claims 1 to 16, comprising at least one further component (c) from the series of the paraffin- or wax-based water repellants, flameproofing agents, dyes, biocidal substances and fragrances.
18. A composite material according to any of claims 1 to 17, obtainable by
- bringing dried or moist cellulose- or lignocellulose-containing material (a)
 - into contact with a composite according to (b),
 - bringing the cellulose or lignocellulose material treated in this manner into a desired form and then hot-pressing it.
19. A process for the production of a composite material according to any of claims 1 to 18, by
- treating dried or moist cellulose- or lignocellulose-containing material (a) with
 - a composite according to (b),
 - bringing the material treated in this manner into a desired form and then hot-pressing it.
20. A process according to claim 19, wherein the cellulose- or lignocellulose-containing material (a) is sprayed with the composite (b) in a rotating drum by

means of a glue application apparatus operated with compressed air.

- 5 21. A process according to claim 19 or 20, wherein up to 15% by weight of composite (b), based on absolutely dry cellulose or lignocellulose material, are used.
- 10 22. A process according to any of claims 19 to 21, wherein, in addition to the components (a) and (b) a wax in an amount of up to 8% by weight, based on absolutely dry cellulose or lignocellulose material, is used as further component (c).
- 15 23. A process according to any of claims 19 to 22, wherein the treated cellulose or lignocellulose material is scattered to give a cake, combed, and pressed at a temperature of up to 250°C and a pressure of up to 9 N/mm² and for a time of up to 300 s per mm board thickness.
- 20 24. A process according to any of claims 19 to 23, wherein cellulose or lignocellulose material which has been treated in this manner or to which glue has been applied in this manner is thermally and/or mechanically pretreated before the pressing step.
- 25 25. A process according to any of claims 19 to 24, wherein the shaped articles obtained in the shaping or pressing step are postconditioned.
26. The use of a composite (b) as a binder for the production of wood-based materials according to any of claims 1 to 18.