

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau

(10) International Publication Number

WO 2019/040407 A2

(43) International Publication Date
28 February 2019 (28.02.2019)

(51) International Patent Classification:

C07D 413/10 (2006.01) *C08K 3/013* (2018.01)
C07D 413/14 (2006.01) *C08K 3/04* (2006.01)
C08G 73/02 (2006.01) *C08K 3/22* (2006.01)
C08G 59/50 (2006.01) *C08K 3/32* (2006.01)
C08L 79/04 (2006.01) *C08K 7/14* (2006.01)

(74) Agent: DUNLEAVY, Kevin J.; MENDELSOHN DUNLEAVY, P.C., 1500 John F. Kennedy, Suite 312, Philadelphia, Pennsylvania 19102 (US).

(21) International Application Number:

PCT/US2018/047184

(22) International Filing Date:

21 August 2018 (21.08.2018)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

62/547,952 21 August 2017 (21.08.2017) US

(72) Inventors; and

(71) Applicants: PALMESE, Giuseppe R. [US/US]; 2 Cove Court, Hainesport, New Jersey 08036 (US). YADAV, Santosh K. [IN/US]; 4504 Pine Street, Apt. 1D, Philadelphia, Pennsylvania 19143 (US). LASCALA, John J. [US/US]; 611 Kilburn Road, Wilmington, Delaware 19803 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

(54) Title: RENEWABLE HIGHLY BIOBASED POLYBENZOXAZINE THERMOSETS FOR COMPOSITE APPLICATIONS




FIG. 12

(57) Abstract: Benzoxazine compounds, methods of making them, polymers made therefrom and methods of polymerizing the benzoxazines. These renewable benzoxazine monomers and polymers that utilize the variety of building blocks found in renewable plant biomass, demonstrate excellent processability and large temperature windows for processing of resin systems.

Declarations under Rule 4.17:

— *of inventorship (Rule 4.17(iv))*

Published:

— *without international search report and to be republished upon receipt of that report (Rule 48.2(g))*

RENEWABLE HIGHLY BIOBASED POLYBENZOXAZINE THERMOSETS FOR
COMPOSITE APPLICATIONS

STATEMENT OF GOVERNMENT INTEREST

5 This invention was made with government support under Contract Number W911NF-15-2-0017 awarded by the United States Army Research Laboratory. The Government has certain rights in this invention.

CROSS REFERENCE TO RELATED APPLICATIONS

10 This application claims the benefit of U.S. Provisional Application No. 62/547,952, filed on August 21, 2017, the entire disclosure of which is hereby incorporated by reference as if set forth fully herein.

FIELD OF THE INVENTION

15 The present invention relates to a series of the renewable benzoxazine monomers and polymers that utilizes the variety of building blocks found in renewable plant biomass, which demonstrate excellent processability and large temperature windows for processing of resin systems.

20 **BACKGROUND**

Benzoxazine monomers are the precursor for polybenzoxazine polymers [1]. Benzoxazines are a class of heterocyclic compounds based on a six-membered heterocycle bearing one oxygen and one nitrogen atoms fused to a single aromatic ring and typically synthesized through Mannich type condensation of phenols, amines (aliphatic or aromatic) and formaldehyde or formaldehyde precursors (i.e. paraformaldehyde) without any catalysts [1-3]. Polybenzoxazines possess unique advantages for example, low melt viscosity of the precursors, curing without a strong catalyst and nonvolatile release together with near-zero volumetric change during curing. The cured polybenzoxazines are characterized by high glass transition temperatures (Tg), low water absorption, high char yield, and excellent thermal and electrical properties [2]. Most of these outstanding properties are related to the presence of high density of inter- and intramolecular hydrogen bonding between the phenolic groups and the nitrogen containing Mannich-type bridges. Polybenzoxazines are an alternative to high-performance phenolic resins for high-temperature applications. The rising worldwide fossil fuel crisis and current health and environmental issues are the major challenges for polybenzoxazines in terms of supply and costs [2, 3]. Furthermore, petroleum does not easily afford a variety of chemical

structures or functionality. Recent research efforts have focused on developing renewable alternatives to replace the phenol and amine monomers in benzoxazines [4, 5]. Plants composed of cellulose, hemicellulose, lignin, triglycerides, and other natural chemicals in complex combinations to sustain life and to withstand environmental stress factors [6] may include the 5 needed components. These materials are characterized by distinct building blocks arranged and connected with appropriate chemical functionality so that the systems serve multiple needs such as chemical and microbial resistance, nutrient transport, energy, strength, and toughness. To overcome the limitations of petroleum-derived building blocks, we employed an approach to develop the renewable benzoxazine monomers and polymers inspired by nature that utilizes the 10 variety of building blocks found in renewable plant biomass [5, 7-14].


The present invention sets forth a series of new, highly bio-derived, benzoxazine polymers, which demonstrate improved processability and properties, making them good candidates for replacement of some petroleum-based polymers. These renewable biomass-based polymer systems may be used in tunable-property for various applications due to the ability to 15 combine different bio-based building blocks to yield polymers with the desired properties.

SUMMARY OF THE INVENTION

In accordance with the disclosure, exemplary embodiments provide benzoxazine compounds, methods of preparing the benzoxazine compounds, and polymers formed by 20 benzoxazines.

The following are sentences describing embodiments of the invention.


1. A benzoxazine compound of Formula (I) or Formula (III), wherein Formula (I) has the following structure:



25

(I)

wherein R₁ and R₂ in Formula (I) may independently be selected from hydrogen, a straight or branched alkyl having 1-4 carbon atoms, a straight or branched alkenyl having 1-4 carbon atoms, a straight or branched alkoxy group having 1-4 carbon atoms and -C(=O)H; R₃ may be hydrogen or a group having Formula (II):



(II)

wherein R₁ and R₂ in Formula (II) may independently be selected from the same groups for R₁

and R₂ that are defined above,  represents the bond to the ring carbon of the furan ring in


5 Formula (I), and R₄ in Formula (II) may be selected from hydrogen an optionally substituted alkyl group having 1 to 20 carbon atoms, an optionally substituted alkene group having 2 to 20 carbon atoms, an optionally substituted cycloalkyl group having 3 to 12 carbon atoms, an optionally substituted aryl group having 6 to 16 carbon atoms, and an optionally substituted heterocyclic group having 3 to 16 carbon atoms; wherein the alkyl group, alkene group, cycloalkyl group, aryl group or heterocyclic group can be substituted with 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, an aryl group having 6 to 16 carbon atoms, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms,

10 R₅ in Formula (II) may be selected from hydrogen an optionally substituted alkyl group

15 having 1 to 20 carbon atoms, an optionally substituted alkene group having 2 to 20 carbon atoms, an optionally substituted cycloalkyl group having 3 to 12 carbon atoms, an optionally substituted aryl group having 6 to 16 carbon atoms, and an optionally substituted heterocyclic group having 3 to 16 carbon atoms; wherein the alkyl group, alkene group, cycloalkyl group, aryl group or heterocyclic group can be substituted with 1 to 5 substituents independently selected from a

20 halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, an aryl group having 6 to 16 carbon atoms, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms, wherein R₄ and R₅ in Formula (II) cannot both be hydrogen;

wherein Formula (III) has the following structure:



(III)

wherein R¹ and R² in Formula (III) may be independently selected from the same groups for R₁ and R₂ that are defined above, wherein R⁷ and R⁹ are independently selected from

5 hydrogen, an optionally substituted alkyl group having 1 to 20 carbon atoms, an optionally substituted alkene group having 2 to 20 carbon atoms, an optionally substituted heterocyclic group with 3 to 15 carbon atoms, optionally substituted aryl group having 6 to 15 carbon atoms and an optionally substituted cycloalkyl group having 3 to 12 carbon atoms; wherein the alkyl group, alkene group, heterocyclic group, aryl group, or cycloalkyl group can be substituted with
10 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, an aryl group having 6 to 15 carbon atoms, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms, and wherein the aryl group substituent and the heterocyclic group substituent can be further substituted with hydroxy, an alkoxy group having 1 to 20 carbon atoms, or an alkylamino group having 1 to 2
15 carbon atoms; and

R⁸ is an optionally substituted alkylene group having 1 to 20 carbon atoms, an optionally substituted alkenylene group having 2 to 20 carbon atoms, an optionally substituted heterocyclic group with 3 to 15 carbon atoms, optionally substituted arylene group having 6 to 15 carbon atoms and an optionally substituted cycloalkylene group having 3 to 12 carbon atoms; wherein
20 the alkylene group, alkenylene group, heterocyclic group, arylene group, or cycloalkylene group can be substituted with 1 to 4 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms.

2. The benzoxazine compound of the preceding sentence, wherein R₁ and R₂ of
25 Formula (I) and R¹ and R² of Formula (III) may be independently selected from methyl, isopropyl, methoxy, -C(=O)H and -CH₂-CH=CH₂ and R₃ may be hydrogen.

3. The benzoxazine compound of any preceding sentence, wherein R₃ may be a group having Formula (II) and the benzoxazine compound may be symmetrical in that R₁ and R₂ of Formula (I) are identical to R1 and R2 of Formula (II), respectively.

4. The benzoxazine compound of any preceding sentence, wherein R₁ and R₂ of Formula (I) may not be hydrogen and are bonded at the 6-position and 8-position of the benzoxazine ring, respectively.

5. The benzoxazine compound of any one of sentences 1-3, wherein (a) R₁ and R₂ of Formula (I) may not be hydrogen and are bonded at the 6-position and 8-position of the benzoxazine ring, respectively, and R₁ and R₂ of Formula (II) are not hydrogen and are bonded at the 6-position and 8-position of the benzoxazine ring, respectively; or (b) R₁ and R₂ of Formula (I) are not hydrogen and are bonded at the 5-position and 8-position of the benzoxazine ring, respectively, and R₁ and R₂ of Formula (II) are not hydrogen and are bonded at the 5-position and 8-position of the benzoxazine ring, respectively.

6. The benzoxazine compound of sentence 1, wherein: R₄ and R₅ are each independently selected from hydrogen, an optionally substituted alkyl group having 7 to 20 carbon atoms, an optionally substituted alkene group having 3 to 20 carbon atoms, an optionally substituted cycloalkyl group having 3 to 12 carbon atoms and an optionally substituted phenyl group, wherein the alkyl group, alkene group, cycloalkyl group or phenyl group can be substituted with 1 to 5 substituents independently selected from an alkyl group having 1-10 carbon atoms, a hydroxyl group, and an alkoxy group having 1 to 20 carbon atoms, wherein both R₄ and R₅ cannot be hydrogen.

7. The benzoxazine compound of sentence 1, wherein R₄ may be hydrogen; R₅ may be a phenyl group which is optionally substituted with a hydroxyl group, an alkoxy group having 1 to 4 carbon atoms, an alkyl group having 1 to 6 carbon atoms, and an alkene group having 2 to 4 carbon atoms.

8. The benzoxazine compound of sentence 1, wherein R₄ and R₅ may be each independently selected from: hydrogen, an optionally substituted alkyl group having 8 to 18 carbon atoms, an optionally substituted alkene group having 4 to 18 carbon atoms, and an optionally substituted cycloalkyl group having 3 to 8 carbon atoms, wherein the alkyl group, alkene group, or cycloalkyl group can be substituted with 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 8 carbons, and an alkoxy group having 1 to 8 carbon atoms; and wherein only one of R₄ and R₅ can be hydrogen.

9. The benzoxazine compound of sentence 1, wherein the benzoxazine may be


35 a) bis(5-((2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane;

b) 3,3'-(5,5'-methylenebis(furan-5,2-diyl))bis(methylene))bis(8-methoxy-3,4-dihydro-2H-benzo[e][1,3]oxazine-6-carbaldehyde);
 c) 3-(furan-2-ylmethyl)-5-isopropyl-8-methyl-3,4-dihydro-2H-benzo[e][1,3]oxazine;
 d) bis(5-((5-isopropyl-8-methyl-2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane; or
 5 e) bis(5-((6-allyl-8-methoxy-2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane.

10. A method of forming the benzoxazine compound of Formula (I) of sentence 1, which may include reacting a furfurylamine compound, a formaldehyde compound, and a phenol compound.


11. The method of sentence 1, wherein the phenol compound may be selected from phenol, bisphenol A, bisguaiacol, vanillin, carvacrol, and eugenol.

12. The method of any one of sentences 10-11, wherein the furfurylamine compound may be a compound of Formula (IV) or a compound of Formula (V), wherein the compound of 15 Formula (IV) is a difuran diamine compound having the following structure:



wherein R and R¹ are independently selected from hydrogen, an optionally substituted alkyl group having 1 to 20 carbon atoms, an optionally substituted alkene group having 2 to 20 carbon atoms, an optionally substituted cycloalkyl group having 3 to 12 carbon atoms, an optionally substituted aryl group having 6 to 16 carbon atoms, and an optionally substituted heterocyclic group having 3 to 16 carbon atoms; wherein the alkyl group, alkene group, cycloalkyl group, aryl group or heterocyclic group can be substituted with 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms, 20 wherein only one of R and R¹ can be hydrogen;
 25 wherein only one of R and R¹ can be hydrogen;

wherein the compound of Formula (V) is a tetrafuran tetraamine compound with the following structure:



wherein R⁷ and R⁹ are independently selected from hydrogen, an optionally substituted alkyl group having 1 to 20 carbon atoms, an optionally substituted alkene group having 2 to 20 carbon atoms, an optionally substituted heterocyclic group with 3 to 15 carbon atoms, optionally substituted aryl group having 6 to 15 carbon atoms and an optionally substituted cycloalkyl group having 3 to 12 carbon atoms; wherein the alkyl group, alkene group, heterocyclic group, aryl group, or cycloalkyl group can be substituted with 1 to 5 substituents independently selected

from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, an aryl group having 6 to 15 carbon atoms, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms, and wherein the aryl group substituent and the heterocyclic group substituent can be further substituted with hydroxy, an alkoxy group having 1 to 20 carbon atoms, or an alkylamino group having 1 to 2 carbon atoms; and

R⁸ is an optionally substituted alkylene group having 1 to 20 carbon atoms, an optionally substituted alkenylene group having 2 to 20 carbon atoms, an optionally substituted heterocyclic group with 3 to 15 carbon atoms, optionally substituted arylene group having 6 to 15 carbon atoms and an optionally substituted cycloalkylene group having 3 to 12 carbon atoms; wherein the alkylene group, alkenylene group, heterocyclic group, arylene group, or cycloalkylene group can be substituted with 1 to 4 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms.


13. The method of any one of sentences 10-12, wherein the formaldehyde compound is selected from formaldehyde and paraformaldehyde.

14. The method of sentence 10, wherein the method may further include an inert organic solvent, and heating a reaction mixture including the furfurylamine compound, the formaldehyde compound, and the phenol compound at temperatures between 60-85°C.

15. The method of sentence 14, wherein the inert organic solvent may be selected from an aliphatic or cycloaliphatic alcohol, an ester, a ketone, an aromatic or aliphatic hydrocarbon, a halogenated hydrocarbon and a mixture of one or more of the foregoing solvents.

16. The method of sentence 15, wherein the inert organic solvent may be a halogenated hydrocarbon selected from chloroform and methylene chloride.

17. A polymer formed by ring opening polymerization of at least benzoxazine compound of the Formula (I) or Formula (III) of sentence 1, and optionally including an epoxidation reaction with a diepoxide of the following Formula (VI):




wherein R₆ is an alkylene group having 1 to 20 carbon atoms, an alkenylene group having 2 to 20 carbon atoms, an heterocyclic group with 3 to 15 carbon atoms, an arylene group having 6 to 15

10 carbon atoms and a cycloalkylene group having 3 to 12 carbon atoms; wherein the alkylene group, alkenylene group, heterocyclic group, arylene group, or cycloalkylene group can be substituted with 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms.

15 18. A polymer formed by ring opening polymerization of at least one benzoxazine compound of the Formula (I) or Formula (III) of claim 1, and optionally including an epoxidation reaction with an epoxide selected from the group consisting of dibisphenol A epoxy resin, bisphenol F epoxy resin, novolac epoxy resin, aliphatic epoxy resin, glycidylamine epoxy resin, phenyl glycidyl ether, tetraglycidyl 4,4'-diaminodiphenylmethane, diepoxide having a phenyl-20 sulfone-phenyl group, and diglycidyl ether having a Bisphenol B, C, D, or E group.


19. The polymer of sentence 17 or 18, wherein the epoxy group-containing compound is a bisphenol-A diglycidyl ether (DGEBA) epoxy resin compound or an oligomer thereof.

20. A polymer including at least one repeating unit selected from a unit of Formula (VII) and a unit of Formula (VIII):




25

(VII)




(VIII)

wherein R₁ and R₂ in Formulae (VII) and (VIII) are independently selected from hydrogen, a straight or branched alkyl, alkenyl, or alkoxy group having 1-4 carbon atoms and -C(=O)H, n is up to 1000; and R₃ is hydrogen, or at least one group of the Formula (II) as defined in claim 1, the Formula (IX) and the Formula (X):



(IX)



(X)

wherein R₁ and R₂ in Formulae (IX) and (X) are independently selected from hydrogen, a straight or branched alkyl, alkenyl, or alkoxy group having 1-4 carbon atoms and -C(=O)H, n is up to 1000,

wherein the circled methylene group in Formula (IX) and Formula (X) is optionally substituted with R₄ and R₅ or R₇ and R₉ as defined in sentence 1.

21. The compound or method or polymer of any one of sentences 1-20, wherein in R₁, R₂ and R₃ of Formula (I), R₁, R₂, R₄ and R₅ of Formula (II), R₁, R₂, R₇ and R₉ of Formula (III), R and R₁ of Formula (IV), R₇ and R₉ of Formula (V), R₁, R₂ and R₃ of Formula (VII), R₁, R₂ and R₃ of Formula (VIII), R₁ and R₂ of Formula (IX), and R₁ and R₂ of Formula (X):

10 the alkyl group is selected from a straight or branched chain butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl and dodecyl,

the alkene group is selected from a vinyl, propenyl, or a straight or branched chain butenyl, pentenyl, hexenyl, heptenyl, octenyl, nonenyl, decenyl, undecenyl and dodecenyl,

15 the cycloalkyl group is selected from a cyclopentyl or cyclohexyl,

the aryl group is selected from phenyl, tolyl, and biphenyl,

the heterocyclic group is selected from pyrrolidine, pyrrole, tetrahydrofuran, furan, tetrahydrothiophene, thiophene, imidazolidine, pyrazolidine, imidazole, pyrazole, oxazolidine, isoxazolidine, oxazole, isoxazole, thiazolidine, isothiazolidine, thiazole,

20 isothiazole, dioxolane, dithiolane, piperidine, pyridine, bipyridine, tetrahydropyran, pyran, piperazine, diazines, morpholine, oxazine, thiomorpholine, and thiazine; and

wherein in R₈ of Formula (III), R₈ of Formula (V), and R₆ of Formula (VI):

the alkylene group is selected from a straight or branched chain butylene, pentylene, hexylene, heptylene, octylene, nonylene, decylene, undecylene and dodecylene,

25 the alkenylene group is selected from a vinylene, propenylene, or a straight or branched chain butenylene, pentenylene, hexenylene, heptenylene, octenylene, nonenylene, decenylene, undecenylene and dodecenylene,

the cycloalkylene group is selected from a cyclopentylene or cyclohexylene,

the arylene group is selected from phenylene, tolylene, and biphenylene; and

30 wherein the groups may be optionally substituted with 1-4 substituents and the optional substituents are selected from the group consisting of an alkyl group having 1 to 3 carbons, an aldehyde, a hydroxyl group and methoxy group.

22. A polymer composition including the polymer of any one of sentences 17-20, and further including one or more of fibers, clays, silicates, fillers, whiskers, pigments, corrosion inhibitors, flow additives, film formers, defoamers, coupling agents, antioxidants, stabilizers, flame retardants, reheating aids, plasticizers, flexibilizers, anti-fogging agents, nucleating agents, or combinations thereof.

23. The polymer composition according to sentence 22, including the pigment, the corrosion inhibitor and the fibers and wherein the pigment is selected from titanium dioxide, iron oxides, carbon black and mixtures thereof; the corrosion inhibitor is zinc phosphate; and the fibers are glass fibers.

10 24. The polymer of any one of sentences 17-23, wherein the glass transition temperature ranges from 100°C to 300°C, or 120°C to 280°C or 170°C to 275°C.

25. The polymer of any one of sentences 17-23, wherein the flexural modulus ranges from 2 GPa to 4 GPa at room temperature, or from 2.2 GPa to 3.8 GPa at room temperature, or from 2.5 GPa to 3.7 GPa at room temperature.

15 26. The polymer of any one of sentences 17-23, wherein the flexural strength is greater than 20 MPa at room temperature, or greater than 22 MPa at room temperature, or greater than 25 MPa at room temperature.

27. The polymer of any one of sentences 17-23, wherein the UL-94 flammability (standard of 2017) is a V-0 or a V-1 rating.

20 Additional details and advantages of the disclosure will be set forth in part in the description which follows, and/or may be learned by practice of the disclosure. The details and advantages of the disclosure may be realized and attained by means of the elements and combinations particularly pointed out in the appended claims.

25 **BRIEF DESCRIPTION OF THE DRAWINGS**

FIG. 1 shows the ¹H-NMR spectrum of bis(5-((2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane; (BZ-DFDA-phenol).

Fig. 2 shows the ¹H-NMR spectrum of 3,3'-(5,5'-methylenebis(furan-5,2-diyl))bis(methylene))bis(8-methoxy-3,4-dihydro-2H-benzo[e][1,3]oxazine-6-carbaldehyde); (BZ-DFDA-vanillin).

30 FIG. 3 shows the ¹H-NMR spectrum of 3-(furan-2-ylmethyl)-5-isopropyl-8-methyl-3,4-dihydro-2H-benzo[e][1,3]oxazine; (Bz-FA-carvacrol).

FIG. 4 shows the ¹H-NMR spectrum of bis(5-((5-isopropyl-8-methyl-2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane; (Bz-DFDA-carvacrol)

FIG. 5 shows the Fourier-transform infrared (FTIR) spectra of the benzoxazine monomers.

FIG. 6 shows the Differential scanning calorimetry (DSC) curves of the BZ-DFDA-phenol monomer.

5 FIG. 7 shows the Differential scanning calorimetry (DSC) curves of the BZ-DFDA-vanillin monomer.

FIG. 8 shows the Differential scanning calorimetry (DSC) curves of the BZ-FA-carvacrol monomer.

10 FIG. 9 shows the Differential scanning calorimetry (DSC) curves of the BZ-DFDA-10 carvacrol monomer.

FIG. 10 shows the Dynamic mechanical analysis (DMA) data of the BZ-DFDA-phenol/glass fiber composites.

FIG. 11 shows the Dynamic mechanical analysis (DMA) data of the BZ-DFDA-vanillin/glass fiber composites.

15 FIG. 12 shows the Dynamic mechanical analysis (DMA) data of the BZ-FA-carvacrol/glass fiber composites.

FIG. 13 shows the Dynamic mechanical analysis (DMA) data of the BZ-DFDA-carvacrol/glass fiber composites.

20 **DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS**


For illustrative purposes, the principles of the present invention are described by referencing various exemplary embodiments thereof. Although certain embodiments of the invention are specifically described herein, one of ordinary skill in the art will readily recognize that the same principles are equally applicable to, and can be employed in other systems and methods. Before explaining the disclosed embodiments of the present invention in detail, it is to be understood that the invention is not limited in its application to the details of any particular embodiment shown. Additionally, the terminology used herein is for the purpose of description and not of limitation. Further, although certain methods are described with reference to certain steps that are presented herein in certain order, in many instances, these steps may be performed in any order as may be appreciated by one skilled in the art, and the methods are not limited to the particular arrangement of steps disclosed herein.

30 As used herein and in the appended claims, the singular forms “a”, “an”, and “the” include plural references unless the context clearly dictates otherwise. The terms “a” (or “an”), “one or more” and “at least one” can be used interchangeably herein. It is also to be noted that 35 the terms “comprising”, “including”, and “having” can be used interchangeably.

The Benzoxazine Compound


The present invention relates to a benzoxazine compound and a method of preparing the benzoxazine compound.

Suitable benzoxazine compounds of the present invention may be selected from Formula (I) or Formula (III), wherein Formula (I) has the following structure:



(I)

wherein R₁ and R₂ in Formula (I) are independently selected from hydrogen, a straight or branched alkyl having 1-4 carbon atoms, a straight or branched alkenyl having 1-4 carbon atoms, a straight or branched alkoxy group having 1-4 carbon atoms and -C(=O)H; R₃ is hydrogen or a group having Formula (II):



(II)

wherein R₁ and R₂ in Formula (II) are independently selected from the same groups for R₁ and R₂


that are defined above, represents the bond to the ring carbon of the furan ring in Formula (I), and R₄ in Formula (II) is selected from hydrogen an optionally substituted alkyl group having 1 to 20 carbon atoms, an optionally substituted alkene group having 2 to 20 carbon atoms, an optionally substituted cycloalkyl group having 3 to 12 carbon atoms, an optionally substituted aryl group having 6 to 16 carbon atoms, and an optionally substituted heterocyclic group having 3 to 16 carbon atoms; wherein the alkyl group, alkene group, cycloalkyl group, aryl group or heterocyclic group can be substituted with 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, an aryl group having 6 to 16 carbon atoms, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms,

R₅ in Formula (II) is selected from hydrogen an optionally substituted alkyl group having 1 to 20 carbon atoms, an optionally substituted alkene group having 2 to 20 carbon atoms, an

optionally substituted cycloalkyl group having 3 to 12 carbon atoms, an optionally substituted aryl group having 6 to 16 carbon atoms, and an optionally substituted heterocyclic group having 3 to 16 carbon atoms; wherein the alkyl group, alkene group, cycloalkyl group, aryl group or heterocyclic group can be substituted with 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, an aryl group having 6 to 16 carbon atoms, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms

5 wherein R_4 and R_5 in Formula (II) cannot both be hydrogen;

wherein Formula (III) has the following structure:



10

(III)

wherein R^1 and R^2 in Formula (III) are independently selected from the same groups for R_1 and R_2 that are defined above, wherein R^7 and R^9 are independently selected from hydrogen, an optionally substituted alkyl group having 1 to 20 carbon atoms, an optionally substituted alkene

15 group having 2 to 20 carbon atoms, an optionally substituted heterocyclic group with 3 to 15 carbon atoms, optionally substituted aryl group having 6 to 15 carbon atoms and an optionally substituted cycloalkyl group having 3 to 12 carbon atoms; wherein the alkyl group, alkene group, heterocyclic group, aryl group, or cycloalkyl group can be substituted with 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group

20 having 1 to 20 carbons, an aryl group having 6 to 15 carbon atoms, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms, and wherein the aryl group substituent and the heterocyclic group substituent can be further substituted with hydroxy, an alkoxy group having 1 to 20 carbon atoms, or an alkylamino group having 1 to 2 carbon atoms; and

25 R^8 is an optionally substituted alkylene group having 1 to 20 carbon atoms, an optionally substituted alkenylene group having 2 to 20 carbon atoms, an optionally substituted heterocyclic

group with 3 to 15 carbon atoms, optionally substituted arylene group having 6 to 15 carbon atoms and an optionally substituted cycloalkylene group having 3 to 12 carbon atoms; wherein the alkylene group, alkenylene group, heterocyclic group, arylene group, or cycloalkylene group can be substituted with 1 to 4 substituents independently selected from a halogen, hydroxy, 5 amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms.

In other embodiments, R_1 and R_2 of Formula (1) and R^1 and R^2 of Formula (III) are independently selected from methyl, isopropyl, methoxy, $-C(=O)H$ and $-CH_2-CH=CH_2$ and R_3 is hydrogen.

10 In other embodiments, R_3 may be a group having Formula (II) and the benzoxazine compound is symmetrical in that R_1 and R_2 of Formula (I) are identical to R_1 and R_2 of Formula (II), respectively.

In other embodiments, R_1 and R_2 of Formula (I) are not hydrogen and are bonded at the 6-position and the 8-position of the benzoxazine ring, respectively.

15 In other embodiments, the benzoxazine compound is a compound, wherein
(a) R_1 and R_2 of Formula (I) are not hydrogen and are bonded at the 6-position and 8-position of the benzoxazine ring, respectively, and R_1 and R_2 of Formula (II) are not hydrogen and are bonded at the 6-position and 8-position of the benzoxazine ring, respectively; or
(b) R_1 and R_2 of Formula (I) are not hydrogen and are bonded at the 5-position and 8-position 20 of the benzoxazine ring, respectively, and R_1 and R_2 of Formula (II) are not hydrogen and are bonded at the 5-position and 8-position of the benzoxazine ring, respectively.

In other embodiments, R_4 and R_5 are each independently selected from: hydrogen, an optionally substituted alkyl group having 7 to 20 carbon atoms, an optionally substituted alkene group having 3 to 20 carbon atoms, an optionally substituted cycloalkyl group 25 having 3 to 12 carbon atoms and an optionally substituted phenyl group, wherein the alkyl group, alkene group, cycloalkyl group or phenyl group can be substituted with 1 to 5 substituents independently selected from an alkyl group having 1-10 carbon atoms, a hydroxyl group, and an alkoxy group having 1 to 20 carbon atoms, wherein both R_4 and R_5 cannot be hydrogen.

30 In other embodiments, R_4 is hydrogen; R_5 is a phenyl group which is optionally substituted with a hydroxyl group, an alkoxy group having 1 to 4 carbon atoms, an alkyl group having 1 to 6 carbon atoms, and an alkene group having 2 to 4 carbon atoms.

In other embodiments, R_4 and R_5 are each independently selected from hydrogen, an 35 optionally substituted alkyl group having 8 to 18 carbon atoms, an optionally substituted alkene group having 4 to 18 carbon atoms, and an optionally substituted cycloalkyl group having 3 to 8 carbon atoms, wherein the alkyl group, alkene group, or cycloalkyl group can be substituted with

1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 8 carbons, and an alkoxy group having 1 to 8 carbon atoms; and wherein only one of R₄ and R₅ can be a hydrogen.


Non-limiting examples of suitable benzoxazine compounds of the present disclosure

5 include bis(5-((2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane; 3,3'-(5,5'-methylenebis(furan-5,2-diyl))bis(methylene))bis(8-methoxy-3,4-dihydro-2H-benzo[e][1,3]oxazine-6-carbaldehyde); 3-(furan-2-ylmethyl)-5-isopropyl-8-methyl-3,4-dihydro-2H-benzo[e][1,3]oxazine; bis(5-((5-isopropyl-8-methyl-2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane; and bis(5-((6-allyl-8-methoxy-2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane.

10

Preferably, the benzoxazine compound is selected from benzoxazine compounds of the present disclosure include bis(5-((2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane; 3,3'-(5,5'-methylenebis(furan-5,2-diyl))bis(methylene))bis(8-methoxy-3,4-dihydro-2H-benzo[e][1,3]oxazine-6-carbaldehyde); 3-(furan-2-ylmethyl)-5-isopropyl-8-methyl-3,4-dihydro-15 2H-benzo[e][1,3]oxazine; bis(5-((5-isopropyl-8-methyl-2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane; and bis(5-((6-allyl-8-methoxy-2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane.

The benzoxazine compounds of Formula (I) may be prepared by reacting a furfurylamine compound, a formaldehyde compound, and a phenol compound. The following schematic is a reaction mechanism of one way the benzoxazines may be prepared:



Suitable examples of the phenol compound may be selected from phenol, bisphenol A, bisguaiacol, vanillin, carvacrol, eugenol, 4-hydroxybenzaldehyde, o-cresol, m-cresol, 1,3,5-xylenol. Preferably, the phenol compound is selected from phenol, vanillin, carvacrol and 25 eugenol.


Suitable furfurylamine compounds for making the benzoxazine compound of Formula (I) are compounds according to the Formula (IV) or compounds according to the Formula (V), wherein the compound of Formula (IV) is a difuran diamine compound having the following structure:



(IV)

wherein R and R¹ are independently selected from hydrogen, an optionally substituted alkyl group having 1 to 20 carbon atoms, an optionally substituted alkene group having 2 to 20 carbon atoms, an optionally substituted cycloalkyl group having 3 to 12 carbon atoms, an optionally substituted aryl group having 6 to 16 carbon atoms, and an optionally substituted heterocyclic group having 3 to 16 carbon atoms; wherein the alkyl group, alkene group, cycloalkyl group, aryl group or heterocyclic group can be substituted with 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms, wherein only one of R and R¹ can be hydrogen;

the compound of Formula (V) is a tetrafuran tetramine compound with the following structure,



(V)

wherein R⁷ and R⁹ are independently selected from hydrogen, an optionally substituted alkyl group having 1 to 20 carbon atoms, an optionally substituted alkene group having 2 to 20 carbon atoms, an optionally substituted heterocyclic group with 3 to 15 carbon atoms, optionally substituted aryl group having 6 to 15 carbon atoms and an optionally substituted cycloalkyl group having 3 to 12 carbon atoms; wherein the alkyl group, alkene group, heterocyclic group, aryl group, or cycloalkyl group can be substituted with 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, an aryl group having 6 to 15 carbon atoms, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms, and wherein the aryl group substituent and the heterocyclic group substituent can be further substituted with hydroxy, an alkoxy group having 1 to 20 carbon atoms, or an alkylamino group having 1 to 2 carbon atoms; and

R⁸ is an optionally substituted alkylene group having 1 to 20 carbon atoms, an optionally substituted alkenylene group having 2 to 20 carbon atoms, an optionally substituted heterocyclic

group with 3 to 15 carbon atoms, optionally substituted arylene group having 6 to 15 carbon atoms and an optionally substituted cycloalkylene group having 3 to 12 carbon atoms; wherein the alkylene group, alkenylene group, heterocyclic group, arylene group, or cycloalkylene group can be substituted with 1 to 4 substituents independently selected from a halogen, hydroxy, 5 amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms.

Suitable formaldehyde compounds may be selected from formaldehyde and paraformaldehyde.

The method of preparing the benzoxazine compound may further include use of an inert 10 organic solvent and heating the reaction mixture comprising the furfurylamine compound, the formaldehyde compound, and the phenol compound at a temperature of from 60°C to 85°C, or from 65°C to 80°C.

Suitable inert organic solvents may be selected from an aliphatic or cycloaliphatic 15 alcohol, an ester, a ketone, an aromatic or aliphatic hydrocarbon, a halogenated hydrocarbon and a mixture of one or more of the foregoing solvents. Preferably, the inert organic solvent is a halogenated hydrocarbon. Even more preferably, the halogenated hydrocarbon is selected from chloroform and methylene chloride.

In other embodiments of the benzoxazine compound and method of preparing the compound, in R₁, R₂ and R₃ of Formula (I), R₁, R₂, R₄ and R₅ of Formula (II), R₁, R₂, R₇ and R₉ 20 of Formula (III), R and R₁ of Formula (IV), R₇ and R₉ of Formula (V), R₁, R₂ and R₃ of Formula (VII), R₁, R₂ and R₃ of Formula (VIII), R₁ and R₂ of Formula (IX), and R₁ and R₂ of Formula (X):

the alkyl group is selected from a straight or branched chain butyl, pentyl, hexyl, heptyl, 25 octyl, nonyl, decyl, undecyl and dodecyl,

the alkene group is selected from a vinyl, propenyl, or a straight or branched chain butenyl, pentenyl, hexenyl, heptenyl, octenyl, nonenyl, decenyl, undecenyl and dodecenyl,

the cycloalkyl group is selected from a cyclopentyl or cyclohexyl,

the aryl group is selected from phenyl, tolyl, and biphenyl,

the heterocyclic group is selected from pyrrolidine, pyrrole, tetrahydrofuran, furan, 30 tetrahydrothiophene, thiophene, imidazolidine, pyrazolidine, imidazole, pyrazole, oxazolidine, isoxazolidine, oxazole, isoxazole, thiazolidine, isothiazolidine, thiazole, isothiazole, dioxolane, dithiolane, piperidine, pyridine, bipyridine, tetrahydropyran, pyran, piperazine, diazines, morpholine, oxazine, thiomorpholine, and thiazine; and

wherein in R₈ of Formula (III), R₈ of Formula (V), and R₆ of Formula (VI):

the alkylene group is selected from a straight or branched chain butylene, pentylene, hexylene, heptylene, octylene, nonylene, decylene, undecylene and dodecylene,

the alkenylene group is selected from a vinylene, propenylene, or a straight or branched chain butenylene, pentenylene, hexenylene, heptenylene, octenylene, nonenylene, decenylene, 5 undecenylene and dodecenylene,

the cycloalkylene group is selected from a cyclopentylene or cyclohexylene,


the arylene group is selected from phenylene, tolylene, and biphenylene; and

wherein the groups are optionally substituted with 1-4 substituents and the optional substituents are selected from group consisting of an alkyl group having 1 to 3 carbons, an 10 aldehyde, a hydroxyl group and methoxy group.

Polymers

The present invention also relates to polymers formed from the benzoxazine compounds.

In one embodiment, the polymer may be formed by ring opening polymerization of at least one 15 benzoxazine compound according to Formula (I) or Formula (III) as set forth above, and optionally including an epoxidation reaction with a diepoxide of Formula (VI):




wherein R₆ is an alkylene group having 1 to 20 carbon atoms, an alkenylene group having 2 to 20 carbon atoms, an heterocyclic group with 3 to 15 carbon atoms, an arylene group having 6 to 15 carbon atoms and a cycloalkylene group having 3 to 12 carbon atoms; wherein the alkylene group, alkenylene group, heterocyclic group, arylene group, or cycloalkylene group can be substituted with 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms. Preferably, the epoxy group-containing compound is bisphenol-A diglycidyl ether (DGEBA) epoxy resin compound or an oligomer thereof.

In another embodiment, the polymer may be formed by ring opening polymerization of at least one benzoxazine compound according to Formula (I) or Formula (III) as set forth above, 30 and optionally including an epoxidation reaction with an epoxide selected from the group consisting of dibisphenol A epoxy resin, bisphenol F epoxy resin, novolac epoxy resin, aliphatic epoxy resin, glycidylamine epoxy resin, phenyl glycidyl ether, tetraglycidyl 4,4'-diaminodiphenylmethane, diepoxide having a phenyl-sulfone-phenyl group, and diglycidyl ether


having a Bisphenol B, C, D, or E group. Preferably, the epoxy group-containing compound is bisphenol-A diglycidyl ether (DGEBA) epoxy resin compound or an oligomer thereof.

In another embodiment, the polymer may comprise at least one repeating unit selected from the unit of Formula (VII) and the unit of Formula (VIII):




5

(VII)




(VIII)

wherein R₁ and R₂ in Formulae (VII) and (VIII) are independently selected from hydrogen, a straight or branched alkyl, alkenyl, or alkoxy group having 1-4 carbon atoms and -C(=O)H, n is up to 1000; and R₃ is hydrogen, or at least one group of the Formula (II) as set forth above, the Formula (IX) and the Formula (X):



(IX)



(X)

wherein R₁ and R₂ in Formulae (IX) and (X) are independently selected from hydrogen, a straight or branched alkyl, alkenyl, or alkoxy group having 1-4 carbon atoms and

5 -C(=O)H, n is up to 1000,

wherein the circled methylene group in Formula (IX) and Formula (X) is optionally substituted with R₄ and R₅ or R₇ and R₉ as set forth above.

In another embodiment, in R₁, R₂ and R₃ of Formula (I), R₁, R₂, R₄ and R₅ of Formula (II), R₁, R₂, R₇ and R₉ of Formula (III), R and R₁ of Formula (IV), R₇ and R₉ of Formula (V), R₁, 10 R₂ and R₃ of Formula (VII), R₁, R₂ and R₃ of Formula (VIII), R₁ and R₂ of Formula (IX), and R₁ and R₂ of Formula (X)

the alkyl group is selected from a straight or branched chain butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl and dodecyl,

the alkene group is selected from a vinyl, propenyl, or a straight or branched chain 15 butenyl, pentenyl, hexenyl, heptenyl, octenyl, nonenyl, decenyl, undecenyl and dodecenyl,

the cycloalkyl group is selected from a cyclopentyl or cyclohexyl,

the aryl group is selected from phenyl, tolyl, and biphenyl,

the heterocyclic group is selected from pyrrolidine, pyrrole, tetrahydrofuran, furan, tetrahydrothiophene, thiophene, imidazolidine, pyrazolidine, imidazole, pyrazole, oxazolidine, 20 isoxazolidine, oxazole, isoxazole, thiazolidine, isothiazolidine, thiazole, isothiazole, dioxolane, dithiolane, piperidine, pyridine, bipyridine, tetrahydropyran, pyran, piperazine, diazines, morpholine, oxazine, thiomorpholine, and thiazine; and

wherein in R₈ of Formula (III), R₈ of Formula (V), and R₆ of Formula (VI)

the alkylene group is selected from a straight or branched chain butylene, pentylene,

25 hexylene, heptylene, octylene, nonylene, decylene, undecylene and dodecylene,

the alkenylene group is selected from a vinylene, propenylene, or a straight or branched chain butenylene, pentenylene, hexenylene, heptenylene, octenylene, nonenylene, decenylene, undecenylene and dodecenylene,

the cycloalkylene group is selected from a cyclopentylene or cyclohexylene,

5 the arylene group is selected from phenylene, tolylene, and biphenylene; and

wherein the groups are optionally substituted with 1-4 substituents and the optional substituents are selected from group consisting of an alkyl group having 1 to 3 carbons, an aldehyde, a hydroxyl group and methoxy group.

In one aspect of the invention, the present invention relates to a polymer composition

10 comprising the polymer as set forth above, further including one or more of fiber, clays, silicates, fillers, whiskers, pigments, corrosion inhibitors, flow additives, film formers, defoamers, coupling agents, antioxidants, stabilizers, flame retardants, reheating aids, plasticizers, flexibilizers, anti-fogging agents, nucleating agents, or combinations thereof. Preferably, the polymer composition comprises a pigment, a corrosion inhibitor, and fibers.

15 Suitable pigments may be selected from titanium dioxides, iron oxides, carbon black and mixtures thereof. Preferably, the corrosion inhibitor is zinc phosphate and the fibers are glass fibers.

The polymers of the present invention may have a glass transition temperature range of from 100°C to 300°C, or from 120°C to 280°C, or from 170°C to 275°C.

20 The polymers may have a flexural modulus ranges from 2 GPa to 4 GPa at room temperature, or from 2.2 GPa to 3.8 GPa at room temperature, or from 2.5 GPa to 3.7 GPa at room temperature.

25 The polymers of the present invention may have a flexural strength is greater than 20 MPa at room temperature, or greater than 22 MPa at room temperature, or greater than 25 MPa at room temperature.

The polymers of the present invention may have a UL-94 flammability (standard of 2017) of V-0 or V-1 rating.

Preparation of molding compositions

30 In another aspect of the invention, the benzoxazine-containing compound may be used to prepare benzoxazine-containing molding compositions, which can be prepared by any conventional methods. For example, the materials (including resins and other additives) can be finely ground, dry blended, densified on a hot differential roll mill, and then followed by granulation. The molding composition, as described above, can be used for coating electronic devices such as semiconductors or circuit boards. The prepared compositions can be molded by

any suitable molding apparatus. An example of such an apparatus is a transfer press equipped with a multi-cavity mold. For more detail on methods for preparing molding compositions and for coating electronic devices, see U.S. Pat. No. 5,476,716.

The following list includes examples of suitable additives that may be included in the 5 molding composition and preferred weight ranges of the additives, based on the total weight percent of the composition:

(1) A flame retardant such as a brominated epoxy novolac flame retardant (e.g., BREN, available from Nippon Kayaku). The preferred molding composition can contain up to 3.0 wt %, more preferably, 0.1-1.0 wt % of a flame retardant.

10 (2) A flame retardant synergist such as Sb₂O₅ or WO₃. The preferred molding composition can contain up to 3.0 wt %, more preferably, 0.25-1.5 wt % of a flame retardant synergist.

(3) A filler such as silica, calcium silicate, and aluminum oxide. The preferred molding composition can contain 70-90 wt %, more preferably, 75-85 wt % of a filler.

(4) A colorant such as carbon black colorant. The preferred molding composition can contain 15 0.1-2.0 wt %, more preferably, 0.1-1.0 wt % of a colorant.

(5) A wax or a combination of waxes such as carnauba wax, paraffin wax, S-wax, and E-wax. The preferred molding composition can contain 0.1-2.0 wt %, more preferably, 0.3-1.5 wt % of a wax.


(6) Fumed silica such as aerosil. The preferred molding composition can contain 0.3-5.0 wt %, 20 more preferably, 0.7-3.0 wt % of fumed silica.

EXAMPLES

The following examples are illustrative, but not limiting of the methods and compositions of the present disclosure.

25 The following materials were employed throughout the examples. Furfurylamine (99%), guaiacol (98%), carvacrol (98%), eugenol (99%), vanillin (99%), paraformaldehyde (95%), phenol (99%), (hydrochloric acid (37%), chloroform, sodium hydroxide (98%) and tetrahydrofuran (THF, 99.9%) were supplied by Sigma-Aldrich, USA. All chemicals were used as received. 5,5'-methylenedifurfurylamine (DFDA) was synthesized according to the literature 30 method [15].


The following schematic shows a general reaction mechanism for preparing benzoxazines compounds:



Preparation of renewable benzoxazine monomers

Example 1

5 Preparation of bis(5-((2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane; (Bz-DFDA-phenol) (1)




Bz-DFDA-phenol (1)

5,5'-methylenedifurfurylamine (DFDA) (2 g, 9.71 mmol) and paraformaldehyde (1.166 g, 38.84 mmol) and chloroform (20 mL) were stirred in a round-bottomed flask at room temperature for 30 min. After that phenol (1.827 g, 19.42 mmol) was slowly added. The reaction mixture was heated to 70 °C and refluxed for 20 h. A brownish viscous liquid solution was obtained. The solution was washed several times with 0.1 M NaOH aqueous solution and distilled water. The solution was precipitated in diethyl ether, filtered, and dried under vacuum to obtain Bzs as a brown solid. ¹H NMR (500 MHz, CDCl₃, ppm): δ 7.15 (d, 2H); 6.94 (d, 2H); 6.88 (d, 2H); 6.79 (m, 2H); 6.17 (d, 2H); 6.03 (d, 2H); 4.90 (s, 4H); 4.03 (s, 4H); 3.99 (s, 4H); 3.87 (s, 2H).

Example 2

Preparation of 3,3'-(5,5'-methylenebis(furan-5,2-diyl))bis(methylene))bis(8-methoxy-3,4-dihydro-2H-benzo[e][1,3]oxazine-6-carbaldehyde); (Bz-DFDA-vanillin) (2)

20 +




Bz-DFDA-vanillin (2)

5,5'-methylenedifurfurylamine (DFDA) (2 g, 9.71 mmol) and paraformaldehyde (1.166 g, 38.84 mmol) and chloroform (20 mL) were stirred in a round-bottomed flask at room temperature for 30 min. After that vanillin (2.954 g, 19.42 mmol) was slowly added. The reaction mixture was heated to 70 °C and refluxed for 20 h. A brownish viscous liquid solution was obtained. The solution was washed several times with 0.1 M NaOH aqueous solution and distilled water. The organic phase was precipitated in diethyl ether and dried under vacuum to obtain Bzs as a yellow powder. ^1H NMR (500 MHz, CDCl_3 , ppm): δ 9.82 (s, 2H); 7.45 (s, 2H); 7.15 (s, 2H); 6.19 (d, 2H); 6.03 (d, 2H); 5.03 (s, 4H); 4.10 (s, 6H); 3.98 (s, 4H); 3.94 (s, 4H); 3.89 (s, 2H).

Example 3

Preparation of 3-(furan-2-ylmethyl)-5-isopropyl-8-methyl-3,4-dihydro-2H-benzo[e][1,3]oxazine; (Bz-FA-carvacrol) (3)




Bz-FA-carvacrol (3)

Furfurylamine (5 g, 58.48 mmol), paraformaldehyde (3.091 g, 102.965 mmol) and carvacrol (7.73 g, 102.965 mmol) were mixed and stirred at room temperature. The mixture was refluxed at 70 °C for 20 h, cooled to room temperature, and concentrated under reduced pressure to obtain Bzf as a yellow solid. ^1H NMR (500 MHz, CDCl_3 , ppm): δ 7.44 (d, 1H); 7.01 (d, 1H); 6.76 (d, 1H); 6.35 (m, 1H); 6.23 (d, 1H); 4.91 (s, 2H); 4.02 (s, 2H); 3.92 (s, 2H); 2.78 (m, 1H); 2.17 (s, 3H); 1.17 (d, 6H).

Example 4

Preparation of bis(5-((5-isopropyl-8-methyl-2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane; (Bz-DFDA-carvacrol) (4)




Bz-DFDA-carvacrol (4)

5,5'-methylenedifurfurylamine (DFDA) (2 g, 9.71 mmol) and paraformaldehyde (1.166 g, 38.84 mmol) and chloroform (20 mL) were stirred in a round-bottomed flask at room temperature for 30 min. After that carvacrol (2.916 g, 19.42 mmol) was slowly added. The 5 reaction mixture was heated to 70 °C and refluxed for 20 h. A brownish viscous liquid solution was obtained. The solution was washed several times with 0.1 M NaOH aqueous solution and distilled water. The organic phase was precipitated in methanol and filtered and dried under vacuum to obtain Bzs as a yellow powder. ¹H NMR (500 MHz, CDCl₃, ppm): δ 7.0 (d, 2H); 6.96 (d, 2H); 6.15 (d, 2H); 6.01 (d, 2H); 4.91 (s, 4H); 4.03 (s, 4H); 3.88 (s, 4H); 2.78 (s, 2H); 2.17 (s, 10 6H); 1.18 (d, 12H).

Example 5

Preparation of bis(5-((6-allyl-8-methoxy-2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane; (Bz-DFDA-eugenol) (5)



15 **Bz-DFDA-eugenol (5)**

5,5'-methylenedifurfurylamine (DFDA) (2 g, 9.71 mmol) and paraformaldehyde (1.166 g, 38.84 mmol) and chloroform (20 mL) were stirred in a round-bottomed flask at room temperature for 30 min. After that eugenol (2.954 g, 19.42 mmol) was slowly added. The 20 reaction mixture was heated to 70 °C and refluxed for 20 h. A brownish viscous liquid solution was obtained. The solution was washed several times with 0.1 M NaOH aqueous solution and distilled water. The organic phase was dried over anhydrous MgSO₄ and the solvent was removed. The residual solid obtain Bzs as a yellow powder. ¹H NMR (500 MHz, CDCl₃, ppm): δ 7.15 (d, 2H); 6.78 (d, 2H); 6.17 (d, 2H); 6.05 (d, 2H); 5.92 (m, 2H); 5.01 (s, 4H); 5.04 (s, 2H); 4.79 (d, 2H); 3.83 (s, 6H); 3.76 (s, 4H); 3.70 (s, 4H); 3.51 (s, 2H); 3.33 (d, 4H).

Preparation of benzoxazine/Glass Fiber Composites

The thermal profiles obtained from the DMA measurement of benzoxazine and glass fiber composites showed curing kinetic behavior of polyimide composites. The initial sharp initial loss 30 of storage modulus benzoxazine/glass fiber composites results from the melt of the monomers. It is evident that the chemical reaction leading to chain extension does not occur below 100 °C. It

suggest that the furan-based benzoxazine monomers have large temperature window for processing of resin systems. Further, the storage modulus of benzoxazine/glass fiber composites tends to increase at higher temperature, which reflect the occurrence of thermally activated chemical reactions within the matrix networks lead to further crosslinking and other form of matrix developments.

Material Characterization

Mid-IR was used to identify functional groups on the benzoxazines using a Thermo Nicolet Nexus 870 FT-IR spectrometer in absorbance mode with 32 scans and an 8 cm⁻¹ resolution at RT with a deuterated tryglycine sulfate (DTGS) detector in 650-4000 cm⁻¹ range. Dynamic mechanical analysis (DMA) and thermogravimetric analysis (TGA) were used to investigate the thermal and mechanical properties of cured samples. DMA samples were tested using a TA Q800 DMA in single cantilever geometry with a 1 Hz frequency, 15 µm amplitude and 2 °C/min ramp rate from 25 to 400°C. Each sample was tested twice and the first and second both scan were reported, the first scan was used to obtain its glass transition temperature (T_g). A TA Q50 TGA was employed to investigate the thermal stability of samples in argon and air environment by heating from 25°C to 800°C with 1°C/min ramp rate.

The structures of the novel biobased benzoxazine monomers are supported by the IR spectra shown in FIG. 5. The oxazine ring is indicated by the aromatic C-O-C between 1220 cm⁻¹ and 1235 cm⁻¹ and aliphatic C-N stretching at 1020 cm⁻¹, indicating the formation of an oxazine ring fused to the benzene ring. The characteristic peaks attributable to the furan ring of Bzf are observed at 1584 cm⁻¹ for all the biobased benzoxazine. The monomer BZ-DFDA-vanillin displayed the peak at 1686 cm⁻¹ for the C=O stretching of carbonyl. The BZ-DFDA-carvacrol and BZ-FA-carvacrol show the distinguish peak at 1359 cm⁻¹ due to the isopropyl group. As can be seen FIG. 6, BZ-DFDA-phenol does not show the melt endotherm. The BZ-DFDA Vanillin, BZ-FA-carvacrol, BZ-DFDA-carvacrol benzoxazine monomers exhibit melting endotherms 55, 60 and 150 °C respectively. A significant influence of the monomer structure on melting temperatures is observed. In addition to melting endotherm, all benzoxazine monomers present a relatively broad range of exothermic peak between 200 and 275°C which is characteristic for the curing process of conventional non-activated.

The exothermic final for the BZ-DFDA-phenol, BZ-DFDA-vanillin, BZ-FA-carvacrol and BZ-DFDA-carvacrol monomers was observed at 242, 201, 266 and 271 °C, respectively (FIGs. 6-9). It is well known that ring-opening polymerization of benzoxazine will exhibit an exothermic peak around 200-280 °C. The biobased benzoxazines monomers also demonstrated a similar exothermic manners in the high-temperature range. The processing window is defined as

the temperature difference between the melting point and onset of polymerization. All the monomer shows a wide processing window.

The thermal profiles obtained from the DMA measurement of benzoxazine monomers and glass fiber composites showed curing kinetic behavior of benzoxazine composites (FIGs. 10-13).

5 The initial sharp loss of storage modulus of Bz-DFDA-phenol/glass fiber, Bz-DFDA-vanillin/glass fiber and Bz-FA-carvacrol/glass fiber around 40-60 °C results from the melt of the monomers. However, the higher (150 °C) initial loss of storage modulus was observed for Bz-DFDA-carvacrol/glass fiber composites. It is evident that the chemical reaction leading to chain extension does not occur below 100 °C. Further the storage modulus of Bz-DFDA-phenol/glass 10 fiber, Bz-DFDA-vanillin/glass fiber, Bz-FA-carvacrol/glass fiber, and Bz-DFDA-carvacrol/glass fiber composites tends to increase around 140, 165, 250 and 235 °C respectively, which reflect the occurrence of thermally activated chemical reactions within the matrix networks lead to further crosslinking and other form of matrix developments. Which matches with the DSC data and it suggest that the furan-based benzoxazines have large temperature windows for processing 15 of resin systems.

REFERENCES

The following references may be useful in understanding some of the principles discussed herein:

20 [1] Lligadas G, Tuzun A, Ronda JC, Galia M, Cadiz V. Polybenzoxazines: new players in the bio-based polymer arena. *Polymer Chemistry*. 2014;5:6636-44.

[2] Takeichi T, Kawauchi T, Agag T. High Performance Polybenzoxazines as a Novel Type of Phenolic Resin. *Polym J*. 2008;40:1121-31.

25 [3] Ghosh NN, Kiskan B, Yagci Y. Polybenzoxazines—New high performance thermosetting resins: Synthesis and properties. *Progress in Polymer Science*. 2007;32:1344-91.

[4] Sini NK, Bijwe J, Varma IK. Renewable benzoxazine monomer from Vanillin: Synthesis, characterization, and studies on curing behavior. *Journal of Polymer Science Part A: Polymer Chemistry*. 2014;52:7-11.

30 [5] Kotzebue LRV, Ribeiro FWM, Sombra VG, Feitosa JPA, Mele G, Mazzetto SE, et al. Spectral and thermal studies on the synthesis and catalyzed oligomerization of novel cardanol-based benzoxazines. *Polymer*. 2016;92:189-200.

[6] Baroncini EA, Kumar Yadav S, Palmese GR, Stanzione JF. Recent advances in bio-based epoxy resins and bio-based epoxy curing agents. *Journal of Applied Polymer Science*. 2016;133:n/a-n/a.

[7] Puchot L, Verge P, Fouquet T, Vancaeyzeele C, Vidal F, Habibi Y. Breaking the symmetry of dibenzoxazines: a paradigm to tailor the design of bio-based thermosets. *Green Chemistry*. 2016;18:3346-53.

[8] Sini NK, Bijwe J, Varma IK. Thermal behaviour of bis-benzoxazines derived from renewable feed stock 'vanillin'. *Polymer Degradation and Stability*. 2014;109:270-7.

[9] Froimowicz P, R. Arza C, Han L, Ishida H. Smart, Sustainable, and Ecofriendly Chemical Design of Fully Bio-Based Thermally Stable Thermosets Based on Benzoxazine Chemistry. *ChemSusChem*. 2016;9:1921-8.

[10] Periyasamy T, Asrafali SP, Muthusamy S. New benzoxazines containing polyhedral oligomeric silsesquioxane from eugenol, guaiacol and vanillin. *New Journal of Chemistry*. 2015;39:1691-702.

[11] Wang J, Liu W, Feng T. Chapter 28 - Furan-Based Benzoxazines A2 - Ishida, Hatsuo. In: Froimowicz P, editor. *Advanced and Emerging Polybenzoxazine Science and Technology*. Amsterdam: Elsevier; 2017. p. 533-67.

[12] Dumas L, Bonnaud L, Olivier M, Poorteman M, Dubois P. Eugenol-based benzoxazine: from straight synthesis to taming of the network properties. *Journal of Materials Chemistry A*. 2015;3:6012-8.


[13] Thirukumaran P, Shakila Parveen A, Sarojadevi M. Synthesis and Copolymerization of Fully Biobased Benzoxazines from Renewable Resources. *ACS Sustainable Chemistry & Engineering*. 2014;2:2790-801.

[14] Wang C, Sun J, Liu X, Sudo A, Endo T. Synthesis and copolymerization of fully bio-based benzoxazines from guaiacol, furfurylamine and stearylamine. *Green Chemistry*. 2012;14:2799-806.

[15] Hu F, Yadav SK, La Scala JJ, Sadler JM, Palmese GR. Preparation and Characterization of Fully Furan-Based Renewable Thermosetting Epoxy-Amine Systems. *Macromolecular Chemistry and Physics*. 2015;216:1441-6.

CLAIMS:


1. A benzoxazine compound of Formula (I) or Formula (III), wherein Formula (I) has the following structure:



5

(I)

wherein R₁ and R₂ in Formula (I) are independently selected from hydrogen, a straight or branched alkyl having 1-4 carbon atoms, a straight or branched alkenyl having 1-4 carbon atoms, a straight or branched alkoxy group having 1-4 carbon atoms and -C(=O)H; R₃ is hydrogen or a group having Formula (II):



10

(II)

wherein R₁ and R₂ in Formula (II) are independently selected from the same groups for R₁ and R₂ that are defined above, $\text{---}^{\text{+}}$ represents the bond to the ring carbon of the furan ring in Formula (I), and R₄ in Formula (II) is selected from hydrogen an optionally substituted alkyl group having


15 1 to 20 carbon atoms, an optionally substituted alkene group having 2 to 20 carbon atoms, an optionally substituted cycloalkyl group having 3 to 12 carbon atoms, an optionally substituted aryl group having 6 to 16 carbon atoms, and an optionally substituted heterocyclic group having 3 to 16 carbon atoms; wherein the alkyl group, alkene group, cycloalkyl group, aryl group or heterocyclic group can be substituted with 1 to 5 substituents independently selected from a
20 halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, an aryl group having 6 to 16 carbon atoms, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms,

R₅ in Formula (II) is selected from hydrogen an optionally substituted alkyl group having 1 to 20 carbon atoms, an optionally substituted alkene group having 2 to 20 carbon atoms, an
25 optionally substituted cycloalkyl group having 3 to 12 carbon atoms, an optionally substituted aryl group having 6 to 16 carbon atoms, and an optionally substituted heterocyclic group having

3 to 16 carbon atoms; wherein the alkyl group, alkene group, cycloalkyl group, aryl group or heterocyclic group can be substituted with 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, an aryl group having 6 to 16 carbon atoms, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms

5 wherein R₄ and R₅ in Formula (II) cannot both be hydrogen;

wherein Formula (III) has the following structure:



(III)

10 wherein R¹ and R² in Formula (III) are independently selected from the same groups for R₁ and R₂ that are defined above, wherein R⁷ and R⁹ are independently selected from hydrogen, an optionally substituted alkyl group having 1 to 20 carbon atoms, an optionally substituted alkene group having 2 to 20 carbon atoms, an optionally substituted heterocyclic group with 3 to 15 carbon atoms, optionally substituted aryl group having 6 to 15 carbon atoms and an optionally 15 substituted cycloalkyl group having 3 to 12 carbon atoms; wherein the alkyl group, alkene group, heterocyclic group, aryl group, or cycloalkyl group can be substituted with 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, an aryl group having 6 to 15 carbon atoms, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms, and wherein the aryl group 20 substituent and the heterocyclic group substituent can be further substituted with hydroxy, an alkoxy group having 1 to 20 carbon atoms, or an alkylamino group having 1 to 2 carbon atoms; and

25 R⁸ is an optionally substituted alkylene group having 1 to 20 carbon atoms, an optionally substituted alkenylene group having 2 to 20 carbon atoms, an optionally substituted heterocyclic group with 3 to 15 carbon atoms, optionally substituted arylene group having 6 to 15 carbon atoms and an optionally substituted cycloalkylene group having 3 to 12 carbon atoms; wherein

the alkylene group, alkenylene group, heterocyclic group, arylene group, or cycloalkylene group can be substituted with 1 to 4 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms.

5

2. The benzoxazine compound of claim 1, wherein R_1 and R_2 of Formula (I) and R^1 and R^2 of Formula (III) are independently selected from methyl, isopropyl, methoxy, $-C(=O)H$ and $-CH_2-CH=CH_2$ and R_3 is hydrogen.

10

3. The benzoxazine compound of any one of claims 1-2, wherein R_3 is a group having Formula (II) and the benzoxazine compound is symmetrical in that R_1 and R_2 of Formula (I) are identical to R_1 and R_2 of Formula (II), respectively.

15

4. The benzoxazine compound of any one of claims 1-3, wherein R_1 and R_2 of Formula (I) are not hydrogen and are bonded at the 6-position and 8-position of the benzoxazine ring, respectively.

5. The benzoxazine compound of any one of claims 1-3, wherein:

(a) R_1 and R_2 of Formula (I) are not hydrogen and are bonded at the 6-position and 8-position of the benzoxazine ring, respectively, and R_1 and R_2 of Formula (II) are not hydrogen and are bonded at the 6-position and 8-position of the benzoxazine ring, respectively; or

(b) R_1 and R_2 of Formula (I) are not hydrogen and are bonded at the 5-position and 8-position of the benzoxazine ring, respectively, and R_1 and R_2 of Formula (II) are not hydrogen and are bonded at the 5-position and 8-position of the benzoxazine ring, respectively.

25

6. The benzoxazine compound of claim 1, wherein:

R_4 and R_5 are each independently selected from:

hydrogen, an optionally substituted alkyl group having 7 to 20 carbon atoms, an optionally substituted alkene group having 3 to 20 carbon atoms, an optionally substituted cycloalkyl group having 3 to 12 carbon atoms and an optionally substituted phenyl group,

wherein the alkyl group, alkene group, cycloalkyl group or phenyl group can be substituted with 1 to 5 substituents independently selected from an alkyl group having 1-10 carbon atoms, a hydroxyl group, and an alkoxy group having 1 to 20 carbon atoms, and wherein both R_4 and R_5 cannot be hydrogen.

35

7. The benzoxazine compound of claim 1, wherein:

R₄ is hydrogen; R₅ is a phenyl group which is optionally substituted with a hydroxyl group, an alkoxy group having 1 to 4 carbon atoms, an alkyl group having 1 to 6 carbon atoms, and an alkene group having 2 to 4 carbon atoms.

5

8. The benzoxazine compound of claim 1, wherein:

R₄ and R₅ are each independently selected from:

hydrogen, an optionally substituted alkyl group having 8 to 18 carbon atoms, an optionally substituted alkene group having 4 to 18 carbon atoms, and an optionally substituted cycloalkyl group having 3 to 8 carbon atoms, wherein the alkyl group, alkene group, or cycloalkyl group can be substituted with 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 8 carbons, and an alkoxy group having 1 to 8 carbon atoms; and

wherein only one of R₄ and R₅ can be a hydrogen.

15

9. The benzoxazine compound of claim 1, which is:

- a. bis(5-((2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane;
- b. 3,3'-(5,5'-methylenebis(furan-5,2-diyl))bis(methylene))bis(8-methoxy-3,4-dihydro-2H-benzo[e][1,3]oxazine-6-carbaldehyde);
- c. 3-(furan-2-ylmethyl)-5-isopropyl-8-methyl-3,4-dihydro-2H-benzo[e][1,3]oxazine;
- d. bis(5-((5-isopropyl-8-methyl-2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane; or
- e. bis(5-((6-allyl-8-methoxy-2H-benzo[e][1,3]oxazin-3(4H)-yl)methyl)furan-2-yl)methane.

25


10. A method of forming the benzoxazine compound of Formula (I) of claim 1, comprising reacting a furfurylamine compound, a formaldehyde compound, and a phenol compound.

30

11. The method of claim 10, wherein the phenol compound is selected from phenol, bisphenol A, bisguaiacol, vanillin, carvacrol and eugenol.

12. The method of any one of claims 10-11, wherein the furfurylamine compound is a compound of Formula (IV) or a compound of Formula (V),


35 wherein the compound of Formula (IV) is a difuran diamine compound having the following structure,



(IV)

wherein R and R¹ are independently selected from hydrogen, an optionally substituted alkyl group having 1 to 20 carbon atoms, an optionally substituted alkene group having 2 to 20 carbon atoms, an optionally substituted cycloalkyl group having 3 to 12 carbon atoms, an optionally substituted aryl group having 6 to 16 carbon atoms, and an optionally substituted heterocyclic group having 3 to 16 carbon atoms; wherein the alkyl group, alkene group, cycloalkyl group, aryl group or heterocyclic group can be substituted with 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms, wherein only one of R and R¹ can be hydrogen;

wherein the compound of Formula (V) is a tetrafuran tetramine compound with the following structure,



15

(V)

wherein R⁷ and R⁹ are independently selected from hydrogen, an optionally substituted alkyl group having 1 to 20 carbon atoms, an optionally substituted alkene group having 2 to 20 carbon atoms, an optionally substituted heterocyclic group with 3 to 15 carbon atoms, optionally substituted aryl group having 6 to 15 carbon atoms and an optionally substituted cycloalkyl group having 3 to 12 carbon atoms; wherein the alkyl group, alkene group, heterocyclic group, aryl group, or cycloalkyl group can be substituted with 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, an aryl group having 6 to 15 carbon atoms, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms, and wherein the aryl group substituent and the heterocyclic group substituent can be further substituted with hydroxy, an alkoxy group having 1 to 20 carbon atoms, or an alkylamino group having 1 to 2 carbon atoms; and

R⁸ is an optionally substituted alkylene group having 1 to 20 carbon atoms, an optionally substituted alkenylene group having 2 to 20 carbon atoms, an optionally substituted heterocyclic

group with 3 to 15 carbon atoms, optionally substituted arylene group having 6 to 15 carbon atoms and an optionally substituted cycloalkylene group having 3 to 12 carbon atoms; wherein the alkylene group, alkenylene group, heterocyclic group, arylene group, or cycloalkylene group can be substituted with 1 to 4 substituents independently selected from a halogen, hydroxy, 5 amino, nitro, cyano, carboxy, an alkyl group having 1 to 20 carbons, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms.

13. The method of any one of claims 10-12 wherein the formaldehyde compound is selected from formaldehyde and paraformaldehyde.

10

14. The method of claim 10, further comprising an inert organic solvent, and heating a reaction mixture comprising said furfurylamine compound, said formaldehyde compound, and said phenol compound at temperatures between 60-85°C.


15

15. The method of claim 14, wherein the inert organic solvent is selected from an aliphatic or cycloaliphatic alcohol, an ester, a ketone, an aromatic or aliphatic hydrocarbon, a halogenated hydrocarbon and a mixture of one or more of the foregoing solvents.

20

16. The method of claim 15, wherein the inert organic solvent is a halogenated hydrocarbon selected from chloroform and methylene chloride.

17. A polymer formed by ring opening polymerization of at least one benzoxazine compound of the Formula (I) or Formula (III) of claim 1, and optionally including an epoxidation reaction with a diepoxide of the following Formula (VI):




25

wherein R₆ is an alkylene group having 1 to 20 carbon atoms, an alkenylene group having 2 to 20 carbon atoms, an heterocyclic group with 3 to 15 carbon atoms, an arylene group having 6 to 15 carbon atoms and a cycloalkylene group having 3 to 12 carbon atoms; wherein the alkylene group, alkenylene group, heterocyclic group, arylene group, or cycloalkylene group can be substituted with 1 to 5 substituents independently selected from a halogen, hydroxy, amino, nitro, 30 cyano, carboxy, an alkyl group having 1 to 20 carbons, a heterocyclic group having 3 to 16 carbons, and an alkoxy group having 1 to 20 carbon atoms.


18. A polymer formed by ring opening polymerization of at least one benzoxazine compound of the Formula (I) or Formula (III) of claim 1, and optionally including an epoxidation reaction with an epoxide selected from the group consisting of dibisphenol A epoxy resin, bisphenol F epoxy resin, novolac epoxy resin, aliphatic epoxy resin, glycidylamine epoxy resin, phenyl glycidyl ether, tetraglycidyl 4,4'-diaminodiphenylmethane, diepoxide having a phenyl-sulfone-phenyl group, and diglycidyl ether having a Bisphenol B, C, D, or E group.

19. The polymer of claim 17 or 18, wherein the epoxy group-containing compound is a
10 bisphenol-A diglycidyl ether (DGEBA) epoxy resin compound or an oligomer thereof.

20. A polymer comprising at least one repeating unit selected from a unit of Formula (VII) and a unit of Formula (VIII)




(VII)




(VIII)

wherein R₁ and R₂ in Formulae (VII) and (VIII) are independently selected from hydrogen, a straight or branched alkyl, alkenyl, or alkoxy group having 1-4 carbon atoms and -C(=O)H, n is up to 1000; and R₃ is hydrogen, or at least one group of the Formula (II) as defined in claim 1, the Formula (IX) and the Formula (X):



(IX)



(X)

5 wherein R_1 and R_2 in Formulae (IX) and (X) are independently selected from hydrogen, a straight or branched alkyl, alkenyl, or alkoxy group having 1-4 carbon atoms and $-C(=O)H$, n is up to 1000, and

wherein the circled methylene group in Formula (IX) and Formula (X) is optionally substituted with R_4 and R_5 or R_7 and R_9 as defined in claim 1.

10

21. The compound or polymer of any one of claims 1-9 and 17-20,

wherein in R_1 , R_2 and R_3 of Formula (I), R_1 , R_2 , R_4 and R_5 of Formula (II), R_1 , R_2 , R_7 and R_9 of Formula (III), R and R_1 of Formula (IV), R_7 and R_9 of Formula (V), R_1 , R_2 and R_3 of Formula (VII), R_1 , R_2 and R_3 of Formula (VIII), R_1 and R_2 of Formula (IX), and R_1 and R_2 of Formula (X)

the alkyl group is selected from a straight or branched chain butyl, pentyl, hexyl, heptyl, octyl, nonyl, decyl, undecyl and dodecyl,

the alkene group is selected from a vinyl, propenyl, or a straight or branched chain butenyl, pentenyl, hexenyl, heptenyl, octenyl, nonenyl, decenyl, undecenyl and dodecenyl,

5 the cycloalkyl group is selected from a cyclopentyl or cyclohexyl,

the aryl group is selected from phenyl, tolyl, and biphenyl,

the heterocyclic group is selected from pyrrolidine, pyrrole, tetrahydrofuran, furan, tetrahydrothiophene, thiophene, imidazolidine, pyrazolidine, imidazole, pyrazole, oxazolidine, isoxazolidine, oxazole, isoxazole, thiazolidine, isothiazolidine, thiazole, isothiazole, dioxolane, 10 dithiolane, piperidine, pyridine, bipyridine, tetrahydropyran, pyran, piperazine, diazines, morpholine, oxazine, thiomorpholine, and thiazine; and

wherein in R₈ of Formula (III), R₈ of Formula (V), and R₆ of Formula (VI)

the alkylene group is selected from a straight or branched chain butylene, pentylene, hexylene, heptylene, octylene, nonylene, decylene, undecylene and dodecylene,

15 the alkenylene group is selected from a vinylene, propenylene, or a straight or branched chain butenylene, pentenylene, hexenylene, heptenylene, octenylene, nonenylene, decenylene, undecenylene and dodecenylene,

the cycloalkylene group is selected from a cyclopentylene or cyclohexylene,

the arylene group is selected from phenylene, tolylene, and biphenylene; and

20 wherein the groups are optionally substituted with 1-4 substituents and the optional substituents are selected from group consisting of an alkyl group having 1 to 3 carbons, an aldehyde, a hydroxyl group and methoxy group.

22. A polymer composition comprising the polymer of any one of claims 17-20 and further

25 comprising one or more of fibers, clays, silicates, fillers, whiskers, pigments, corrosion inhibitors, flow additives, film formers, defoamers, coupling agents, antioxidants, stabilizers, flame retardants, reheating aids, plasticizers, flexibilizers, anti-fogging agents, nucleating agents, or combinations thereof.

30 23. The polymer composition according to claim 22, comprising the pigment, the corrosion inhibitor and the fibers and wherein the pigment is selected from titanium dioxide, iron oxides, carbon black and mixtures thereof; the corrosion inhibitor is zinc phosphate; and the fibers are glass fibers.

24. The polymer of any one of claims 17-23, wherein the glass transition temperature ranges from 100°C to 300°C, or 120°C to 280°C or 170°C to 275°C.

25. The polymer of any one of claims 17-23, wherein the flexural modulus ranges from 2 GPa to

5 4 GPa at room temperature, or from 2.2 GPa to 3.8 GPa at room temperature, or from 2.5 GPa to 3.7 GPa at room temperature.

26. The polymer of any one of claims 17-23, wherein the flexural strength is greater than 20 MPa at room temperature, or greater than 22 MPa at room temperature, or greater than 25 MPa at

10 room temperature.

27. The polymer of any one of claims 17-23, wherein the UL-94 flammability (standard of 2017) is a V-0 or a V-1 rating.




FIG. 1




FIG. 2




FIG. 3







FIG. 4

**FIG. 5**

**FIG. 6****FIG. 7**




FIG. 8






FIG. 9

**FIG. 10****FIG. 11**




FIG. 12




FIG. 13