

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
22 January 2009 (22.01.2009)

PCT

(10) International Publication Number
WO 2009/010445 A2

(51) International Patent Classification:
B22F 9/00 (2006.01) **C22C 33/02** (2006.01)

(21) International Application Number:
PCT/EP2008/058999

(22) International Filing Date: 10 July 2008 (10.07.2008)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
PA 2007 01057 17 July 2007 (17.07.2007) DK
60/935,004 20 July 2007 (20.07.2007) US

(71) Applicant (for all designated States except US): **Höganäs AB (publ)** [SE/SE]; S-263 83 Höganäs (SE).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **LARSSON, Mats** [SE/SE]; Mäster Jacobs gata 3 A, S-254 36 Helsingborg (SE).

(74) Agent: **Zacco Denmark A/S**; Hans Bekkevolds Allé 7, DK-2900 Hellerup (DK).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished upon receipt of that report

(54) Title: IRON-BASED POWDER COMBINATION

(57) Abstract: The invention relates to a powder metallurgical combination comprising: - an iron-based powder A comprising core particles of iron to which core particles nickel is diffusion alloyed and wherein said nickel diffusion alloyed to said core particles comprise 4-7%, preferably 4,5-6% by weight of said iron-based powder A, and - a powder B, substantially consisting of particles of pure iron. Further the invention relates to a method for preparing a powder metallurgical combination.



WO 2009/010445 A2

IRON-BASED POWDER COMBINATIONFIELD OF THE INVENTION

The present invention refers to iron-based powder
5 metallurgical combinations and to methods for preparing
sintered powder metallurgical components there from. More
specifically the invention refers to the production of
sintered components including nickel and nickel together
with copper by using these combinations.

10

BACKGROUND OF THE INVENTION

Within the powder metallurgical field, copper and nickel
has since long been used as alloying elements in the
15 production of high strength sintered components.

Sintered iron-based components can be produced by mixing
alloying elements with iron based powders. However, this
may cause problems with dust and segregation which may
20 lead to variations in size and mechanical properties of
the sintered component. As for nickel powder used in
powder metallurgy the absence of "dusting" is of outmost
importance as nickel dust is hazardous and creates a work
environmental problem. In order to avoid segregation the
25 alloying elements may be pre-alloyed or diffusion alloyed
with the iron powder. In one method the iron powder is
diffusion alloyed with copper and nickel for production
of sintered components from iron-based powder
compositions containing nickel and copper.

30

It is however obvious that, when producing a sintered
iron-based component, from a powder wherein copper and
nickel are diffusion alloyed, the content of the alloying

elements in the sintered iron-based component will be substantially identical with the content of alloying elements in the used diffusion alloyed powder, and that in order to reach different contents of the alloying elements in the sintered component yielding different properties, iron-based powders having different contents of the alloying elements have to be used.

A problem is, among other things, that a specific powder is required for each desired chemical composition of a sintered iron-based component having alloying elements from e.g. nickel, or nickel in combination with copper. Another problem is to assure proper mechanical properties of such a sintered iron-based component having alloying elements from nickel, or nickel in combination with copper component and combined with pure iron powder.

SUMMARY OF THE INVENTION

It is an object of the present invention to, among other things, solve the abovementioned technical problem of the prior art.

It has surprisingly been found that the content of nickel diffusion bonded to the iron powder, both when the nickel containing diffusion alloyed powder is used in combination with essentially pure iron powder, and also when the nickel alloyed iron-based powder is used in combination with iron powder having copper diffusion bonded to the surface and essentially pure iron powder, is of outmost importance for properties such as:

- the dimensional change between the compacted and sintered component,
- mechanical properties of the sintered component,
- compressibility of the diffusion bonded nickel containing powder and
- the degree of bonding of nickel to the iron powder.

- In order to obtain sufficient hardness, tensile strength and yield strength and sufficient low and stable dimensional change for components containing iron, nickel and carbon, in combination with high degree of bonded
5 nickel particles, it has been found that the amount of nickel diffusion bonded to the surface of the nickel containing diffusion alloyed powder should be between 4-7% by weight, preferably 4,5- 6% by weight.
- 10 Further the present invention provides a method of eliminating the need of producing a specific powder for each desired chemical composition of the sintered iron-based component having alloying elements from nickel, or
15 offers the advantage of providing a combination of iron powder, iron powder diffusion alloyed with copper and iron powder diffusion alloyed with nickel wherein the segregation of alloying elements and hence the variation of mechanical properties of components produced from said
20 combination is minimized.

In brief the invention concerns a powder metallurgical combination of a nickel-alloyed iron-based powder mixed with substantially pure iron powder. The nickel-alloyed
25 iron-based powder is comprised of core particles of iron, which is diffusion alloyed with nickel.

Additionally, the powder metallurgical powder may further comprise pure iron powder particles additionally
30 diffusion alloyed with copper.

The invention also concerns the iron-based powder comprising core particles of iron, which is diffusion alloyed with nickel.
35

The invention also concerns a method comprising the steps of combining essentially pure iron powder with iron powder having nickel diffusion bonded to the surface of

the iron powder or combining essentially pure iron powder with iron powder having nickel diffusion bonded to the surface the iron powder and iron powder having copper diffusion bonded to the surface of the iron powder,
5 mixing the iron-based powders in predetermined amounts, possibly mixing the combination with graphite and/or optionally other additives, compacting the mixture and sintering the obtained green bodies into sintered bodies having a negligible variation of alloying elements and
10 variation of mechanical properties.

DETAILED DESCRIPTION OF THE INVENTION

Specifically the iron-based powder metallurgical
15 combination according to the invention may for example comprise or consist of:

- an iron-based powder A essentially consisting of core particles of iron, whereby 4-7%, preferably 4,5-6% by weight of nickel is diffusion alloyed to the core
20 particles, and
- an iron-based powder B, essentially consisting of particles of pure iron.

That the iron-based powder B essentially consists of particles of pure iron or consists of essentially pure
25 iron, or that the iron-based powder A essentially consists of core particles of iron diffusion alloyed with nickel means that the total amount of particles only contains the defined particles and trace amounts of other components, where "trace amounts" indicate that the other
30 components are not intentionally added.

In particular the essentially pure iron powder is not pre-alloyed with any other metal.

Optionally, the powder metallurgical combination may comprise an iron-based powder, C, essentially consisting
35 of core particles of iron having copper diffusion alloyed to the core particles. "Essentially consisting of" has the same definition for powder C as for powder A and B. Suitable powders may be Distaloy Cu and Distaloy ACu

available from Höganäs AB, Sweden, having about 10 % by weight of copper diffusion alloyed to the iron powder, or of Distaloy MH, available from Höganäs AB, Sweden, having about 25 % by weight of copper diffusion alloyed to the
5 iron powder.

Other elements pre-alloyed to the base powder of powder A, B and C, may be present, for example impurities, such as nickel, copper, chromium, silicon, phosphorous and
10 manganese.

In order to produce a sintered component from the powder combination according to the present invention the respective amounts of powder A, and B or powder A, B and
15 C are determined and mixed with graphite in the amount required in order to obtain sufficient mechanical properties, the obtained mixture may be mixed with other additives before compaction and sintering. The amount of graphite which is mixed in the powder combination is up
20 to 1%, preferably 0.2-0.8%.

Other additives may be selected from the group consisting of lubricants, binders, other alloying elements, hard phase materials, machinability enhancing agents.

25

The relation between powder A, B and C is preferably chosen so that the copper content will be 0-4%, preferably 0,5-3% by weight and the nickel content will be 0,5-6%, preferably 1-5 % by weight of the sintered
30 component.

The powders are mixed with graphite to obtain the final desired carbon content. The powder combination is compacted at a compaction pressure between 400-1000 MPa
35 and the obtained green body is sintered at 1100-1300°C for 10-60 minutes in a protective atmosphere. The sintered body may be subjected to further post

treatments, such as heat treatment, surface densification, machining etc.

According to the present invention sintered components
5 containing various amounts of nickel or copper and nickel
may be produced. This is achieved by using a combination
of two (A and B) or three (A and B and C) different
powders, which are mixed in different proportions to
achieve a powder having the required chemical composition
10 for the actual sintered component.

Example 1

This example demonstrates the influence of different
15 contents of nickel diffusion bonded to the surface of the
iron powder.

Iron- based powders having different content of nickel
diffusion bonded to the surface of the iron powder were
produced by mixing 2%, 4%, 6%, 10%, 15% and 20 % by
20 weight respectively, of Ni - powder, INCO 123 from the
company INCO Europe Ltd, UK, according to table 1, with
the iron powder ASC100.29 from Höganäs AB, Sweden.
The mixed powders were then subjected to a diffusion
bonding treatment by annealing the powders at 840°C
25 during 60 minutes in an atmosphere of dissociated
ammonia, (25 % hydrogen, 75 % nitrogen). The obtained
material was further crushed and sieved and powders
having a particle size less than 212 µm were obtained.

30 Metallographic structures and mechanical properties

The above produced powders were further mixed with
ASC100.29, (except sample 2-2 and 4-4), graphite UF4 from
Kropfmühl AG, Germany and as lubricant amide wax from
35 Clariant, Germany giving powder metallurgical
compositions containing 2% or 4 % by weight of nickel,
0,8 % of graphite and 0,8 % of amide wax, according to
table 1. For comparison reasons powder metallurgical

compositions having 2% or 4 % by weight of admixed nickel powder, 0,8 % by weight of graphite and 0,8 % by weight of amide wax were produced, (sample 2-0 and 4-0).

- 5 The compositions were pressed at 600 MPa into tensile test samples according to ISO 2740, the samples were further sintered at 1120°C for 30 minutes in an atmosphere of 90 % nitrogen/10 % hydrogen.

10 Table 1

Sample no	Ni content of composition [% by weight]	Ni content of diffusion bonded powder [% by weight]	Graphite [% by weight]	Amide wax [% by weight]
2-0	2	-	0,8	0,8
2-2	2	2	0,8	0,8
2-4	2	4	0,8	0,8
2-6	2	6	0,8	0,8
2-10	2	10	0,8	0,8
2-15	2	15	0,8	0,8
2-20	2	20	0,8	0,8
4-0	4	-	0,8	0,8
4-4	4	4	0,8	0,8
4-6	4	6	0,8	0,8
4-10	4	10	0,8	0,8
4-15	4	15	0,8	0,8
4-20	4	20	0,8	0,8

The obtained sintered samples were tested with regards to tensile and yield strength according to EN 10002-1, hardness according to ISO 4498, dimensional change according to ISO 4492.

Metallographic examinations were performed by light optical microscopy. Table 2 shows result from metallographic examination and table 3 shows result from mechanical testing.

10

Table 2

Sample no	Metallographic examination
2-0	Uneven distribution of nickel, large areas of coarse pearlite
2-2	Even distribution of nickel, smaller and finer pearlite areas
2-4	Even distribution of nickel, both finer and coarser pearlite areas.
2-6	Uneven distribution of nickel, both finer and coarser pearlite areas.
2-10	Uneven distribution of nickel, large areas of coarse pearlite.
2-15	Matrix contains coarse pearlite and large austenitic areas due to locally high nickel content.
2-20	Matrix contains coarse pearlite and large austenitic areas due to locally high nickel content.
4-0	Uneven distribution of nickel, large areas of austenite and coarse pearlite
4-4	Even distribution of nickel, smaller and finer pearlite areas
4-6	Uneven distribution of nickel, both finer and coarser pearlite areas.
4-10	Uneven distribution of nickel, large areas of

	coarse pearlite.
4-15	Matrix contains coarse pearlite and large austenitic areas due to locally high nickel content.
4-20	Matrix contains coarse pearlite and large austenitic areas due to locally high nickel content.

The result presented in table 2 shows that when nickel powder is admixed to the iron powder the distribution of nickel in the matrix is uneven and less desirable

5 metallographic structures are obtained, (samples 2-0 and 4-0). On the other hand, when substantially more than 6 % by weight of nickel is diffusion bonded (diffusion alloyed) to the iron powder the structure contains coarse pearlite and austenite which has a negative influence on

10 mechanical properties, especially fatigue strength.

Table 3

Sample no	Tensile strength [MPa]	Yield strength [MPa]	Dimensional change [%]	Hardness [HV10]
2-0	477	285	-0,18	143
2-2	463	283	-0,09	156
2-4	465	275	-0,10	152
2-6	463	272	-0,10	151
2-10	460	258	-0,10	151
2-15	457	262	-0,09	153
2-20	450	260	-0,09	154
4-0	538	320	-0,34	181
4-4	520	319	-0,20	178
4-6	519	308	-0,21	177

10

4-10	507	288	-0,20	177
4-15	494	285	-0,18	178
4-20	493	282	-0,17	165

Table 3 shows that when nickel powder is admixed to the iron powder the dimensional change is substantially higher compared to when nickel is diffusion bonded to the iron powder. Further the tensile strength and yield strength is negatively influenced by an increasing amount of nickel, diffusion bonded to the iron powder, which about above 6 % by weight of the diffusion bonded powder may be regarded as not acceptable.

10

Determination of compressibility

The obtained diffusion bonded powders having 2%, 4% 6%, 10 %, 15% and 20 % by weight of nickel diffusion bonded to the surface of the iron powder were further tested with regards to compressibility. The samples were compacted at 600 MPa into green density test samples according to ISO 3927 with lubricated tool die. Table 4 shows the result of green density measurements.

20

Table 4

Amount of diffusion bonded Ni [% by weight]	Green density [g/cm ³]
2	7,15
4	7,13
6	7,12
10	7,09
15	7,07

20	7,05
----	------

The result from table 4 indicates that when substantially more than 6 % of nickel powder is diffusion bonded to the iron powder an unacceptable negatively influence on the compressibility is obtained.

Determination of degree of bonding

The amount of particles smaller than 8,8 μm and 18 μm respectively were determined by a laser diffraction method, instrument Sympatec, according to ISO 13320-1 for the diffusion bonded powders having 2%, 4%, 6%, 10 %, 15% and 20 % by weight of nickel diffusion bonded to the surface of the iron powder. Table 5 shows the result of measurements of degree of bonding.

Table 5

Amount of diffusion bonded Ni [% by weight]	Amount smaller than 8,8 μm [% by weight]	Amount smaller than 18 μm [% by weight]	Estimated amount Ni powder smaller than 18 μm [% by weight of total Ni powder]
2	0	0,6	0
4	0	0,6	0
6	0	1,0	7
10	0,1	1,4	10
15	0,3	2,2	13
20	0,3	2,8	11

As substantially all particles of the iron powder, used for the production of the diffusion bonded powder, are greater than 8,8 μm and only about 0,6 % by weight of the particles of the iron powder are smaller than 18 μm , the amount of particles smaller than 8,8 μm , and the amount of particles above 0,6 % by weight of particles smaller than 18 μm are substantially nickel particles, the amount of not bonded nickel powder can be estimated. Table 5 shows that when substantially more than 6 % of nickel powder, by weight of the resulting diffusion bonded powder, about more than 10 % of the nickel powder will be present as not bonded nickel and also present as finer respirable dust, below 10 μm .

15 Example 2

This example shows the influence of the amount of nickel powder diffusion bonded to the surface of the iron powder on the mechanical properties of sintered components, when the diffusion bonded nickel containing powders are combined with diffusion bonded copper containing iron powder and graphite.

Iron- based powders having different contents of nickel, 5%, 6%, 10%, 15% and 20% by weight respectively, of nickel powder diffusion bonded to the surface of the iron powder were produced according to example 1.

The obtained nickel containing diffusion bonded powders were further mixed with a copper containing diffusion bonded iron powder, Distaloy ACu, available from Höganäs AB, Sweden, and having 10 % of copper diffusion bonded to a core iron powder, graphite, and 0,8 % of amide wax as described in example 1. Table 6 shows the obtained compositions.

Samples were produced and tested according to example 1, and the following table 7 shows the results.

Table 6

Sample no	Ni content of composition [% by weight]	Ni content of diffusion bonded powder [% by weight]	Cu content of composition [% by weight]	Graphite content of composition [% by weight]
1Cu08C-4-5	4	5	1	0,8
1Cu08C-4-6	4	6	1	0,8
1Cu08C-4-10	4	10	1	0,8
1Cu08C-4-15	4	15	1	0,8
1Cu08C-4-20	4	20	1	0,8
2Cu05C-4-5	2	5	2	0,5
2Cu05C-4-6	2	6	2	0,5
2Cu05C-4-10	4	10	2	0,5
2Cu05C-4-15	4	15	2	0,5
2Cu05C-4-20	4	20	2	0,5

Table 7

Sample no	Tensile strength [MPa]	Yield strength [MPa]	Hardness [HV10]
1Cu08C-4-5	580	365	201
1Cu08C-4-6	569	357	191
1Cu08C-4-10	562	349	193
1Cu08C-4-15	558	337	188
1Cu08C-4-20	538	330	177
2Cu05C-4-5	587	354	185
2Cu05C-4-6	581	356	176
2Cu05C-4-10	563	337	162

14

2Cu05C-4-15	544	329	164
2Cu05C-4-20	532	317	158

The results presented in table 7 show that higher tensile strength, yield strength and hardness are obtained when copper is admixed and that the mechanical properties are negatively influenced by an increasing amount of nickel, diffusion bonded to the iron powder, which about above 6% by weight of the diffusion bonded powder may be regarded as not acceptable.

10

CLAIMS

1. A powder metallurgical combination comprising:
 - an iron-based powder A consisting of core particles of
5 iron to which core particles nickel is diffusion alloyed
and wherein said nickel diffusion alloyed to said core
particles comprise 4-7%, preferably 4,5-6% by weight of
said iron-based powder A, and
 - a powder B, substantially consisting of particles of
10 pure iron.
2. A powder metallurgical combination according to claim
1, wherein the powder metallurgical combination further
comprises an iron-based powder C consisting of core
15 particles of iron to which core particles copper is
diffusion alloyed.
3. A powder metallurgical combination according to claim
2 wherein said copper diffusion alloyed to said core
20 particles comprise 5-30%, preferably 5-15% by weight of
said iron-based powder C.
4. The powder metallurgical combination according to
anyone of claims 1 to 3, wherein the amount of copper in
25 the powder metallurgical combination is within the range
0-4%, preferably 0.5-3% by weight.
5. The powder metallurgical combination according to
anyone of the preceding claims, wherein the amount of
30 nickel in the powder metallurgical combination is within
the range 0.5-6%, preferably 1-5% by weight.
6. The powder metallurgical combination according to
anyone of the preceding claims wherein the powder
35 metallurgical combination further comprises graphite,
preferably up to 1%, more preferably 0.2-0.8% graphite by
weight.

7. The powder metallurgical combination according to anyone of the preceding claims further comprising additives selected from the group consisting of lubricants, binders, other alloying elements, hard phase materials, machinability enhancing agents.

8. A diffusion alloyed iron-based powder comprising core particles of iron, whereby 4-7%, preferably 4,5-6% by weight of nickel is diffusion alloyed to the core particles.

9. A method of preparing a powder metallurgical combination, the method comprising the steps of
- mixing an iron-based powder A comprising core particles of iron to which core particles nickel is diffusion alloyed to the powder metallurgical combination wherein said nickel diffusion alloyed to said core particles comprise 4-7%, preferably 4,5-6% by weight of said iron-based powder A, and
- mixing a powder B substantially consisting of particles of pure iron to the powder metallurgical combination.

10. A method according to claim 9, wherein the method further comprises the step of
- mixing an iron-based powder C comprising core particles of iron to which core particles copper is diffusion alloyed to the powder metallurgical combination.

11. A method according to claim 10, wherein the amount of copper in the powder metallurgical combination is within the range 0.5-4%, preferably 0.5-3% by weight.

12. A method according to anyone of claims 10 to 11, wherein the amount of nickel in the powder metallurgical combination is within the range 0.5-6%, preferably 1-5% by weight.

13. A method according to anyone of claims 10 to 12,
wherein the method further comprises mixing graphite to
the powder metallurgical combination.
- 5 14. A method according to anyone of claims 10 to 13,
wherein the method further comprises mixing additives
selected from the group consisting of lubricants,
binders, other alloying elements, hard phase materials,
machinability enhancing agents, to the powder
10 metallurgical combination.
15. A method according to anyone of claims 10 to 14,
wherein the method further comprises compacting the
powder metallurgical combination to form a compacted
15 body.
16. A method according to claim 15, wherein the method
further comprises sintering said compacted body.