

UNITED STATES PATENT OFFICE.

HARRY F. GLAIR AND OSCAR E. BRANSKY, OF WHITING, INDIANA, ASSIGNORS TO
STANDARD OIL COMPANY, OF WHITING, INDIANA, AND CHICAGO, ILLINOIS, A
CORPORATION OF INDIANA.

ART OF REMOVING WAX FROM OIL.

No Drawing.

Application filed July 7, 1922. Serial No. 573,473.

To all whom it may concern:

Be it known that we, HARRY F. GLAIR and OSCAR E. BRANSKY, citizens of the United States, residing at Whiting, in the county of Lake and State of Indiana, have invented a new and useful Improvement in the Art of Removing Wax from Oil, of which the following is a specification.

The present invention relates to the art of removing wax from lighter wax-bearing distillates from mineral oils which have been subjected to little or no cracking or thermal decomposition during distillation. An example of such an oil is that known as "34° distillate" from continuous or batch fire and steam distillation of crude oil. This distillate derives its name from the fact that the "cut" forming it is started when the stream from the still has a gravity of approximately 32 to 34° Baumé. The average gravity of "34° distillate" is from 29 to 31° Baumé.

Light wax-bearing, substantially uncracked oils of this character have hitherto not been freed from wax by chilling and filter pressing by reason of the fact that the nature of the wax differs from that of ordinary paraffine or "crystalline" wax and clogs or blocks the filter cloths of the presses. It has hence been customary, in order to free this type of oil from wax, to subject it to a further distillation, usually with steam present in such limited quantities as to permit a considerable cracking or thermal decomposition of the oil during its distillation. As a result of this redistillation, the character of the wax appeared to be altered, enabling it to be readily filtered through filter presses when chilled.

We have found that oil of the character described above may be freed from its wax content without redistillation by diluting it with an oil, preferably substantially wax-free, of somewhat lower viscosity so that the diluted oil will have a viscosity of 75 seconds Saybolt or lower at a temperature of 100° F. The average viscosity of the 34° distillate is 80 to 85 seconds Saybolt at 100° F. We have found that the most satisfactory and practical results are secured by dilution to a viscosity of 55 to 65 seconds Saybolt and preferably about 60. After such dilution the oil may be chilled and filter-pressed in the usual manner in accord-

ance with the cold test desired in the product. Any suitable diluent oil may be employed; for example, pressed distillate, or an unpressed distillate of somewhat lower viscosity, such as the 30° Baumé gravity distillate from tower or coking stills having a viscosity of about 50 seconds Saybolt at 100° F., and the like. The presence of wax in the diluent, for example, in the case of the last-mentioned diluent, does not interfere with the present operation. We may also use as a diluent the substantially wax-free portion of distillate from the fire and steam or continuous stills just preceding the "34° distillate"; for example, we may include with the "34° distillate" the cut preceding it beginning, for example, at about 37° Baumé. The diluent employed is of a lubricating oil type; that is, of higher specific gravity and viscosity than burning oils.

The proportion of diluent employed may vary in accordance with the nature of the diluent and the viscosity to which it is desired to reduce the diluted mixture. For example, when pressed distillate or tower still distillate is employed as the diluent, from 10 to 25% may be used. The precise proportion employed does not substantially affect the effectiveness of the filter-press operation, but is controlled by the expense of further refining subsequent to pressing and like operations.

The diluted oil is chilled in the usual manner, for example, to 0° or -10° F. and forced through the filter-presses, in which wax is removed. The oil separates freely from the wax in the filter-presses, and is subsequently further refined for the production of the desired lubricants in any desired manner. It is sometimes found desirable, as in pressing other oils, to carry out the filter-pressing in two stages, chilling, say to 10 to 15° F. and filter-pressing in the first stage and subsequently chilling the once-pressed oil to a lower temperature, say 0° F. or -10° F. and again pressing the oil.

We claim:

1. The method of separating wax from lighter wax-bearing, substantially uncracked oil distillates which consists in admixing therewith a hydrocarbon oil of lower viscosity and heavier than burning oil, chilling and filter-pressing the mixture.

2. The method of separating wax from lighter wax-bearing, substantially uncracked oil distillates which consists in admixing therewith a hydrocarbon oil of lower viscosity and heavier than burning oil in quantity sufficient to produce a mixture having a viscosity below 75 seconds Saybolt at 100° F., chilling and filter-pressing the mixture.
3. The method of separating wax from 34° distillate which consists in admixing therewith sufficient lower viscosity hydrocarbon oil heavier than burning oil to reduce its viscosity to below 75 seconds Saybolt at 100° F., chilling and filter-pressing the mixture.
4. The method of separating paraffin wax from the first wax-bearing cut from the fire and steam distillation of petroleum oil which consists in incorporating in said oil sufficient of the cut from the distillation of petroleum oil preceding the first wax bearing cut to reduce its viscosity to below 75 seconds Saybolt at 100° F., chilling and filter-pressing the mixture.

HARRY F. GLAIR.
OSCAR E. BRANSKY.