



Europäisches Patentamt

19

European Patent Office

Office européen des brevets



11 Publication number : **0 341 574 B1**

12

EUROPEAN PATENT SPECIFICATION

45 Date of publication of patent specification :
30.10.91 Bulletin 91/44

21 Application number : **89108062.4**

22 Date of filing : **04.05.89**

51 Int. Cl.⁵ : **C10M 111/04, C10M 169/04,
C10M 101/02,
// (C10M169/04, 101:02,
107:08, 167:00),
(C10M111/04, 101:02,
107:08), C10N20:00,
C10N40:04**

54 **Lubricating oil composition.**

30 Priority : **13.05.88 JP 114739/88**

43 Date of publication of application :
15.11.89 Bulletin 89/46

45 Publication of the grant of the patent :
30.10.91 Bulletin 91/44

84 Designated Contracting States :
BE CH DE FR GB IT LI NL SE

56 References cited :
**EP-A- 0 291 006
CH-A- 475 340
US-A- 3 838 049
US-A- 3 912 617**

73 Proprietor : **IDEMITSU KOSAN COMPANY
LIMITED
1-1, Marunouchi 3-chome Chiyoda-ku
Tokyo (JP)**

72 Inventor : **Hitoshi, Hata
c/o Idemitsu Kosan Co., Ltd. 24-4,
Anesaikagan
Ichihara-shi Chiba-ken (JP)**

74 Representative : **Türk, Gille, Hrabal
Brucknerstrasse 20
W-4000 Düsseldorf 13 (DE)**

EP 0 341 574 B1

Note : Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

DescriptionBACKGROUND OF THE INVENTION

5 1. Field of the Invention

The present invention relates to a lubricating oil composition. More specifically, it is concerned with a lubricating oil composition which is low in fatigue failure of a metal under repeated high contact stress, and also high in a traction coefficient, and yet excellent in oxidation resistance. Thus, the lubricating oil composition is suitable for a lubricating oil for power transmitting devices such as gears, bearings, traction drive mechanisms, etc.

2. Description of the Prior Art

15 Heretofore, as lubricating oils for gear, bearing and traction drive mechanisms, a paraffin type mineral oil having a high viscosity index (that is, low temperature dependency of the viscosity) and a relatively high oxidation resistance has generally and widely been used.

Lubricating oils using such paraffin type mineral oils, however, are unsatisfactory in pitting resistance or traction coefficient under repeated high contact stress, and there also is a problem that oxidation resistance is not sufficiently satisfied.

SUMMARY OF THE INVENTION

25 The present inventor has conducted earnest research to overcome the problems of the aforesaid conventional lubricating oils and to develop a lubricating oil showing high fatigue failure resistance, high traction characteristics and excellent oxidation resistance under repeated high contact stress.

As the result, it has been found that the composition in which a mineral oil having a specific property or this mineral oil and a polybutene are used as base oil(s) and additives such as an extreme pressure agent, an anti-wear agent, an oiliness agent, etc. are added thereto, becomes one having the desired properties listed above. The present invention has been accomplished based on such findings.

30 That is, the present invention is to provide a lubricating oil composition which comprises a base oil of (A) 100 to 5% by weight of a mineral oil having a kinematic viscosity at 40°C of 2 to 2000 mm²/s (cSt), a viscosity index of 70 or higher, a nitrogen content of 20 ppm or less and a bromine value of 25 or less (component(A)), and
 35 (B) 0 to 95% by weight of polybutene having a molecular weight of 200 to 1000 (component(B)) ; and at least one additive selected from an extreme pressure agent, an anti-wear agent and an oiliness agent.

DESCRIPTION OF PREFERRED EMBODIMENTS

40 In the composition of the present invention, the mineral oil alone of the component (A), or a mixture of the component (A) and the component (B), a polybutene having a molecular weight of 200 to 1000, is used as the base oil for the lubricating oil. The mineral oil to be used as the component (A) has the kinematic viscosity at 40°C of 2 to 2000 mm²/s (cSt), preferably 5 to 1000 and more preferably 10 to 500 mm²/s (cSt). If it is less than 2 mm²/s (cSt), oil film forming ability is low so that friction becomes undesirably marked. On the other hand, if
 45 it exceeds 2000 mm²/s (cSt), it causes the problem that power loss due to viscosity resistance becomes too large. Also, this mineral oil should have a viscosity index of 70 or higher, preferably 75 or higher. Here, if the viscosity index is less than 70, oxidation resistance of the composition is insufficient. Further, the above mineral oil should have a nitrogen content of 20 ppm or less, preferably 10 ppm or less. Regarding the bromine value, it should have 25 or less, preferably 10 or less. If either the nitrogen content exceeds 20 ppm or the bromine
 50 value exceeds 25, it is undesirable since fatigue lifetime lowers.

As the mineral oil of the component (A) to be used in the composition of the present invention, any mineral oils can be used so long as they have the aforesaid properties, but considering a low temperature characteristic, it is preferred that they have a pour point of -20°C or lower, more preferably -30°C or lower.

55 As the mineral oil to be used as the component (A), any materials which can be obtained by various methods are acceptable so long as they have the aforesaid properties, but more preferably, there may be mentioned a purified oil which is obtained by purifying a distillate oil with the usual method, said distillate oil having been obtained by atmospheric distillation of a paraffin base crude oil or an intermediate base crude oil, or by vacuum distillation of a residual oil resulting from the atmospheric distillation, and a deep dewaxed oil which is obtained

by subjecting the above purified oil to deep dewaxing treatment. In this case, the process for purification of the distillate oil is not critical, and various methods can be employed. Usually, the distillate oil is purified by applying such treatments as (a) hydrogenation, (b) dewaxing (solvent dewaxing or hydrogenation dewaxing), (c) solvent extraction, (d) alkali distillation or sulfuric acid treatment, and (e) clay filtration, alone or in combination with one another. It is also effective to apply the same treatment repeatedly in multi-stages. For example, (1) a method in which the distillate oil is hydrogenated, or after hydrogenation, further subjected to alkali distillation or sulfuric acid treatment, (2) a method in which the distillate oil is hydrogenated and then is subjected to dewaxing treatment, (3) a method in which the distillate oil is subjected to solvent extraction treatment and then to hydrogenation treatment, (4) a method in which the distillate oil is subjected to two or three-stage hydrogenation treatment, or after the treatment further subjected to alkali distillation or sulfuric acid treatment, (5) a method in which after the treatment of the distillate oil by the methods (1) to (4) as described above, it is again subjected to dewaxing treatment to obtain a deep dewaxed oil, and so forth can be employed.

In utilizing any of the above methods, it suffices that processing conditions be controlled so that the resulting base oil has a kinematic viscosity, a viscosity index, a nitrogen content and a bromine value each falling within the above-specified range.

In particular, in the present invention, a mineral oil obtained by deep dewaxing is preferred as the base oil. This deep dewaxing treatment is carried out by solvent dewaxing under severe conditions, or by catalytic hydrogenation dewaxing using a Zeolite catalyst.

In the composition of the present invention, the above mineral oil of the component (A) may be singly used as the base oil, and a combination of a polybutene having a molecular weight of 200 to 1000 of the component (B) and the mineral oil may be also used as the base oil. Here, the polybutene of the component (B) has a molecular weight of 200 to 1000 (this corresponds to a kinematic viscosity at 40°C of 2 to 4000 mm²/s (cSt)), and preferably 300 to 800. Also, this polybutene may be one which is hydrogenated or not hydrogenated.

By adding such polybutenes to the above mineral oils to make a base oil for the lubricating oil, elongation of life time and greater improvement in traction property can be established while maintaining oxidation resistance.

The base oil for the lubricating oil of the present invention contains 100 to 5% by weight, preferably 100 to 20% by weight, most preferably 90 to 20% by weight of the mineral oil of the component (A), and 0 to 95% by weight, preferably 0 to 80% by weight, most preferably 10 to 80% by weight of the polybutene of the component (B). If the ratio of the mineral oil is less than 5% by weight, it causes the problem that the anti-wear resistance and anti-seizure property become insufficient under severe conditions (poor lubricating condition).

Also, in the composition of the present invention, to the base oil for the lubricating oil comprising the above component (A) or a mixture of the component (A) and the component (B), at least one additive selected from an extreme pressure agent, an anti-wear agent and an oiliness agent, is necessarily formulated. Here, as the extreme pressure agent, various compounds can be used. Specifically, sulfur-based extreme pressure agents such as sulfides, sulfoxides, sulfone, thiophosphinates, thiocarbonates, dithiocarbamates, alkylthiocarbamoyls, fats and oils, sulfurized fats and oils, sulfurized olefin and the like ; phosphorus-based extreme pressure agents such as phosphoric acid esters, phosphorous acid esters, phosphoric acid ester amine salts, phosphorous acid ester amine salts, and the like ; halogen-based extreme pressure agents such as chlorinated hydrocarbons, chlorinated oils and fats, and the like ; organometallic extreme pressure agents such as thiophosphoric acid salts (e.g., zinc dithiophosphate (ZnDTP)) and thiocarbamic acid salts, and so on can be used.

Anti-wear agents which can be used include organomolybdenum compounds such as molybdenum dithiophosphate (MoDTP), molybdenum dithiocarbamate (MoDTC) and the like ; organoboric compounds such as alkylmercaptyl borate and the like ; solid lubricant-based anti-wear agents such as graphite, molybdenum disulfide, antimony sulfide, boron-containing compound, polytetrafluoroethylene and the like, and so on.

Also, oiliness agents which can be used include higher fatty acids such as oleic acid, stearic acid, and the like ; higher alcohols such as oleyl alcohol and the like ; amines ; esters ; oils and fats and so on.

These extreme pressure agents, anti-wear agents and oiliness agents cannot be strictly distinguished, and they are generally referred to as load carrying additives together. Also, in the compounds as mentioned above, there exist compounds in which some functions are combined.

In the composition of the present invention, to the base oil for the lubricating oil comprising the above component (A) or the combination of the component (A) and the component (B), one or more agents selected from these extreme pressure agents, anti-wear agents and oiliness agents may be added in a suitable amount. In general, these agents are added in the range of 0.01 to 20 parts by weight based on 100 parts by weight of the base oil for the lubricating oil.

In the composition of the present invention, various known additives including antioxidants, rust preventives, metal deactivators, viscosity index improvers, pour point depressors, deforming agents, etc. may further

be effectively formulated depending on the purpose. Here, as antioxidants, various kinds thereof are included, for example, phenol-based antioxidants as exemplified by 2,6-di-t-butyl-p-cresol ; amine-based antioxidants as exemplified by dioctyldiphenylamine ; sulfur, phosphorus-based antioxidants such as zinc dithiophosphate ; and so on.

5 Also, as rust preventives, various compounds can be used. For example, carboxylic acids or esters or salts thereof as exemplified by alkylsuccinic acid, alkenylsuccinic acid and esters thereof, sulfonic acid salts as exemplified by calcium sulfonate, barium sulfonate, sodium sulfonate, alcohols, phosphoric acids or phosphoric acid salts, etc.

10 Metal deactivators may be those which have been employed conventionally and may include, for example, thiazole-based or dithiazole-based metal deactivators. Regarding viscosity index improvers, polymers such as polymethacrylate, etc. can suitably be used.

As described above, when the lubricating oil composition of the present invention is used, fatigue damage of a metal is decreased and it shows good oxidation resistance. Further, it shows a high traction coefficient and also has excellent low temperature properties.

15 Accordingly, the lubricating composition of the present invention can be widely and effectively utilized as a lubricating oil for power transmission devices, particularly as a lubricating oil for gears, rolling bearings and traction drive mechanisms

The present invention will be described in more detail with reference to the following Examples and Comparative Examples.

20

EXAMPLES 1 TO 8, AND COMPARATIVE EXAMPLES 1 TO 3

Firstly, base oils as shown in the following Table 1 were prepared.

25 Then, by formulating various additives to these base oils, lubricating oil compositions were prepared. Thereafter, with respect to these lubricating compositions, various characteristic tests were carried out. The results are shown in Table 2.

30 In the above characteristic tests, fatigue lifetime was measured by the rolling four-ball test (as described in Japanese Patent Application Laid-Open No. 147263/1984), oxidation resistances were measured in accordance with JIS K 2514 item 3.3 and traction coefficients were measured in accordance with the method as described in Japanese Patent Application Laid-Open No. 53398/1987.

35

40

45

50

55

Table 1

	<u>Base oil (a)</u>	<u>Base oil (b)</u>	<u>Base oil (c)</u>	<u>Base oil (d)</u>	<u>Base oil (e)</u>
Kinds	Deep dewaxed oil	Two-stage hydrogenated oil	Hydrogenated polybutene	Unhydrogenated polybutene	Solvent purified oil
Kinematic viscosity at 40°C (cSt)(mm ² /s)	105.6	99.9	105.2	103.6	105.0
Viscosity index	93	106	72	92	95
Nitrogen content (ppm)	5 >	5 >	5 >	5 >	50
Bromine value	3.5	0.5	3.2	9.2	39.0
Pour point (°C)	-40	-17.5	-40 >	-40 >	-15

Table 2

	Example 1	Example 2	Example 3	Example 4	Example 5	Example 6	Comparative example 1	Comparative example 2	Example 7	Example 8	Comparative example 3
<u>Composition ratio (parts by weight)</u>											
Base oil (a)	100	-	25	50	50	75	-	-	100	50	-
Base oil (b)	-	100	-	-	-	-	-	-	-	-	-
Base oil (c)	-	-	75	50	-	25	-	50	-	50	50
Base oil (d)	-	-	-	-	50	-	-	-	-	-	-
Base oil (e)	-	-	-	-	-	-	100	50	-	-	50
Additive I*1	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	-	-	-
Additive II*2	1.0	1.0	1.0	1.0	1.0	1.0	1.0	1.0	-	-	-
Additive III*3	-	-	-	-	-	-	-	-	6.55	6.55	6.55
<u>Characteristics</u>											
Fatigue lifetime (min)	46	48	56	53	52	50	39	42	57	61	44
Oxidation resistance (min)	310	342	356	336	324	319	264	270	343	372	280
Traction coefficient	0.056	0.050	0.072	0.068	0.068	0.063	0.051	0.061	0.058	0.068	0.061

*1 SP type extreme pressure agent (trade name: Lubrizol 5034, available from The Lubrizol Corp.)

*2 A mixture of antioxidant (2,6-di-t-butyl-p-cresol), pour point depressant (polymethacrylate, weight average molecular weight: 40,000) and rust preventive agent (alkenylsuccinate)

*3 A mixture of extreme pressure agent (anti-abrasive agent) (1 part by weight of ZnDTP and 0.5 part by weight of tricresylphosphate), viscosity index improver (polymethacrylate, weight average molecular weight of 40,000, 5 parts by weight) and rust preventive agent (alkenylsuccinate, 0.05 part by weight)

As can be seen from the above Table 2, samples in Examples 1 to 6 each have long fatigue lifetimes and good oxidation resistance. Particularly, the samples of Examples 3 to 6 in which mixed base oils are used, have high performance and great improvements in traction coefficient. Also, in the samples of Examples 7 and 8, fatigue life-times are extremely long, they have excellent oxidation resistance and also in the sample of Example 8, traction coefficient is remarkably improved.

Claims

1. A lubricating oil composition which comprises a base oil of
 - (A) 100 to 5% by weight of a mineral oil having a kinematic viscosity at 40°C of 2 to 2000 mm²/s (cSt), a viscosity index of 70 or higher, a nitrogen content of 20 ppm or less and a bromine value of 25 or less, and
 - (B) 0 to 95% by weight of polybutene having a molecular weight of 200 to 1000 ; and
 at least one additive selected from an extreme pressure agent, an anti-wear agent and an oiliness agent.
2. The lubricating oil composition as claimed in Claim 1, wherein said mineral oil has a pour point of -20°C or lower.
3. The lubricating oil composition as claimed in Claim 1, wherein said mineral oil has a pour point of -30°C or lower.
4. The lubricating oil composition as claimed in Claim 1, wherein said mineral oil has a kinematic viscosity at 40°C of 5 to 1000 mm²/s (cSt).
5. The lubricating oil composition as claimed in Claim 1, wherein said mineral oil has a viscosity index of 75 or higher.
6. The lubricating oil composition as claimed in Claim 1, wherein said mineral oil has a nitrogen content of 10 ppm or less.
7. The lubricating oil composition as claimed in Claim 1, wherein said mineral oil has a bromine value of 10 or less.
8. The lubricating oil composition as claimed in Claim 1, wherein said polybutene has a molecular weight of 300 to 800.
9. The lubricating oil composition as claimed in Claim 1, wherein the base oil is composed of (A) 100 to 20% by weight of the mineral oil and (B) 0 to 80% by weight of the polybutene.
10. The lubricating oil composition as claimed in Claim 1, wherein the base oil is composed of (A) 90 to 20% by weight of the mineral oil and (B) 10 to 80% by weight of the polybutene.
11. The lubricating oil composition as claimed in Claim 1, wherein the additive is added in the range of 0.01 to 20 parts by weight based on 100 parts by weight of the base oil.

Patentansprüche

1. Schmierölszusammensetzung, welche ein Basisöl umfaßt von
 - (A) 100 bis 5 Gew.-% eines Mineralöls, das bei 40°C eine kinematische Viskosität von 2 bis 2000 mm²/s (cSt), einen Viskositätsindex von 70 oder höher, einen Stickstoffgehalt von 20 ppm oder weniger und einen Bromwert von 25 oder weniger hat, und
 - (B) 0 bis 95 Gew.-% eines Polybutens, mit einem Molekulargewicht von 200 bis 1000 ; und
 wenigstens ein Additiv ausgewählt aus einem EP-Mittel, einem Anti-Verschleißmittel und einem Öligkeitsmittel.
2. Schmierölszusammensetzung nach Anspruch 1, worin genanntes Mineralöl einen Fließpunkt von -20°C oder tiefer hat.
3. Schmierölszusammensetzung nach Anspruch 1, worin genanntes Mineralöl einen Fließpunkt von -30°C oder tiefer hat.
4. Schmierölszusammensetzung nach Anspruch 1, worin genanntes Mineralöl bei 40°C eine kinematische Viskosität von 5 bis 1000 mm²/s (cSt) hat.
5. Schmierölszusammensetzung nach Anspruch 1, worin genanntes Mineralöl einen Viskositätsindex von 75 oder höher hat.
6. Schmierölszusammensetzung nach Anspruch 1, worin genanntes Mineralöl einen Stickstoffgehalt von 10 ppm oder weniger hat.
7. Schmierölszusammensetzung nach Anspruch 1, worin genanntes Mineralöl einen Bromwert von 10 oder weniger hat.
8. Schmierölszusammensetzung nach Anspruch 1, worin genanntes Polybuten ein Molekulargewicht von

300 bis 800 hat.

9. Schmierölzusammensetzung nach Anspruch 1, worin das Basisöl aus (A) 100 bis 20 Gew.-% des Mineralöls und (B) 0 bis 80 Gew.-% des Polybutens zusammengesetzt ist.

5 10. Schmierölzusammensetzung nach Anspruch 1, worin das Basisöl aus (A) 90 bis 20 Gew.-% des Mineralöls und (B) 10 bis 80 Gew.-% des Polybutens zusammengesetzt ist.

11. Schmierölzusammensetzung nach Anspruch 1, worin das Additiv in Bereich von 0,01 bis 20 Gewichtsteilen bezogen auf 100 Gewichtsteile des Basisöls hinzugefügt ist.

10 **Revendications**

1. Une composition d'huile lubrifiante, qui comporte une huile de base comprenant :

15 (A) 100 à 5% en poids d'une huile minérale présentant une viscosité cinématique à 40°C de 2 à 2000 mm²/s (cSt), un indice de viscosité de 70 ou supérieur, une teneur en azote de 20 ppm ou inférieure et un indice de brome de 25 ou inférieur, et

(B) 0 à 95% en poids de polybutène présentant un poids moléculaire de 200 à 1000 ; et au moins un additif choisi parmi un agent de pression extrême, un agent anti-usure et un agent d'onctuosité.

2. La composition d'huile lubrifiante telle que revendiquée dans la revendication 1, dans laquelle ladite huile minérale présente un point d'écoulement de -20°C ou inférieur.

20 3. La composition d'huile lubrifiante telle que revendiquée dans la revendication 1, dans laquelle ladite huile minérale présente un point d'écoulement de -30°C ou inférieur.

4. La composition d'huile lubrifiante telle que revendiquée dans la revendication 1, dans laquelle ladite huile minérale présente une viscosité cinématique à 40°C de 5 à 1000 mm²/s (cSt).

25 5. La composition d'huile lubrifiante telle que revendiquée dans la revendication 1, dans laquelle ladite huile minérale présente un indice de viscosité de 75 ou supérieur.

6. La composition d'huile lubrifiante telle que revendiquée dans la revendication 1, dans laquelle ladite huile minérale présente une teneur en azote de 10 ppm ou moins.

7. La composition d'huile lubrifiante telle que revendiquée dans la revendication 1, dans laquelle ladite huile minérale présente un indice de brome de 10 ou inférieur.

30 8. La composition d'huile lubrifiante telle que revendiquée dans la revendication 1, dans laquelle ledit polybutène présente un poids moléculaire de 300 à 800.

9. La composition d'huile lubrifiante telle que revendiquée dans la revendication 1, dans laquelle l'huile de base est constituée de (A) 100 à 20% en poids d'huile minérale et (B) 0 à 80% en poids de polybutène.

35 10. La composition d'huile lubrifiante telle que revendiquée dans la revendication 1, dans laquelle l'huile de base est composée de (A) 90 à 20% en poids d'huile minérale et (B) 10 à 80% de polybutène.

11. La composition d'huile lubrifiante telle que revendiquée dans la revendication 1, dans laquelle l'additif est ajouté dans l'intervalle de 0,01 à 20 parties en poids en se basant sur 100 parties en poids d'huile de base.

40

45

50

55