

[19] Patents Registry
The Hong Kong Special Administrative Region
香港特別行政區
專利註冊處

[11] 1237707 B
EP 3205397 B1

[12] **STANDARD PATENT (R) SPECIFICATION**
轉錄標準專利說明書

[21] Application no. 申請編號 17111430.6
[51] Int. Cl. B01J 23/58 (2006.01) B01J 23/62 (2006.01)
[22] Date of filing 提交日期 22.12.2014
C07C 5/333 (2006.01)

[54] PROCESS FOR THE DEHYDROGENATION OF BUTENES OR MIXTURES OF BUTANES AND BUTENES TO GIVE 1,3-BUTADIENE
用於丁烯類或丁烷類和丁烯類的混合物脫氫得到 1, 3-丁二烯的方法

[62] Derived from application no. 14112784.9 under section 22 of the Patents Ordinance (Chapter 514)
根據《專利條例》(第 514 章) 第 22 條, 此為申請編號 14112784.9 的分開申請
[30] Priority 優先權 28.12.2011 IT MI20112403
[43] Date of publication of application 申請發表日期 20.04.2018
[45] Date of publication of grant of patent 批予專利的發表日期 11.02.2021
EP Application no. & date 歐洲專利申請編號及日期
EP 17162823.3 24.12.2012
EP Publication no. & date 歐洲專利申請發表編號及日期
EP 3205397 16.08.2017
Date of grant in designated patent office 指定專利當局批予專利日期
06.05.2020

[73] Proprietor 專利所有人
VERSALIS S.P.A.
Piazza Boldrini 1
20097 San Donato Milanese (MI)
ITALY
[72] Inventor 發明人
IEZZI, Rodolfo
MANZINI, Giulio
POLLESEL, Paolo
DEL SEPPIA, Alessandro
[74] Agent and / or address for service 代理人及/或送達地址
SPRUSON & FERGUSON (HONG KONG) LIMITED
5001 Hopewell Centre
183 Queen's Road East, Wan Chai
HONG KONG

(19)



(11)

EP 3 205 397 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
06.05.2020 Bulletin 2020/19

(51) Int Cl.:
B01J 23/58 ^(2006.01) **B01J 23/62** ^(2006.01)
C07C 5/333 ^(2006.01)

(21) Application number: **17162823.3**

(22) Date of filing: **24.12.2012**

(54) **PROCESS FOR THE DEHYDROGENATION OF BUTENES OR MIXTURES OF BUTANES AND BUTENES TO GIVE 1,3-BUTADIENE**

VERFAHREN ZUR DEHYDRIERUNG VON BUTENEN ODER GEMISCHTEN AUS BUTANEN UND BUTENEN ZUR GEWINNUNG VON 1,3-BUTADIEN

PROCÉDÉ POUR LA DÉSHYDRÉGÉNATION DE BUTÈNES OU DE MÉLANGES DE BUTANES ET DE BUTÈNES POUR DONNER DU 1,3-BUTADIÈNE

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO RS SE SI SK SM TR

(30) Priority: **28.12.2011 IT MI20112403**

(43) Date of publication of application:
16.08.2017 Bulletin 2017/33

(62) Document number(s) of the earlier application(s) in accordance with Art. 76 EPC:
12826559.2 / 2 797 689

(73) Proprietor: **VERSALIS S.P.A.**
20097 San Donato Milanese (MI) (IT)

(72) Inventors:
• **IEZZI, Rodolfo**
20097 SAN DONATO MILANESE (MI) (IT)
• **MANZINI, Giulio**
20098 SAN GIULIANO MILANESE (MI) (IT)
• **POLLESEL, Paolo**
20097 SAN DONATO MILANESE (MI) (IT)
• **DEL SEPPIA, Alessandro**
46047 PORTO MANTOVANO (MN) (IT)

(74) Representative: **Bottero, Carlo et al**
Barzanò & Zanardo Milano S.p.A.
Via Borgonuovo, 10
20121 Milano (IT)

(56) References cited:
WO-A1-2005/063658 US-A- 4 677 237

EP 3 205 397 B1

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] The present invention relates to a process wherein a catalytic composition is used for the production of 1,3-butadiene starting from single butenes, or mixtures thereof, or mixtures of butanes and butenes.

[0002] In the state of the art, the product 1,3-butadiene is prevalently provided by Steam Cracking processes from which it is selectively extracted from streams containing C₄ products or by the dehydrogenation of C₄ olefins and C₄ paraffins. With respect to the dehydrogenation, the technologies in use are the "Catadiene" process of CB&I Lummus technology, and the "OXO-D Process" developed by Petro-Tex (currently Texas Petrochemicals). Both of these processes are described in *Perp Report* Nexant Chem Systems Butadiene/Butylenes 09/10-5.

[0003] The "Catadiene" technology operates on a fixed adiabatic bed and under vacuum. As the catalyst must be frequently regenerated (the cycles last for less than an hour), more reactors are necessary for production continuity. The catalyst used is an extruded product based on chromium oxide and alumina.

[0004] The critical aspects linked to the Catadiene technology are described hereunder. The residual hexavalent Chromium, which therefore remains on the catalyst, is toxic and consequently has a significant environmental impact. The reaction takes place in the same reactor in which the catalyst is regenerated by air, thus creating conditions for a potential risk due to the mixing of air with hydrocarbon, in the case of a breakdown in the programming sequence of the large motorized valves for intercepting the streams between dehydrogenation, stripping, regeneration, stripping.

[0005] The ovens in which the feedstock is preheated, before being introduced into the catalytic bed, are sources of gaseous pollutants in particular NO_x. As reactors for regeneration and stripping are required in addition to the reaction, the reaction volumes are high with significant investments.

[0006] The "OXO-D" technology operates with a fixed bed reactor in which the oxidative dehydrogenation of butenes is carried out, which are fed to the reactor mixed with vapour and air. This process operates without regeneration of the catalyst. There are essentially two critical aspects of the "OXO-D" technology.

[0007] The presence of oxygen imposes a severe section for the purification of 1,3-butadiene from oxygen, the latter being critical for the polymerization of 1,3-butadiene. The selectivity to useful product suffers from the presence of oxygen which favours the formation of combustion products consequently requiring that the OXO-D process operates through campaigns when there is a significant difference in price of 1,3-butadiene and that of butenes.

[0008] Various patents and patent applications are known, which describe catalytic compositions based on gallium, tin, platinum and alkaline or alkaline earth metals that the Applicant has listed hereunder:

US 2010168493 discloses:

- a multi-metallic catalyst based on noble metals for dehydrogenation reactions starting from hydrocarbons, preferably light paraffins such as butanes and iso-butanes, or pentanes and iso-pentanes.
- the use of the catalyst described in a dehydrogenation process of light paraffins (C₄-C₅) recovered after the extraction of unsaturated compounds from fractions coming from steam-cracking or catalytic-cracking.

[0009] The multi-metallic catalyst described in US 2010168493 comprises a noble metal M selected from Pt, Pd, Rh, Ir, at least one promoter X1 selected from Sn, Ge, Pb, possibly at least one promoter X2 selected from Ga, Ir and Tl, an alkaline or alkaline earth metal, supported on a substrate selected from Mg oxides, Ti oxides, Zr oxides, alumina, silica and mixtures thereof (silico-aluminates), wherein the atomic ratio X1/M ranges from 0.3 to 8, wherein the ratio H_{ir}/M is higher than 0.4 and the bimetallic index BMI is higher than 108. The quantity of noble metal ranges from 0.01% wt. to 10% wt.

[0010] US 2005033101 discloses:

- a catalytic composition containing a noble metal, an alkaline or alkaline earth metal, a compound selected from Sn, Ge, Pb, In, Ga, Tl or mixtures thereof;
- a catalytic composition containing a noble metal (Pt), an alkaline or alkaline earth metal present as both metal and oxide, a third component selected from Sn as both metal and oxide, Ge, Pb, In, Ga, Tl and mixtures thereof, supported on a carrier having a surface area lower than 120 m²/g combined with a bulk apparent density higher than 0.5 g/cm³;
- a process comprising a catalytic dehydrogenation step in a fluid or mobile bed starting from hydrocarbons such as paraffins and C₂-C₃₀ olefins, in particular butanes, which generates a stream rich in hydrogen in vapour phase, a separation step which generates a liquid stream rich in hydrocarbons which is further separated according to a fractionation scheme.

[0011] According to US 2005033101, the carrier of the catalyst is alumina and it is essential for it to have a surface area lower than 120 m²/g combined with a bulk apparent density higher than 0.5 g/cm³. It is also essential for the molar ratio of the alkaline or alkaline earth metal on the third component to be higher than 16. Finally, the quantity of Pt ranges from 0.01% wt. to 5% wt with respect to the final composition. The alkaline metal is present as both metal and oxide

EP 3 205 397 B1

and ranges from 0.9% wt. to 1.1% wt with respect to the final composition. The third component ranges from 0.01% wt. to 10% wt with respect to the final composition. Sn is present as both metal and oxide.

[0012] EP 1492620 discloses:

- 5 • a catalytic composition containing a first component selected from noble metals (Pt) or mixtures thereof, a second component ranging from 0.9% wt. to 1.1% wt with respect to the total weight of the final composition selected from alkaline or alkaline earth metals, a third component selected from Sn, Ge, Pb, In, Ga, Tl and mixtures thereof, supported on alumina having a surface area ranging from 50 to 120 m²/g combined with a bulk apparent density higher than 0.5 g/cm³, wherein the molar ratio of the first component on the third component ranges from 1.5 to 1.7;
- 10 • a catalytic composition comprising Pt, K in a quantity ranging from 0.9% wt. to 1.1% wt with respect to the total weight of the composition, a third component selected from Sn, Ge, Pb, In, Ga, Tl and mixtures thereof, supported on alumina (theta-alumina) having a surface area ranging from 50 to 120 m²/g combined with a bulk apparent density higher than 0.6 g/cm³, wherein the molar ratio of the Pt on the third component ranges from 1.5 to 1.7;
- 15 • a process comprising a dehydrogenation step in a fluid or mobile bed wherein the hydrocarbon, preferably paraffins or C₂-C₃₀ olefins, is put in contact with the above catalyst, said step generating a stream rich in hydrogen in vapour phase, a separation step which generates a stream rich in liquid hydrocarbons which is further separated according to a fractionation scheme. The non-reacted hydrocarbons can be recirculated to the dehydrogenation step.

[0013] According to EP 1492620, the carrier of the catalyst is alumina and it is essential for it to have a surface area ranging from 50 to 120 m²/g combined with a bulk apparent density higher than 0.5 g/cm³. The quantity of noble metal ranges from 0.01% wt. to 5% wt with respect to the final composition (0.01% wt. is equivalent to 100 ppm by weight). The alkaline metal is present as both metal and oxide and varies from 0.9% wt. to 1.1% wt. with respect to the final composition. The third component ranges from 0.01% wt. to 10% wt with respect to the final composition. The Sn is present as both metal and oxide.

[0014] KR 0142305 describes a catalytic composition for the dehydrogenation of paraffins which comprises from 0.1% wt. to 1.5% wt. of Pt, from 0.05% wt. to 1%wt. of tin, from 0.05% wt. to 1% wt. of Ga and from 0.5% wt to 5%wt. of an alkaline metal on gamma-alumina.

[0015] US 4914075 discloses:

- 30 • a catalytic composition containing a first component selected from noble metals (Pt), a second component selected from alkaline or alkaline earth metals present as both metal and oxide, a third component selected from Sn as both metal and oxide, Ge, Pb, In, Ga, Tl and mixtures thereof, supported on alumina having a surface area lower than 120 m²/g combined with a bulk apparent density higher than 0.5 g/cm³;
- 35 • a process comprising a catalytic dehydrogenation step in a fluid or mobile bed starting from hydrocarbons such as paraffins and C₂-C₃₀ olefins, in particular butanes, which generates a stream rich in hydrogen in vapour phase, a separation step of the stream rich in hydrogen which generates a stream rich in liquid hydrocarbons which is further separated according to a fractionation scheme.

[0016] According to US 4914075, the carrier of the catalyst is alumina and it is essential for it to have a surface area lower than 120 m²/g combined with a bulk apparent density higher than 0.5 g/cm³. The quantity of noble metal ranges from 0.01% wt. to 5% wt with respect to the final composition. The alkaline metal is present as both metal and oxide and varies from 0.01% wt. to 10% wt. with respect to the final composition. The third component ranges from 0.01% wt. to 10% wt with respect to the final composition. The Sn is present as both metal and oxide.

[0017] US 7235706 discloses:

- 45 • a catalytic system containing gallium or gallium compounds (Ga₂O₃) in a quantity ranging from 0.1 to 33.6% wt., platinum in a quantity ranging from 1 to 99 ppm, oxides of alkaline or alkaline earth metals in a quantity ranging from 0% wt. to 5% wt. on alumina modified with silica, the silica being present in a quantity ranging from 0.08% wt. to 3% wt. ;
- 50 • a process for converting C₂-C₅ paraffins to C₂-C₅ olefins comprising a dehydrogenation step and a regeneration step of the catalyst.

[0018] WO 2010107591 discloses:

- 55 • a catalytic composition comprising a first component selected from Sn, Ga, Ge, Pb, In, Tl and their compounds among which the oxides (they are all alternative to each other), a second component selected from noble metals, from 0 to 2% wt. of an alkaline or earth alkaline metal also in oxide form, a carrier based on alumina or alumina modified with silica;

EP 3 205 397 B1

- a catalytic composition comprising 0.25-5% wt. of a first component selected from Sn, Ga, Ge, Pb, In, Tl and their compounds among which the oxides (preferably Ga), from 5 ppm to 0.05% wt. of a second component selected from noble metals, from 0 to 2% wt. of an alkaline or earth alkaline metal also in oxide form, a carrier based on alumina or alumina modified with silica;
- a catalytic dehydrogenation process of butanes to butylene with a regeneration step of the catalyst; the reactor can be a fast-riser.

[0019] US 6281160 discloses:

- a catalytic composition comprising at least one carrier, at least one metal selected from group VIII (Pt) of the periodic table, at least one element M selected from Ge, Sn, Pb, Re, Ga, In and Tl, and also a metal selected from alkaline or earth alkaline metals; the carrier is an oxide among which alumina, silica alone or in a mixture;
- a dehydrogenation process starting from butanes to the corresponding olefins which uses the catalyst claimed.

[0020] The quantity of noble metals ranges from 0.1% wt. to 10% wt. The quantity of M ranges from 0.01% wt. to 10% wt. and the quantity of alkaline or earth alkaline metals ranges from 0.1% wt. to 3% wt.

[0021] US 6187985 discloses:

- a catalytic composition comprising at least one carrier, at least one metal selected from group VIII (Pt) of the periodic table, at least one element M selected from Ge, Sn, Pb, Re, Ga, In and Tl, and also a metal selected from alkaline or earth alkaline metals; the carrier is an oxide among which alumina, silica alone or in a mixture;
- use of the catalyst in dehydrogenation processes of C₅ paraffins which are recovered after extracting unsaturated compounds from the C₅ fractions coming from steam-cracking or catalytic cracking.

[0022] The quantity of noble metals ranges from 0.1% wt. to 10% wt, the quantity of M ranges from 0.01% wt. to 10% wt. and finally, the quantity of alkaline or earth alkaline metals ranges from 0.1% wt. to 3% wt.

[0023] A further critical aspect is linked to dehydrogenation catalysts containing significant quantities of platinum to be treated with chlorinated compounds or chloro-gas, or in regeneration phase or after this, to favour re-dispersion of the platinum to restore its catalytic activity. The treatment with chlorinated compounds is followed by reduction treatment in which the catalyst comes into contact with hydrogen to reduce the platinum to the metallic state before the dehydrogenation reaction. The use of chlorinated compounds leads to the introduction into the atmosphere of acid gases in addition to being critical for the corrosion of the equipment. The Applicant has now found an extremely active catalytic composition which is capable of operating with low contact times, comprising microspheroidal alumina, preferably modified with silica, and an active component containing a mixture comprising Gallium and/or Gallium oxides, Tin and/or Tin oxides, a quantity ranging from 1 ppm to 500 ppm with respect to the total weight of the catalytic composition of platinum and/or platinum oxides, and oxides of alkaline and/or alkaline earth metals.

[0024] The innovative idea is based on an extremely active, non-toxic catalytic composition, which, used in a reactor preferably of the fast-riser or fluid bed type, also exerts the function of thermal vector in the process, to compensate for the endothermic nature of the dehydrogenation reaction, and overcomes the critical aspects of current commercial technologies.

[0025] The continuous regeneration of the catalyst reduces the reaction volumes with the same productivity, and at the same time avoids problems of safety associated with the air-hydrocarbon mixture, as the regeneration of the catalytic system is effected in an operative unit specifically dedicated to regeneration.

[0026] Further objectives and advantages of the present invention will appear more evident from the following description and enclosed figures, provided for purely illustrative and non-limiting purposes.

[0027] Figure 1 illustrates a process scheme relating to an embodiment according to the present invention wherein (1) is the feeding to the process, (2) is the inert product, (3) is the hot catalyst, (4) is the carrier gas of the catalyst, (5) is nitrogen for stripping, (6) is air, (7) is fuel gas, (8) are the combustion effluents, (9) is the recycling of the partially exhausted catalyst to the reaction section, (10) is the partially exhausted catalyst, (11) is the effluent of the reactor, (12) is the nitrogen for stripping, (R-1) is the "Fast Riser" dehydrogenation section, (R-2) is the regenerator for regenerating the catalyst, (S-1) is the separation section of the catalyst, (S-2) is the stripping section of the regenerator, (S-3) is the stripping section of the Fast Riser, V-1 and V-2 are two valves.

[0028] WO 2005/063658 discloses a process for the production of butadiene starting from a feed gas comprising n-butane, such as a LPG mixture or a refined C₄ stream from crackers or refineries. This process comprises a two-step dehydrogenation (DH) treatment of the starting hydrocarbon mixture to produce a stream containing butadiene among others compounds, followed by a step of extractive distillation (ED) of the stream containing butadiene. The ED step produces a stream e₂ containing butadiene and a stream e₁ consisting substantially of n-butane and 2-butene (par. [0085]). The stream e₁ is recycled to the DH treatment. The stream e₁ is optionally sent to a hydrogenation step to

produce 1- and/or 2-butene.

[0029] US 4,677,237 discloses a process for dehydrogenating dehydrogenatable hydrocarbons, comprising the step of contacting the dehydrogenatable hydrocarbons at dehydrogenation conditions with a catalytic composite. Said catalytic composite comprises a platinum component, preferably present in the amount 0.01-5 wt. %, a tin component, a potassium component, a lithium component, and an alumina support, wherein the lithium to potassium atomic ratio of said catalytic composite is in the range of from 3:1 to 5:1.

Detailed description

[0030] An object of the present invention relates to a dehydrogenation process starting from reagents selected from single butenes, mixtures thereof, or mixtures of butenes with butanes, to give 1-3 butadiene.

[0031] Said process comprises the following phases:

- diluting said reagents with an inert product before feeding them to a dehydrogenation section;
- dehydrogenating said reagents in said dehydrogenation section in the presence of a catalytic composition which comprises microspheroidal alumina and an active component containing a mixture comprising Gallium and/or Gallium oxides, Tin and/or Tin oxides, a quantity ranging from 1 ppm to 500 ppm with respect to the total weight of the catalytic composition of platinum and/or platinum oxides, and oxides of alkaline and/or alkaline earth metals, thus producing a gaseous effluent containing 1-3 butadiene;
- sending at least a part of the exhausted catalytic composition to a regenerator;
- at least partially regenerating said catalytic composition, exhausted after the reaction, in the regenerator by feeding a stream containing an oxidant selected from air, air poor or rich in oxygen;
- sending the regenerated catalytic composition back to the dehydrogenation section.

[0032] The extremely active catalytic composition is capable of operating with low contact times in a single dehydrogenation section having reduced dimensions.

[0033] The alumina carrier is preferably modified with silica.

[0034] It is fundamental for the present invention that the platinum and/or platinum oxides be present in modest quantities in the catalytic composition, preferably from 1 ppm to 99 ppm by weight, even more preferably from 1 ppm to 50 ppm by weight. Excessively high quantities of platinum in the catalytic composition, in fact, make it necessary for the catalyst, possibly regenerated, to be subjected to further treatment with chlorine-based dispersing agents to reduce sintering problems. For this purpose, the Applicant uses extremely low quantities of Pt and/or Pt oxides so that after regeneration, the catalytic composition can be immediately re-used without further treatment neither for re-dispersion nor for reduction. The absence of the re-dispersion phase avoids acid emissions into the atmosphere.

[0035] The gallium oxides are preferably selected from Ga_2O_3 , Ga_2O and mixtures thereof. The tin oxides are preferably selected from SnO , SnO_2 and mixtures thereof. The platinum oxides are preferably selected from PtO , PtO_2 and mixtures thereof. An oxide of alkaline metals is preferably K_2O .

[0036] A preferred catalytic composition comprises a mixture of gallium oxides, oxides of alkaline and/or alkaline earth metals, tin and a quantity of platinum lower than 250 ppm, supported on microspheroidal alumina modified with silica.

[0037] A further preferred catalytic composition comprises a mixture of Ga_2O_3 , K_2O , SnO and Platinum supported on microspheroidal alumina modified with silica.

[0038] The described catalytic composition preferably contains a microspheroidal alumina carrier modified with silica, as it is particularly suitable if the reaction takes place in fluid bed reactors or in a Fast Riser reactor. The active part is deposited on the microspheres of alumina modified with silica, and can be modified with modest quantities of Platinum.

[0039] The quantity of Gallium and/or Gallium oxides preferably ranges from 0.1% by weight to 34% by weight, more preferably from 0.2% by weight to 3.8% by weight, with respect to the total weight of the catalytic composition.

[0040] The quantity of oxides of alkaline and/or alkaline earth metals preferably ranges from 0.05% by weight to 5% by weight, more preferably from 0.2% by weight to 3.8% by weight, with respect to the total weight of the catalytic composition.

[0041] The quantity of tin and/or tin oxides preferably ranges from 0.001% by weight to 1% by weight, more preferably from 0.05% by weight to 0.4% by weight, with respect to the total weight of the catalytic composition.

[0042] The concentration of platinum preferably ranges from 1 ppm to 500 ppm by weight, more preferably from 1 ppm to 99 ppm by weight, even more preferably from 1 to 50 ppm, with respect to the total weight of the catalytic composition.

[0043] The quantity of silica present in the carrier ranges from 0.05% by weight to 5% by weight, more preferably from 0.03% by weight to 3% by weight, with respect to the total weight of the catalytic composition, the remaining percentage being alumina. The surface area of the microspheroidal alumina is preferably lower than or equal to $150 \text{ m}^2/\text{g}$.

[0044] The concentration of Ga_2O_3 more preferably ranges from 0.1% by weight to 34% by weight, more preferably

from 0.2% by weight to 3.8% by weight, with respect to the total weight of the catalytic composition. The quantity of K_2O preferably ranges from 0.05% by weight to 5% by weight, more preferably from 0.1% by weight to 3% by weight, with respect to the total weight of the catalytic composition. The SnO preferably ranges from 0.001% by weight to 1% by weight, more preferably from 0.05% by weight to 0.4% by weight, with respect to the total weight of the catalytic composition. The quantity of platinum preferably ranges from 1 ppm to 500 ppm by weight, more preferably from 1 ppm to 99 ppm by weight, even more preferably from 1 ppm to 50 ppm, with respect to the total weight of the catalytic composition.

[0045] The described catalytic composition is suitable for operating with fixed-bed and mobile-bed reactors.

[0046] The described catalytic compositions obtained by means of a process, which essentially consists of dispersing the precursors of the active principles on the microspheres of modified alumina. This dispersion treatment can consist of impregnating said carrier with a solution containing the precursors of the active principles, followed by drying and calcination; or by means of ionic absorption, followed by separation of the liquid and activation, or by surface adsorption of volatile species of the precursors, and possible calcination of the solid. Among those listed, the preferred procedures are: impregnation of the carrier with the volume of solution equal to that given by the pores (specific porosity of the carrier [cc/g] multiplied by the gr. of carrier to be impregnated) which corresponds to the amount of carrier to be treated. This impregnation procedure is known as incipient wetness process. Or immersion of the carrier in a volume of solution, in excess with respect to that which corresponds to the pores, in which the precursors of the active ingredients are dissolved, followed by evaporation and subsequent calcination. The precursors of the active principles can be contemporaneously dispersed, in a single step, on the carrier, modified with silica, or in several steps:

- in the first step, the carrier, preferably modified with silica, is impregnated with the solution containing a precursor of gallium and potassium, followed by drying and calcination; or the carrier, preferably modified with silica, is impregnated with the solution containing a precursor of gallium, potassium and tin, followed by drying and calcination;
- in the second step, the calcined product coming from the first step is impregnated with the solution containing the precursor of platinum and tin, the impregnated product is dried and finally calcined; or the calcined product coming from the first step is impregnated with a precursor of platinum, the impregnated product is dried and finally calcined.

[0047] The part of the catalytic composition that is sent to the regenerator preferably ranges from 50% to 80% and consequently the part that is not regenerated ranges from 50% to 20%. The part of the catalytic composition that is not sent to the regenerator is recirculated directly to the dehydrogenation section.

[0048] The reaction device for dehydrogenation according to the present invention can be similar to that adopted in "Fluid Catalytic Cracking" (F.C.C.) processes, thus obtaining a reduction in the reaction volumes. A regenerator of the catalytic composition described and claimed in the present text is associated with the dehydrogenation section. The regeneration preferably provides combustion with air of the coke deposited on the catalyst during the dehydrogenation and forms combustion products. The dehydrogenation reaction and regeneration are effected in two separate apparatuses thus avoiding the formation of mixtures of hydrocarbon in air, which is potentially risky. The catalytic composition is always recirculated between the reaction section and a regenerator and viceversa, using a carrier gas. The same carrier gas can be used for diluting the feedstock at the inlet of the reaction section. The inert product for diluting the feedstock can be selected from nitrogen, methane, or another fuel gas with a maximum hydrogen content equal to 1% by weight.

[0049] The inert product has the function of lowering the partial pressure of the reagents and products in order to increase the conversion and reduce the kinetics of parasite reactions to preserve the selectivity to the desired product. The carrier gas can be nitrogen, or methane or another fuel gas with a maximum hydrogen content equal to 1% by weight, which offer the advantage, with respect to nitrogen, of recovering the calorific value of the hydrogen without the need for cryogenic separation.

[0050] In the process, object of the present invention, the use of ovens for preheating the feedstock is not envisaged, thus reducing the formation and emission of NO_x . The same catalytic composition described and claimed in the present text forms the thermal vector of the dehydrogenation reaction yielding the sensitive heat accumulated during the regeneration. The combustion of the coke present on the exhausted catalytic system generates heat entirely recovered for the dehydrogenation reaction and integrated with aliquots of fuel gas added in the regeneration device to be able to completely balance the endothermic dehydrogenation reaction. Natural gas or hydrogen or fuel gas obtained from a mixture of the two, can be used as fuel gas in the regeneration section.

[0051] Preferably the dehydrogenation section suitable for the present invention can be a fixed-bed reactor, a fluid-bed reactor or a mobile-bed reactor. Even more preferably, the reaction device is a "Fast Riser" reactor into whose base the feedstock to be dehydrogenated is charged. In the dehydrogenation section, the feedstock is mixed with the at least partially regenerated catalytic composition, described and claimed in the present text, which enters the base of the reactor. The feedstock is dehydrogenated in said reactor as the catalytic composition and feedstock advance in equi-current, until they have passed through the whole reactor. The catalytic system is separated from the gaseous effluent at the head of the reactor, and is sent to the regeneration device. The catalytic composition, object of the present

EP 3 205 397 B1

invention, can be entirely or partially sent to regeneration. The non-regenerated part is recycled directly to the reaction device. After regeneration, the catalytic composition is re-circulated to the reactor.

[0052] In the dehydrogenation section, it is preferable to operate at a temperature ranging from 450°C to 700°C. The dehydrogenation pressure preferably ranges from 0.2 atm absolute to 2 atm. The ratio inert product/feedstock (v/v) ranges from 0 to 20, preferably from 1 to 9. The inert product for diluting the feedstock can be selected from nitrogen, methane, or another fuel gas with a hydrogen content equal to 1% by weight.

[0053] If the reactor is a Fast Riser, the residence time of the gas phase is less than a minute, and preferably ranges from 0.2 sec. to 5 sec.

[0054] The regeneration is preferably effected in a fluid bed at a temperature higher than the operating temperature of the reaction section, preferably higher than 700°C. The pressure in the regeneration section is slightly higher than atmospheric pressure. The residence time of the catalytic system during the regeneration ranges from 5 to 60 minutes, preferably from 20 to 40 minutes. During the regeneration, the hourly space velocity of the gas phase (GHSV in NI/h air per litre of catalyst) ranges from 1,000 to 5,000 h⁻¹, preferably from 2,000 to 3,000 h⁻¹.

[0055] The regeneration of the catalytic system and combustion of the fuel can be effected with air, oxygen or any other fuel.

[0056] The advantages of a reactor-regenerator system, and particularly a Fast Riser reactor-regenerator, can be summarized as follows.

- reduction in the reaction volumes and consequent investment;
- the heat required for the reaction is transferred directly by the regenerated catalyst, there are no ovens for preheating the feedstock upstream of the reaction section, with the possibility of the formation of undesired combustion by-products;
- no specific treatment is necessary for reducing emissions of gaseous pollutants;
- the reaction and regeneration take place in physically separate areas and there can be no mixing of hydrocarbon streams with streams containing oxygen;
- the regeneration of the catalyst effected in a fluid bed prevents the formation of high-temperature points, due to the vigorous remixing of the bed, preventing thermal stress of the catalytic formulate;
- the functioning of the plant does not have to be interrupted for the substitution of the catalyst as aliquots are periodically discharged and replaced with equal amounts of fresh catalyst when the unit is operating.

[0057] Some non-limiting examples of the present invention are now provide hereunder.

EXAMPLE 1

[0058] A microspheroidal pseudoboehmite modified with silica (1.2% by weight) is prepared, having a particle diameter ranging from 5 μm to 300 μm, by spray drying a solution of alumina hydrate and Ludox silica. A part of the pseudoboehmite is calcined at 450°C for an hour and subsequently treated at 1140°C for 4 hours. The calcined product has a specific surface of 70 m²/g and a specific porosity of 0.2 cc/g. A sample of 3250 g of calcined product is impregnated, by means of the incipient wetness procedure, with an aqueous solution consisting of: 573 gr of a solution of gallium nitrate (titre 9.3% by weight of Ga), 131.8 gr of a solution of potassium nitrate (titre 6.86% by weight of K) and water until the volume of the solution is brought to 1040 cc. The impregnated product was dried at 120°C for 4 hours and finally calcined according to the thermal profile: from room temperature to 460°C in 533 minutes and an isotherm step of 180 minutes at 460°C. 3270 gr of the calcined product consisting of 2.15% by weight of Ga₂O₃, 0.33% by weight of K₂O, Al₂O₃ and SiO₂ for the remaining part, were impregnated with the incipient wetness procedure with an aqueous solution containing dissolved: 230 g of anhydrous citric acid, 33.343 g of a solution of tin tetrachloride (titre 7.52% by weight of Sn) and 1.335 g of solid ammonium tetrachloro-platinite (titre 52% by weight of Pt) and water until the volume of the solution had been brought to 1046 cc. The impregnated product was dried at 120°C for 4 hours and finally calcined according to the thermal profile: from room temperature to 120°C in 120 minutes, followed by an isotherm step at 120°C for 120 minutes, then from 120°C to 250°C in 120 minutes, from 250°C to 730 °C in 210 minutes, followed by an isotherm step at 730°C for 90 minutes. The weight composition of the catalytic system proves to be: 2.15% by weight of Ga₂O₃, 0.33% by weight of K₂O, 212 ppm by weight of Pt, 766 ppm by weight of Sn, the remaining part being Al₂O₃ and SiO₂.

EXAMPLE 2

[0059] A 3250 g sample of the same calcined boehmite as Example 1 was impregnated using the same procedure described in Example 1 with an aqueous solution containing, dissolved: 573 gr of a solution of gallium nitrate (titre 9.3% by weight of Ga), 131.8 gr of a solution of potassium nitrate (titre 6.86% by weight of K) and water until the volume of the solution was brought to 1040 cc. The impregnated product was dried and calcined under the same conditions

EP 3 205 397 B1

described in Example 1. 3270 gr of the calcined product consisting of 2.15% by weight of Ga₂O₃, 0.33% by weight of K₂O, the remaining part being Al₂O₃ and SiO₂, were impregnated with the same procedure as Example 1, with a solution containing: 230 g of anhydrous citric acid, 1.3354 g of ammonium tetrachloro-platinite (titre 52% by weight of Pt), 65.337 g of a solution of tin tetrachloride (titre 7.52% by weight of Sn). The impregnated product was dried and calcined following the same procedure adopted for preparing the catalytic system described in Example 1. The weight chemical composition of the catalytic system is: 2.15% by weight of Ga₂O₃, 0.33% by weight of K₂O, 212 ppm by weight of Pt, 1500 ppm by weight of Sn, the remaining part being Al₂O₃ and SiO₂.

[0060] The catalytic systems prepared were tested for dehydrogenating mixtures of butenes in the co-presence of C₄ paraffins, prevalently n-Butane, in a circulating fluid-bed pilot plant equipped with a reactor and regenerator. The catalytic performances are indicated in Table 2, in which conversion (A) and selectivity (B) are calculated according to the following formulae:

(A)

$$\left\{ \frac{[\Sigma(\Sigma\text{butanes} + \Sigma\text{butenes})_{\text{reactor inlet}} - \Sigma(\Sigma\text{butanes} + \Sigma\text{butenes})_{\text{reactor outlet}}]}{\Sigma(\Sigma\text{butanes} + \Sigma\text{butenes})_{\text{reactor inlet}}} \right\} * 100$$

(B)

$$\left\{ \frac{1,3\text{butadiene}_{\text{reactor outlet}}}{[\Sigma(\Sigma\text{butanes} + \Sigma\text{butenes})_{\text{reactor inlet}} - \Sigma(\Sigma\text{butanes} + \Sigma\text{butenes})_{\text{reactor outlet}}]} \right\} * 100$$

[0061] The composition of the feedstocks treated in both Examples are indicated in Table 1.

Table 1

Components	MIX 1 % by weight	MIX 2 % by weight
N2	2.288	absent
CH4	absent	absent
	0,001	absent
CO2	absent	absent
C2H6	absent	absent
C2H4	absent	absent
C2H2	0.083	absent
C3H4	0.086	absent
C3H8	0.058	absent
C3H6	0.018	absent
n-C4H10	12.903	27.98
iso-C4H10	3.563	absent
iso-C4H8	0.690	absent
1-C4H8	52.381	13.21
2-C-C4H8	12.362	21.5
2-Trans C4H8	15.450	37.31
1-3 C4H6 (BTD)	0.057	absent
1-2C4H6	0.000	absent
C5H12	0.030	absent
C5H10	0.030	absent
C6H14	0.001	absent

Table 2

Catalytic Performances								
Ex.	Feed	Riser head T°C	τ (sec) of reagents In Riser	Molar fract. hydroc. feed at react. inlet	Inert type for feed dilution	Operating. press (abs. atm)	Conv. (%)	Selectiv. %wt 1,3 butadiene
1	Mix 1	528	1	0.11	Nitrogen	2	17.2	88.6
1	Mix 1	554	1	0.11	Nitrogen	2	19.9	87.7
1	Mix 1	569	1	0.11	Nitrogen	2	21.8	85.3
1	Mix 1	528	1	0.11	Methane	2	16	89.5
1	Mix 1	554	1	0.11	Methane	2	19	87.5
1	Mix 1	569	1	0.11	Methane	2	20.5	86.1
1	Mix 2	530	1	0.11	Nitrogen	2	17	87.7
1	Mix 2	550	1	0.11	Nitrogen	2	21	86
1	Mix 2	570	1	0.11	Nitrogen	2	24	82
2	Mix 2	530	1	0.11	Nitrogen	2	20	90
2	Mix 2	550	1	0.11	Nitrogen	2	23	88
2	Mix 2	570	1	0.11	Nitrogen	2	26	84

Claims

- A dehydrogenation process starting from reagents selected from single butenes, or mixtures thereof, or mixtures of butenes with butanes, to give 1-3 butadiene, which comprises the following phases:

 - diluting said reagents with an inert product before feeding them to a dehydrogenation section;
 - dehydrogenating said reagents in said dehydrogenation section in the presence of a catalytic composition which comprises microspheroidal alumina and an active component containing a mixture comprising Gallium and/or Gallium oxides, Tin and/or Tin oxides, a quantity ranging from 1 ppm to 500 ppm with respect to the total weight of the catalytic composition of platinum and/or platinum oxides, and oxides of alkaline and/or alkaline earth metals, thus producing a gaseous effluent containing 1-3 butadiene;
 - sending at least a part of the exhausted catalytic composition to a regenerator;
 - at least partially regenerating said catalytic composition, exhausted after the reaction, in the regenerator by feeding a stream containing an oxidant selected from air, air poor or rich in oxygen;
 - sending the regenerated catalytic composition back to the dehydrogenation section.
- The dehydrogenation process according to claim 1, wherein in said catalytic composition the alumina is modified with silica.
- The dehydrogenation process according to claim 1, wherein in said catalytic composition the gallium oxides are selected from Ga_2O_3 , Ga_2O and mixtures thereof.
- The dehydrogenation process according to anyone of claims from 1 to 3, wherein in said catalytic composition the tin oxides are selected from SnO , SnO_2 and mixtures thereof.
- The dehydrogenation process according to anyone of claims from 1 to 4, wherein in said catalytic composition the platinum oxides are selected from PtO , PtO_2 and mixtures thereof.
- The dehydrogenation process according to anyone of claims from 1 to 5, wherein in said catalytic composition the oxides of alkaline metals are K_2O .
- The dehydrogenation process according to anyone of claims from 1 to 6, wherein in said catalytic composition the active component is a mixture comprising gallium oxides, oxides of alkaline and/or alkaline earth metals, tin and a quantity of platinum lower than 250 ppm, supported on microspheroidal alumina or on microspheroidal alumina

modified with silica.

- 5
8. The dehydrogenation process according to anyone of claims from 1 to 7, wherein in said catalytic composition the quantity of Gallium and/or Gallium oxides ranges from 0.05% by weight to 34% by weight with respect to the total weight of the catalytic composition.
- 10
9. The dehydrogenation process according to anyone of claims from 1 to 8, wherein in said catalytic composition the quantity of oxides of alkaline and/or alkaline earth metals ranges from 0.1% by weight to 5% by weight with respect to the total weight of the catalytic composition.
- 15
10. The dehydrogenation process according to claim 8, wherein in said catalytic composition the quantity of Gallium and/or Gallium oxides ranges from 0.2% by weight to 3.8% by weight with respect to the total weight of the catalytic composition.
- 20
11. The dehydrogenation process according to claim 9, wherein in said catalytic composition the quantity of oxides of alkaline and/or alkaline earth metals ranges from 0.1% by weight to 3% by weight with respect to the total weight of the catalytic composition.
- 25
12. The dehydrogenation process according to anyone of claims from 1 to 11, wherein in said catalytic composition the quantity of Sn and/or tin oxides ranges from 0.001% by weight to 1% by weight with respect to the total weight of the catalytic composition.
- 30
13. The dehydrogenation process according to claim 12, wherein in said catalytic composition the quantity of Sn and/or tin oxides ranges from 0.05% by weight to 0.4% by weight with respect to the total weight of the catalytic composition.
- 35
14. The dehydrogenation process according to anyone of claims from 1 to 13, wherein in said catalytic composition the quantity of platinum and/or platinum oxides ranges from 1 to 99 ppm by weight with respect to the total weight of the catalytic composition.
- 40
15. The dehydrogenation process according to claim 14, wherein in said catalytic composition the quantity of platinum and/or platinum oxides ranges from 1 to 50 ppm by weight with respect to the total weight of the catalytic composition.
- 45
16. The dehydrogenation process according to anyone of claims from 1 to 15, wherein in said catalytic composition the surface area of the microspheroidal alumina is lower than or equal to 150 m²/g.
- 50
17. The dehydrogenation process according to anyone of claims from 1 to 16, wherein in said catalytic composition the quantity of silica ranges from 0.05% by weight to 5% by weight.
- 55
18. The process according to anyone of claims from 1 to 17, wherein the remaining part of the catalytic composition, which is not sent to the regenerator, is recycled directly to the dehydrogenation section.
19. The process according to anyone of claims from 1 to 18, wherein the dehydrogenation temperature ranges from 450°C to 700°C.
20. The process according to anyone of claims from 1 to 19, wherein the volumetric ratio: inert product/reagent, ranges from 0 to 20.
21. The process according to anyone of claims from 1 to 20, wherein the dehydrogenation pressure ranges from 0.2 atm absolute to 2 atm.
22. The process according to anyone of claims from 1 to 21, wherein the inert product is selected from nitrogen, nitrogen mixed with methane, methane, methane in the presence of hydrogen.
23. The process according to anyone of claims from 1 to 22, wherein the dehydrogenation section comprises at least one "Fast Riser" reactor.
24. The process according to claim 23, wherein the residence time of the gas phase in the reactor preferably ranges from 0.2 seconds to 5 seconds.

Patentansprüche

- 5
1. Dehydrierungsverfahren, ausgehend von Reagenzien, ausgewählt aus einzelnen Butenen, oder Mischungen davon, oder Mischungen von Butenen mit Butanen, um 1-3-Butadien zu erhalten, welches die folgenden Phasen umfasst:
- 10
- Verdünnen der Reagenzien mit einem inerten Produkt vor Einspeisen derselben in eine Dehydrierungssektion;
 - Dehydrierung der Reagenzien in der Dehydrierungssektion in der Gegenwart einer katalytischen Zusammensetzung, die mikrosphäroidales Alumina umfasst und eine aktive Komponente, enthaltend eine Mischung, umfassend Gallium und/oder Galliumoxide, Zinn und/oder Zinnoxide, in einer Menge in einem Bereich von 1 ppm bis 500 ppm, bezogen auf das Gesamtgewicht der katalytischen Zusammensetzung aus Platin und/oder Platinoxiden, und Oxiden von Alkali- und/oder Erdalkali-Metallen, um einen gasförmigen Ausfluss zu erhalten, der 1-3-Butadien enthält;
 - Leiten mindestens eines Teils der verbrauchten katalytischen Zusammensetzung zu einem Regenerator;
 - zumindest teilweise Regenerierung der katalytischen Zusammensetzung, verbraucht nach der Reaktion, in dem Regenerator durch Einspeisen eines Stroms, enthaltend ein Oxidationsmittel, ausgewählt aus Luft, Luft arm oder reich an Sauerstoff;
 - Leiten der regenerierten katalytischen Zusammensetzung zurück zu der Dehydrierungssektion.
- 15
2. Dehydrierungsverfahren nach Anspruch 1, wobei in der katalytischen Zusammensetzung das Alumina mit Silica modifiziert ist.
- 20
3. Dehydrierungsverfahren nach Anspruch 1, wobei in der katalytischen Zusammensetzung die Galliumoxide ausgewählt sind aus Ga_2O_3 , Ga_2O und Mischungen davon.
- 25
4. Dehydrierungsverfahren nach irgendeinem der Ansprüche 1 bis 3, wobei in der katalytischen Zusammensetzung die Zinnoxide ausgewählt sind aus SnO , SnO_2 und Mischungen davon.
- 30
5. Dehydrierungsverfahren nach irgendeinem der Ansprüche 1 bis 4, wobei in der katalytischen Zusammensetzung die Platinoxide ausgewählt sind aus PtO , PtO_2 und Mischungen davon.
- 35
6. Dehydrierungsverfahren nach irgendeinem der Ansprüche 1 bis 5, wobei in der katalytischen Zusammensetzung die Oxide der Alkalimetalle K_2O sind.
- 40
7. Dehydrierungsverfahren nach irgendeinem der Ansprüche 1 bis 6, wobei in der katalytischen Zusammensetzung die aktive Komponente eine Mischung ist, umfassend Galliumoxide, Oxide von Alkali- und/oder Erdalkali-Metallen, Zinn und einer Menge an Platin geringer als 250 ppm, geträgert auf mikrosphäroidalem Alumina oder auf mikrosphäroidalem Alumina modifiziert mit Silica.
- 45
8. Dehydrierungsverfahren nach irgendeinem der Ansprüche 1 bis 7, wobei in der katalytischen Zusammensetzung die Menge an Gallium und/oder Galliumoxiden in einem Bereich von 0,05 Gew.-% bis 34 Gew.-% ist, bezogen auf das Gesamtgewicht der katalytischen Zusammensetzung.
- 50
9. Dehydrierungsverfahren nach irgendeinem der Ansprüche 1 bis 8, wobei in der katalytischen Zusammensetzung die Menge an Oxiden der Alkali- und/oder Erdalkali-Metalle in einem Bereich von 0,1 Gew.-% bis 5 Gew.-% ist, bezogen auf die Gesamtmenge der katalytischen Zusammensetzung.
- 55
10. Dehydrierungsverfahren nach Anspruch 8, wobei in der katalytischen Zusammensetzung die Menge an Gallium und/oder Galliumoxiden in einem Bereich von 0,2 Gew.-% bis 3,8 Gew.-% ist, bezogen auf das Gesamtgewicht der katalytischen Zusammensetzung.
11. Dehydrierungsverfahren nach Anspruch 9, wobei in der katalytischen Zusammensetzung die Menge an Oxiden der Alkali- und/oder Erdalkalimetalle in einem Bereich von 0,1 Gew.-% bis 3 Gew.-% ist, bezogen auf das Gesamtgewicht der katalytischen Zusammensetzung.
12. Dehydrierungsverfahren nach irgendeinem der Ansprüche 1 bis 11, wobei in der katalytischen Zusammensetzung die Menge an Zinn und/oder Zinnoxiden in einem Bereich von 0,001 Gew.-% bis 1 Gew.-% ist, bezogen auf das Gesamtgewicht der katalytischen Zusammensetzung.

EP 3 205 397 B1

13. Dehydrierungsverfahren nach Anspruch 12, wobei in der katalytischen Zusammensetzung die Menge an Zinn und/oder Zinnoxiden in einem Bereich von 0,05 Gew.-% bis 0,4 Gew.-% ist, bezogen auf das Gesamtgewicht der katalytischen Zusammensetzung.
- 5 14. Dehydrierungsverfahren nach irgendeinem der Ansprüche 1 bis 13, wobei in der katalytischen Zusammensetzung die Menge an Platin und/oder Platinoxiden in einem Bereich von 1 bis 99 ppm in Gewichtsteilen ist, bezogen auf das Gesamtgewicht der katalytischen Zusammensetzung.
- 10 15. Dehydrierungsverfahren nach Anspruch 14, wobei in der katalytischen Zusammensetzung die Menge an Platin und/oder Platinoxiden in einem Bereich von 1 bis 50 ppm in Gewichtsteilen ist, bezogen auf das Gesamtgewicht der katalytischen Zusammensetzung.
- 15 16. Dehydrierungsverfahren nach irgendeinem der Ansprüche 1 bis 15, wobei in der katalytischen Zusammensetzung die Oberfläche des mikrosphäroidalen Alumina geringer oder gleich zu 150 m²/g ist.
17. Dehydrierungsverfahren nach irgendeinem der Ansprüche 1 bis 16, wobei in der katalytischen Zusammensetzung die Menge an Silica in einem Bereich von 0,05 Gew.-% bis 5 Gew.-% ist.
- 20 18. Verfahren nach irgendeinem der Ansprüche 1 bis 17, wobei der verbleibende Teil der katalytischen Zusammensetzung, die nicht in den Regenerator geleitet wird, direkt zu der Dehydrierungssektion rezykliert wird.
19. Verfahren nach irgendeinem der Ansprüche 1 bis 18, wobei die Dehydrierungstemperatur in einem Bereich von 450°C bis 700°C liegt.
- 25 20. Verfahren nach irgendeinem der Ansprüche 1 bis 19, wobei das Volumenverhältnis: inertes Produkt/Reagenz in einem Bereich von 0 bis 20 liegt.
21. Verfahren nach irgendeinem der Ansprüche 1 bis 20, wobei der Dehydrierungsdruck in einem Bereich von 0,2 atm absolut bis 2 atm ist.
- 30 22. Verfahren nach irgendeinem der Ansprüche 1 bis 21, wobei das inerte Produkt ausgewählt ist aus Stickstoff, Stickstoff vermischt mit Methan, Methan, Methan in der Gegenwart von Wasserstoff.
- 35 23. Verfahren nach irgendeinem der Ansprüche 1 bis 22, wobei die Dehydrierungssektion mindestens einen "Fast Riser"-Reaktor umfasst.
24. Verfahren nach Anspruch 23, wobei die Verweilzeit der Gasphase in dem Reaktor vorzugsweise in einem Bereich von 0,2 Sekunden bis 5 Sekunden liegt.

40

Revendications

1. Procédé de déshydrogénation à partir de réactifs choisis parmi des butènes individuels, des mélanges de tels butènes, et des mélanges de butènes avec des butanes, en vue de produire du 1,3-butadiène, lequel procédé comporte les phases suivantes :
- 45
- diluer lesdits réactifs avec un produit inerte avant de les introduire dans une section de déshydrogénation,
 - déshydrogéner lesdits réactifs dans ladite section de déshydrogénation, en présence d'une composition catalytique qui comprend de l'alumine microsphéroïdale et un composant actif contenant un mélange comportant

50 du gallium et/ou des oxydes de gallium, de l'étain et/ou des oxydes d'étain, du platine et/ou des oxydes de platine en une proportion comprise dans l'intervalle allant de 1 ppm à 500 ppm par rapport au poids total de la composition catalytique, et des oxydes de métaux alcalins et/ou alcalino-terreux, et produire ainsi un effluent gazeux contenant du 1,3-butadiène, - envoyer dans un régénérateur au moins une partie de la composition catalytique une fois épuisée,

55 - régénérer au moins partiellement, dans le régénérateur, ladite composition catalytique épuisée après la réaction, en introduisant un courant contenant un agent oxydant choisi dans l'ensemble formé par de l'air, de l'air appauvri en oxygène et de l'air enrichi en oxygène, - renvoyer la composition catalytique ainsi régénérée dans la section de déshydrogénation.

EP 3 205 397 B1

2. Procédé de déshydrogénation conforme à la revendication 1, étant entendu que, dans ladite composition catalytique, l'alumine est modifiée par de la silice.
- 5 3. Procédé de déshydrogénation conforme à la revendication 1, étant entendu que, dans ladite composition catalytique, les oxydes de gallium sont choisis parmi les oxydes de formules Ga_2O_3 et Ga_2O , et les mélanges de ceux-ci.
- 10 4. Procédé de déshydrogénation conforme à n'importe laquelle des revendications 1 à 3, étant entendu que, dans ladite composition catalytique, les oxydes d'étain sont choisis parmi les oxydes de formules SnO et SnO_2 , et les mélanges de ceux-ci.
- 15 5. Procédé de déshydrogénation conforme à n'importe laquelle des revendications 1 à 4, étant entendu que, dans ladite composition catalytique, les oxydes de platine sont choisis parmi les oxydes de formules PtO et PtO_2 , et les mélanges de ceux-ci.
- 20 6. Procédé de déshydrogénation conforme à n'importe laquelle des revendications 1 à 5, étant entendu que, dans ladite composition catalytique, les oxydes de métaux alcalins sont de l'oxyde de potassium de formule K_2O .
- 25 7. Procédé de déshydrogénation conforme à n'importe laquelle des revendications 1 à 6, étant entendu que, dans ladite composition catalytique, le composant actif est un mélange comportant des oxydes de gallium, des oxydes de métaux alcalins et/ou alcalino-terreux, de l'étain, et une proportion de platine inférieure à 250 ppm, sur un support d'alumine microsphéroïdale ou un support d'alumine microsphéroïdale modifiée par de la silice.
- 30 8. Procédé de déshydrogénation conforme à n'importe laquelle des revendications 1 à 7, étant entendu que, dans ladite composition catalytique, la proportion de gallium et/ou d'oxydes de gallium est comprise dans l'intervalle allant de 0,05 % en poids à 34 % en poids par rapport au poids total de la composition catalytique.
- 35 9. Procédé de déshydrogénation conforme à n'importe laquelle des revendications 1 à 8, étant entendu que, dans ladite composition catalytique, la proportion d'oxydes de métaux alcalins et/ou alcalino-terreux est comprise dans l'intervalle allant de 0,1 % en poids à 5 % en poids par rapport au poids total de la composition catalytique.
- 40 10. Procédé de déshydrogénation conforme à la revendication 8, étant entendu que, dans ladite composition catalytique, la proportion de gallium et/ou d'oxydes de gallium est comprise dans l'intervalle allant de 0,2 % en poids à 3,8 % en poids par rapport au poids total de la composition catalytique.
- 45 11. Procédé de déshydrogénation conforme à la revendication 9, étant entendu que, dans ladite composition catalytique, la proportion d'oxydes de métaux alcalins et/ou alcalino-terreux est comprise dans l'intervalle allant de 0,1 % en poids à 3 % en poids par rapport au poids total de la composition catalytique.
- 50 12. Procédé de déshydrogénation conforme à n'importe laquelle des revendications 1 à 11, étant entendu que, dans ladite composition catalytique, la proportion d'étain et/ou d'oxydes d'étain est comprise dans l'intervalle allant de 0,001 % en poids à 1 % en poids par rapport au poids total de la composition catalytique.
- 55 13. Procédé de déshydrogénation conforme à la revendication 12, étant entendu que, dans ladite composition catalytique, la proportion d'étain et/ou d'oxydes d'étain est comprise dans l'intervalle allant de 0,05 % en poids à 0,4 % en poids par rapport au poids total de la composition catalytique.
14. Procédé de déshydrogénation conforme à n'importe laquelle des revendications 1 à 13, étant entendu que, dans ladite composition catalytique, la proportion de platine et/ou d'oxydes de platine est comprise dans l'intervalle allant de 1 à 99 ppm en poids par rapport au poids total de la composition catalytique.
15. Procédé de déshydrogénation conforme à la revendication 14, étant entendu que, dans ladite composition catalytique, la proportion de platine et/ou d'oxydes de platine est comprise dans l'intervalle allant de 1 à 50 ppm en poids par rapport au poids total de la composition catalytique.
16. Procédé de déshydrogénation conforme à n'importe laquelle des revendications 1 à 15, étant entendu que, dans ladite composition catalytique, l'aire massique (surface spécifique) de l'alumine microsphéroïdale est inférieure ou égale à 150 m^2/g .

EP 3 205 397 B1

17. Procédé de déshydrogénation conforme à n'importe laquelle des revendications 1 à 16, étant entendu que, dans ladite composition catalytique, la proportion de silice est comprise dans l'intervalle allant de 0,05 % en poids à 5 % en poids.
- 5 18. Procédé conforme à n'importe laquelle des revendications 1 à 17, dans lequel la fraction restante de la composition catalytique qui n'est pas envoyée dans le régénérateur est recyclée directement dans la section de déshydrogénation.
- 10 19. Procédé conforme à n'importe laquelle des revendications 1 à 18, dans lequel la température de déshydrogénation est comprise dans l'intervalle allant de 450 °C à 700 °C.
- 15 20. Procédé conforme à n'importe laquelle des revendications 1 à 19, dans lequel le rapport volumétrique de produit inerte à réactif est compris dans l'intervalle allant de 0 à 20.
- 20 21. Procédé conforme à n'importe laquelle des revendications 1 à 20, dans lequel la pression de déshydrogénation est comprise dans l'intervalle allant de 0,2 atm (pression absolue) à 2 atm.
- 25 22. Procédé conforme à n'importe laquelle des revendications 1 à 21, dans lequel le produit inerte est choisi dans l'ensemble formé par de l'azote, de l'azote mélangé à du méthane, du méthane et du méthane en présence d'hydrogène.
- 30 23. Procédé conforme à n'importe laquelle des revendications 1 à 22, dans lequel la section de déshydrogénation comprend au moins un réacteur du type « Fast Riser ».
- 35 24. Procédé conforme à la revendication 23, dans lequel le temps de séjour de la phase gazeuse dans le réacteur est compris, de préférence, dans l'intervalle allant de 0,2 seconde à 5 secondes.
- 40
- 45
- 50
- 55




Fig. 1

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 2010168493 A [0008] [0009]
- US 2005033101 A [0010] [0011]
- EP 1492620 A [0012] [0013]
- KR 0142305 [0014]
- US 4914075 A [0015] [0016]
- US 7235706 B [0017]
- WO 2010107591 A [0018]
- US 6281160 B [0019]
- US 6187985 B [0021]
- WO 2005063658 A [0028]
- US 4677237 A [0029]