

592974 RESOLUTION 9

Sydney

TO : THE COMMISSIONER OF PATENTS
COMMONWEALTH OF AUSTRALIA

COMMONWEALTH OF AUSTRALIA
Patents Act 1952-1962

DECLARATION IN SUPPORT OF A CONVENTION OR NON-CONVENTION
APPLICATION FOR A PATENT OR PATENT OF ADDITION

In Support of the Application No.

made by RAYCHEM CORPORATION a company organised according to the laws of the State of California of 300 Constitution Drive, Menlo Park, California 94025, U.S.A.

for a ~~PATENT/PATENT OF ADDITION~~ for an invention entitled

PROTECTIVE ARTICLE

I, HERBERT G. BURKARD of 256 Prior Lane, Atherton, California 94025, U.S.A., do solemnly and sincerely declare as follows:

1. ~~We are the applicants for the patent/patent of addition.~~

1. I am authorised by the above mentioned applicant for the patent/~~patent of addition~~ to make the declaration on its behalf.

2. The basic application(s) as defined by Section 141 of the Act was/were made in the following country or countries on the following date(s) by the following applicant(s) namely:

<u>BY</u>	<u>COUNTRY</u>	<u>DATED</u>
William David UKEN - U.S.A.		25 March 1985
William David UKEN - U.S.A. and Robert D. DUBROW		02 May 1985

3. ~~I am/We are the actual inventor(s) of the invention.~~

UKEN, William David of 4159 Glenwood Street, Fremont California 94538 U.S.A. DUBROW, Robert S. 334 Roble Avenue Redwood City California 94061 U.S.A.


is/are the actual inventor(s) of the invention and the facts upon which the applicant(s) is/are entitled to make the application as follows: -- as regards entitlement under Section 34 of the Act:- BY AN ASSIGNMENT FROM THE INVENTORS TO THE APPLICANTS

--as regards entitlement under Part XVI of the Act:- BY AN ASSIGNMENT FROM THE INVENTORS TO THE APPLICANTS

4. The basic application(s) referred to in paragraph 2 of the Declaration was/were the first applications made in a convention country in respect of the invention the subject of the application.

Declared at MENLO PARK this 25th day of March 1986

TO: The Commissioner of Patents
Commonwealth of Australia


HERBERT G BURKARD
Assistant Secretary

(12) PATENT ABRIDGMENT (11) Document No. AU-B-55237/86
(19) AUSTRALIAN PATENT OFFICE (10) Acceptance No. 592974

(54) Title
PROTECTING SUBSTRATES FROM ADVERSE ENVIROMENTS

International Patent Classification(s)
(51)^a B32B 007/10 B32B 001/02 B32B 031/12 B32B 031/30
C23F 011/00 C23F 015/00

(21) Application No. : 55237/86 (22) Application Date : 25.03.86

(30) Priority Data

(31) Number	(32) Date	(33) Country
715799	25.03.85	US UNITED STATES OF AMERICA
730699	02.05.85	US UNITED STATES OF AMERICA

(43) Publication Date : 02.10.86

(44) Publication Date of Accepted Application : 01.02.90

(71) Applicant(s)
RAYCHEM CORPORATION - A DELAWARE CORPORATION

(72) Inventor(s)
WILLIAM DAVID UKEN; ROBERT D. DUBROW

(74) Attorney or Agent
GRIFFITH HACK & CO. SYDNEY

(56) Prior Art Documents
AU 573728 20044/83 H01R 4/70

(57) Claim

1. An article for protecting a substrate, comprising:
a first preshaped member having an internal surface shape
shaped similar to an outer surface shape of at least part of
the substrate to be protected, the member having an open
side; and

a thin layer of gel secured to the member for
protecting the substrate when the member is disposed over
the substrate, the gel being elastic and having a cone
penetration between 150 and 350 (10^{-1} mm) and an ultimate
elongation in excess of 100%, a volume of the gel being
substantially less than a volume enclosed by the internal
surface shape and the open side of the member, the gel being
cured prior to coming into contact with any part of the
substrate, wherein the thin layer of gel is secured to the
member so as to be disposed across the open side of the
member so as to form an open cavity between the gel and the
internal surface shape of the member.

19. The article as claimed in Claim 1, the internal surface shape of the member corresponding to a shape of either an outer surface of a bolt and nut or part of a shape of tube-like members interconnected by a fitting.

22. A method of making an article for protecting a substrate, comprising:

transporting a backing material past a gel dispenser;
dispensing a gel from the gel dispenser onto the backing; and

deforming the backing and the gel into a predetermined shape such that at least a major portion of an inner surface of the backing has gel thereon, the shape being similar to an external surface shape of at least part of a substrate to be protected, wherein the gel is elastic and has a cone penetration between 150 and 350 (10^{-1} mm) and an ultimate elongation in excess of 100%.



592974

Form 10

PATENTS ACT 1952

COMPLETE SPECIFICATION

(ORIGINAL)

FOR OFFICE USE

Short Title:

Int. Cl:

Application Number: 55237/86.
Lodged:Complete Specification—Lodged:
Accepted:
Lapsed:
Published:

This document contains the
amendments made to the
Specification of the invention
in accordance with the
provisions of the Patents Act 1952.

Priority:

Related Art:

TO BE COMPLETED BY APPLICANT

Name of Applicant:

RAYCHEM CORPORATION - *H. Dubrow Corporation*

Address of Applicant:

300 Constitution Drive,
Menlo Park, California 94025, U.S.A.

Actual Inventor:

WILLIAM DAVID UKEN and ROBERT D. DUBROW

Address for Service:

GRIFFITH HASSEL & FRAZER
71 YORK STREET
SYDNEY, N.S.W. 2000, AUSTRALIA

Complete Specification for the invention entitled: "PROTECTIVE ARTICLE"

The following statement is a full description of this invention, including the best method of performing it known to me:—

* Note: The description is to be typed in double spacing, pica type face, in an area not exceeding 250 mm in depth and 160 mm in width, on tough white paper of good quality and it is to be inserted inside this form.



Background of the Invention

The present invention relates to an article for protecting a substrate from environmental effects such as corrosion, electrical currents, etc.

5 Various ways have been proposed in the prior art for protecting a substrate from adverse environmental effects. For example, in the case of nuts and bolts, in very severe environments such as those encountered on ocean-traversing vessels, multiple layers of paint are often disposed on
10 exposed portions of the nuts and bolts for protecting them from corrosion. As an alternative to paint, various types of greases have also been utilized in many circumstances for protecting substrates from adverse environmental
15 contaminants, such as water, and for electrical insulation protection, and also for insulating metal substrates. These methods are disadvantageous in that insufficient corrosion protection is afforded, reentry is difficult, the protection lasts for a relatively short period of time, they are labor intensive, and relatively expensive.

20 U.S. Patent numbers 4,600,261 and 4,634,207, both assigned to the assignee of the present invention, disclose various containers which are substantially filled with gel material, the containers subsequently being disposed in contact with a substrate subsequent to curing the gel.
25 Though these gel filled containers are quite effective in protecting substrates, they are disadvantageous in that they are relatively inefficient since a relatively large amount of gel is required per substrate to be protected.

Summary of the Invention

30 Accordingly, it is an object of the invention to eliminate the above-noted drawbacks and to provide an article for protecting a substrate which is relatively inexpensive to produce, is easy to install over the substrate, lasts a relatively long period of time, and can
35 be made easily reenterable, if desired.

According to a first aspect of the invention there is provided an article for protecting a substrate, comprising:



a first preshaped member having an internal surface shape shaped similar to an outer surface shape of at least part of the substrate to be protected, the member having an open side; and

- 5 a thin layer of gel secured to the member for protecting the substrate when the member is disposed over the substrate, the gel being elastic and having a cone penetration between 150 and 350 (10^{-1} mm) and an ultimate elongation in excess of 100%, a volume of the gel being
- 10 substantially less than a volume enclosed by the internal surface shape and the open side of the member, the gel being cured prior to coming into contact with any part of the substrate, wherein the thin layer of gel is secured to the member so as to be disposed across the open side of the
- 15 member so as to form an open cavity between the gel and the internal surface shape of the member.

These and other objects are achieved by articles, and methods of producing such articles, the articles including a

20

25



preshaped member which has an internal surface shape which is similar to an outer surface shape of the substrate to be protected. In one embodiment, an open surface defined by the preshaped member has a flexible gel disposed thereover, 5 the flexible gel comprising a relatively thin layer of gel, such that when the member is disposed over the substrate, the gel is deformed over and around an outer surface of the substrate and is in intimate contact therewith. According to another embodiment of the invention, the thin layer of 10 flexible gel is disposed into intimate contact with substantially the entire inner surface of the preshaped member. With this embodiment, since the internal surface shape of the

15

20

25



6562571s

-5-

member is similar to the outer surface shape of the substrate, when the member is disposed over the substrate, again the gel is in intimate contact therewith. Accordingly, both embodiments utilize very small amounts of gel per substrate to be protected.

5 The gel preferably comprises a three-dimensional open cell network, is elastic, has finite elongation, preferably in excess of 200%, and has a cone penetration between 150 and 350 (10^{-1} mm).

10 According to a method of the invention for producing the article having the gel disposed into intimate contact with the internal surface of the member, one embodiment of the method comprises continuously disposing a gel onto a backing and subsequently deforming the gel and backing using a vacuum thermoforming process whereby the backing and gel are heated, and
15 deformed such that the gel is stretched upon deformation of the backing, the backing being chosen from a material which has sufficient structural strength upon being cooled to keep the gel in its expanded deformed state and in intimate contact with the
20 backing. Subsequent to deforming the backing, a die station is used to separate the deformed backing having gel thereon, which then comprises an article of the invention.

25

30

According to one preferred embodiment, the gel is disposed onto the backing in a non-cured state, a thickness of the gel is controlled using a doctor blade, the gel is then cured using either chemical means or radiation, the gel is secured to the backing, again using either radiation or chemical means such as an adhesive, and subsequently the cured gel and backing are deformed. According to another preferred embodiment of a method of the invention, a pre-cured gel is disposed on the backing, and the pre-cured gel is secured to the backing using either radiation or chemical means prior to deforming the cured gel and backing.

Such an article provides an excellent means for protecting irregularly shaped articles using a minimum amount of gel in an efficient manner.

Brief Description of the Drawings

Figure 1 is a cross-sectional view of a first preferred embodiment of the invention;

Figure 2 is a full perspective view of the article of Figure 1 disposed in close proximity to a substrate to be protected, and a partial view of an installed article;

5 Figures 3-6 illustrate further embodiments of the invention;

Figures 7a and 7b illustrate further preferred embodiments of articles of the invention; and

10 Figures 8-9 illustrate alternative exemplary embodiments for making the articles of Figures 7a and 7b.

15

20

25

30

Description of the Preferred Embodiments

Figure 1 illustrates a cross-sectional view of an article 1 constructed according to a first preferred embodiment of the invention with Figure 2 illustrating, on the left, a perspective view of the article of Figure 1 in close proximity to a substrate 2 to be protected, and on the right, the article as installed on the substrate. In the embodiment illustrated, the substrate 2 is a bolt 3 having a nut 5 therearound, and the article 1 is generically termed a bolt cover. However, it should be appreciated that the substrate 2 can comprise any kind of element which requires some sort of protection from the environment, such as protection from corrosion, protection from electrical discharge, etc., and that the article 1 comprises any member suitable for protecting such a substrate. The invention is most suitable for use with substrates having irregular shapes, though the invention is also suitable for protecting substrates having uniform shapes as well. Though the invention is described with reference to a few exemplary embodiments, in particular a few specific shaped substrates, it should be understood that the invention is applicable to pro-

protecting numerous other types and shapes of substrates as well even though the vast majority of substrates in existence which require some kind of protection are not illustrated in the drawings.

5 The article 1 includes a preshaped member 4 which has an internal surface 6 which has a shape similar to an external surface of the substrate 2 which is to be protected. In particular, the shapes of the surfaces 6, 8 are substantially the same, e.g., most preferably mirror images of one another. The member 4 can be shaped so as to form a tight fit about the
10 substrate 2 when installed, and it is even possible to form the member 4 so as to be slightly smaller in size than the substrate 2 which causes the member 4 to elastically stretch about the substrate when installed providing excellent
15 adhesion.

 A protective flexible gel 10 is disposed across an open side 12 defined by the shape of the preshaped member 4, and is secured to the preshaped member 4 at a periphery 13 by any
20 appropriate means such as, for example, by an adhesive or by a mechanical clamp. The gel is preferably one of the types
25

30

described in U.S. Serial Nos. 434,011 filed October 12, 1982;
504,000 filed June 13, 1983; 507,433 filed June 23, 1983; and
646,555 filed October 31, 1984; all cited above and assigned to
the assignee of the present invention. In particular, the gel can
comprise a urethane, a silicone, or a nonsilicone liquid rubber
with low or no unsaturation which has been crosslinked, with
silicone being a preferred embodiment. The gel is a material
having an open loop three-dimensional network such that it is
elastic and has a finite amount of elongation, and is relatively
soft. A preferred embodiment is to use a gel having a cone
penetration between 150 and 350 (10^{-1} mm), and an ultimate
elongation of at least 100%, as measured in accordance with
American National Standard Designation ASTM-D217 and ASTM-D638,
respectively. Preferably, the cone penetration is between 200
and 300 (10^{-1} mm), and more preferably between 260 and 280 (10^{-1}
mm). A release sheet 9 is disposed over the gel 10, the sheet
keeping the gel 10 clean and being releasable therefrom prior to
installing the article on the substrate.

The ultimate elongation is most preferably in excess of
200%, and most preferably is at least 400%. In addition, as

-11-

noted, the gel is also elastic such that it tends to resist deformation and generates a restoration force upon being deformed.

5 Furthermore, another preferred embodiment is to contain the gel 10 in a three-dimensional foam network, such as that disclosed in parent application U.S. Serial No. 507,435 filed June 23, 1983, cited above. Specifically, the foam network is characterized by a flexible matrix having a plurality of open interstices having an average volume of less than 0.01 inch³, the gel including a plurality of interconnected segments which lie within the interstices of the matrix, the matrix and the gel being such that when they are stretched, the matrix reaches its ultimate elongation before the gel reaches its ultimate elongation. 15 The thickness of the gel and the matrix need not be large, e.g. it can be less than 10 mm, preferably less than 5 mm, and more preferably less than 1 mm. One important function of the matrix is to provide tensile and shear strength for the gel. Accordingly, the matrix, though desirable, is not necessary so long as care is taken in sizing the article such that the ultimate elongation of the gel is not exceeded when the article is 20

25

30

-12-

placed over the substrate. In the case where the gel is made of a polysiloxane material, a suitable adhesive for securing the gel to the member is a silicone pressure sensitive adhesive.

5 In operation, the article 1 as described is disposed over the substrate 2 and placed thereon such that the protective gel 10 is deformed so as to take on a shape roughly illustrated by the dotted line 14 in Figure 1. One embodiment is to provide a small air escape hole to provide a means for air release from cavity 23 between the member 4 and gel 10 as the cavity 23 contracts in volume upon installation of the article 1.

10 It should be understood the hole 21 is not required. Without the hole 21, air confined within the cavity 23 which contracts upon installation of the article 1 can escape between the periphery 13 of the member 4 and the gel 10 after which the gel, due to its tackiness, re-adheres and seals to the periphery 13. With this construction, atmospheric pressure contributes to maintaining the member 4 in its installed position since removal of the member 4 subsequent to installation requires that the volume of the cavity 23 be enlarged which

15

20

25

30

-13-

results in a pressure decrease in the cavity 23 whereas pressure outside the member 4 and cavity 23 remains constant thereby creating a pressure differential therebetween.

5 Even though the elastic deformation of the gel produces a small force tending to push the article off the substrate, several means are available for preventing this from occurring even if the article is subjected to other external, possibly larger forces, e.g., vibrations. First, if the hole 21 is not
10 provided, as already explained, atmospheric pressure forces would keep the article installed and in place. In addition, the tackiness of the gel also produces a retention force since it is in contact with the substrate and adheres and seals thereto. If the hole 21 is provided, the tackiness of the gel
15 can be made so as to produce sufficient retention forces. In addition, grooves and recesses 16 for engaging threads 17 can be formed on an inner surface of the member 4. If a substrate not having threads is to be protected, it will be apparent to those skilled in the art that the member 4 may be able to be shaped so
20 as to closely conform in shape to the substrate so as to produce a retention force like that obtained with grooves and recesses

25

30

-14 -

which mate with threads, e.g. such as for example grooves and recesses formed on the member 4 which closely conform in shape to similar grooves and recesses on the substrate. Also, the member 4 can be sized so as to form a close fit around at least selected portions of the substrate when installed, and if the material of the member 4 is slightly elastic, it is even possible to size the fit such that the member is caused to stretch around the substrate upon installation which creates relatively large frictional engagement forces therebetween. Any combination of the above is possible when external forces, which may otherwise tend to dislodge the article 1 from the substrate, are anticipated.

Accordingly, it can be appreciated that the article 1 can be made to remain in place and to provide good environmental protection means for the substrate 2 such that it is protected from adverse environmental contaminants, such as water or other corrosion-producing substances. In addition, if desired, the article 1 is suitable for protecting substrates 2 from electrical currents, e.g., the article 1 can have a gel which is electrically insulating.

-15-

Figures 3-6 illustrate further embodiments of the invention. In Figure 3, the substrate 32 comprises pipes or hoses 32 interconnected by a fitting 33, and the article 34 comprises first and second parts 31, 31, each comprising a preformed member 4 and gel 10. The parts 31 are assembled as shown in Figure 4. The tackiness of the gel can be used to keep the parts 31 interconnected, and/or mechanical clamps 36, either integrally formed with the parts 31 or separately attached, can also be used. In Figures 5 and 6, the parts 1 are interconnected on one side by a hinge 35, this embodiment further illustrating the mechanical clamp 36.

For more complicated structured substrates, it can be appreciated that any number of the parts 31 in excess of two can be formed so as to be mutually engagable and provide a complete environmental seal for the complicated structured substrate.

Figure 7a illustrates another preferred embodiment of the invention. In Figure 7a, an article 11 is formed such that the gel 10 is in intimate contact with the internal surface 6 of the member 4. This embodiment is advantageous in that any risk of

-16-

the gel tearing by being stretched upon being installed onto the substrate 2 is eliminated since the gel of Figure 7a is not substantially deformed by the installation process. Reference numeral 62 denotes a release sheet disposed onto the gel so as to cover an otherwise exposed surface of the gel. In Figure 7b, the release sheet 9 is disposed across the open side of the deformed backing subsequent to its deformation.

Figure 8 illustrates one preferred process of producing the article of Figure 7, this method being adaptable to continuous production. According to this process, a backing 50 is preferably continuously transported from a roll 51 past a gel dispenser 52 having uncured gel 10 therein, past a doctor blade 54, past a beam 56 for curing and crosslinking the gel to give it desired properties (such as a desired cone penetration, elongation, elasticity, tackiness, etc.), past a thermoforming station 58 which heats the cured gel and backing and forms it into a desired shape 64, past a release sheet dispenser 60 which dispenses a release sheet 62 across an open side of the thermoformed shape 64, and finally to a die cut station 66 which separates the thermoformed shapes 64 which then correspond to the articles 11.

-17-

In this embodiment, the beam 56 crosslinks and cures the gel, and further functions to adhere the gel to the backing 50 by crosslinking the gel where it contacts the backing.

Alternatively, a separate beam 57 can be utilized to crosslink the gel contacting the backing, the separate beam 57 radiating the backing and gel through a surface of the backing opposite the gel. The beams 56, 57 can comprise electron beams and/or ultraviolet beams, and the intensity of and dose of radiation is determined to obtain optimum adhesion between the backing and the gel, and to achieve optimum and desired gel properties.

As an alternative to radiation for curing the gel, chemical crosslinking agents can be utilized and mixed with the uncured gel for curing the gel. In addition, if desired, chemical crosslinking agents can be used to also crosslink the gel to the backing and secure it thereto. Alternatively, an adhesive can be used to secure the gel to the backing rather than radiation or chemical crosslinking agents. When the gel comprises a polysiloxane material, a suitable adhesive is a silicone pressure sensitive adhesive.

25

30

-18-

Another alternative embodiment is illustrated in Figure 9 wherein a cured gel is applied to the backing rather than an uncured gel as illustrated in Figure 8.

5 In the embodiment of Figure 9, the cured gel can be applied as part of and embedded within a three dimensional matrix having characteristics as described above with reference to the embodiment of Figure 1, or can be applied as a unitary layer. According to these additional embodiments, the cured gel can be
10 secured to the backing using adhesives, or radiation as illustrated, as described in the embodiment of Figure 8. If radiation is used, the kind of radiation used and its direction of application (e.g. from the backing side or the gel side) are optional, though it should be understood that the radiation may
15 cause additional crosslinking in the gel, especially if applied from the gel side, and this should be considered in formulating the cured gel which is to be disposed on the backing. In Figure 9, since the gel is precured, a doctor blade is not needed, and this embodiment illustrates radiation grafting of the gel to the
20 backing, though it should be understood that chemical grafting could be used instead. Also, this figure illustrates dispensing

25

30

-19-

the release sheet 62 onto the exposed surface of the gel subsequent to dispensing the gel but prior to the theremoforming operation, which produces the article of Figure 7a, rather than the article of 7b produced when the release sheet is applied subsequent to theremoforming.

The thermoforming station 58 heats the cured gel and backing, and subjects the heated gel and backing to a vacuum pressure (which may be augmented by pressure from the above side) within a chamber 59 having a shape corresponding to a final desired shape of the article 11, 64 such that the gel and backing are deformed into the shape of the chamber 59. In addition to pressure, mechanical means can also be utilized to deform the cured gel and backing, numerous kinds and types of deforming pressures and mechanical means being known in the art for thermoforming processes. The thermoformed shape 64 thus created is cooled. A material of the backing is chosen such that its physical integral strength in its cooled state produces forces tending to maintain this shape which are greater than elastic forces generated by the gel when stretched and deformed by the thermoforming station 58 such that the article remains in the thermoformed shape sub-

-20-

sequent to being cooled. Typical materials suitable for the backing include high density polyethylene, kynar, polycarbonate, etc.

5 Though the invention has been described with reference to particular preferred embodiments thereof, it should be appreciated that numerous modifications thereto can be made within the level of skill of the ordinary skilled artisan. For example, the invention is suitable for protecting a wide
10 variety of types of substrates as well as shapes thereof, and is not specifically limited only to bolts, nuts, and pipe fittings, these substrates being described only for illustrative purposes. In addition, by utilizing plural parts 31 as
15 described, it can readily be appreciated that a large degree of freedom is possible in utilizing the invention for protecting a vast array of different types of substrates having various shapes, and the number of preformed members having gel disposed
20 thereon can vary and exceed one or two per substrate when the irregular or unique shape of the substrate makes the use of multiple members in excess of two more practicable. In addition, though several preferred means are described for producing the

25

30

-21-

unique articles of the invention in a continuous manner, it should be appreciated that many variations to the methods described are possible. Accordingly, the invention is not to be limited by the various specific embodiments described, and is to be limited only by the appended claims.

10

15

20

25

30

THE CLAIMS DEFINING THE INVENTION ARE AS FOLLOWS:

1. An article for protecting a substrate, comprising:
a first preshaped member having an internal surface shape
shaped similar to an outer surface shape of at least part of
the substrate to be protected, the member having an open
side; and

a thin layer of gel secured to the member for
protecting the substrate when the member is disposed over
the substrate, the gel being elastic and having a cone
penetration between 150 and 350 (10^{-1} mm) and an ultimate
elongation in excess of 100%, a volume of the gel being
substantially less than a volume enclosed by the internal
surface shape and the open side of the member, the gel being
cured prior to coming into contact with any part of the
substrate, wherein the thin layer of gel is secured to the
member so as to be disposed across the open side of the
member so as to form an open cavity between the gel and the
internal surface shape of the member.

2. The article as claimed in Claim 1, an internal
surface shape of the preshaped member being substantially a
mirror image of at least part of the outer surface shape of
the substrate.

3. The article as claimed in Claim 1, the volume
enclosed by the internal surface shape and the open side of
the preshaped member being slightly smaller than a volume
defined by the at least part of the outer surface shape of
the substrate.

4. The article as claimed in Claim 1, the volume
enclosed by the internal surface shape and the open side of
the preshaped member being substantially the same as a
volume defined by at least part of the outer surface shape
of the substrate.

5. The article as claimed in Claim 1, further
comprising means for securing the gel about a perimeter of
the preshaped member, the securing means being an adhesive
or a mechanical clamp, the adhesive being a silicone
pressure sensitive adhesive.



6. The article as claimed in Claim 1, the member being disposed around the substrate and being sized so as to urge the gel into intimate contact with the substrate to protect the substrate.

5 7. The article as claimed in Claim 1, the gel comprising a material having a cone penetration between 200 and 300 (10^{-1} mm), the gel comprising a material having an ultimate elongation in excess of 200%, the gel being less than 10 mm thick.

10 8. The article as claimed in Claim 7, the gel comprising a material having a cone penetration between 260 and 280 (10^{-1} mm).

9. The article as claimed in Claim 7 or 8, the gel having an ultimate elongation in excess of 400%.

15 10. The article as claimed in any one of claims 7 to 9, the gel being less than 1 mm thick.

11. The article as claimed in any one of Claims 7 to 10, the gel being disposed in a flexible matrix.

20 12. The article as claimed in Claim 11, the flexible matrix comprising a material having a plurality of open interstices having an average volume of less than 0.01 inch³.

25 13. The article as claimed in Claim 12, the gel including a plurality of interconnected segments which lie within the interstices of the matrix.

30 14. The article as claimed in Claim 13, the matrix and the gel being such that when the gel and the matrix are stretched, the matrix reaches its ultimate elongation before the gel reaches its ultimate elongation.

15. The article as claimed in any one of Claims 11 to 14, an outer surface of the gel being tacky, and further comprising a release sheet.

35 16. The article as claimed in Claim 15, wherein the release sheet is disposed either across the open side of the member and/or in contact with a substantial portion of an upper surface of the gel.



17. The article as claimed in Claim 1, further comprising means for keeping the member around the substrate.

18. The article as claimed in Claim 1, further comprising a second preshaped member having an internal surface shape shaped similar to another part of the external surface shape of the substrate and having an open side;

a second thin layer of gel, the second layer of gel being disposed either across the open side of the second member or in intimate contact with at least a substantial portion of the internal surface shape of the second member, a volume of the second thin layer of gel being substantially less than a volume enclosed by the internal surface shape and the open side of the second member; and

means for securing the first and second members together.

19. The article as claimed in Claim 1, the internal surface shape of the member corresponding to a shape of either an outer surface of a bolt and nut or part of a shape of tube-like members interconnected by a fitting.

20. The article as claimed in Claim 1, the member having a hole through an otherwise closed surface thereof for allowing communication between the cavity and an atmosphere.

21. The article as claimed in Claim 1, the member and thin layer of gel together forming a completely closed surface.

22. A method of making an article for protecting a substrate, comprising:

transporting a backing material past a gel dispenser; dispensing a gel from the gel dispenser onto the backing; and

deforming the backing and the gel into a predetermined shape such that at least a major portion of an inner surface of the backing has gel thereon, the shape being similar to an external surface shape of at least part of a substrate to be protected, wherein the gel is elastic and has a cone penetration between 150 and 350 (10^{-1} mm) and an ultimate elongation in excess of 100%



6342S/1s

23. The method as claimed in Claim 22, the gel dispenser dispensing a non-cured gel onto the backing, and further comprising the step of curing the dispensed gel prior to deforming the backing.

5 24. The method as claimed in Claim 23, further comprising the step of securing the gel to the backing prior to deforming the backing such that the gel stretches and sticks to the backing when deforming the backing, the backing being continuously transported, the deformed backing
10 being severed from a remainder of the backing subsequent to its deformation.

25. The method as claimed in Claim 24, the backing being made from a material selected from the group of materials consisting of high density polyethylene, kynar,
15 and polycarbonate.

26. The method of Claims 23 or 24, the gel being tacky subsequent to being cured, and further comprising the step of covering an open side of the deformed backing with a release sheet.

20 27. The method of Claim 26, the gel being cured by utilizing a chemical agent or radiation.

28. The method of Claim 27, the radiation being beta particles or ultraviolet radiation.

29. An article for protecting a substrate
25 substantially as described herein with reference to Figures 1, 2, 3, 4, 5, 6, 8 and 9 of the accompanying drawings.

30. A method of making an article for protecting a substrate substantially as described herein with reference to the accompanying drawings.




30 DATED this 5th day of November 1989

RAYCHEM CORPORATION

By their Patent Attorneys

35 GRIFFITH HACK & CO.








Fig 4




Fig 5




Fig 6




Fig 7a




Fig 7b




Fig 8

55 237/86




Fig 9