



(22) Date de dépôt/Filing Date: 2011/12/21
(41) Mise à la disp. pub./Open to Public Insp.: 2012/06/28
(45) Date de délivrance/Issue Date: 2018/02/27
(62) Demande originale/Original Application: 2 821 573
(30) Priorité/Priority: 2010/12/21 (US12/975,196)

(51) Cl.Int./Int.Cl. *E21B 33/14* (2006.01),
C09K 8/473 (2006.01), *E21B 33/138* (2006.01)

(72) Inventeurs/Inventors:
BRENNEIS, CHAD D., US;
KARCHER, JEFFREY D., US;
RODDY, CRAIG WAYNE, US

(73) Propriétaire/Owner:
HALLIBURTON ENERGY SERVICES, INC., US

(74) Agent: NORTON ROSE FULBRIGHT CANADA
LLP/S.E.N.C.R.L., S.R.L.

(54) Titre : COMPOSITIONS DURCISSABLES COMPRENANT DE LA PERLITE NON EXPANSEE ET PROCEDES DE
CIMENTATION DANS DES FORMATIONS SOUTERRAINES
(54) Title: SETTABLE COMPOSITIONS COMPRISING UNEXPANDED PERLITE AND METHODS OF CEMENTING IN
SUBTERRANEAN FORMATIONS

(57) **Abrégé/Abstract:**

An embodiment of the present invention comprises a method of cementing comprising: placing a settable composition into a well bore, the settable composition comprising unexpanded perlite, cement kiln dust, and water; and allowing the settable composition to set. Another embodiment of the present invention comprises a method of cementing comprising: placing a settable composition into a well bore, the settable composition comprising ground unexpanded perlite, Portland cement interground with pumicite, and water; and allowing the settable composition to set. Yet another embodiment of the present invention comprises a settable composition comprising: ground unexpanded perlite; cement kiln dust; and water.

ABSTRACT

An embodiment of the present invention comprises a method of cementing comprising: placing a settable composition into a well bore, the settable composition comprising unexpanded perlite, cement kiln dust, and water; and allowing the settable composition to set. Another embodiment of the present invention comprises a method of cementing comprising: placing a settable composition into a well bore, the settable composition comprising ground unexpanded perlite, Portland cement interground with pumicite, and water; and allowing the settable composition to set. Yet another embodiment of the present invention comprises a settable composition comprising: ground unexpanded perlite; cement kiln dust; and water.

SETTABLE COMPOSITIONS COMPRISING UNEXPANDED PERLITE AND METHODS OF CEMENTING IN SUBTERRANEAN FORMATIONS

BACKGROUND

[0001] The present invention relates to cementing operations and, more particularly, in certain embodiments, to methods and compositions that comprise unexpanded perlite with cement kiln dust (“CKD”), pumicite, or a combination thereof.

[0002] In cementing methods, such as well construction and remedial cementing, settable compositions are commonly utilized. As used herein, the term “settable composition” refers to a composition(s) that hydraulically sets or otherwise develops compressive strength. Settable compositions may be used in primary cementing operations whereby pipe strings, such as casing and liners, are cemented in well bores. In performing primary cementing, a settable composition may be pumped into an annulus between a subterranean formation and the pipe string disposed in the subterranean formation. The settable composition should set in the annulus, thereby forming an annular sheath of hardened cement (*e.g.*, a cement sheath) that should support and position the pipe string in the well bore and bond the exterior surface of the pipe string to the walls of the well bore. Settable compositions also may be used in remedial cementing methods, such as the placement of cement plugs, and in squeeze cementing for sealing voids in a pipe string, cement sheath, gravel pack, formation, and the like.

SUMMARY

[0003] The present invention relates to cementing operations and, more particularly, in certain embodiments, to compositions and methods that include unexpanded perlite, CKD, and/or pumicite.

[0004] According to one aspect of the present invention, there is provided a method of cementing comprising: placing a settable composition into a well bore, the settable composition comprising unexpanded perlite, cement kiln dust and/or Portland cement interground with pumicite, and water; and allowing the settable composition to set. Either cement kiln dust or Portland cement interground with pumicite, or both, may be employed.

[0005] In one aspect of the present invention, there is provided a method of cementing comprising: placing a settable composition into a well bore, the settable composition comprising unexpanded perlite, cement kiln dust, and water; and allowing the settable composition to set.

[0006] In another aspect of the present invention, there is provided a method of cementing comprising: placing a settable composition into a well bore, the settable composition comprising ground unexpanded perlite, Portland cement interground with pumicite, and water; and allowing the settable composition to set.

[0007] In a further aspect of the present invention, there is provided a settable composition comprising: ground unexpanded perlite; cement kiln dust; and water.

[0008] The features and advantages of the present invention will be readily apparent to those skilled in the art. While numerous changes may be made by those skilled in the art, such changes are within the scope of the invention.

DESCRIPTION OF PREFERRED EMBODIMENTS

[0009] The present invention relates to cementing operations and, more particularly, in certain embodiments, to methods and compositions that comprise unexpanded perlite with CKD, pumicite, or a combination thereof. There may be several potential advantages to the methods and compositions of the present invention, only some of which may be alluded to herein. One of the many potential advantages of embodiments of the present invention is that the inclusion of the unexpanded perlite in embodiments of the settable composition may increase the compressive strength of the settable composition after setting. Another potential advantage of embodiments of the present invention is that the CKD, unexpanded perlite, pumicite, or a combination thereof may be used to reduce the amount of a higher cost component, such as Portland cement, resulting in a more economical settable composition. Yet another potential advantage of embodiments of the present invention is that reduction of the amount of Portland cement can reduce the carbon footprint of the cementing operation.

[0010] The settable compositions of the present invention may comprise unexpanded perlite with CKD, pumicite or a combination thereof. The settable compositions further may comprise water, for example, in an amount sufficient to form a pumpable slurry. Preferably, the

settable composition may comprise a cementitious component that comprises unexpanded perlite and CKD. Or, the settable composition may comprise a cementitious component that comprises unexpanded perlite, CKD, and pumicite. Or, the settable composition may comprise a cementitious component that comprises unexpanded perlite and pumicite. Or, the settable composition may comprise a cementitious component that comprises unexpanded perlite and pumicite interground with a hydraulic cement. Or, the settable composition may comprise a cementitious component that comprises unexpanded perlite interground with a hydraulic cement. Optionally, the settable compositions described herein may comprise lime. In one particular embodiment, the settable composition comprises a cementitious component that comprises unexpanded perlite, CKD, pumicite, and/or lime. Other optional additives may also be included in embodiments of the settable compositions as desired, including, but not limited to, fly ash, slag cement, metakaolin, shale, zeolite, combinations thereof, and the like. The settable compositions may be foamed and/or extended as desired by those of ordinary skill in the art.

[0011] The settable compositions of the present invention should have a density suitable for a particular application as desired by those of ordinary skill in the art, with the benefit of this disclosure. In some embodiments, the settable compositions may have a density in the range of from about 8 pounds per gallon (“ppg”) to about 16 ppg. In other embodiments, the settable compositions may be foamed to a density in the range of from about 8 ppg to about 13 ppg.

[0012] The settable compositions generally may comprise unexpanded perlite. Perlite is an ore and generally refers to a naturally occurring volcanic, amorphous siliceous rock comprising mostly silicon dioxide and aluminum oxide. A characteristic of perlite is that it may expand to form a cellular, high-porosity particle or hollow sphere containing multi-cellular cores when exposed to high temperatures due to the sudden vaporization of water within the perlite. The expanded perlite may be used as a density-reducing additive for making lightweight settable compositions.

[0013] It has recently been discovered the addition of unexpanded perlite to settable compositions comprising CKD and/or pumicite may provide unexpected increases in compressive strengths. In accordance with the present invention, the unexpanded perlite may be used to increase the compressive strength of settable compositions comprising CKD and/or pumicite. In addition, unexpanded perlite can increase the compressive strength of settable

compositions comprising Portland cement. It is believed that the unexpanded perlite may be particularly suited for use at elevated well bore temperatures in accordance with the present invention, such as at temperatures greater than about 80°F, alternatively greater than about 120°F, and alternatively greater than about 140°F.

[0014] Preferably, unexpanded perlite may be used, among other things, to replace higher cost cementitious components, such as Portland cement, resulting in more economical settable compositions. In addition, substitution of the Portland cement for the unexpanded perlite should result in a settable composition with a reduced carbon footprint.

[0015] The unexpanded perlite can be ground to any size suitable for use in cementing operations. In an embodiment, the unexpanded perlite is ground to a mean particle size of about 1 micron to about 400 microns, alternatively, about 1 micron to about 100 microns and, alternatively, about 1 micron to about 25 microns. The mean particle size corresponds to d50 values as measured by commercially available particle size analyzers such as those manufactured by Malvern Instruments, Worcestershire, United Kingdom. In another embodiment, the unexpanded perlite has a particle size distribution of about 1 micron to about 1,000 microns with a mean particle size of about 1 micron to about 100 microns. The particle size distribution corresponds to the maximum and minimum sizes allowed in the distribution. An example of a suitable ground unexpanded perlite is available from Hess Pumice Products, Inc., Malad City, Idaho, under the tradename IM-325 with a mesh size of 325.

[0016] In one aspect of the invention, the unexpanded perlite can be interground with hydraulic cement, such as Portland cement, for example. In another embodiment, the unexpanded perlite can be interground with hydraulic cement and pumicite. The ground perlite/cement mixture may contain hydraulic cement in an amount of about 25% to about 75% by weight of the mixture and unexpanded perlite in an amount of about 25% to about 75% by weight of the mixture. The hydraulic cement may be a Portland cement classified as ASTM Type V cement. In accordance with the invention, the hydraulic cement and unexpanded perlite may be combined and ground to any size suitable for use in cementing operations. The hydraulic cement and unexpanded perlite may be ground prior to combination. The ground perlite/cement mixture may have a mean particle size of about 0.1 microns to about 400 microns, alternatively, about 0.5 microns to about 50 microns, and alternatively, about 0.5 microns to about 10 microns.

The mean particle size corresponds to d50 values as measured by commercially available particle size analyzers such as those manufactured by Malvern Instruments, Worcestershire, United Kingdom.

[0017] The unexpanded perlite may be included in the settable compositions in an amount sufficient to provide the desired compressive strength, density, cost reduction, and/or reduced carbon footprint. The unexpanded perlite may be present in the settable compositions of the present invention in an amount in the range of from about 1% to about 75% by weight of cementitious components. Cementitious components include those components or combinations of components of the settable compositions that hydraulically set, or otherwise harden, to develop compressive strength, including, for example, unexpanded perlite, CKD, fly ash, pumicite, slag, lime, shale, and the like. The unexpanded perlite may be present, in certain embodiments, in an amount of about 5%, about 10%, about 15%, about 20%, about 25%, about 30%, about 35%, about 40%, about 45%, about 50%, about 55%, about 60%, about 65%, or about 70%. In one embodiment, the unexpanded perlite may be present in the settable compositions in an amount in the range of from about 5% to about 50% by weight of cementitious components. In another embodiment, the unexpanded perlite may be present in an amount in the range of from about 10% to about 40% by weight of cementitious components. In yet another embodiment, the unexpanded perlite may be present in an amount in the range of from about 20% to about 30% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of unexpanded perlite to include for a chosen application.

[0018] The settable compositions generally may comprise CKD. Usually, large quantities of CKD are collected in the production of cement that are commonly disposed of as waste. Disposal of the waste CKD can add undesirable costs to the manufacture of the cement, as well as the environmental concerns associated with its disposal. The chemical analysis of CKD from various cement manufactures varies depending on a number of factors, including the particular kiln feed, the efficiencies of the cement production operation, and the associated dust collection systems. CKD generally may comprise a variety of oxides, such as SiO_2 , Al_2O_3 , Fe_2O_3 , CaO , MgO , SO_3 , Na_2O , and K_2O .

[0019] The CKD generally may exhibit cementitious properties, in that it may set and harden in the presence of water. In accordance with the present invention, the CKD may be used, among other things, to replace higher cost cementitious components, such as Portland cement, resulting in more economical settable compositions. In addition, substitution of the Portland cement for the CKD can result in a settable composition with a reduced carbon footprint.

[0020] The CKD may be included in the settable compositions in an amount sufficient to provide the desired compressive strength, density, cost reduction, and/or reduced carbon footprint. The CKD may be present in the settable compositions of the present invention in an amount in the range of from about 1% to about 95% by weight of cementitious components. The CKD may be present in an amount of about 5%, about 10%, about 15%, about 20%, about 25%, about 30%, about 35%, about 40%, about 45%, about 50%, about 55%, about 60%, about 65%, about 70%, about 75%, about 80%, or about 90%. The CKD may be present in the settable compositions in an amount in the range of from about 5% to about 95% by weight of cementitious components. Or, the CKD may be present in an amount in the range of from about 50% to about 90% by weight of cementitious components. Or, the CKD may be present in an amount in the range of from about 60% to about 80% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of CKD to include for a chosen application.

[0021] The settable compositions further may comprise pumicite. Generally, pumicite is a volcanic rock that exhibits cementitious properties, in that it may set and harden in the presence of hydrated lime and water. Hydrated lime may be used in combination with the pumicite, for example, to provide sufficient calcium ions for the pumicite to set. In accordance with the present invention, the pumicite may be used, among other things, to replace higher cost cementitious components, such as Portland cement, resulting in more economical settable compositions. As previously mentioned, replacement of the Portland cement should also result in a settable composition with a reduced carbon footprint.

[0022] Where present, the pumicite may be included in an amount sufficient to provide the desired compressive strength, density, cost reduction and/or reduced carbon footprint for a particular application. The pumicite may be present in the settable compositions of the present

invention in an amount in the range of from about 1% to about 95% by weight of cementitious components. For example, the pumicite may be present in an amount of about 5%, about 10%, about 15%, about 20%, about 25%, about 30%, about 35%, about 40%, about 45%, about 50%, about 55%, about 60%, about 65%, about 70%, about 75%, about 80%, or about 90%. The pumicite may be present in the settable compositions of the present invention in an amount in the range of from about 5% to about 95% by weight of cementitious components. Or, the pumicite may be present in an amount in the range of from about 5% to about 80% by weight of cementitious components. Or, the pumicite may be present in an amount in the range of from about 10% to about 50% by weight of cementitious components. Or, the pumicite may be present in an amount in the range of from about 25% to about 50% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the pumicite to include for a chosen application.

[0023] The water that may be used in the settable compositions include, for example, freshwater, saltwater (*e.g.*, water containing one or more salts dissolved therein), brine (*e.g.*, saturated saltwater produced from subterranean formations), seawater, or combinations thereof. Generally, the water may be from any source, provided that the water does not contain an excess of compounds that may undesirably affect other components in the settable composition. Preferably, the water may be included in an amount sufficient to form a pumpable slurry. The water may be included in the settable compositions of the present invention in an amount in the range of about 40% to about 200% by weight of cementitious components. Or, the water may be included in an amount in the range of about 40% to about 150% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of water to include for a chosen application.

[0024] The settable compositions further may comprise lime. The lime may be hydrated lime. The lime may be included in the settable compositions, for example, to form a hydraulic composition with other components of the settable compositions, such as the pumicite, fly ash, slag, and/or shale. Where present, the lime may be included in the settable compositions in an amount sufficient for a particular application. The lime may be present in an amount in the range of from about 1% to about 40% by weight of cementitious components. For example, the lime may be present in an amount of about 5%, about 10%, about 15%, about 20%, about 25%, about

30%, or about 35%. For example, the lime may be present in an amount in the range of from about 5% to about 20% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the lime to include for a chosen application.

[0025] It should be understood that use of Portland cement in the settable compositions can be reduced or even eliminated to provide, for example, the desired cost savings and/or reduced carbon footprint. Accordingly, the settable compositions of the present invention may comprise Portland cement in an amount of 0% to about 75%. For example, the Portland cement may be present in an amount of about 1%, 5%, about 10%, about 15%, about 20%, about 24%, about 25%, about 30%, about 35%, about 40%, about 50%, about 55%, about 60%, about 65%, or about 70%. The Portland cement may be present in an amount in the range of from about 0% to about 20%. Or, the Portland cement may be present in an amount in the range of from about 0% to about 10%. Or, the settable compositions may be essentially free of Portland cement. As used herein, the term “essentially free” means less than about 1% by weight of cementitious components. The settable composition may contain Portland cement in an amount less than about 0.1 % by weight of cementitious components and, alternatively, less than about 0.01% by weight of cementitious components. By way of example, the settable composition may be free of Portland cement, in that the settable composition contains no Portland cement.

[0026] The Portland cements include those classified as Classes A, C, G, and H cements according to American Petroleum Institute, API Specification for Materials and Testing for Well Cements, API Specification 10, Fifth Ed., July 1, 1990. In addition, the Portland cements include those classified as ASTM Type I, II, or III.

[0027] One example of a suitable hydraulic cement comprises a mixture of Portland cement and pumicite. The cement/pumicite mixture may contain Portland cement in an amount of about 25% to about 75% by weight of the mixture and pumicite in an amount of about 25% to about 75% by weight of the mixture. Preferably, the cement/pumicite mixture contains about 40% Portland cement by weight and about 60% pumicite by weight. The hydraulic cement may comprise Portland cement interground with pumicite. The Portland cement may be classified as ASTM Type V cement. In accordance with the invention, the Portland cement and pumicite may be combined and ground to any size suitable for use in cementing operations. The Portland

cement and pumicite may be ground prior to combination. Preferably, the cement/pumicite mixture of Portland cement and pumicite has a mean particle size of about 0.1 microns to about 400 microns, alternatively, about 0.5 microns to about 50 microns, and alternatively, about 0.5 microns to about 10 microns. The mean particle size corresponds to d50 values as measured by commercially available particle size analyzers such as those manufactured by Malvern Instruments, Worcestershire, United Kingdom. An example of a suitable cement/pumicite mixture is available from Halliburton Energy Services, Inc., under the trade name FineCem[™] 925 cement.

[0028] It is believed that hydraulic cement interground with pumicite when used in a settable composition in combination with unexpanded perlite may provided synergistic effects. For example, it is believed that the combination of unexpanded perlite and the cement/pumicite mixture may provide significantly higher compressive strength, particularly at elevated well bore temperatures. Accordingly, the combination of unexpanded perlite and the cement/pumicite mixture may be particularly suited for use in settable compositions at elevated well bore temperatures, such as at temperatures greater than about 80°F, alternatively greater than about 120°F, and alternatively greater than about 140°F.

[0029] The settable compositions further may comprise fly ash. A variety of fly ashes may be suitable, including fly ash classified as Class C and Class F fly ash according to American Petroleum Institute, API Specification for Materials and Testing for Well Cements, API Specification 10, Fifth Ed., July 1, 1990. Class C fly ash comprises both silica and lime so that, when mixed with water, it should set to form a hardened mass. Class F fly ash generally does not contain sufficient lime, so an additional source of calcium ions is typically required for the Class F fly ash to form a hydraulic composition. Lime may be mixed with Class F fly ash in an amount in the range of about 0.1% to about 25% by weight of the fly ash. In some instances, the lime may be hydrated lime. Suitable examples of fly ash include, but are not limited to, POZMIX[®] A cement additive, commercially available from Halliburton Energy Services, Inc.

[0030] Where present, the fly ash generally may be included in the settable compositions in an amount sufficient to provide the desired compressive strength, density, and/or cost. The fly ash may be present in the settable compositions of the present invention in an amount in the range of about 1% to about 75% by weight of cementitious components. Preferably, the fly ash

may be present in an amount in the range of about 10% to about 60% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the fly ash to include for a chosen application.

[0031] The settable compositions further may comprise a slag cement. A slag cement that may be suitable for use may comprise slag. Slag generally does not contain sufficient basic material, so slag cement further may comprise a base to produce a hydraulic composition that may react with water to set to form a hardened mass. Examples of suitable sources of bases include, but are not limited to, sodium hydroxide, sodium bicarbonate, sodium carbonate, lime, and combinations thereof.

[0032] Where present, the slag cement generally may be included in the settable compositions in an amount sufficient to provide the desired compressive strength, density, and/or cost. The slag cement may be present in the settable compositions of the present invention in an amount in the range of about 1% to about 75% by weight of cementitious components. The slag cement may be present in an amount in the range of about 5% to about 50% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the slag cement to include for a chosen application.

[0033] The settable compositions further may comprise metakaolin. Generally, metakaolin is a white pozzolan that may be prepared by heating kaolin clay, for example, to temperatures in the range of about 600°C to about 800°C. The metakaolin may be present in the settable compositions of the present invention in an amount in the range of about 1% to about 75% by weight of cementitious components. The metakaolin may be present in an amount in the range of about 10% to about 50% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the metakaolin to include for a chosen application.

[0034] The settable compositions further may comprise shale. Among other things, shale included in the settable compositions may react with excess lime to form a suitable cementing material, for example, calcium silicate hydrate. A variety of shales may be suitable, including those comprising silicon, aluminum, calcium, and/or magnesium. An example of a suitable shale comprises vitrified shale. Suitable examples of vitrified shale include, but are not limited to, PRESSUR-SEAL FINE LCM^{*} material and PRESSUR-SEAL COARSE LCM^{*} material, which

* Trademark

are commercially available from TXI Energy Services, Inc. Generally, the shale may have any particle size distribution as desired for a particular application. The shale may have a particle size distribution in the range of about 37 micrometers to about 4,750 micrometers.

[0035] Where present, the shale may be included in the settable compositions of the present invention in an amount sufficient to provide the desired compressive strength, density, and/or cost. The shale may be present in the settable compositions of the present invention in an amount in the range of about 1% to about 75% by weight of cementitious components. For example, the shale may be present in an amount in the range of about 10% to about 35% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the shale to include for a chosen application.

[0036] The settable compositions further may comprise zeolite. Zeolites generally are porous alumino-silicate minerals that may be either a natural or synthetic material. Synthetic zeolites are based on the same type of structural cell as natural zeolites, and may comprise aluminosilicate hydrates. As used herein, the term “zeolite” refers to all natural and synthetic forms of zeolite. Examples of suitable zeolites are described in more detail in U.S. Patent No. 7,445,669. An example of a suitable source of zeolite is available from the C2C Zeolite Corporation of Calgary, Canada. The zeolite may be present in the settable compositions of the present invention in an amount in the range of about 1% to about 65% by weight of cementitious components. For example, the zeolite may be present in an amount in the range of about 10% to about 40% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the zeolite to include for a chosen application.

[0037] The settable compositions further may comprise a set retarding additive. As used herein, the term “set retarding additive” refers to an additive that retards the setting of the settable compositions of the present invention. Examples of suitable set retarding additives include, but are not limited to, ammonium, alkali metals, alkaline earth metals, metal salts of sulfoalkylated lignins, organic acids (*e.g.*, hydroxycarboxy acids), copolymers that comprise acrylic acid or maleic acid, and combinations thereof. One example of a suitable sulfoalkylated lignin comprises a sulfomethylated lignin. Suitable set retarding additives are disclosed in more detail in United States Patent No. Re. 31,190.

Suitable set retarding additives are commercially available from Halliburton Energy Services, Inc. under the trademarks HR[®] 4, HR[®] 5, HR[®] 7, HR[®] 12, HR[®]15, HR[®]25, HR[®]601, SCR[™] 100, and SCR[™] 500 retarders. Generally, where used, the set retarding additive may be included in the settable compositions of the present invention in an amount sufficient to provide the desired set retardation. The set retarding additive may be present in the settable compositions of the present invention an amount in the range of about 0.1% to about 5% by weight of cementitious components. One of ordinary skill in the art, with the benefit of this disclosure, will recognize the appropriate amount of the set retarding additive to include for a chosen application.

[0038] Optionally, other additional additives may be added to the settable compositions of the present invention as deemed appropriate by one skilled in the art, with the benefit of this disclosure. Examples of such additives include, but are not limited to, strength-retrogression additives, set accelerators, weighting agents, lightweight additives, gas-generating additives, mechanical property enhancing additives, lost-circulation materials, filtration-control additives, dispersants, fluid loss control additives, defoaming agents, foaming agents, oil-swellable particles, water-swellable particles, thixotropic additives, and combinations thereof. Specific examples of these, and other, additives include crystalline silica, amorphous silica, fumed silica, salts, fibers, hydratable clays, microspheres, rice husk ash, elastomers, elastomeric particles, resins, latex, combinations thereof, and the like. A person having ordinary skill in the art, with the benefit of this disclosure, will readily be able to determine the type and amount of additive useful for a particular application and desired result.

[0039] As will be appreciated by those of ordinary skill in the art, the settable compositions may be used in a variety of subterranean applications, including primary and remedial cementing. The settable compositions may be introduced into a subterranean formation and allowed to set therein. For example, the settable composition may be placed into a space between a subterranean formation and a conduit located in the subterranean formation. The cement compositions may comprise, for example, water and one or more of unexpanded perlite, CKD, or pumicite.

[0040] In primary cementing embodiments, for example, a settable composition may be introduced into a space between a subterranean formation and a conduit (*e.g.*, pipe strings, liners)

located in the subterranean formation. The settable composition may be allowed to set to form an annular sheath of hardened cement in the space between the subterranean formation and the conduit. Among other things, the set settable composition may form a barrier, preventing the migration of fluids in the well bore. The set settable composition also may, for example, support the conduit in the well bore.

[0041] In remedial cementing embodiments, a settable composition may be used, for example, in squeeze-cementing operations or in the placement of cement plugs. By way of example, the settable composition may be placed in a well bore to plug a void or crack in the formation, in a gravel pack, in the conduit, in the cement sheath, and/or a microannulus between the cement sheath and the conduit.

[0042] To facilitate a better understanding of the present invention, the following examples of certain aspects of some embodiments are given. In no way should the following examples be read to limit, or define, the scope of the invention.

EXAMPLE 1

[0043] A series of samples were prepared and subjected to 24-hour crush strength tests in accordance with API Specification 10 to analyze force resistance properties of settable compositions that comprise unexpanded perlite. The sample compositions were allowed to cure in a water bath at the temperature indicated in the table below for twenty-four hours. Immediately after removal from the water bath, crush strengths were determined using a Tinius Olsen tester. The results of the crush strength tests are set forth in the table below.

[0044] Test Nos. 1-6 were performed on samples with a 14.2 ppg and containing water, Portland class II cement, ground unexpanded perlite, lime, and water, as indicated in the table below. The ground unexpanded perlite was IM-325* from Hess Pumice Products with a particle size of about 325 U.S. Standard Mesh.

[0045] Test Nos. 7-8 were performed on samples with a density of 14.2 ppg and containing water, Portland class H cement, pumicite, and lime, as indicated in the table below. The pumicite was about 200 U.S. Standard Mesh in size.

[0046] Test Nos. 9-14 were performed on samples with a density of 14.2 ppg and containing water, a ground cement/pumicite mixture (FineCem[™] 925 cement), unexpanded

* Trademark

perlite, lime, and water, as indicated in the table below. The ground cement/pumicite mixture comprised Portland Type V cement (40% by weight) interground with pumicite (60% by weight). The ground cement/pumicite mixture had a mean particle size in the range of about 1 to about 4 microns. The ground unexpanded perlite was IM-325 from Hess Pumice Products with a particle size of about 325 U.S. Standard Mesh.

[0047] In the following table, percent by weight is based on the weight of the Portland cement, cement/pumicite mixture, pumicite, and unexpanded perlite in the sample, and gallons per sack (gal/sk) is based on a 94-pound sack of the Portland cement, cement/pumicite mixture, pumicite, and unexpanded perlite.

TABLE 1
Crush Strength Tests

Test No.	Water (gal/sk)	Portland Cement (% by wt)	Ground Pumicite/Cement Mixture (% by wt)	Pumicite (% by wt)	Ground Unexpanded Perlite (% by wt)	Lime (% by wt)	Temp. (°F)	24-Hr Crush Strength (psi)
1	7.44	100		--	--	--	80	330
2	7.44	100		--	--	--	140	674
3	6.74	75		--	25	--	80	290
4	6.74	75		--	25	--	140	777
5	6.95	75		--	25	5	80	352
6	6.95	75		--	25	5	140	886
7	6.74	75		25	--	--	140	835
8	6.95	75		25	--	5	140	734
9	6.03	--	100	--	--	--	80	827
10	6.03	--	100	--	--	--	140	1877
11	5.68	--	75	--	25	--	80	597
12	5.68	--	75	--	25	--	140	2740
13	5.89	--	75	--	25	5	80	530
14	5.89	--	75	--	25	5	140	2610

[0048] Example 1 thus indicates that replacement of at least a portion of the Portland cement with unexpanded perlite may increase the crush strength of the settable compositions. At 140° F, for example, the Test Nos. 6 and 4 with unexpanded perlite had crush strengths of 886

psi and 777 psi as compared to a crush strength of 674 psi for Test No. 2 with 100% Portland cement by weight.

[0049] Example 1 further indicates that the ground pumicite/cement mixture in combination with the unexpanded perlite may have synergistic effects on the settable composition, in that this combination may provide increased crush strengths at elevated temperatures. At 140° F, for example, Test Nos. 12 and 14 with the ground pumicite/cement mixture and unexpanded perlite had crush strengths of 2740 psi and 2610 psi. This crush strength is markedly higher than the crush strengths for compositions with 100% Portland cement (674 psi at 140°F) and compositions with Portland cement and pumicite that were not ground to fine particle sizes (835 psi and 734 psi at 140°F). This increased compressive strength for combinations of ground pumicite/cement mixture and unexpanded perlite cannot be attributed solely to the addition of unexpanded perlite as the combination had significantly higher crush strength than seen with addition of unexpanded perlite to Portland cement (777 psi and 886 psi at 140°F). In addition, this increased compressive strength for combinations of ground pumicite/cement mixture and unexpanded perlite cannot be attributed solely to the addition of unexpanded perlite as the combination had significantly higher crush strength than seen with the ground pumicite/cement mixture alone (1877 psi at 140°F).

EXAMPLE 2

[0050] An additional series of sample settable compositions were prepared and tested to analyze the force resistance properties of settable compositions that comprise CKD and unexpanded perlite. The sample compositions were allowed to cure in a water bath at the temperature indicated in the table below for either 24 or 72 hours. Immediately after removal from the water bath, crush strengths were determined using a Tinius Olsen tester. The results of the crush strength tests are set forth in the table below.

[0051] Test Nos. 15-28 were performed on samples with a density of 14.2 ppg and containing water, CKD, ground unexpanded perlite, and lime, as indicated in the table below. The samples further contained a cement set retarder (CFR-3™ cement set retarder, Halliburton Energy Services, Inc.) in an amount of about 0.4% by weight. The ground unexpanded perlite was IM-325 from Hess Pumice Products with a particle size of about 325 U.S. Standard Mesh.

[0052] In the following table, percent by weight is based on the weight of the CKD and unexpanded perlite in the sample, and gallons per sack (gal/sk) is based on a 94-pound sack of the CKD and unexpanded perlite.

TABLE 2
Crush Strength Tests

Test No.	Water (gal/sk)	CKD (% by wt)	Ground Unexpanded Perlite (% by wt)	Lime (% by wt)	Temp. (°F)	Time (Hr)	Crush Strength (psi)
15	5.99	100	--	--	80	24	21.7
16	5.99	100	--	--	140	24	267
17	6.19	100	--	5	80	72	173
18	6.19	100	--	5	140	72	457
19	5.65	75	25	--	80	24	23.8
20	5.65	75	25	--	140	24	969
21	5.87	75	25	5	80	24	19.6
22	5.87	75	25	5	140	24	1004
23	5.5	50	50	5	80	72	124
24	5.5	50	50	5	140	72	1191
25	5.15	25	75	5	80	72	52
26	5.15	25	75	5	140	72	613
27	4.81	--	100	5	80	72	14
28	4.81	--	100	5	140	72	145

[0053] Example 2 thus indicates that unexpanded perlite may be used to enhance the crush strength of CKD-containing compositions. In addition, this effect is particularly pronounced at increased temperatures. At 140° F (60°C), for example, Test No. 20 with 75% CKD and 25% unexpanded perlite had a 24-hour crush strength of 969 psi (6681 kPa) as compared to a 24-hour crush strength of 267 psi (1841 kPa) for Test No. 16 with 100% CKD.

EXAMPLE 3

[0054] An additional series of sample settable compositions were prepared and tested to further analyze the force resistance properties of settable compositions that comprise CKD and unexpanded perlite. The sample compositions were allowed to cure in a water bath at the temperature indicated in the table below for 24 hours. Immediately after removal from the water

bath, crush strengths were determined using a Tinius Olsen tester. The results of the crush strength tests are set forth in the table below.

[0055] Test Nos. 29-37 were performed on samples with a density of 14.2 ppg and containing water, CKD, ground unexpanded perlite, and lime, as indicated in the table below. The samples further contained a cement dispersant in an amount of about 0.4% by weight. The ground unexpanded perlite was IM-325 from Hess Pumice Products with a particle size of about 325 U.S. Standard Mesh.

[0056] In the following table, percent by weight is based on the weight of the CKD and unexpanded perlite in the sample, and gallons per sack (gal/sk) is based on a 94-pound sack of the CKD and unexpanded perlite.

TABLE 3
Crush Strength Tests

Test No.	Water (gal/sk)	CKD (% by wt)	Ground Unexpanded Perlite (% by wt)	Lime (% by wt)	Temp. (°F)	24-Hr Crush Strength (psi)
29	6.19	100	--	5	140	278
30	5.48	90	10	--	140	649
31	6.05	90	10	5	140	533
32	5.7	80	20	--	140	934
33	5.92	80	20	5	140	958
34	5.42	60	40	--	140	986
35	5.64	60	40	5	140	1241
36	5.28	50	50	--	140	897
37	5.5	50	50	5	140	1197

[0057] Example 3 thus indicates that unexpanded perlite may be used to enhance the crush strength of CKD-containing compositions. For example, as indicated in the table above, the crush strength of the samples steadily increased as the concentration of unexpanded perlite in the sample was increased from 0% by weight to 40% by weight.

EXAMPLE 4

[0058] An additional series of sample settable compositions were prepared and tested to further analyze the force resistance properties of settable compositions that comprise CKD and unexpanded perlite. The sample compositions were allowed to cure in a water bath at the

temperature indicated in the table below for 24 hours. Immediately after removal from the water bath, crush strengths were determined using a Tinius Olsen tester. The results of the crush strength tests are set forth in the table below.

[0059] Test Nos. 38-43 were performed on samples with a density of 14.2 ppg and containing water, CKD, perlite, and lime, as indicated in the table below. The samples further contained a cement dispersant in an amount of about 0.4% by weight. Test Nos. 38 and 39 contained a ground unexpanded perlite (IM-325) from Hess Pumice Products with a particle size of about 325 U.S. Standard Mesh. Test Nos. 40 and 41 contained unground perlite ore having a mean particle size (d50) of about 190 microns. Test Nos. 42 and 43 contained expanded perlite.

[0060] In the following table, percent by weight is based on the weight of the CKD and perlite in the sample, and gallons per sack (gal/sk) is based on a 94-pound sack of the CKD and perlite.

TABLE 4
Crush Strength Tests

Test No.	Water (gal/sk)	CKD (% by wt)	Ground Unexpanded Perlite (% by wt)	Perlite Ore (% by wt)	Expanded Perlite (% by wt)	Lime (% by wt)	Temp. (°F)	24-Hr Crush Strength (psi)
38	5.65	75	25	--	--	--	140	969
39	5.87	75	25	--	--	5	140	1004
40	5.63	75	--	25	--	--	140	199
41	5.85	75	--	25	--	5	140	204
42	1.07	75	--	--	25	--	140	Not mixable
43	1.29	75	--	--	25	5	140	Not mixable

[0061] Example 4 thus indicates that unexpanded perlite provides superior strength enhancement to CKD-containing compositions when compared to unground perlite ore and expanded perlite. Indeed, the sample with the expanded perlite could not even be tested due to mixability problems.

EXAMPLE 5

[0062] An additional series of sample settable compositions were prepared and tested to further analyze settable compositions that comprise CKD and unexpanded perlite. The sample compositions were allowed to cure in a water bath at the temperature indicated in the table below for 24 hours. Immediately after removal from the water bath, crush strengths were determined using a Tinius Olsen tester. The results of the crush strength tests are set forth in the table below. The thickening time for each sample was also determined at 140° F in accordance with API Specification 10.

[0063] Test Nos. 44-56 were performed on samples with a density of 12.5 ppg and containing CKD, perlite, and lime, as indicated in the table below. The samples further contained a cement dispersant in an amount of about 0.4% by weight and a cement set retarder (HR[®] 5 cement retarder, Halliburton Energy Services, Inc.). Test Nos. 45, 48, 51, and 54 contained a ground unexpanded perlite (IM-325) from Hess Pumice Products with a particle size of about 314 U.S. Standard Mesh. Test Nos. 46, 49, 52, and 55 contained unground perlite ore having a mean particle size (d50) of about 190 microns. Test Nos. 47, 50, 53, and 56 contained expanded perlite.

[0064] In the following table, percent by weight is based on the weight of the CKD and perlite in the sample, and gallons per sack (gal/sk) is based on a 94-pound sack of the CKD and perlite.

TABLE 5
Crush Strength and Thickening Time Tests

Test No.	Water (gal/sk)	CKD (% by wt)	Ground Unexpanded Perlite (% by wt)	Perlite Ore (% by wt)	Expanded Perlite (% by wt)	Lime (% by wt)	Set Retarder (% by wt)	Temp. (°F)	Thick. Time to 70 Bc hr.min	24-Hr Crush Strength (psi)
44	10.51	100	--	--	--	5	0.3	140	4:06	126
45	10.34	90	10	--	--	5	0.3	140	4:17	178.2
46	10.36	90	--	10	--	5	0.3	140	5:16	119
47		90	--	-	10	5	0.6	140	Mixable not pumpable	
48	10.18	80	20	--	--	5	0.3	140	4:20	311
49	10.18	80	--	20	--	5	0.3	140	5:49	100
50		80	--	--	20	5	0.3	140	Not mixable	
51	9.84	60	40	--	--	5	0.3	140	5:05	508
52		60	--	40	--	5	0.15	140	9:44	88
53		60	--	--	40	5	0.3	140	Not mixable	
54	9.67	50	50	--	--	5	0.3	140	8:04	616
55		50	--	50	--	5	0	140	23:30	78
56		50	--	--	50	5	0.3	140	Not mixable	

BC = Bearden units of consistency

[0065] Example 5 thus indicates that unexpanded perlite provides enhanced strength to CKD-containing compositions when compared to unground perlite ore and expanded perlite. In a similar manner to the preceding example, the samples with expanded perlite could not even be tested due to mixability problems.

EXAMPLE 6

[0066] An additional series of sample settable compositions were prepared and tested to further analyze settable compositions that comprise CKD and unexpanded perlite. The sample compositions were allowed to cure in a water bath at the temperature indicated in the table below for 24 hours. Immediately after removal from the water bath, crush strengths were determined using a Tinius Olsen tester. The results of the crush strength tests are set forth in the table below.

[0067] Test No. 57 was performed on a sample with a density of 12.5 ppg and containing water, Portland Type V cement, CKD, unground perlite ore, and pumicite, as indicated in the table below. The unground perlite ore had a mean particle size (d50) of about 190 microns. The pumicite had a mean particle size (d50) of about 4 microns.

[0068] Test No. 58 was performed on a sample with a density of 12.5 ppg and containing water, ground cement/pumicite mixture, CKD, and ground unexpanded perlite. The ground cement/pumicite mixture comprised Portland Type V cement (40% by weight) interground with pumicite (60% by weight). The ground cement/pumicite mixture had a mean particle size of about 1-4 microns. The ground unexpanded perlite was IM-325 from Hess Pumice Products with a particle size of about 325 U.S. Standard Mesh.

[0069] In the following table, percent by weight is based on the weight of the CKD, cement, perlite, pumicite, and/or pumicite/cement mixture in the sample, and gallons per sack (gal/sk) is based on a 94-pound sack of the CKD, cement, perlite, pumicite, and/or pumicite/cement mixture in the sample.

TABLE 6
Crush Strength Tests

Test No.	Water (gal/sk)	Portland Type V Cement (% by wt)	Pumicite (% by wt)	Ground Pumicite Cement Mixture (% by wt)	CKD (% by wt)	Ground Unexpanded Perlite (% by wt)	Perlite Ore (% by wt)	Temp. (°F)	24-Hr Crush Strength (psi)
57	9.52	20	30	--	25	--	25	140	201
58	9.72	--	--	50	25	25	--	140	1086

[0070] Example 6 thus indicates that unexpanded perlite in combination with ground pumicite provides enhanced strength to CKD-containing compositions in comparison to compositions with standard cement, pumicite, and unground perlite ore.

[0071] It should be understood that the compositions and methods are described in terms of “comprising,” “containing,” or “including” various components or steps, the compositions and methods can also “consist essentially of” or “consist of” the various components and steps.

[0072] For the sake of brevity, only certain ranges are explicitly disclosed herein. However, ranges from any lower limit may be combined with any upper limit to recite a range not explicitly recited, as well as, ranges from any lower limit may be combined with any other lower limit to recite a range not explicitly recited, in the same way, ranges from any upper limit may be combined with any other upper limit to recite a range not explicitly recited. Additionally, whenever a numerical range with a lower limit and an upper limit is disclosed, any number and any included range falling within the range is specifically disclosed. In particular, every range of values (of the form, “from about a to about b,” or, equivalently, “from approximately a to b,” or, equivalently, “from approximately a-b”) disclosed herein is to be understood to set forth every number and range encompassed within the broader range of values even if not explicitly recited. Thus, every point or individual value may serve as its own lower or upper limit combined with any other point or individual value or any other lower or upper limit, to recite a range not explicitly recited.

[0073] Therefore, the present invention is well adapted to attain the ends and advantages mentioned as well as those that are inherent therein. The particular embodiments disclosed above are illustrative only, as the present invention may be modified and practiced in different but equivalent manners apparent to those skilled in the art having the benefit of the teachings herein. Although individual embodiments are discussed, the invention covers all combinations of all those embodiments. Furthermore, no limitations are intended to the details of construction or design herein shown, other than as described in the claims below. Also, the terms in the claims have their plain, ordinary meaning unless otherwise explicitly and clearly defined by the patentee. It is therefore evident that the particular illustrative embodiments disclosed above may be altered or modified and all such variations are considered within the scope of the present invention.

CLAIMS:

1. A method of cementing comprising:
placing a settable composition into a well bore, the settable composition comprising:
unexpanded perlite in an amount of about 20% to about 50% by weight of cementitious components, wherein unexpanded perlite is ground to a mean particle size of about 1 micron to about 100 microns,
cement kiln dust in an amount of about 50% to about 80% by weight of the cementitious components,
lime in an amount of about 1% to about 10% by weight of the cementitious components, and water; and
allowing the settable composition to set.
2. The method of claim 1 wherein the settable composition has a density of about 8 pounds per gallon to about 16 pounds per gallon, and wherein the water is present in an amount of about 40% to about 200% by weight of cementitious components.
3. The method of claim 1 wherein the settable composition further comprises at least one additive selected from the group consisting of fly ash, slag cement, metakaolin, shale, zeolite, crystalline silica, amorphous silica, fumed silica, salt, fiber, hydratable clay, microsphere, rice husk ash, elastomer, elastomeric particle, resin, latex, and any combination thereof.
4. The method of claim 1 wherein the settable composition further comprises at least one additive selected from the group consisting of a set retarding additive, a strength-retrogression additive, a set accelerator, a weighting agent, a lightweight additive, a gas-generating additive, a mechanical property enhancing additive, a lost-circulation material, a filtration-control additive, a dispersant, a fluid loss control additive, a defoaming agent, a foaming agent, an oil-swellable particle, a water-swellable particle, a thixotropic additive, and any combination thereof.

5. The method of claim 1 wherein the settable composition is allowed to set in the well bore in an annulus between a subterranean formation and a conduit in the well bore.
6. The method of claim 1 further comprising squeezing the settable composition in an opening, the opening comprising at least one opening selected from the group consisting of an opening in a subterranean formation, an opening in a gravel pack, an opening in a conduit, and a microannulus between a cement sheath and a conduit.