



(86) Date de dépôt PCT/PCT Filing Date: 2014/03/28
(87) Date publication PCT/PCT Publication Date: 2014/10/02
(45) Date de délivrance/Issue Date: 2017/09/12
(85) Entrée phase nationale/National Entry: 2015/09/16
(86) N° demande PCT/PCT Application No.: JP 2014/001832
(87) N° publication PCT/PCT Publication No.: 2014/156187
(30) Priorités/Priorities: 2013/03/29 (JP2013-074655);
2013/03/29 (JP2013-074654)

(51) Cl.Int./Int.Cl. *C22C 38/06* (2006.01),
C21D 8/10 (2006.01), *C22C 38/02* (2006.01),
C22C 38/04 (2006.01), *F17C 1/00* (2006.01)
(72) Inventeurs/Inventors:
TAKAGI, SHUSAKU, JP;
NAGAO, AKIHIDE, JP
(73) Propriétaire/Owner:
JFE STEEL CORPORATION, JP
(74) Agent: SMART & BIGGAR

(54) Titre : MATERIAU D'ACIER ET RECIPIENT D'HYDROGENE ET PROCEDES DE FABRICATION DE CELUI-CI
(54) Title: STEEL MATERIAL, HYDROGEN CONTAINER, METHOD FOR PROUCING THE STEEL MATERIAL, AND
METHOD FOR PRODCUING THE HYDROGEN CONTAINER

(57) **Abrégé/Abstract:**

Provided are a steel material and a hydrogen container that achieves a lower fatigue crack propagation rate in a high-pressure hydrogen atmosphere than steels used in the related art, a method for producing the steel material, and a method for producing the hydrogen container.

The steel material includes: a composition containing, by mass, C: 0.05% to 0.60%, Si: 0.01% to 2.0%, Mn: 0.3% to 3.0%, P: 0.001% to 0.040%, S: 0.0001% to 0.010%, N: 0.0001% to 0.0060%, Al: 0.01% to 1.5%, one or more elements selected from Ti: 0.01% to 0.20%, Nb: 0.01% to 0.20%, and V: 0.01% or more and less than 0.05%, and one or more elements selected from B: 0.0001% to 0.01%, Mo: 0.005% to 2.0%, and Cr: 0.005% to 3.0%, with the balance being Fe and inevitable impurities; and a steel microstructure that includes 95% or more of tempered martensite on a volume fraction basis, that includes a precipitate having a diameter of 100 nm or less and including one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen at a density of 50 particles/ μm^2 or more, and that includes prior austenite having a grain diameter of 3 μm or more.

- 74 -

ABSTRACT

Provided are a steel material and a hydrogen container that achieves a lower fatigue crack propagation rate in a high-pressure hydrogen atmosphere than steels used in the related art, a method for producing the steel material, and a method for producing the hydrogen container.

The steel material includes: a composition containing, by mass, C: 0.05% to 0.60%, Si: 0.01% to 2.0%, Mn: 0.3% to 3.0%, P: 0.001% to 0.040%, S: 0.0001% to 0.010%, N: 0.0001% to 0.0060%, Al: 0.01% to 1.5%, one or more elements selected from Ti: 0.01% to 0.20%, Nb: 0.01% to 0.20%, and V: 0.01% or more and less than 0.05%, and one or more elements selected from B: 0.0001% to 0.01%, Mo: 0.005% to 2.0%, and Cr: 0.005% to 3.0%, with the balance being Fe and inevitable impurities; and a steel microstructure that includes 95% or more of tempered martensite on a volume fraction basis, that includes a precipitate having a diameter of 100 nm or less and including one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen at a density of 50 particles/ μm^2 or more, and that includes prior austenite having a grain diameter of 3 μm or more.

- 1 -

DESCRIPTION

[Title of Invention] STEEL MATERIAL, HYDROGEN CONTAINER,
METHOD FOR PRODUCING THE STEEL MATERIAL, AND METHOD FOR
PRODUCING THE HYDROGEN CONTAINER

[Technical Field]

[0001]

The present invention relates to a steel material and a hydrogen container that have high resistance to fatigue crack propagation in a high-pressure hydrogen atmosphere (or a high-pressure hydrogen environment), a method for producing the steel material, and a method for producing the hydrogen container. The term "steel material" used herein refers to a steel sheet, a steel plate, a steel pipe, and the like.

[Background Art]

[0002]

In recent years, worldwide attention has been focused on hydrogen as a clean energy source and as an energy source that enables energy diversification to be achieved. In particular, development of fuel-cell vehicles that use high-pressure hydrogen as a fuel source has been strongly anticipated, and studies on the development of fuel-cell vehicles have been carried out all over the world. In some of the studies, a test for practical use has already been conducted.

- 2 -

[0003]

Fuel-cell vehicles run on hydrogen contained in a tank mounted thereon instead of on gasoline. Thus, in order to spread the use of fuel-cell vehicles, hydrogen-filling stations, at which refueling is performed instead of gas stations, are required. At a hydrogen-filling station, a hydrogen fuel tank mounted on a vehicle is filled with hydrogen supplied from a hydrogen container, in which hydrogen is stored at a high pressure. While the maximum filling pressure of a vehicle-mounted hydrogen tank is currently 35 MPa, it is desired to increase the maximum filling pressure to 70 MPa in order to increase the driving ranges of fuel-cell vehicles to a level comparable to the driving ranges of gasoline vehicles. Thus, it is required to store and supply hydrogen with safety under such a high-pressure hydrogen atmosphere. Accordingly, the pressure in a hydrogen container used in a hydrogen-filling station, that is, a high-pressure hydrogen storage tank, is currently required to be 40 MPa. If the maximum filling pressure is increased to 70 MPa, the pressure in the high-pressure hydrogen storage tank used in a hydrogen-filling station would be required to be 80 MPa. In other words, in such a case, the high-pressure hydrogen storage tank used in a hydrogen-filling station would be subjected to an 80-MPa atmosphere. It is also desired that steel materials used

- 3 -

for producing equipment or the like of hydrogen-filling stations be capable of, for example, storing and supplying hydrogen with safety even under a high-pressure hydrogen atmosphere of 80 MPa.

[0004]

However, it is known that intrusion of hydrogen into a low-alloy steel causes embrittlement. In the case where the hydrogen pressure is about 15 MPa or less, low-alloy steel plate having a sufficiently large thickness can be used. However, a hydrogen pressure exceeding about 15 MPa increases the risk of hydrogen embrittlement fracture that may occur during service. Therefore, low-alloy steels are not used and, for example, austenitic stainless steels such as SUS316L steel, which are less likely to cause hydrogen embrittlement than low-alloy steels, are used instead.

[0005]

Since steel materials such as SUS316L steel are expensive and have low strengths, a high-pressure hydrogen storage tank that is designed so as to withstand a hydrogen pressure of 80 MPa needs to have a considerably large thickness. Furthermore, the price of such a high-pressure hydrogen storage tank becomes considerably high. Thus, development of a high-pressure hydrogen storage tank for hydrogen-filling stations which is capable of withstanding a pressure of 80 MPa at a lower cost has been anticipated.

- 4 -

[0006]

In order to address the above-described issues, several techniques for using low-alloy steel materials for producing a high-pressure hydrogen storage tank have been studied. Patent Literature 1 proposes a steel for high-pressure hydrogen embrittlement resistance in which nondiffusible hydrogen is produced by using a MnS-based or Ca-based inclusion or VC as a hydrogen-trapping site in the steel in order to reduce the risk of embrittlement caused by diffusible hydrogen. Patent Literature 2 and Patent Literature 3 propose a low-alloy high-strength steel having high resistance to high-pressure hydrogen atmosphere embrittlement. The tensile strength of the low-alloy high-strength steel material is controlled within a considerably narrow range of 900 to 950 MPa by performing a tempering treatment at a relatively high temperature during thermal refining of a Cr-Mo steel. Patent Literature 4 proposes a low-alloy steel material for high-pressure hydrogen embrittlement resistance in which a V-Mo-based carbide and increase of tempering temperature are used in order to enhance resistance to high-pressure hydrogen atmosphere embrittlement. Patent Literature 5 proposes a steel material for high-pressure hydrogen storage container which has high resistance to hydrogen. Large amounts of Mo and V are added to the steel material and, during production of

- 5 -

steel plate, stress-relief annealing is performed subsequent to a normalizing treatment for long hours to cause a large amount of (Mo,V)C to precipitate. Patent Literature 6 proposes a technique in which the amount of hydrogen intrusion is reduced by reducing the sizes of cementite particles and thereby the toughness of the base material is increased in order to reduce the risk of hydrogen embrittlement. Patent Literature 7 proposes a technique in which formation of coarse cementite particles and island-like martensite (i.e., martensite-austenite constituent (MA)) is inhibited and thereby occurrences of hydrogen intrusion and ductility deterioration are limited in order to reduce the risk of hydrogen embrittlement. The fatigue crack propagation characteristic of ordinary low-alloy steels is described in, for example, Non Patent Literature 1 and Non Patent Literature 2.

[Citation List]

[Patent Literature]

[0007]

[PTL 1] Japanese Unexamined Patent Application
Publication No. 2005-2386

[PTL 2] Japanese Unexamined Patent Application
Publication No. 2009-46737

[PTL 3] Japanese Unexamined Patent Application
Publication No. 2009-275249

- 6 -

[PTL 4] Japanese Unexamined Patent Application
Publication No. 2009-74122

[PTL 5] Japanese Unexamined Patent Application
Publication No. 2010-37655

[PTL 6] Japanese Unexamined Patent Application
Publication No. 2012-107332

[PTL 7] Japanese Unexamined Patent Application
Publication No. 2012-107333

[Non Patent Literature]

[0008]

[NPL 1] Yoru WADA: "Journal of the Hydrogen Energy
Systems Society of Japan", Vol. 35, No. 4 (2010), pp. 38-44

[NPL 2] Taisuke MIYAMOTO et al.: "Transactions of The
Japan Society of Mechanical Engineers (Series A)", Vol. 78,
No. 788 (2012), pp. 531-546

[Summary of Invention]

[Technical Problem]

[0009]

A high-pressure hydrogen storage tank, which is used in a particularly high-pressure hydrogen atmosphere, is subjected to a cyclic stress since the storage tank is repeatedly filled with hydrogen, which makes it difficult to achieve a long service life. In order to increase the service life, it is important to reduce fatigue crack propagation rate. In general, the fatigue crack propagation

- 7 -

rate is evaluated in the following manner: the relationship between fatigue crack propagation rate da/dN (da/dN : amount of crack propagation per cycle of cyclic load) and stress intensity factor range ΔK is determined empirically, and the value of da/dN when ΔK is about $25 \text{ MPa}\cdot\text{m}^{1/2}$ is used for evaluating the characteristic. It is considered that, in high-pressure hydrogen, the required characteristic is achieved when the value of da/dN is $1.0 \times 10^{-6} \text{ m/cycle}$ or less. The inventors of the present invention have also found that, in addition to the above-described index, it is desirable to set the C-value, which is determined on the basis of Paris' law $da/dN = \log(C(\Delta K)^m)$ (where C and m are constants primarily based on the material used) using data having a stress intensity factor range ΔK of about 20 to about $50 \text{ MPa}\cdot\text{m}^{1/2}$, to 8.0×10^{-11} or less, which enables the above-described characteristic to be achieved more consistently. However, in the above-described techniques of the related art, it is still impossible to reduce the fatigue crack propagation rate and the C-value to sufficiently low degrees.

[0010]

The present invention was made in light of the above-described fact. An object of the present invention is to provide a steel material and a hydrogen container that achieves a lower fatigue crack propagation rate in a high-

- 8 -

pressure hydrogen atmosphere than steel material used in the related art, a method for producing such a steel material, and a method for producing such a hydrogen container.

[0011]

Steel materials such as steel pipes and hydrogen containers such as high-pressure hydrogen storage tanks, which are used in the above-described high-pressure hydrogen atmosphere, preferably have a tensile strength TS of less than 900 MPa in order to further increase safety and further reduce the risk of hydrogen embrittlement. In such a case, the tensile strength TS is more preferably set to 700 MPa or more in order to increase the strength of a steel material and thereby reduce the thickness of the container in consideration with the ease of installation of the container.

[0012]

In the case where primary importance is placed on an increase in strength and weight reduction, the tensile strength TS is desirably set to 900 MPa or more.

[Solution to Problem]

[0013]

The inventors of the present invention have conducted extensive studies in order to address the above-described issues and, as a result, found that it is possible to markedly reduce the fatigue crack propagation rate by

- 9 -

dispersing a fine precipitate in a steel material including tempered martensite as a main microstructure. It is possible to markedly reduce the fatigue crack propagation rate by dispersing a fine precipitate in a steel material including tempered martensite as a main microstructure in any of the following cases (i) and (ii):

i) In order to further increase safety, the tensile strength TS of a steel material is preferably set to less than 900 MPa and is more preferably set to 700 MPa or more.

ii) In the case where primary importance is placed on weight reduction, the tensile strength TS of a steel material is set to 900 MPa or more.

[0014]

Specifically, the summary of the present invention is as follows.

[0015]

[1] A steel material having a good fatigue crack propagation characteristic in a high-pressure hydrogen atmosphere, the steel material including: a composition containing, by mass, C: 0.05% to 0.60%, Si: 0.01% to 2.0%, Mn: 0.3% to 3.0%, P: 0.001% to 0.040%, S: 0.0001% to 0.010%, N: 0.0001% to 0.0060%, Al: 0.01% to 1.5%, one or more elements selected from Ti: 0.01% to 0.20%, Nb: 0.01% to 0.20%, and V: 0.01% or more and less than 0.05%, and one or more elements selected from B: 0.0001% to 0.01%, Mo: 0.005%

- 10 -

to 2.0%, and Cr: 0.005% to 3.0%, with the balance being Fe and inevitable impurities;

and a steel microstructure

that includes 95% or more of tempered martensite on a volume fraction basis,

that includes a precipitate having a diameter of 100 nm or less and including one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen at a density of 50 particles/ μm^2 or more,

and that includes prior austenite having a grain diameter of 3 μm or more.

[0016]

[2] The steel material having a good fatigue crack propagation characteristic in a high-pressure hydrogen atmosphere which is described in [1] above, the steel material including, by mass, C: 0.05% or more and less than 0.21%.

[0017]

[3] The steel material having a good fatigue crack propagation characteristic in a high-pressure hydrogen atmosphere which is described in [1] above, the steel material including, by mass, C: 0.21% to 0.60%.

[0018]

[4] The steel material having a good fatigue crack propagation characteristic in a high-pressure hydrogen

- 11 -

atmosphere which is described in any one of [1] to [3] above, the steel material further including, by mass, one or more elements selected from Ni: 0.005% to 0.70% and Cu: 0.005% to 2.00%.

[0019]

[5] The steel material having a good fatigue crack propagation characteristic in a high-pressure hydrogen atmosphere which is described in any one of [1] to [4] above, the steel material further including, by mass, one or more elements selected from Ca: 0.001% to 0.01% and REM: 0.001% to 0.01%.

[0020]

[6] The steel material having a good fatigue crack propagation characteristic in a high-pressure hydrogen atmosphere which is described in any one of [1] to [5] above, the steel material further including, by mass, one or more elements selected from Mg: 0.001% to 0.01% and Zr: 0.001% to 0.01%.

[0021]

[7] The steel material having a good fatigue crack propagation characteristic in a high-pressure hydrogen atmosphere which is described in any one of [1] to [6] above, the steel material further including, by mass, Sb: 0.0001% to 0.1%.

[0022]

- 12 -

[8] The steel material having a good fatigue crack propagation characteristic in a high-pressure hydrogen atmosphere which is described in any one of [1] to [7] above, the steel material further including, by mass, W: 0.001% to 1%.

[0023]

[9] The steel material having a good fatigue crack propagation characteristic which is described in any one of [1] to [8] above, the steel material being a steel pipe.

[0024]

[10] A hydrogen container having a good fatigue crack propagation characteristic in a high-pressure hydrogen atmosphere including: the composition described in any one of [1] to [8] above;

and a steel microstructure

that includes 95% or more of tempered martensite on a volume fraction basis,

that includes a precipitate having a diameter of 100 nm or less and including one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen at a density of 50 particles/ μm^2 or more,

and that includes prior austenite having a grain diameter of 3 μm or more.

[0025]

[11] A method for producing a steel material having a

- 13 -

good fatigue crack propagation characteristic in a high-pressure hydrogen atmosphere,

the steel material including a steel microstructure that includes 95% or more of tempered martensite on a volume fraction basis,

that includes a precipitate having a diameter of 100 nm or less and including one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen at a density of 50 particles/ μm^2 or more,

and that includes prior austenite having a grain diameter of 3 μm or more,

the method including: heating a steel having the composition described in any one of [1] to [8] to 1100°C or more; performing working in such a manner that a working ratio from 950°C to a finishing temperature is 20% or less, the finishing temperature being 800°C or more; performing cooling to 350°C or less at a cooling rate of 1°C/sec. or more; performing heating to 400°C or more and 750°C or less, followed by holding for 60 seconds or more; and performing cooling.

[0026]

[12] A method for producing a steel pipe having a good fatigue crack propagation characteristic in a high-pressure hydrogen atmosphere,

the steel pipe including a steel microstructure

- 14 -

that includes 95% or more of tempered martensite on a volume fraction basis,

that includes a precipitate having a diameter of 100 nm or less and including one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen at a density of 50 particles/ μm^2 or more,

and that includes prior austenite having a grain diameter of 3 μm or more,

the method including: heating a steel having the composition described in any one of [1] to [8] to 1100°C or more; performing working in such a manner that a pipe-expanding ratio from 950°C to a finishing temperature is 20% or less, the finishing temperature being 800°C or more; performing cooling to 350°C or less at a cooling rate of 1°C/sec. or more; performing heating to 400°C or more and 750°C or less, followed by holding for 60 seconds or more; and performing cooling.

[0027]

[13] A method for producing a steel material having a good fatigue crack propagation characteristic in a high-pressure hydrogen atmosphere,

the steel material including a steel microstructure

that includes 95% or more of tempered martensite on a volume fraction basis,

that includes a precipitate having a diameter of 100 nm

- 15 -

or less including one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen at a density of 50 particles/ μm^2 or more,

and that includes prior austenite having a grain diameter of 3 μm or more,

the method including: heating a steel material having the composition described in any one of [1] to [8] to 800°C or more, the steel material having a microstructure having an average particle diameter of 3 μm or more, the microstructure being formed by performing saturated picric acid etching, followed by holding for 60 seconds or more; performing cooling to 350°C or less at a cooling rate of 1°C/sec. or more; performing heating to 400°C or more and 750°C or less, followed by holding for 60 seconds or more; and performing cooling.

[0028]

[14] A method for producing a hydrogen container having a good fatigue crack propagation characteristic in a high-pressure hydrogen atmosphere,

the hydrogen container including a steel microstructure that includes 95% or more of tempered martensite on a volume fraction basis,

that includes a precipitate having a diameter of 100 nm or less and including one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and

- 16 -

nitrogen at a density of 50 particles/ μm^2 or more,

and that includes prior austenite having a grain diameter of 3 μm or more,

the method including: forming a steel material having the composition described in any one of [1] to [8] into a container having a desired shape, the steel material having a microstructure having an average particle diameter of 3 μm or more, the microstructure being formed by performing saturated picric acid etching; performing heating to 800°C or more, followed by holding for 60 seconds or more; performing cooling to 350°C or less at a cooling rate of 1°C/sec. or more; performing heating to 400°C or more and 750°C or less, followed by holding for 60 seconds or more; and performing cooling.

[Advantageous Effects of Invention]

[0029]

According to the present invention, a markedly low fatigue crack propagation rate in a high-pressure hydrogen atmosphere of 80 MPa or more, which is lower than those of steels used in the related art, may be achieved. Furthermore, the service lives of high-pressure hydrogen storage tanks or the like used in a high-pressure hydrogen atmosphere may be increased. In addition, the safety of hydrogen storage containers used in a high-pressure hydrogen atmosphere may be increased. The steel material and the

73461-125

- 17 -

container according to the present invention can also be used even in a hydrogen atmosphere in a relatively low-hydrogen-pressure atmosphere.

[Description of Embodiments]

[0030]

The present invention is described specifically below.

First, the reasons for limiting the composition of the steel material to the above-described ranges in the present invention are described. Hereinafter, when referring to a composition, the symbol "%" refers to "% by mass" unless otherwise specified.

[0031]

C: 0.05% to 0.60%

Carbon (C) is an element that is necessary for increasing the strength of a martensite microstructure. C reacts with Ti, Nb, V, Mo, or Cr to form an alloy carbide, which reduces the risk of local accumulation of dislocation that may occur during fatigue deformation in a high-pressure hydrogen atmosphere. In a steel having a TS of less than 900 MPa, this effect occurs when the C content is 0.05% or more. In a steel having a TS of 900 MPa or more, this effect occurs when the C content is 0.21% or more. Thus, the C content needs to be 0.05% or more. In order to produce a steel having a TS of 900 MPa or more, the C content is preferably set to 0.21% or more. However, if the

- 18 -

C content exceeds 0.60%, the effect may become saturated. In addition, it may become difficult to perform working such as rolling in the production of the steel material. Furthermore, it may become difficult to forming the steel material into a container. Accordingly, in the present invention, the C content is limited to 0.05% or more and 0.60% or less. If the C content is 0.21% or more, it may become difficult to produce a steel having a TS of less than 900 MPa. Thus, in order to produce a steel having a TS of less than 900 MPa, the C content is preferably set to 0.05% or more and less than 0.21% and is further preferably set to 0.10% or more and 0.15% or less. In order to produce a steel having a TS of 900 MPa or more, the C content is preferably set to 0.21% or more and 0.60% or less and is further preferably 0.23% or more and 0.35% or less.

[0032]

Si: 0.01% to 2.0%

Silicon (Si) is an element that causes solid solution strengthening to occur, thereby contributes to an increase in strength, and reduces the risk of local accumulation of dislocation. This effect occurs when the Si content is 0.01% or more. Accordingly, the Si content is set to 0.01% or more and is preferably set to 0.02% or more. However, if the Si content exceeds 2.0%, the effect may become saturated. Moreover, it may become difficult to perform rolling and

- 19 -

forming. Accordingly, the Si content is set to 2.0% or less and is preferably set to 0.5% or less. Thus, the Si content is limited to 0.01% or more and 2.0% or less.

[0033]

Mn: 0.3% to 3.0%

Manganese (Mn) is an element that causes solid solution strengthening to occur, enhances hardenability (or quench hardenability), thereby contributes to an increase in the strength of a steel, and reduces the risk of local accumulation of dislocation. This effect occurs when the Mn content is 0.3% or more. Accordingly, the Mn content is set to 0.3% or more and is preferably set to 0.5% or more. However, if the Mn content exceeds 3.0%, the effect may become saturated. Moreover, it may become difficult to perform rolling and forming. In addition, fatigue crack propagation rate may be increased. Furthermore, large amounts of untempered hard martensite and austenite may remain, which deteriorates fatigue characteristic. Accordingly, the Mn content is set to 3.0% or less and is preferably set to 1.5% or less. Thus, the Mn content is limited to 0.3% or more and 3.0% or less and is preferably set to 0.3% or more and 1.5% or less.

[0034]

P: 0.001% to 0.040%

Phosphorus (P) is an element that contributes to an

- 20 -

increase in strength. However, on the other hand, this element may reduce toughness and increase fatigue crack propagation rate. This disadvantageous effect may become significant if the P content exceeds 0.040%. Accordingly, the P content is set to 0.040% or less, is preferably set to 0.025% or less, and is more preferably set to 0.015% or less. However, an excessively low P content of less than 0.001% may increase the production cost in a steelmaking process. Accordingly, the P content is set to 0.001% or more. Thus, the P content is limited to 0.001% or more and 0.040% or less, is preferably set to 0.001% or more and 0.025% or less, and is more preferably set to 0.001% or more and 0.015% or less.

[0035]

S: 0.0001% to 0.010%

An increase in the sulfur (S) content may cause hot and red brittleness to occur, which leads to problems in a production process. In addition, an inclusion MnS may be formed, which reduces toughness. Furthermore, an increase in the S content increases fatigue crack propagation rate. However, these disadvantageous effects are negligible when the S content is 0.010% or less. Accordingly, the S content is set to 0.010% or less and is preferably set to 0.0030% or less. However, an excessively low S content of less than 0.0001% may increase the desulfurization cost in a

- 21 -

steelmaking process. Accordingly, the S content is set to 0.0001% or more. Thus, the S content is limited to 0.0001% or more and 0.010% or less and is preferably set to 0.0001% or more and 0.0030% or less.

[0036]

N: 0.0001% to 0.0060%

Since the impact of nitrogen (N) on hydrogen embrittlement is small, the advantageous effects of the present invention are not impaired when the N content is 0.0060% or less. Accordingly, the N content is set to 0.0060% or less and is preferably set to 0.004% or less. A low N content is desirable in order to increase toughness, but leads to a high steelmaking cost. Accordingly, the lower limit of the N content is set to 0.0001%. Thus, the N content is set to 0.0001% or more and 0.0060% or less.

[0037]

Al: 0.01% to 1.5%

Aluminum (Al) is an element used as a deoxidizer in a steelmaking process in an effective manner. Al also inhibits precipitation of cementite and causes cementite to be dispersed in the form of fine particles. In order to enable these effects to occur, the Al content is set to 0.01% or more and is preferably set to 0.02% or more. However, if the Al content exceeds 1.5%, the alloy cost of the steel may be increased. Furthermore, the Ac3 point may

- 22 -

be considerably increased, which deteriorates hardenability. Accordingly, the Al content is set to 1.5% or less, is preferably set to 1.0% or less, and is more preferably set to 0.5% or less. Thus, the Al content is limited to 0.01% or more and 1.5% or less, is preferably set to 0.02% or more and 1.0% or less, and is further preferably set to 0.5% or less.

[0038]

One or More Elements Selected from Ti: 0.01% to 0.20%, Nb: 0.01% to 0.20%, and V: 0.01% or More and Less Than 0.05%

Titanium (Ti), niobium (Nb), and vanadium (V) each react with C or N to form a fine carbide or a fine nitride during hardening or tempering. This reduces the risk of local accumulation of dislocation that may occur during fatigue deformation in hydrogen atmosphere and thereby reduces fatigue crack propagation rate. In order to enable this effect to occur, one or more elements selected from Ti: 0.01% or more, Nb: 0.01% or more, and V: 0.01% or more are added to a steel. The contents of Ti, Nb, and V are preferably Ti: 0.07% or more, Nb: 0.12% or more, and V: 0.02% or more. However, if the Ti content exceeds 0.20%, the Nb contents exceeds 0.20%, or the V content is 0.05% or more, the effect may become saturated. Accordingly, the contents of Ti, Nb, and V are set to Ti: 0.20% or less, Nb: 0.20% or less, and V: less than 0.05% and are preferably set

- 23 -

to Ti: 0.15% or less, Nb: 0.15% or less, and V: 0.03% or less. Thus, the contents of Ti, Nb, and V are limited to Ti: 0.01% or more and 0.20% or less, Nb: 0.01% or more and 0.20% or less, and V: 0.01% or more and less than 0.05%.

[0039]

One or More Elements Selected from B: 0.0001% to 0.01%, Mo: 0.005% to 2.0%, and Cr: 0.005% to 3.0%

Boron (B), molybdenum (Mo), and chromium (Cr) may be added to a steel in order to increase ease of hardening performed subsequent to annealing and thereby achieve a high TS. Mo and Cr also contribute to formation of an alloy carbide, which reduces fatigue crack propagation rate. In order to enable these effects to occur, one or more elements selected from B: 0.0001% or more, Mo: 0.005% or more, and Cr: 0.005% or more are added to a steel. The contents of B, Mo, and Cr are preferably B: 0.0015% or more, Mo: 0.30% or more, and Cr: 0.02% or more and are more preferably B: 0.0020% or more, Mo: 0.50% or more, and Cr: 0.50% or more. However, if the B content exceeds 0.01%, the Mo content exceeds 2.0%, or the Cr content exceeds 3.0%, the effects may become saturated. Accordingly, the contents of B, Mo, and Cr are set to B: 0.01% or less, Mo: 2.0% or less, and Cr: 3.0% or less and are preferably set to B: 0.003% or less, Mo: 1.5% or less, and Cr: 2.0% or less. Thus, the contents of B, Mo, and Cr are limited to B: 0.0001% or more and 0.01%

- 24 -

or less, Mo: 0.005% or more and 2.0% or less, and Cr: 0.005% or more and 3.0% or less.

[0040]

In the present invention, the above-described components are essential in order to reduce fatigue crack propagation rate in a high-pressure hydrogen atmosphere. In the present invention, optionally, the following components may be added to a steel alone or in combination as needed: one or more elements selected from Ni: 0.005% to 0.70% and Cu: 0.005% to 2.00%; one or more elements selected from Ca: 0.001% to 0.01% and REM: 0.001% to 0.01%; one or more elements selected from Mg: 0.001% to 0.01% and Zr: 0.001% to 0.01%; Sb: 0.0001% to 0.1%; and W: 0.001% to 1%. The balance other than the above-described components is composed of Fe and inevitable impurities.

[0041]

Ni: 0.005% to 0.70%

Nickel (Ni) may be added to a steel in order to increase ease of hardening performed subsequent to annealing, which makes it easy to increase TS. This effect occurs when the Ni content is 0.005% or more. However, if the Ni content exceeds 0.70%, large amounts of untempered hard martensite and austenite are likely to remain. Accordingly, when Ni is added to a steel, the Ni content is set to 0.005% or more and 0.70% or less and is preferably set to 0.02% or

- 25 -

more and 0.05% or less.

[0042]

Cu: 0.005% to 2.00%

Similarly to Ni, copper (Cu) may be added to a steel in order to increase ease of hardening performed subsequent to annealing, which makes it easy to increase TS. This effect occurs when the Cu content is 0.005% or more, but may become saturated if the Cu content exceeds 2.00%. Accordingly, when Cu is added to a steel, the Cu content is set to 0.005% or more and 2.00% or less and is preferably set to 0.02% or more and 1.00% or less.

[0043]

Ca: 0.001% to 0.01%

Calcium (Ca) enables the shapes of sulfides such as MnS to be controlled and thereby increases toughness. This effect occurs when the Ca content is 0.001% or more, but may become saturated if the Ca content exceeds 0.01%. Accordingly, when Ca is added to a steel, the Ca content is set to 0.001% or more and 0.01% or less and is preferably set to 0.001% or more and 0.005% or less.

[0044]

REM: 0.001% to 0.01%

Similarly to Ca, REM enables the shapes of sulfides such as MnS to be controlled and thereby increases toughness. This effect occurs when the REM content is 0.001% or more,

- 26 -

but may become saturated if the REM content exceeds 0.01%. Accordingly, when REM is added to a steel, the REM content is set to 0.001% or more and 0.01% or less and is preferably set to 0.001% or more and 0.005% or less. Note that "REM" is an abbreviation for "rare earth metal".

[0045]

Mg: 0.001% to 0.01%

Magnesium (Mg) causes a precipitate to be formed, which reduces the risk of local accumulation of dislocation that may occur during fatigue deformation in a hydrogen atmosphere and thereby reduces fatigue crack propagation rate. In order to enable this effect to occur, the Mg content needs to be 0.001% or more. However, if the Mg content exceeds 0.01%, the effect may become saturated. Accordingly, when Mg is added to a steel, the Mg content is set to 0.001% or more and 0.01% or less.

[0046]

Zr: 0.001% to 0.01%

Similarly to Mg, zirconium (Zr) causes a precipitate to be formed, which reduces the risk of local accumulation of dislocation that may occur during fatigue deformation in a hydrogen atmosphere and thereby reduces fatigue crack propagation rate. In order to enable this effect to occur, the Zr content needs to be 0.001% or more. However, if the Zr content exceeds 0.01%, the effect may become saturated.

- 27 -

Accordingly, when Zr is added to a steel, the Zr content is set to 0.001% or more and 0.01% or less.

[0047]

Sb: 0.0001% to 0.1%

Antimony (Sb) inhibits the deviation of the grain diameter in the surface layer of a steel plate, thereby improves the surface quality, and inhibits decarburization of the surface portion of the steel plate. In order to enable this effect to occur, the Sb content needs to be 0.0001% or more and is preferably set to 0.0010% or more. However, if the Sb content exceeds 0.1%, the effect may become saturated and the cost is rapidly increased. Accordingly, the Sb content is set to 0.1% or less and is preferably set to 0.01% or less. Thus, when Sb is added to a steel, the Sb content is set to 0.0001% or more and 0.1% or less.

[0048]

W: 0.001% to 1%

Tungsten (W) reacts with C to form a fine carbide, thereby, similarly to Ti, Nb, and the like, reduces the risk of local accumulation of dislocation that may occur during fatigue deformation in a hydrogen atmosphere, and reduces fatigue crack propagation rate. In order to enable this effect to occur, the W content need to be 0.001% or more and is preferably set to 0.01% or more. However, if the W

73461-125

- 28 -

content exceeds 1%, the effect may become saturated and the cost is rapidly increased. Accordingly, the W content is set to 1% or less and is preferably set to 0.1% or less. Thus, when W is added to a steel, the W content is set to 0.001% or more and 1% or less.

[0049]

Next, the microstructure of the steel material is described.

The steel material and the hydrogen container composed of a steel according to the present invention have a steel microstructure that includes 95% or more of tempered martensite on a volume fraction basis, that includes a precipitate having a diameter of 100 nm or less and including one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen at a density of 50 particles/ μm^2 or more, and that includes prior austenite having a grain diameter of 3 μm or more.

[0050]

Volume Fraction of Tempered Martensite: 95% or More

A microstructure mainly constituted by tempered martensite needs to be formed in order to achieve a tensile strength TS of less than 900 MPa and more preferably achieve a tensile strength TS of 700 MPa or more and to disperse the precipitate having a diameter of 100 nm or less described below at a density of 50 particles/ μm^2 or more in the case

- 29 -

where the C content is set to 0.05% or more and less than 0.21%. A microstructure mainly constituted by tempered martensite needs to be formed in order to achieve a tensile strength TS of 900 MPa or more and to disperse the precipitate having a diameter of 100 nm or less described below at a density of 50 particles/ μm^2 or more in the case where the C content is set to 0.21% or more and 0.60% or less. It is necessary to form a microstructure mainly constituted by tempered martensite in order to cause a precipitate to be formed during tempering performed subsequent to hardening, which enables the precipitate to be uniformly and finely dispersed. If a microstructure other than tempered martensite serves as a main microstructure, the precipitate may be dispersed nonuniformly and the desired characteristic may fail to be achieved. Although mixing of a microstructure other than tempered martensite may limit the reduction in fatigue crack propagation rate and reduce toughness, the advantageous effects of the present invention are not impaired when the volume fraction of tempered martensite is 95% or more. In other words, the allowable total fraction of microstructures other than tempered martensite is 5% or less. Thus, the volume fraction of tempered martensite is set to 95% or more. Examples of the microstructures other than tempered martensite include martensite, austenite, bainite, tempered

- 30 -

bainite, ferrite, and pearlite. As described above, one or more microstructures selected from these microstructures may be mixed in such a manner that the total volume fraction of the microstructures is 5% or less.

[0051]

Density of Precipitate Having Diameter of 100 nm or Less Which Includes One or More Elements Selected from Ti, Nb, and V and One or More Elements Selected from Carbon and Nitrogen: 50 Particles/ μm^2 or More

A microstructure including a precipitate which has a diameter of 100 nm or less and which includes one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen (i.e., one or more selected from a carbide, a nitride, and a carbonitride) at a density of 50 particles/ μm^2 or more, may reduce fatigue crack propagation rate in a hydrogen atmosphere. The precipitate may further include, in addition to these elements, Mo, Cr, and the like.

[0052]

A precipitate including one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen is likely to be finely formed in alignment with base metal and is likely to trap hydrogen therein. The above-described precipitate having a diameter of 100 nm or less is likely to trap hydrogen in the

- 31 -

periphery of the precipitate and thereby reduces the risk of local accumulation of hydrogen. If the diameter of the precipitate exceeds 100 nm, fatigue cracking is likely to occur and the reduction in fatigue crack propagation in a hydrogen atmosphere may be limited. If the precipitate density is less than 50 particles/ μm^2 , the reduction in the risk of local accumulation of hydrogen may be limited. Accordingly, in the present invention, the density of a precipitate having a diameter of 100 nm or less which includes one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen is set to 50 particles/ μm^2 or more. The diameter of the precipitate is preferably 50 nm or less. The diameter of the precipitate is preferably 1 nm or more. The precipitate density is preferably 80 particles/ μm^2 or more. The precipitate density is preferably 200 particles/ μm^2 or less.

[0053]

Grain Diameter of Prior Austenite: 3 μm or More

If the grain diameter of prior austenite is less than 3 μm , cracks are likely to link up with one another, which increases the speed of crack propagation. As a result, the desired characteristic may fail to be achieved. Accordingly, the grain diameter of prior austenite is set to 3 μm or more. It is preferable to set the grain diameter of prior austenite to be large. Specifically, the grain diameter of

- 32 -

prior austenite is preferably 10 μm or more and is more preferably 15 μm or more. The grain diameter of prior austenite is preferably 30 μm or less.

[0054]

A method and the like for producing the steel material such as a steel sheet, a steel plate, or a steel pipe and the hydrogen container according to the present invention are not particularly limited as long as a steel material or a hydrogen container has the above-described chemical composition and the above-described microstructure. Preferable methods for producing the steel material and the hydrogen container are described below.

[0055]

Preferable conditions for producing the steel material according to the present invention are described below.

A steel such as a slab is produced from a molten steel having the above-described composition by a continuous casting process or an ingot-making and slabbing method. After being heated to 1100°C or more, the steel is subjected to working with a finishing temperature of 800°C or more in such a manner that the working ratio from 950°C to the finishing temperature is 20% or less. Subsequently, cooling to 350°C or less at a cooling rate of 1°C/sec. or more, heating to 400°C or more and 750°C or less, followed by holding for 60 seconds or more, and cooling are performed.

- 33 -

Thus, the steel material is worked into a desired form. Examples of the form of the steel material include, but are not particularly limited to, a plate material, a pipe material, and a shape material. For example, the above-described steel material may be worked into the form of a pipe material, that is, a steel pipe, and used as a material of a high-pressure storage tank or as a hydrogen transportation pipe. The term "working" used herein refers to working for producing a steel material. For example, in the case where the steel material has a plate-like shape such as a steel plate, the term "working" refers to rolling and the term "working ratio" refers to rolling reduction ratio. In the case where the steel material is a steel pipe, the term "working" refers to pipe expanding and the term "working ratio" refers to pipe-expanding ratio.

[0056]

Specifically, for example, a steel material having a plate-like shape, such as a steel plate, is produced in the following manner. After being heated to 1100°C or more, the steel is subjected to rolling with a finishing temperature of 800°C or more in such a manner that the rolling reduction ratio from 950°C to the finishing temperature is 20% or less. Subsequently, cooling to 350°C or less at a cooling rate of 1°C/sec. or more, heating to 400°C or more and 750°C or less, followed by holding for 60 seconds or more, and cooling are

- 34 -

performed. Thus, the steel material is worked into a desired form. In the case where the steel material is a steel pipe, the steel material is produced in the following manner. After being heated to 1100°C or more, the steel is subjected to pipe expanding with a finishing temperature of 800°C or more in such a manner that the pipe-expanding ratio from 950°C to the finishing temperature is 20% or less. Subsequently, cooling to 350°C or less at a cooling rate of 1°C/sec. or more, heating to 400°C or more and 750°C or less, followed by holding for 60 seconds or more, and cooling are performed. Thus, the steel material is worked into a desired form.

[0057]

The specific ranges to which the conditions for producing the above-described steel material are limited and the reasons for limiting the ranges are described specifically below.

Steel-Heating Temperature: 1100°C or More

Since one or more elements selected from Ti, Nb, and V are used in the present invention, these elements, that is, Ti, Nb, and V, precipitate in a steel such as a steel slab in the form of large particles during solidification. It is necessary to dissolve this precipitate while heating is performed prior to hot working such as hot rolling or hot pipe-expanding. Accordingly, it is necessary to set the

- 35 -

steel-heating temperature to 1100°C or more. Heating the steel to 1100°C or more is also advantageous in order to scale-off the defects such as voids or segregation which may occur in the surface layer of a steel such as a slab, thereby reduce cracks and irregularities formed in the surface of the steel plate, and achieve smooth surface of the steel plate. Thus, the steel-heating temperature is set to 1100°C or more and is preferably set to 1150°C or more. This effect may become saturated and the cost may be increased if the heating temperature exceeds 1300°C. Thus, the steel-heating temperature is preferably 1300°C or less and is more preferably 1250°C or less.

[0058]

Performing Working in Such Manner That the Working Ratio from 950°C to Finishing Temperature of 800°C or More Is 20% or Less, Followed by Cooling to 350°C or Less at Cooling Rate of 1°C/sec. or More

If the finishing temperature for hot working is less than 800°C, ferrite is likely to be mixed in the final microstructure. If the working ratio from 950°C to the finishing temperature exceeds 20%, ferrite transformation and bainite transformation are likely to occur during cooling, which may inhibit formation of the predetermined microstructure. If the cooling rate is less than 1°C/sec. or the cooling target temperature (i.e., cooling stop

- 36 -

temperature) exceeds 350°C, it may be difficult to set the volume fraction of a martensite microstructure to 95% or more and the volume fraction of a tempered martensite to 95% or more. Accordingly, working with a finishing temperature of 800°C or more is performed in such a manner that the working ratio from 950°C to the finishing temperature is 20% or less, and subsequently cooling to 350°C or less at a cooling rate of 1°C/sec. or more is performed. The finishing temperature is preferably set to 850°C or more. The cooling rate is preferably set to 10°C/sec. or more.

As described above, the term "working ratio" used herein refers to roll reduction ratio in the case where rolling is performed and pipe-expanding ratio in the case where pipe expanding is performed. The working ratio is preferably set to 15% or less. The working ratio is preferably set to 2% or more. The finishing temperature is preferably 1000°C or less because a finishing temperature exceeding 1000°C may increase the cost. If the cooling rate exceeds 500°C/sec, hardening cracking and shape defects may occur in the steel material. Accordingly, the cooling rate is preferably set to 500°C/sec. or less and is more preferably set to 100°C/sec. or less. The target temperature during cooling is preferably as low as possible. Specifically, the target temperature during cooling is preferably 100°C or less. Cooling may be performed in

- 37 -

accordance with the conventional method. For example, water cooling, oil cooling, air cooling, and mist cooling may be employed.

[0059]

Performing Heating to 400°C or More and 750°C or Less,
Followed by Holding for 60 Seconds or More, and Subsequently
Performing Cooling

The steel material including a martensite microstructure, which has been subjected to the above-described working and cooling, is heated (reheated) to 400°C or more and subsequently held for 60 seconds or more in order to perform tempering and cause a desired precipitate to be formed. Heating is preferably performed to 550°C or more. The holding time is preferably set to 1800 seconds or more. If the heating temperature during tempering exceeds 750°C, a part of the martensite microstructure may be transformed into austenite, which increases the amounts of untempered hard martensite and austenite that occur after cooling. Accordingly, the heating temperature during tempering is set to 750°C or less and is preferably set to 720°C or less. In order to increase the amount of precipitate, the heating temperature during tempering is preferably set to 550°C or more and 720°C or less, and the holding time is preferably set to 1800 seconds or more. The holding time is preferably set to about 3 hours or less

- 38 -

because an excessively long holding time may increase the cost.

[0060]

Alternatively, the steel material according to the present invention may also be produced by heating a steel material having a microstructure having an average grain diameter of 3 μm or more to 800°C or more, the microstructure being formed by performing saturated picric acid etching, followed by holding for 60 seconds or more; performing cooling to 350°C or less at a cooling rate of 1°C/sec. or more; performing heating to 400°C or more and 750°C or less, followed by holding for 60 seconds or more; and performing cooling.

[0061]

Average Grain Diameter of Microstructure Formed by Performing Saturated Picric Acid Etching: 3 μm or More

It is possible to remove phosphorus segregation parts, that is, the prior-austenite grain boundary, the ferrite grain boundary, the pearlite region boundary, and the bainite region boundary, by performing saturated picric acid etching. Therefore, the average diameter of these grains can be determined by measuring the average grain diameter of the microstructure formed by performing saturated picric acid etching. Hereinafter, this average diameter is referred to as "average grain diameter". If the average

grain diameter of the microstructure formed by subjecting the steel material, which serves as a raw material, to saturated picric acid etching is less than 3 μm , the grain diameter of prior-gamma may become small while the steel material, which serves as a raw material, is heated and, during cooling, ferrite transformation and bainite transformation may occur. As a result, the desired characteristic may fail to be achieved. Accordingly, a steel material having a microstructure having an average grain diameter of 3 μm or more, the microstructure being formed by performing saturated picric acid etching, is used as a raw material. The average grain diameter of the microstructure is more preferably 5 μm or more. The average grain diameter is preferably 30 μm or less because the performances may become saturated if the average grain diameter is more than 30 μm .

[0062]

Performing Heating to 800°C or More, Followed by Holding for 60 Seconds or More, and Subsequently Performing Cooling to 350°C or Less at Cooling Rate of 1°C/sec. or More

If the heating temperature is set to less than 800°C, ferrite is likely to be mixed in the final microstructure. If the holding time is set to less than 60 seconds, the temperature of the steel plate may become nonuniform in the thickness direction, which results in production of faulty

- 40 -

products. If the cooling rate is less than 1°C/sec. or the cooling target temperature exceeds 350°C, it may be difficult to set the fraction of a martensite microstructure to 95% or more. Accordingly, the heating temperature is set to 800°C or more and, after holding for 60 seconds or more, cooling to 350°C or less at a cooling rate of 1°C/sec. or more is performed. The heating temperature is preferably 820°C or more. The holding time is preferably 120 seconds or more. The cooling rate is preferably 8°C/sec. or more. The heating temperature is preferably 1000°C or less because a heating temperature exceeding 1000°C may increase the cost. The holding time is preferably 1 hour or less because an excessively long holding time may increase the cost. If the cooling rate exceeds 500°C/sec, hardening cracking and shape defects may occur in the steel material. Therefore, the cooling rate is preferably 500°C/sec. or less and is more preferably 100°C/sec. or less. The target temperature during cooling is preferably as low as possible. Specifically, the target temperature during cooling is preferably 100°C or less. Cooling may be performed by the conventional method. For example, water cooling, oil cooling, air cooling, and mist cooling may be employed.

[0063]

Performing Heating to 400°C or More and 750°C or Less,
Followed by Holding for 60 Seconds or More, and Subsequently

- 41 -

Performing Cooling

It is necessary to perform heating (reheating) to 400°C or more in order to temper the martensite to form tempered martensite. It is preferable to perform heating to 550°C or more. Performing tempering at a temperature exceeding 750°C may cause a part of the steel microstructure to transform into austenite, which increases the amounts of hard untempered martensite and austenite that occur after cooling. Accordingly, heating to 750°C or less is performed. It is preferable to perform heating to 720°C or less. It is necessary to perform holding for 60 seconds or more in order to temper the steel material or the steel pipe uniformly in the thickness direction. The holding time is preferably 1800 seconds or more. In order to increase the amount of precipitate, it is preferable to perform tempering at 550°C or more and 720°C or less for 1800 seconds or more. The holding time is preferably 3 hours or less because an excessively long holding time may increase the cost.

[0064]

Preferable conditions for producing the hydrogen container are described below.

The hydrogen container according to the present invention is produced by forming a steel material having the above-described composition and having a microstructure having an average grain diameter of 3 μm or more into a

- 42 -

container having a desired shape, the microstructure being formed by performing saturated picric acid etching; subsequently performing heating to 800°C or more, followed by holding for 60 seconds or more; performing cooling to 350°C or less at a cooling rate of 1°C/sec. or more; performing heating to 400°C or more and 750°C or less, followed by holding for 60 seconds or more; and then cooling the container. The specific ranges to which the conditions for producing the above-described hydrogen container are limited and the reasons for limiting the ranges are described specifically below.

[0065]

Average Grain Diameter of Microstructure Formed by Performing Saturated Picric Acid Etching: 3 μm or More

It is possible to remove phosphorus segregation parts, that is, the prior-austenite grain boundary, the ferrite grain boundary, the pearlite region boundary, and the bainite region boundary, by performing saturated picric acid etching. Therefore, the average diameter of these grains can be determined by measuring the average grain diameter of the microstructure formed by performing saturated picric acid etching. Hereinafter, this average diameter is referred to as "average grain diameter". If the average grain diameter of the microstructure formed by subjecting the steel material, which serves as a raw material, to

73461-125

- 43 -

saturated picric acid etching is less than 3 μm , the grain diameter of prior-gamma may become small while the steel material, which serves as a raw material, is heated and, during cooling, ferrite transformation and bainite transformation may occur. As a result, the desired characteristic may fail to be achieved. Accordingly, a steel material having a microstructure having an average grain diameter of 3 μm or more, the microstructure being formed by performing saturated picric acid etching, is used as a raw material. The average grain diameter of the microstructure is more preferably 5 μm or more. The average grain diameter is preferably 30 μm or less because the performances may become saturated if the average grain diameter is more than 30 μm .

The steel material may be formed into a container having a desired shape by any conventional method. It is not necessary to limit the conditions and the like.

[0066]

Performing Heating to 800°C or More, Followed by Holding for 60 Seconds or More, and Subsequently Performing Cooling to 350°C or Less at Cooling Rate of 1°C/sec. or More

If the heating temperature is set to less than 800°C, ferrite is likely to be mixed in the final microstructure. If the holding time is set to less than 60 seconds, the temperature of the steel plate may become nonuniform in the

- 44 -

thickness direction, which results in production of faulty products. If the cooling rate is less than 1°C/sec. or the cooling target temperature exceeds 350°C, it may be difficult to set the fraction of a martensite microstructure to 95% or more. Accordingly, the heating temperature is set to 800°C or more and, after holding for 60 seconds or more, cooling to 350°C or less at a cooling rate of 1°C/sec. or more is performed. The heating temperature is preferably 820°C or more. The holding time is preferably 120 seconds or more. The cooling rate is preferably 8°C/sec. or more. The heating temperature is preferably 1000°C or less because a heating temperature exceeding 1000°C may increase the cost. The holding time is preferably 1 hour or less because an excessively long holding time may increase the cost. If the cooling rate exceeds 500°C/sec, hardening cracking and shape defects may occur in the steel material. Therefore, the cooling rate is preferably 500°C/sec. or less and is more preferably 100°C/sec. or less. The target temperature during cooling is preferably as low as possible. Specifically, the target temperature during cooling is preferably 100°C or less.

[0067]

Performing Heating to 400°C or More and 750°C or Less,
Followed by Holding for 60 Seconds or More, and Subsequently
Performing Cooling

- 45 -

It is necessary to perform heating (reheating) to 400°C or more in order to temper the martensite to form tempered martensite. It is preferable to perform heating to 550°C or more. Performing tempering at a temperature exceeding 750°C may cause a part of the steel microstructure to transform into austenite, which increases the amounts of hard untempered martensite and austenite that occur after cooling. Accordingly, heating to 750°C or less is performed. It is preferable to perform heating to 720°C or less. It is necessary to perform holding for 60 seconds or more in order to temper the container uniformly in the wall-thickness (i.e., plate-thickness) direction. The holding time is preferably 1800 seconds or more. In order to increase the amount of precipitate, it is preferable to perform tempering at 550°C or more and 720°C or less for 1800 seconds or more. The holding time is preferably 3 hours or less because an excessively long holding time may increase the cost.

[EXAMPLE 1]

[0068]

Molten steels having the compositions shown in Table 1 were each formed into a steel plate having a thickness of 25 mm under the specific conditions shown in Table 2. The molten steels were also each formed into a steel pipe having a thickness of 25 mm under the specific conditions shown in Table 3. Note that the "Working ratio" in Table 2 (where

- 46 -

the product type is "Steel plate") refers to rolling reduction ratio, while the "Working ratio" in Table 3 (where the product type is "Steel pipe") refers to pipe-expanding ratio. The "Cooling rate" refers to the average cooling rate from the finishing temperature to 350°C. Cooling was performed until the temperature reached 350°C or less. The "Reheating temperature" in Tables 2 and 3 refers to a temperature at which heating (reheating) was performed after cooling was performed at the cooling rate. The "Holding time" refers to a holding time during reheating.

[0069]

The steel materials having the compositions shown in Table 1 were each formed into a steel plate, a steel pipe, or a container having a plate thickness or a wall thickness of 25 mm under the specific conditions shown in Table 4. In the case where the product type was "Container", the steel pipe having the specific composition shown in Table 1 was used as a steel material. The steel material was formed into a container, and the container was heated to the specific heating temperature shown in Table 4. The "Cooling rate" in Table 4 refers to the average cooling rate over the heating temperature to 350°C except for the samples in which the cooling termination temperature exceeded 350°C; in the samples in which the cooling termination temperature exceeded 350°C, the "Cooling rate" refers to the average

- 47 -

cooling rate over the heating temperature to the cooling termination temperature. The "Reheating temperature" in Table 4 refers to a temperature at which heating (reheating) was performed after cooling was performed at the cooling rate. The "Initial grain diameter of steel material" in Table 4 refers to the average grain diameter determined from an image of the microstructure formed by performing saturated picric acid etching.

[0070]

The steel plates, steel pipes, and containers prepared under the respective conditions shown in Tables 2, 3, and 4 were examined in terms of steel microstructure and tensile property and subjected to a fatigue crack propagation test in hydrogen at 110 MPa. Tables 2, 3, and 4 summarize the results. In Table 4, the product type of each sample, that is, "Steel plate", "Steel pipe", or "Container", is described. The same results were obtained regardless of the product type because the raw material was heated to 800°C or more, that is, an austenite-single phase region, subsequently cooled, and subjected to a heat treatment. Specifically, performing heating to an austenite single-phase region caused a steel microstructure to be transformed into austenite. Therefore, the thermal history of the raw material which was recorded subsequent to heating to the austenite single-phase region greatly affected the steel

- 48 -

microstructure regardless of the history of the raw material which was recorded prior to heating to the austenite single-phase region. Thus, the same results were obtained regardless of the product type. Material tests and material property evaluations were conducted in the following manner.

[0071]

(1) Steel Microstructure

An electron scanning microscope (SEM) image of a cross section of the steel plate or steel pipe which was parallel to the rolling direction was captured at the 1/4-thickness position at an appropriate magnification of 1000 to 3000 times in order to observe tempered martensite, ferrite, bainite, and pearlite. The ferrite phase, the bainite phase, the pearlite phase, and cementite were visually distinguished in order to determine the microstructures. In order to determine the fractions of the microstructures, the above-described SEM image was subjected to an image analysis to calculate the volume fraction of each phase. Portions other than the above-described phases were considered to be hard untempered martensite or austenite. In the case where the product type was "Container", the above-described examination was conducted in the direction of the steel material constituting the container.

In order to determine the size and number of the precipitate particles, a transmission electron microscope

- 49 -

(TEM) sample at the 1/4-thickness position was prepared by a thin-film method, a precipitate formed at tempered martensite portions was observed by a transmission method at a magnification of 10000 to 300000 times, and the diameters of the precipitate particles and the density of the precipitate particles having a diameter of 100 nm or less were measured. The precipitate density was calculated over an area of 1 μm^2 or more. The diameters of the precipitate particles were measured by a method of section. Whether the precipitate included one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen was determined using an energy-dispersive X-ray spectroscopy system (EDX).

The grain diameter of prior austenite included in the product (i.e., grain diameter of prior-gamma included in the microstructure) was determined by performing saturated picric acid etching.

[0072]

(2) Tensile Property

A tensile test conforming to JIS Z2241 was conducted using a No. 5 test piece described in JIS Z2201 (1980) in a longitudinal direction (tensile direction) that was the rolling direction of the steel plate or the steel pipe in order to make an evaluation. In the case where the product type was "Container", the above-described examination was

- 50 -

conducted in the direction of the steel material constituting the container.

[0073]

(3) Fatigue Crack Propagation Test

A fatigue crack propagation test was conducted in accordance with ASTM E647 using compact tension specimens (CT specimens) in order to determine fatigue crack propagation rate. The test specimens were taken at a position of $t/2$ (t : plate thickness) of the steel material so as to have a thickness of 10 mm. Both surfaces of a crack propagation portion were subjected to mirror polishing. In the case where the product type was "Steel plate" or "Steel pipe", the examination was conducted using a test specimen taken so that the fatigue cracks propagated in a direction perpendicular to the rolling direction when a tensile or compression load was applied in the rolling direction. In the case where the product type was "Container", the examination was conducted as in the cases of "Steel plate" and "Steel pipe" by applying a tensile or compression load in the rolling direction of the steel material constituting the container. The stress ratio was set to minus one. The fatigue crack propagation test was conducted as described above, and a fatigue crack propagation rate at $\Delta K = 25 \text{ MPa}\cdot\text{m}^{1/2}$ was determined. Furthermore, the C-value was determined on the basis of

- 51 -

Paris' law $da/dN = \log(C(\Delta K)^m)$ (where C and m are constants primarily based on the material used) using data having a stress intensity factor range ΔK of 20 to 50 MPa·m^{1/2}, which is a stable growth region in which Paris' law holds.

[0074]

As summarized in Tables 2, 3, and 4, in the invention examples, 700 MPa ≤ TS < 900 MPa was satisfied when 0.05% ≤ the C content < 0.21%, and TS ≥ 900 MPa was satisfied when 0.21% ≤ the C content ≤ 0.60%. In the invention examples, the C-value determined in the fatigue crack propagation test achieved $C \leq 8.0 \times 10^{-11}$, and a fatigue crack propagation rate at $\Delta K = 25 \text{ MPa} \cdot \text{m}^{1/2}$ achieved $1.0 \times 10^{-6} \text{ m/cycle}$ or less.

[0075]

[Table 1]

Steel type	Chemical composition (mass%)																					Remark
	C	Si	Mn	P	S	Al	N	Ti	Nb	V	B	Mo	Cr	Ni	Cu	Ca	REM	Mg	Zr	Sb	W	
LA	0.10	0.26	0.61	0.011	0.0014	0.03	0.003	0.09	-	-	0.0014	0.88	0.97	-	-	-	-	-	-	-	-	Within the range of invention
LB	0.12	0.24	0.54	0.004	0.0012	0.04	0.002	-	0.12	-	-	0.63	1.11	-	-	-	-	-	-	-	-	Within the range of invention
LC	0.15	0.22	1.32	0.010	0.0020	0.02	0.003	0.07	0.06	-	-	0.58	1.22	-	-	-	-	-	-	-	-	Within the range of invention
LD	0.17	0.06	0.41	0.021	0.0017	0.03	0.002	0.09	0.02	-	0.0022	-	-	-	-	-	-	-	-	-	-	Within the range of invention
LE	0.20	0.83	0.53	0.022	0.0025	0.02	0.003	0.07	0.03	-	-	-	2.35	-	-	-	-	-	-	-	-	Within the range of invention
LF	0.07	0.24	1.38	0.006	0.0014	0.04	0.004	0.08	0.06	-	-	0.33	-	-	-	-	-	-	-	-	-	Within the range of invention
LG	0.18	0.39	2.36	0.011	0.0008	0.03	0.002	0.05	0.02	-	0.0023	-	0.74	-	-	0.002	-	-	-	-	-	Within the range of invention
LH	0.13	0.44	0.69	0.010	0.0009	0.04	0.004	-	0.05	-	0.0012	0.70	1.08	-	0.09	-	-	-	-	-	-	Within the range of invention
LI	0.11	0.34	0.81	0.009	0.0012	0.02	0.003	0.12	-	-	0.0011	1.05	0.91	0.05	-	-	0.002 (La)	-	-	-	-	Within the range of invention
LJ	0.17	0.98	2.12	0.014	0.0009	0.31	0.003	-	0.04	-	0.0008	0.58	0.54	-	-	-	-	0.002	-	-	-	Within the range of invention
LK	0.19	0.55	1.75	0.014	0.0032	0.02	0.004	-	-	0.04	0.0015	0.99	1.46	-	-	-	-	-	0.002	-	-	Within the range of invention
LL	0.03	0.21	0.81	0.020	0.0033	0.03	0.003	0.03	0.03	-	-	0.53	-	-	-	-	-	-	-	-	-	Out of the range of invention
LM	0.25	0.25	0.67	0.012	0.0011	0.03	0.003	-	0.06	-	-	0.65	1.04	-	-	-	-	-	-	-	-	Within the range of invention
LN	0.13	0.31	3.23	0.015	0.0015	0.03	0.003	0.04	-	-	0.0010	0.55	0.85	-	-	-	-	-	-	-	-	Out of the range of invention
LO	0.14	0.24	0.33	0.075	0.0024	0.04	0.002	-	0.06	-	-	1.28	0.92	-	-	-	-	-	-	-	-	Out of the range of invention
LP	0.15	0.27	0.95	0.010	0.0180	0.02	0.004	-	-	-	0.0014	0.32	-	-	-	-	-	-	-	-	-	Out of the range of invention
LQ	0.09	0.27	0.82	0.013	0.0020	0.04	0.002	0.05	-	-	0.0016	0.80	0.99	-	-	-	-	-	-	0.0009	-	Within the range of invention
LR	0.16	0.22	1.38	0.015	0.0029	0.06	0.003	0.01	0.02	-	-	-	0.65	-	-	-	-	-	-	-	0.03	Within the range of invention

[0076]

[Table 2]

Sample No.	Steel type	Product type	Heating temperature of steel (°C)	Finishing temperature (°C)	Working ratio from 950°C to finishing temperature (%)	Cooling rate (°C/sec)	Reheating temperature (°C)	Holding time (second)	TS (MPa)	Volume fraction of tempered martensite (%)	Average diameter of precipitate (nm)	Density of precipitate (particles/ μm^2)	Grain diameter of prior gamma in microstructure (μm)	C/10 ⁻¹¹	da/dN/10 ⁻⁶ (m/cycle)	Remark
L1	LA	Steel plate	1230	920	10	12	600	2700	749	100	10	164	11.9	6.1	0.71	Invention example
L2	LA	Steel plate	1050	920	10	12	600	2700	692	100	10	7	9.7	10.5	1.49	Comparative example
L3	LB	Steel plate	1150	910	15	30	580	3600	783	100	8	172	10.4	6.2	0.72	Invention example
L4	LB	Steel plate	1150	770	15	30	580	3600	792	86	8	169	2.4	17.1	1.72	Comparative example
L5	LC	Steel plate	1230	900	12	15	630	1800	816	100	12	134	10.3	6.5	0.73	Invention example
L6	LC	Steel plate	1230	900	12	0.1	630	1800	655	74	12	120	11.3	10.9	1.15	Comparative example
L7	LD	Steel plate	1250	850	8	20	650	2400	845	100	16	108	8.3	7.1	0.84	Invention example
L8	LD	Steel plate	1250	850	8	20	300	2400	1014	100	3	18	8.4	69.2	7.01	Comparative example
L9	LD	Steel plate	1250	850	8	20	780	2400	892	76	19	91	8.2	61.1	6.24	Comparative example
L10	LE	Steel plate	1280	910	10	12	700	1800	795	100	18	106	9.4	7.2	0.86	Invention example
L11	LE	Steel plate	1280	910	10	12	700	30	1021	100	7	31	9.4	39.4	3.50	Comparative example
L12	LF	Steel plate	1150	890	12	30	580	3000	720	97	8	161	8.6	7.4	0.84	Invention example
L13	LG	Steel plate	1220	920	19	100	720	600	793	99	19	127	6.3	7.5	0.86	Invention example
L14	LH	Steel plate	1200	940	17	50	600	2100	825	100	11	158	15.6	6.0	0.74	Invention example
L15	LI	Steel plate	1230	900	5	30	580	2400	813	100	9	165	10.3	6.5	0.72	Invention example
L16	LJ	Steel plate	1250	890	7	20	730	300	764	100	21	195	9.1	7.7	0.89	Invention example
L17	LK	Steel plate	1300	880	3	100	480	7200	887	100	5	81	13.3	7.8	0.84	Invention example
L18	LL	Steel plate	1200	900	10	15	620	1800	642	100	13	42	14.2	11.4	1.27	Comparative example
L19	LM	Steel plate	1150	900	15	20	620	2700	983	100	13	124	10.6	7.0	0.72	Invention example
L20	LN	Steel plate	1220	900	15	30	640	1800	788	92	15	106	7.6	21.1	2.34	Comparative example
L21	LO	Steel plate	1200	920	15	30	640	2400	806	100	16	122	11.6	36.5	3.78	Comparative example
L22	LP	Steel plate	1220	880	10	40	550	3600	824	100	6	149	16.4	31.2	3.87	Comparative example
L23	LQ	Steel plate	1200	880	15	20	550	3600	753	100	7	149	9.5	6.8	0.72	Invention example
L24	LR	Steel plate	1180	920	10	25	580	3000	830	100	9	110	9.4	7.4	0.83	Invention example

Note) "Density of precipitate" refers to the density of the particles of precipitate having a diameter of 100 nm or less which include one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen.

[0077]

[Table 3]

Sample No.	Steel type	Product type	Heating temperature of steel (°C)	Finishing temperature (°C)	Working ratio from 950°C to finishing temperature (%)	Cooling rate (°C/sec)	Reheating temperature (°C)	Holding time (second)	TS (MPa)	Volume fraction of tempered martensite (%)	Average diameter of precipitate (nm)	Density of precipitate (particles/μm ²)	Grain diameter of prior gamma in microstructure (μm)	C/10 ⁻¹¹	da/dN/10 ⁻⁶ (m/cycle)	Remark
L25	LA	Steel pipe	1230	920	11	15	600	2700	764	100	11	152	12.1	6.2	0.73	Invention example
L26	LA	Steel pipe	1050	920	11	15	600	2700	724	100	11	5	10.0	10.7	1.50	Comparative example
L27	LB	Steel pipe	1150	910	14	35	580	3600	794	100	9	157	10.7	6.3	0.74	Invention example
L28	LB	Steel pipe	1150	770	14	35	580	3600	824	89	9	160	2.4	17.0	1.70	Comparative example
L29	LC	Steel pipe	1230	900	10	20	630	1800	822	100	14	128	10.5	6.7	0.74	Invention example
L30	LC	Steel pipe	1230	900	10	0.2	630	1800	664	83	14	115	11.4	11.0	1.14	Comparative example
L31	LD	Steel pipe	1250	850	7	15	650	2400	842	100	18	101	7.8	7.2	0.83	Invention example
L32	LD	Steel pipe	1250	850	7	15	300	2400	1007	100	5	16	8.2	69.1	7.00	Comparative example
L33	LD	Steel pipe	1250	850	7	15	780	2400	871	74	20	84	8.5	61.3	6.26	Comparative example
L34	LE	Steel pipe	1280	910	9	10	700	1800	781	100	20	94	9.8	7.3	0.87	Invention example
L35	LE	Steel pipe	1280	910	9	10	700	30	1000	100	10	28	9.5	39.6	3.51	Comparative example
L36	LF	Steel pipe	1150	890	13	30	580	3000	742	98	7	179	8.8	7.5	0.86	Invention example
L37	LG	Steel pipe	1220	920	17	100	720	600	806	99	22	111	6.3	7.6	0.87	Invention example
L38	LH	Steel pipe	1200	940	18	50	600	2100	810	100	9	169	15.9	6.6	0.76	Invention example
L39	LI	Steel pipe	1230	900	4	30	580	2400	821	100	10	157	10.0	6.4	0.74	Invention example
L40	LJ	Steel pipe	1250	890	6	15	730	300	774	100	24	184	9.3	7.8	0.90	Invention example
L41	LK	Steel pipe	1300	880	2	100	480	7200	891	100	7	73	13.2	7.9	0.83	Invention example
L42	LL	Steel pipe	1200	900	10	15	620	1800	632	100	15	39	14.3	11.3	1.26	Comparative example
L43	LM	Steel pipe	1150	900	15	20	620	2700	954	100	14	120	13.0	6.6	0.73	Invention example
L44	LN	Steel pipe	1220	900	15	30	640	1800	781	93	15	107	7.4	21.3	2.35	Comparative example
L45	LO	Steel pipe	1200	920	15	30	640	2400	792	100	18	115	11.8	36.3	3.80	Comparative example
L46	LP	Steel pipe	1220	880	10	40	550	3600	801	100	8	142	16.8	31.3	3.88	Comparative example

Note) "Density of precipitate" refers to the density of the particles of precipitate having a diameter of 100 nm or less which include one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen.

[Table 4]

Sample No.	Steel type	Product type	Initial grain diameter of steel material (μm)	Heating temperature of steel material or container ($^{\circ}\text{C}$)	Holding time (heating time) (second)	Cooling rate ($^{\circ}\text{C}/\text{sec}$)	Cooling termination temperature ($^{\circ}\text{C}$)	Reheating temperature ($^{\circ}\text{C}$)	Holding time (during reheating) (second)	TS (MPa)	Volume fraction of tempered martensite (%)	Average diameter of precipitate (nm)	Density of precipitate (particles/ μm^2)	Grain diameter of prior gamma microstructure (μm)	C/10 ⁻¹¹	da/dN/10 ⁻⁶ (m/cycle)	Remark
L47	LA	Steel plate	6.2	900	300	30	50	580	2400	783	100	9	145	10.5	6.4	0.72	Invention example
L48	LA	Steel plate	2.1	900	300	30	50	580	2400	815	92	10	140	7.2	13.5	1.38	Comparative example
L49	LB	Steel pipe	7.3	940	1200	40	35	620	1800	752	100	8	159	10.8	6.6	0.75	Invention example
L50	LB	Steel pipe	7.3	750	1200	40	35	620	1800	803	88	10	164	4.3	19.5	2.23	Comparative example
L51	LC	Container	8.5	920	1800	100	75	570	3600	823	100	12	181	10.2	6.5	0.74	Invention example
L52	LC	Container	8.5	920	1800	0.2	75	570	3600	654	68	10	176	11.1	21.5	2.31	Comparative example
L53	LD	Steel plate	4.2	850	900	50	25	600	7200	864	100	14	173	7.4	7.4	0.82	Invention example
L54	LD	Steel plate	4.2	850	900	50	400	600	7200	821	75	25	43	7.6	32.6	3.41	Comparative example
L55	LE	Steel pipe	6.4	820	600	60	100	650	3600	824	100	18	131	7.8	7.5	0.87	Invention example
L56	LE	Steel pipe	6.4	820	600	60	100	300	3600	1034	25	9	202	7.9	35.7	3.74	Comparative example
L57	LE	Steel pipe	6.4	820	600	60	100	780	3600	893	54	36	68	7.8	24.3	2.63	Comparative example
L58	LF	Container	10.2	880	1500	80	30	500	3600	759	98	8	142	11.6	7.3	0.85	Invention example
L59	LF	Container	10.2	880	1500	80	30	500	5	923	98	3	25	11.6	26.5	2.89	Comparative example
L60	LG	Steel plate	9.3	860	2400	250	200	700	600	832	100	17	144	10.4	7.8	0.92	Invention example
L61	LH	Steel pipe	9.3	950	3600	30	25	590	2700	802	100	10	171	11.0	6.2	0.71	Invention example
L62	LI	Container	11.3	930	1800	80	25	620	1800	763	100	10	141	12.2	6.6	0.77	Invention example
L63	LJ	Steel plate	7.4	840	1800	150	300	720	600	782	100	19	181	8.3	7.8	0.92	Invention example
L64	LK	Steel pipe	3.7	980	1800	60	25	460	9000	883	100	6	85	7.3	8.0	0.86	Invention example
L65	LL	Container	5.9	900	1800	50	50	600	3600	631	100	12	38	10.2	11.6	1.35	Comparative example
L66	LM	Steel plate	5.1	880	1800	100	50	500	3600	963	100	10	149	8.3	6.8	0.71	Invention example
L67	LN	Steel pipe	9.6	900	1800	50	25	650	3600	825	93	15	103	10.9	21.8	2.74	Comparative example
L68	LO	Container	8.3	920	1800	30	50	600	3600	927	100	14	136	9.6	36.9	3.85	Comparative example
L69	LP	Steel plate	11.6	900	1800	50	25	550	3600	822	100	9	152	11.7	31.3	3.98	Comparative example

Note 1) "Initial grain diameter of steel material" refers to an average grain diameter observed in a microstructure obtained by saturated picric acid etching.

Note 2) "Density of precipitate" refers to the density of the particles of precipitate having a diameter of 100 nm or less which include one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen.

- 56 -

[EXAMPLE 2]

[0079]

Molten steels having the compositions shown in Table 5 (Tables 5-1 and 5-2) were each formed into a steel plate having a thickness of 25 mm under the specific conditions shown in Table 6 (Tables 6-1 and 6-2). The molten steels were also each formed into a steel pipe having a thickness of 25 mm under the specific conditions shown in Table 7. Note that the "Working ratio" in Table 6 (where the product type is "Steel plate") refers to rolling reduction ratio, while the "Working ratio" in Table 7 (where the product type is "Steel pipe") refers to pipe-expanding ratio. The "Cooling rate" refers to the average cooling rate from the finishing temperature to 350°C. Cooling was performed until the temperature reached 350°C or less. The "Reheating temperature" in Tables 6 and 7 refers to a temperature at which heating (reheating) was performed after cooling was performed at the cooling rate. The "Holding time" refers to a holding time during reheating.

[0080]

The steel materials having the compositions shown in Table 5 were each formed into a steel plate, a steel pipe, or a container having a plate thickness or a wall thickness of 25 mm under the specific conditions shown in Table 8. In the case where the product type was "Container", the steel

- 57 -

pipe having the specific composition shown in Table 5 was used as a steel material. The steel material was formed into a container, and the container was heated to the specific heating temperature shown in Table 8. The "Cooling rate" in Table 8 refers to the average cooling rate from the heating temperature to 350°C except for the samples in which the cooling termination temperature exceeded 350°C; in the samples in which the cooling termination temperature exceeded 350°C, the "Cooling rate" refers to the average cooling rate from the heating temperature to the cooling termination temperature. The "Reheating temperature" in Table 8 refers to a temperature at which heating (reheating) was performed after cooling was performed at the cooling rate. The "Initial grain diameter of steel material" in Table 8 refers to the average grain diameter determined from an image of the microstructure formed by performing saturated picric acid etching.

[0081]

The steel plates, steel pipes, and containers prepared under the respective conditions shown in Tables 6, 7, and 8 were examined in terms of steel microstructure and tensile property and subjected to a fatigue crack propagation test in hydrogen at 110 MPa. Tables 6, 7, and 8 summarize the results. In Table 8, the product type of each sample, that is, "Steel plate", "Steel pipe", or "Container", is

- 58 -

described. The same results were obtained regardless of the product type because the raw material was heated to 800°C or more, that is, an austenite-single phase region, subsequently cooled, and subjected to a heat treatment. Specifically, performing heating to an austenite single-phase region caused a steel microstructure to be transformed into austenite. Therefore, the thermal history of the raw material which was recorded subsequent to heating to the austenite single-phase region greatly affected the steel microstructure regardless of the history of the raw material which was recorded prior to heating to the austenite single-phase region. Thus, the same results were obtained regardless of the product type. Material tests and material property evaluations were conducted in the following manner as in Example 1.

[0082]

(1) Steel Microstructure

An electron scanning microscope (SEM) image of a cross section of the steel plate or steel pipe which was parallel to the rolling direction was captured at the 1/4-thickness position at an appropriate magnification of 1000 to 3000 times in order to observe tempered martensite, ferrite, bainite, and pearlite. The ferrite phase, the bainite phase, the pearlite phase, and cementite were visually distinguished in order to determine the microstructures. In

- 59 -

order to determine the fractions of the microstructures, the above-described SEM image was subjected to an image analysis to calculate the volume fraction of each phase. Portions other than the above-described phases were considered to be hard untempered martensite or austenite. In the case where the product type was "Container", the above-described examination was conducted in the direction of the steel material constituting the container.

In order to determine the size and number of the precipitate particles, a transmission electron microscope (TEM) sample at the 1/4-thickness position was prepared by a thin-film method, a precipitate formed at tempered martensite portions was observed by a transmission method at a magnification of 10000 to 300000 times, and the grain diameters of the precipitate particles and the density of the precipitate particles having a diameter of 100 nm or less were measured. The precipitate density was calculated over an area of 1 μm^2 or more. The diameters of the precipitate particles were measured by a method of section. Whether the precipitate included one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen was determined using an energy-dispersive X-ray spectroscopy system (EDX).

The grain diameter of prior austenite included in the product (i.e., grain diameter of prior-gamma included in the

- 60 -

microstructure) was determined by performing saturated picric acid etching.

[0083]

(2) Tensile Property

A tensile test conforming to JIS Z2241 was conducted using a No. 5 test piece described in JIS Z2201 (1980) in a longitudinal direction (tensile direction) that was the rolling direction of the steel plate or the steel pipe in order to make an evaluation. In the case where the product type was "Container", the above-described examination was conducted in the direction of the steel material constituting the container.

[0084]

(3) Fatigue Crack Propagation Test

A fatigue crack propagation test was conducted in accordance with ASTM E647 using compact tension specimens (CT specimens) in order to determine fatigue crack propagation rate. The test specimens were taken at a position of $t/2$ (t : plate thickness) of the steel material so as to have a thickness of 10 mm. Both surfaces of a crack propagation portion were subjected to mirror polishing. In the case where the product type was "Steel plate" or "Steel pipe", the examination was conducted using a test specimen taken so that the fatigue cracks propagated in a direction perpendicular to the rolling direction when a

- 61 -

tensile or compression load was applied in the rolling direction. In the case where the product type was "Container", the examination was conducted as in the cases of "Steel plate" and "Steel pipe" by applying a tensile or compression load in the rolling direction of the steel material constituting the container. The stress ratio was set to minus one. The fatigue crack propagation test was conducted as described above, and a fatigue crack propagation rate at $\Delta K = 25 \text{ MPa}\cdot\text{m}^{1/2}$ was determined. Furthermore, the C-value was determined on the basis of Paris' law $da/dN = \log(C(\Delta K)^m)$ (where C and m are constants primarily based on the material used) using data having a stress intensity factor range ΔK of 20 to 50 $\text{MPa}\cdot\text{m}^{1/2}$, which is a stable growth region in which Paris' law holds.

[0085]

As summarized in Tables 6, 7, and 8, in the invention examples, $700 \text{ MPa} \leq \text{TS} < 900 \text{ MPa}$ was satisfied when $0.05\% \leq \text{the C content} < 0.21\%$, and $\text{TS} \geq 900 \text{ MPa}$ was satisfied when $0.21\% \leq \text{the C content} \leq 0.60\%$. In the invention examples, the C-value determined in the fatigue crack propagation test achieved $C \leq 8.0 \times 10^{-11}$, and a fatigue crack propagation rate at $\Delta K = 25 \text{ MPa}\cdot\text{m}^{1/2}$ achieved $1.0 \times 10^{-6} \text{ m/cycle}$ or less.

[0086]

[Table 5-1]

Steel type	Chemical composition (mass%)																					Remark
	C	Si	Mn	P	S	Al	N	Ti	Nb	V	B	Mo	Cr	Ni	Cu	Ca	REM	Mg	Zr	Sb	W	
HA	0.23	0.20	0.55	0.003	0.0018	0.04	0.002	0.03	-	-	0.0011	0.92	0.95	-	-	-	-	-	-	-	-	Within the range of invention
HB	0.25	0.25	0.67	0.012	0.0011	0.03	0.003	-	0.06	-	-	0.65	1.04	-	-	-	-	-	-	-	-	Within the range of invention
HC	0.28	0.27	1.21	0.010	0.0024	0.02	0.002	0.05	0.03	-	-	0.54	1.24	-	-	-	-	-	-	-	-	Within the range of invention
HD	0.35	0.05	0.45	0.024	0.0011	0.04	0.003	0.10	0.01	-	0.0025	-	-	-	-	-	-	-	-	-	-	Within the range of invention
HE	0.45	0.73	0.56	0.009	0.0032	0.02	0.004	0.07	0.02	-	-	-	2.31	-	-	-	-	-	-	-	-	Within the range of invention
HF	0.52	0.22	1.42	0.010	0.0009	0.03	0.004	0.05	0.05	-	-	0.31	-	-	-	-	-	-	-	-	-	Within the range of invention
HG	0.58	0.24	0.35	0.006	0.0008	0.04	0.002	0.02	0.12	0.02	0.0021	1.24	-	0.05	-	-	-	-	-	-	-	Within the range of invention
HH	0.26	0.37	2.42	0.022	0.0018	0.02	0.003	0.03	0.04	-	0.0014	-	0.69	-	-	0.002	-	-	-	-	-	Within the range of invention
HI	0.27	0.42	0.74	0.011	0.0025	0.04	0.003	-	0.04	-	0.0012	0.72	1.02	-	0.11	-	-	-	-	-	-	Within the range of invention
HJ	0.36	0.36	0.83	0.012	0.0015	0.03	0.004	0.05	-	-	0.0009	1.09	0.84	-	-	-	0.001 (Y)	-	-	-	-	Within the range of invention
HK	0.42	1.05	2.05	0.009	0.0009	0.54	0.003	-	0.03	-	-	0.55	0.57	-	-	-	-	0.002	-	-	-	Within the range of invention
HL	0.31	0.21	1.71	0.014	0.0020	0.02	0.002	-	-	0.03	0.0013	0.92	1.42	-	-	-	-	-	0.001	-	-	Within the range of invention
HM	0.18	0.22	0.84	0.015	0.0034	0.03	0.003	0.03	0.02	-	-	0.51	-	-	-	-	-	-	-	-	-	Within the range of invention
<u>HN</u>	0.26	0.34	<u>3.14</u>	0.021	0.0022	0.04	0.002	0.05	-	-	0.0011	0.57	0.82	-	-	-	-	-	-	-	-	Out of the range of invention
<u>HO</u>	0.27	0.23	0.34	<u>0.080</u>	0.0015	0.03	0.003	-	0.06	-	-	1.24	0.97	-	-	-	-	-	-	-	-	Out of the range of invention
<u>HP</u>	0.31	0.28	0.95	0.011	<u>0.0150</u>	0.04	0.004	-	-	-	0.0015	0.37	-	-	-	-	-	-	-	-	-	Out of the range of invention
HQ	0.27	0.24	1.40	0.009	0.0015	0.03	0.003	0.05	0.02	-	0.0015	0.32	-	0.04	-	0.003	-	-	-	-	-	Within the range of invention
HR	0.32	0.19	0.99	0.008	0.0021	0.04	0.003	0.03	0.06	0.02	0.0010	0.64	0.19	-	0.05	-	-	0.001	-	-	-	Within the range of invention
HS	0.24	0.39	1.02	0.006	0.0012	0.03	0.004	0.02	0.03	-	0.0013	-	0.32	-	-	-	0.001 (La)	-	0.001	-	-	Within the range of invention

[0087]

[Table 5-2]

Steel type	Chemical composition (mass%)																				Remark	
	C	Si	Mn	P	S	Al	N	Ti	Nb	V	B	Mo	Cr	Ni	Cu	Ca	REM	Mg	Zr	Sb		W
HT	0.34	0.21	1.16	0.012	0.0020	0.31	0.004	0.03	-	-	0.0021	0.35	0.48	0.03	0.02	0.001	-	0.003	-	-	-	Within the range of invention
HU	0.28	0.32	1.23	0.009	0.0016	0.05	0.003	-	0.03	-	-	0.55	-	-	-	-	-	-	-	0.0005	-	Within the range of invention
HV	0.31	0.24	1.36	0.015	0.0024	0.04	0.002	0.02	-	0.03	-	-	0.67	-	-	-	-	-	-	-	0.02	Within the range of invention
HW	0.34	0.16	1.39	0.014	0.0025	0.03	0.004	0.06	0.04	-	0.0019	0.42	-	-	-	-	0.005 (Nd)	-	-	-	-	Within the range of invention
HX	0.28	0.08	1.49	0.013	0.0012	0.03	0.003	-	0.06	-	0.0008	-	1.64	0.02	-	-	-	-	-	0.0008	-	Within the range of invention
HY	0.26	0.13	1.01	0.012	0.0007	0.02	0.004	0.02	0.05	-	-	0.31	0.57	-	-	0.001	-	-	-	0.0010	-	Within the range of invention
HZ	0.23	0.42	1.46	0.014	0.0013	0.04	0.003	0.08	-	-	0.0029	-	0.08	-	-	-	-	0.003	-	0.0006	-	Within the range of invention
HAA	0.32	0.20	0.77	0.010	0.0015	0.06	0.004	0.03	0.02	-	0.0043	0.39	1.54	-	0.04	-	-	-	-	-	0.03	Within the range of invention
HAB	0.40	1.24	1.85	0.020	0.0016	0.04	0.002	0.07	0.03	-	0.0006	0.05	0.34	-	-	-	0.002 (Y) 0.004 (Nd)	-	-	-	-	Within the range of invention
HAC	0.33	0.44	1.46	0.014	0.0020	0.02	0.002	-	0.04	-	0.0022	0.31	-	0.01	-	-	-	-	0.002	0.0019	-	Within the range of invention
HAD	0.35	0.37	0.52	0.013	0.0019	0.15	0.003	0.01	0.04	-	-	0.42	0.71	-	-	0.002	-	0.003	-	0.0013	-	Within the range of invention
HAE	0.31	0.29	1.37	0.015	0.0013	0.04	0.004	0.15	-	-	0.0037	-	-	-	0.10	-	-	-	0.001	0.0024	-	Within the range of invention
HAF	0.29	0.14	1.16	0.011	0.0025	0.02	0.003	0.03	0.03	-	0.0011	0.33	0.12	0.03	-	-	-	0.003	-	-	0.01	Within the range of invention
HAG	0.34	0.14	0.94	0.011	0.0030	0.03	0.004	-	0.08	-	0.0009	-	1.52	-	-	0.003	0.006 (Nd)	0.003	0.002	-	-	Within the range of invention
HAH	0.26	0.32	1.41	0.013	0.0009	0.03	0.002	0.05	-	-	0.0017	-	0.40	0.03	-	-	0.002 (Nd)	0.003	-	-	0.02	Within the range of invention
HAI	0.47	0.32	1.93	0.022	0.0012	0.04	0.002	-	0.15	-	-	0.16	0.37	-	0.05	-	0.002 (Ce)	0.003	-	0.0009	-	Within the range of invention
HAJ	0.29	0.25	1.37	0.013	0.0016	0.02	0.002	-	0.03	-	-	-	0.52	0.04	0.02	0.001	-	-	0.002	-	0.09	Within the range of invention
HAK	0.31	0.48	0.55	0.008	0.0022	0.05	0.004	0.03	0.06	-	0.0020	0.61	0.29	0.05	0.03	0.008	0.004 (Nd)	0.003	-	0.0016	-	Within the range of invention

[0088]

[Table 6-1]

Sample No.	Steel type	Product type	Heating temperature of steel (°C)	Finishing temperature (°C)	Working ratio from 950°C to finishing temperature (%)	Cooling rate (°C/sec)	Reheating temperature (°C)	Holding time (second)	TS (MPa)	Volume fraction of tempered martensite (%)	Average diameter of precipitate (nm)	Density of precipitate (particles/μm ²)	Grain diameter of prior gamma in microstructure (μm)	C/10 ⁻¹¹	da/dN/10 ⁻⁶ (m/cycle)	Remark
H1	HA	Steel plate	1200	910	12	15	580	3600	954	100	8	150	10.9	6.6	0.69	Invention example
H2	HA	Steel plate	1050	910	12	15	580	3600	910	100	8	10	8.3	13.9	1.43	Comparative example
H3	HB	Steel plate	1150	900	15	20	620	2700	983	100	13	124	10.6	7.0	0.72	Invention example
H4	HB	Steel plate	1150	750	15	20	620	2700	992	92	13	117	2.3	24.2	2.50	Comparative example
H5	HC	Steel plate	1250	880	10	10	650	1800	961	100	17	113	10.3	7.1	0.74	Invention example
H6	HC	Steel plate	1250	880	10	0.1	650	1800	721	71	16	108	11.0	9.0	1.05	Comparative example
H7	HD	Steel plate	1230	850	5	15	600	2100	996	100	12	115	9.6	7.6	0.79	Invention example
H8	HD	Steel plate	1230	850	5	15	350	2100	1152	100	4	12	9.4	71.9	7.38	Comparative example
H9	HD	Steel plate	1230	850	5	15	800	2100	1054	52	20	82	9.2	63.3	6.37	Comparative example
H10	HE	Steel plate	1280	900	8	10	700	1800	1004	100	16	128	7.2	7.9	0.81	Invention example
H11	HE	Steel plate	1280	900	8	10	700	30	1157	100	5	20	7.5	42.2	4.33	Comparative example
H12	HF	Steel plate	1200	870	12	12	680	2400	1035	99	16	121	6.3	7.8	0.83	Invention example
H13	HG	Steel plate	1300	880	17	30	700	600	1051	98	18	132	5.2	7.9	0.84	Invention example
H14	HH	Steel plate	1200	900	10	50	630	1800	994	99	14	128	10.4	6.9	0.74	Invention example
H15	HI	Steel plate	1180	920	3	100	580	1800	1011	100	10	143	10.2	7.3	0.76	Invention example
H16	HJ	Steel plate	1230	890	5	70	600	2400	972	100	12	131	7.6	7.7	0.84	Invention example
H17	HK	Steel plate	1250	920	7	50	730	300	993	100	22	103	6.0	7.6	0.82	Invention example
H18	HL	Steel plate	1250	900	15	100	500	5400	983	100	6	64	12.6	7.7	0.83	Invention example
H19	HM	Steel plate	1200	870	10	30	640	1800	841	100	14	115	13.7	5.0	0.64	Invention example
H20	HN	Steel plate	1220	900	10	50	620	1800	928	90	13	119	7.2	22.8	2.43	Comparative example
H21	HO	Steel plate	1200	900	15	30	620	2400	954	100	12	123	10.3	38.3	3.97	Comparative example
H22	HP	Steel plate	1220	880	10	10	550	2400	943	100	8	142	12.4	33.2	3.56	Comparative example

Note) "Density of precipitate" refers to the density of the particles of precipitate having a diameter of 100 nm or less which include one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen.

[Table 6-2]

Sample No.	Steel type	Product type	Heating temperature of steel (°C)	Finishing temperature (°C)	Working ratio from 950°C to finishing temperature (%)	Cooling rate (°C/sec)	Reheating temperature (°C)	Holding time (second)	TS (MPa)	Volume fraction of tempered martensite (%)	Average diameter of precipitate (nm)	Density of precipitate (particles/ μm^2)	Grain diameter of prior gamma in microstructure (μm)	C/10 ⁻¹¹	da/dN/10 ⁻⁶ (m/cycle)	Remark
H23	HQ	Steel plate	1180	910	12	30	550	1800	960	97	8	143	11.4	6.7	0.70	Invention example
H24	HR	Steel plate	1160	920	15	50	590	2400	1008	100	10	149	10.5	6.9	0.72	Invention example
H25	HS	Steel plate	1150	900	15	70	550	2400	994	100	8	137	10.1	7.1	0.73	Invention example
H26	HT	Steel plate	1200	880	10	30	600	3600	1006	98	12	109	9.2	7.1	0.72	Invention example
H27	HU	Steel plate	1210	900	12	15	550	3600	1015	100	7	137	10.3	7.2	0.70	Invention example
H28	HV	Steel plate	1190	880	12	30	590	7200	972	100	9	116	9.4	7.2	0.70	Invention example
H29	HW	Steel plate	1210	900	15	40	590	2400	955	100	8	121	9.9	7.3	0.72	Invention example
H30	HX	Steel plate	1230	920	10	50	560	3000	942	100	7	134	11.3	7.0	0.71	Invention example
H31	HY	Steel plate	1250	930	15	40	560	1800	980	100	9	139	12.6	6.9	0.71	Invention example
H32	HZ	Steel plate	1180	900	10	60	520	2400	960	100	6	82	11.7	7.7	0.79	Invention example
H33	HAA	Steel plate	1180	920	7	50	590	3600	937	97	10	113	11.1	7.5	0.77	Invention example
H34	HAB	Steel plate	1250	910	15	40	620	3600	941	100	15	148	12.6	6.7	0.68	Invention example
H35	HAC	Steel plate	1220	900	12	30	600	2100	925	100	12	102	10.6	7.7	0.78	Invention example
H36	HAD	Steel plate	1200	930	12	30	600	1800	976	100	10	106	12.7	7.6	0.78	Invention example
H37	HAE	Steel plate	1230	910	7	30	570	2400	1003	100	10	129	11.4	7.0	0.72	Invention example
H38	HAF	Steel plate	1200	890	7	50	550	3600	1025	97	8	128	9.7	7.1	0.72	Invention example
H39	HAG	Steel plate	1250	880	5	30	590	2400	1034	95	11	131	8.6	7.0	0.73	Invention example
H40	HAH	Steel plate	1200	900	15	20	550	1800	1058	100	7	110	9.7	7.5	0.79	Invention example
H41	HAI	Steel plate	1180	900	12	50	670	2400	926	100	20	99	12.7	7.7	0.83	Invention example
H42	HAJ	Steel plate	1190	880	12	50	560	2400	964	100	10	101	9.0	7.6	0.83	Invention example
H43	HAK	Steel plate	1150	870	15	40	570	3600	972	100	10	137	8.3	7.1	0.72	Invention example

Note) "Density of precipitate" refers to the density of the particles of precipitate having a diameter of 100 nm or less which include one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen.

[0090]

[Table 7]

Sample No.	Steel type	Product type	Heating temperature of steel (°C)	Finishing temperature (°C)	Working ratio from 950°C to finishing temperature (%)	Cooling rate (°C/sec)	Reheating temperature (°C)	Holding time (second)	TS (MPa)	Volume fraction of tempered martensite (%)	Average diameter of precipitate (nm)	Density of precipitate (particles/μm ²)	Grain diameter of prior gamma in microstructure (μm)	C/10 ⁻¹¹	da/dN/10 ⁻⁶ (m/cycle)	Remark
H44	HA	Steel pipe	1210	900	11	12	570	3600	956	100	8	153	11.0	6.4	0.68	Invention example
H45	HA	Steel pipe	1050	900	11	12	570	3600	915	100	8	14	8.5	13.8	1.41	Comparative example
H46	HB	Steel pipe	1170	890	14	18	600	2400	987	100	12	126	10.8	6.9	0.72	Invention example
H47	HB	Steel pipe	1170	740	14	18	600	2400	998	90	12	121	2.4	23.9	2.49	Comparative example
H48	HC	Steel pipe	1230	870	10	8	630	2000	964	100	17	119	10.6	7.2	0.72	Invention example
H49	HC	Steel pipe	1230	870	10	0.2	630	2000	725	75	15	113	10.8	10	1.04	Comparative example
H50	HD	Steel pipe	1220	840	6	15	600	2200	1001	100	12	118	9.3	7.7	0.79	Invention example
H51	HD	Steel pipe	1220	840	6	15	340	2200	1158	100	10	12	9.2	71.7	7.38	Comparative example
H52	HD	Steel pipe	1220	840	6	15	780	2200	1062	47	17	88	9.1	63.2	6.34	Comparative example
H53	HE	Steel pipe	1280	890	8	10	700	1800	1008	100	15	134	7.5	7.6	0.82	Invention example
H54	HE	Steel pipe	1280	890	8	10	700	30	1155	100	5	20	7.7	42.2	4.32	Comparative example
H55	HF	Steel pipe	1200	870	10	12	680	2400	1039	98	14	119	6.5	7.8	0.81	Invention example
H56	HG	Steel pipe	1300	880	18	25	680	900	1057	99	15	136	5.1	7.9	0.84	Invention example
H57	HH	Steel pipe	1220	910	12	40	630	1500	989	97	12	124	10.4	7.4	0.78	Invention example
H58	HI	Steel pipe	1170	920	3	100	580	1800	1013	100	10	145	10.3	7.2	0.74	Invention example
H59	HJ	Steel pipe	1230	880	5	75	600	2400	972	100	14	133	7.8	7.7	0.83	Invention example
H60	HK	Steel pipe	1250	920	7	50	730	600	998	100	25	106	6.1	7.9	0.86	Invention example
H61	HL	Steel pipe	1230	900	14	100	500	5400	986	100	8	65	12.6	7.8	0.83	Invention example
H62	HM	Steel pipe	1190	880	10	30	640	1800	835	100	14	111	14	5.2	0.66	Invention example
H63	HN	Steel pipe	1220	920	12	60	620	1800	932	87	12	122	7.0	22.8	2.44	Comparative example
H64	HO	Steel pipe	1180	910	15	20	620	2400	957	100	10	127	10.4	38.7	3.95	Comparative example
H65	HP	Steel pipe	1220	880	8	15	550	2400	945	100	8	145	12.6	33.3	3.55	Comparative example

Note) "Density of precipitate" refers to the density of the particles of precipitate having a diameter of 100 nm or less which include one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen.

[0091]

[Table 8]

Sample No.	Steel type	Product type	Initial grain diameter of steel material (μm)	Heating temperature of steel material or container ($^{\circ}\text{C}$)	Holding time (heating time) (second)	Cooling rate ($^{\circ}\text{C}/\text{sec}$)	Cooling termination temperature ($^{\circ}\text{C}$)	Reheating temperature ($^{\circ}\text{C}$)	Holding time (during reheating) (second)	TS (MPa)	Volume fraction of tempered martensite (%)	Average diameter of precipitate (nm)	Density of precipitate (particles/ μm^2)	Grain diameter of prior gamma in microstructure (μm)	C/10 ⁻¹¹	da/dN/10 ⁻⁶ (m/cycle)	Remark
H66	HA	Steel plate	6	900	60	12	40	570	3600	956	100	9	149	11.4	6.4	0.68	Invention example
H67	HA	Steel plate	2.3	900	600	12	40	570	3600	915	100	9	11	8.7	13.8	1.41	Comparative example
H68	HB	Steel pipe	7.5	890	1800	18	30	600	2400	987	100	13	121	11.8	6.9	0.72	Invention example
H69	HB	Steel pipe	7.5	740	1800	18	30	600	2400	998	90	13	114	2.4	23.9	2.49	Comparative example
H70	HC	Container	8.2	870	1200	8	80	630	2000	964	100	15	115	11.4	7.2	0.72	Invention example
H71	HC	Container	8.2	870	1200	0.2	80	630	2000	725	75	16	107	11.8	10	1.04	Comparative example
H72	HD	Steel plate	4.8	840	3600	15	30	600	2200	1001	100	13	117	10.6	7.7	0.79	Invention example
H73	HD	Steel plate	4.8	840	3600	15	30	340	2200	1158	100	9	9	9.8	71.7	7.38	Comparative example
H74	HE	Steel pipe	6.5	890	2400	10	100	780	1800	1062	47	15	88	10.1	63.2	6.34	Comparative example
H75	HE	Steel pipe	6.5	890	2400	10	100	700	1800	1008	100	14	124	8.6	7.6	0.82	Invention example
H76	HE	Steel pipe	6.5	890	2400	10	100	700	30	1155	100	7	12	8.6	42.2	4.32	Comparative example
H77	HF	Container	10.7	870	300	12	25	680	2400	1039	98	13	115	7.2	7.9	0.81	Invention example
H78	HF	Container	10.7	870	300	12	420	680	2400	863	64	23	34	6.2	8.8	0.97	Comparative example
H79	HG	Steel plate	9.1	910	900	40	180	630	1500	989	97	13	128	10.8	7.6	0.78	Invention example
H80	HH	Steel pipe	9.1	920	1800	100	20	580	1800	1013	100	11	139	9.6	7.3	0.74	Invention example
H81	HI	Container	11.1	880	1500	75	25	600	2400	972	100	15	136	9.1	6.8	0.72	Invention example
H82	HJ	Steel plate	7.8	920	1800	50	250	730	600	998	100	25	111	7.2	7.6	0.82	Invention example
H83	HK	Steel pipe	4.3	900	600	100	25	500	5400	986	100	10	59	13.5	7.8	0.85	Invention example
H84	HL	Container	6.2	880	3600	30	40	640	1800	965	100	13	108	14.5	5.2	0.66	Invention example
H85	HM	Steel plate	5.7	920	1800	60	50	620	1800	835	97	10	117	7.8	5.3	0.71	Invention example
H86	HN	Steel pipe	9.2	910	1800	20	30	620	2400	957	100	9	125	10.7	38.7	3.95	Comparative example
H87	HO	Container	8.4	880	1800	15	50	550	2400	945	100	9	146	13.3	33.3	3.55	Comparative example
H88	HP	Steel pipe	10.9	880	1800	15	25	550	2400	945	100	8	140	13.0	33.3	3.55	Comparative example

Note 1) "Initial grain diameter of steel material" refers to an average grain diameter observed in a microstructure obtained by saturated picric acid etching.

Note 2) "Density of precipitate" refers to the density of the particles of precipitate having a diameter of 100 nm or less which include one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen.

- 68 -

CLAIMS

[Claim 1]

A steel material comprising: a composition containing, by mass, C: 0.05% to 0.60%, Si: 0.01% to 2.0%, Mn: 0.3% to 3.0%, P: 0.001% to 0.040%, S: 0.0001% to 0.010%, N: 0.0001% to 0.0060%, Al: 0.01% to 1.5%, one or more elements selected from Ti: 0.01% to 0.20%, Nb: 0.01% to 0.20%, and V: 0.01% or more and less than 0.05%, and one or more elements selected from B: 0.0001% to 0.01%, Mo: 0.005% to 2.0%, and Cr: 0.005% to 3.0%, with the balance being Fe and inevitable impurities;

and a steel microstructure

that includes 95% or more of tempered martensite on a volume fraction basis,

that includes a precipitate having a diameter of 100 nm or less and including one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen at a density of 50 particles/ μm^2 or more,

and that includes prior austenite having a grain diameter of 3 μm or more.

[Claim 2]

The steel material according to Claim 1, the steel material comprising, by mass, C: 0.05% or more and less than 0.21%.

[Claim 3]

- 69 -

The steel material according to Claim 1, the steel material comprising, by mass, C: 0.21% to 0.60%.

[Claim 4]

The steel material according to any one of Claims 1 to 3, the steel material further comprising, by mass, one or more elements selected from Ni: 0.005% to 0.70% and Cu: 0.005% to 2.00%.

[Claim 5]

The steel material according to any one of Claims 1 to 4, the steel material further comprising, by mass, one or more elements selected from Ca: 0.001% to 0.01% and REM: 0.001% to 0.01%.

[Claim 6]

The steel material according to any one of Claims 1 to 5, the steel material further comprising, by mass, one or more elements selected from Mg: 0.001% to 0.01% and Zr: 0.001% to 0.01%.

[Claim 7]

The steel material according to any one of Claims 1 to 6, the steel material further comprising, by mass, Sb: 0.0001% to 0.1%.

[Claim 8]

The steel material according to any one of Claims 1 to 7, the steel material further comprising, by mass, W: 0.001% to 1%.

- 70 -

[Claim 9]

The steel material according to any one of Claims 1 to 8, the steel material being a steel pipe.

[Claim 10]

A hydrogen container comprising: the composition according to any one of Claims 1 to 8;

and a steel microstructure

that includes 95% or more of tempered martensite on a volume fraction basis,

that includes a precipitate having a diameter of 100 nm or less and including one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen at a density of 50 particles/ μm^2 or more,

and that includes prior austenite having a grain diameter of 3 μm or more.

[Claim 11]

A method for producing a steel material having a steel microstructure

that includes 95% or more of tempered martensite on a volume fraction basis,

that includes a precipitate having a diameter of 100 nm or less and including one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen at a density of 50 particles/ μm^2 or more,

and that includes prior austenite having a grain

- 71 -

diameter of 3 μm or more,

the method comprising: heating a steel having the composition according to any one of Claims 1 to 8 to 1100°C or more; performing working in such a manner that a working ratio from 950°C to a finishing temperature is 20% or less, the finishing temperature being 800°C or more; performing cooling to 350°C or less at a cooling rate of 1°C/sec. or more; performing heating to 400°C or more and 750°C or less, followed by holding for 60 seconds or more; and performing cooling.

[Claim 12]

A method for producing a steel pipe having a steel microstructure

that includes 95% or more of tempered martensite on a volume fraction basis,

that includes a precipitate having a diameter of 100 nm or less and including one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen at a density of 50 particles/ μm^2 or more,

and that includes prior austenite having a grain diameter of 3 μm or more,

the method comprising: heating a steel having the composition according to any one of Claims 1 to 8 to 1100°C or more; performing working in such a manner that a pipe-expanding ratio from 950°C to a finishing temperature is 20%

- 72 -

or less, the finishing temperature being 800°C or more; performing cooling to 350°C or less at a cooling rate of 1°C/sec. or more; performing heating to 400°C or more and 750°C or less, followed by holding for 60 seconds or more; and performing cooling.

[Claim 13]

A method for producing a steel material having a steel microstructure

that includes 95% or more of tempered martensite on a volume fraction basis,

that includes a precipitate having a diameter of 100 nm or less and including one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen at a density of 50 particles/ μm^2 or more,

and that includes prior austenite having a grain diameter of 3 μm or more,

the method comprising: heating a steel material having the composition according to any one of Claims 1 to 8 to 800°C or more, the steel material having a microstructure having an average particle diameter of 3 μm or more, the microstructure being formed by performing saturated picric acid etching, followed by holding for 60 seconds or more; performing cooling to 350°C or less at a cooling rate of 1°C/sec. or more; performing heating to 400°C or more and 750°C or less, followed by holding for 60 seconds or more;

- 73 -

and performing cooling.

[Claim 14]

A method for producing a hydrogen container having a steel microstructure

that includes 95% or more of tempered martensite on a volume fraction basis,

that includes a precipitate having a diameter of 100 nm or less and including one or more elements selected from Ti, Nb, and V and one or more elements selected from carbon and nitrogen at a density of 50 particles/ μm^2 or more,

and that includes prior austenite having a grain diameter of 3 μm or more,

the method comprising: forming a steel material having the composition according to any one of Claims 1 to 8 into a container having a desired shape, the steel material having a microstructure having an average particle diameter of 3 μm or more, the microstructure being formed by performing saturated picric acid etching; performing heating to 800°C or more, followed by holding for 60 seconds or more; performing cooling to 350°C or less at a cooling rate of 1°C/sec. or more; performing heating to 400°C or more and 750°C or less, followed by holding for 60 seconds or more; and performing cooling.