



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 530 802 B1

(12)

EUROPEAN PATENT SPECIFICATION

- (49) Date of publication of patent specification: **29.11.95** (51) Int. Cl.⁶: **B41M 5/38**, G03F 3/10
(21) Application number: **92115076.9**
(22) Date of filing: **03.09.92**

(54) **Mixture of dyes for black dye donor for thermal color proofing.**

(30) Priority: **06.09.91 US 755726**

(43) Date of publication of application:
10.03.93 Bulletin 93/10

(45) Publication of the grant of the patent:
29.11.95 Bulletin 95/48

(84) Designated Contracting States:
DE FR GB

(56) References cited:
US-A- 5 024 990
US-A- 5 041 411

PATENT ABSTRACTS OF JAPAN vol. 13, no.
385 (M-864)(3733) 25 August 1989 & JP-A-11
36 787.

(73) Proprietor: **EASTMAN KODAK COMPANY**
343 State Street
Rochester,
New York 14650-2201 (US)

(72) Inventor: **Evans, Steven, c/o Eastman Kodak**
Company
Patent Legal Staff,
343 State Street
Rochester,
New York 14650-2201 (US)
Inventor: **Chapman, Derek David, c/o Eastman**
Kodak Company
Patent Legal Staff,
343 State Street
Rochester,
New York 14650-2201 (US)

(74) Representative: **Brandes, Jürgen, Dr.**
Wuesthoff & Wuesthoff
Patent- und Rechtsanwälte
Schweigerstrasse 2
D-81541 München (DE)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

EP 0 530 802 B1

Description

This invention relates to use of a mixture of cyan, yellow and magenta dyes in a black dye-donor element for thermal dye transfer imaging which can be used in a four-color proofing system that accurately represents the hue of a printed color image obtained from a printing press.

In order to approximate the appearance of continuous-tone (photographic) images via ink-on-paper printing, the commercial printing industry relies on a process known as halftone printing. In halftone printing, color density gradations are produced by printing ink as patterns of "dots" of varying sizes, but of constant color density, instead of varying the color density continuously as is done in photographic printing.

There is an important commercial need to obtain a color proof image before a printing press run is made which will emulate the final printed image as closely as possible. Such a pre-press proof will be used as a guide to the press operator during the set-up and calibration of the printing press. It is desired that the color proof will accurately represent at least the neutral (gray) and color tone scales of the prints obtained on the printing press. In many cases, it is also desirable that the color proof accurately represent the image quality and halftone pattern of the prints obtained on the printing press. Traditionally, such color separation proofs have involved silver halide photographic, high-contrast lithographic systems or non-silver halide (for example the Signature® electrophotographic analog proofing system available from Eastman Kodak) light-sensitive systems which require many exposure and processing steps before a final, full-color proof is assembled.

Colorants that are used in the printing industry are insoluble pigments dispersed in a suitable carrier liquid to make an ink. In particular, carbon is often used in such a black ink and results in fairly uniform absorbance across the visible spectrum. In thermal transfer color printing systems that use diffusible dyes it is often difficult to find a blend of two or more dyes which yields both uniform neutral (black) color and fulfills the other requirements of the printing system such as transfer efficiency and donor storage stability.

In EP-A-0 454 083 (prior art according to Article 54(3) EPC), a process is described for producing a direct digital, halftone color proof of an original image on a dye-receiving element by means of laser thermal dye transfer. The proof can then be used to represent a printed color image obtained from a printing press. The process described therein comprises:

- a) generating a set of electrical signals which is representative of the shape and color scale of an original image;
- b) contacting a dye-donor element comprising a support having thereon a dye layer and an infrared-absorbing material with a first dye-receiving element comprising a support having thereon a polymeric, dye image-receiving layer;
- c) using the signals to imagewise-heat by means of a diode laser the dye-donor element, thereby transferring a dye image to the first dye-receiving element; and
- d) retransferring the dye image to a second dye image-receiving element which has the same substrate as the printed color image.

In the above process, multiple dye-donors are used to obtain a complete range of colors in the proof. For example, for a full-color proof, four colors: cyan, magenta, yellow and black are normally used.

By using the above process, the image dye is transferred by heating the dye-donor containing the infrared-absorbing material with the diode laser to volatilize the dye, the diode laser beam being modulated by the set of signals which is representative of the shape and color of the original image, so that the dye is heated to cause volatilization only in those areas in which its presence is required on the dye-receiving layer to reconstruct the original image.

Similarly, a thermal transfer proof can be generated by using a thermal head in place of a diode laser as described in U.S. Patent 4,923,846. Commonly available thermal heads are not capable of generating halftone images of adequate resolution but can produce high quality continuous tone proof images which are satisfactory in many instances. U.S. Patent 4,923,846 also discloses the choice of mixtures of dyes for use in thermal imaging proofing systems. The dyes are selected on the basis of values for hue error and turbidity. The Graphic Arts Technical Foundation Research Report No. 38, "Color Material" (58-5) 293-301, 1985 gives an account of this method.

An alternative and more precise method for color measurement and analysis uses the concept of uniform color space known as CIELAB in which a sample is analyzed mathematically in terms of its spectrophotometric curve, the nature of the illuminant under which it is viewed and the color vision of a standard observer. For a discussion of CIELAB and color measurement, see "Principles of Color Technology", 2nd Edition, p.25-110, Wiley-Interscience and "Optical Radiation Measurements", Volume 2, p.33-145, Academic Press.

In using CIELAB, colors can be expressed in terms of three parameters: L^* , a^* and b^* , where L^* is a lightness function, and a^* and b^* define a point in color space. Thus, a plot of a^* v. b^* values for a color sample can be used to accurately show where that sample lies in color space, i.e., what its hue is. This allows different samples to be quantitatively compared.


5 In color proofing in the printing industry, it is important to be able to match the proofing ink references provided by the International Prepress Proofing Association. These ink references are density patches made with standard 4-color process inks and are known as SWOP (Specifications Web Offset Publications) Color References. For additional information on color measurement of inks for web offset proofing, see "Advances in Printing Science and Technology", Proceedings of the 19th International Conference of Printing Research
10 Institutes, Eisenstadt, Austria, June 1987, J. T. Ling and R. Warner, p.55.

Thus, this invention relates to the use of a mixture of cyan, yellow and magenta dyes for thermal dye transfer imaging to approximate a hue match of the black SWOP Color Reference. The mixtures of dyes described in this invention provide a closer hue match to the SWOP standard and better transfer density than the preferred dye mixtures of U.S. Patent 4,923,846.

15 In U.S. Patent No. 4,816,435, a combination of thermally transferrable dyes is disclosed for use in producing black images. The dye types disclosed are di- and tri-cyanovinylanilines (for the yellow and magenta respectively) and phenol-based indoaniline cyan dyes. There is a problem with using these dyes in dye-donors in that the storage stability is not as good as one would like it to be. It is an object of this invention to provide a black dye-donor with good storage stability.

20 In JP 01/136,787, a combination of thermally-transferrable dyes is disclosed for use in producing black images. Quinophthalone, dicyanovinyl aniline and azopyridone yellow dyes are described along with imidazolylazonaniline magenta and phenol-based indoaniline cyan dyes. Here again, there is a problem with using these dyes in dye-donors in that the storage stability is not as good as one would like it to be.

Accordingly, this invention relates to a black dye-donor element for thermal dye transfer comprising a
25 support having thereon a dye layer comprising a mixture of cyan, yellow and magenta dyes dispersed in a polymeric binder, at least one of the cyan dyes having the formula:



wherein:

R^1 and R^2 each independently represents hydrogen; an alkyl group having from 1 to 10 carbon atoms; a cycloalkyl group having from 5 to 7 carbon atoms; allyl; or such alkyl, cycloalkyl or allyl groups
40 substituted with one or more groups such as alkyl, aryl, alkoxy, aryloxy, amino, halogen, nitro, cyano, thiocyno, hydroxy, acyloxy, acyl, alkoxycarbonyl, aminocarbonyl, alkoxycarbonyloxy, carbamoyloxy, acylamino, ureido, imido, alkylsulfonyl, arylsulfonyl, alkylsulfonamido, arylsulfonamido, alkylthio, arylthio, trifluoromethyl, etc., e.g., methyl, ethyl, propyl, isopropyl, butyl, pentyl, hexyl, methoxyethyl, benzyl, 2-methanesulfonamidoethyl, 2-hydroxyethyl, 2-cyanoethyl, methoxycarbonylmethyl, cyclohexyl, cyclopentyl,
45 phenyl, pyridyl, naphthyl, thienyl, pyrazolyl, p-tolyl, p-chlorophenyl, m-(N-methyl-sulfamoyl)phenyl-methyl, methylthio, butylthio, benzylthio, methanesulfonyl, pentanesulfonyl, methoxy, ethoxy, 2-methane-sulfonamidoethyl, 2-hydroxyethyl, 2-cyanoethyl, methoxy-carbonylmethyl, imidazolyl, naphthyloxy, furyl, p-tolylsulfonyl, p-chlorophenylthio, m-(N-methyl sulfamoyl)phenoxy, ethoxy-carbonyl, methoxyethoxycarbonyl, phenoxy-carbonyl, acetyl, benzoyl, N,N-dimethyl-carbamoyl, dimethylamino, morpholino, anilino, pyrrolidino
50 etc.; with the proviso that R^1 and R^2 cannot both be hydrogen;

or R^1 and R^2 can be joined together to form, along with the nitrogen to which they are attached, a 5- to 7-membered heterocyclic ring such as morpholine or pyrrolidine;

or either or both of R^1 and R^2 can be combined with an R^3 to form a 5- to 7-membered heterocyclic ring;

55 each R^3 independently represents hydrogen, substituted or unsubstituted alkyl, cycloalkyl or allyl as described above for R^1 and R^2 ; alkoxy, aryloxy, halogen, thiocyno, acylamino, ureido, alkylsulfonamido, arylsulfonamido, alkylthio, arylthio or trifluoromethyl;

or any two of R^3 may be combined together to form a 5- or 6-membered carbocyclic or heterocyclic

ring;

or one or two of R^3 may be combined with either or both of R^1 and R^2 to complete a 5- to 7-membered ring;


m is an integer of from 0 to 4;

5 R^4 represents hydrogen or an electron withdrawing group such as cyano, alkoxycarbonyl, aminocarbonyl, alkylsulfonyl, arylsulfonyl, acyl, nitro, etc.;

R^5 represents an electron withdrawing group such as those listed above for R^4 ; an aryl group having from 6 to 10 carbon atoms; a hetaryl group having from 5 to 10 atoms; or such aryl or hetaryl groups substituted with one or more groups such as are listed above for R^1 and R^2 ;

10 R^6 and R^7 each independently represents an electron withdrawing group such as those described above for R^4 ; or R^6 and R^7 may be combined to form the residue of an active methylene compound such as a pyrazolin-5-one, a pyrazoline-3,5-dione, a thiohydantoin, a barbituric acid, a rhodanine, a furanone, an indandione, etc.;

15 or a compound according to formula I wherein R^1 and R^2 are C_2H_5 , R^3 is CH_3 and is located meta to the NR^1R^2 group, R^5 is 1-dibenzofuranyl, R^4 , R^6 and R^7 are CN and m is 1; and at least one of the yellow dyes having the formula:



wherein:

30 R^8 , R^9 and R^{11} each independently represents a substituted or unsubstituted alkyl group of from 1 to 10 carbon atoms, such as those listed above for R^1 ; a cycloalkyl group of from 5 to 7 carbon atoms, such as those listed above for R^1 ; an allyl group, such as those listed above for R^1 ; or a substituted or unsubstituted aryl group of from 6 to 10 carbon atoms, such as phenyl, naphthyl, p-tolyl, m-chlorophenyl, p-methoxyphenyl, m-bromophenyl, o-tolyl, etc.;

or R^8 and R^9 can be joined together to form, along with the nitrogen to which they are attached, a 5- or 6-membered heterocyclic ring, such as a pyrrolidine or morpholine ring;

35 or either or both of R^8 and R^9 can be joined to the carbon atom of the benzene ring at a position ortho to the position of attachment of the anilino nitrogen to form a 5- or 6-membered ring, thus forming a polycyclic system such as 1,2,3,4-tetrahydroquinoline, julolidine, 2,3-dihydroindole, or benzomorpholine;

40 R^{10} represents hydrogen; a substituted or unsubstituted alkyl group of from 1 to 10 carbon atoms, such as those listed above for R^1 ; a cycloalkyl group of from 5 to 7 carbon atoms, such as those listed above for R^1 ; an allyl group, such as those listed above for R^1 ; halogen; carbamoyl, such as N,N-dimethylcarbamoyl; or alkoxycarbonyl, such as ethoxycarbonyl or methoxyethoxy-carbonyl;

45 R^{12} represents a substituted or unsubstituted alkoxy group having from 1 to 10 carbon atoms, such as methoxy, ethoxy, methoxyethoxy or 2-cyanoethoxy; a substituted or unsubstituted aryloxy group having from 6 to 10 carbon atoms, such as phenoxy, m-chlorophenoxy, or naphthoxy; NHR^{13} , $NR^{13}R^{14}$ or the atoms, such as O, CH_2 , S, NR^{13} , etc., necessary to complete a 6-membered ring fused to the benzene ring;


R^{13} and R^{14} each independently represents any of the groups for R^8 , or R^{13} and R^{14} may be joined together to form, along with the nitrogen to which they are attached, a 5- or 6-membered heterocyclic ring, such as a pyrrolidine or morpholine ring;

n is a positive integer from 1 to 5; and

50 G represents hydrogen; a substituted or unsubstituted alkyl or alkoxy group of from 1 to 10 carbon atoms, such as those listed above for R^1 and R^{12} ; halogen; aryloxy; or represents the atoms necessary to complete a 5- or 6-membered ring, thus forming a fused ring system such as naphthalene, quinoline, isoquinoline or benzothiazole;

55 or a compound according to formula II wherein R^8 is CH_3 , R^9 is $CH_3CO_2CH_2CH_2$, R^{10} is hydrogen, R^{11} is 2-pyridyl, R^{12} is NHC_6H_5 and G is $-N=CH-CH=CH-$ and completes a fused ring system with the nitrogen ortho to the NR^8R^9 group;

and at least one of the magenta dyes having the formula:



wherein:

R¹⁵ represents hydrogen or a substituted or unsubstituted alkyl or allyl group of from 1 to 10 carbon atoms, such as those listed above for R¹;

15 Q is R¹⁵, an alkoxy group of from 1 to 4 carbon atoms or taken together with R¹⁶ represents the atoms which form a 5- or 6-membered heterocyclic ring;

R¹⁶ is a substituted or unsubstituted alkyl or allyl group of from 1 to 10 carbon atoms, such as those listed above for R¹, or can be combined with Q as described above;

20 R¹⁸ is a substituted or unsubstituted alkyl group of from 1 to 10 carbon atoms such as those listed above for R¹, or a substituted or unsubstituted aryl group of from 6 to 10 carbon atoms, such as those listed above for R⁸;


J is CO, CO₂, -SO₂- or CONR¹⁹-;






R¹⁷ is a substituted or unsubstituted alkyl or allyl group of from 1 to 10 carbon atoms, such as those listed above for R¹, or a substituted or unsubstituted aryl group of from 6 to 10 carbon atoms, such as those listed above for R⁸; and



25 R¹⁹ is hydrogen or R¹⁸.




In a preferred embodiment for compounds according to formula I employed in the invention, R⁴, R⁶ and R⁷ are cyano. In another preferred embodiment for compounds according to formula I employed in the invention, R¹ is C₂H₅, C₂H₄OH, or n-C₃H₇. In yet another preferred embodiment for compounds according to formula I employed in the invention, R² is C₂H₅ or n-C₃H₇. In yet still another preferred embodiment for compounds according to formula I employed in the invention, R³ is hydrogen, OC₂H₅, CH₃ or NHCOCH₃. In another preferred embodiment for compounds according to formula I employed in the invention, R⁵ is p-C₆H₄Cl, m-C₆H₄NO₂ or naphthyl.


Compounds included within the scope of formula I employed in the invention include the following:



Compound	R ¹	R ²	R ³	R ⁵
I-1	C ₂ H ₅	C ₂ H ₅	CH ₃	C ₆ H ₅
I-2	C ₂ H ₅	C ₂ H ₅	H	C ₆ H ₅
I-3	C ₂ H ₄ OH	C ₂ H ₅	CH ₃	C ₆ H ₅
I-4	C ₂ H ₅	C ₂ H ₅	OC ₂ H ₅	C ₆ H ₅
I-5	n-C ₃ H ₇	n-C ₃ H ₇	NHCOCH ₃	C ₆ H ₅
I-6	C ₂ H ₅	C ₂ H ₅	CH ₃	o-C ₆ H ₄ OCH ₃
I-7	C ₂ H ₅	C ₂ H ₅	CH ₃	p-C ₆ H ₄ OCH ₃
I-8	C ₂ H ₅	C ₂ H ₅	CH ₃	p-C ₆ H ₄ Cl
I-9	C ₂ H ₅	C ₂ H ₅	CH ₃	m-C ₆ H ₄ NO ₂
I-10	C ₂ H ₅	C ₂ H ₅	CH ₃	
I-11	C ₂ H ₅	C ₂ H ₅	CH ₃	
I-12	C ₂ H ₅	C ₂ H ₅	CH ₃	
I-13	C ₂ H ₅	C ₂ H ₅	H	
I-14	C ₂ H ₅	C ₂ H ₅	CH ₃	p-C ₆ H ₄ F
I-15	C ₂ H ₅	C ₂ H ₅	CH ₃	o-C ₆ H ₄ Cl
I-16	C ₂ H ₅	C ₂ H ₅	CH ₃	p-C ₆ H ₄ CN
I-17	C ₂ H ₅	C ₂ H ₅	CH ₃	3,4-C ₆ H ₃ Cl ₂
I-18	C ₂ H ₅	C ₂ H ₅	CH ₃	2,4-C ₆ H ₃ Cl ₂
I-19	C ₂ H ₅	C ₂ H ₅	CH ₃	

Compound	R ¹	R ²	R ³	R ⁵
I-20	C ₂ H ₅	C ₂ H ₅	CH ₃	
I-21	C ₂ H ₅	C ₂ H ₅	CH ₃	
I-22	C ₂ H ₄ OH	C ₂ H ₅	CH ₃	p-C ₆ H ₄ Cl
I-23	C ₂ H ₄ NH-SO ₂ CH ₃	C ₂ H ₅	CH ₃	p-C ₆ H ₄ Cl





The above dyes may be prepared analogously to the method described in Example 1 below.


In a preferred embodiment for compounds according to formula II employed in the invention, R^{11} is phenyl; R^{12} is ethoxy or NHR^{13} , wherein R^{13} is methyl or phenyl; n is 1; and R^{10} is hydrogen.



In another preferred embodiment for compounds according to formula II employed in the invention, R^{12} is O and completes a 6-membered ring fused to the benzene ring. In another preferred embodiment for compounds according to formula II employed in the invention, R^{12} is $NR^{13}R^{14}$, wherein each R^{13} and R^{14} is methyl or R^{13} is ethyl and R^{14} is phenyl.

In another preferred embodiment for compounds according to formula II employed in the invention, R^{12} is $NR^{13}R^{14}$, wherein R^{13} and R^{14} are joined together to form, along with the nitrogen to which they are attached, a pyrrolidine or morpholine ring.


The compounds of formula II employed in the invention above may be prepared by any of the processes disclosed in U.S. Patent 4,866,029.

Compounds included within the scope of formula II employed in the invention include the following:




Cmpd.	G	R ⁸	R ⁹	R ¹⁰	R ¹¹	R ¹²
II-1	H	C ₂ H ₅	C ₂ H ₅	H	C ₆ H ₅	N(CH ₃) ₂
II-2	H	CH ₃	CH ₃	H	C ₆ H ₅	N(CH ₃) ₂
II-3	H	n-C ₄ H ₉	n-C ₄ H ₉	H	C ₆ H ₅	N(CH ₃) ₂
II-4	3-CH ₃	C ₂ H ₅	CF ₃ CH ₂ O ₂ CCH ₂	H	C ₆ H ₅	N(CH ₃) ₂
II-5	H			H	C ₆ H ₅	N(CH ₃) ₂
II-6	H	C ₂ H ₅	C ₂ H ₅	H	C ₆ H ₅	NHC ₆ H ₅
II-7	H	C ₂ H ₅	C ₂ H ₅	H	C ₆ H ₅	
II-8	H	C ₂ H ₅	C ₂ H ₅	H	C ₆ H ₅	
II-9	H	C ₂ H ₅	C ₂ H ₅	H	C ₆ H ₅	NHCH ₃
II-10	H	C ₂ H ₅	C ₂ H ₅	H	C ₆ H ₅	N(C ₂ H ₅)- (C ₆ H ₅)
II-11	3-OCH ₃	C ₂ H ₅	C ₂ H ₅	H	C ₆ H ₅	N(CH ₃) ₂
II-12	H	n-C ₄ H ₉	n-C ₄ H ₉	H	C ₆ H ₅	OC ₂ H ₅
II-13	3-Cl	CH ₃	C ₂ H ₅ O ₂ CCH ₂	H	C ₁₀ H ₉	N(CH ₃) ₂
II-14	H			H	4-Cl-C ₆ H ₄	OCH ₃
II-15	3-CH ₃	ClC ₂ H ₄	ClC ₂ H ₄	H	CH ₂ C ₆ H ₅	OC ₆ H ₅
II-16	3-C ₂ H ₅	C ₆ H ₅ CH ₂	C ₂ H ₅	H	CH ₃	N(CH ₃) ₂
II-17	2,5-(OCH ₃) ₂	CH ₃	CH ₃	H	3,5-(Cl) ₂ -C ₆ H ₃	NHCH ₃
II-18	H	CH ₃	CH ₃	CO ₂ C ₂ H ₅	C ₆ H ₅	N(CH ₃) ₂
II-19	H	CH ₃	CH ₃	Cl	C ₆ H ₅	N(CH ₃) ₂
II-20	3-CH ₃	C ₂ H ₅	C ₆ H ₅ CH ₂	H	C ₆ H ₅	OC ₂ H ₅
II-21	H	C ₂ H ₅	C ₂ H ₅	H	C ₆ H ₅	OC ₃ H ₇ -i
II-22	3-CH ₃	C ₂ H ₅	C ₂ H ₅	H	C ₆ H ₅	OC ₂ H ₅


II-23




II-24




II-25




II-26




II-27




II-28



II-29




II-30



In a preferred embodiment for compounds according to formula III employed in the invention, R^{15} and R^{16} are each C_3H_7 , Q is H , J is CO , R^{18} is CH_3 and R^{17} is $3-CH_2CO_2C_2H_5$. In another preferred embodiment of the invention, R^{15} and R^{16} are each C_3H_7 , Q is H , J is CO , R^{18} is CH_3 and R^{17} is $CH_2CH=CH_2$.

The compounds of formula III above employed in the invention may be prepared by any of the processes disclosed in U.S. Patent 4,097,475.

Magenta dyes included within the scope of formula III include the following:



Dye	R15	R16	Q	R17	R18	J
III-1	n-C ₃ H ₇	n-C ₃ H ₇	H	CH ₂ CO ₂ C ₂ H ₅	CH ₃	CO
III-2	H	C ₂ H ₅	OCH ₃	CH ₂ CO ₂ C ₂ H ₅	CH ₃	CO
III-3	C ₂ H ₅	-C(CH ₃) ₂ CH ₂ CH(CH ₃)-		C ₂ H ₅	C ₂ H ₅	CO
III-4	C ₂ H ₅	C ₂ H ₅	H	CH ₂ COCH ₃	CH ₃	CO
III-5	n-C ₃ H ₇	C ₂ H ₅	H	CH ₂ CO ₂ CH ₃	C ₂ H ₅	CO
III-6	CH ₃	CH ₃	H	CH ₂ COCH ₃	CH ₃	SO ₂
III-7	H	n-C ₃ H ₇	OC ₂ H ₅	CH ₂ CO ₂ CH ₃	C ₂ H ₅	CO
III-8	C ₂ H ₅	C ₂ H ₅	H	CH ₂ COCH ₃	(CH ₃) ₃ C	CO
III-9	n-C ₃ H ₇	n-C ₃ H ₇	H	CH ₂ CN	C ₂ H ₅	SO ₂
III-10	CH ₃	CH ₃	H	C ₆ H ₁₃	CH ₃	CO
III-11	CH ₃	CH ₃	H	CH ₂ COCH ₃	C ₆ H ₅	CO
III-12	H	CH ₃	OCH ₃	CH ₂ COCH ₃	C ₆ H ₅	CO
III-13	C ₆ H ₅ (CH ₂) ₂	C ₂ H ₅	H	CH ₂ CO ₂ CH ₃	CH ₃	CO
III-14	H	C ₂ H ₅	OCH ₂ C ₆ H ₅	C ₆ H ₅	C ₂ H ₅	CO
III-15	CH ₃ O(CH ₂) ₂	CH ₃	H	CH ₂ CN	n-C ₃ H ₇	CO
III-16	C ₂ H ₅	C ₂ H ₅	H	CH ₂ COCH ₃	CH ₃	CON(CH ₃)
III-17	H	n-C ₃ H ₇	O(CH ₂) ₂ OCH ₃	CH ₃	CH ₃	CO
III-18	C ₆ H ₅ CH ₂	C ₂ H ₅	H	CH ₂ C ₆ H ₅	CH ₃	CO ₂
III-19	n-C ₃ H ₇	n-C ₃ H ₇	H	-CH ₂ CH=CH ₂	CH ₃	CO

The use of dye mixtures in the dye-donor of the invention permits a wide selection of hue and color that enables a close hue match to a variety of printing inks and also permits easy transfer of images one or more times to a receiver if desired. The use of dyes also allows easy modification of image density to any desired level. The dyes of the dye-donor element of the invention may be used at a coverage of from about 0.05 to about 1 g/m².

The dyes in the dye-donor of the invention are dispersed in a polymeric binder such as a cellulose derivative, e.g., cellulose acetate hydrogen phthalate, cellulose acetate, cellulose acetate propionate, cellulose acetate butyrate, cellulose triacetate or any of the materials described in U. S. Patent 4,700,207; a polycarbonate; polyvinyl acetate; poly(styrene-co-acrylonitrile); a poly(sulfone) or a poly(phenylene oxide). The binder may be used at a coverage of from about 0.1 to about 5 g/m².

The dye layer of the dye-donor element may be coated on the support or printed thereon by a printing technique such as a gravure process.

Any material can be used as the support for the dye-donor element of the invention provided it is dimensionally stable and can withstand the heat of the laser or thermal head. Such materials include polyesters such as poly(ethylene terephthalate); polyamides; polycarbonates; cellulose esters; fluorine polymers; polyethers; polyacetals; polyolefins; and polyimides. The support generally has a thickness of from about 5 to about 200 μm. It may also be coated with a subbing layer, if desired, such as those materials described in U. S. Patents 4,695,288 or 4,737,486.

The reverse side of the dye-donor element may be coated with a slipping layer to prevent the printing head from sticking to the dye-donor element. Such a slipping layer would comprise either a solid or liquid lubricating material or mixtures thereof, with or without a polymeric binder or a surface active agent. Preferred lubricating materials include oils or semi-crystalline organic solids that melt below 100 °C such as poly(vinyl stearate), beeswax, perfluorinated alkyl ester polyethers, poly(capro-lactone), silicone oil, poly(tetrafluoroethylene), carbowax, poly(ethylene glycols), or any of those materials disclosed in U. S. Patents

4,717,711; 4,717,712; 4,737,485; and 4,738,950. Suitable polymeric binders for the slipping layer include poly(vinyl alcohol-co-butyral), poly(vinyl alcohol-co-acetal), poly(styrene), poly(vinyl acetate), cellulose acetate butyrate, cellulose acetate propionate, cellulose acetate or ethyl cellulose.

The amount of the lubricating material to be used in the slipping layer depends largely on the type of lubricating material, but is generally in the range of about .001 to about 2 g/m². If a polymeric binder is employed, the lubricating material is present in the range of 0.1 to 50 weight %, preferably 0.5 to 40, of the polymeric binder employed.

The dye-receiving element that is used with the dye-donor element of the invention usually comprises a support having thereon a dye image-receiving layer. The support may be a transparent film such as a poly(ether sulfone), a polyimide, a cellulose ester such as cellulose acetate, a poly(vinyl alcohol-co-acetal) or a poly(ethylene terephthalate). The support for the dye-receiving element may also be reflective such as baryta-coated paper, polyethylene-coated paper, an ivory paper, a condenser paper or a synthetic paper such as duPont Tyvek®. Pigmented supports such as white polyester (transparent polyester with white pigment incorporated therein) may also be used.

The dye image-receiving layer may comprise, for example, a polycarbonate, a polyurethane, a polyester, polyvinyl chloride, poly(styrene-co-acrylonitrile), poly(caprolactone), a poly(vinyl acetal) such as poly(vinyl alcohol-co-butyral), poly(vinyl alcohol-co-benzal), poly(vinyl alcohol-co-acetal) or mixtures thereof. The dye image-receiving layer may be present in any amount which is effective for the intended purpose. In general, good results have been obtained at a concentration of from about 1 to about 5 g/m².

As noted above, the dye-donor elements of the invention are used to form a dye transfer image. Such a process comprises imagewise-heating a dye-donor element as described above and transferring a dye image to a dye-receiving element to form the dye transfer image.

The dye-donor element of the invention may be used in sheet form or in a continuous roll or ribbon. If a continuous roll or ribbon is employed, it may have only the dyes thereon as described above or may have alternating areas of other different dyes or combinations, such as sublimable cyan and/or yellow and/or black or other dyes. Such dyes are disclosed in U. S. Patent 4,541,830. Thus, one-, two-, three- or four-color elements (or higher numbers also) are included within the scope of the invention.

Thermal printing heads which can be used to transfer dye from the dye-donor elements of the invention are available commercially. There can be employed, for example, a Fujitsu Thermal Head (FTP-040 MCS001), a TDK Thermal Head F415 HH7-1089 or a Rohm Thermal Head KE 2008-F3.

A laser may also be used to transfer dye from the dye-donor elements of the invention. When a laser is used, it is preferred to use a diode laser since it offers substantial advantages in terms of its small size, low cost, stability, reliability, ruggedness, and ease of modulation. In practice, before any laser can be used to heat a dye-donor element, the element must contain an infrared-absorbing material, such as carbon black, cyanine infrared absorbing dyes as described in U.S. Patent 4,973,572 or other materials as described in U.S. Patents 4,948,777, 4,950,640, 4,950,639, 4,948,776, 4,948,776, 4,948,778, 4,942,141, 4,952,552 and 4,912,083. The laser radiation is then absorbed into the dye layer and converted to heat by a molecular process known as internal conversion. Thus, the construction of a useful dye layer will depend not only on the hue, transferability and intensity of the image dyes, but also on the ability of the dye layer to absorb the radiation and convert it to heat.

Lasers which can be used to transfer dye from dye-donors employed in the invention are available commercially. There can be employed, for example, Laser Model SDL-2420-H2 from Spectra Diode Labs, or Laser Model SLD 304 V/W from Sony Corp.

A thermal printer which uses the laser described above to form an image on a thermal print medium is described and claimed in European Patent Application 90 901 207.0 (EP-A-0 445 224).

Spacer beads may be employed in a separate layer over the dye layer of the dye-donor in the above-described laser process in order to separate the dye-donor from the dye-receiver during dye transfer, thereby increasing the uniformity and density of the transferred image. That invention is more fully described in U.S. Patent 4,772,582. Alternatively, the spacer beads may be employed in the receiving layer of the dye-receiver as described in U.S. Patent 4,876,235. The spacer beads may be coated with a polymeric binder if desired.

The use of an intermediate receiver with subsequent retransfer to a second receiving element may also be employed in the invention. A multitude of different substrates can be used to prepare the color proof (the second receiver) which is preferably the same substrate used for the printing press run. Thus, this one intermediate receiver can be optimized for efficient dye uptake without dye-smearing or crystallization.

Examples of substrates which may be used for the second receiving element (color proof) include the following: Flo Kote Cove® (S. D. Warren Co.), Champion Textweb® (Champion Paper Co.), Quintessence Gloss® (Potlatch Inc.), Vintage Gloss® (Potlatch Inc.), Khrome Kote® (Champion Paper Co.), Consolith

Gloss® (Consolidated Papers Co.), Ad-Proof Paper® (Appleton Papers, Inc.) and Mountie Matte® (Potlatch Inc.).

As noted above, after the dye image is obtained on a first dye-receiving element, it is retransferred to a second dye image-receiving element. This can be accomplished, for example, by passing the two receivers between a pair of heated rollers. Other methods of retransferring the dye image could also be used such as using a heated platen, use of pressure and heat, external heating, etc.

Also as noted above, in making a color proof, a set of electrical signals is generated which is representative of the shape and color of an original image. This can be done, for example, by scanning an original image, filtering the image to separate it into the desired additive primary colors-red, blue and green, and then converting the light energy into electrical energy. The electrical signals are then modified by computer to form the color separation data which is used to form a halftone color proof. Instead of scanning an original object to obtain the electrical signals, the signals may also be generated by computer. This process is described more fully in Graphic Arts Manual, Janet Field ed., Arno Press, New York 1980 (p. 358ff).

A thermal dye transfer assemblage of the invention comprises

- a) a dye-donor element as described above, and
- b) a dye-receiving element as described above, the dye-receiving element being in a superposed relationship with the dye-donor element so that the dye layer of the donor element is in contact with the dye image-receiving layer of the receiving element.

The above assemblage comprising these two elements may be preassembled as an integral unit when a monochrome image is to be obtained. This may be done by temporarily adhering the two elements together at their margins. After transfer, the dye-receiving element is then peeled apart to reveal the dye transfer image.

When a three-color image is to be obtained, the above assemblage is formed three times using different dye-donor elements. After the first dye is transferred, the elements are peeled apart. A second dye-donor element (or another area of the donor element with a different dye area) is then brought in register with the dye-receiving element and the process repeated. The third color is obtained in the same manner.


The following examples are provided to illustrate the invention.

Example 1 Synthesis of Compound I-1

A. Synthesis of 2-phenyl-1,1,3-tricyano-propene (intermediate for Compound I-1)

A mixture of benzoylacetonitrile (9.94 g, 0.0685 mole), malononitrile (11.3 g, 0.17 mole), ammonium acetate (5.4 g, 0.07 mole) and ethanol (100 ml) was heated at reflux for 1.5 hours. After cooling to room temperature, the reaction mixture was diluted with water (50 ml) and concentrated hydrochloric acid (7.5 ml) was added dropwise over 5 minutes. The resulting precipitate was collected by filtration and washed with water and ligroin. The yield was 10.0 g (76%), m.p. 92-98° C.

B. Synthesis of Compound I-1: 2-phenyl-1,1,3-tricyano-3-(4-diethylamino-2-methylphenylimino)-propene



A mixture of the phenyltricyanopropene above (0.58 g, 0.003 mole) and 2-amino-5-diethylaminotoluene hydrochloride (0.64 g, 0.003 mole) in a solution of methanol (30 ml) and water (10 ml) was treated with concentrated ammonium hydroxide (1.8 ml). To this mixture was slowly added a solution of potassium ferricyanide (4.94 g, 0.015 mole) in water (20 ml), keeping the temperature below 20° C with external cooling. After stirring for 2 hours, the reaction mixture was diluted with water (100 ml) and the resulting precipitate was collected by filtration and washed well with water. The crude dye was crystallized from

methanol to yield 0.85 g (81%) of a dark green powder. The dye had a λ_{max} of 604 nm with a molar extinction coefficient of 44,200 (in acetone solution).

Example 2

5

A black dye-donor element was prepared by coating on a 100 μm poly(ethylene terephthalate) support:
1) a subbing layer of poly(acrylonitrile-co-vinylidene chloride-co-acrylic acid) (0.054 g/m²) (14:79:7 wt. ratio); and

10 2) a dye layer containing a mixture of cyan dye I-8, yellow dye II-22 and magenta dye III-1 illustrated above, (total dye coverage of 0.65g/m²) and the cyanine infrared absorbing dye illustrated below (0.054 g/m²) in a cellulose acetate propionate binder (2.5% acetyl, 45% propionyl) (0.27 g/m²) coated from dichloromethane.


Other dye-donors according to the invention were prepared as above except using the dyes identified below in the Table and illustrated above. Comparison dye-donors using a mixture of cyan, yellow and
15 magenta dyes of the prior art as identified below, at a total coverage of 0.65 g/m², were also prepared similar to the dye-donor described above.

Cyanine Infrared Absorbing Dye

20

25

30



35 An intermediate dye-receiving element was prepared by coating on an unsubbed 100 μm thick poly-(ethylene terephthalate) support a layer of crosslinked poly(styrene-co-divinylbenzene) beads (14 μm average diameter) (0.11 g/m²), triethanolamine (0.09 g/m²) and DC-510® Silicone Fluid (Dow Corning Company) (0.01 g/m²) in a Butvar® 76 binder, a poly(vinyl alcohol-co-butyral), (Monsanto Company) (4.0 g/m²) from 1,1,2-trichloroethane or dichloromethane.

40 Single color images were printed as described below from dye-donors onto a receiver using a laser imaging device as described in U.S. Patent 4,876,235. The laser imaging device consisted of a single diode laser connected to a lens assembly mounted on a translation stage and focused onto the dye-donor layer.

The dye-receiving element was secured to the drum of the diode laser imaging device with the receiving layer facing out. The dye-donor element was secured in face-to-face contact with the receiving element.

45 The diode laser used was a Spectra Diode Labs No. SDL-2430-H2, having an integral, attached optical fiber for the output of the laser beam, with a wavelength of 816 nm and a nominal power output of 250 milliwatts at the end of the optical fiber. The cleaved face of the optical fiber (100 μm core diameter) was imaged onto the plane of the dye-donor with a 0.33 magnification lens assembly mounted on a translation stage giving a nominal spot size of 33 μm and a measured power output at the focal plane of 115 milliwatts.

50 The drum, 312 mm in circumference, was rotated at 500 rev/min and the imaging electronics were activated. The translation stage was incrementally advanced across the dye-donor by means of a lead screw turned by a microstepping motor, to give a center-to-center line distance of 14 μm (714 lines per centimeter, or 1800 lines per inch). For a continuous tone stepped image, the current supplied to the laser was modulated from full power to 16% power in 4% increments. Maximum transfer density can be
55 increased at the expense of printing speed by slowing the drum rotation while keeping all other operating parameters constant.

After the laser had scanned approximately 12 mm, the laser exposing device was stopped and the intermediate receiver was separated from the dye donor. The intermediate receiver containing the stepped

dye image was laminated to Ad-Proof Paper® (Appleton Papers, Inc.) 60 pound stock paper by passage through a pair of rubber rollers heated to 120 °C. The polyethylene terephthalate support was then peeled away leaving the dye image and polyvinyl alcohol-co-butylal firmly adhered to the paper. The paper stock was chosen to represent the substrate used for a printed ink image obtained from a printing press.

The Status T density of each of the stepped images was read using an X-Rite® 418 Densitometer to find the single step image within 0.05 density unit of the SWOP Color Reference. For the black standard, this density was 1.6.

The a* and b* values of the selected step image of transferred dye-mixture was compared to that of the SWOP Color Reference by reading on an X-Rite® 918 Colorimeter set for D50 illuminant and a 10 degree observer. The L* reading was checked to see that it did not differ appreciably from the reference. The a* and b* readings were recorded and the distance from the SWOP Color Reference calculated as the square root of the sum of differences squared for a* and b*:

$$\text{i.e. } \sqrt{(a_e^* - a_s^*)^2 + (b_e^* - b_s^*)^2}$$

e = experiment (transferred dye)

s = SWOP Color Reference

In addition, the above dye-donors were evaluated for storage stability by comparing transmission spectra of the donor before and after incubation at 50 °C/50% RH for 4 days.

The following results were obtained:

Table 1

Dyes (Weight Ratio)	a*	b*	Distance From Reference	Density @ 500 rpm	Storage Stability
SWOP	1.5	2.0	-	-	-
I-8/II-22/III-1 (21:22:17)	4.7	0	4	2.1	no change
I-8/II-1/III-19 (21:21:18)	3.8	2.8	3	2.3	no change
I-8/II-1/III-1 (1:1:1)	2.2	1.3	1	1.9	no change
Control 1 ^a	-1.2 ^b	-5.4 ^b	8.0	0.8	no change
Control 2 ^c	-2.4	-1.5	5.5	1.6	75% of cyan component decomposed; magenta dye sublimates from coating at room temperature
Control 3 ^d	-6.4	-2.1	9	1.7	30% of cyan component decomposed

^a Similar to Example C-17, Table C-17, from U.S. Patent 4,923,846, a mixture of Solvent Blue 36, Solvent Red 19 and Foron Brilliant Yellow S-6GL (structures below) in a ratio of 7:4:4.

^b In order to obtain sufficient density for colorimetric comparisons, the laser imaging device had to be slowed to 400 rev/min.


^c Similar to Example 1 of U.S. patent 4,186,435, a mixture of dyes C-1, C-3 and C-5 in a 32:12.5:15.5 ratio (structures below)

^d Similar to Example 3 of JP 01/136,787, a mixture of dyes C-6, C-4, C-2 and C-1 (structures below) in a 2:3:3:2 ratio.

CYAN CONTROL DYES

5


10



SOLVENT BLUE 36

15


20



C-1

25

30




C-2

35

MAGENTA CONTROL DYES

40


45




C-3

50


55




SOLVENT RED 19 (SUDAN RED 7B)




C-4

YELLOW CONTROL DYES

FORON YELLOW S-6GL



C-5




C-6

The data in the Table show that the dye combination of the invention provides high transfer density, neutral black hue very close to the SWOP Color Reference and excellent donor storage stability. The dyes of the prior art are further away from the SWOP Color Reference. In addition, the dyes disclosed in US 4,923,846 are not capable of yielding high transfer density while the dyes of US 4,186,435 and JP01-136787 exhibit very poor storage stability.

Claims

1. A black dye-donor element for thermal dye transfer comprising a support having thereon a dye layer comprising a mixture of at least one cyan, magenta and yellow dyes dispersed in a polymeric binder, characterized in that at least one of the cyan dyes has the formula:



wherein:

R¹ and R² each independently represents hydrogen; a substituted or unsubstituted alkyl group having from 1 to 10 carbon atoms; a substituted or unsubstituted cycloalkyl group having from 5 to 7 carbon atoms or a substituted or unsubstituted allyl group; with the proviso that R¹ and R² cannot both be hydrogen;

or R¹ and R² can be joined together to form, along with the nitrogen to which they are attached, a 5- to 7-membered heterocyclic ring;

or either or both of R¹ and R² can be combined with an R³ to form a 5- to 7-membered heterocyclic ring;

each R³ independently represents hydrogen, substituted or unsubstituted alkyl, cycloalkyl or allyl as described above for R¹ and R², alkoxy, aryloxy, halogen, thiocyno, acylamino, ureido, alkylsulfonamido, arylsulfonamido, alkylthio, arylthio or trifluoromethyl;

or any two of R³ may be combined together to form a 5- or 6-membered carbocyclic or heterocyclic ring; or one or two of R³ may be combined with either or both of R¹ and R² to complete a 5- to 7-membered ring;

m is an integer of from 0 to 4;

R⁴ represents hydrogen or an electron withdrawing group;


R⁵ represents an electron withdrawing group, a substituted or unsubstituted aryl group having from 6 to 10 carbon atoms or a substituted or unsubstituted hetaryl group having from 5 to 10 atoms;

R⁶ and R⁷ each independently represents an electron withdrawing group; and

R⁶ and R⁷ may be combined to form the residue of an active methylene compound;

or a compound according to formula I wherein R¹ and R² are C₂H₅, R³ is CH₃ and is located meta to the NR¹R² group, R⁵ is 1-dibenzofuranyl, R⁴, R⁶ and R⁷ are CN and m is 1;

and at least one of the yellow dyes having the formula:



wherein:

R⁸, R⁹ and R¹¹ each independently represents a substituted or unsubstituted alkyl group of from 1 to 10 carbon atoms; a cycloalkyl group of from 5 to 7 carbon atoms; a substituted or unsubstituted allyl group; or a substituted or unsubstituted aryl group of from 6 to 10 carbon atoms;

or R⁸ and R⁹ can be joined together to form, along with the nitrogen to which they are attached, a 5- or 6-membered heterocyclic ring;

or either or both of R⁸ and R⁹ can be joined to the carbon atom of the benzene ring at a position ortho to the position of attachment of the anilino nitrogen to form a 5- or 6-membered ring, thus forming

a polycyclic system;

R¹⁰ represents hydrogen; a substituted or unsubstituted alkyl group of from 1 to 10 carbon atoms; a cycloalkyl group of from 5 to 7 carbon atoms; a substituted or unsubstituted allyl group; halogen; carbamoyl; or alkoxy carbonyl;

R¹² represents a substituted or unsubstituted alkoxy group having from 1 to 10 carbon atoms; a substituted or unsubstituted aryloxy group having from 6 to 10 carbon atoms; NHR¹³; NR¹³R¹⁴ or the atoms necessary to complete a 6-membered ring fused to the benzene ring;


R¹³ and R¹⁴ each independently represents any of the groups for R⁸; or R¹³ and R¹⁴ may be joined together to form, along with the nitrogen to which they are attached, a 5- or 6-membered heterocyclic ring;

n is a positive integer from 1 to 5; and

G represents hydrogen; a substituted or unsubstituted alkyl or alkoxy group of from 1 to 10 carbon atoms; halogen; aryloxy; or represents the atoms necessary to complete a 5- or 6-membered ring, thus forming a fused ring system;

or a compound according to formula II wherein R¹⁰ is hydrogen, R¹¹ is 2-pyridyl, R¹² is NHC₆H₅, R⁸ is CH₃, R⁹ is CH₃CO₂CH₂CH₂ and G is -N=CH-CH=CH- and completes a fused ring system with the nitrogen ortho to the NR⁸R⁹ group;

and at least one of the magenta dyes having the formula:



wherein:

R¹⁵ represents hydrogen or a substituted or unsubstituted alkyl or allyl group of from 1 to 10 carbon atoms;

Q is R¹⁵, an alkoxy group of from 1 to 4 carbon atoms or taken together with R¹⁶ represents the atoms which form a 5- or 6-membered heterocyclic ring;

R¹⁶ is a substituted or unsubstituted alkyl or allyl group of from 1 to 10 carbon atoms or can be combined with Q as described above;

R¹⁸ is a substituted or unsubstituted alkyl group of from 1 to 10 carbon atoms or a substituted or unsubstituted aryl group of from 6 to 10 carbon atoms;

J is CO, CO₂, -SO₂ - or CONR¹⁹;

R¹⁷ is a substituted or unsubstituted alkyl or allyl group of from 1 to 10 carbon atoms or a substituted or unsubstituted aryl group of from 6 to 10 carbon atoms; and

R¹⁹ is hydrogen or R¹⁸.

2. The element of Claim 1 characterized in that in formula I, R⁴, R⁶ and R⁷ are cyano and R¹ is C₂H₅, C₂H₄OH, or n-C₃H₇.

3. The element of Claim 1 characterized in that in formula I, R² is C₂H₅ or n-C₃H₇; R³ is hydrogen, OC₂H₅, CH₃ or NHC(=O)CH₃; and R⁵ is p-C₆H₄Cl, m-C₆H₄NO₂ or naphthyl.

4. The element of Claim 1 characterized in that R¹¹ is phenyl, R¹² is ethoxy or NHR¹³, wherein R¹³ is methyl or phenyl, n is 1 and R¹⁰ is hydrogen.


5. The element of Claim 1 characterized in that R¹² is O and completes a 6-membered ring fused to the benzene ring.

6. The element of Claim 1 characterized in that R¹² is NR¹³R¹⁴ wherein each R¹³ and R¹⁴ is methyl or R¹³ is ethyl and R¹⁴ is phenyl.

7. The element of Claim 1 characterized in that R¹² is NR¹³R¹⁴, wherein R¹³ and R¹⁴ are joined together to form, along with the nitrogen to which they are attached, a pyrrolidine or morpholine ring.
8. The element of Claim 1 characterized in that R¹⁵ and R¹⁶ are each C₃H₇, Q is H, J is CO, R¹⁸ is CH₃ and R¹⁷ is 3-CH₂CO₂C₂H₅; or R¹⁵ and R¹⁶ are each C₃H₇, Q is H, J is CO, R¹⁸ is CH₃ and R¹⁷ is CH₂CH=CH₂.
9. A process of forming a dye transfer image comprising imagewise-heating a black dye-donor element according to claim 1.
10. A thermal dye transfer assemblage comprising:
 - a) a black dye-donor element according to claim 1, and
 - b) a dye-receiving element comprising a support having thereon a dye image-receiving layer, said dye-receiving element being in a superposed relationship with said black dye-donor element so that said dye layer is in contact with said dye image-receiving layer.


Patentansprüche

- 20 1. Schwarzes Farbstoff-Donorelement für die thermische Farbstoffübertragung mit einem Träger, auf dem sich eine Farbstoffschicht befindet mit einer Mischung aus mindestens einem blaugrünen, purpurroten und gelben Farbstoff, dispergiert in einem polymeren Bindemittel, dadurch gekennzeichnet, daß mindestens einer der blaugrünen Farbstoffe die Formel hat:



worin bedeuten: R¹ und R² jeweils unabhängig voneinander Wasserstoff; eine substituierte oder unsubstituierte Alkylgruppe mit 1 bis 10 Kohlenstoffatomen; eine substituierte oder unsubstituierte Cycloalkylgruppe mit 5 bis 7 Kohlenstoffatomen oder eine substituierte oder unsubstituierte Allylgruppe; wobei gilt, daß R¹ und R² nicht beide für Wasserstoff stehen können; oder R¹ und R² bilden gemeinsam mit dem Stickstoff, an das sie gebunden sind, einen 5- bis 7-gliedrigen heterocyclischen Ring; oder einer oder beide der Reste R¹ und R² können mit einem Rest R³ verbunden sein, unter Bildung eines 5- bis 7-gliedrigen heterocyclischen Ringes; R³ steht jeweils unabhängig voneinander für Wasserstoff, substituiertes oder unsubstituiertes Alkyl, Cycloalkyl oder Allyl, wie oben für R¹ und R² beschrieben, Alkoxy, Aryloxy, Halogen, Thiocyno, Acylamino, Ureido, Alkylsulfonamido, Arylsulfonamido, Alkylthio, Arylthio oder Trifluoromethyl; oder zwei der Reste R³ können gemeinsam einen 5- oder 6-gliedrigen carbocyclischen oder heterocyclischen Ring bilden; oder einer oder zwei Reste R³ können mit entweder einem oder beiden der Reste R¹ und R² gemeinsam einen 5- bis 7-gliedrigen Ring bilden; m eine ganze Zahl von 0 bis 4; R⁴ Wasserstoff oder eine Elektronen abziehende Gruppe; R⁵ eine Elektronen abziehende Gruppe, eine substituierte oder unsubstituierte Arylgruppe mit 6 bis 10 Kohlenstoffatomen oder eine substituierte oder unsubstituierte Hetarylgruppe mit 5 bis 10 Atomen; R⁶ und R⁷ jeweils unabhängig voneinander eine Elektronen abziehende Gruppe; und R⁶ und R⁷ können miteinander verbunden sein, unter Bildung des Restes einer aktiven Methylenverbindung; oder der Farbstoff ist eine Verbindung gemäß Formel I, in der R¹ und R² stehen für -C₂H₅, R³ steht für -CH₃ und befindet sich in meta-Stellung zu der -NR¹R²-Gruppe, R⁵ steht für 1-Dibenzofuranyl, R⁴, R⁶ und R⁷ stehen für -CN und m ist 1;

und daß mindestens einer der gelben Farbstoffe die folgende Formel hat:



worin bedeuten: R⁸, R⁹ und R¹¹ stehen jeweils unabhängig voneinander für eine substituierte oder unsubstituierte Alkylgruppe mit 1 bis 10 Kohlenstoffatomen; eine Cycloalkylgruppe mit 5 bis 7 Kohlenstoffatomen; eine substituierte oder unsubstituierte Allylgruppe; oder eine substituierte oder unsubstituierte Arylgruppe mit 6 bis 10 Kohlenstoffatomen;

oder R⁸ und R⁹ bilden gemeinsam mit dem Stickstoff, an das sie gebunden sind, einen 5- oder 6-gliedrigen heterocyclischen Ring;

oder einer oder beide der Reste R⁸ und R⁹ sind an das Kohlenstoffatom des Benzolringes in einer Position ortho zur Position der Bindung des Anilino-Stickstoffes gebunden, unter Bildung eines 5- oder 6-gliedrigen Ringes, unter Bildung eines polycyclischen Systems;

R¹⁰ Wasserstoff; eine substituierte oder unsubstituierte Alkylgruppe mit 1 bis 10 Kohlenstoffatomen; eine Cycloalkylgruppe mit 5 bis 7 Kohlenstoffatomen; eine substituierte oder unsubstituierte Allylgruppe; Halogen; Carbamoyl oder Alkoxycarbonyl;

R¹² eine substituierte oder unsubstituierte Alkoxygruppe mit 1 bis 10 Kohlenstoffatomen; eine substituierte oder unsubstituierte Aryloxygruppe mit 6 bis 10 Kohlenstoffatomen; -NHR¹³; -NR¹³R¹⁴ oder die Atome, die zur Vervollständigung eines 6-gliedrigen Ringes erforderlich sind, der an den Benzolring ankondensiert ist;


R¹³ und R¹⁴ jeweils unabhängig voneinander eine der für R⁸ angegebenen Gruppen; oder R¹³ und R¹⁴ bilden gemeinsam mit dem Stickstoff, an das sie gebunden sind, einen 5- oder 6-gliedrigen heterocyclischen Ring;

n eine positive Zahl von 1 bis 5; und

G Wasserstoff, eine substituierte oder unsubstituierte Alkyl- oder Alkoxygruppe mit 1 bis 10 Kohlenstoffatomen; Halogen; Aryloxy oder die Atome, die zur Vervollständigung eines 5- oder 6-gliedrigen Ringes erforderlich sind, unter Erzeugung eines ankondensierten Ringsystems;

oder eine Verbindung gemäß Formel II, worin bedeuten: R¹⁰ Wasserstoff, R¹¹ 2-Pyridyl, R¹² -NHC₆H₅, R⁸ -CH₃, R⁹ -CH₃CO₂CH₂CH₂ und G ist gleich -N=CH-CH=CH- und vervollständigt ein ankondensiertes Ringsystem mit dem Stickstoff in ortho-Position zu der -NR⁸R⁹-Gruppe;

und daß mindestens einer der purpurroten Farbstoffe die folgende Formel hat:



worin bedeuten: R¹⁵ ein Wasserstoffatom oder eine substituierte oder unsubstituierte Alkyl- oder Allylgruppe mit 1 bis 10 Kohlenstoffatomen;

Q gleich R¹⁵, eine Alkoxygruppe mit 1 bis 4 Kohlenstoffatomen oder gemeinsam mit R¹⁶ die Atome, die zur Bildung eines 5- oder 6-gliedrigen heterocyclischen Ringes erforderlich sind;

R¹⁶ eine substituierte oder unsubstituierte Alkyl- oder Allylgruppe mit 1 bis 10 Kohlenstoffatomen, oder R¹⁶ kann mit Q kombiniert sein, wie oben beschrieben;

R¹⁸ eine substituierte oder unsubstituierte Alkylgruppe mit 1 bis 10 Kohlenstoffatomen oder eine substituierte oder unsubstituierte Arylgruppe mit 6 bis 10 Kohlenstoffatomen;

J gleich -CO-, -CO₂-, -SO₂- oder -CONR¹⁹-;


R¹⁷ eine substituierte oder unsubstituierte Alkyl- oder Allylgruppe mit 1 bis 10 Kohlenstoffatomen oder

eine substituierte oder unsubstituierte Arylgruppe mit 6 bis 10 Kohlenstoffatomen; und R¹⁹ Wasserstoff oder eine Gruppe wie für R¹⁸ angegeben.

2. Element nach Anspruch 1, dadurch gekennzeichnet, daß in der Formel I R⁴, R⁶ und R⁷ für Cyano stehen, und R¹ steht für -C₂H₅, -C₂H₄OH oder n-C₃H₇.
3. Element nach Anspruch 1, dadurch gekennzeichnet, daß in Formel I R² steht für -C₂H₅ oder n-C₃H₇; R³ steht für Wasserstoff, -OC₂H₅, -CH₃ oder -NHCOCH₃; und R⁵ steht für p-C₆H₄Cl, m-C₆H₄NO₂ oder Naphthyl.
4. Element nach Anspruch 1, dadurch gekennzeichnet, daß R¹¹ steht für Phenyl, R¹² steht für Ethoxy oder -NHR¹³, worin R¹³ steht für Methyl oder Phenyl, n ist gleich 1 und R¹⁰ steht für Wasserstoff.
5. Element nach Anspruch 1, dadurch gekennzeichnet, daß R¹² steht für O und vervollständigt einen 6-gliedrigen Ring, der an den Benzolring ankondensiert ist.
6. Element nach Anspruch 1, dadurch gekennzeichnet, daß R¹² steht für -NR¹³R¹⁴, worin R¹³ und R¹⁴ jeweils stehen für Methyl oder R¹³ steht für Ethyl und R¹⁴ für Phenyl.
7. Element nach Anspruch 1, dadurch gekennzeichnet, daß R¹² steht für -NR¹³R¹⁴, worin R¹³ und R¹⁴ gemeinsam mit dem Stickstoff, an das sie gebunden sind, einen Pyrrolidin- oder Morpholinring bilden.
8. Element nach Anspruch 1, dadurch gekennzeichnet, daß R¹⁵ und R¹⁶ jeweils stehen für -C₃H₇, Q für H, J für -CO-, R¹⁸ für -CH₃ und R¹⁷ für 3-CH₂CO₂C₂H₅; oder R¹⁵ und R¹⁶ stehen jeweils für -C₃H₇, Q steht für H, J steht für -CO-, R¹⁸ steht für -CH₃ und R¹⁷ steht für -CH₂CH=CH₂.
9. Verfahren zur Herstellung eines Farbstoffübertragungsbildes, bei dem ein schwarzes Farbstoff-Donor-element nach Anspruch 1 bildweise erhitzt wird.
10. Zusammenstellung für die thermische Farbstoffübertragung mit:
 - a) einem schwarzen Farbstoff-Donorelement gemäß Anspruch 1, und
 - b) einem Farbstoff-Empfangelement mit einem Träger, auf dem sich eine Farbbild-Empfangsschicht befindet,
 wobei sich das Farbstoff-Empfangelement in einer übergeordneten Position bezüglich des schwarzen Farbstoff-Donorelementes befindet, derart, daß die Farbstoffschicht in Kontakt mit der Farbbild-Empfangsschicht gelangt.

Revendications

1. Élément donneur de colorant noir utilisé pour le transfert de colorant par la chaleur comprenant un support recouvert d'une couche de colorant constituée d'un mélange d'au moins un colorant cyan, magenta et jaune dispersé dans un liant polymère, caractérisé en ce qu'au moins l'un des colorants cyan est représenté par la formule :



- où :
- R¹ et R² représente chacun indépendamment l'hydrogène ; un groupe alkyle substitué ou non de 1 à 10 atomes de carbone ; un groupe cycloalkyle substitué ou non de 5 à 7 atomes de carbone ou un groupe allyle substitué ou non ; à la condition que R¹ et R² ne soient pas tous deux l'hydrogène ;

ou R¹ et R² peuvent être joints pour former, avec l'atome d'azote auquel ils sont rattachés, un hétérocycle de 5 à 7 chaînons ;

ou R¹ et/ou R² peuvent être combinés avec un groupe R³ pour former un hétérocycle de 5 à 7 chaînons ;

5 chaque groupe R³ représente indépendamment l'hydrogène, un groupe alkyle, cycloalkyle, allyle substitué ou non, tel que précédemment décrit pour R¹ et R² ; alcoxy, aryloxy, halogène, thiocyno, acylamino, uréido, alkylsulfonamido, arylsulfonamido, alkylthio, arylthio ou trifluorométhyle ;

ou deux quelconques des groupes R³ peuvent être combinés pour former un hétérocycle ou un carbocycle à 5 ou 6 chaînons ; ou un ou deux des groupes R³ peuvent être combinés avec l'un et/ou l'autre des groupes R¹ et R² pour compléter un cycle de 5 à 7 chaînons ;

m est un entier de 0 à 4 ;

R⁴ représente l'hydrogène ou un groupe attracteur d'électrons ;


R⁵ représente un groupe attracteur d'électrons, un groupe aryle substitué ou non de 6 à 10 atomes de carbone ou un groupe hétéroaryle substitué ou non de 5 à 10 atomes de carbone ;

15 R⁶ et R⁷ représente chacun indépendamment un groupe attracteur d'électrons ; et

R⁶ et R⁷ peuvent être combinés pour former le résidu d'un composé méthylène actif ; ou un composé selon la formule I, où :

R¹ et R² sont C²H⁵, R³ est CH³ et est placé en position méta par rapport au groupe NR¹R², R⁵ est 1-dibenzofuranyle, R⁴, R⁶ et R⁷ sont CN et m est 1 ;

20 et au moins l'un des colorants jaune est représenté par la formule :



30

où :

R⁸, R⁹ et R¹¹ représente chacun indépendamment un groupe alkyle substitué ou non de 1 à 10 atomes de carbone ; un groupe cycloalkyle de 5 à 7 atomes de carbone ; un groupe allyle substitué ou non ;

35 ou un groupe aryle substitué ou non de 6 à 10 atomes de carbone ;

ou R⁸ et R⁹ peuvent être joints pour former, avec l'atome d'azote auquel ils sont rattachés, un hétérocycle à 5 ou 6 chaînons ;

ou R⁸ et/ou R⁹ peuvent être rattachés à l'atome de carbone du cycle benzène en position ortho par rapport à la position de rattachement de l'atome d'azote du cycle anilino pour former un cycle à 5 ou 6 chaînons, formant ainsi un système polycyclique ;

40 R¹⁰ représente l'hydrogène, un groupe alkyle substitué ou non de 1 à 10 atomes de carbone, un groupe cycloalkyle de 5 à 7 atomes de carbone, un groupe allyle substitué ou non, halogène, carbamoyl ou alcoxycarbonyl ;

45 R¹² représente un groupe alcoxy substitué ou non de 1 à 10 atomes de carbone ; un groupe aryloxy substitué ou non de 6 à 10 atomes de carbone ; NHR¹³ ; NR¹³R¹⁴ ou les atomes nécessaires pour compléter un cycle à 6 chaînons condensé sur le cycle benzène ;

R¹³ et R¹⁴ représente chacun indépendamment l'un quelconque des groupes utilisés pour R⁸ ; ou R¹³ et R¹⁴ peuvent être joints pour former, avec l'atome d'azote auquel ils sont rattachés, un hétérocycle à 5 ou 6 chaînons ;


50 n est un entier positif de 1 à 5 ; et

G représente l'hydrogène, un groupe alkyle ou alcoxy substitué ou non de 1 à 10 atomes de carbone ; halogène ; aryloxy ; ou représente les atomes nécessaires pour compléter un cycle à 5 ou 6 chaînons, formant ainsi un système cyclique condensé ou un composé selon la formule II, où :

55 R⁸ est CH₃, R⁹ est CH₃CO₂-CH₂CH₂, R¹⁰ est l'hydrogène, R¹¹ est 2-pyridyle, R¹² est NHC₆H₅ et G est -N=CH-CH=CH- et complète un système cyclique condensé, l'atome d'azote étant en position ortho par rapport au groupe NR⁸R⁹ ;

et au moins l'un des colorants magenta étant représenté par la formule :

III



où :

R¹⁵ représente l'hydrogène ou un groupe alkyle ou allyle substitué ou non de 1 à 10 atomes de carbone ;

Q est R¹⁵, un groupe alcoxy de 1 à 4 atomes de carbone ou pris ensemble avec R¹⁶ représente les atomes nécessaires pour former un hétérocycle à 5 ou 6 chaînons ;

R¹⁶ est un groupe alkyle ou allyle substitué ou non de 1 à 10 atomes de carbone ou peut être combiné avec Q tel que précédemment décrit ;

R¹⁸ est un groupe alkyle substitué ou non de 1 à 10 atomes de carbone ou un groupe aryle substitué ou non de 6 à 10 atomes de carbone ;

J est CO, CO₂, -SO₂- ou CONR¹⁹;

R¹⁷ est un groupe alkyle ou allyle substitué ou non de 1 à 10 atomes de carbone ou un groupe aryle substitué ou non de 6 à 10 atomes de carbone ; et

R¹⁹ est l'hydrogène ou R¹⁸.

2. Élément selon la revendication 1, caractérisé en ce que dans la formule I, R⁴, R⁶ et R⁷ sont cyano et R¹ est C₂H₅, C₂H₄OH, ou n-C₃H₇.

3. Élément selon la revendication 1, caractérisé en ce que dans la formule I, R² est C₂H₅ ou n-C₃H₇, R³ est l'hydrogène, OC₂H₅, CH₃ ou NHCOCH₃ ; et R⁵ est p-C₆H₄Cl, m-C₆H₄NO₂ ou naphthyle.

4. Élément selon la revendication 1, caractérisé en ce que R¹¹ est phényle, R¹² est éthoxy ou NHR¹³ où R¹³ est méthyle ou phényle, n est 1 et R¹⁰ est l'hydrogène.

5. Élément selon la revendication 1, caractérisé en ce que R¹² est O et complète un cycle à 6 chaînons condensé sur le cycle benzène.

6. Élément selon la revendication 1, caractérisé en ce que R¹² est NR¹³R¹⁴, où chaque R¹³ et chaque R¹⁴ est méthyle ou R¹³ est éthyle et R¹⁴ est phényle.

7. Élément selon la revendication 1, caractérisé en ce que R¹² est NR¹³R¹⁴, où R¹³ et R¹⁴ sont joints pour former, avec l'atome d'azote auquel ils sont rattachés, un cycle pyrrolidine ou morpholine.

8. Élément selon la revendication 1, caractérisé en ce que R¹⁵ et R¹⁶ sont chacun C₃H₇, Q est H, J est CO, R¹⁸ est CH₃ et R¹⁷ est 3-CH₂CO₂C₂H₅ ; ou R¹⁵ et R¹⁶ sont chacun C₃H₇, Q est H, J est CO, R¹⁸ est CH₃ et R¹⁷ est CH₂CH=CH₂.

9. Procédé de formation d'une image par transfert de colorant consistant à chauffer conformément à l'image un élément donneur de colorant noir selon la revendication 1.

10. Assemblage pour le transfert de colorant par la chaleur comprenant :

a) un élément donneur de colorant noir selon la revendication 1, et

b) un élément récepteur de colorant comprenant un support recouvert d'une couche réceptrice d'image de colorant, ledit élément récepteur de colorant étant superposé audit élément donneur de colorant noir, de manière que ladite couche de colorant soit au contact de ladite couche réceptrice d'image de colorant.