



- (51) **International Patent Classification:**
C09J 11/00 (2006.01)
- (21) **International Application Number:**
PCT/US2012/037429
- (22) **International Filing Date:**
11 May 2012 (11.05.2012)
- (25) **Filing Language:** English
- (26) **Publication Language:** English
- (30) **Priority Data:**
61/486,379 16 May 2011 (16.05.2011) US
- (71) **Applicant (for all designated States except US):** **AVERY DENNISON CORPORATION** [US/US]; 150 N. Orange Grove Blvd., Pasadena, CA 91103 (US).
- (72) **Inventors; and**
- (75) **Inventors/Applicants (for US only):** **WIBAUX, Anne, Marie** [FR/BE]; Avery Dennison Corporation, 150 N. Orange Grove Blvd., Pasadena, CA 91103 (US). **JOHNSON, Peter** [US/US]; Avery Dennison Corporation, 150 N. Orange Grove Blvd., Pasadena, CA 91103 (US).
- (74) **Agents:** **BEMBENICK, Brian, G.** et al.; Avery Dennison Corporation, 8080 Norton Parkway, 22-d, Mentor, OH 44060 (US).
- (81) **Designated States (unless otherwise indicated, for every kind of national protection available):** AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ,

CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

- (84) **Designated States (unless otherwise indicated, for every kind of regional protection available):** ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))

Published:

- without international search report and to be republished upon receipt of that report (Rule 48.2(g))



WO 2012/158483 A2

(54) **Title:** ADHESIVE CONTAINING MICROPARTICLES

(57) **Abstract:** Methods for forming and incorporating microparticles containing one or more active agents into adhesives are described. The methods involve spray drying a liquid of the one or more active agents and obtaining the active agent in a particulate form. The dry powder is then blended or otherwise incorporated with the adhesive of interest. Also described are various medical products utilizing the adhesive and one or more active agents in microparticle form, and related methods of use.

ADHESIVE CONTAINING MICROPARTICLES

CROSS REFERENCES TO RELATED APPLICATIONS

[0001] The present application claims the benefit of U.S. Provisional Patent Application No. 61/486,379 filed May 16, 2011, which is incorporated herein by reference in its entirety.

FIELD

[0002] The present invention relates to adhesives containing microparticles of one or more active agents, methods for incorporating microparticles of actives into an adhesive, and products using such adhesives.

BACKGROUND

[0003] A wide array of medical products use adhesive for affixing the product onto a user's skin. As will be appreciated, it is desirable to include one or more active agents such as antimicrobial agents in the medical product or adhesive to prevent or at least minimize microbial growth or reproduction along the skin, as such can readily lead to infection and other undesirable conditions.

[0004] Accordingly, artisans have attempted to incorporate a wide range of antimicrobial agents into medical products or materials. Although certain agents have been incorporated into adhesives, effective incorporation into an adhesive composition presents a formidable technical challenge. It is difficult to efficiently disperse such agents within the adhesive. Furthermore, certain antimicrobial agents undergo a loss in efficacy upon incorporation in an adhesive formulation due to the presence of solvents or other components in the adhesive.

[0005] Accordingly, it would be desirable to provide a method for incorporating one or more active agents and particularly an antimicrobial agent into an adhesive formulation such that the agent is effectively dispersed and retains its efficacy when residing in the adhesive.

SUMMARY

[0006] The difficulties and drawbacks associated with previously known compositions, products, and practices are addressed in the present methods, adhesive compositions, products using such compositions and related methods of use.

[0007] In one aspect, the present subject matter provides an adhesive composition comprising an adhesive and microparticles dispersed in the adhesive. The microparticles include a matrix material and at least one active agent.

[0008] As will be realized, the subject matter is capable of other and different embodiments and its several details are capable of modifications in various respects, all without departing from the invention. Accordingly, the description is to be regarded as illustrative and not restrictive.

DETAILED DESCRIPTION OF THE EMBODIMENTS

[0009] The present subject matter generally provides an adhesive composition comprising microparticles that include one or more active agents. The present subject matter also provides various methods relating to the preparation of the adhesives and microparticles, and various products using such adhesives.

Active Agents and Forming Microparticles

[0010] A wide array of one or more active agents can be incorporated in the adhesives described herein. Preferably, the active agents are hydrophilic. Non-limiting examples of preferred active agents include benzocaine, procaine hydrochloride, tetracaine, tetracaine hydrochloride, dibucaine, lidocaine,

lidocaine hydrochloride, bupivacaine, dyclonin, etidocaine, mepivacaine, butamen picrate, dimethisoquin hydrochloride, cyclomethylcaine sulfate, and the like; analgesics and anti-inflammatory agents such as buprenorphin, butophanol tartrate, acetaminophen, fentanyl, mefenamic acid, flutenamic acid, diclofenac, oxyphenbutazone, phenybutazone, ibuprofen, flurbiprofen, naproxen, menthol, methyl salicylate, phenol, salicylic acid, benzyl alcohol, camphor, camphorated metacresol, juniper tar, resorcinol, allyl isothiocyanate, capsaicin, and the like; corticosteroids such as alclometasone dipropionate, amcinocid, hydrocortisone, betamethasone dipropionate, betamethasone valerate, desoximetasone, clobetasol propionate, flurandrenolide, halcinonide, halobetasol, estradiol, testosterone, progesterone, fluticasone, clobetasol, dexamethasone, dexonide, fluocinolone acetonide, flucinonide, medroxyprogesterone, mometasone furoate, triamcinolone, and the like; antibiotics such as bacitracin, bacitracin zinc, chlortetracycline hydrochloride, chlorhexadine gluconate, clindamycin, cliquinol, neomycin sulfate, polymyxin B sulfate, erythromycin, gentamicin, sulfathiazole, sulfacetamide, sulfabenzamide, oxytetracycline hydrochloride, tetracycline, and the like; antimicrobial agents such as benzalkonium chloride, chlorhexidine gluconate, hexachlorophene, mafenide acetate, nitrofurazone, nystatin, acetosulfamine, clortrimazole, povidone-iodine, and the like; antifungal agents such as amphotericin B, butoconazole, cetylpyridinium chloride, chlorxylenol, cyclopirox olamine, clioquinol, clotrimazole, sulconazole nitrate, nystatin, oxyconazole, econazole nitrate, ketoconazole, miconazole nitrate, naftifine hydrochloride, pentamycin, pyrrolinitrin, terbinafine, triacetin, and the like; debriding agents such as deoxyribonuclease, collagenolytic, debridement, fibrinolytic or proteolytic enzymes, papain, papain-urea, and the like; antihistamines such as chlorcyclizine hydrochloride, diphenylhydramine hydrochloride, tripeleminamine hydrochloride, and the like; antiepileptics such as nitrazepam, meprobamate, clonazepam, and the like; coronary vasodilators such as nitroglycerine, dipyridamole, erythritol, tetranitrate, pentaerythritol tetranitrate, propatyinitrate, and the like; dermatological agents such as retinal, retinol, retinoic acid and their derivatives, hydroxyacids,

alphaketoacids, and the like; and other drugs such as benzoyl peroxide, podofilox, masoprocol, nicotine, scopolamine, nitroglycerine, fluorouracil, hydrocolloids, hydroquinone, monobenzene, tretinoin and acyclovir. Preferred drugs for use herein include acne-benzoyl peroxide, Vitamin C, and Vitamin E.

[0011] Although the one or more active agent(s) incorporated in the microparticles are preferably hydrophilic, the subject matter includes the incorporation of one or more active(s) that are hydrophobic, and the incorporation of a combination of hydrophilic agents and hydrophobic agents.

[0012] The microparticles may also comprise one or more matrix binder, or excipient materials. Preferably, the matrix materials are inert or substantially so. Non-limiting examples of matrix materials include binders such as saccharide binders, protein binders, and synthetic polymer binders; fillers such as plant cellulose, dibasic calcium phosphate, vegetable fats and oils, sugar fillers, calcium carbonate, and magnesium stearate; preservatives such as antioxidants, amino acid preservatives, citric acid, sodium citrate, synthetic preservatives such methyl paraben and propyl paraben; sorbents; and other additives.

[0013] Utilizing one or more matrix materials in conjunction with one or more active agent(s) enables a formulator to selectively provide a desired concentration of active in the adhesive composition. Furthermore, in certain applications it may be desired to utilize a relatively high concentration or loading of microparticles in the adhesive. Utilizing a matrix material in the microparticles enables selected or relatively low concentrations of active(s) to be attained.

[0014] A preferred method of forming microparticles of one or more actives is spray drying. Spray drying is a method of producing a dry powder from a liquid or slurry by rapidly drying with a hot gas. This is the preferred method of drying of many thermally sensitive materials such as foods and pharmaceuticals. A consistent particle size distribution is a reason for spray drying some industrial products such as catalysts. Air is typically the heated drying media. However, if the liquid is a flammable solvent or the product is oxygen-sensitive then nitrogen can be used.

[0015] In forming the preferred embodiment microparticles, one or more active agents are placed in a liquid form, if not already in such form. If any matrix materials are used, those are combined with the active(s). Additional amounts of solvent or liquid medium may be added to adjust viscosity as desired. Dispersants and/or surfactants can be added to promote mixing and/or dispersion of the active agent(s) in the solvent or carrier. The liquid is then administered to one or more spray dryers.

[0016] All spray dryers use some type of atomizer or spray nozzle to disperse the liquid or slurry into a controlled drop size spray. The most common of these are rotary nozzles and single fluid pressure swirl nozzles. Alternatively, for some applications two-fluid or ultrasonic nozzles are used. Depending on the process requirements, drop sizes from 10 to 500 micrometers can be achieved with the appropriate nozzle selection. The most common drop sizes are in the 100 to 200 micrometer diameter range. The resulting dry powder is often free-flowing.

[0017] The hot drying gas can be passed as a co-current or counter-current flow to the atomizer direction. A co-current flow enables the particles to have a lower residence time within the system and the particle separator (typically a cyclone device) operates more efficiently. The counter-current flow method enables a greater residence time of the particles in the chamber and usually is paired with a fluidized bed system.

Microparticles and/or Encapsulated Active Agent(s)

[0018] The subject matter also provides additional embodiments in which microparticles of one or more active agents are produced which are then incorporated into an adhesive formulation or adhesive intermediate. The term "microparticles" as used herein refers to particles having an average diameter or span of from about 0.1 microns to about 500 microns, more preferably from about 1 micron to about 200 microns, more preferably from about 5 microns to about 100 microns, and most preferably from about 5 microns to about 50 microns. The preferred embodiment microparticles can be in a variety of different shapes. For example, the microparticles may be spherical, oblong, or in the form of a thin

sheet or flake. The term "span" as used herein refers to the maximum dimension of the particle. Preferably, the microparticles are spherical or generally so.

[0019] The microparticles can be relatively homogenous and exhibit a uniform structure throughout their interior or substantially so. Alternatively, the microparticles can include one or more layers and/or discrete interior regions differing in structure, composition, and/or physical characteristics. A preferred configuration for microparticles containing an active agent is that such microparticles contain an outer layer of a polymer or other material that dissolves or otherwise degrades upon exposure to saline, other bodily fluids, or conditions of basic pH, such as a pH greater than 7. The preferred material for the outer layer is generally referred to herein as a water sensitive material and is described in greater detail herein. These preferred microparticles may in other embodiments, include a core which is preferably hydrophilic. Upon incorporation of the preferred microparticles containing an active agent in an adhesive or adhesive intermediate and subsequent use of the adhesive in a medical product, a delayed release of one or more active agents occurs upon exposure to saline or body fluids. That is, once the outer layer of dissolvable or degradable material is removed, an interior layer or region of the microparticles containing the active agent(s) is exposed, thereby enabling migration of the one or more active agents from the microparticles. This strategy provides a convenient technique for establishing long lasting delivery of active agents.

[0020] Although not wishing to bound to any particular theory, it is believed that the inclusion of a hydrophilic core in the preferred embodiment microparticles tends to promote incorporation of one or more active agents, and particularly those which are highly hydrophilic. The core of such microparticles can comprise one or multiple active agents. The outer layer or shell in microparticles having a core and shell construction can be hydrophilic or hydrophobic.

[0021] As noted, in certain embodiments in which the active agent(s) are formed into microparticles, it may be preferred to provide one or more outer layers of a water sensitive polymer

that dissolves or is otherwise removed upon exposure to certain agents. Non-limiting examples of such polymers include starch; materials based on amylase; polysaccharides such as cellulose and derivatives, chitin, chitosan, dextran, alginate; proteins such as casein, albumin, gelatin; and synthetic polymers such as polyvinyl pyrrolidone, polyethylene oxide, polyvinyl alcohol. Combinations of these materials can be used. For certain charged antimicrobials, a charged polymer can be used to assist in the delivery and/or retention of the antimicrobial.

[0022] For embodiments in which one or more active agents are incorporated within the interior of microparticles, the release of the active agent can generally be controlled by the following parameters - the diameter or span of the microparticles, the proportion of water sensitive polymer as compared to the amount of the active agent, the nature of the water sensitive polymer and particularly its dissolution rate, and the chemistry of the adhesive and its sensitivity to moisture, water, or other agents.

[0023] The various versions of the preferred embodiment microparticles comprising one or more active agents can be prepared in a variety of techniques. A preferred technique is to use a spray drying operation as described herein to form the noted microparticles. One or more outer layers and preferably layer(s) of a water sensitive material can be applied or otherwise deposited upon the outer surface of the microparticles by techniques known in the art.

[0024] In a preferred aspect, microparticles of one or more active agents consisting of a core embedded into a water sensitive polymer are produced by a spray drying process. Upon incorporation in an adhesive matrix, solid microparticles will release the one or more active agents over a relatively long period of time.

Incorporation of Microparticles in Adhesive

[0025] As previously noted, for embodiments in which the active agent(s) is in the form of coated microparticles exhibiting a delayed release characteristic, the microparticles can be incorporated directly into an adhesive formulation by blending and/or mixing.

[0026] The adhesive containing the microparticles of active agent(s) are then incorporated in a product or used as desired. For example, conventional coating and drying operations can be performed to form an adhesive layer on a medical product. Representative non-limiting examples of such medical products include surgical goods such as incise films, and device fixation products; wound care products; and ostomy pouches.

[0027] In certain embodiments, the adhesive can be covered with a carrier, preferably a polyurethane film or any alternative material.

Adhesives

[0028] The methods of the present subject matter can be used to incorporate one or more active agents into a wide array of adhesives, and preferably a solvent based adhesive or a hot melt adhesive. Non limiting examples of suitable types of adhesives include acrylic adhesives, rubber adhesives, silicone adhesives, polyurethane adhesives, and variants and combinations thereof. Generally, the resulting microparticles of active agent(s) can be incorporated into nearly any non-aqueous based adhesive. Preferably, the adhesive is a solvent based adhesive. More preferably, the adhesive is a solvent based acrylic adhesive.

[0029] The present subject matter also includes combining microparticles of one or more active agent(s) with an adhesive component such as an adhesive ingredient and/or an adhesive premix. This strategy provides an alternative approach for subsequent formation of an adhesive comprising actives in the form of delayed release microparticles.

[0030] For embodiments in which the one or more active agents are hydrophilic and in a microparticle form, another advantage results when the microparticles are incorporated into a hydrophobic adhesive matrix. Due to their hydrophilic properties, such active agents will easily release from a hydrophobic adhesive matrix.

[0031] The preferred embodiment adhesive compositions include the microparticles as described herein in a proportion of from about 0.01% to about 50% or more, by weight, based upon the total weight of the adhesive. Preferably, the microparticles constitute from about 0.1% to about 40% by weight, and most preferably from about 1% to about 30% by weight of the adhesive composition.

Additional Additives

[0032] One or more additional additives can be incorporated into the adhesive and active microparticle formulation. Preferably the additional additives include medicinal compounds. Such medicinal compounds include, but are not limited to, antimicrobials, antibiotics, antifungal agents, antiviral agents, antithrombogenic agents, anesthetics, anti-inflammatory agents, analgesics, anticancer agents, vasodilation substances, wound healing agents, angiogenic agents, angiostatic agents, immune boosting agents, growth factors, and other biological agents. Suitable antimicrobial agents include, but are not limited to, biguanide compounds; triclosan; penicillins; tetracyclines; aminoglycosides, such as gentamicin and Tobramycin™; polymyxins; rifampicins; bacitracins; erythromycins; vancomycins; neomycins; chloramphenicols; miconazole; quinolones, such as oxolinic acid, norfloxacin, nalidixic acid, pefloxacin, enoxacin, and ciprofloxacin; sulfonamides; nonoxynol 9; fusidic acid; cephalosporins; and combinations of such compounds and similar compounds. The additional antimicrobial compounds provide for enhanced antimicrobial activity.

[0033] The present subject matter is believed to provide a significant advance in the art. For example, use of the preferred embodiment adhesive composition with delayed release microparticles can provide extended release of one or more active agents over relatively long periods of time, such as over a time period of at least 3 days, or at least 5 days, or at least 7 days for example. Furthermore, the preferred embodiment adhesive formulations can be used to administer two or more otherwise incompatible actives in the same formulation. Thus, one population of microparticles containing a first active and another population of microparticles containing a second active which is incompatible with

the first active can be provided. In addition, use of the preferred embodiment adhesives as described herein can be formulated to protect an active agent from oxidation and/or degradation during an adhesive coating process. Moreover, the composition can be tailored to trigger release of the one or more active agents upon occurrence of certain conditions such as for example existence of a particular pH, moisture level, and/or presence of certain enzymes.

[0034] Many other benefits will no doubt become apparent from future application and development of this technology.

[0035] All patents, published applications, and articles noted herein are hereby incorporated by reference in their entirety.

[0036] It will be understood that any one or more feature or component of one embodiment described herein can be combined with one or more other features or components of another embodiment. Thus, the present subject matter includes any and all combinations of components or features of the embodiments described herein.

[0037] As described hereinabove, the present subject matter solves many problems associated with previous type products, adhesives and practices. However, it will be appreciated that various changes in the details, materials and arrangements of components and operations, which have been herein described and illustrated in order to explain the nature of the subject matter, may be made by those skilled in the art without departing from the principle and scope of the subject matter, as expressed in the appended claims.

Claims

What is claimed is:

1. An adhesive composition comprising:
an adhesive; and
microparticles dispersed in the adhesive, the microparticles including a matrix material and at least one active agent.
2. The adhesive of claim 1 wherein the adhesive is selected from the group consisting of acrylic adhesives, rubber adhesives, silicone adhesives, polyurethane adhesives, and combinations thereof.
3. The adhesive of any one of claims 1-2 wherein the adhesive is one of a solvent based adhesive and a hot melt adhesive.
4. The adhesive of any one of claims 1-3 wherein the microparticles have an average span of from about 0.1 microns to about 500 microns.
5. The adhesive of any one of claims 1-3 wherein the microparticles have an average span of from about 1 micron to about 200 microns.
6. The adhesive of any one of claims 1-3 wherein the microparticles have an average span of from about 5 microns to about 100 microns.

7. The adhesive of any one of claims 1-3 wherein the microparticles have an average span of from about 5 microns to about 50 microns.

8. The adhesive of any one of claims 1-7 wherein the active agent is selected from the group consisting of pain reducing agents, analgesics and anti-inflammatory agents, corticosteroids, antibiotics, antimicrobial agents, antifungal agents, debriding agents, antihistamines, antiepileptics, coronary vasodilators, dermatologicals, ancillary drugs, and combinations thereof.

9. The adhesive of claim 8 wherein the active agent is a pain reducing agent.

10. The adhesive of claim 9 wherein the pain reducing agent is selected from the group consisting of pain reducing agents such as benzocaine, procaine hydrochloride, tetracaine, tetracaine hydrochloride, dibucaine, lidocaine, lidocaine hydrochloride, bupivacaine, dyclonin, etidocaine, mepivacaine, butamen picrate, dimethisoquin hydrochloride, cyclomethylcaine sulfate, and combinations thereof.

11. The adhesive of claim 8 wherein the active agent is an analgesic and anti-inflammatory agent.

12. The adhesive of claim 11 wherein the analgesic and anti-inflammatory agent is selected from the group consisting of buprenorphin, butophanol tartrate, acetaminophen, fentanyl, mefenamic acid, flutenamic acid, diclofenac, oxyphenbutazone, phenybutazone, ibuprofen, flurbiprofen, naproxen, menthol, methyl salicylate, phenol, salicylic acid, benzyl alcohol, camphor, camphorated metacresol, juniper tar, resorcinol, allyl isothiocyanate, capsaicin, and combinations thereof.

13. The adhesive of claim 8 wherein the active agent is a corticosteroid.
14. The adhesive of claim 13 wherein the corticosteroid is selected from the group consisting of alclometasone dipropionate, amcinocide, hydrocortisone, betamethasone dipropionate, betamethasone valerate, desoximetasone, clobetasol propionate, flurandrenolide, halcinonide, halobetasol, estradiol, testosterone, progesterone, fluticasone, clobetasol, dexamethasone, dexonide, flucinolone acetonide, flucinonide, medroxyprogesterone, mometasone furoate, triamcinolone, and combination thereof.
15. The adhesive of claim 8 wherein the active agent is an antibiotic.
16. The adhesive of claim 15 wherein the antibiotic is selected from the group consisting of bacitracin, bacitracin zinc, chlortetracycline hydrochloride, chlorhexadine gluconate, clindamycin, cliquinol, neomycin sulfate, polymyxin B sulfate, erythromycin, gentamicin, sulfathiazole, sulfacetamide, sulfabenzamide, oxytetracycline hydrochloride, tetracycline, and combinations thereof.
17. The adhesive of claim 8 wherein the active agent is an antimicrobial agent.
18. The adhesive of claim 17 wherein the antimicrobial agent is selected from the group consisting of benzalkonium chloride, chlorhexidine gluconate, hexachlorophene, mafenide acetate, nitrofurazone, nystatin, acetosulfamine, clortrimazole, povidone-iodine, and combinations thereof.
19. The adhesive of claim 8 wherein the active agent is an antifungal agent.

20. The adhesive of claim 19 wherein the antifungal agent is selected from the group consisting of amphotericin B, butoconazole, cetylpyridinium chloride, chlorxylenol, cyclopirox olamine, clioquinol, clotrimazole, sulconazole nitrate, nystatin, oxyconazole, econazole nitrate, ketoconazole, miconazole nitrate, naftifine hydrochloride, pentamycin, pyrrolinitrin, terbinafine, triacetin, and combinations thereof.

21. The adhesive of claim 8 wherein the active agent is a debriding agent.

22. The adhesive of claim 21 wherein the debriding agent is selected from the group consisting of deoxyribonuclease, collagenolytic, debridement, fibrinolytic or proteolytic enzymes, papain, papain-urea, and combinations thereof.

23. The adhesive of claim 8 wherein the active agent is an antihistamine.

24. The adhesive of claim 23 wherein the antihistamine is selected from the group consisting of chlorcyclizine hydrochloride, diphenylhydramine hydrochloride, tripelemamine hydrochloride, and combinations thereof.

25. The adhesive of claim 8 wherein the active agent is an antiepileptic.

26. The adhesive of claim 25 wherein the antiepileptic is selected from the group consisting of nitrazepam, meprobamate, clonazepam, and combinations thereof.

27. The adhesive of claim 8 wherein the active agent is a coronary vasodilator.
28. The adhesive of claim 27 wherein the coronary vasodilator is selected from the group consisting of nitroglycerine, dipyridamole, erythritol, tetranitrate, pentaerythritol tetranitrate, propatyinitrate, and combinations thereof.
29. The adhesive of claim 8 wherein the active agent is a dermatological agent.
30. The adhesive of claim 29 wherein the dermatological agent is selected from the group consisting of dermatologicals such as retinal, retinol, retinoic acid and their derivatives, hydroxyacids, alphaketoacids, and combinations thereof.
31. The adhesive of claim 8 wherein the active agent is an ancillary drug.
32. The adhesive of claim 31 wherein the ancillary drug is selected from the group consisting of benzoyl peroxide, podofilox, masoprocol, nicotine, scopolamine, nitroglycerine, fluorouracil, hydrocolloids, hydroquinone, monobenzene, tretinoin and acyclovir, Vitamin C, Vitamin E, and combinations thereof.
33. The adhesive of any one of claims 1-32 wherein the matrix material is selected from the group consisting of binders, fillers, preservatives, sorbents, other additives, and combinations thereof.
34. The adhesive of claim 33 wherein the matrix material is a binder.

35. The adhesive of claim 34 wherein the binder is selected from the group consisting of saccharide binders, protein binders, synthetic polymer binders, and combinations thereof.

36. The adhesive of claim 33 wherein the matrix material is a filler.

37. The adhesive of claim 36 wherein the filler is selected from the group consisting of plant cellulose, dibasic calcium phosphate, vegetable fats and oils, sugar fillers, calcium carbonate, magnesium stearate, and combinations thereof.

38. The adhesive of claim 33 wherein the matrix material is a preservative.

39. The adhesive of claim 38 wherein the preservative is selected from the group consisting of antioxidants, amino acid preservatives, citric acid, sodium citrate, synthetic preservatives, and combinations thereof.

40. The adhesive of any one of claims 1-39 wherein at least one active agent is hydrophilic.

41. The adhesive of any one of claims 1-40 wherein the microparticles further include an outer layer of a water sensitive material that dissolves or otherwise degrades upon exposure to at least one of (i) saline, (ii) other bodily fluids, and basic pH.

42. The adhesive of claim 41 wherein the water sensitive material includes an agent selected from the group consisting of starch, materials based on amylase, polysaccharides, proteins, synthetic polymers, and combinations thereof.

43. The adhesive of claim 42 wherein the water sensitive material is starch.
44. The adhesive of claim 42 wherein the water sensitive material is a material based on amylase.
45. The adhesive of claim 42 wherein the water sensitive material is a polysaccharide.
46. The adhesive of claim 45 wherein the polysaccharide is selected from the group consisting of cellulose and its derivatives, chitin, chitosan, dextran, alginate, and combinations thereof.
47. The adhesive of claim 42 wherein the water sensitive material is a protein.
48. The adhesive of claim 47 wherein the protein is selected from the group consisting of casein, albumin, gelatine, and combinations thereof.
49. The adhesive of claim 42 wherein the water sensitive material is a synthetic polymer.
50. The adhesive of claim 49 wherein the synthetic polymer is selected from the group consisting of polyvinyl pyrrolidone, polyethylene oxide, polyvinyl alcohol, and combinations thereof.
51. The adhesive composition of any one of claims 1-50 wherein the microparticles constitute from about 0.01% to about 50% by weight of the total weight of the composition.

52. The adhesive composition of claim 51 wherein the microparticles constitute from about 0.1% to about 40% by weight of the total weight of the composition.

53. The adhesive composition of claim 52 wherein the microparticles constitute from about 1% to about 30% by weight of the total weight of the composition.