



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C09J 163/04	A1	(11) International Publication Number: WO 93/22392 (43) International Publication Date: 11 November 1993 (11.11.93)
(21) International Application Number: PCT/SE93/00338 (22) International Filing Date: 19 April 1993 (19.04.93) (30) Priority data: 24 April 1992 (24.04.92) SE (71) Applicant (for all designated States except US): CASCO NOBEL AB [SE/SE]; Box 11538, S-100 61 Stockholm (SE). (72) Inventors; and (75) Inventors/Applicants (for US only) : BONINI, Maria [SE/SE]; Hackspettsvägen 6, S-134 42 Gustavsberg (SE). JANACKOVIC, Anna [SE/SE]; Sickla Strand 78, S-131 34 Nacka (SE). NASLI-BAKIR, Ben [SE/SE]; Sickla Strand 49, S-131 34 Nacka (SE).		(74) Agent: SCHÖLD, Zaid; Nobel Industries AB, Patent Department, Box 11554, S-100 61 Stockholm (SE). (81) Designated States: CA, FI, JP, NO, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: ADHESIVE COMPOSITION BASED ON NOVOLAC (57) Abstract An adhesive composition based on resorcinol novolac or resorcinol-phenolic novolac contains 35-75 % by weight of novolac, less than 25 % by weight of water, and 10-40 % by weight of an aliphatic divalent, trivalent or tetravalent alcohol. The adhesive composition may also contain up to 20 % by weight of filler, based on the amount of novolac, water and alcohol. In a method for preparing the adhesive composition based on resorcinol novolac or resorcinol-phenolic novolac, the novolac is produced by conventional condensation, whereupon an aliphatic divalent, trivalent or tetravalent alcohol is added and water in the novolac is distilled off, resulting in an adhesive composition as defined above. Alternatively, the amount of water can be reduced in the condensation of the novolac to be replaced with an aliphatic divalent, trivalent or tetravalent alcohol.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NL	Netherlands
BE	Belgium	GN	Guinea	NO	Norway
BF	Burkina Faso	GR	Greece	NZ	New Zealand
BG	Bulgaria	HU	Hungary	PL	Poland
BJ	Benin	IE	Ireland	PT	Portugal
BR	Brazil	IT	Italy	RO	Romania
CA	Canada	JP	Japan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SK	Slovak Republic
CI	Côte d'Ivoire	LJ	Liechtenstein	SN	Senegal
CM	Cameroon	LK	Sri Lanka	SU	Soviet Union
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	MC	Monaco	TG	Togo
DE	Germany	MG	Madagascar	UA	Ukraine
DK	Denmark	ML	Mali	US	United States of America
ES	Spain	MN	Mongolia	VN	Viet Nam
FI	Finland				

ADHESIVE COMPOSITION BASED ON NOVOLAC

The present invention relates to a new adhesive composition based on resorcinol novolac or resorcinol-phenolic novolac. More specifically, the invention concerns a novolac-based adhesive composition containing an aliphatic divalent, trivalent or tetravalent alcohol. The adhesive composition mixed with a hardener has low emission of formaldehyde.

Resorcinol resin and resorcinol-phenolic resin adhesives are commonly used in the wood industry, inter alia because of their satisfactory ageing stability, as well as good water and weather resistance of the glue line. Also, they may readily be cured at room temperature.

Generally, resorcinol resins and resorcinol-phenolic resins are used in the form of novolacs, i.e. precondensates of resorcinol/phenol with formaldehyde, in which the ratio of formaldehyde to resorcinol/phenol is less than 1. The precondensates are cured by further addition of formaldehyde. Since resorcinol is very reactive, a considerable amount of the formaldehyde is added to the resin as curing agent. As a rule, this is done by the user when about to use the resin. It is common that the novolacs are cured with pulverulent curing agents based on paraformaldehyde.

It is well-known that the use of formaldehyde-based adhesives involves the problem of odorous formaldehyde emissions. When the pulverulent paraformaldehyde is dissolved in the precondensate, formaldehyde is released and the adhesive smells. SE 408,063 discloses an attempt to solve this problem by having a curing agent in the form of a suspension of paraformaldehyde in a non-volatile suspending agent. This curing agent does not cause any smell problems when fresh, but when added to the adhesive, the paraformaldehyde reacts with the water in the adhesive mixture, and formaldehyde is released, making the adhesive smell. In attempts to reduce the amount of water in the novolac, viscosity has increased to an unacceptable level, making it impossible to spread the adhesive.

An object of the present invention therefore is to produce an adhesive based on resorcinol novolac or resorcinol-phenolic novolac and having a low emission of formaldehyde after the addition of the formaldehyde based hardener. Another object of the invention is to produce
5 such an adhesive having satisfactory application and gluing properties.

These objects are achieved by an adhesive composition, as defined in the appended claims, which is based on
10 resorcinol novolac or resorcinol-phenolic novolac and is characterized in that it contains 35-75% by weight of novolac, less than 25% by weight of water, and 10-40% by weight of an aliphatic divalent, trivalent or tetravalent alcohol. It was surprisingly found that by reducing the
15 water content in the novolac and replacing it with a divalent, trivalent or tetravalent alcohol, one obtained an adhesive composition which, upon the addition of pulverulent paraformaldehyde, gave off much less formaldehyde smell. The alcohols instead bind the formaldehyde in a
20 larger molecule which does not evaporate and thus does not give off any smell. This molecule is decomposed only at the rate of reaction of the formaldehyde with the resin. Since a divalent, trivalent or tetravalent alcohol is added instead of water, the resulting adhesive will have a
25 viscosity which makes it suitable for spreading. Despite the fact that so much of the water was replaced with the hydroxy compound, the gluing properties of the resin were not impaired, which is highly surprising.

Suitable aliphatic divalent, trivalent or tetravalent
30 alcohols include compounds of the type $\text{HO-R}_1\text{-OH}$ or $\text{HO-R}_1\text{-O-R}_2\text{-OH}$, where R_1 , R_2 are $(\text{CH}_2)_n$, n being ≤ 5 , such as ethylene glycol, diethylene glycol, 1,3-propanediol, 1,3-butanediol, 1,4-butanediol, and various kinds of trivalent and tetravalent alcohols, for instance glycerol and pentaerythritol. The aliphatic divalent, trivalent or tetravalent alcohol should be added in such an amount that the
35 resulting adhesive composition contains 10-40% by weight thereof, preferably 15-30% by weight. Further, the adhesive

composition should contain less than 25% by weight of water, preferably less than 20% by weight. Most preferred, the amount of water lies in the range of 5-15% by weight. The amount of novolac in the adhesive composition should be 5 35-75% by weight, preferably 45-60% by weight. Together, the novolac, the divalent, trivalent or tetravalent alcohol and the water make up 100% by weight of the adhesive composition.

The novolac used in the adhesive composition according to the invention can be produced in conventional manner. The molar ratio of formaldehyde to resorcinol, or of formaldehyde to resorcinol phenol, should be less than 0.9:1. When a mixture of resorcinol phenol is used, the amount of phenol may be up to 80 mole %, preferably 40-60 15 mole %, based on the total amount of resorcinol and phenol. Conveniently, the pH of the novolac is adjusted to a value in the range of 6.8-8.7. This results in a good balance between formaldehyde emission and curing speed.

The adhesive composition according to the invention 20 may also contain such conventional fillers as olive-stone meal and almond-shell meal or the like in contents of up to $\leq$ 20% by weight, based on the amount of novolac, alcohol and water.

The adhesive composition can be produced by preparing 25 a novolac by conventional condensation. Then, the desired amount of divalent, trivalent or tetravalent alcohol is added, and water in the novolac is distilled off. Alternatively, the binder can be prepared by reducing the amount of water as early as in the novolac condensation, e.g. by 30 using raw materials of such a low water content that there is no need of any distillation. If so, the alcohol is suitably added at an early stage of the condensation. The viscosity of the resulting binder lies in the range of 300-10,000 mPas, based on a pure resin solution. The 35 adhesive composition is then cured in known manner by adding formaldehyde in an amount giving the binder the desired final molar ratio. Suitably, the final molar ratio in resorcinol/resorcinol-phenolic resins of formaldehyde to

resorcinol/resorcinol phenol lies in the range of 0.75-1.7, preferably 0.9-1.2. The formaldehyde is preferably added in the form of a pulverulent curing agent based on paraformaldehyde.

- 5 The invention will now be described in more detail below with the aid of the following Examples, in which the figures are in per cent by weight and parts by weight, unless otherwise stated.

Example 1

- 10 Here, 677 g of phenol, 540 g of formaldehyde (40%), 216 g of water and 21.6 g of NaOH (45%) were added. pH was adjusted to 7.50-8.0.

- The mixture was heated to 65°C and maintained at this temperature for 1 h. Then, the mixture was heated to boiling
15 and allowed to boil for 1.5 h.

- The mixture was cooled to 75°C, and 842 g of water, 1584 g of resorcinol and 432 g of formaldehyde (40%) were added. pH was measured, and adjusted with acid to 7.3-7.6 (under cooling). Then, the mixture was again heated to 65°C and
20 kept at this temperature for 1 h, whereupon it was heated to boiling and condensed to a viscosity of 200 mPas at 25°C, measured according to the Höppler method.

This batch was divided into two parts, in the following referred to as Example 1A and Example 1B.

- 25 In Example 1A, pH was adjusted to 7.4, and in Example 1B, pH was adjusted to 8.5. Then, 39 parts by weight and 24 parts by weight, respectively, of ethylene glycol was added to 100 parts by weight of resin in Examples 1A and 1B, and the corresponding amount of water was distilled
30 off. A portion of 1A and a portion of 1B were kept without any glycol added.

The following 6 resin compositions were obtained. The resin content was 56%.

	pH	water	ethylene glycol
Example 1A	7.4	5%	39%
	"	20%	24%
	"	44%	0%
Example 1B	8.5	5%	39%
	"	20%	24%
	"	44%	0%

These six resins were brought to a temperature of 20°C, whereupon paraformaldehyde was added as curing agent (100 parts by weight of resin + 6 parts by weight of paraformaldehyde). Immediately after the addition, 8 g was weighed in a dish having a height of 30 mm and a diameter of 50 mm. The dish was then immediately placed under a hood, and air was drawn past the adhesive mixture into a formaldehyde measuring instrument of the type Interscan, air flow 1.1 l/min.

The following emission values for formaldehyde were measured. These values are converted into % of the resin that only contains water as solvent.

		Water	5	20	44
	pH	Ethylene glycol	39	24	0
Example 1A	7.4		1.2	7.6	100
Example 1B	8.5		10.9	58	100

Example 2

Here, 658 g of phenol, 525 g of formaldehyde (40%), 210 g of water and 21 g of NaOH (45%) were added. pH was adjusted to 7.50-8.0. The mixture was heated to 65°C and kept at this temperature for 1 h. Then, the mixture was heated to boiling and allowed to boil for 1.5 h. The mixture was cooled to 75°C, and 518 g of water, 1925 g of resorcinol and 578 g of formaldehyde (40%) were added. pH was measured and adjusted with acid to 7.7-8.0. Then, the mixture was again heated to 65°C and kept at this temperature for 1 h. The mixture was thereafter heated to boiling, and condensed to a viscosity of 200 mPas at 25°C,

measured according to the Höppler method.

The final pH was adjusted to 7.8.

After the pH adjustment to 7.8, the batch was divided into three portions. To portion 2A was added ethylene glycol in an amount of 35 parts by weight and 22 parts by weight, respectively, per 100 parts by weight of resin. To portion 2B was added 1,4-butanediol in an amount of 35 parts by weight and 22 parts by weight, respectively, per 100 parts by weight of resin. The corresponding amount of water was distilled off. Portion 3 was kept unchanged.

Then, the temperature was adjusted and paraformaldehyde was added exactly as in Example 1. Measurements of formaldehyde emission, performed exactly as in Example 1, yielded the following results. The values are converted into % of the resin that only contains water as solvent.

Water %	5	18	5	18	40
Ethylene glycol %	35	22	0	0	0
1,4-butanediol %	0	0	35	22	0
	5.7	18	12.6	31	100

This Example shows that both ethylene glycol and 1,4-butanediol act as solvents in low-emission adhesives.

25 Example 3

In this Example, adhesive formulations according to Example 1, i.e. containing 100 parts by weight of resin and 6 parts by weight of paraformaldehyde, were used for block gluings under the following conditions.

30 Kind of wood: Pine

Dimensions: 250 x 55 x 22 mm

Glue spread: 300 g/m²

Assembly time closed (TA): about 8 min and about 30 min

Press temperature: 20C

35 Pressure: 8 bar

Press time: 18 h.

Two glue lines were made for each variable. In the Table below, the results are indicated as % fibre rupture

7

after cutting up the glue lines immediately after the process. Each reported value represents the mean value of two lines.

5	<u>Solvent System</u>			<u>Fibre Rupture %</u>	
	<u>Water %</u>	<u>Ethylene glycol %</u>	<u>pH</u>	<u>TA 8 min</u>	<u>TA 30 min</u>
	5	39	7.4	20	20
	5	39	8.5	65	85
	20	24	7.4	30	40
10	20	24	8.5	80	75
	44	0	7.4	5	5
	44	0	8.5	75	45

Obviously, the fibre rupture is as satisfactory when some of the water has been replaced with ethylene glycol.

Example 4

In this Example, the gluing operations were performed as in Example 3, but the resin had the same pH (7.8) and different solvents were used. The same resin as in Example 2 was used as adhesive.

25	<u>Solvent</u>			<u>Fibre Rupture %</u>	
	<u>Water %</u>	<u>Ethylene glycol %</u>	<u>1,4-butane-diol %</u>	<u>TA 8 min</u>	<u>TA 30 min</u>
	5	35	0	40	50
	5	0	35	20	15
	18	22	0	35	70
	18	0	22	10	20
30	40	0	0	10	30

Example 5

Also in this Example, the gluing operations were performed as in Examples 3 and 4. The same adhesive and mixtures of curing agents were used as in Examples 3 and 4. Instead of cutting up the glue lines immediately after pressing, a delamination test was made according to American Standard ASTM D1101 - 59 well-known in the art. Prior

to delamination, the samples were conditioned for 1 week at 20g and 65% RF. Two delamination cycles were run. After measuring the delamination, the glue lines were cut up for an assessment of the fibre rupture.

- 5 The results indicated below represent mean values of two glue lines.

10	Solvent			Delamina-		Fibre rupture		
				tion in %		%		
	H2O	Ethylene	1,4-butane-	TA	TA	TA	TA	
	%	glycol %	diol %	pH	8 min	30 min	8 min	30 min
	5	39	0	7.4	0	0	80	25
	20	24	0	7.4	32	14	75	45
15	44	0	0	7.4	3.6	0	40	75
	5	39	0	8.5	0	0	80	80
	20	24	0	8.5	0	0	65	90
	44	0	0	8.5	0	0	95	90
	5	0	35	7.8	18	0	20	70
20	18	0	22	7.8	0	45	50	45
	40	0	0	7.8	27	60	10	40
	5	35	0	7.8	0	0	75	80
	18	22	0	7.8	0	0	65	80
	40	0	0	7.8	9	0	35	80
25								

As appears from these results, the glue lines are roughly equally good when water is replaced with glycol.

CLAIMS

1. An adhesive composition based on resorcinol novolac or resorcinol-phenolic novolac, characterised in that it contains 35-75% by weight of novolac, less than 25% by weight of water, and 10-40% by weight of an aliphatic divalent, trivalent or tetravalent alcohol.
2. An adhesive composition as claimed in claim 1, characterised in that the novolac has a molar ratio of formaldehyde to resorcinol or resorcinol phenol of less than 0.9:1.
3. An adhesive composition as claimed in claim 1, characterised in that the proportion of phenol is up to 80 mole % of the total amount of resorcinol and phenol.
4. An adhesive composition as claimed in claim 3, characterised in that the proportion of phenol is 40-60 mole % of the total amount of resorcinol and phenol.
5. An adhesive composition as claimed in claim 1, characterised in that the viscosity is in the range of 300-10,000 mPas.
6. An adhesive composition as claimed in claim 1, characterised in that it further contains up to 20% by weight of filler, based on the amount of novolac, water and alcohol.
7. An adhesive composition as claimed in claim 1, characterised in that the divalent alcohol used is ethylene glycol, 1,3-propanediol or 1,4-butanediol.
8. A method for preparing an adhesive composition based on resorcinol novolac or resorcinol-phenolic novolac, characterised by producing a novolac by conventional condensation, and then adding an aliphatic divalent, trivalent or tetravalent alcohol and distilling off water in the novolac, such that the adhesive composition contains 35-75% by weight of novolac, less than 25% by weight of water, and 10-40% by weight of an aliphatic divalent, trivalent or tetravalent alcohol.

9. A method for preparing an adhesive composition based on resorcinol novolac or resorcinol-phenolic novolac, characterised by reducing the amount of water in the condensation of the novolac and replacing it with an aliphatic divalent, trivalent or tetravalent alcohol, the resulting adhesive composition containing 35-75% by weight of novolac, less than 25% by weight of water, and 10-40% by weight of an aliphatic divalent, trivalent or tetravalent alcohol.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 93/00338

A. CLASSIFICATION OF SUBJECT MATTER

IPC5: C09J 163/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC5: C09J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI, CLAIMS

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	SE, B, 408063 (AB CASCO), 14 May 1979 (14.05.79), page 2, line 12 - page 3, line 5 -----	1-9

☐ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

14 July 1993

Date of mailing of the international search report

20-07-1993

Name and mailing address of the ISA/

Swedish Patent Office

Box 5055, S-102 42 STOCKHOLM

Facsimile No. +46 8 666 02 86

Authorized officer

Anita Skeppstedt

Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

Information on patent family members

28/05/93

International application No.

PCT/SE 93/00338

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
SE-B- 408063	14/05/79	SE-A- 7514289	18/06/77