




(86) Date de dépôt PCT/PCT Filing Date: 2018/12/10
(87) Date publication PCT/PCT Publication Date: 2019/06/20
(45) Date de délivrance/Issue Date: 2022/07/05
(85) Entrée phase nationale/National Entry: 2020/06/05
(86) N° demande PCT/PCT Application No.: JP 2018/045357
(87) N° publication PCT/PCT Publication No.: 2019/117096
(30) Priorité/Priority: 2017/12/12 (JP2017-238063)

(51) Cl.Int./Int.Cl. *C22C 38/00* (2006.01),
C22C 38/60 (2006.01), *H01F 1/147* (2006.01),
C21D 8/12 (2006.01)
(72) Inventeurs/Inventors:
ZAIZEN, YOSHIAKI, JP;
ODA, YOSHIHIKO, JP;
HIRATANI, TATSUHIKO, JP
(73) Propriétaire/Owner:
JFE STEEL CORPORATION, JP
(74) Agent: ROBIC

(54) Titre : TOLE D'ACIER ELECTROMAGNETIQUE MULTICOUCHE
(54) Title: MULTILAYER ELECTRICAL STEEL SHEET



(57) Abrégé/Abstract:

Provided is a multilayer electrical steel sheet having both low high-frequency iron loss and high magnetic flux density. The multilayer electrical steel sheet has an inner layer and surface layers provided on both sides of the inner layer, in which the surface layers and the inner layer have a predetermined chemical composition, the multilayer electrical steel sheet having: ΔSi of 0.5 mass% to 4.0 mass%, ΔSi being defined as a difference in Si content between the surface layers and the inner layer; ΔAl of 0.05 mass% or less, ΔAl being defined as an absolute value of a difference in Al content between the surface layers and the inner layer; a ratio of t_s to t represented by t_s/t of from 0.10 to 0.70, where t_s denotes a total thickness of the surface layers and t denotes a sheet thickness of the multilayer electric steel sheet; a magnetic flux density at a magnetic field intensity of 1000 A/m represented by B_{10} of 1.3 T or more; and a ratio of B_1 to B_{10} represented by B_1/B_{10} of 0.45 or more, where B_1 denotes a magnetic flux density at a magnetic field intensity of 100 Alm; and an iron loss at a frequency of 1 kHz and a largest magnetic flux density of 1.0 T represented by $W_{10/1k}$ in W/kg and the sheet thickness t in mm satisfy the following formula (1): $W_{10/1k} \leq 15 + 140 \times t(1)$.

ABSTRACT

Provided is a multilayer electrical steel sheet having both low
 high-frequency iron loss and high magnetic flux density. The multilayer
 electrical steel sheet has an inner layer and surface layers provided on both
 5 sides of the inner layer, in which the surface layers and the inner layer have a
 predetermined chemical composition, the multilayer electrical steel sheet
 having: ΔSi of 0.5 mass% to 4.0 mass%, ΔSi being defined as a difference in
 Si content between the surface layers and the inner layer; ΔAl of 0.05 mass%
 or less, ΔAl being defined as an absolute value of a difference in Al content
 10 between the surface layers and the inner layer; a ratio of t_1 to t represented by
 t_1/t of from 0.10 to 0.70, where t_1 denotes a total thickness of the surface
 layers and t denotes a sheet thickness of the multilayer electric steel sheet; a
 magnetic flux density at a magnetic field intensity of 1000 A/m represented by
 B_{10} of 1.3 T or more; and a ratio of B_1 to B_{10} represented by B_1/B_{10} of 0.45 or
 15 more, where B_1 denotes a magnetic flux density at a magnetic field intensity
 of 100 A/m; and an iron loss at a frequency of 1 kHz and a largest magnetic
 flux density of 1.0 T represented by $W_{10/1k}$ in W/kg and the sheet thickness t
 in mm satisfy the following formula (1): $W_{10/1k} \leq 15 + 140 \times t$ (1).

MULTILAYER ELECTRICAL STEEL SHEET

TECHNICAL FIELD

5 [0001] This disclosure relates to a multilayer electrical steel sheet, and in particular, a multilayer electrical steel sheet having both low high-frequency iron loss and high magnetic flux density.

BACKGROUND

10 [0002] Motors for hybrid electric vehicles and cleaners are driven in a high-frequency region such as 400 Hz to 2 kHz from the viewpoint of reducing the size and achieving high efficiency. Therefore, for non-oriented electrical steel sheets used for core materials of such motors, electrical steel sheets having low high-frequency iron loss and high magnetic flux density are demanded.

15 [0003] To reduce the high-frequency iron loss, it is effective to increase specific resistance. Therefore, high-Si steel having increased specific resistance through the increase in the Si content has been developed. However, since Si is a non-magnetic element, the increase in the Si content leads to lower saturation magnetization.

20 [0004] Therefore, as means for achieving both high-frequency iron loss reduction and high magnetic flux density, gradient Si magnetic materials having controlled Si concentration gradient in a thickness direction of electrical steel sheets have been developed. For example, JP H11-293422 A (PTL 1) proposes an electrical steel sheet having a Si concentration gradient
25 in a thickness direction in which the Si concentration in a surface of the steel sheet is higher than that of a mid-thickness part of the steel sheet. Specifically, the electrical steel sheet has a mid-thickness part with a Si concentration of 3.4 % or more while having, on its both surfaces, surface layers with a Si concentration of 5 mass% to 8 mass%. Further, the thickness
30 of the surface layers is 10 % or more of the sheet thickness.

CITATION LIST

Patent Literature

[0005] PTL 1: JP H11-293422 A

SUMMARY

(Technical Problem)

[0006] However, when conventional gradient Si magnetic materials as proposed in PTL 1 are used as the iron core materials of electric appliances whose highest frequency is several kHz, the hysteresis loss is high and thus the iron loss is not sufficiently reduced.

[0007] It could thus be helpful to provide a multilayer electrical steel sheet having both low high-frequency iron loss and high magnetic flux density.

(Solution to Problem)

[0008] The inventors made intensive studies of a method of solving the problem, and as a result, found that in order to reduce high-frequency iron loss, it is important to suitably control the difference in Si concentration between surface layers and an inner layer of a steel sheet and add at least one selected from the group consisting of P, Sn, and Sb. This disclosure is based on the above finding and has the following primary features.

[0009] 1. A multilayer electrical steel sheet comprising an inner layer and surface layers provided on both sides of the inner layer, wherein

each of the surface layers has a chemical composition containing (or preferably consisting of), in mass%,

Si: 2.5 % to 6.0 % and

at least one selected from the group consisting of P: 0.01 % to 0.1 %, Sn: 0.001 % to 0.1 % and Sb: 0.001 % to 0.1 %, with the balance being Fe and inevitable impurities,

the inner layer has a chemical composition containing (or preferably consisting of), in mass%,

Si: 1.5 % to 4.0 % and

at least one selected from the group consisting of P: 0.01 % to 0.1 %, Sn: 0.001 % to 0.1 % and Sb: 0.001 % to 0.1 %, with the balance being Fe and inevitable impurities, and

the multilayer electrical steel sheet has:

ΔSi of 0.5 mass% to 4.0 mass%, ΔSi being defined as a difference between a Si content in each of the surface layers $[\text{Si}]_1$ and a Si content in the inner layer $[\text{Si}]_0$ represented by $[\text{Si}]_1 - [\text{Si}]_0$;

ΔAl of 0.05 mass% or less, ΔAl being defined as an absolute value of a difference between a content of Al contained as an inevitable impurity in each of the surface layers $[\text{Al}]_1$ and a content of Al contained as an inevitable impurity in the inner layer $[\text{Al}]_0$ represented by $|[\text{Al}]_1 - [\text{Al}]_0|$;

a ratio of t_1 to t represented by t_1/t of from 0.10 to 0.70, where t_1 denotes a total thickness of the surface layers and t denotes a sheet thickness of the multilayer electric steel sheet;

B_{10} of 1.3 T or more, where B_{10} denotes a magnetic flux density at a magnetic field intensity of 1000 A/m;

a ratio of B_1 to B_{10} represented by B_1/B_{10} of 0.45 or more, where B_1 denotes a magnetic flux density at a magnetic field intensity of 100 A/m; and

an iron loss at a frequency of 1 kHz and a largest magnetic flux density of 1.0 T represented by $W_{10/1k}$ in W/kg and the sheet thickness t in mm satisfy the following formula (1):

$$W_{10/1k} \leq 15 + 140 \times t \quad (1).$$

[0010] 2. The multilayer electrical steel sheet according to 1., wherein at least one of the chemical composition of each of the surface layers or the chemical composition of the inner layer further contains, in mass%, Mo: 0.001 % to 0.1 %.

(Advantageous Effect)

[0011] According to this disclosure, it is possible to provide a multilayer electrical steel sheet having both low high-frequency iron loss and high magnetic flux density.

BRIEF DESCRIPTION OF THE DRAWINGS

[0012] In the accompanying drawings:

FIG. 1 is a schematic diagram illustrating the structure of a multilayer electrical steel sheet according to one of the embodiments of this disclosure;

FIGS. 2A and 2B are schematic diagrams illustrating examples of the Si content profile in a thickness direction of the multilayer electrical steel sheet;

FIG. 3 is a graph illustrating a correlation between the difference in Si content between surface layers and an inner layer (ΔSi) and the total iron loss




FIG. 4 is a graph illustrating a correlation between the difference in Si content between the surface layers and the inner layer (ΔSi) and the magnetic flux density ratio (B_1/B_{10}); and

10

[0013] Detailed description is given below. The following description merely presents examples of preferred embodiments of this disclosure, and this disclosure is not limited to these embodiments.

15

20

25

30

the total sheet thickness of the steel sheet is defined as a "surface layer" and a part having a lower Si content than the average is defined as an "inner layer". As described below, when the multilayer electrical steel sheet is manufactured by cladding two types of steel materials having different Si contents (high Si material and low Si material) with each other, typically, a part made of the high Si material is a surface layer and a part made of the low Si material is an inner layer. In this case, the Si content in each of the surface layers is substantially constant and the Si content in the inner layer is also substantially constant.

10 **[0017] [Chemical Composition]**

First, the chemical compositions of each of the surface layers and the inner layer are described. When components are expressed in "%", this refers to "mass%" unless otherwise stated.

[0018] [Chemical Composition of Surface Layer]

15 First, the chemical composition of each of the surface layers will be described. In this disclosure, both the first surface layer provided on one surface of the multilayer electrical steel sheet and the second surface layer provided on the other surface of the multilayer electrical steel sheet have the chemical composition described below. The chemical composition of the first surface layer and the chemical composition of the second surface layer may be typically the same but may be different from each other. Further, the content of an element in each of the surface layers indicates an average content of the element in each surface layer.

[0019] Si: 2.5 % to 6.0 %

25 Si is an element having an effect of increasing the electrical resistance of the steel sheet and reducing eddy current loss. When the Si content in each of the surface layers ($[Si]_1$) is less than 2.5 %, the eddy current loss cannot be effectively reduced. Therefore, the Si content in each of the surface layers is set to 2.5 % or more, preferably 3.0 % or more, and more preferably more than 3.5 %. On the other hand, when the Si content in each of the surface layers is more than 6.0 %, the magnetic flux density decreases due to lower saturation magnetization. Therefore, the Si content in each of the surface layers is set to 6.0 % or less, preferably less than 5.5 %, and more preferably 5.0 % or less. As described above, a Si content of 2.5 % to 6.0 %

in each of the surface layers means that the average Si content in the first surface layer is 2.5 % to 6.0 % and the average Si content in the second surface layer is 2.5 % to 6.0 %. The average Si content in the first surface layer may be the same with or different from the average Si content in the second surface layer. The same definition applies to other elements.

[0020] The chemical composition in each of the surface layers further contains at least one selected from the group consisting of P: 0.01 % to 0.1 %, Sn: 0.001 % to 0.1 %, and Sb: 0.001 % to 0.1 %.

[0021] P: 0.01 % to 0.1 %

The addition of P greatly improves the texture, which makes it possible to improve the magnetic flux density and lower the hysteresis loss. When P is added, to obtain this effect, the P content is set to 0.01 % or more. On the other hand, a P content exceeding 0.1 % causes saturation of the effect and additionally, lowers the manufacturability and increases the cost.

Therefore, the P content is set to 0.1 % or less.

[0022] Sn: 0.001 % to 0.1 %

As with P, the addition of Sn greatly improves the texture, which makes it possible to improve the magnetic flux density and lower the hysteresis loss. When Sn is added, to obtain this effect, the Sn content is set to 0.001 % or more. On the other hand, a Sn content exceeding 0.1 % causes saturation of the effect and additionally, lowers the manufacturability and increases the cost. Therefore, the Sn content is set to 0.1 % or less.

[0023] Sb: 0.001 % to 0.1 %

As with P and Sn, the addition of Sb greatly improves the texture, which makes it possible to improve the magnetic flux density and lower the hysteresis loss. When Sb is added, to obtain this effect, the Sb content is set to 0.001 % or more. On the other hand, a Sb content exceeding 0.1 % causes saturation of the effect and additionally, lowers the manufacturability and increases the cost. Therefore, the Sb content is set to 0.1 % or less.

[0024] In one embodiment of this disclosure, each of the surface layers has a chemical composition containing the above elements with the balance being Fe and inevitable impurities.

[0025] Examples of elements which may be contained as the inevitable impurities in the multilayer electrical steel sheet include Al. When the Al

content is limited to 0.1 % or less, the magnetic flux density can be further improved. Therefore, the Al content is preferably limited to 0.1 % or less.

[0026] Further, in another embodiment of this disclosure, the chemical composition of each of the surface layers may further contain Mo in an amount described below.

[0027] Mo: 0.001 % to 0.1 %

Mo is an element having an effect of suppressing the oxidation of the surface layers of the steel sheet to thereby further reduce iron loss. When Mo is added, to obtain this effect, the Mo content is set to 0.001 % or more. On the other hand, when the Mo content exceeds 0.1 %, carbides are formed, leading to an increase in iron loss. Therefore, the Mo content is set to 0.1 % or less.

[0028] Each of the surface layers according to one embodiment of this disclosure may have a chemical composition containing, in mass%,

Si: 2.5 % to 6.0 %, at least one selected from the group consisting of P: 0.01 % to 0.1 %, Sn: 0.001 % to 0.1 %, and Sb: 0.001 % to 0.1 %, and optionally, Mo: 0.001 % to 0.1 %, with the balance being Fe and inevitable impurities.

[0029] Further, each of the surface layers according to another embodiment of this disclosure may have a chemical composition containing, in mass%,

Si: 2.5 % to 6.0 %, at least one selected from the group consisting of P: 0.01 % to 0.1 %, Sn: 0.001 % to 0.1 %, and Sb: 0.001 % to 0.1 %, and optionally, Mo: 0.001 % to 0.1 %, with the balance being Fe and inevitable impurities.

[0030] [Chemical Composition of Inner Layer]

Next, the chemical composition of the inner layer will be described. The content of an element in the inner layer indicates an average content of the element in the inner surface.

[0031] Si: 1.5 % to 5.0 %

A Si content in the inner layer ([Si]₀) of less than 1.5 % causes an increase in high-frequency iron loss. Therefore, the Si content of the inner layer is set to 1.5 % or more. On the other hand, a Si content in the inner

layer of more than 5.0 % causes cracking of a motor core in punching the core. Therefore, the Si content in the inner layer is set to 5.0 % or less. The Si content in the inner layer is preferably set to 4.0 % or less and more preferably 2.8 % or less.

- 5 **[0032]** The chemical composition in the inner layer further contains at least one selected from the group consisting of P: 0.01 % to 0.1 %, Sn: 0.001 % to 0.1 %, and Sb: 0.001 % to 0.1 %.

[0033] P: 0.01 % to 0.1 %

 The addition of P greatly improves the texture, which makes it possible to improve the magnetic flux density and lower the hysteresis loss. When P is added, to obtain this effect, the P content is set to 0.01 % or more. On the other hand, a P content exceeding 0.1 % causes saturation of the effect and additionally, lowers the manufacturability and increases the cost. Therefore, the P content is set to 0.1 % or less.

- 15 **[0034]** Sn: 0.001 % to 0.1 %

 As with P, the addition of Sn greatly improves the texture, which makes it possible to improve the magnetic flux density and lower the hysteresis loss. When Sn is added, to obtain this effect, the Sn content is set to 0.001 % or more. On the other hand, a Sn content exceeding 0.1 % causes saturation of the effect and additionally, lowers the manufacturability and increases the cost. Therefore, the Sn content is set to 0.1 % or less.

[0035] Sb: 0.001 % to 0.1 %

 As with P and Sn, the addition of Sb greatly improves the texture, which makes it possible to improve the magnetic flux density and lower the hysteresis loss. When Sb is added, to obtain this effect, the Sb content is set to 0.001 % or more. On the other hand, a Sb content exceeding 0.1 % causes saturation of the effect and additionally, lowers the manufacturability and increases the cost. Therefore, the Sb content is set to 0.1 % or less.

[0036] In one embodiment of this disclosure, the inner layer has a chemical composition containing the above elements with the balance being Fe and inevitable impurities.

[0037] Examples of elements which can be contained as the inevitable impurities in the multilayer electrical steel sheet include Al. When the Al content is limited to 0.1 % or less, the magnetic flux density can be further

improved. Therefore, the Al content is preferably limited to 0.1 % or less.

[0038] Further, in another embodiment of this disclosure, the chemical composition of the inner layer may further contain Mo in an amount described below.

5 **[0039]** Mo: 0.001 % to 0.1 %

As described above, Mo is an element having an effect of suppressing the oxidation of the surface layers of the steel sheet to thereby further reduce iron loss. To prevent the oxidation, it suffices that Mo exists in the surface layers of the steel sheet, but Mo may be added to the inner layer. For example, when the multilayer electrical steel sheet is manufactured by a siliconizing treatment as described below, in order to add Mo to the surface layers, it suffices to add Mo to the entire steel sheet and in this case, Mo also exists in the inner layer. Further, even the multilayer electrical steel sheet is manufactured by a method other than the siliconizing treatment, Mo may be added to the inner layer. From the viewpoint of manufacture, when Mo is added to the inner layer, the Mo content in the inner layer is set to 0.001 % or more as with the Mo content in each of the surface layers. On the other hand, when the Mo content exceeds 0.1 %, carbides are formed, leading to an increase in iron loss. Therefore, the Mo content is set to 0.1 % or less.

20 **[0040]** The inner layer according to one embodiment of this disclosure may have a chemical composition containing, in mass%,

Si: 1.5 % to 5.0 %,

at least one selected from the group consisting of P: 0.01 % to 0.1 %, Sn: 0.001 % to 0.1 %, and Sb: 0.001 % to 0.1 %, and

25 optionally, Mo: 0.001 % to 0.1 %, with the balance being Fe and inevitable impurities.

[0041] Further, the inner layer according to another embodiment of this disclosure may have a chemical composition containing, in mass%,

Si: 1.5 % to 5.0 %,

30 at least one selected from the group consisting of P: 0.01 % to 0.1 %, Sn: 0.001 % to 0.1 %, and Sb: 0.001 % to 0.1 %, and

optionally, Mo: 0.001 % to 0.1 %, with the balance being Fe and inevitable impurities.

[0042] [Difference in Si Content]

To examine the effect of the difference in Si content between the surface layers and the inner layer (ΔSi) on the magnetic properties, multilayer electrical steel sheets having different ΔSi were manufactured by the following procedures and the magnetic properties were evaluated.

5 [0043] First, steel for the surface layers was attached to both surfaces of steel for the inner layer so that the ratio of the thickness of the surface layers to the sheet thickness (total thickness) of the multilayer electrical steel sheet was 0.30 and subjected to hot rolling to obtain a hot-rolled steel sheet. Each of the steel for the surface layers and the steel for the inner layer was melted so
10 as to obtain a desired chemical composition to prepare an ingot. The Si content in the inner layer $[\text{Si}]_0$ was set to 2.0 % and the Si content in each of the surface layers $[\text{Si}]_1$ was changed in the range of 2.1 % to 6.5 %. The Al content was set to 0.001 % and the Sn content was set to 0.04 % in both the surface layers and the inner layer. The chemical compositions of each of the
15 surface layers and the inner layer had the balance of Fe and inevitable impurities. The surface layers on both surfaces had the same chemical composition.

[0044] After the hot rolling, the hot-rolled steel sheet was subjected to hot-rolled sheet annealing of $950\text{ }^{\circ}\text{C} \times 30\text{ s}$, followed by cold rolling to obtain
20 a cold-rolled steel sheet having a sheet thickness of 0.20 mm. Subsequently, the cold-rolled steel sheet was subjected to final annealing of $1000\text{ }^{\circ}\text{C} \times 30\text{ s}$ to obtain a multilayer electrical steel sheet.

[0045] A test piece having a width of 30 mm and a length of 180 mm was collected from the obtained multilayer electrical steel sheet and subjected to
25 the Epstein test to evaluate the magnetic properties. In the Epstein test, an L-direction test piece collected so that the length direction of the test piece was parallel to the rolling direction (L direction) and a C-direction test piece collected so that the length direction of the test piece was parallel to the direction orthogonal to the rolling direction (C direction) were used in equal
30 amounts to measure the averages of the magnetic properties in the L direction and the C direction.

[0046] FIG. 3 indicates a correlation between ΔSi (mass%) and the total iron loss at 1.0 T and 1 kHz represented by $W_{10/1k}$ (W/kg), ΔSi being defined as a difference in Si content between each of the surface layers and the inner layer

($[\text{Si}]_1 - [\text{Si}]_0$). Further, FIG. 4 indicates a correlation between ΔSi and the magnetic flux density ratio. The “magnetic flux density ratio” indicates the ratio of B_1 to B_{10} represented by B_1/B_{10} , where B_1 denotes a magnetic flux density at a magnetic field intensity of 100 A/m and B_{10} denotes a magnetic flux density at a magnetic field intensity of 1000 A/m.

[0047] As can be seen from the results illustrated in FIG. 3, when ΔSi is 0.5 mass% or more and 4.0 mass% or less, the iron loss can be reduced to low. Further, as can be seen from the results illustrated in FIG. 4, when ΔSi exceeds 4.0 mass%, the magnetic flux density ratio is suddenly lowered. This is believed to be because of the following reasons. Specifically, when the Si content in each of the surface layers is higher than that in the inner layer, the magnetic permeability of each of the surface layers is higher than that of the inner layer. As a result, magnetic fluxes concentrate to the surface layer, lowering the eddy current loss. However, when ΔSi is excessively large, the difference in lattice constant and the difference in magnetostriction between each of the surface layers and the inner layer become large. As a result, since the stress applied during the magnetization of the steel sheet is increased, the hysteresis loss increases and the magnetic flux density decreases in low and middle magnetic field ranges.

[0048] For the above reasons, in this disclosure, ΔSi defined as a difference between the Si content in each of the surface layers and the Si content in the inner layer ($[\text{Si}]_1 - [\text{Si}]_0$) is set to 0.5 mass% to 4.0 mass%.

[0049] [Difference in Al content]

Although the magnetostriction in the surface layers and the inner layer is strongly influenced by the Si content, it is also influenced by the texture. For example, since the formation of the texture greatly varies during final annealing when the amount of impurities is different between the surface layers and the inner layer, the difference in magnetostriction between the surface layers and the inner layer becomes large. In particular, Al is an element which greatly influences the formation of the texture. Therefore, ΔAl is set to 0.05 mass% or less, where ΔAl is defined as an absolute value of the difference between the content of Al contained as an inevitable impurity in each of the surface layers $[\text{Al}]_1$ and the content of Al contained as an inevitable impurity in the inner layer $[\text{Al}]_0$ ($|[\text{Al}]_1 - [\text{Al}]_0|$). On the other hand,

no lower limit is placed on ΔAl , but ΔAl may be 0.

[0050] [Multilayer ratio]

Next, to examine the effect of the ratio of the total thickness of the surface layers t_1 to the sheet thickness of the multilayer electrical steel sheet t (t_1/t) (hereinafter, also referred to as “multilayer ratio”) on the magnetic properties, multilayer electrical steel sheets having different multilayer ratios were manufactured by the following procedures and the magnetic properties were evaluated. The “total thickness of the surface layers” indicates the sum of the thicknesses of the surface layers provided on both sides.

[0051] First, steel for the surface layers and steel for the inner layer were attached with each other so as to obtain a multilayer ratio of 0.02 to 0.80 and subjected to hot rolling to obtain a hot-rolled steel sheet. Each of the steel for the surface layers and the steel for the inner layer was melted so as to obtain a desired chemical composition to prepare an ingot. The Si content in each of the surface layers $[Si]_0$ was set to 4.5 % and the Si content in the inner layer $[Si]_1$ was set to 2.0 %. Further, both in each of the surface layers and in the inner layer, the P content was set to 0.05 %, the Sn content was set to 0.05 %, the Sb content and the content of Al contained as an inevitable impurity were each set to 0.001 %. The balance was Fe and inevitable impurities. The surface layers on both surfaces had the same chemical composition.

[0052] After the hot rolling, the hot-rolled steel sheet was subjected to hot-rolled sheet annealing of $950\text{ }^{\circ}\text{C} \times 30\text{ s}$, followed by cold rolling to obtain a cold-rolled steel sheet having a sheet thickness of 0.10 mm. Subsequently, the cold-rolled sheet was subjected to final annealing of $1000\text{ }^{\circ}\text{C} \times 30\text{ s}$ to obtain a multilayer electrical steel sheet.

[0053] FIG. 5 illustrates a correlation between the multilayer ratio (t_1/t) and the total iron loss ($W_{10/1k}$). From the result, it is found that when the multilayer ratio is from 0.10 to 0.70, the iron loss is greatly reduced. The reduction in the iron loss is believed to be because of the following reasons. First, since the ratio of the surface layers which have high resistance is low when the multilayer ratio is less than 0.10, the eddy current which concentrates on the surface layers cannot be effectively reduced. On the other hand, since the difference in magnetic permeability between the surface

layers and the inner layer is small when the multilayer ratio is more than 0.70, the magnetic flux penetrates to the inner surface and the eddy current loss also occurs from the inner surface. Therefore, the iron loss can be reduced by setting the multilayer ratio in a range of from 0.10 to 0.70. For the above
 5 reasons, the multilayer ratio (t_1/t) in this disclosure is set to 0.10 to 0.70.

[0054] [Sheet Thickness]

The sheet thickness of the multilayer electrical steel sheet t is not particularly limited and t may be any value. However, when the multilayer electrical steel sheet is excessively thin, it is difficult to perform cold rolling
 10 and annealing in manufacturing the multilayer electrical steel sheet, which may cause an increase in costs. Therefore, from the viewpoint of reducing the manufacturing cost, t is preferably set to 0.03 mm or more. On the other hand, when t is set to 0.3 mm or less, the eddy current loss can be further reduced, and as a result, the total iron loss can be further lowered. Therefore,
 15 t is preferably set to 0.3 mm or less.

[0055] [Magnetic Flux Density]

B_{10} : 1.3 T or more

The multilayer electrical steel sheet of this disclosure has high magnetic flux density. Specifically, the magnetic flux density at a magnetic
 20 field intensity of 1000 A/m represented by B_{10} is 1.3 T or more. Increasing the magnetic flux density in the electrical steel sheet is effective for improving the torque of a motor manufactured using the electrical steel sheet. Further, when the magnetic flux density is high, the same torque can be obtained with low current, and as a result, copper loss can be reduced.

25 **[0056] B_1/B_{10} : 0.45 or more**

The ratio of B_1 to B_{10} represented by B_1/B_{10} is set to 0.45 or more, where B_1 denotes a magnetic flux density at a magnetic field intensity of 100 A/m. By increasing B_1/B_{10} , a good rise can be obtained in a magnetization
 30 curve in a designed magnetic flux density region used in a small motor. Since this reduces a motor current required to obtain a predetermined torque, the copper loss is reduced and thus, the motor efficiency can be improved.

[0057] [Iron Loss]

In this disclosure, the iron loss at a frequency of 1 kHz and a largest magnetic flux density of 1.0 T (total iron loss) $W_{10/1k}$ (W/kg) and the sheet

thickness t in mm need to satisfy the following formula (1):

$$W_{10/1k} \leq 15 + 140 \times t \quad (1).$$

[0058] The reason is that when the relation of the formula (1) is not satisfied, an extremely large amount of heat is generated in stator cores, significantly lowering the motor efficiency. Since the iron loss depends on the sheet thickness, the upper limit of the iron loss is defined in the formula (1), considering the effect of the sheet thickness.

[0059] In the electrical steel sheet, when the magnetic flux density is increased, the iron loss is typically increased. Therefore, common motor cores are designed so that the magnetic flux density is about 1.0 T. On the other hand, the multilayer electrical steel sheet of this disclosure achieves both high magnetic flux density and low iron loss which are conflicting properties by controlling the chemical compositions of the surface layers and the inner layer and the multilayer ratio of the steel sheet as described above.

[0060] [Manufacturing Method]

The method of manufacturing the multilayer electrical steel sheet of this disclosure is not particularly limited and may be any method. Examples of the manufacturing method include a method of cladding steel raw materials having different Si contents. The chemical compositions of the steel raw materials can be adjusted by, for example, blowing materials having different compositions in a converter to obtain molten steel and subjecting the molten steel to degassing treatment.

[0061] The cladding method is not particularly limited. However, for example, a steel slab for the surface layers and a steel slab for the inner layer each having the chemical composition described above may be prepared and the steel slab for the surface layers may be attached, with a thickness such that the eventual multilayer ratio is a desired value, to both surfaces of the steel slab for the inner layer, followed by rolling. The rolling may be, for example, at least one selected from the group consisting of hot rolling, warm rolling, and cold rolling. In general, the combination of hot rolling and subsequent warm rolling or the combination of hot rolling and subsequent cold rolling is preferable. After the hot rolling, hot-rolled sheet annealing is preferably performed. Further, the warm rolling and cold rolling may be performed twice or more with intermediate annealing performed therebetween. The

rolling finish temperature and the coiling temperature during the hot rolling are not particularly limited and may be determined according to the conventional method. After the rolling, final annealing is performed. The multilayer electrical steel sheet obtained by cladding the steel materials having different Si contents has the Si content profile as illustrated in, for example, FIG. 2B.

[0062] As another manufacturing method, siliconizing treatment may be used. When the siliconizing treatment is used, by subjecting a steel sheet having a constant Si content in the thickness direction to siliconizing treatment, the Si content in the surface layers on both sides of the steel sheet can be increased. The method of the siliconizing treatment is not particularly limited and may be any method. For example, a method in which Si is deposited on the surfaces of the steel sheet by a chemical vapor deposition method (CVD method) and subsequently heat treatment is performed to diffuse Si to the inside of the steel sheet can be used. The Si contents of the surface layers and the inner layer can be controlled by adjusting the amount of Si deposited by the CVD method and heat treatment conditions. The multilayer electrical steel sheet obtained by the siliconizing treatment has the Si content profile as illustrated in, for example, FIG. 2A.

EXAMPLES

[0063] To determine the effect of this disclosure, multilayer electrical steel sheets were manufactured in the following procedures and their magnetic properties were evaluated.

[0064] First, for each multilayer electrical steel sheet, two types of steel slabs for a surface layer and an inner layer having the chemical compositions listed in Table 1 were prepared. Next, the steel slab for a surface layer was stacked on both sides of the steel slab for an inner layer. The outer periphery of the stacked steel slabs was welded. Therefore, the surface layers on both sides had the same chemical composition. The chemical compositions of the steel slabs were adjusted by blowing the steel slabs in a converter and subsequently subjecting them to degassing treatment. The chemical compositions were maintained in the resulting multilayer electrical steel sheet.

[0065] Next, the stacked steel slabs were heated at 1130 °C for 1 hr, and

subsequently hot rolled to obtain a hot-rolled steel sheet having a sheet thickness of up to 2.0 mm. The hot rolling finish temperature in the hot rolling was set to 800 °C. Then, the hot-rolled steel sheet was coiled at a coiling temperature of 610 °C, and then subjected to hot-rolled sheet annealing of 940 °C × 30 s. Subsequently, the hot-rolled steel sheet was subjected to pickling and cold rolling, followed by annealing at a final annealing temperature listed in Table 1 to obtain a multilayer electrical steel sheet. The sheet thickness of the resulting multilayer electrical steel sheet and a ratio of a total thickness of the surface layers t_1 to t (i.e., a multilayer ratio) were as listed in Table 2.

[0066] For comparison, normal electrical steel sheets without cladding were subjected to the same test (Nos. 1 and 2). These electrical steel sheets as comparative examples had the same chemical composition in the surface layers and the inner layer.

[0067] Further, the multilayer electrical steel sheet of No. 33 was manufactured by a siliconizing method. Specifically, a cold-rolled steel sheet having a Si content of 2.0 % and a sheet thickness of 0.2 mm was subjected to siliconizing treatment at 1200 °C. The average of Si contents over the total sheet thickness of the steel sheet was calculated. A part having a higher Si concentration than the average was defined as a surface layer and a part having a lower Si concentration than the average was defined as an inner layer. The Si content in each of the surface layers was an average of Si contents in the surface layers. Further, listed as the magnetostriction measurements of the surface layers and the inner layer are the magnetostriction measurements of a steel sheet having the same Si content as the average of Si contents and the same chemical composition as that of the multilayer electrical steel sheet of No. 33 except for the Si content.

[0068] (Magnetic Properties)

Next, each of the obtained multilayer electrical steel sheets was measured for its magnetic properties. The measurement of the magnetic properties was performed using a 25 cm Epstein frame according to JIS C 2550-1. As the magnetic properties, the iron loss at 1.0 T and 1 kHz represented by $W_{10/1k}$ (W/kg), the magnetic flux density at a magnetic field intensity of 1000 A/m represented by B_{10} , and the magnetic flux density at a

magnetic field intensity of 100 A/m represented by B_1 were measured. The measurement results are as listed in Table 2.

[0069] As can be seen from the results of Tables 1 and 2, the multilayer electrical steel sheets of our examples satisfying the conditions of this disclosure had excellent properties, i.e., low high-frequency iron loss and high magnetic flux density. Therefore, the multilayer electrical steel sheets according to this disclosure can be extremely suitably used as motor cores of hybrid electric vehicles, electric vehicles, cleaners, high speed power generators, air compressors, machine tools, and the like which are driven at high frequencies, and further as core materials of transformers, reactors, and the like.

[0070]

Table 1

No.	Chemical composition (mass%)													
	Surface layer*						Inner layer*						Δ Si	Δ Al
	Si	Al	P	Sn	Sb	Mo	Si	Al	P	Sn	Sb	Mo		
1	2.5	0.0010	0.05	0.0010	0.0010	0.0010	2.5	0.0010	0.05	0.0010	0.0010	0.0010	<u>0.00</u>	0.0000
2	5.5	0.0010	0.01	0.0400	0.0010	0.0010	<u>5.5</u>	0.0010	0.01	0.0400	0.0010	0.0010	<u>0.00</u>	0.0000
3	4.0	0.0010	0.04	0.0010	0.0010	0.0010	2.4	0.0005	0.04	0.0010	0.0010	-	1.60	0.0005
4	4.2	0.0010	0.04	0.0400	0.0010	0.0010	2.0	0.0010	0.04	0.0400	0.0010	-	2.20	0.0000
5	4.7	0.0010	0.01	0.0600	0.0200	0.0010	2.5	0.0010	0.01	0.0600	0.0200	-	2.20	0.0000
6	6.0	0.0020	0.03	0.0010	0.0010	0.0010	1.7	0.0010	0.03	0.0010	0.0010	0.0010	<u>4.30</u>	0.0010
7	4.0	0.0025	0.07	0.0300	0.0010	0.0010	<u>1.2</u>	0.0010	0.07	0.0300	0.0010	0.0010	2.80	0.0015
8	4.0	0.0030	-	-	-	0.0010	2.0	0.0030	-	-	-	0.0010	2.00	0.0000
9	4.3	0.0010	0.06	0.0400	0.0010	0.0010	1.9	0.0010	0.06	0.0400	0.0010	0.0010	2.40	0.0000
10	4.3	0.0010	0.01	0.0400	0.0300	0.0010	1.9	0.0010	0.01	0.0400	0.0300	0.0010	2.40	0.0000
11	4.3	0.0010	0.01	0.0010	0.0800	0.0010	1.9	0.0010	0.01	0.0010	0.0800	0.0010	2.40	0.0000
12	4.3	0.0010	0.05	0.0400	0.0010	0.0100	1.9	0.0010	0.05	0.0400	0.0010	0.0100	2.40	0.0000
13	4.5	0.0010	0.03	0.0300	0.0010	0.0010	2.1	0.0010	0.03	0.0300	0.0010	-	2.40	0.0000
14	4.5	0.0010	0.03	0.0300	0.0010	0.0010	2.1	0.0010	0.03	0.0300	0.0010	-	2.40	0.0000
15	4.5	0.0010	0.03	0.0300	0.0010	0.0010	2.1	0.0010	0.03	0.0300	0.0010	-	2.40	0.0000
16	4.5	0.0010	0.03	0.0300	0.0010	0.0010	2.1	0.0010	0.03	0.0300	0.0010	0.0010	2.40	0.0000
17	4.2	0.0024	0.04	0.0400	0.0010	0.0030	2.2	0.0010	0.04	0.0400	0.0010	0.0030	2.00	0.0014
18	4.2	0.0600	0.04	0.0400	0.0010	0.0030	2.2	0.0010	0.04	0.0400	0.0010	0.0030	2.00	<u>0.0590</u>
19	4.1	0.0010	0.05	0.0400	0.0010	0.0010	2.5	0.0020	0.05	0.0400	0.0010	-	1.60	0.0010
20	4.1	0.0010	0.01	0.0600	0.0010	0.0010	2.5	0.0020	0.01	0.0600	0.0010	-	1.60	0.0010
21	4.1	0.0010	0.05	0.0400	0.0010	0.0010	2.5	0.0020	0.05	0.0400	0.0010	-	1.60	0.0010
22	4.1	0.0010	0.05	0.0010	0.0400	0.0010	2.5	0.0020	0.05	0.0010	0.0400	-	1.60	0.0010
23	4.3	0.0010	0.01	0.0400	0.0300	0.0010	1.9	0.0020	0.01	0.0400	0.0300	-	2.40	0.0010
24	4.3	0.0010	0.01	0.0600	0.0010	0.0010	1.9	0.0020	0.01	0.0600	0.0010	-	2.40	0.0010
25	4.3	0.0010	0.01	0.0010	0.0700	0.0010	1.9	0.0020	0.01	0.0010	0.0700	-	2.40	0.0010
26	4.3	0.0010	0.01	0.0400	0.0400	0.0010	1.9	0.0020	0.01	0.0400	0.0400	-	2.40	0.0010
27	4.2	0.0010	0.06	-	-	-	2.4	0.0010	0.06	-	-	-	1.80	0.0000
28	4.2	0.0010	-	0.0500	-	-	2.4	0.0010	-	0.0500	-	-	1.80	0.0000
29	4.2	0.0010	-	-	0.0500	-	2.4	0.0010	-	-	0.0500	-	1.80	0.0000
30	4.2	0.0010	0.05	0.0500	-	-	2.4	0.0010	0.05	0.0500	-	-	1.80	0.0000
31	5.8	0.0010	0.04	-	-	-	3.5	0.0010	0.04	-	-	-	2.30	0.0000
32	3.2	0.0010	-	0.0400	-	-	2.0	0.0010	-	0.0400	-	-	1.20	0.0000
33	4.5	0.0010	0.05	0.0500	-	-	2.0	0.0010	0.05	0.0500	-	-	2.50	0.0000

*The balance is Fe and inevitable impurities.

[0071]

Table 2

No.	Sheet thickness t (mm)	Multilayer ratio t ₁ /t	Final annealing temperature (°C)	Magnetic properties						Remarks
				15+140t	W _{10/1k} (W/kg)	Conditions of formula (1)	B ₁ (T)	B ₁₀ (T)	B ₁ /B ₁₀	
1	0.20	-	1000	43	44.0	unsatisfied	1.10	1.51	0.73	Comparative Example
2	0.20	-	1000	43	38.0	satisfied	1.07	1.25	0.86	Comparative Example
3	0.25	0.30	1020	50	44.0	satisfied	1.10	1.48	0.74	Example
4	0.20	0.30	1000	43	37.5	satisfied	1.15	1.45	0.79	Example
5	0.20	0.30	1000	43	37.2	satisfied	1.02	1.44	0.71	Example
6	0.20	0.30	1050	43	44.0	unsatisfied	0.65	1.24	0.52	Comparative Example
7	0.15	0.30	1150	36	40.0	unsatisfied	1.15	1.54	0.75	Comparative Example
8	0.25	0.30	1000	50	51.0	unsatisfied	0.95	1.25	0.76	Comparative Example
9	0.20	0.30	1000	43	38.0	satisfied	1.15	1.50	0.77	Example
10	0.15	0.30	1000	36	33.5	satisfied	1.12	1.45	0.77	Example
11	0.10	0.30	1000	29	27.5	satisfied	1.08	1.43	0.76	Example
12	0.10	0.30	1000	29	26.5	satisfied	1.10	1.43	0.77	Example
13	0.20	0.30	1000	43	36.8	satisfied	1.08	1.47	0.73	Example
14	0.20	0.15	1000	43	39.8	satisfied	1.10	1.49	0.74	Example
15	0.20	0.50	1000	43	36.5	satisfied	1.08	1.44	0.75	Example
16	0.20	0.80	1000	43	44.5	unsatisfied	1.05	1.39	0.76	Comparative Example
17	0.20	0.30	980	43	38.5	satisfied	1.10	1.49	0.74	Example
18	0.20	0.30	980	43	45.0	unsatisfied	0.87	1.24	0.70	Comparative Example
19	0.25	0.40	1100	50	44.0	satisfied	1.10	1.48	0.74	Example
20	0.20	0.40	1100	43	37.0	satisfied	1.08	1.45	0.74	Example
21	0.10	0.40	1100	29	27.0	satisfied	1.08	1.45	0.74	Example
22	0.08	0.40	1100	26	24.0	satisfied	1.04	1.41	0.74	Example
23	0.20	0.40	1050	43	37.2	satisfied	1.08	1.44	0.75	Example
24	0.10	0.40	1050	29	27.4	satisfied	1.08	1.43	0.76	Example
25	0.08	0.40	1050	26	25.1	satisfied	1.04	1.40	0.74	Example
26	0.06	0.40	1050	23	22.1	satisfied	1.01	1.40	0.72	Example
27	0.20	0.50	1050	43	38.0	satisfied	1.10	1.48	0.74	Example
28	0.20	0.50	1050	43	38.5	satisfied	1.10	1.48	0.74	Example
29	0.20	0.50	1050	43	38.2	satisfied	1.10	1.48	0.74	Example
30	0.20	0.50	1050	43	37.5	satisfied	1.10	1.48	0.74	Example
31	0.20	0.50	1050	43	40.0	satisfied	1.01	1.32	0.77	Example
32	0.20	0.50	1050	43	40.5	satisfied	1.10	1.45	0.76	Example
33	0.20	0.50	1200	43	37.5	satisfied	1.10	1.45	0.76	Example

REFERENCE SIGNS LIST

[0072]	1	Multilayer electrical steel sheet
	10	Inner layer
	20	Surface layer

CLAIMS

1. A multilayer electrical steel sheet comprising an inner layer and surface layers provided on both sides of the inner layer, wherein

each of the surface layers has a chemical composition containing, in mass%,

Si: 2.5 % to 6.0 % and

at least one selected from the group consisting of P: 0.01 % to 0.1 %, Sn: 0.001 % to 0.1 % and Sb: 0.001 % to 0.1 %, with the balance being Fe and inevitable impurities,

the inner layer has a chemical composition containing, in mass%,

Si: 1.5 % to 4.0 % and

at least one selected from the group consisting of P: 0.01 % to 0.1 %, Sn: 0.001 % to 0.1 % and Sb: 0.001 % to 0.1 %, with the balance being Fe and inevitable impurities, and

the multilayer electrical steel sheet has:

ΔSi of 0.5 mass% to 4.0 mass%, ΔSi being defined as a difference between a Si content in each of the surface layers $[\text{Si}]_1$ and a Si content in the inner layer $[\text{Si}]_0$ represented by $[\text{Si}]_1 - [\text{Si}]_0$;

ΔAl of 0.05 mass% or less, ΔAl being defined as an absolute value of a difference between a content of Al contained as an inevitable impurity in each of the surface layers $[\text{Al}]_1$ and a content of Al contained as an inevitable impurity in the inner layer $[\text{Al}]_0$ represented by $|[\text{Al}]_1 - [\text{Al}]_0|$;

a ratio of t_1 to t represented by t_1/t of from 0.10 to 0.70, where t_1 denotes a total thickness of the surface layers and t denotes a sheet thickness of the multilayer electric steel sheet;

B_{10} of 1.3 T or more, where B_{10} denotes a magnetic flux density at a magnetic field intensity of 1000 A/m;

a ratio of B_1 to B_{10} represented by B_1/B_{10} of 0.45 or more, where B_1 denotes a magnetic flux density at a magnetic field intensity of 100 A/m; and


an iron loss at a frequency of 1 kHz and a largest magnetic flux density of 1.0 T represented by $W_{10/1k}$ in W/kg and the sheet thickness t in mm satisfy the following formula (1):

$$W_{10/1k} \leq 15 + 140 \times t \quad (1).$$



2. The multilayer electrical steel sheet according to claim 1, wherein at least one of the chemical composition of each of the surface layers or the chemical composition of the inner layer further contains, in mass%, Mo: 0.001 % to 0.1 %.

1 / 5


FIG. 1




2/5



3/5

FIG. 3

4 / 5

FIG. 4

5/5

FIG. 5