

(12) STANDARD PATENT
(19) AUSTRALIAN PATENT OFFICE

(11) Application No. **AU 2007251550 B2**

(54) Title
Sheet steel product provided with an anticorrosion coating and process for producing it

(51) International Patent Classification(s)
C23C 2/06 (2006.01)

(21) Application No: **2007251550** (22) Date of Filing: **2007.05.15**

(87) WIPO No: **WO07/132007**

(30) Priority Data

(31) Number **06113962.2** (32) Date **2006.05.15** (33) Country **EP**

(43) Publication Date: **2007.11.22**
(44) Accepted Journal Date: **2012.05.03**

(71) Applicant(s)
ThyssenKrupp Steel AG

(72) Inventor(s)
Warnecke, Wilhelm;Meurer, Manfred;Schonenberg, Rudolf;Keller, Michael;Elsner, Alexander

(74) Agent / Attorney
Davies Collison Cave, 1 Nicholson Street, Melbourne, VIC, 3000

(56) Related Art
WO 1989/09844 A

(12) NACH DEM VERTRAG ÜBER DIE INTERNATIONALE ZUSAMMENARBEIT AUF DEM GEBIET DES
PATENTWESENS (PCT) VERÖFFENTLICHTE INTERNATIONALE ANMELDUNG

(19) Weltorganisation für geistiges Eigentum
Internationales Büro



(43) Internationales Veröffentlichungsdatum
22. November 2007 (22.11.2007)

PCT

(10) Internationale Veröffentlichungsnummer
WO 2007/132007 A1

(51) Internationale Patentklassifikation:
C23C 2/06 (2006.01)

(21) Internationales Aktenzeichen: PCT/EP2007/054711

(22) Internationales Anmeldedatum:
15. Mai 2007 (15.05.2007)

(25) Einreichungssprache: Deutsch

(26) Veröffentlichungssprache: Deutsch

(30) Angaben zur Priorität:
06113962.2 15. Mai 2006 (15.05.2006) EP

(71) Anmelder (für alle Bestimmungsstaaten mit Ausnahme von
US): ThyssenKrupp Steel AG [DE/DE]; Kaiser-Wilhelm-
Strasse 100, 47166 Duisburg (DE).

(72) Erfinder; und

(75) Erfinder/Anmelder (nur für US): WARNECKE, Wil-
helm [DE/DE]; Buschfeld 21, 46499 Hamminkeln (DE).
MEURER, Manfred [DE/DE]; Johannes-Laers-Strasse
57a, 47495 Rheinberg (DE). SCHÖNENBERG, Rudolf
[DE/DE]; Westendorffstrasse 50, 58675 Hemer (DE).
KELLER, Michael [DE/DE]; Zum Bohnengarten 19,
57258 Freudenberg (DE). ELSNER, Alexander [DE/DE];
Schöne Aussicht 2, 57462 Olpe (DE).

(74) Anwalt: COHAUSZ & FLORACK; Bleichstrasse 14,
40211 Düsseldorf (DE).

(81) Bestimmungsstaaten (soweit nicht anders angegeben, für
jede verfügbare nationale Schutzrechtsart): AE, AG, AL,
AM, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA,
CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG,
ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL,
IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK,
LR, LS, LT, LU, LY, MA, MD, MG, MK, MN, MW, MX,
MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO,
RS, RU, SC, SD, SE, SG, SK, SL, SM, SV, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Bestimmungsstaaten (soweit nicht anders angegeben, für
jede verfügbare regionale Schutzrechtsart): ARIPO (BW,
GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG,
ZM, ZW), eurasisches (AM, AZ, BY, KG, KZ, MD, RU,
TJ, TM), europäisches (AT, BE, BG, CH, CY, CZ, DE, DK,
EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC,
MT, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF,
CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD,
TG).

Veröffentlicht:

- mit internationalem Recherchenbericht
- vor Ablauf der für Änderungen der Ansprüche geltenden
Frist; Veröffentlichung wird wiederholt, falls Änderungen
eintreffen

Zur Erklärung der Zweibuchstaben-Codes und der anderen Ab-
kürzungen wird auf die Erklärungen ("Guidance Notes on Co-
des and Abbreviations") am Anfang jeder regulären Ausgabe der
PCT-Gazette verwiesen.

(54) Title: SHEET STEEL PRODUCT PROVIDED WITH AN ANTICORROSION COATING AND PROCESS FOR PRODUC-
ING IT

(54) Bezeichnung: MIT EINEM KORROSIONSSCHUTZÜBERZUG VERSEHENES STAHLFLACHPRODUKT UND VER-
FAHREN ZU SEINER HERSTELLUNG

(57) Abstract: The present invention relates to a sheet steel product and a process for producing it, which is formed by a steel substrate such as a steel strip or sheet and a zinc-based anticorrosion coating containing (in % by weight) Mg: 0.25-2.5%, Al: 0.2-3.0%, Fe ≤ 4.0% and, if desired, a total of up to 0.8% of one or more elements from the group consisting of "Pb, Bi, Cd, Ti, B, Si, Cu, Ni, Co, Cr, Mn, Sn and rare earths", balance zinc and unavoidable impurities applied to at least one side of the steel substrate, with the anticorrosion coating having, in an intermediate layer which extends between a surface layer directly adjoining the surface of the sheet steel product and a boundary layer adjoining the steel substrate and whose thickness is at least 20% of the total thickness of the anticorrosion coating, an Al content of not more than 0.5% by weight. The sheet steel product of the invention has an optimal combination of high corrosion resistance and optimized weldability and is particularly suitable for use as material for automobile body construction, for general building purposes or for construction of household appliances.

(57) Zusammenfassung: Die vorliegende Erfindung betrifft ein Stahlflachprodukt und ein Verfahren zu dessen Herstellung, das aus einem Stahlsubstrat, wie einem Stahlband oder -blech, und einem mindestens auf eine Seite des Stahlsubstrat aufgetragenen zinkbasierten Korrosionsschutzüberzug gebildet ist, der in (in Gew.-%) Mg: 0,25 - 2,5 %, Al: 0,2 - 3,0 %, Fe ≤ 4,0 %, sowie wahlweise in Summe bis zu 0,8 % an einem oder mehreren Elementen aus der Gruppe "Pb, Bi, Cd, Ti, B, Si, Cu, Ni, Co, Cr, Mn, Sn sowie Seltene Erden", Rest Zink und unvermeidbare Verunreinigungen enthält, wobei der Korrosionsschutzüberzug in einer Zwischenschicht, die sich zwischen einer unmittelbar an die Oberfläche des Stahlflachprodukts angrenzenden Oberflächenschicht und einer an das Stahlsubstrat angrenzenden Grenzschicht erstreckt und deren Dicke mindestens 20 % der Gesamtdicke des Korrosionsschutzüberzugs beträgt, einen Al-Gehalt von höchstens 0,5 Gew.-% aufweist. Das erfindungsgemäße Stahlflachprodukt besitzt eine optimale Kombination von hoher Korrosionsbeständigkeit und optimierter Schweißbarkeit und eignet sich insbesondere für die Verwendung als Werkstoff für den Automobilkarosseriebau, für allgemeine Bauzwecke oder für den Hausgerätebau.

WO 2007/132007 A1

SI/cs 060619WO

15 May 2007

**FLAT STEEL PRODUCT WITH A CORROSION PROTECTION COATING AND
METHOD FOR ITS PRODUCTION**

The invention concerns a flat steel product which is formed from a steel substrate, such as strip or sheet steel, and a zinc-based corrosion protection coating applied to at least one side of the steel substrate. In addition the invention concerns a method with which such flat steel products can be produced.

To improve the corrosion resistance, metal coatings are applied to sheet or strip steel which in most applications are based on zinc or zinc alloys. Such zinc or zinc alloy coatings, because of their barrier and cathodic protective effect, provide good corrosion protection in practical use for the correspondingly coated sheet steel.

The thickness of the coating required for adequate corrosion resistance in the prior art however causes problems in processing i.e. when forming and welding. This applies for example when in practical use flanges subject to high corrosion load are to be spot-welded. This requirement exists in particular in the field of car body construction, in general building applications or in the construction of housings for domestic appliances. The connection produced by such welding, for an adequate welding current, must have a minimum spot diameter of $4 \times \sqrt{t}$ (t = individual sheet thickness) and be able to be welded without spatter.

In the context of the problems in processing conventional sheets coated with a relatively thick Zn layer, highly corrosion-resistant Zn-Mg or Zn-Mg-Al layer systems have been developed which, with a greatly reduced layer thickness, offer corrosion protection comparable to that of a conventional 7.5 μm thick zinc coating but are significantly easier to process.

One possibility for producing such hot galvanised sheet steel with increased corrosion resistance and simultaneously reduced coating mass is described in EP 0 038 904 B1. According to this prior art, a zinc coating containing 0.2 wt.% Al and 0.5 wt.% Mg is applied to a steel substrate by hot dip coating. Although the metal coated in this way has improved resistance to rust formation, in practice it does not fulfil the requirements imposed today for corrosion resistance of such panels, in particular in the area of connecting flanges of a car body.

A further sheet provided with a metallic protective coating with increased corrosion resistance is known from EP 1 621 645 A1. The sheet steel described there is coated, by conventional hot galvanising, with a protective coating which contains (in wt.%) 0.3 to 2.3% Mg, 0.6 to 2.3% Al, optionally < 0.2% other active constituents and the remainder zinc and unavoidable impurities. Due to the high proportion of Al and Mg, such metal has particularly good resistance to corrosion. Practical tests however have shown that even the panels produced according to EP 1 621 645 A1 do not fulfil the requirements imposed by the processing industry for the weldability of such panels. It is also shown that the panels concerned have a phosphatisation

2007251550 10 Apr 2012

- 3 -

capacity which is inadequate according to present standards.

It would therefore be desirable to create a sheet steel product which has an optimum combination of high corrosion resistance and optimised processability and which is suitable in particular for use as a material for car body construction, for general building purposes or for domestic appliance construction. Also a method is specified for production of such a flat product.

10 According to the invention there is provided a flat steel product which is formed from a steel substrate, such as strip or sheet steel, and a zinc-based corrosion protection coating applied to at least one side of the steel substrate, wherein the corrosion protection coating contains in (wt.%)

15 Mg: 0.25 to 2.5%
 Al: 0.2 to 3.0%
 Fe: > 0.3 to 4.0%

and optionally in total up to 0.8% of one or more elements from the group Bi, Cd, Ti, B, Si, Cu, Ni, Co, Cr, Mn, Sn and rare earths, remainder zinc and unavoidable impurities, and wherein the corrosion protection coating has an intermediate layer extending between a surface layer directly adjacent to the surface of the flat steel product and a border layer adjacent to the steel substrate, said intermediate layer having an Al content of maximum 0.5 wt.% and a thickness amounting to at least 20% of the total thickness of the corrosion protection coating.

Further according to the invention there is provided a method for production of a flat steel product in which on a steel substrate, such as strip or sheet steel, a corrosion protection coating is produced, wherein the steel substrate is annealed and, starting from

the annealing temperature, cooled to a strip immersion temperature of 400 to 600°C at which the steel substrate enters a melt bath containing (in wt.%) 0.1 to 0.4% Al, 0.25 to 2.5% Mg, up to 0.2% Fe, and optionally in total up to 0.8% of one or more elements of the group Bi, Cd, Ti, B, Si, Cu, Ni, Co, Cr, Mn, Sn and rare earths, remainder zinc and unavoidable impurities and heated to a bath temperature of 420 to 500°C, where the difference between the strip immersion temperature and the bath temperature varies in the range from -20°C to + 100°C so that on the steel substrate a corrosion protection coating is formed which contains (in wt.%)

Mg: 0.25 to 2.5%
Al: 0.2 to 3.0%
Fe: > 0.3 to 4.0%

and optionally in total up to 0.8% of one or more elements of the group Bi, Cd, Ti, B, Si, Cu, Ni, Co, Cr, Mn, Sn and rare earths, remainder zinc and unavoidable impurities, and which has an intermediate layer extending between a surface layer directly adjacent to the surface of the flat steel product and a border layer adjacent to the steel substrate, said intermediate layer having an Al content of maximum 0.5 wt.% and a thickness amounting to at least 20% of the total thickness of the corrosion protection coating.

The invention is based on the knowledge that general properties, such as e.g. adhesion and weldability of a steel sheet or strip with a Zn-Mg-Al coating as protection against corrosion, depend decisively on the distribution of the aluminium in the coating layer. It has been found surprisingly that if, as specified by the invention, low Al contents are present in an intermediate layer, close to the surface, of sufficient thickness according to the invention, the weldability improves in comparison with

2007251550 10 Apr 2012

2007251550 10 Apr 2012

- 5 -

conventionally formed sheets even though the Al content of the coating as a whole is at a level which guarantees a high corrosion protection. The sheets formed correspondingly according to the invention with a high Al concentration in the area of the border
5 layer at the transition to the steel substrate, retain the positive effect of the aluminium on the corrosion protection despite the low proportion of Al in the intermediate layer.

Flat steel products formed according to the invention also, as a
10 result of the low content of Al on their surface and in the intermediate layer, are particularly suitable for phosphatising so that for example they can be given an organic paint coating without special additional measures. Elements from the group Bi, Cd, Ti, B, Si, Cu, Ni, Co, Cr, Mn, Sn and rare earths can be present up to a
15 total of their contents of 0.8 wt.% in the coating according to the invention. Bi and Cd can serve to form a larger crystal structure (flowers of zinc), Ti, B, Si to improve formability, Cu, Ni, Co, Cr, Mn to influence the border layer reactions, Sn to influence the surface oxidation and rare earths, in particular lanthanum and
20 cerium, to improve the flow behaviour of the melt. The impurities which may be present in a corrosion protection coating according to the invention include the constituents which, as a result of the hot dip coating, transfer from the steel substrate to the coating in quantities which do not affect the properties of the coating.

25 It has been shown that with the relatively low Al content of a melt bath used for performance of the method according to the invention, by suitable setting of the strip immersion and/or bath temperature, even the nature of the layer structure desired according to the
30 invention can be directly influenced. The method according to the invention achieves that high Al and Mg contents are enriched in the

2007251550 10 Apr 2012

- 6 -

border layer adjacent to the steel substrate, whereas in the intermediate layer in particular low Al contents are present. The difference between the strip temperature on immersion and the temperature of the melt bath is particularly significant. As this difference varies in the range from -20°C to 100°C, preferably -10°C to 70°C, the presence of Al minimised according to the invention in the intermediate layer can be set securely and in a targeted manner.

Particularly favourable welding properties occur when the aluminium content of the intermediate layer is reduced as far as possible. Therefore an advantageous embodiment of the invention allows for the Al content of the intermediate layer to be no more than 0.25 wt.%.

In addition the layer structure used by the invention has a particularly positive effect on the weldability and phosphatising capacity, while still retaining the good corrosion protection effect of the coating, when the thickness of the intermediate layer according to the invention amounts to at least 25% of the total thickness of the corrosion protection coating. The figures given here and in the claims for the structure of the corrosion protection coating and its individual layers relate to a layer profile determined by means of a GDOS measurement (glow discharge optical emission spectrometry). The GDOS measurement method described for example in the VDI Glossary of Materials Technology, published by Hubert Grafen, VDI Verlag GmbH, Diisseldorf 1993 is a standard method for fast detection of a concentration profile of coatings.

With the flat steel profiles produced according to the invention, such a GDOS measurement shows that in the surface layer immediately adjacent to the surface of the coating, as a result of oxidation due to production, inevitably an increased Al content is produced. As

the thickness of this surface layer is however very low compared with the total thickness of the coating, on welding of a flat steel product according to the invention the surface layer is easily punctured and only insignificantly influences the welding result.

- 5 In order to exclude any possible negative effect of the surface coating with high Al content, the thickness of the surface coating should be restricted to less than 10%, preferably less than 1% of the total thickness of the corrosion protection coating. Practical tests have confirmed that with flat steel products produced
- 10 according to the invention, the surface layer is maximum 0.2 μm thick so that with conventional coating thicknesses of 6 μm and more, the proportion of surface border layer in the total thickness of the coating structure is around 3.5% or considerably less.
- 15 With flat steel products according to the invention the coating preferably has Fe contents which amount to more than 0.4 wt.%, and more preferably more than 0.5 wt.%. The relatively high Fe contents are present in particular in the area of the border layer adjacent to the steel substrate. Here preferably an alloy is formed which
- 20 guarantees an optimised adhesion of the coating to the steel substrate. In this way a flat steel product produced according to the invention has usage properties which are superior to those of conventional flat steel products if the protective coating has high Mg and Al contents.
- 25 In order, in addition to the layer structure according to the invention of the corrosion protection coating, to optimise further the weldability and phosphatisation capacity of a flat steel product according to the invention, the Al content of the corrosion
- 30 protection coating can be restricted to less than 0.6 wt.%, preferably less than 0.5 wt.%.

2007251550 10 Apr 2012

2007251550 10 Apr 2012

To secure its effect, the total thickness of the corrosion protection coating should be at least $2.5\mu\text{m}$, preferably at least $5\mu\text{m}$, more preferably at least $7\mu\text{m}$. A coating mass distribution of the corrosion protection coating of at least 17.5 g/m^2 is preferred. A coating mass distribution of at least 100g/m^2 has proved particularly favourable with regard to protective effect. Despite higher coating masses and thickness of the corrosion protection coating, because of the distribution of the Al content specified according to the invention, the weldability is not adversely affected.

Particularly good product results are achieved if the bath temperature of the melt bath is 440 to 480°C .

Surprisingly it has been found that the speed with which the steel substrate passes through the melt bath only has a secondary influence on the coating result. Therefore for example this can be varied within the range from 50 to 200 m/min in order to achieve the optimum working result with maximum productivity.

The annealing of the steel strip prior to the melt bath should be carried out under an inert gas atmosphere in order to avoid oxidation of the metal surface. The inert gas atmosphere in the known manner can contain more than $3.5\text{ vol.}\% \text{H}_2$ and the remainder N_2 . The annealing temperature can also lie in the range from 700 to 900°C in the known manner.

The deviation, in the range from -20°C to $+100^\circ\text{C}$, of the bath inlet temperature of the steel substrate from the temperature of the melt bath ensures that the melt bath retains its optimum temperature

2007251550 10 Apr 2012

- 9 -

evenly despite the introduction of the steel substrate. The preferred temperature difference range is from -10°C to $+70^{\circ}\text{C}$. The preferred strip immersion or bath inlet temperature is 410°C to 510°C .

5

The melt bath itself preferably in any case contains only traces of iron since, according to the invention, the Fe content of the corrosion protection coating is to be set by the inclusion of iron from the steel substrate. Consequently the Fe content of the melt bath is preferably restricted to maximum 0.1 wt.%, in particular maximum 0.07 wt.%.

The good processability, the simultaneously good corrosion protection and good phosphatisation capacity exist irrespective of the nature and composition of the steel substrate. Practical tests have shown that there are no substantial differences in the properties of the flat steel products produced according to the invention if the substrate comprises an IF steel, for example a conventional micro-alloy steel, or a normal alloy steel such as a conventional high-grade steel.

The invention is now described below with reference to embodiment examples and reference examples. These show:

25 Diag. 1 The graphic depiction of the distribution obtained by GDOS measurement of the contents of Zn, Mg, Al and Fe over the thickness of a first

corrosion protection coating applied to a steel substrate.

Diag. 2 The graphic depiction of the distribution obtained by GDOS measurement of the contents of Zn, Mg, Al and Fe over the thickness of a second corrosion protection coating applied to a steel substrate.

To produce specimens structured according to the invention, which can be easily spot welded and phosphatised, of flat steel products with high corrosion resistance, a steel strip serving as a steel substrate is annealed under a nitrogen atmosphere containing 5% H₂ with dew point $-30^{\circ}\text{C} \pm 2^{\circ}\text{C}$ for a holding time of 60 s in each case. The annealing temperature was 800°C with a heating rate of 10°C/s .

After annealing, the steel strip was rapidly cooled with a cooling rate of 5 to 30°C/s to a temperature of $470^{\circ}\text{C} \pm 5^{\circ}\text{C}$ at which it was held for 30 s. The steel strip was then introduced at a strip immersion speed of 100 m/min into a melt bath with bath temperature $460^{\circ}\text{C} \pm 5^{\circ}\text{C}$. The bath inlet temperature of the steel strip was 5°C above the bath temperature of the melt bath.

The respective composition of the melt bath and the analyses of the specimens, passing through the hot galvanising in the melt bath on the upper and lower sides of the corrosion protection coating, are shown in Table 1 for twelve specimens E1 to E12 coated in the manner described above, where determined. It is found that the coatings formed on the steel substrate have high

proportions of Fe. The alloying with Fe which occurs during production of the coating ensures a particularly high adhesion capacity of the coating to the steel substrate.

In addition, analyses of the distribution of the contents of Zn, Al, Mg and Fe over the thickness of the corrosion protection coating formed in each case on the steel substrate have shown that the Al content of the coating is in each case less than 0.2% in an intermediate layer close to the surface, the thickness of which amounts to more than 25% of the layer thickness (total thickness) of the coating in each case. The corresponding distribution over the thickness D (surface $D = 0 \mu\text{m}$) is shown graphically for specimens E1 and E2 in diagrams 1 and 2.

The diagrams show that, at the surface of the coating concerned, a surface border layer has formed with an Al content which is high as a result of oxidation. The thickness of this surface border layer is however maximum $0.2 \mu\text{m}$ and it is therefore easily punctured on spot or laser welding with no deterioration in the quality of the welding result.

Next to the surface border layer is an intermediate layer approximately $2.5 \mu\text{m}$ thick, the Al content of which is less than 0.2%. The thickness of the intermediate layer is therefore around 36% of the total layer thickness of the respective corrosion protection coating of $7 \mu\text{m}$.

The intermediate layer transforms into a border layer next to the steel substrate in which the content of Al, Mg and

2007251550 10 Apr 2012

- 12 -

Fe is substantially higher in relation to the corresponding contents of the intermediate layer.

- In order to check the dependency of the layer structure and the composition of a corrosion coating generated on the steel substrate processed in each case and on the bath inlet and outlet temperature, based on a conventional micro-alloy steel IF and an equally conventional high-grade steel QS, further specimens E13 to E22 were produced with a corrosion protection coating in a laboratory test.
- 10 The composition of steels IF and QS is given in Table 3.

- The operating parameters set in the laboratory tests and an analysis of the coating layer generated accordingly are shown in Table 2. It is found that the result of the coating, in particular with regard
- 15 to the inclusion of high Fe contents arising from the steel substrate and the formation of the intermediate layer close to the surface with an Al content of less than 0.25% wt.%, is independent of the composition of the steel substrate.

- 20 In total, tests performed on specimens E1 to E22 have confirmed that with the corrosion protection coating generated, in the surface border layer immediately adjacent to the surface of the coating, the elements Mg and Al are present in enriched form as oxides. In addition, Zn oxide is present at the surface.

- 25 In addition, operating tests B1 to B19 have been performed in which the steel substrate was steel strips comprising high-grade steel QS. The operating parameters set, the respective melt bath composition and an analysis of the corrosion protection layer obtained on the
- 30 steel substrate in each case, are given in Table 4.

The operating tests confirmed in full the result of the preceding laboratory tests. The thickness of the surface border layer absorbing the superficial oxidation in the specimens studied amounts

2007251550 10 Apr 2012

- 13 -

to maximum 0.2 μm and in relation to the layer profile determined by GDOS measurement lies in the range of up to 2.7% of the total layer thickness. The amount of Al enrichment at the immediate surface is maximum approximately 1 wt.%. This is followed, up to a thickness
5 of at least 25% of the total thickness of the coating, by the intermediate layer with a low Al content of maximum 0.25 wt.%. In the border layer then the Al content rises to 4.5% at the border to the steel substrate. The Mg enrichment at the immediate surface of the coating is clearly greater than the Al enrichment. Here, Mg
10 proportions of up to 20% are achieved. Thereafter, the Mg proportion diminishes over the intermediate layer and at a depth of around 25% of the total layer thickness of the coating amounts to 0.5 to 2%. Over the border layer there is a rise in the Mg content in the direction of the steel substrate. At the border to the steel
15 substrate the Mg coating amounts to 3.5%.

The reference in this specification to any prior publication (or information derived from it), or to any matter which is known, is not, and should not be taken as an acknowledgment or admission or
20 any form of suggestion that that prior publication (or information derived from it) or known matter forms part of the common general knowledge in the field of endeavour to which this specification relates.

Specimen	Melt Bath			Layer Analysis Top					Layer Analysis Underside				
	Al	Fe	Mg	Al	Fe	Mg	Coating mass	Coating Thickness	Al	Fe	Mg	Coating mass	Coating Thickness
	%			%			g/m ²	μm	%			g/m ²	μm
E1	0.201	0.011	1.589	1.16	1.06	1.52	41.5	7.0	n.d.	n.d.	n.d.	n.d.	9.0
E2	0.205	0.090	2.024	1.18	1.07	1.90	40.5	7.0	n.d.	n.d.	n.d.	n.d.	8.5
E3	0.189	0.021	0.733	0.47	0.37	0.75	75.9	10.6	n.d.	n.d.	n.d.	n.d.	7.7
E4	0.189	0.021	0.733	0.66	0.58	0.75	50.0	6.7	1.61	1.69	0.77	17.6	2.1
E5	0.202	0.013	0.790	1.38	1.37	0.76	20.7	4.0	n.d.	n.d.	n.d.	n.d.	2.9
E6	0.209	n.d.	0.825	0.63	0.55	0.81	47.8	n.d.	0.71	0.61	0.82	43.5	n.d.
E7	0.218	n.d.	0.498	0.87	0.8	0.48	37.4	n.d.	1.22	1.25	0.48	24.4	n.d.
E8	0.218	n.d.	0.498	0.69	0.57	0.47	57.3	n.d.	1.19	1.11	0.48	30.1	n.d.
E9	0.231	n.d.	1.265	1.16	1.13	1.29	35.1	n.d.	1.96	2.15	1.29	20.0	n.d.
E10	0.231	n.d.	1.265	1.12	1.11	1.24	28.7	n.d.	1.35	1.42	1.24	21.4	n.d.
E11	0.196	n.d.	0.288	1.65	1.94	n.d.	27.3	n.d.	2.96	3.88	0.27	14.6	n.d.
E12	0.200	0.011	0.297	1.02	1.09	n.d.	43.2	n.d.	0.59	0.62	0.27	83.8	n.d.

*) Remainder Zn and unavoidable impurities; n.d. = not determined.

Table 1

Specimen	Steel	Annealing Temp	Bath Inlet Temp	Bath Temp	Coating mass	[g]				[g/m ²]			
						Al	Fe	Mg		Al	Fe	Mg	
		[°C]	[°C]	[°C]	[g/m ²]								
E13	IF	800	445	440	51.6	0.52	0.36	1.21		0.27	0.19	0.62	
E14	QS	800	445	440	55.9	0.56	0.40	1.16		0.31	0.22	0.65	
E15	IF	800	465	460	64.3	0.81	0.75	1.15		0.52	0.48	0.74	
E16	QS	750	465	460	54.1	0.98	0.84	1.21		0.53	0.45	0.65	
E17	IF	800	485	460	49.4	1.08	0.97	1.18		0.53	0.48	0.58	
E18	QS	750	485	460	55.1	0.97	0.84	1.19		0.53	0.46	0.66	
E19	IF	800	500	460	54.3	1.14	1.08	1.20		0.62	0.59	0.65	
E20	QS	750	500	460	36.7	1.50	1.41	1.19		0.55	0.52	0.44	
E21	IF	800	485	480	62.4	1.15	1.26	1.15		0.72	0.79	0.72	
E22	QS	750	485	480	43.6	1.57	1.68	1.16		0.68	0.73	0.51	

Table 2

Steel	C	Si	Mn	[wt.-%]			
				P	S	Ti	Al
IF	0.003	0.02	0.13	0.010	0.012	0.07	0.03
QS	0.07	0.04	0.40	0.012	0.005	0.005	0.04

Remainder iron and unavoidable impurities

Table 3

Test	Strip immersion temp BET	Bath Temp BT	Difference BET-BT	Coating Thickness	Coating mass	Al	Fe	Mg	Al	Fe						
[°C]											[wt. %] *			[g/m²]		
B1	516	466	50	4.9	34.7	1.61	1.46	0.81	0.56	0.51						
B2	536	478	58	7.8	55.1	1.00	0.88	0.82	0.55	0.48						
B3	500	472	28	11.4	80.6	0.65	0.51	0.82	0.52	0.41						
B4	522	472	50	10.2	72.1	0.94	0.82	0.81	0.68	0.59						
B5	493	467	26	5.7	40.2	0.66	0.47	0.81	0.27	0.19						
B6	457	456	1	11.2	79.2	0.43	0.20	0.81	0.34	0.15						
B7	483	464	19	4.8	34.4	0.97	0.92	0.83	0.33	0.32						
B8	509	466	43	9.2	65.5	0.72	0.61	0.81	0.47	0.40						
B9	509	466	43	9.5	67.7	0.84	0.74	0.81	0.57	0.50						
B10	506	471	35	7.0	49.6	1.14	1.05	0.81	0.56	0.52						
B11	506	471	35	5.2	37.1	1.13	1.05	0.81	0.42	0.39						
B12	521	457	64	5.5	39.1	1.32	1.22	0.81	0.51	0.48						
B13	521	457	64	8.1	57.6	1.01	0.94	0.81	0.58	0.54						
B14	479	460	19	7.3	51.8	0.55	0.41	1.11	0.28	0.21						
B15	479	460	19	10.7	75.8	0.46	0.29	1.10	0.35	0.22						
B16	460	471	-11	4.3	30.7	0.66	0.56	1.11	0.20	0.17						
B17	460	471	-11	7.1	50.5	0.47	0.32	1.11	0.24	0.16						
B18	460	460	0	7.2	50.9	0.48	0.32	1.11	0.24	0.16						
B19	460	460	0	4.6	32.6	0.79	0.65	1.11	0.26	0.21						
Mean	494	466	28	7.4	52.9	0.83	0.42	0.70	0.35	0.91						
Max	536	478	64	11.4	80.6	1.61	0.68	1.46	0.59	1.11						
Min	457	456	-11	4.3	30.7	0.43	0.20	0.20	0.15	0.81						

*) remainder Zn and unavoidable impurities

Table 4

CLAIMS

1. Flat steel product which is formed from a steel substrate, such as strip or sheet steel, and a zinc-based corrosion protection coating applied to at least one side of the steel substrate, wherein the corrosion protection coating contains in (wt.%)

Mg: 0.25 to 2.5%

Al: 0.2 to 3.0%

Fe: > 0.3 to 4.0%

and optionally in total up to 0.8% of one or more elements from the group Bi, Cd, Ti, B, Si, Cu, Ni, Co, Cr, Mn, Sn and rare earths, remainder zinc and unavoidable impurities, and wherein the corrosion protection coating has an intermediate layer extending between a surface layer directly adjacent to the surface of the flat steel product and a border layer adjacent to the steel substrate, said intermediate layer having an Al content of maximum 0.5 wt.% and a thickness amounting to at least 20% of the total thickness of the corrosion protection coating.

2. Flat steel product according to claim 1, characterised in that the Al content of the intermediate layer is no more than 0.25 wt.%.

3. Flat steel product according to any one of the preceding claims, characterised in that the thickness of the intermediate layer is at least 25% of the total thickness of the corrosion protection coating.

4. Flat steel product according to any one of the preceding claims, characterised in that the thickness of the surface layer amounts to less than 10% of the total thickness of the corrosion protection coating.

2007251550 10 Apr 2012

- 18 -

5. Flat steel product according to claim 4, characterised in that the thickness of the surface layer is less than 1% of the total thickness of the corrosion protection coating.

6. Flat steel product according to any one of the preceding claims, characterised in that the Fe content of the corrosion protection coating amounts to more than 0.5 wt.%.

7. Flat steel product according to any one of the preceding claims, characterised in that the Al content of the corrosion protection coating is less than 0.6 wt.%.

8. Flat steel product according to claim 7, characterised in that the Al content of the corrosion protection coating is less than 0.5 wt.%.

9. Flat steel product according to any one of the preceding claims, characterised in that the total thickness of the corrosion protection coating is at least 2.5 μm .

10. Flat steel product according to claim 9, characterised in that the total thickness of the corrosion protection coating is at least 5 μm .

11. Flat steel product according to any one of the preceding claims, characterised in that the coating mass distribution of the corrosion protection coating is at least 17.5 g/m².

12. Flat steel product according to claim 1 and substantially as herein described.

2007251550 10 Apr 2012

2007251550 10 Apr 2012

- 19 -

13. Method for production of a flat steel product in which on a steel substrate, such as strip or sheet steel, a corrosion protection coating is produced, wherein the steel substrate is annealed and, starting from the annealing temperature, cooled to a strip immersion temperature of 400 to 600°C at which the steel substrate enters a melt bath containing (in wt.%) 0.1 to 0.4% Al, 0.25 to 2.5% Mg, up to 0.2% Fe, and optionally in total up to 0.8% of one or more elements of the group Bi, Cd, Ti, B, Si, Cu, Ni, Co, Cr, Mn, Sn and rare earths, remainder zinc and unavoidable impurities and heated to a bath temperature of 420 to 500°C, where the difference between the strip immersion temperature and the bath temperature varies in the range from -20°C to +100°C so that on the steel substrate a corrosion protection coating is formed which contains (in wt.%)

Mg: 0.25 to 2.5%

Al: 0.2 to 3.0%

Fe: > 0.3 to 4.0%

and optionally in total up to 0.8% of one or more elements of the group Bi, Cd, Ti, B, Si, Cu, Ni, Co, Cr, Mn, Sn and rare earths, remainder zinc and unavoidable impurities,

and which has an intermediate layer extending between a surface layer directly adjacent to the surface of the flat steel product and a border layer adjacent to the steel substrate, said intermediate layer having an Al content of maximum 0.5 wt.% and a thickness amounting to at least 20% of the total thickness of the corrosion protection coating.

14. Method according to claim 13, characterised in that the bath temperature is 440 to 480°C.

15. Method according to either of claims 13 and 14, characterised in that the difference between the strip immersion temperature and the bath temperature varies in the range from -10°C to +70°C.

- 20 -

16. Method according to any one of claims 13 to 15, characterised in that the strip immersion temperature is 410 to 510°C.

17. Method according to any one of claims 13 to 16, characterised in that the Fe content of the melt bath is ≤ 0.1 wt.%.

18. Method according to claim 13 and substantially as herein described.

2007251550 10 Apr 2012



