

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 June 2009 (18.06.2009)

PCT

(10) International Publication Number
WO 2009/076025 A1

(51) International Patent Classification:
BOID 71/00 (2006.01) BOID 69/00 (2006.01)

(74) Common Representative: UOP LLC; 25 East Algonquin Road, P. O. Box 5017, Des Plaines, Illinois 60017-5017 (US).

(21) International Application Number:
PCT/US2008/084144

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW

(22) International Filing Date:
20 November 2008 (20.11.2008)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
11/954,447 12 December 2007 (12.12.2007) US
11/954,454 12 December 2007 (12.12.2007) US
11/954,463 12 December 2007 (12.12.2007) US

(71) Applicant (for all designated States except US): UOP LLC [US/US]; 25 East Algonquin Road, P. O. Box 5017, Des Plaines, Illinois 60017-5017 (US).

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventors; and

(75) Inventors/Applicants (for US only): LIU, Chunqing [CN/US]; UOP LLC, 25 East Algonquin Road, P. O. Box 5017, Des Plaines, Illinois 60017-5017 (US). WILSON, Stephen, T [US/US]; UOP LLC, 25 East Algonquin Road, P. O. Box 5017, Des Plaines, Illinois 60017-5017 (US). LESCH, David, A. [US/US]; UOP LLC, 25 East Algonquin Road, P. O. Box 5017, Des Plaines, Illinois 60017 (US).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments



WO 2009/076025 A1

(54) Title: MOLECULAR SIEVE/POLYMER MIXED MATRIX MEMBRANES

(57) Abstract: The present invention discloses an approach for making mixed matrix membranes (MMMs) and methods for using these membranes. These MMMs contain a continuous polymer matrix and dispersed microporous molecular sieve particles. In particular, the present invention is directed to making asymmetric thin-film composite MMMs, asymmetric hollow fiber MMMs and asymmetric flat sheet MMMs. These MMMs are characterized as having a thin dense selective mixed matrix layer equal or larger in thickness than any of said molecular sieve particles. The MMMs of the present invention are suitable for a variety of liquid, gas, and vapor separations. The MMMs of the present invention have at least 20% increase in selectivity for these separations compared to the polymer membranes prepared from their corresponding continuous polymer matrices.

MOLECULAR SIEVE/POLYMER MIXED MATRIX MEMBRANES

FIELD OF THE INVENTION

[0001] This invention pertains to an approach for making molecular sieve/polymer mixed matrix membranes (MMMs) and methods for using these membranes. The MMM prepared in the present invention comprising molecular sieves dispersed in a continuous polymer matrix exhibits a selectivity increase of at least 20% relative to a polymer membrane made from the continuous polymer matrix without molecular sieves.

BACKGROUND OF THE INVENTION

[0002] Gas separation processes using membranes have undergone a major evolution since the introduction of the first membrane-based industrial hydrogen separation process about two decades ago. The disclosure of new materials and efficient methods for making membranes will further advance the membrane gas separation processes within the next decade.

[0003] The gas transport properties of many glassy and rubbery polymers have been measured as part of the search for materials with high permeability and high selectivity for potential use as gas separation membranes. Unfortunately, an important limitation in the development of new membranes for gas separation applications is a well-known trade-off between permeability and selectivity of polymers. By comparing the data of hundreds of different polymers, Robeson demonstrated that selectivity and permeability seem to be inseparably linked to one another, in a relation where selectivity increases as permeability decreases and vice versa.

[0004] Despite concentrated efforts to tailor polymer structure to improve separation properties; current polymeric membrane materials have seemingly reached a limit in the trade-off between productivity and selectivity. For example, many polyimide and polyetherimide glassy polymers such as Ultem[®] 1000 have much higher intrinsic CO₂/CH₄ selectivities (*O₂/cm*) (~30 at 50⁰C and 690 kPa (100 psig) pure gas tests) than those of polymers such as cellulose acetate (-22), which are more attractive for practical gas separation applications. These polyimide and polyetherimide glassy polymers, however, do not have permeabilities attractive for commercialization compared to current commercial cellulose acetate membrane products. On the other hand, some inorganic membranes, such as

SAPO-34 and DDR zeolite membranes and carbon molecular sieve membranes, offer much higher permeability and selectivity than polymeric membranes for separations, but are too brittle, expensive, and difficult for large-scale manufacture. Therefore, it remains highly desirable to provide an alternate cost-effective membrane with improved separation
5 properties compared to the polymer membranes.

[0005] Based on the need for a more efficient membrane, a new type of membrane, mixed matrix membrane (MMM), has been developed. MMMs are hybrid membranes containing inorganic particles such as molecular sieves dispersed in a continuous polymer matrix.

[0006] MMMs have the potential to achieve higher selectivity and/or greater permeability compared to the existing polymer membranes, while maintaining their advantages such as low cost and easy processability. Much of the research conducted to date on MMMs has focused on the combination of a dispersed solid molecular sieving phase, such as molecular sieves or carbon molecular sieves, with an easily processed continuous polymer matrix. For
10 example, see US 6,626,980; US 2005/0268782; US 2007/0022877; and US 7,166,146. The sieving phase in a solid/polymer mixed matrix scenario can have a selectivity that is significantly larger than the pure polymer. Therefore, in theory the addition of a small volume fraction of molecular sieves to the polymer matrix will significantly increase the overall separation efficiency. Typical inorganic sieving phases in MMMs include various molecular
15 sieves, carbon molecular sieves, and traditional silica. Many organic polymers, including cellulose acetate, polyvinyl acetate, polyetherimide (commercially Ultem®), polysulfone (commercial Udel®), polydimethylsiloxane, polyethersulfone, and several polyimides (including commercial Matrimid®), have been used as the continuous phase in MMMs.

[0007] Most recently, significant research efforts have been focused on materials
25 compatibility and adhesion at the inorganic molecular sieve/polymer interface of the MMMs in order to achieve separation property enhancements over traditional polymers. For example, Kulkarni et al. and Marand et al. reported the use of organosilicon coupling agent functionalized molecular sieves to improve the adhesion at the sieve particle/polymer interface of the MMMs. See US 6,508,860 and US 7,109,140. This method, however, has a
30 number of drawbacks including: 1) prohibitively expensive organosilicon coupling agents; 2) very complicated time consuming molecular sieve purification and organosilicon coupling agent recovery procedures after functionalization. Therefore, the cost of making such MMMs

having organosilicon coupling agent functionalized molecular sieves in a commercially viable scale can be very expensive. Most recently, Kulkarni et al. also reported the formation of MMMs with minimal macrovoids and defects by using electrostatically stabilized suspensions. See US 2006/0117949. US 2005/0139065 A1 to Miller et al., entitled "Mixed
5 matrix membranes with low silica-to-alumina ratio molecular sieves and methods for making and using the membranes", reports the incorporation of low silica-to-alumina (Si/Al) ratio molecular sieves into a polymer membrane with a Si/Al molar ratio of the molecular sieves preferably less than 1.0. Miller et al. claim that when the low Si/Al ratio molecular sieves are properly interspersed with a continuous polymer matrix, the MMM ideally will exhibit
10 improved gas separation performance.

[0008] While the polymer "upper-bound" curve has been surpassed using solid/polymer MMMs, there are still many issues that need to be addressed for large-scale industrial production of these new types of MMMs. One feature that needs improvement is the excessive thickness of the MMMs. Most of the molecular sieve/polymer MMMs reported in
15 the literature are in the form of thick symmetric mixed matrix dense films with a thickness of 50 μm and molecular sieve particles with relatively large particle sizes in the micron range have been used. Commercially available polymer membranes, such as cellulose acetate and polysulfone membranes, however, have an asymmetric membrane structure with a less than 500 nm thin dense selective layer supported on a porous non-selective layer. As a
20 consequence, the dense selective layer thickness of the mixed matrix membranes is much thinner than the particle size of the molecular sieve particles. Voids and defects, which result in reduced overall selectivity, are easily formed at the interface of the large molecular sieve particles and the thin polymer matrix of the asymmetric MMMs. Therefore, controlling the thickness of the thin dense selective mixed matrix membrane layer and the particle size of the
25 molecular sieve particles is critical for making large scale asymmetric MMMs with at least 20% increase in selectivity compared to the corresponding asymmetric polymer membranes containing no molecular sieves.

SUMMARY OF THE INVENTION

[0009] This invention pertains to a new approach for making molecular sieve/polymer
30 mixed matrix membranes (MMM) and methods for using such membranes. This invention also pertains to methods to control the thickness of a thin dense selective mixed matrix layer

that is equal to or greater than the particle size of the largest molecular sieve particles for making large scale asymmetric MMMs with at least 20% increase in selectivity compared to the corresponding asymmetric polymer membranes containing no molecular sieves.

[0010] The MMMs described in the current invention contain a thin dense selective

5 permeable layer which comprises a continuous polymer matrix and discrete molecular sieve particles uniformly dispersed throughout the continuous polymer matrix. The molecular sieves in the MMMs can produce membranes having a selectivity and/or permeability that is significantly higher than the pure polymer membranes for separations. Addition of a small weight percent of molecular sieves to the polymer matrix, therefore, increases the overall
10 separation efficiency significantly. The molecular sieves used in the MMMs of current invention include microporous and mesoporous molecular sieves, carbon molecular sieves, and porous metal-organic frameworks (MOFs). The microporous molecular sieves are selected from alumino-phosphate molecular sieves such as A1PO-18, A1PO-14, A1PO-53, and A1PO-17, aluminosilicate molecular sieves such as 4A, 5A, UZM-5, UZM-25, and UZM-9,
15 silico-alumino-phosphate molecular sieves such as SAPO-34, and mixtures thereof. The continuous polymer matrix is selected from glassy polymers such as cellulose acetates, cellulose triacetates, polyimides, and polymers of intrinsic microporosity.

[0011] The present invention is directed to making an asymmetric thin-film composite (TFC) MMM with a selectivity increase of at least 20% compared to the corresponding

20 asymmetric polymer membranes containing no molecular sieves. The MMM is prepared by coating a thin layer of molecular sieve/polymer mixed matrix solution on top of a porous support membrane followed by drying the membrane to remove organic solvents. The molecular sieve/polymer mixed matrix solution is prepared by: (a) dispersing molecular sieve particles in an organic solvent or a mixture of two or more organic solvents by ultrasonic
25 mixing and/or mechanical stirring or other method to form a molecular sieve slurry; (b) if necessary, dissolving a polymer in the molecular sieve slurry to functionalize the surface of molecular sieve particles; (c) dissolving a polymer or a blend of two polymers that serves as a continuous polymer matrix in the molecular sieve slurry to form a stable molecular sieve/polymer solution.

30 [0012] The MMM described in the present invention is in a form of thin-film composite (TFC). In connection with the process for preparation of a MMM, a membrane post-treatment step can be added after making the asymmetric TFC MMM to improve selectivity without

changing or damaging the membrane, or LeenSteven@aol.com causing the membrane to lose performance with time. The membrane post-treatment step can involve coating the selective layer surface of the MMM with a thin layer of material such as a polysiloxane, a fluoropolymer, a thermally curable silicone rubber, or a UV radiation curable silicone rubber

5 [0013] One important requirement is to control the minimal thickness of the thin dense selective mixed matrix layer equal or larger than the particle size of the largest molecular sieve particles dispersed in the polymer matrix.

[0014] The MMMs fabricated using the approach described in the present invention combine the solution-diffusion mechanism of polymer membrane and the molecular sieving and sorption mechanism of molecular sieves, and assure maximum selectivity and consistent performance among different membrane samples comprising the same molecular sieve/polymer composition.

10 [0015] The approaches described herein for producing voids and defects free, high performance MMMs are suitable for large scale membrane production and can be integrated into commercial polymer membrane manufacturing processes.

[0016] The invention provides a process for separating at least one gas from a mixture of gases using the MMMs, the process comprising: (a) providing such MMM comprising molecular sieve particles uniformly dispersed in a continuous polymer matrix which is permeable to said at least one gas; (b) contacting the mixture on one side of the MMM to cause said at least one gas to permeate the MMM; and (c) removing from the opposite side of the membrane a permeate gas composition comprising a portion of said at least one gas which permeated said membrane.

25 [0017] The MMMs of the present invention are suitable for a variety of liquid, gas, and vapor separations such as deep desulphurization of gasoline and diesel fuels, ethanol/water separations, pervaporation dehydration of aqueous/organic mixtures, CO₂/CH₄, CO₂/N₂, H₂/CH₄, O₂/N₂, olefin/paraffin, iso/normal paraffins separations, and other light gas mixture separations. The MMMs of the present invention have significantly improved selectivity and/or flux for these separations compared to the polymer membranes prepared from their corresponding continuous polymer matrices.

DETAILED DESCRIPTION OF THE INVENTION

[0018] This invention pertains to an approach for making molecular sieve/polymer mixed matrix membranes (MMMs) and methods for using these membranes. This invention also pertains to methods to control the thickness of the thin dense selective mixed matrix layer equal or greater than the particle size of the largest molecular sieve particles for making large scale asymmetric MMMs. The MMM prepared in the present invention comprising molecular sieves dispersed in a continuous polymer matrix exhibits a selectivity increase of at least 20% relative to a polymer membrane made from the continuous polymer matrix without molecular sieves.

[0019] The MMMs of the current invention are prepared from stabilized molecular sieve/polymer mixed matrix solution (or dope) by controlling the thickness of the thin dense selective mixed matrix layer equal to or greater than the particle size of the largest molecular sieve particles. The term "mixed matrix" as used in this invention means that the membrane has a thin dense selective permeable layer which comprises a continuous polymer matrix and discrete molecular sieve particles uniformly dispersed throughout the continuous polymer matrix. The terms "nano-sized" and "nano-particle" as used in this invention mean that the particle size is ≤ 500 nm. The term "small pore" refers to molecular sieves which have less than or equal to 8-ring openings in their framework structure.

[0020] The MMMs described in the current invention contain a thin dense selective permeable layer which comprises a continuous polymer matrix and discrete molecular sieve particles uniformly dispersed throughout the continuous polymer matrix. The molecular sieves in the MMMs provided in this invention can have selectivity and/or permeability that are significantly higher than the pure polymer membranes for separations. Addition of a small weight percent of molecular sieves to the polymer matrix, therefore, increases the overall separation efficiency significantly. The molecular sieves used in the MMMs of current invention include microporous and mesoporous molecular sieves, carbon molecular sieves, and porous metal-organic frameworks (MOFs).

[0021] Molecular sieves improve the performance of the MMM by including selective holes/pores with a size that permits a gas such as carbon dioxide to pass through, but either does not permit another gas such as methane to pass through, or permits it to pass through at a significantly slower rate. The molecular sieves should have higher selectivity for the desired separations than the original polymer to enhance the performance of the MMM. In order to

obtain the desired gas separation in the MMM, it is preferred that the steady-state permeability of the faster permeating gas component in the molecular sieves be at least equal to that of the faster permeating gas in the original polymer matrix phase. Molecular sieves have framework structures which may be characterized by distinctive wide-angle X-ray diffraction patterns. Zeolites are a subclass of molecular sieves based on an aluminosilicate composition. Non-zeolitic molecular sieves are based on other compositions such as aluminophosphates, silico-aluminophosphates, and silica. Molecular sieves of different chemical compositions can have the same framework structure.

[0022] Zeolites can be further broadly described as molecular sieves in which complex aluminosilicate molecules assemble to define a three-dimensional framework structure enclosing cavities occupied by ions and water molecules which can move with significant freedom within the zeolite matrix. In commercially useful zeolites, the water molecules can be removed or replaced without destroying the framework structure. A zeolite composition can be represented by the following formula: $M_{2/n}O : Al_2O_3 : xSiO_2 : yH_2O$, wherein M is a cation of valence n, x is greater than or equal to 2, and y is a number determined by the porosity and the hydration state of the zeolites, generally from 0 to 8. In naturally occurring zeolites, M is principally represented by Na, Ca, K, Mg and Ba in proportions usually reflecting their approximate geochemical abundance. The cations M are loosely bound to the structure and can frequently be completely or partially replaced with other cations or hydrogen by conventional ion exchange. Acid forms of molecular sieve sorbents can be prepared by a variety of techniques including ammonium exchange followed by calcination or by direct exchange of alkali ions for protons using mineral acids or ion exchangers.

[0023] Microporous molecular sieve materials are microporous crystals with pores of a well-defined size ranging from 0.2 to 2 nm. This discrete porosity provides molecular sieving properties to these materials which have found wide applications as catalysts and sorption media. Molecular sieve structure types can be identified by their structure type code as assigned by the IZA Structure Commission following the rules set up by the IUPAC Commission on Zeolite Nomenclature. Each unique framework topology is designated by a structure type code consisting of three capital letters. Exemplary compositions of such small pore alumina containing molecular sieves include non-zeolitic molecular sieves (NZMS) comprising certain aluminophosphates (AlPO's), silicoaluminophosphates (SAPO's),

metallo-aluminophosphates (MeAPO's), elemental aluminophosphates (ElAPO's), metallo-silicoaluminophosphates (MeAPSO's) and elemental silicoaluminophosphates (ElAPSO's).

[0024] To date, almost all of the studies on mixed matrix membranes use large molecular sieve particles with particle sizes in the micron range. See Yong, et al., J. MEMBR. SCI., 188:151 (2001); US 5,127,925; US 4,925,562; US 4,925,459; US 2005/0043167 A1. Commercially available polymer membranes, such as CA and polysulfone membranes, however, have an asymmetric membrane structure with a less than 500 nm thin dense selective layer supported on a porous non-selective layer. As a consequence, the dense selective layer thickness of the asymmetric mixed matrix membranes is much thinner than the particle size of the molecular sieves. Voids and defects, which result in poor mechanical stability and poor selectivity, are easily formed in these asymmetric MMMs. Nano-sized molecular sieves have been developed recently, which leads to the possibility to prepare high selectivity, thin dense selective mixed matrix layer of ≤ 500 nm. See Zhu, et al., CHEM. MATER., 10:1483 (1998); Ravishankar, et al., J. PHYS. CHEM., 102:2633 (1998); Huang, et al., J. AM. CHEM. SOC., 122:3530 (2000). As an example, Brown et al. reported the synthesis of nano-sized SAPO-34 molecular sieve having a cubic-like crystal morphology with edges of less than 100 nm. See Brown et al., US 2004/0082825 A1 (2004). Vankelecom et al. reported the first incorporation of nano-sized zeolites in thick symmetric mixed matrix membranes by dispersing colloidal silicalite-1 in polydimethylsiloxane polymer membrane. See Moermans, et al., CHEM. COMMUN., 2467 (2000). Homogeneous symmetric thick polymer/zeolite mixed matrix membranes have also been fabricated by the incorporation of dispersible template-removed zeolite A nanocrystals into polysulfone matrix. See Yan, et al., J. MATER. CHEM., 12:3640 (2002).

[0025] Some preferred microporous molecular sieves used in the current invention include small pore molecular sieves such as SAPO-34, Si-DDR, UZM-9, AlPO-14, AlPO-34, AlPO-53, AlPO-17, SSZ-62, SSZ-13, AlPO-18, ERS-12, CDS-I, MCM-65, MCM-47, 4A, 5A, UZM-5, UZM-25, AlPO-34, SAPO-44, SAPO-47, SAPO-17, CVX-7, SAPO-35, SAPO-56, AlPO-52, SAPO-43, medium pore molecular sieves such as silicalite-1, and large pore molecular sieves such as NaX, NaY, and CaY.

[0026] The microporous molecular sieves used in the current invention are capable of separating mixtures of molecular species based on the molecular size or kinetic diameter

(molecular sieving mechanism). The separation is accomplished by the smaller molecular species entering the intracrystalline void space while excluding larger species.

[0027] The microporous molecular sieves used in the current invention improve the performance of the MMM by including selective holes/pores with a size that permit a smaller gas molecule to pass through, but do not permit another larger gas molecule to pass through, or permit it to pass through at a significantly slower rate.

[0028] Another type of molecular sieves used in the MMMs provided in this invention are mesoporous molecular sieves. Examples of preferred mesoporous molecular sieves include MCM-41, SBA-15, and surface functionalized MCM-41 and SBA-15, etc.

[0029] Metal-organic frameworks (MOFs) can also be used as the molecular sieves in the MMMs described in the present invention. MOFs are a new type of highly porous crystalline zeolite-like materials and are composed of rigid organic units assembled by metal-ligands. They possess vast accessible surface areas per unit mass. See Yaghi et al., SCIENCE, 295: 469 (2002); Yaghi et al., MICROPOR. MESOPOR. MATER., 73: 3 (2004); Dybtsev et al., ANGEW. CHEM. INT. ED., 43: 5033 (2004). MOF-5 is a prototype of a new class of porous materials constructed from octahedral Zn-O-C clusters and benzene links. Most recently, Yaghi et al. reported the systematic design and construction of a series of frameworks (IRMOF) that have structures based on the skeleton of MOF-5, wherein the pore functionality and size have been varied without changing the original cubic topology. For example, IRMOF-I ($Zn_4O(R)-BDC)_3$) has the same topology as that of MOF-5, but was synthesized by a simplified method. In 2001, Yaghi et al. reported the synthesis of a porous metal-organic polyhedron (MOP) $Cu_{24}(In-BDC)_{24}(DMF)_{14}(H_2O)_{50}(DMF)_6(C_2H_5OH)_6$, termed " α -MOP-1" and constructed from 12 paddle-wheel units bridged by m-BDC to give a large metal-carboxylate polyhedron. See Yaghi et al., J. AM. CHEM. SOC, 123: 4368 (2001). These MOF, IR-MOF and MOP materials exhibit analogous behaviour to that of conventional microporous materials such as large and accessible surface areas, with interconnected intrinsic micropores. Moreover, they may reduce the hydrocarbon fouling problem of the polyimide membranes due to relatively larger pore sizes than those of zeolite materials. MOF, IR-MOF and MOP materials are also expected to allow the polymer to infiltrate the pores, which would improve the interfacial and mechanical properties and would in turn affect permeability. Therefore, these MOF, IR-MOF and MOP materials (all termed "MOF" herein this invention) are used as molecular sieves in the preparation of MMMs in the present invention.

[0030] The particle size of the molecular sieves dispersed in the continuous polymer matrix of the MMMs in the present invention is less than or equal to the thickness of the thin dense selective mixed matrix layer. The median particle size should be less than 10 μm , preferably less than 5 μm , and more preferably less than 1 μm . Most preferably, nano-molecular sieves (or "molecular sieve nanoparticles") should be used in the MMMs of the current invention.

[0031] Nano-molecular sieves described herein are sub-micron size molecular sieves with particle sizes in the range of 5 to 500 nm. Nano-molecular sieve selection for the preparation of MMMs includes screening the dispersity of the nano-molecular sieves in organic solvent, the porosity, particle size, and surface functionality of the nano-molecular sieves, the adhesion or wetting property of the nano-molecular sieves with the polymer matrix. Nano-molecular sieves for the preparation of MMMs should have suitable pore size to allow selective permeation of a smaller sized gas, and also should have appropriate particle size in the nanometer range to prevent defects in the membranes. The nano-molecular sieves should be easily dispersed without agglomeration in the polymer matrix to maximize the transport property.

[0032] Representative examples of nano-molecular sieves suitable to be incorporated into the MMMs described herein include silicalite-1, SAPO-34, Si-DDR, AIPO-14, A1PO-34, A1PO-53, A1PO-18, SSZ-62, UZM-5, UZM-9, UZM-25, MCM-65, AIPO-17, ERS-12, CDS-1, SAPO-44, SAPO-47, SAPO-17, CVX-7, SAPO-35, SAPO-56, A1PO-52, and SAPO-43.

[0033] The MMMs described in the current invention contain a thin dense selective permeable layer which comprises a continuous polymer matrix and discrete molecular sieve particles uniformly dispersed throughout the continuous polymer matrix. The polymer that serves as the continuous polymer matrix in the MMM of the present invention provides a wide range of properties important for separations, and modifying it can improve membrane selectivity. A material with a high glass transition temperature (T_g), high melting point, and high crystallinity is preferred for most gas separations. Glassy polymers (i.e., polymers below their T_g) have stiffer polymer backbones and therefore let smaller molecules such as hydrogen and helium permeate the membrane more quickly and larger molecules such as hydrocarbons permeate the membrane more slowly. For the MMM applications in the present invention, it is preferred that the membrane fabricated from the pure polymer, which can be used as the continuous polymer matrix in MMMs, exhibits a carbon dioxide over methane

selectivity of at least 8, more preferably at least 15 at 50°C and 690 kPa (100 psig) pure carbon dioxide or methane testing pressure. Preferably, the polymer that serves as the continuous polymer matrix in the MMM of the present invention is a rigid, glassy polymer. The weight ratio of the molecular sieves to the polymer that serves as the continuous polymer matrix in the MMM of the current invention can be within a broad range from 1:100 (1 weight part of molecular sieves per 100 weight parts of the polymer that serves as the continuous polymer matrix) to 2:1 (200 weight parts of molecular sieves per 100 weight parts of the polymer that serves as the continuous polymer matrix) depending upon the properties sought as well as the dispersibility of the molecular sieve particles in the particular continuous polymer matrix.

[0034] Typical polymers that serve as the continuous polymer matrix in the MMM can be selected from, but not limited to, polysulfones; sulfonated polysulfones; polyethersulfones (PESs); sulfonated PESs; polyethers; polyetherimides such as Ultem (or Ultem 1000) sold under the trademark Ultem®, manufactured by Sabic Innovative Plastics, poly(styrene)s, including styrene-containing copolymers such as acrylonitrilestyrene copolymers, styrene-butadiene copolymers and styrene-vinylbenzylhalide copolymers; polycarbonates; cellulosic polymers, such as cellulose acetate, cellulose triacetate, cellulose acetate-butyrate, cellulose propionate, ethyl cellulose, methyl cellulose, nitrocellulose; polyamides; polyimides such as Matrimid sold under the trademark Matrimid® by Huntsman Advanced Materials (Matrimid® 5218 refers to a particular polyimide polymer sold under the trademark Matrimid®) and P84 or P84HT sold under the tradename P84 and P84HT respectively from HP Polymers GmbH; polyamide/imides; polyketones, polyether ketones; poly(arylene oxide)s such as poly(phenylene oxide) and poly(xylene oxide); poly(esteramide-diisocyanate); polyurethanes; polyesters (including polyarylates), such as poly(ethylene terephthalate), poly(alkyl methacrylate)s, poly(acrylate)s, poly(phenylene terephthalate), etc.; polysulfides; polymers from monomers having alpha-olefinic unsaturation other than mentioned above such as poly(ethylene), poly(propylene), poly(butene-1), poly(4-methyl pentene-1), polyvinyls, e.g., poly(vinyl chloride), poly(vinyl fluoride), poly(vinylidene chloride), poly(vinylidene fluoride), poly(vinyl alcohol), poly(vinyl ester)s such as poly(vinyl acetate) and poly(vinyl propionate), poly(vinyl pyridine)s, poly(vinyl pyrrolidone)s, poly(vinyl ether)s, poly(vinyl ketone)s, poly(vinyl aldehyde)s such as poly(vinyl formal) and poly(vinyl butyral), poly(vinyl amide)s, poly(vinyl amine)s, poly(vinyl urethane)s, poly(vinyl urea)s, poly(vinyl

phosphate)s, and poly(vinyl sulfate)s; polyallyls; poly(benzobenzimidazole)s; polybenzoxazoles; polyhydrazides; polyoxadiazoles; polytriazoles; poly(benzimidazole)s; polycarbodiimides; polyphosphazines; microporous polymers; and interpolymers, including block interpolymers containing repeating units from the above such as interpolymers of acrylonitrile-vinyl bromide-sodium salt of para-sulfophenylmethallyl ethers; and grafts and blends containing any of the foregoing. Typical substituents providing substituted polymers include halogens such as fluorine, chlorine and bromine; hydroxyl groups; lower alkyl groups; lower alkoxy groups; monocyclic aryl; lower acryl groups and the like.

[0035] Some preferred polymers that can serve as the continuous polymer matrix include, but are not limited to, polysulfones, sulfonated polysulfones, polyethersulfones (PESs), sulfonated PESs, polyvinyl alcohol)s, polyetherimides such as Ultem (or Ultem 1000) sold under the trademark Ultem®, manufactured by Sabic Innovative Plastics, cellulosic polymers such as cellulose acetate and cellulose triacetate, polyamides, polyimides such as Matrimid sold under the trademark Matrimid® by Huntsman Advanced Materials (Matrimid® 5218 refers to a particular polyimide polymer sold under the trademark Matrimid®), P84 or P84HT sold under the tradename P84 and P84HT respectively from HP Polymers GmbH, poly(3,3',4,4'-benzophenone tetracarboxylic dianhydride-pyromellitic dianhydride-3,3',5,5'-tetramethyl-4,4'-methylene dianiline) (poly(BTDA-PMDA-TMMDA)), poly(3,3',4,4'-diphenylsulfone tetracarboxylic dianhydride-3,3',5,5'-tetramethyl-4,4'-methylene dianiline) (poly(DSDA-TMMDA)), poly(3,3',4,4'-benzophenone tetracarboxylic dianhydride-3,3',5,5'-tetramethyl-4,4'-methylene dianiline) (poly(BTDA-TMMDA)), poly(3,3',4,4'-diphenylsulfone tetracarboxylic dianhydride-pyromellitic dianhydride-3,3',5,5'-tetramethyl-4,4'-methylene dianiline) (poly(DSDA-PMDA-TMMDA)), poly[2,2'-bis-(3,4-dicarboxyphenyl)hexafluoropropane dianhydride-1,3-phenylenediamine] (poly(6FDA-m-PDA)), poly[2,2'-bis-(3,4-dicarboxyphenyl) hexafluoropropane dianhydride-1,3-phenylenediamine-3,5-diaminobenzoic acid] (poly(6FDA-m-PDA-DABA)), poly(3,3',4,4'-benzophenone tetracarboxylic dianhydride-pyromellitic dianhydride-4,4' oxydiphthalic anhydride-3,3',5,5'-tetramethyl-4,4'-methylene dianiline) (poly(BTDA-PMDA-ODP A-TMMDA)), poly[2,2'-bis-(3,4-dicarboxyphenyl)hexafluoropropane dianhydride-2,2-bis(3-amino-4-hydroxyphenyl)-hexafluoropropane] (poly(6FDA-bis-AP-AF)), polyamide/imides, polyketones, polyether ketones, and polymers of intrinsic microporosity.

[0036] The most preferred polymers that can serve as the continuous polymer matrix include, but are not limited to, polyimides such as Matrimid®, P84®, poly(BTDA-PMDA-TMMDA), poly(BTDA-PMDA-ODPA-TMMDA), poly(DSDA-TMMDA), poly(BTDA-TMMDA), poly(6FDA~bis-AP-AF), and poly(DSDA-PMDA-TMMDA), polyetherimides such as Ultem®, polyethersulfones, polysulfones, cellulose acetate, cellulose triacetate, poly(vinyl alcohol)s, polybenzoxazoles, and polymers of intrinsic microporosity.

[0037] Microporous polymers (or as so-called "polymers of intrinsic microporosity") described herein are polymeric materials that possess microporosity that is intrinsic to their molecular structures. See McKeown, et al., CHEM. COMMUN., 2780 (2002); Budd, et al., ADV. MATER., 16:456 (2004); McKeown, et al., CHEM. EUR. J., 11:2610 (2005). This type of microporous polymers can be used as the continuous polymer matrix in MMMs in the current invention. The microporous polymers have a rigid rod-like, randomly contorted structure to generate intrinsic microporosity. These microporous polymers exhibit behavior analogous to that of conventional microporous molecular sieve materials, such as large and accessible surface areas, interconnected intrinsic micropores of less than 2 nm in size, as well as high chemical and thermal stability, but, in addition, possess properties of conventional polymers such as good solubility and easy processability. Moreover, these microporous polymers possess polyether polymer chains that have favorable interaction between carbon dioxide and the ethers.

[0038] The solvents used for dispersing molecular sieve particles and dissolving the continuous polymer matrix are chosen primarily for their ability to completely dissolve the polymers and for ease of solvent removal in the membrane formation steps. Other considerations in the selection of solvents include low toxicity, low corrosive activity, low environmental hazard potential, availability and cost. Representative solvents for use in this invention include most amide solvents that are typically used for the formation of polymeric membranes, such as N-methylpyrrolidone (NMP) and N,N-dimethyl acetamide (DMAC), methylene chloride, THF, acetone, isopropanol, octane, methanol, ethanol, DMF, DMSO, toluene, dioxanes, 1,3-dioxolane, mixtures thereof, others known to those skilled in the art and mixtures thereof.

[0039] In the present invention, MMMs can be fabricated from the stabilized molecular sieve/polymer mixed matrix solution (or dope) containing a mixture of solvents, molecular sieve particles, and a continuous polymer matrix.

[0040] The present invention is directed to make an asymmetric TFC MMM with a selectivity increase of at least 20% compared to the corresponding asymmetric polymer membranes containing no molecular sieves. The MMM is prepared by coating a thin layer of molecular sieve/polymer mixed matrix solution on top of a porous support membrane
5 followed by drying the membrane at a sufficient temperature to remove the organic solvents. The molecular sieve/polymer mixed matrix solution is prepared by: (a) dispersing molecular sieve particles in an organic solvent or a mixture of two or more organic solvents by ultrasonic mixing and/or mechanical stirring or other method to form a molecular sieve slurry; (b) dissolving a polymer in the molecular sieve slurry to functionalize the surface of
10 molecular sieve particles; In some cases, this step (b) is not necessary; (c) dissolving a polymer or a blend of two polymers that serves as a continuous polymer matrix in the molecular sieve slurry to form a stable molecular sieve/polymer solution. In some cases a membrane post-treatment step can be added after making the asymmetric TFC MMM to improve selectivity without changing or damaging the membrane, or causing the membrane
15 to lose performance with time. The membrane post-treatment step can involve coating the top surface of the asymmetric TFC MMM with a thin layer of material such as a polysiloxane, a fluoro-polymer, a thermally curable silicone rubber, or a UV radiation curable silicone rubber.

[0041] One critical requirement for this approach is to control the final minimal thickness
20 of the mixed matrix coating layer equal or larger than the particle size of the largest molecular sieve particles dispersed in the polymer matrix.

[0042] The MMMs fabricated using the novel approaches described in the present invention combine the solution-diffusion mechanism of polymer membrane and the molecular sieving and sorption mechanism of molecular sieves, and assure maximum
25 selectivity and consistent performance among different membrane samples comprising the same molecular sieve/polymer composition.

[0043] The approaches of the current invention for producing high performance MMMs is suitable for large scale membrane production and can be integrated into commercial polymer membrane manufacturing processes. The MMMs fabricated by the approaches
30 described in the current invention exhibit at least 20% increase in selectivity compared to the asymmetric polymer membranes prepared from their corresponding polymer matrices.

[0044] The invention provides a process for separating at least one gas from a mixture of gases using the MMMs described in the present invention, the process comprising: (a) providing a MMM comprising molecular sieve particles uniformly dispersed in a continuous polymer matrix which is permeable to said at least one gas; (b) contacting the mixture on one side of the MMM to cause said at least one gas to permeate the MMM; and (c) removing from the opposite side of the membrane a permeate gas composition comprising a portion of said at least one gas which permeated said membrane.

[0045] The MMMs of the present invention are especially useful in the purification, separation or adsorption of a particular species in the liquid or gas phase. In addition to separation of pairs of gases, these MMMs may, for example, be used for the separation of proteins or other thermally unstable compounds, e.g. in the pharmaceutical and biotechnology industries. The MMMs may also be used in fermenters and bioreactors to transport gases into the reaction vessel and transfer cell culture medium out of the vessel. Additionally, the MMMs may be used for the removal of microorganisms from air or water streams, water purification, ethanol production in a continuous fermentation/membrane pervaporation system, and in detection or removal of trace compounds or metal salts in air or water streams.

[0046] The MMMs of the present invention are especially useful in gas separation processes in air purification, petrochemical, refinery, and natural gas industries. Examples of such separations include separation of volatile organic compounds (such as toluene, xylene, and acetone) from an atmospheric gas, such as nitrogen or oxygen and nitrogen recovery from air. Further examples of such separations are for the separation of CO₂ from natural gas, H₂ from N₂, CH₄, and Ar in ammonia purge gas streams, H₂ recovery in refineries, olefin/paraffin separations such as propylene/propane separation, and iso/normal paraffin separations. Any given pair or group of gases that differ in molecular size, for example nitrogen and oxygen, carbon dioxide and methane, hydrogen and methane or carbon monoxide, helium and methane, can be separated using the MMMs described herein. More than two gases can be removed from a third gas. For example, some of the gas components which can be selectively removed from a raw natural gas using the membrane described herein include carbon dioxide, oxygen, nitrogen, water vapor, hydrogen sulfide, helium, and other trace gases. Some of the gas components that can be selectively retained include hydrocarbon gases.

[0047] The MMMs described in the current invention are also especially useful in gas/vapor separation processes in chemical, petrochemical, pharmaceutical and allied industries for removing organic vapors from gas streams, e.g. in off-gas treatment for recovery of volatile organic compounds to meet clean air regulations, or within process streams in production plants so that valuable compounds (e.g., vinylchloride monomer, propylene) may be recovered. Further examples of gas/vapor separation processes in which these MMMs may be used are hydrocarbon vapor separation from hydrogen in oil and gas refineries, for hydrocarbon dew pointing of natural gas (i.e. to decrease the hydrocarbon dew point to below the lowest possible export pipeline temperature so that liquid hydrocarbons do not separate in the pipeline), for control of methane number in fuel gas for gas engines and gas turbines, and for gasoline recovery. The MMMs may incorporate a species that adsorbs strongly to certain gases (e.g. cobalt porphyrins or phthalocyanines for O₂ or silver (I) for ethane) to facilitate their transport across the membrane.

[0048] These MMMs may also be used in the separation of liquid mixtures by pervaporation, such as in the removal of organic compounds (e. g., alcohols, phenols, chlorinated hydrocarbons, pyridines, ketones) from water such as aqueous effluents or process fluids. A membrane which is ethanol-selective would be used to increase the ethanol concentration in relatively dilute ethanol solutions (5-10% ethanol) obtained by fermentation processes. Another liquid phase separation example using these MMMs is the deep desulfurization of gasoline and diesel fuels by a pervaporation membrane process similar to the process described in US 7,048,846, incorporated by reference herein in its entirety. The MMMs that are selective to sulfur-containing molecules would be used to selectively remove sulfur-containing molecules from fluid catalytic cracking (FCC) and other naphtha hydrocarbon streams. Further liquid phase examples include the separation of one organic component from another organic component, e. g. to separate isomers of organic compounds. Mixtures of organic compounds which may be separated using an inventive membrane include: ethylacetate-ethanol, diethylether-ethanol, acetic acid-ethanol, benzene-ethanol, chloroform-ethanol, chloroform-methanol, acetone-isopropylether, allyl alcohol-allylether, allyl alcohol-cyclohexane, biitanol-butylacetate, butanol-1-butylether, ethanol-ethylbutylether, propylacetate-propanol, isopropylether-isopropanol, methanol-ethanol-isopropanol, and ethylacetate-ethanol-acetic acid.

[0049] The MMMs may be used for separation of organic molecules from water (e.g. ethanol and/or phenol from water by pervaporation) and removal of metal and other organic compounds from water.

[0050] An additional application of the MMMs is in chemical reactors to enhance the yield of equilibrium-limited reactions by selective removal of a specific product in an analogous fashion to the use of hydrophilic membranes to enhance esterification yield by the removal of water.

[0051] The MMMs described in the current invention have immediate applications for the separation of gas mixtures including carbon dioxide removal from natural gas. The MMM permits carbon dioxide to diffuse through at a faster rate than the methane in the natural gas. Carbon dioxide has a higher permeation rate than methane because of higher solubility, higher diffusivity, or both. Thus, carbon dioxide enriches on the permeate side of the membrane, and methane enriches on the feed (or reject) side of the membrane.

EXAMPLES

[0052] The following examples are provided to illustrate one or more preferred embodiments of the invention, but are not limited embodiments thereof. Numerous variations can be made to the following examples that lie within the scope of the invention.

EXAMPLE 1

[0053] A "Control" poly(DSDA-PMDA-TMMDA)-PES(50:50) (abbreviated as Control 1) polymer membrane was prepared. 3.0 g of poly(DSDA-PMDA-TMMDA) polyimide polymer and 3.0 g of polyethersulfone (PES) were dissolved in a solvent mixture of NMP and 1,3-dioxolane by mechanical stirring for 2 hours to form a homogeneous casting dope. The resulting homogeneous casting dope was allowed to degas overnight. A "Control 1" blend polymer membrane was prepared from the bubble free casting dope on a clean glass plate using a doctor knife with a 20-mil gap. The membrane together with the glass plate was then put into a vacuum oven. The solvents were removed by slowly increasing the vacuum and the temperature of the vacuum oven. Finally, the membrane was dried at 200°C under vacuum for at least 48 hours to completely remove the residual solvents to form "Control 1".

EXAMPLE 2

[0054] 23% AIPO-14/poly(DSDA-PMDA-TMMDA)-PES(50:50) mixed matrix membranes were prepared. A series of 23% AIPO-14/poly(DSDA~PMDA-TMMDA)-PES(50:50) MMMs with different thicknesses and containing 23 wt-% of dispersed AIPO-14 molecular sieve particles (the particle size of AIPO-14 $\leq 5 \mu\text{m}$, AIPO-14/(AIPO-14+PES+poly(DSDA-PMDA-TMMDA)) = 23 wt-%) in poly(DSDA-PMDA-TMMDA) polyimide and PES blend continuous polymer matrix were prepared as follows:

[0055] 1.8 g of AIPO-14 molecular sieve particles were dispersed in a mixture of 11.6 g of NMP and 17.2 g of 1,3-dioxolane by mechanical stirring and ultrasonication for 1 hour to form a slurry. Then 0.6 g of PES was added in the slurry. The slurry was stirred for at least 1 hour to completely dissolve PES polymer. After that, 3.0 g of poly(DSDA-PMDA-TMMDA) polyimide polymer and 2.4 g of PES polymer were added to the slurry and the resulting mixture was stirred for another 2 hours to form a stable casting dope containing 23 wt-% of dispersed AIPO-14 in the continuous poly(DSDA-PMDA-TMMDA) and PES blend polymer matrix. The stable casting dope was allowed to degas overnight.

[0056] A series of 23% AIPO-14/poly(DSDA-PMDA-TMMDA)-PES(50:50) MMMs with different thicknesses were prepared on clean glass plates from the bubble free stable casting dope using a casting knife. The thicknesses of the MMMs were controlled by the gap between the bottom surface of the casting knife and the surface of the glass plates. The film together with the glass plate was then put into a vacuum oven. The solvents were removed by slowly increasing the vacuum and the temperature of the vacuum oven. Finally, the membranes were dried at 200°C under vacuum for at least 48 hours to completely remove the residual solvents to form 23% AIPO-14/poly(DSDA-PMDA-TMMDA)-PES(50:50) MMMs with thicknesses of 72.6 μm (abbreviated as MMM 1), 27.9 μm (abbreviated as MMM 2), 17.8 μm (abbreviated as MMM 3), 12.2 μm (abbreviated as MMM 4), 6.35 μm (abbreviated as MMM 5), and 4.57 μm (abbreviated as MMM 6).

EXAMPLE 3

[0057] CO_2/CH_4 separation properties of Control 1, MMM 1, MMM 2, MMM 3, MMM 4, MMM 5, and MMM 6 were determined. The effect of the thickness of 23% AIPO-14/poly(DSDA-PMDA-TMMDA)-PES(50:50) MMMs on their CO_2/CH_4 separation

performance has been studied. MMMs with six different thicknesses from 72.6 μm to 4.57 μm have been prepared using AIPO- 14 molecular sieves with particle size $\leq 5 \mu\text{m}$ (table below). The MMMs including MMM 1, MMM 2, MMM 3, MMM 4, and MMM 5 with thicknesses from 72.6 μm to 6.35 μm , which are greater than the largest particle size of AIPO- 14 molecular sieve particles, have shown a similar -40% increase in $O_{\text{CO}_2/\text{CH}_4}$ and -55% increase in P_{CO_2} compared to a poly(DSDA-PMD A-TMMD A)-PES blend polymer membrane (Control 1) ($P_{\text{CO}_2} = 10.9$ Barrers and $\alpha_{\text{CO}_2/\text{CH}_4} = 23.2$). However, MMM 6 with thickness of 4.57 μm , which is less than the largest particle size of AIPO-14 molecular sieve particles, has shown major defects and no CO_2/CH_4 selectivity has been observed. These results have demonstrated that MMMs with significantly improved CO_2/CH_4 selectivity and CO_2 permeability can be prepared using AIPO- 14 molecular sieves with the largest particle size less than or equal to the thickness of the dense selective mixed matrix layer of the MMMs.

Pure gas permeation test results of Control 1, MMM 1, MMM 2, MMM 3, MMM 4, MMM 5, and MMM 6 for CO_2/CH_4 separation ^a

Membrane	P_{CO_2} (Barrer) ^b	$\alpha_{\text{CO}_2/\text{CH}_4}$
Control 1	10.9	23.2
MMM 1	17.2	32.9
MMM 2	16.8	31.4
MMM 3	17.0	34.7
MMM 4	17.6	31.0
MMM 5	17.0	34.4
MMM 5, repeat	17.3	32.9
MMM 6	leaky	

^a Tested at 50⁰C under 690 kPa (100 psig) pure gas pressure.

^b 1 Barrer = $10^{-10} \text{ cm}^3(\text{STP}).\text{cm}/\text{cm}^2.\text{sec}.\text{cmHg}$.

EXAMPLE 4

[0058] A 29% AIPO- 14/poly(BTDA-PMD A-ODPA-TMMD A)-PES(90: 10) asymmetric TFC MMM (abbreviated as MMM 7) was prepared. 4.0 g of AIPO- 14 molecular sieves with particle size of 0.5-2.5 μm were dispersed in a mixture of 70 g of NMP and 100 g of 1,3-dioxolane by mechanical stirring for 1 hour and then ultrasonication for 20 minutes to form a slurry. Then 1.0 g of PES was added to functionalize AIPO- 14 molecular sieves in the slurry. The slurry was stirred for at least 1 hour and then ultrasonicated for 20 minutes to completely

dissolve the PES polymer and functionalize the surface of AIPO- 14. After that, 9.0 g of poly(BTDA-PMDA-ODPA-TMMDA) polyimide polymer was added to the slurry and the resulting mixture was stirred for another 2 hours to form a stable MMM casting dope containing 29 wt-% of dispersed AIPO- 14 molecular sieves in the continuous poly(BTDA-
5 PMDA-ODPA-TMMDA) and PES blend polymer matrix (weight ratio of AIPO- 14/(AIPO- 14+poly(DSDA-PMDA-TMMDA))+PES) is 29:100; weight ratio of PES to poly(BTDA-PMDA-ODPA-TMMDA) is 10:90). The stable MMM casting dope was allowed to degas overnight.

[0059] An asymmetric TFC MMM 7 was prepared by dip-coating a thin layer of the
10 bubble free MMM casting dope on a porous non-selective cross-linked polyacrylonitrile support membrane. The thin layer of the MMM casting dope was evaporated at 55°C for 12 hours. Then the resulting asymmetric TFC MMM was dried at 85°C in an oven for 2 hours to completely remove the solvents. The dried asymmetric TFC MMM was coated with a thermally cross-linkable silicon rubber solution (RTV615A+B Silicon Rubber from GE
15 Silicons) containing 9 wt-% RTV615A and 1 wt-% RTV615B catalyst and 90 wt-% hexane solvent). The RTV615A+B coated membrane was cured at 85°C for 2 hours in an oven to cross-linked RTV615A+B silicon coating form the final MMM 7 asymmetric TFC mixed matrix membrane.

CLAIMS:

1. A process of making a mixed matrix membrane selected from the group consisting of asymmetric thin-film composite mixed matrix membranes, asymmetric hollow fiber mixed matrix membranes, and asymmetric flat sheet mixed matrix membranes wherein said process
5 comprises forming a solution comprising a mixture of molecular sieve particles, organic solvents and a polymer or blend of polymers, forming a thin layer of said solution on a substrate, and drying said mixture to remove said organic solvent wherein said thin layer is equal to or larger in thickness than any of said molecular sieve particles.

2. The process of claim 1 wherein said asymmetric thin-film composite mixed matrix
10 membranes are prepared by preparing a molecular sieve slurry by first dispersing a quantity of said molecular sieve particles in one or more of said organic solvents, then dissolving said polymer or a blend of polymers into said molecular sieve slurry to form said solution and then coating said thin layer of said solution on a top surface of a porous support membrane followed by said drying at a temperature sufficient to remove said organic solvents.

3. The process of claim 1 for making said asymmetric hollow fiber mixed matrix
15 membranes wherein said asymmetric hollow fiber membranes have at least 20% increase in selectivity compared to asymmetric polymer membranes prepared from their corresponding polymer matrices, wherein said process comprises:

a) dispersing said molecular sieve particles in said organic solvent or a mixture of
20 two or more organic solvents to form a molecular sieve slurry;

b) dissolving said polymer or a blend of two polymers that serve as a continuous
polymer matrix in the molecular sieve slurry;

c) adding one or more organic solvents that cannot dissolve the continuous polymer
matrix to the molecular sieve slurry and stirring to form a stable molecular
25 sieve/polymer spinning solution;

d) spinning hollow fiber mixed matrix membranes from the stable molecular
sieve/polymer spinning solution using a hollow fiber spinning machine;

e) evaporating the organic solvents for a certain time by controlling the air gap to
form a wet hollow fiber mixed matrix membrane with said thin dense selective
30 mixed matrix layer with said thickness equal to or greater than the particle size of the largest molecular sieve particles on the surface;

- f) dipping the wet hollow fiber mixed matrix membrane into a water bath to generate the porous non-selective pure polymer or mixed matrix membrane support layer below the thin dense selective mixed matrix top layer by phase inversion; and
- g) washing and drying the asymmetric hollow fiber mixed matrix membrane.

5

4. The process of claim 1 for making said asymmetric flat sheet mixed matrix membranes wherein said asymmetric flat sheet mixed matrix membranes have at least a 20% increase in selectivity compared to asymmetric polymer membranes prepared from a corresponding polymer matrices, said process comprising:

10

- a) dispersing said molecular sieve particles in said organic solvent or a mixture of two or more organic solvents to form a molecular sieve slurry;

- b) dissolving said polymer or a blend of two polymers that serve as a continuous polymer matrix in the molecular sieve slurry;

15

- c) adding one or more organic solvents that cannot dissolve the polymer matrix to the molecular sieve/polymer slurry and stirring for a sufficient time to form a stable molecular sieve/polymer casting dope;

- d) casting a thin layer of the molecular sieve/polymer casting dope on top of a porous fabric support to form said thin layer of said solution;

20

- e) evaporating the organic solvents for a sufficient time to form a wet mixed matrix membrane with a thin dense selective mixed matrix layer with said thickness equal to or greater than said particle size of the largest molecular sieve particles on said top of said porous fabric support;

- f) dipping the wet mixed matrix membrane into a cold water bath to generate a porous non-selective mixed matrix support layer below the thin dense selective mixed matrix layer by phase inversion;

25

- g) dipping the asymmetric mixed matrix membrane into a hot water bath to remove residue organic solvents in the mixed matrix membrane; and

- h) washing and drying the asymmetric flat sheet mixed matrix membrane.

5. The process of claim 2, 3 or 4 further comprising dissolving a second polymer in the molecular sieve slurry to functionalize an outer surface of said molecular sieve particles.

30

6. The process of claim 1 wherein a coating is added to a top surface of said mixed matrix membrane wherein said coating comprises a material selected from the group

consisting of a polysiloxane, a fluoropolymer, a thermally curable silicone rubber and a UV radiation curable silicone polymer.

7. The process of claim 1 wherein said mixed matrix membrane exhibits at least 20% increase in selectivity compared to the polymer membrane prepared from its corresponding polymer matrix.

8. The process of claim 5 wherein said second polymer is selected from the group consisting of polyethersulfones, sulfonated polyethersulfones, hydroxyl group-terminated poly(ethylene oxide)s, amino group-terminated poly(ethylene oxide)s, or isocyanate group-terminated poly(ethylene oxide)s, poly(esteramide-diisocyanate)s, hydroxyl group-terminated poly(propylene oxide)s, hydroxyl group-terminated co-block-poly(ethylene oxide)-poly(propylene oxide)s, hydroxyl group-terminated tri-block-poly(propylene oxide)-block-poly(ethylene oxide)-block-poly(propylene oxide)s, tri-block-poly(propylene glycol)-block-poly(ethylene glycol)-block-poly(propylene glycol) bis(2-aminopropyl ether), polyether ketones, poly(ethylene imine)s, poly(amidoamine)s, poly(vinyl alcohol)s, poly(allyl amine)s, poly(vinyl amine)s, and cellulosic polymers.

9. The process of claim 1, 2, 3 or 4 wherein said polymer is selected from the group consisting of polysulfones; polyetherimides; cellulosic polymers; polyamides; polyimides; polyamide/imides; polyether ketones; poly(ether ether ketone)s, poly(arylene oxides); poly(esteramide-diisocyanate); polyurethanes; poly(benzobenzimidazole)s; polyhydrazides; polyoxadiazoles; polytriazoles; poly(benzimidazole)s; polybenzoxazoles; polycarbodiimides; polyphosphazines; microporous polymers; and mixtures thereof.

10. The process of claim 1, 2, 3 or 4 wherein said mixed matrix membrane is used for a separation selected from the group consisting of deep desulfurization of gasoline or diesel fuels, ethanol/water separations, pervaporation dehydration of aqueous/organic mixtures, or gas separations.

A. CLASSIFICATION OF SUBJECT MATTER**BOID 71/00(2006.01)1, BOID 69/00(2006.01)1**

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC BOID 53/22, 71/06, BOIJ 20/28

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

eKIPASS(KIPO internal) "method, molecular sieve, polymer, mixed matrix membrane, polysiloxane, PVA, spinning, casting"

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No
X	US 07166146 B2 (Stephen J Miller, etc) 23 Jan 2007	1, 7, 9, 10
Y	See abstract, columns 1—22, and claims 1—38	2-6, 8
Y	KR 10200501 13974 A 1 (KOREA RES INS OF CHEM TECH) 05 Dec 2005 See abstract, pages 1-4, and claims 1-3	2, 5, 6, 8
Y	US 07109140 B2 (Eva Marand, etc) 19 Sep 2006 See abstract, columns 1-19, and claims 1-25	3, 4, 5, 8

 Further documents are listed in the continuation of Box C See patent family annex

* Special categories of cited documents

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance, the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance, the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

20 MAY 2009 (20 05 2009)

Date of mailing of the international search report

21 MAY 2009 (21.05.2009)

Name and mailing address of the ISA/KR

Korean Intellectual Property Office
Government Complex-Daejeon, 139 Seonsa-ro, Seo-
gu, Daejeon 302-701, Republic of Korea

Facsimile No 82-42-472-7140

Authorized officer

CHO Jun Bae

Telephone No 82-42-481-8292



INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2008/084144

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 7166146 B2	23.01.2007	AU 2004-311621 A 1 P 1 0418045 A CA 2551497 A 1 CN 1898008 A GB 0614169 DO JP 2007-520334 T US 2005-0139066 A 1 US 7166146 B2 WO 2005-065112 A2 WO 2005-065112 A3	21.07.2005 17.04.2007 21.07.2005 17.01.2007 30.08.2006 26.07.2007 30.06.2005 23.01.2007 21.07.2005 05.01.2006
KR 1020050113974 A 1	NONE		
US 7109140 B2	19.09.2006	US 2003-0220188 A 1	27.11.2003