

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(10) International Publication Number

WO 2018/020228 A1

(43) International Publication Date  
01 February 2018 (01.02.2018)

(51) International Patent Classification:  
*G21F 9/00* (2006.01)      *G21F 9/06* (2006.01)  
*C25F 1/00* (2006.01)

(74) Agent: BECKHAM, Robert; 5 Bushwood Drive, Dorridge, Solihull B93 8JL (GB).

(21) International Application Number:  
PCT/GB2017/052162

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(22) International Filing Date:  
25 July 2017 (25.07.2017)

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

(25) Filing Language: English


(26) Publication Language: English

(30) Priority Data:  
1612951.2      26 July 2016 (26.07.2016)      GB

(71) Applicant: C-TECH INNOVATION LIMITED [GB/GB]; Capenhurst Technology Park, Capenhurst Cheshire CH1 6EH (GB).

(72) Inventors: COLLINS, John; C-Tech Innovation Limited, Capenhurst Technology Centre, Capenhurst Cheshire CH1 6EH (GB). CRAWFORD, Robert; C-Tech Innovation Limited, Capenhurst Technology Centre, Capenhurst Cheshire CH1 6EH (GB).

(54) Title: ELECTROLYTIC TREATMENT FOR NUCLEAR DECONTAMINATION



(57) Abstract: A method of removing nuclear contamination from a surface comprising applying a DC-biased AC waveform in an electro-pickling process using nitric acid as the electrolyte.

WO 2018/020228 A1

[Continued on next page]

**Published:**

- *with international search report (Art. 21(3))*
- *with amended claims (Art. 19(1))*

## Description

### Title of Invention: Electrolytic Treatment for Nuclear Decontamination

#### Technical Field

[0001] This invention relates to the treatment of nuclear contamination especially its removal from surfaces.

#### Background Art

[0002] Decontamination of metal surfaces is a common problem in industry, including in the nuclear industry where metal comes into contact with radionuclides and becomes contaminated. Contaminated metal may include ducting, pipework, glove boxes, storage vessels, mechanical parts such as stirrers etc. Once the metal has been in contact with media containing radioactive species then there remains behind on the surface some residual radioactivity which cannot be removed by simple rinsing or washing, since the radioactive elements have either reacted with the surface or else penetrated a short way into it. There may be some diffusion into the surface, either directly into the surface of the metal and or along cracks propagating into the metal. The result is that there is radioactivity associated with the surface. Radioactive elements include uranium, plutonium and decay products thereof and also radioactive isotopes of other elements that have been exposed to radioactivity.

[0003] This is a problem because it makes the handling and disposal of such material hazardous. Operators cannot get close to it, or else they are not able to be near it for long, since proximity contributes to the allowable radiation exposure. Additional precautions and methods and facilities are required therefore to deal with this contamination, with the objectives of containing the contamination, minimising hazard to health, and recovering metal decontaminated metal for re-use via conventional recycling processes.

[0004] An additional challenge is that surface contamination is not static – it can change in response to a surface treatment. It is found in some instances that after removal of a contaminated surface layer that the contamination “sweats back” – that is to say that the radioactivity at the surface is reduced after the decontamination treatment but then subsequently increases. This is as a result of diffusion of species from the sub-surface layer to the newly created surface. This underlines the need for having effective control over any decontamination process.

[0005] A conventional means to deal with this problem is the physical removal and disposal of the whole item. The obvious drawback to this method is that the volume of con-

taminated material to be disposed of or stored is larger, and there is no possibility to return any of the material to general use via recycling.

[0006] A second means is to use a smelter as described in **US 5268128 A** (WESTINGHOUSE) 07-Dec-93 “Method and apparatus for cleaning contaminated particulate material”, with operating conditions such that the radioactive contamination ends up in the slag, which can be isolated and then stored indefinitely, combined with treatment of the radioactive metal waste using melt decontamination as described in **US US2013296629 A** (KEPCO NUCLEAR FUEL CO LTD ) 07-Nov-13 and recovering the bulk of the metal as an uncontaminated stream for reuse. This process is operated commercially. The disadvantage of this approach is that a large facility is required, which itself requires extensive control measures.

[0007] It is preferable therefore to have a means of decontaminating the material such that the larger part of the metallic base can be recycled without further precaution. This may be applied in-situ, to vessels for example, so that dismantling and decommissioning operations can be carried out with reduced hazard, and it may be applied after dismantling and with the objective of recovering more material for re-use.

[0008] The first step in any such process is the removal of any contaminants such as grease or paint. Suitable processes may include the use of solvents to remove greases and the use of abrasive techniques such as grit blasting to remove paint. Laser ablation as described **US 2009060780 A** (WESTINGHOUSE ELECTRIC GERMANY ) 05-Mar-09 “Device & method for the treatment and or decontamination of surfaces” or machining of surfaces may also be used. These methods are effective but are slow and manually intensive processes that generate particulate waste and vapours and therefore present additional hazard control and containment challenges. Solvent based processes have the additional disadvantage that organic material may be introduced that subsequently contaminates the downstream processing and extraction of radionuclides.

[0009] Having removed grease and paint a means of removing the surface layer of metal is required. There are various means known.

[0010] One method is to chemically dissolve the contaminated layer of metal, including any oxide or other deposited layer. The challenge is to dissolve this contaminated layer completely whilst at the same time dissolving only a finite and controlled amount of the uncontaminated substrate metal. Acid treatments are used for mild steel and stainless steel including 304 stainless steel and also for other materials. Nitric acid is commonly used in the nuclear industry because of the high solubility of the contaminants of interest as nitrates, and also because of the good corrosion resistance of 304 stainless steel to nitric acid. The radioactive contamination is recovered from the nitric acid by standard means including precipitation and flocculation, for example as used in the Enhanced Actinide Removal Plant (EARP) at Sellafield, UK.

[0011] Other chemical treatments of metal surfaces are known in the metals finishing industries where thermal processing of metals gives rise to an oxide surface layer which must be removed before further processing steps can be carried out. Various chemical treatments are known including the use of acetic acid (hence the use of the term “pickling”), sulphuric acid and other or additional agents such as hydrochloric acid for mild steel and hydrofluoric acid for stainless steel, or hydrofluoric/nitric acid mixtures. These treatments are not preferred for use in nuclear decontamination because they are incompatible with the stainless steel construction of the downstream effluent treatment plants.

[0012] A limitation with the use of nitric acid as a dissolution agent is that the dissolution reaction is slow so that very long treatment times are required. The rate of reaction can be increased through the addition of complexing agents such as chloride, fluoride, and organic complexing agents such as citric acid, oxalic acid and ethylene diamine tetra acetic acid. These agents increase the rate of reaction with the surface contamination but at the expense of creating a liquid which is more corrosive and which cannot be treated using conventional nuclear effluent treatment plant, being corrosive to the metals used in their construction.

[0013] A different method of surface decontamination is to use an electrochemical process, for example as disclosed in **US 7384529 B** (US ENERGY) 10-Jun-08 “Method for electrochemical decontamination of radioactive metal”, where a current is passed through the contaminated article using a conductive electrolyte bath. Electrochemical descaling (or “electro-pickling”) is commonly used in metals processing. This method has the significant advantage over chemical methods in that the rate of surface removal is very much greater than with chemical methods. The practical consequence is that for a given through-put of surface to be decontaminated an electrochemical treatment requires a much smaller quantity of acid reagent than a chemical treatment. An additional advantage is that electrochemical processes are easily controllable since an electrochemical process responds immediately to the level of current passing which in turn is determined by the electrical potential applied. Electrochemical processes have the significant drawback however in that they are only effective where the geometry allows the placement of the counter-electrode close to the working piece. This is because the electric field and hence the current density decreases quickly with increasing distance from the counter electrode. In the present invention this limitation is referred to as a limited “throwing power” compared to chemical etching methods which act wherever fresh solution comes into contact with metal. “Throwing power” is a term used in the electroplating industry. A good throwing power in an electro-plating process refers to relatively higher rates of electro-plating in areas where the electric field is weak, in comparison with poor throwing power where the rate of deposition is

relatively slower in the same areas of weak electric field. In describing this invention “throwing power” is used in the following sense for electro-chemical removal of surface layers: a good throwing power means that the rate of surface removal is relatively high in areas of weak electric field compared to a process with poorer throwing power where the rate of removal in an area of weak electric field is relatively lower.

[0014] The choice of electrical waveform for use in electro-pickling has been the subject of previous study and it has been found advantageous to combine a direct current offset to an alternating current waveform principally because this gives a much faster process than either the use of DC current alone or the use of chemical methods. It has been shown in **US 2003075456 A** (COLLINS ET AL ) 24-Apr-03 that it is possible to descale a wide range of metals coated with oxide films more rapidly using AC waveforms with DC bias, than when using AC waveforms without DC bias. It was also shown that it can be advantageous to periodically reverse the polarity of the DC bias. Removal or cleaning of the oxide layers on the surface of metals was shown to be faster when a DC bias was applied to an AC waveform, compared to the use of AC current alone. The cleaning mechanism involves some dissolution of the contaminated layer, some undercutting where the underlying metal is dissolved, and some scrubbing action resulting from the generation of gas bubbles at the interface.

[0015] AC with DC bias allows breakdown of oxide film faster – because in the potential range where dissolution occurs DC current alone leads to either passivation of the surface or oxygen evolution and pitting, whereas AC current alone gives a reduced dissolution effect. AC current with DC bias is found to give the optimum dissolution whilst minimising localised pitting.

[0016] Ultrasonic energy may be applied in the electro-pickling process. Ultrasonic energy is known to improve the effectiveness of some electrochemical processes, by a combination of physical effects, including increased rates of diffusion at surfaces and the break-up of solid material close to the surface. Ultrasonic energy is difficult to apply in-situ in all situations however, because of geometrical constraints in locating transducers.

[0017] In summary, there are various surface treatment decontamination methods known in the nuclear industry, but none that achieve the desired combination of rapid surface decontamination, good controllability, good throwing power, all whilst retaining the ability to use conventional effluent treatment plants built from 304 stainless steel.

[0018] For the nuclear industry it is important to have a rapid and effective process, and one that generates an effluent that can be dealt with subsequently using conventional plant, which is to say that it does not corrode that plant, and in particular the use of chloride or organic anions is avoided.

## Disclosure of Invention

[0019] According to the present invention a method removing nuclear contamination from a surface comprising applying a DC-biased AC waveform in an electro-pickling process using nitric acid as the electrolyte.

[0020] It has been found surprisingly advantageous to have added a chloride or organic chelating additives to the nitric acid.

[0021] One can also include an electrochemical oxidative destruction process. Ideally the electrolyte is recirculated between the electrochemical oxidative destruction process and the electro-pickling process.

[0022] Employing these steps in combination achieves good removal rates and throwing power, good controllability of surface removal, and still allows effluent to be treated in a conventional based downstream treatment plant built to handle nitric acid based effluents.

[0023] The process described can be used for the decontamination of metals in the nuclear industry with effluent being treated in conventional treatment plants whilst at the same time allowing a greater flexibility of electrolyte composition, including the use of halides and organic metal complexing agents. These contribute to the effectiveness of the surface layer removal and are then themselves destroyed by an oxidative electrochemical reaction.

[0024] In the oxidative destruction part of the process, halides are converted to halogens and organic species are converted to carbon dioxide, both of which may be safely removed and disposed of since they are not radioactively contaminated, or only to a very low extent. The radio nucleotides remain in the electrolyte, ready for removal in further process steps such as precipitation and filtration.

[0025] Compared to previous processes this process allows rapid surface treatment, with effective control of the system, and allowing the use of conventional effluent treatment plant. The method combines the throwing power and rate enhancement of more corrosive chemical treatments, the high rate of electrochemical removal processes, the effective control of an electrochemical process, and the use of conventional downstream treatment plant for effective separation of contaminated and uncontaminated streams. In particular the added organic species are removed as gaseous carbon dioxide. The combination of electrical waveform type, organic metal complexing agents or halides in nitric acid, and then electrochemical destruction of organic acids achieve this objective.

[0026] The system has some or all of the following features:

- (a) Recirculation of the electrolyte between the decontamination bath and an electrolytic cell designed to destroy organic metal complexing agents and

reduce halides to halogens.

- (b) Metal sensing electrodes that monitor the concentration of metallic species in solution at various points.
- (c) A control system that adjusts the level of electrical power applied to the decontamination system in response to certain inputs, including the metal concentration sensors and or measured radioactivity.
- (d) Regeneration of the electrolyte in a cell designed to convert organic material to carbon dioxide and halides to halogens.

## **Brief Description of Drawings**

- [0027] Figure 1 shows an example of the voltage/time sequence used in this invention;
- [0028] Figure 2 shows schematically an example electrode set up used to demonstrate the present invention; and
- [0029] Figure 3 illustrates the impact adding hydrochloric acid to nitric acid in an electro-pickling decontamination process.

## **Experimental**

- [0030] Nitric acid is the base electrolyte. This is compatible with standard radio nucleotide recovery plants and does not corrode the materials of construction. Possible additives include hydrochloric acid, various organic acids including citric, oxalic, formic, ethylene diamine tetra acetic acid, other organic metal complexing or chelating agents including those based on nitrogen or phosphorous, as well as glycols and other organic compounds.
- [0031] The electrical waveform for use in the decontamination process is preferably a DC-biased AC waveform. It is also desirable to have the possibility to reverse the polarity of the DC bias periodically. This has the effect of changing the balance between metal dissolution and hydroxyl ion and hydrogen production, the latter being beneficial for preventing passivation and scrubbing of the surface. The DC bias may optionally be varied in a continuous manner.
- [0032] A low power waveform may be generated and then fed into a power amplifier, for example a potentiostat. Although the efficiency of such a process can be low (for example as low as 50%) it is a flexible process since any waveform may be specified.
- [0033] The current density is an important aspect of the invention as it affects the concentration of hydroxyl ions. Hydroxyl ions are important as they help to combat passivation and also hydrogen generation. Greater current densities are beneficial therefore, but only up to a point, since at higher current there is a loss of efficiency due to resistive heating that is proportional to the square of the current. In practice there is an optimum current density. The preferred current density is between 0.1 and 1 amp per square centimetre, and more preferably between 0.4 and 0.7 amps per square

centimetre.

- [0034] The frequency of the AC component of the waveform used may be in the range 1-1000 Hz. The preferred frequency is in the range 5-100 Hz. As frequency increases less of the electrical energy is used in the desired electrochemical conversion, because of the capacitance of the interface, but the alternating current aids removal of passivation via scrubbing and other mechanisms, and in practice a frequency of between 5-100 Hz is preferred. The preferred frequency is dependent on the electrolytes used and also on the composition of the metal surfaces.
- [0035] The added halide ions or other oxidising additive are removed from the nitric acid solution using a second electrochemical treatment. This consists of a separate electrochemical cell through which the treatment solution is passed. This treatment may be carried out continuously or in a batch-wise process, with multiple paths of the solution through the cell to achieve the desired reduction in levels of halide or other additive.
- [0036] An electrochemical surface treatment was carried out on test pieces of 304 stainless steel, followed by an electrochemical oxidation process to remove chloride ions. The effectiveness of the treatment was determined by measuring the thickness and weight loss of the sample pieces and by checking that the level of chloride ions in the electrolyte solution after electrochemical oxidation was below the 10 ppm required for subsequent treatment in conventional nuclear effluent treatment plant. The apparatus consisted of an electrical supply to provide a potential between working and counter-electrodes in an electrochemical pickling bath, an electrochemical pickling bath with 304 stainless steel working and counter electrodes, and a separate electrochemical oxidative step to remove additives (chloride ions in this example) from the nitric acid solution.
- [0037] The electrical supply is composed of a driving circuit which creates an electrical waveform, an H bridge circuit which allows for the reversal of polarity of applied potential to form a square wave, and a DC power supply. The applied potential was 12 V and the power supply was capable of supplying 10 A. The frequency used was 10 Hz, though other frequencies may be used. The waveform used is shown in Figure 1. A single cycle is shown as 72ms of forward or positive bias, followed by 2ms of zero potential, followed by 24ms of negative or reverse bias, followed by 2ms of zero bias, totalling 100ms for a 10 Hz supply. The waveform shown has three times longer duration of forward bias than reverse bias and is therefore a DC-biased AC waveform. The 2 ms zero potential periods are provided to ensure reliable operation of the switching circuits and are not important for the electrochemical operation. The 2 ms periods may be reduced or omitted if the electrical circuit can operate robustly without them. The shape and detail of the waveform may be varied. It does not need to be square waves, and alternative waveforms would be suitable, so long as they conform to

the constraint of being DC-biased AC waveforms. In this case the bias was positive so that the working electrode was anodically biased, but this need not be the case. The bias may usefully be reversed periodically.

[0038] A first experiment, tabulated in table 1 below, shows the very significantly greater rate of surface removal obtained when using an electrochemical process than is obtained when using a chemical process. Two 304 stainless steel coupons of exposed area 3 cm by 3 cm were immersed in a pickling solution that was 3 M in nitric acid and 0.3 M in hydrochloric acid. The rate of loss of metal from the surface of the exposed area was determined by weight loss. Two different treatments were applied. In the first there was no electric potential applied so that the process was a chemical one only. The coupons were exposed for 6 hours and the weight loss measured. In the second treatment the same chemical solution was used but now with the electrical potential applied, with the waveform as described above. The results are given in the table below and show that the electrochemical process gives a rate of removal more two orders of magnitude greater than the chemical process. This finding shows the advantageous rate of surface removal obtained with electrochemical processes compared to chemical processes.

[0039] [Table 0001]

**Table 1**

Treatment applied	Rate of metal surface loss (grams per cm <sup>2</sup> per 24 hours)
0.3 M HNO <sub>3</sub> + 0.3 M HCl No electrical potential 6 hours treatment duration	0.013
0.3 M HNO <sub>3</sub> + 0.3 M HCl, 12V, 10 Hz, 3:1 bias, 0.5 A/cm <sup>2</sup> , 10 minutes treatment duration	4.851

[0040] A second experiment shows the different throwing powers obtained with different solution properties when used in electrochemical surface treatments. The arrangement of electrodes is shown in Figure 2.

[0041] The two rectangular electrodes shown are completely submerged in the electrolyte solution. The holding vessel is omitted for clarity. Wires, 1, connect the electrodes to the power supply. A pickling bath of 800 cm<sup>3</sup> was used. 1mm thick stainless steel 304 test pieces to form electrodes 2 and 3 were cut to size, each 50 mm wide, parallel to one another and 10 mm apart. The working electrode 2 is the piece representing the object that needs to be decontaminated and is 100 mm long. The counter-electrode 3 is

also of 304 stainless steel and is 40 mm long. Suitable materials for the counter-electrode include titanium coated with one of a number of metals and oxides including platinum, platinum oxide, iridium oxide, ruthenium oxide or electrodes composed of carbon composite materials including graphite based materials. The electrical supply to the electrodes is as described above with reference to figure 1. Experiments were carried out for a fixed time of ten minutes. After that time the reduction in thickness of the working electrode 2 was measured at intervals along its length. The end of the working electrode that is adjacent to one end of the counter electrode is marked as 5 on figure 2, the end of the working electrode furthest from the counter electrode is marked as 4 on figure 2. The thickness of the working electrode was measured at ten points one centimetre apart.

[0042] The results are shown in graphical form in figure 3. The horizontal axis shows the distance from the end 4 of the working electrode 2 (of figure 2). Thus the end 4 is at the origin of the graph labelled 0cm. The part of the working electrode labelled 5 in figure 2 is 10 cms from the end labelled 4 and is shown as the 10 cm mark on the horizontal axis of the graph in figure 3. Thus points on the right hand side of the graph correspond to the end of the working electrode near 4 in figure 2, the points on the left hand side correspond to the end of the working electrode near 5 in figure 2.

[0043] The two thick horizontal lines at the top of graph show schematically the relative positions of the working and counter-electrodes. The square points show the effect of an electrochemical process when a nitric acid solution was used. The percentage reduction in thickness of the working electrode is approximately constant at 6% for that part of the working electrode that is parallel to the counter-electrode, and then falls off to a low value further away from the counter-electrode, as is expected. The diamond shaped points show the effect of adding 0.3 M HCl to the solution. There is an overall increase in the thickness loss, equivalent to an increase in the rate of loss. The throwing power 7, shown as the distance between the dashed lines, is effectively increased and this is marked on the graph, showing that reduction in thickness (and rate of material loss) at the 4 cm point 8 in the case with HCl added, is approximately equal to the reduction in thickness at the 6cm point 6 in the case without HCl. The result of adding the HCl can be seen as extending the effective reach of the electrodes by 2 cm.

[0044] In a third experiment the added HCl was removed in a separate electrochemical cell. This cell had the following features. The active electrode areas were 25 cm by 25 cm. The cell was divided using a Nafion cation selective ion exchange membrane (other membrane separators and membranes can be used). The purpose of the ion exchange membrane is to minimises metal deposition on the cathode and prevent parasitic Fe (II)/Fe(III) redox couples arising from the presence of iron ions from the dissolved

stainless steel which would otherwise reduce current efficiency. The cathode material was stainless steel which is preferred when treating nitric acid solutions and the anode was titanium coated with a mixture of iridium and tantalum oxides. The cell had a narrow inter-electrode gap of 5 mm and included turbulence promoters in the form of mesh in the electrode gap to give good mass transport and the capability to operate at a high current density. Other inter-electrode spacings are possible depending on the details of the cell construction. The cell was operated with a current density of 0.4 A/cm<sup>2</sup>. The outcome of treating the electrolyte with this cell was an evolution of chlorine gas and a reduction in the concentration of chloride ions from 0.3 M to below 10ppm (or approximately 3x10<sup>-4</sup> M). This lower level is acceptable for subsequent processing in conventional nuclear effluent treatment plant of 304 stainless steel.

[0045] The foregoing show that rapid electrochemical surface removal with good throwing power can be achieved by the use of hydrochloric acid as an additive to nitric acid in an electro-pickling process, and that the chloride ions can be removed subsequently using an electrochemical oxidative step. It has therefore been shown, surprisingly, that a nitric/hydrochloric acid mix can meet all of the objectives required for a nuclear surface decontamination process.

[0046] Other embodiments of the invention involve the use of different electrode materials and additives to nitric acid. Possible additives to nitric acid include hydrochloric acid, formic acid, ethylene diamine tetra-acetic acid, and hydrogen peroxide amongst others. Any suitable oxidising agent which can be destroyed electrochemically is suitable. Other anode materials in the oxidative destruction step may be used depending on the added reagent that needs to be removed. Iridium, platinum and ruthenium metal and metal oxide coatings on titanium are suitable for chloride ion removal (chlorine gas evolution) and for the oxidation to carbon dioxide of organic acids such as formic acid, by means of the creation of intermediate oxy-chloride ions. Boron-doped diamond electrodes are also effective at evolving chlorine and generating radical ions for oxidation of organic species. The complete system may optionally use a mixture of anode types. A suitable level of chemical oxygen demand (COD) such that solutions can be processed in 304 stainless steel treatment plants is 10 ppm COD.

## Claims

[Claim 0001] A method of removing nuclear contamination from a surface comprising applying a DC-biased AC waveform in an electro-pickling process using nitric acid as the electrolyte.

[Claim 0002] A method of removing nuclear contamination from a surface according to claim 1 in which the nitric acid has added chloride or organic chelating additives.

[Claim 0003] A method according to claim 2 including an electrochemical oxidative destruction process.

[Claim 0004] According to claim 4 in which the electrolyte is recirculated between the electrochemical oxidative destruction process and the electro-pickling process.

[Claim 0005] A method of removing nuclear contamination any preceding claim in which a current density of between 0.1 and 1 amp inclusive per square centimetre is used.

[Claim 0006] A method of removing nuclear contamination according to claim 5 in which a current density of between 0.4 and 0.7 amps inclusive per square centimetre is used.

[Claim 0007] A method of removing nuclear contamination according to any preceding claim where the DC-bias of the applied AC potential is periodically reversed, at a frequency less than that of the frequency of the AC waveform.

[Claim 0008] A method of removing nuclear contamination according to any preceding claim in which the alternating current frequency is between 1 Hz and 1000 Hz inclusive.

[Claim 0009] A method of removing nuclear contamination according to any preceding claim in which the alternating current frequency is between 2 Hz and 500 Hz inclusive.

[Claim 0010] A method of removing nuclear contamination according to any preceding claim in which the alternating current frequency is between 5 Hz and 100 Hz inclusive.

[Claim 0011] A method according to any preceding claim in which the added chloride or other oxidative species is selected from the group containing hydrochloric and hydrofluoric acid, citric acid, oxalic acid, ethylene diamine tetra acetic acid and hydrogen peroxide.

[Claim 0012] A method according to any preceding claim employing a counter-electrode comprising or coated with at least one of iridium, platinum,

ruthenium and metal oxide coatings on titanium.

[Claim 0013]

A method according to any preceding claim including the further step of treating the effluent stream electrochemically to remove chloride and organic additives.

[Claim 0014]

A method according to any preceding claim in which ultrasonic energy is applied to improve the efficiency and effectiveness of the electro-chemical electro-pickling process.

## AMENDED CLAIMS

received by the International Bureau on 27 November 2017 (27.11.17)

## Claims


1. A method of removing nuclear contamination from a surface comprising applying an asymmetric alternating current waveform with a net time-averaged current flow in one sense or the other to the surface in an electro-pickling process using nitric acid as the electrolyte in combination with an electrochemical oxidative destruction process, with electrolyte being recirculated between the two processes to create an effluent stream.
2. A method of removing nuclear contamination from a surface according to claim 1 in which the nitric acid has added chloride or organic chelating additives.
3. A method according to claim 2 including an electrochemical oxidative destruction process.
4. A method of removing nuclear contamination any preceding claim in which a current density of between 0.1 and 1 amp inclusive per square centimetre is used.
5. A method of removing nuclear contamination according to claim 4 in which a current density of between 0.4 and 0.7 amps inclusive per square centimetre is used.
6. A method of removing nuclear contamination according to any preceding claim where the DC-bias of the applied AC potential is periodically reversed, at a frequency less than that of the frequency of the AC waveform.
7. A method of removing nuclear contamination according to any preceding claim in which the alternating current frequency is between 1 Hz and 1000 Hz inclusive.
8. A method of removing nuclear contamination according to any preceding claim in which the alternating current frequency is between 2 Hz and 500 Hz inclusive.
9. A method of removing nuclear contamination according to any preceding claim in which the alternating current frequency is between 5 Hz and 100 Hz inclusive.
10. A method according to any preceding claim in which the added chloride or other oxidative species is selected group the group containing hydrochloric and

hydrofluoric acid, citric acid, oxalic acid, ethylene diamine tetra acetic acid and hydrogen peroxide.

11. A method according to any preceding claim employing a counter-electrode comprises or is coated with at least one of iridium, platinum, ruthenium and metal oxide coatings on titanium.
12. A method according to any preceding claim including the further step of treating the effluent stream electrochemically to remove chloride and organic additives.
13. A method according to any preceding claim in which ultrasonic energy is applied to improve the efficiency and effectiveness of the electrochemical electro-pickling process.

1/3

Fig. 1



2/3

Fig. 2





Fig. 3



# INTERNATIONAL SEARCH REPORT

International application No

PCT/GB2017/052162

**A. CLASSIFICATION OF SUBJECT MATTER**

INV. G21F9/00 C25F1/00 G21F9/06  
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
G21F C25F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	JP 2005 140761 A (CHEMICAL YAMAMOTO KK) 2 June 2005 (2005-06-02)	1,7
Y	paragraphs [0002], [0004], [0007], [0008] -----	2-14
Y	WO 2013/114142 A2 (NAT NUCLEAR LAB LTD [GB]) 8 August 2013 (2013-08-08) paragraphs [0049], [0052], [0062] - [0064] -----	2-4, 11-13
Y	US 2003/075456 A1 (COLLINS JOHN [GB] ET AL) 24 April 2003 (2003-04-24) cited in the application paragraphs [0005] - [0007], [0056] - [0058], [0068] - [0071]; figures 3, 5 -----	5-11
Y	US 2006/016689 A1 (CARSON ROGER W [US] ET AL) 26 January 2006 (2006-01-26) paragraphs [0106] - [0108]; figures 1A, 1B -----	14



Further documents are listed in the continuation of Box C.



See patent family annex.

\* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"E" earlier application or patent but published on or after the international filing date

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"O" document referring to an oral disclosure, use, exhibition or other means

"&" document member of the same patent family

"P" document published prior to the international filing date but later than the priority date claimed

Date of the actual completion of the international search

Date of mailing of the international search report

17 October 2017

26/10/2017

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040,  
Fax: (+31-70) 340-3016

Authorized officer

Sewtz, Michael

**INTERNATIONAL SEARCH REPORT**

Information on patent family members

International application No

PCT/GB2017/052162

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
JP 2005140761	A	02-06-2005	NONE		
WO 2013114142	A2	08-08-2013	EP	2810284 A2	10-12-2014
			GB	2499025 A	07-08-2013
			WO	2013114142 A2	08-08-2013
US 2003075456	A1	24-04-2003	AU	2691001 A	31-07-2001
			EP	1250473 A1	23-10-2002
			GB	2358194 A	18-07-2001
			US	2003075456 A1	24-04-2003
			WO	0153571 A1	26-07-2001
US 2006016689	A1	26-01-2006	AU	2003261271 A1	16-02-2004
			US	2006016689 A1	26-01-2006
			WO	2004012206 A2	05-02-2004