



US009239121B1

(12) **United States Patent**  
**Ragner**

(10) **Patent No.:** **US 9,239,121 B1**  
(45) **Date of Patent:** **Jan. 19, 2016**

(54) **VALLEY SHAPING REINFORCEMENT**

(56) **References Cited**

(75) Inventor: **Gary Dean Ragner**, Gainesville, FL (US)

U.S. PATENT DOCUMENTS

(73) Assignee: **Ragner Technology Corporation**, Gainesville, FL (US)

3,076,737 A	2/1963	Roberts	
3,117,596 A	1/1964	Mahn	
3,194,705 A	7/1965	Caplan	
4,048,362 A *	9/1977	Moring et al.	428/36.7
4,053,275 A *	10/1977	Kramer et al.	425/389
4,104,095 A *	8/1978	Shaw	156/83
4,113,828 A	9/1978	Kramer	
4,295,496 A *	10/1981	Bixby	138/122
4,308,895 A *	1/1982	Greco	138/125
4,360,493 A *	11/1982	Kramer et al.	264/506
4,445,543 A *	5/1984	Mead	138/122
4,633,912 A *	1/1987	Pilkington et al.	138/132
4,674,543 A *	6/1987	Ziemek et al.	138/153
6,024,134 A *	2/2000	Akedo et al.	138/129
6,158,477 A *	12/2000	Waters	138/129
6,948,527 B2	9/2005	Ragner	
7,549,448 B2 *	6/2009	Ragner	138/119
8,418,729 B2 *	4/2013	Martucci et al.	138/121
2006/0095018 A1 *	5/2006	Pursley	604/526

(\* ) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 593 days.

(21) Appl. No.: **13/447,273**

(22) Filed: **Apr. 15, 2012**

**Related U.S. Application Data**

(60) Provisional application No. 61/517,244, filed on Apr. 15, 2011, provisional application No. 61/607,365, filed on Mar. 6, 2012.

\* cited by examiner

*Primary Examiner* — Paul R Durand

*Assistant Examiner* — Andrew P Bainbridge

(74) *Attorney, Agent, or Firm* — Frost Brown Todd LLC

(51) **Int. Cl.**  
**F16L 11/00** (2006.01)  
**F16L 9/14** (2006.01)

(57) **ABSTRACT**


A valley shaping means for bidirectionally reinforced convoluted hoses comprising high strength fibers and/or cords which is designed for bonding and/or integration into the valley portion of the bidirectionally reinforced convoluted hose. The high-strength fibers and/or cords can be pre-coated prior to integration with the bidirectionally reinforced convoluted hose, or be coated and bonded after placed in position at the bottom of the valley portion of the bidirectionally reinforced convoluted hose.


(52) **U.S. Cl.**  
CPC ... **F16L 11/00** (2013.01); **F16L 9/14** (2013.01)

(58) **Field of Classification Search**  
CPC ..... F16L 11/00; F16L 9/14  
USPC ..... 138/122–125, 129–130, 137, 144, 138/118–119

See application file for complete search history.

**15 Claims, 9 Drawing Sheets**








Fig. 2C

Fig. 2B




Fig. 2D

Fig. 2











Fig. 6







## VALLEY SHAPING REINFORCEMENT

## CROSS-REFERENCE TO RELATED APPLICATIONS

This utility application claims priority from U.S. Provisional application Ser. No. 61/517,244, filed on Apr. 15, 2011, titled: "Differentially Stretchable Reinforced Strip and Method of Manufacturing a Reinforced Stretch Hose With The Same", by sole inventor Gary Ragner. Form PTO/SB/16, in Application 61/517,244, incorrectly included a second inventor, Robert de Rochemont, Jr., who's name was accidentally left on the form after copying it from a different patent application for updating.

This Utility Application also claims priority from U.S. Provisional application Ser. No. 61/607,365, filed on Mar. 6, 2012, titled: "Air Mandrel for Hose Manufacturing", by sole inventor Gary Ragner.

## BACKGROUND OF INVENTION

The field of this invention relates to reinforcement for convoluted stretch hoses or conduit, and more specifically to reinforcements that assists in producing a helical valley in the hose or conduit during manufacturing and later use.

Prior art convoluted helical shaped stretch hoses and conduits, are well known. Adding reinforcement to the stretch hose is less well known because of the difficulty of reinforcing a convoluted shaped hose. Even less well known is the use of bidirectional reinforcement on a stretch hose which appears to have only been taught by the Applicant in U.S. Pat. No. 6,948,527, issued on Sep. 27, 2005, titled: "Pressure-Actuated Linearly Retractable and Extendible Hose", and U.S. Pat. No. 7,549,448, issued on Jun. 23, 2009, titled: "Linearly Retractable Pressure Hose". Also, patent application Ser. No. 10/303,941 filed Nov. 25, 2002 and its resulting Divisional patent application Ser. No. 11/234,944 filed Sep. 26, 2005 by the Applicant, do not teach forming neither a u-shaped valley nor a v-shaped valley with cord reinforcements that is parallel to the helical valley of the convoluted hose.

The thin wall construction of a stretch hose does not easily allow reinforcement to be applied. The convoluted helical shape is what allows these hoses to extend to many times their retracted length and consistently retract under their own spring power. For these hoses to self-retract easily, they can be designed with a thin walled body that is indented between coils, or expanded between the coils, to allow the hose body to extend and retract without binding against itself. Because of these physical limitations on the thickness and flexibility of the hose body, most prior art stretch hoses can only withstand pressures of about 5 Pounds per Square Inch (psi) for extended periods of time at room temperature and less at higher temperatures. Thus, some type of reinforcement is required to prevent rupture of this type of stretch hose when used with typical compressed air and household water pressures. Further, the shape of the valley portion of the convoluted hose is a factor in determining the hose's retracting ability and strength. The disclosed fiber reinforcement is applied in the valley of a convoluted stretch hose to provide one or more of the following functions: 1) to provide radial pressure strength for the hose, 2) to provide a means for shaping the hose valley into a predetermined shape, and 3) to substantially maintain the position of the valley during use

and to insure the proper shape for retracting after extended use.

While many prior art stretch hoses discuss "reinforcement" for their hoses, the Examiner should understand that they are generally talking about the helical wire as the "support" or "reinforcement" against crushing, not a flexible fiber reinforcement in the helical valley of the hose to resist internal pressure. The "wire reinforcement" in prior art designs keep the hose bore from collapsing and from crushing and kinking during use, but provide little internal pressure support for resisting internal hydraulic or pneumatic pressure. The disclosed valley reinforcement provides significant pressure support for the disclosed stretch hoses, which helps stabilize the shape of the hose to insure proper extending and retracting operation.

The convoluted helical shape of a stretch hose does not lend itself easily to the addition of reinforcement because of the uneven shape of the surface with its helical peak and valley. Some reinforced conduits have been built, but are made with flat sheet material that is thin enough that the sheet material can crumple under force to allow the conduit be retracted. Such conduits are generally used with a compression spring which is used to keep the hose extended for use, and user must apply force to retract the hose. Most self-retracting stretch hoses, are made from a single extruded strip of elastomer material that can be stretched over the helical wire support and rolled to form the convoluted shaped stretch hose. As soon as bidirectional reinforcement is added, problems arise because the reinforcement material can not deform with the elastomer hose material. Thus, the reinforcement strongly resists any reshaping that might be required to form the convoluted shape. Thus, prior art methods of reinforcement for cylindrically shaped hoses do not work when applied to a convoluted helical stretch hose shape. Wrapping, weaving, and knitting methods of reinforcing a convoluted hose have difficulty forming and holding the proper shape for the valley of the hose, though some methods for forming a u-shaped valley are disclosed in Divisional application Ser. No. 11/234, 944. Preferably the valley can be v-shaped to allow easy extending and retracting of the hose, while also reducing stresses in longitudinal reinforcement. In other configurations, more rounded u-shaped hose valleys can be used for specific hose designs.

The use of the disclosed helical valley reinforcement solves many of the problems with maintaining the shape of the valley by providing a continuous coated yarn reinforcement placed near the center of a convoluted hose valley and/or on the walls of the valley. The yarn reinforcement can be wound in the valley of the hose and over other longitudinal and radial reinforcements. The tension on the valley reinforcement yarn prevents tension in the longitudinal yarn reinforcement from significantly deforming the valley from the desired v-shape. The yarn or cord reinforcement in other configurations can also be placed along the entire valley wall to maintain the v-shape. Thus, knitted or wrapped fiber reinforcement is forced to form a v-shaped valley by properly tensioning one or more yarns of high-strength fibers near the center of the hose valley to define the radius of the hose at the center of the valley. This process of wrapping reinforcement yarn or cord in the valley of the convoluted hose can be done by simply feeding the reinforcement yarn into the hose valley as the hose rotates pass. Such a method of valley reinforcement can produce finished hose or conduit at a rate of about one foot per second.

## DEFINITIONS

The following definitions will be used throughout this document:

The term “fiber” means a unit of matter which is capable of being spun into a yarn, cord or string or made into a fabric by bonding or by interlacing in a variety of methods including weaving, knitting, braiding, felting, twisting, or webbing, and which is the basic structural element of textile products.

The terms “cord” and “yarn” mean a strand of one or more fibers in a form suitable for weaving, knitting, braiding, felting, webbing, or otherwise fabricating into a fabric. The cord can be coated or infused with a lower-strength polymer matrix. The cross-section of the cord may be round or elongated like a ribbon or other shapes. Cords and yarns can comprise woven or braided fibers, and/or cords, in many different patterns if desired, such as, braided straps and string.

The term “fabric” means any sheet material that is woven, knitted, felted, layered or otherwise produced from, or in combination with, any fiber, yarn, cord or substitute for such.

The terms “conduit” and “hose” will be used as synonyms and means a tubular structure such as a hose or tube for conveying water or air or other pressure transferable material.

The phrase “convoluted helical” is used here interchangeably with “convoluted” to describe the shape of a conduit or hose with a helical ridge and a helical valley. In the hose industry, this “convoluted helical” shape is often referred to as simply “convoluted” in shape when referring to hoses, tubes, and conduits that have this shape. A convoluted shaped stretch hose is common in vacuum cleaner industry, where the convoluted stretch hose has an outside diameter defined by a helical spring that encircles the hose along its length and a valley between the helical spring. This outside diameter or ridge where a tension spring wire is located is what provides the retracting force and radial structural support for the hose. Adjacent to this helical outer diameter or ridge is an indentation or valley that runs helically next to the helical outside diameter and forming what appears to be a corrugated hose, or accordion like structure, but is actually helical or convoluted in shape.

The term “bidirectional reinforcement” is used within this document to refer to sheet reinforcement that provides structural support in more than one direction within the plane of the hose body. The bidirectional reinforcement does not necessarily provide equal support in all directions. Bidirectional reinforcement can be provided by reinforcement cords running in at least two directions within the plane of the hose body (i.e. radial yarn and longitudinal yarn reinforcement). All knitted and woven materials provide fibers running in at least two directions to provide bidirectional reinforcement.

The term “spiral lamination manufacturing methods” is used here to describe many different hose manufacturing methods that rotate the hose being manufactured while laminating strip(s) and applying reinforcement onto the rotating hose along a spiral path. Several examples of spiral lamination manufacturing methods are shown in FIGS. 1 through 8.

## SUMMARY

The thin wall nature of the convoluted stretch hoses makes it difficult to manufacture in a continuous process because of problems with damaging the walls of the hose when reinforcement and additional layers are placed on the convoluted shape. A number of methods exist for producing flexible stretch hoses that have a convoluted shape, but they do not incorporate a bidirectional fiber reinforcing layer(s) to make the conduit strong enough to withstand typical compressed

air pressures and/or household water pressures. Other reinforced hoses are manufactured that provide pressure strength, but cannot extend and retract as needed because of the wall thickness of the conduit and also the improper shape and/or lack of valley coils of the hose. These high pressure hoses are also manufactured with a cylindrical shape which makes it much easier to apply reinforcement. The mechanical limitations resulting from the convoluted shape of the hose makes it difficult for prior art stretch hoses to incorporate bidirectional fiber reinforcement. To simplify this construction, the Applicant’s valley reinforcement allows the convoluted hose to hold its shape during use because the valley reinforcement helps define the shape of the valley. Longitudinal reinforcement (along the length of the hose) can be applied under the valley reinforcement to provide longitudinal and/or longitudinal and radial strength to the hose while the valley reinforcement provides mostly radial pressure strength. The disclosed valley shaping reinforcement allows for a simplified manufacturing process that can reshape a longitudinally reinforced convoluted stretch hose into the desired helical convoluted stretch hose shape (u-shaped or v-shaped valley). The disclosed valley shaping reinforcement can work with the bidirectional reinforcements (knitted, woven, wound, wrapped, etc.) as well as, single direction longitudinally reinforcements, to form a retractable and extendable structure that is stable during repeated use. The disclosed valley reinforcement can also be used with un-reinforced polymer stretch hoses (polymer only hose) to provide added radial pressure strength and also to reduce deformation during extended use.

The manufacturing method and process presented here use valley shaping reinforcement that is applied substantially parallel to the helical valley of the convoluted hose. This valley reinforcement shapes the hose or conduit during manufacturing and produces a conduit that will hold its convoluted shape during extended use. By applying the valley reinforcement parallel to the hose valley the valley reinforcement can be used in continuous manufacturing (see FIGS. 1 through 6) where the spools of valley reinforcement can be substantially stationary (simply fed onto the rotating hose during manufacturing). The valley reinforcement can also be used with non-continuous manufacturing techniques that are used in industry such as mandrel wrapping methods (see FIG. 7). With valley reinforcement, a reinforced hose can easily be given the proper v-shape to allow the conduit to easily extend and self-retract. Further, the valley reinforcement will maintain the shape of the valley during repeated uses and extended time periods. Many prior art manufacturing methods that produce bidirectionally reinforced hose can be modified with the disclosed valley reinforcement to shape the bidirectionally reinforcement into the desired u-shaped or v-shaped valley for producing a reinforced stretch hose. For example, prior art reinforced cylindrical hoses with a helical wire support and bidirectional wrapped yarn or fabric reinforcement between the wire coils can be reshaped with the disclosed valley forming reinforcement to force a valley into the hose material between the wire coils with the disclosed valley reinforcement.

## OBJECTIVES AND ADVANTAGES

Accordingly, several objects and advantages of the presented invention are:

- To provide bidirectional reinforcement to increase in radial pressure strength for a convoluted hose.
- To provide a differentially stretchable strip for wrapping onto a convoluted hose.

5

- To provide a differentially stretchable reinforced strip for use in the manufacture of a bidirectionally reinforced convoluted stretch hose.
- To provide a differentially stretchable reinforced strip for use in the manufacture of a bidirectionally reinforced convoluted stretch hose where the reinforced trip comprises more than one elastomer layers of different formulation. 5
- To provide a differentially stretchable reinforced strip for use in the manufacture of a bidirectionally reinforced convoluted stretch hose where the reinforcement comprises diagonally woven cords. 10
- To provide a differentially stretchable reinforced strip for use in the manufacture of a bidirectionally reinforced convoluted stretch hose where the reinforcement comprises two layers of cords oriented at different angles. 15
- To provide a differentially stretchable reinforced strip for use in the manufacture of a bidirectionally reinforced convoluted stretch hose where the reinforcement comprises one or more layers of non-woven fibers and/or cords. 20
- To provide a differentially stretchable reinforced strip for use in the manufacture of a bidirectionally reinforced convoluted stretch hose where the reinforcement comprises knitted cords. 25
- To provide a differentially stretchable reinforced strip for use in the manufacture of a bidirectionally reinforced convoluted stretch hose where the reinforcement comprises a longitudinally differentially stretchable knit fabric. 30
- To provide a differentially stretchable reinforced strip for use in manufacturing a bidirectionally reinforced convoluted stretch hose where the reinforcement comprises a knitted fabric with one or more longitudinally running cords to provide a valley reinforcement that holds a convoluted shape for the hose. 35
- To provide a means of producing a convoluted helical stretch hose or conduit with a hose body comprising a differentially stretched woven reinforcing layer to provide the convoluted helical shape. 40
- To provide a means of producing a convoluted helical stretch hose or conduit with a hose body comprising a differentially stretched knitted reinforcing layer to provide the convoluted helical shape. 45
- To provide means of producing a convoluted helical stretch hose with a hose body comprising a two or more fiber reinforcing layers that are differentially stretched to provide the convoluted helical shape. Wherein the fibers are oriented at an angle with respect to each other to provide substantially bidirectional (two dimensional) reinforcement. 50
- To provide a heat shielding means for differentially stretchable reinforced polymer strips to reduce heating of the strip along a particular transverse portion of the strip (i.e. the centerline of the strip **140**). 55
- To provide a means for shaping and maintaining a v-shaped and/or u-shaped valley structure for a convoluted hose shape. 60
- To provide a means for maintaining the valley shape of a convoluted hose to a specific valley shape during use with pressurized liquids or gasses.
- To provide a means for substantially maintain the depth of the valley of a convoluted hose during use with pressurized fluids or gasses to insure the proper shape for self retraction of the hose after extended use. 65

6

- To provide a means for modifying the shaped of bidirectional reinforcement on a hose to produce a convoluted stretch hose so that the hose can self-retract.
- To provide a means for controlling the radius of the bottom of the valley of a convoluted stretch hose.
- To provide a means for increasing the pressure rating of a convoluted hose with a valley reinforcement cord.
- To provide a means for supporting a plurality of longitudinal reinforcement cords against internal pressure within a convoluted stretch hose.
- To provide a means of shaping a convoluted hose using fiber strand(s) wrapped in the valley of the hose.
- To provide a hose comprising a valley reinforcement cord that substantially follows the bottom of the valley of a convoluted stretch hose.
- To provide a hose comprising two or more valley reinforcement cords that substantially run parallel to the helical valley of a convoluted stretch hose.
- To provide a hose comprising a single valley reinforcement cord that substantially forms and holds the shape of the valley of a convoluted stretch hose during use.
- To provide two or more valley reinforcement cords that substantially forms and holds the shape of the valley of a convoluted stretch hose during use.
- To provide a hose comprising a valley reinforcement cord wrapped over a plurality of substantially longitudinal cords, wherein the valley reinforcement substantially holds the longitudinal cords in the shape of the valley of a convoluted stretch hose and provides support against internal pressure hose.
- To provide a hose comprising two or more valley reinforcement cord over a plurality of substantially longitudinal cords that substantially forms the shape of the valley of a convoluted stretch hose and provides support against internal hose pressure.
- To provide a hose comprising a valley reinforcement cord that follows the valley of a bidirectionally reinforced hose and substantially forms the shape of the valley of a convoluted stretch hose.
- To provide a hose comprising two or more valley reinforcement cord that follows the valley of a bidirectionally reinforced hose and substantially forms the shape of the valley of a convoluted stretch hose.
- To provide a hose comprising a valley reinforcement cord within a differentially stretchable strip for substantially forming the shape of the valley of a convoluted stretch hose.
- To provide a hose comprising two or more valley reinforcement cords within a differentially stretchable strip for substantially shaping the valley of a convoluted stretch hose in the differentially stretchable strip.
- To provide a means for applying rolling pressure to a multi-radius surface that has portions of its surface moving at different linear speeds.
- To provide a means for applying rolling pressure to a multi-radius hose, wherein portions of the roller's surface can move at different linear speeds.
- To provide a roller with multiple disc sections having different radii, wherein the disc sections can rotate independently of other disc section of the roller.
- To provide a roller with multiple disc sections having different radii, wherein some of the disc sections are driven and other disc sections can rotate independently of driven disc sections of the roller.

## DRAWING FIGURES

FIG. 1 Side View of an example of a conduit making machine using a valley reinforcement cord **155** to form a convoluted v-shaped valley.

FIG. 1A Top View of a rectangular segment of reinforced strip **140**, showing fiber orientation before stretching.

FIG. 1B Top View of the rectangular segment of reinforced strip material in FIG. 1A after deformation of the strip, and showing approximate fiber cord orientation after being stretched into a helical convoluted conduit shape.

FIG. 1C Transverse Section View of the reinforced strip material **140**

FIG. 1D Top View of alternate knitted reinforced strip material **140a**, showing longitudinal cords **142b** within the knit pattern for reinforcement and shaping of the hose valley.

FIG. 1E Top View of alternate knitted reinforced strip material **140b**, showing a warp knit with reduced longitudinal stretch stripe **142d** within knit pattern **140b**.

FIG. 2 Side View of a 2th example of a conduit making machine using valley reinforcement cord **155** to form a convoluted v-shaped valley.

FIG. 2A Top View of a rectangular section of reinforced strip material **140** and showing fiber orientation before stretching.

FIG. 2B Top View of the rectangular section of reinforced strip material **140** shown in FIG. 2A, and showing the approximate deformation of the polymer strip section and the fiber orientation after being stretched into a helical convoluted conduit shape.

FIG. 2C Top View of alternate warp knitted reinforced strip material **140d**, showing an example knit with reduced longitudinal stretch stripes **142f** within knit pattern **140d**. Where stripes **142f** are formed and bonded in the valley portion of hose **158a** to shape the valley.

FIG. 2D Section View of alternate strip material **140e**, showing an example of double wide differentially stretchable strip material similar to strip material **140h**.

FIG. 3 Side View of a 3th example of a conduit making machine for the valley portion of a convoluted hose using valley reinforcement yarns **270a-d** to form a convoluted u-shaped valley.

FIG. 3A Transverse Section View of reinforcing cord **270a** through **270d**.

FIG. 4 Side View of a 4th example of a conduit making machine using valley shaping reinforcement cord **155** to form a convoluted v-shaped valley.

FIG. 4A Section view of strip after bonding three strips together.

FIG. 4B Section view of double wide reinforced strip.

FIG. 5 Side View of a 5th example of a conduit making machine using valley shaping reinforcement cord **155** with a mesh reinforcement **140k** to form a v-shaped valley.

FIG. 5A Section view of an alternate non-woven fabric, using a bonding matrix material

FIG. 6 Side View of a 6th example of a conduit making machine with valley shaping provided by valley reinforcement yarns **142** and **142b**.

FIG. 7 Side View of a 7th example of a convoluted conduit making machine for making conduit with valley reinforcement **155** on a rotating mandrel.

FIG. 8 Side View of a 8th example of a conduit making machine that uses diagonal cord wraps and valley reinforcement **155** over the cords on an air mandrel for making convoluted hose.

FIG. 9 Photo of KM-89-SS-HS Spiral Wrapping Machine as an example of wrapping machines **250a** and **250b**.

## DETAILED DESCRIPTION OF THE INVENTION

Valley Reinforcement Cord **155**—FIGS. 1, 2, 4, 5, 6, 7 and 8

In FIGS. 1, 2, 4, 5, 6, 7 and 8, we see examples of valley forming reinforcement cord **155** used with continuous conduit making machines **100**, **100a**, **100c**, **100d**, **100e**, **100f** and **100g**, respectfully. Valley reinforcement cord **155** is used to form and maintain a substantially v-shaped valley on the convoluted hoses made by these machines. Because of the shape of convoluted hoses, valley reinforcement cord **155** naturally tends to seek the bottom of the valley as it is wrapped onto the hose. The smaller radius of the bottom of the valley serves to lock cord **155** in place on the hose. Several different examples of the disclosed valley reinforcement are discussed within this document. The reader should understand that these examples do not provide a complete list of possible configurations for placement and means of manufacturing a hose with valley reinforcement, but instead are selected examples for the invention to give someone skilled in the art of hose making a clear understanding of how to use the valley reinforcement. From these examples, someone skilled in the art of hose making can generate a multitude of additional configurations for the valley reinforcement.

Example Conduit Making Machine **100**—FIG. 1

Conduit making machine **100**, comprises a spring coiling machine **105**, a mandrel **120**, forming roller assemblies **130**, **130a** and **131**, tensioning rollers **150** and **150a**, and heater **151** and **151a** for making finished conduit **158**. Spring bending machine **105** comprises a standard spring bending machine with drive rollers **106** (only one shown for drawing clarity) and wire bending tool **107**. While spring coiling machine **105** (also called a wire bending machine or wire coiling machine) is not drawn here in detail. Spring coiling machines are well known to people in the industry and can be purchased and used for the disclosed conduit making machine with little or no modification. Bending tool **107** is often called a point tool because the wire interacts with the tool at substantially a single point to cause it to bend into a helical spring. Point tool **107** is usually made of a hardened steel or other very hard metal that has very low wear properties. The coil radius is determined by how far the point tool is from the wire feeder guide (hidden behind mandrel **120**) of coiling machine **105**, and at what angle it is oriented, and the type of wire being bent. Many other types and styles of wire coiling machines already exist which can be used in place of coiling machine **105**.

Spring wire **110** can be uncoated, meaning there is no polymer coating, and the wire's metal surface is exposed. This means wire **110** can be plasma sprayed, chemically treated, galvanized and/or other metallic coating process to provide corrosion resistance and tough outer surface without significantly increasing the diameter of the wire. If wire **110** were coated with a polymer coating, point tool **107** would damage the polymer coating with the high contact forces. Thus, for coated wire, alternate wire coiling machine **105a** can be used, which uses a roller point tool **108** seen in FIG. 6, where a coated wire **111** can be bent gradually by roller(s) **108** to reduce stresses on the polymer coating. The material for spring wire **110** is selected to provide the desire retracting force and stiffness needed for the particular conduit being made. A strong resilient spring wire can be chosen for wire **110**, because of the strong retracting force desired for finished conduit **158**. Wire **110** in this example is not coated with polymer to help increase the extension ratio of the conduit by reducing the coil width. Notice that coiled wire **110** does not add significant positive pressure strength to the hose or conduit, but it does provide a significant portion of the crushing

strength of the finished conduit, especially when the conduit is retracted and not pressurized.

Wire **110** can comprise any spring material, such as, spring steel, stainless spring steel, titanium spring alloy, piano wire and even composite springs such as glass fiber composites, graphite composites, and etc. For use with water, wire **110** can be made of a stainless steel alloy to prevent rusting and corrosion. Wire **110** can also be made of a corrodible metal, such as high-carbon steel, and can still be used in wet environments if spray coated with other metals such as tin, zinc and nickel to improve its corrosion resistance and these coatings can be applied in a number of ways, such as, electrolysis, plasma spray, chemical dip, etc. If composite springs or other pre-formed springs are used, then spring coiling machine **105** is not needed and the composite spring would feed onto mandrel **120** at shaft end **121**. In order to feed a spring onto mandrel **120** in this way, support bracket **126** can be used to fix mandrel **120** in place with respect to rollers **130** and **131** and other equipment. Bracket **126** is securely bonded/attached to mandrel **120** in this example and is narrow enough to easily allow coiled spring **110** to feed around it as coiled spring wire **110** is shown in FIG. 1.

In FIG. 1, Mandrel **120** can be made of nearly any hard metal such as hardened steel, stainless steel, etc. and can be fastened to wire coiling machine **105** if desired, or can be fastened to another mechanical support structure (not shown). Mandrel **120** comprises shaft end **121**, spring guide **122**, wire molding groove **122a**, a u-shaped hose forming valley **124**, a v-shaped hose forming valley **124a**, and support bracket **126**. All the mandrels presented in this patent are shaped to form the conduit in its fully extended state. This is to reduce stress on the hose when pressurized and extended. This allows the conduit can be substantially free of creases or wrinkles when extended and pressurized. The mandrel can form convoluted hose at less than its fully extended shape if care is taken to properly shape the hose for that retracted position. When the conduit is retracted, the hose body (strip material) can fold and wrinkle as needed to compress the hose. Since very little stress is on the conduit when retracted there are no high stress points on the strip material to damage it. Mandrel **120** can comprise a number of different alternate designs for rotationally feeding coiled wire **110**, such as, prior art designs with multiple parallel rollers that form the mandrel and rotate in the same direction to feed coiled wire **110** like mandrel **120a** seen in FIG. 2. With rollers on both the inside and the outside portion of overlap region **156**, can provide many low friction rolling surfaces to compress and bond the seam area **156**. Mandrel **120** can be coated with a low friction coating so that strip material **140** can slide freely over the exterior surface of mandrel **120**. For this design mandrel **120** initially has a u-shaped valley **124** for bonding strip **140** together, but then shifts to a v-shaped valley **124a** to allow valley reinforcement to reshape hose **158** into the desired v-shaped conduit. In other designs, the v-shaped valley **124a** can be used along the entire length of the mandrel **120b** as seen in FIGS. 4 and 5.

Within this document, valley forming reinforcement cords **142b**, **142d**, **142f**, **155** and **270d** can comprise nearly any flexible a high strength materials such as nylon, aramids, polypropylene, polyester, glass, carbon, and other high-strength fibers. For highest strength, cords **142b**, **142d**, **142f**, **155** and **270d** can be formed from stretched fibers, or even a monofilament. Cords **142b**, **142d**, **142f**, **155** and **270d** can be formed from twisted or untwisted fibers and can also be woven knitted or braided if desired. Many different weaving, knitting and braiding patterns can be used to form cords **142b**, **142d**, **142f**, **155** and **270d** into the desired structure and shape, such as, braided string and flat straps.

In FIG. 1, hose making machine **100** has an upper speed limit of approximately one-thousand coils per minute for a one inch diameter hose. A 0.020 inch polymer coating on the wire creates 0.040 inches of plastic per coil and adds forty inches to the retracted length of the fifty foot conduit with one-thousand coils. Thus, using wire that does not need to be coated with a polymer has a great advantage in reducing the overall length of stretch conduit **158** when retracted and giving conduit **158** and the other conduits in this patent a greater extension ratio over prior art.

Wire **110** can also be a composite spring, such as glass/resin, carbon fiber/resin, aramid fiber/resin, etc. which can have comparable spring force to steel and highly resistant to corrosion. Multiple resins can be used with composite springs including but not limited to epoxies, polyesters, and urethanes. If a composite spring is used, it can be pre-formed and fed onto mandrel **120** from the left in FIG. 1. Support **126** would provide structural stability for mandrel **120** holding it in place as the composite spring would rotate around mandrel **120** and follow guide **122** just like the metallic spring shown. However, with a composite spring, wire coiling machine **105** would no longer be needed, and the composite spring could be molded prior to going onto mandrel **120**. In alternative designs the composite spring can be formed by hot molding just prior to going on mandrel **120**, **120a**, or **120b**, with sufficient time for cooling and setting of the composite spring in a tension spring configuration before going into conduit making machines **100**, **100a**, **100b**, **100c**, **100d** or **100e**. The use of coiled metallic wire or coiled composite spring is a user preference and either could be used with the example conduit making machines shown in this patent.

In FIG. 1, strip heaters **151** and **151a** can be electric radiant heaters that quickly heat strip **140** and valley reinforcement **155**, respectively, before being wound onto coiled wire **110** as it rotates. If strip **140** were extruded, then heater **151** is not needed since the extruded strip would be very hot already and easily stretched and bonded to itself. Heaters **151** and **151a** can be standard thermally controlled heater that can provide precise heating to polymer strip **140** and coated cord **155**, and in general can enclose the materials fed through it to heat both sides of the strips at the same time. The power level used by heaters **151** and **151a** would be adjusted to sufficiently heat a polymer matrix material **143** so that it can be plastically stretched without undue force. In the case of valley reinforcement cord **155**, heater **151a** might simply heat the underside of the cord as shown in FIG. 1 since only one side of cord **155** makes contacting strip **140** as it is bonded. This heating can also prepare cord **155** for bonding to other portions of the hose's valley besides the bottom of the valley shown in FIG. 1. In some cases, additional heaters might be needed to reheat the outer surface of strip **140** near the location where strip **140** and cord **155** meet to insure a good melt surface and provide consistent bonding. Since hose production with the disclosed machine **100** is very fast (up to one feet per second) there is little time for strip **140** to cool. Heaters **151** and **151a** can be placed near mandrel **120** so the exterior of previously layered strip **140** can receive some of the heat from heaters **151** and **151a**, and keep the surface of strip **140** soft to allow better bonding.

In alternate designs, strips **140**, **140c**, **141**, **143a-b** and **143e** in FIGS. 1, 2, 3, 4, 5, 6, and 7, can be replaced with an extruded polymer strip similar to strip material **143a**, **143b**, and wear strip **141** (see extruded strips **143d** and **143a** in FIGS. 6 and 8, respectfully). These strips can be extruded just prior to being wrapped on the hose. The extrusion process reduces the number of ways the strip can be reinforced, but does allow for reinforcement (i.e. by cross-extrusion with

11

cord reinforcements **142** and **142b** seen in FIG. 6, and cross extrusion of other reinforcements, i.e. fabric strips). The use of extruded strips for strips **140**, **140c**, **141**, **143a-b** and **143e**, an extruded wear strip for wear strip **141** and a cross-extruded cord for valley reinforcement cords **155**, and **270a-d** can eliminate the need for heaters **151**, and **151a-c**, and tensioning rollers **150**, and **150a-c**.

In FIGS. 1-3, 5, 6 and 7, tensioning rollers **150** can comprise a pair of opposed rollers that can sandwich their respective strip between them. In FIG. 1, for example, strip **140** is pressed between rollers **150** so that friction between the rollers and the strip causes the strip to have the same linear speed as the surface of rollers **150**. Mechanical or electronic controls attached to rollers **150** (not shown) can be used to adjust the speed and/or force on the rollers so that the surface speed difference between rollers **150** and coiled spring wire **110** provides the proper amount of stretch as strip **140** is wrapped on wire **110** in the convoluted helical shape of mandrel **120**. Too much stretching of strip **140** and it can narrow transversely so that it does not extend completely between the adjacent coils of wire **110**. Too little stretching of strip **140** and it will not deform completely into valley **124** and form the correctly shaped conduit. In most situations the speed of rollers **150** will be controlled relative to the speed of rotation of coiled wire **110** so that wire **110** stretches reinforced strip **140** the correct amount in transverse portions **152a** and **152b**, and tapering to almost no stretch at the center line of strip **140** (center of transverse portion **154**). Wear strip **141** can also have a tensioning roller assembly **150a** like rollers **150**, but because of the durable nature of strip **141** and the small width (i.e. 0.125 inches wide) a simple friction tension device (not shown) would be sufficient and might consist of nothing more than feeding strip **141** through one or more stationary guides. This is especially true if only the underside (bonding surface) is heated so the strength of the top surface remains to prevent stretching even if friction forces are slightly high or varies with time. Note that in FIGS. 1 through 3, the bottom rollers of tensioning rollers **150** and **150a** can not be seen because the top roller hides it.

In FIGS. 1, 3, 4 and 6, roller assembly **130** comprise two rollers **132** and **134** connected on a single shaft **136**. In alternate designs, single independent rollers can be used or rollers **132** and **134** can rotate independently of each other and/or independently of shaft **136**. Rollers **132** and **134** are representative of the vast number of roller systems that could be used to press together adjacent layers of strip material **140** after heating to fully bond the edges of strip **140** to itself at bonding zone **156**. The rolling surfaces of rollers **132** and **134** can be textured with knurling or other textured patterns for gripping strip **140** securely when wrapped onto wire **110**. This textured rolling surface is especially important if wire **110** is not coated with a polymer and a slippery elastomer like polyvinyl chloride (PVC) is used. Polymer coatings on wire **110** are common for vacuum stretch hoses to give the applied strip something to stick to and prevent slipping. If a polymer coating is not used, strip **140** may not stick to wire **110** and could easily slip off if measures are not taken to hold it in place. By texturing the contact surface of rollers **132** and **134**, and positioning them where strip **140** first contact wire **110** it is possible to wrap strip **140** on coiled wire **110** as shown. For higher speed processing it may be necessary to provide additional rollers and conveyors to insure that strip **140** can be guided and molded around coiled wire **110** without slipping from its desired position.

In FIGS. 1, 2, 3, 4, 5, 6 and 8, forming rollers **130**, **130a**, **131**, **160**, **180** and **180a** can be driven or passive depending on how the manufacturing system is set up. This is because the

12

driving force behind wires **110** from spring coiling machine **105** can be very high. Wire **110** is bent around mandrel **120** with considerable force. This means these roller assemblies can be powered or un-powered. If un-powered, the force of wire **110** would simply rotate the rollers as wire **110** and covering **140** is forced around the mandrel. If powered, rollers **130**, **130a**, **131**, **160**, **180** and **180a** can help pull the conduit around the mandrel. In some cases, it can be desirable for the roller(s) to provide a restricting force or drag on the rotating wire coil to force the strip edges together. In many designs, it can be desirable to have additional powered roller assemblies **130**, **130a**, **131**, **160**, **180** and **180a** surrounding mandrel **120** to provide complete support of the conduit and to provide motivating force to the strip material to keep it moving around its mandrel. For example, by placing many additional powered rollers **130a** in contact with strip **140** a greater motivating force can be applied to strip **140** at wire **110** and keep the hose moving with coiled wire **110** (no slippage). By placing rollers on opposite sides of mandrel **120** forces can cancel so there is only a small force exists pressing strip **140** against mandrel **120** and thus producing only a small friction force resisting the motion of strip **140**. Note that in the presented examples rollers **142** and **144** are angled in the direction of the wire coil (see front roller assembly **130** in FIG. 3). This angling of roller assemblies **130** and **130a**, and others, allows two rollers on a single shaft to align with the wire coil and strip material **140** and press the seam to the desired shape. On-angle rollers (such as rollers **180**) with its axis aligned with the hose axis, cannot have the exact shape of the seam, but can be made wider to allow the off-angle of the wire to roll through the roller without binding.

Roller Assemblies **130a** are similar to roller assemblies **130**, but have two rollers **132** which are the same diameter to roll the same thickness of layered strip material **140**, and the like. While the difference between the thickness at roller **142** and the thickness at roller **144** might only be a few thousandths of an inch, it is discussed here to address the slight difference in surface speed of the hose because of this difference in thickness. In FIG. 1, additional roller assemblies **130a** can be placed further to the right of assembly **130** and assembly **130a** if mandrel **120** were lengthen, which would provide additional support across the conduit bonding section. With rollers like **130**, **130a**, **131**, and **180** completely surrounding mandrel **120**, coiled wire **110** and bonded strip **140** is effectively trapped within the rollers and form a tunnel like set of rollers for coiled wire **110** and strip **140** to revolve within. Placement of rollers on opposite sides of the mandrel can remove much of the friction between wire **110** and mandrel **120** because of the equalization of forces of the rollers. With rollers surrounding the mandrel, wire coil **110** can also be forced into a smaller radial diameter by the rollers and provide greater force without pushing wire **110** against mandrel **120** (mandrel would need to be made smaller to accommodate the smaller compressed wire coil diameter). With surrounding rollers providing a retarding force on the wire, this force results in a radial pressure trying to expand the wire coil which increases the force exerted on rollers **132** and **134** by wire **110**. In this way, friction control of roller assemblies **130** and **130a** can be used as an alternative way to control the pressure exerted to bond strip **140** to itself and mold it around wire **110**. Coiling machine **105a** can be used to replace coiling machine **105** in the disclosed examples when coated wire **111** is used, and can function in the same way as coiling machine **105**.

In FIGS. 1, 1a-c, and 3 polymer strip **140** is an elongated strip of material used to build conduits in a continuous process. Because the process is desired to be continuous, in this

example, the length of strip **140** must be relatively long so that splices between manufactured strips can be widely spaced. Spliced joints would normally be cut out of the finish conduits. Thus, practical conduits strip material lengths must be long enough to produce at least one conduit. Since approximately thirty meters of strip **140** is needed to produce a single fifty foot long linearly retractable garden hose (extended length), strip **140** would preferably come in strip lengths of 1000 meters or more, so that a dozen hoses or more can be made between splices. Also, strip **140** can be replaced by many of the other differentially stretchable strips, such as, strips **140c**, **140d**, **140e**, **140k**, **143a**, **143b**, as well as, extruded strips **143d**, or **143e**, depending on the final use of the hose or conduit. For example, if a low pressure drainage hose is needed, strip **140** might be replaced with unreinforced strip **143a**, or **143b**, or unreinforced extruded strip **143e** to provide a light weight valley reinforced stretch hose.

Strip **140** can have a composite construction comprising a water proof polymer matrix material **143** bonded around a fiber based reinforcement layer comprised of fiber cords **142** and **144**. The exact composition of polymer matrix **143** and cords **142** and **144** is not critical to the invention and many combinations are possible. For example, in FIGS. **1**, **1A-E**, and **3** polymer matrix material **143**, and polymer matrix strips **143a-b** can comprise an engineered polymer, copolymer, or blend of polymers, such as, urethanes, polypropylenes, neoprenes, nylons, etc. combined with plasticizers or other additives (i.e. small incompatible rubber inclusions) to significantly lower the Young's Modulus (tensile modulus) of the matrix and make its properties closer to that of rubber. Polymer materials **143**, and **143a-b**, can also be an elastomer or a thermoplastic elastomers such as, but not limited to, unsaturated rubbers like: natural rubber (NR), polyisoprene (IR), butyl rubber (IIR), halogenated butyl rubber (CIIR and BIIR), polybutadiene (BR), styrene-butadiene (SBR), Nitrile Rubber (NBR and NHBR), chloroprene rubber (CR), polychloroprene (CR), Neoprene (CR), saturated rubbers that cannot be cured by sulfur vulcanization, like: ethylene propylene rubber (EPM), Epichlorohydrin rubber (ECO), Polyacrylic rubber (ACM, ABR), silicone rubber (SI, Q, VMQ), fluoro-silicone rubber (FVMQ), Fluoroelastomers (FKM and FFKM), perfluoroelastomers (FFKM), polyether block amides (PEBA), Chlorosulfonated polyethylene (CSM), Ethylene-vinyl acetate (EVA), and various other types of elastomers, like: Thermoplastic elastomers (TPE), Thermoplastic Vulcanized (TPV), thermoplastic polyurethane (TPU), thermoplastic olefins (TPO), proteins, resilin elastin, and polysulfide rubber. Polymer matrix materials **143**, and **143a-b** can also be made of natural polymers like rubber, and other natural elastic polymers. These matrix materials are infused around cords **142** and **144** to provide a water tight seal that can flex thousands of times without cracking or leaking. In section view of strip **140** in FIG. **1C** we can see that cords **142** and **144** are completely encased in matrix material **143**. Matrix materials **143** and **149** serve the functions of holding cords **142** and **144** together in a fabric or sheet form, and also waterproofing the fabric or sheets and make it substantially impermeable to water and/or air. Cords **142** and **144** when formed around a conduit provide a bidirectional reinforcement that gives the conduit or hose strength in both the radial and longitudinal directions. Matrix materials **143**, and **143a-b** can have a lower ultimate tensile strengths generally less than 10,000 psi (69 MPa) and a Young's Modulus less than 50,000 psi (345 MPa). Typical values for an elastomer for matrix material **143** might have an ultimate tensile strength of 3,000 psi (21 MPa) and an elastic modulus of 5,000 psi (35 MPa). Polymer matrix materials **143**, and **143a-b** should be rela-

tively flexible, and in most conduits, the polymer matrix can have a durometer near eighty-five on the shore A scale. While durometer is not a measure of flexibility, it does give an indication of the flexibility of the material and is used here crudely to give the reader a general sense of the flexibility of the desired matrix material.

Strip **140** and others in this document can have multiple layers of matrix materials as is common in the hose industry. Each layer may have drastically different properties depending on the properties desired for the finished conduit. For example, one can have a high durometer for one particular conduit design that needs high puncture resistance, while another conduit that needs maximum flexibility may require a low durometer for materials **143a-b** and **143**. Thus, matrix materials **143**, and **143a-b** can all be given predetermined durometer, tensile strength, flexural modulus, resistance to solvents, high temperature properties, low temperature properties, and other material properties as is dictated by the needs of a particular conduit and its purpose or end use.

In all the FIGS. **1** through **8** fiber cords **142**, **142b**, **144**, **155**, **252**, **254**, and **270a-d** can comprise one or more strands of any high strength fiber material, including, but not limited to, nylon, aramid, polypropylene, polyester, glass, carbon, and other fibers. Cords **142** and **144** used in the differentially stretchable strips should have a higher deflection temperature than polymer matrix **143** to allow differential stretching. To produce these high strength fibers, manufactures stretch the fibers while hot (melt stretching) or while cold (cold drawing) to align the polymer chains and make the fiber more crystalline. This aligned crystalline state provides very high tensile strength in the longitudinal axis of the fiber. Fiber cords **142**, **142b**, **144**, **155**, **252**, **254**, and **270a-d** are preferably have a tensile strength generally greater than 15,000 psi (211 MPa) and a Young's modulus greater than 50,000 psi (the fiber cords typically have a significantly greater Young's Modulus than that of matrix **143**). Fiber cords **142**, **142b**, **144**, **155**, **252**, **254**, and **270a-d** can have an elastic modulus greater than 1,000,000 psi (7,000 MPa or 7 Gpa), depending on the fiber used, but preferably is made of inexpensive fibers, such as, polyester and/or nylon micro-fibers which have tensile strengths of around 60,000 to 70,000 psi and an linear elastic modulus around 1,000,000 to 2,000,000 psi. The high modulus prevents the fibers from stretching significantly (deforming from their original length) even when under high operating tension. For the example strip **140**, fiber cords **142** and **144** will normally have a much higher melting temperature than matrix **143**. Thus, when matrix **143** is heated near its melting point and/or heat deflection temperature, and/or vicat softening point, and/or becomes plastic (deformable), cords **142** and **144** still may not stretch significantly longitudinally or change length significantly during stretching of matrix **143**. This is because of cords **142** and **144** are designed to have higher deflection temperature. Such fibers generally have a high percentage of crystalline structure and tend not to stretch or deform even when near their melting point. Note that valley forming reinforcement cords **142b**, **155**, and **270a-d** can comprise the same fiber materials as fiber cords **142** and **144**. Similarly, knitted valley reinforcement structures **142d** and **142f** can comprise the same fiber materials as cords **142** and **144**.

In FIGS. **1** through **8**, polymer strips **140**, **140a-e** and **143a-b** can each be made with elastomer **143** and can comprise a woven, wrapped and/or knitted cords **142**, **142b**, **144**, **270a-d**, **252** and **254**, where each set of cords can be formed from many individual fibers. Other examples of ways cords can be positioned within polymer matrix **143** and provide reinforcement are seen in FIGS. **1** through **8**). Cords **142** and

144 can be knitted and/or woven to form a woven bidirectional fabric sheet. Cords 142 and 144 can also be non-woven and placed in layers within polymer 143. In FIG. 1C we see a transverse section view of strip 140. Only the ends of cords 142 and 144 are visible, but the cords preferably weave in and out of each other as one goes further into matrix 143. In FIG. 1D we see a weft knit structure 142a knitted from fiber cord 142 which forms a fabric with valley reinforcement cords 142b woven within the knit. In FIG. 1E, we see strip 140b with a low stretch warp knit fabric structure 142d in the center and a stretchable warp knit fabric structure 142c on the sides can all be knitted from fiber cord(s) 142 or combinations of other cords. In each case, the cords are bonded within matrix material 143 which is preferably an elastomer that can allow that strip to easily flex away from the plane of the strip. For example, fiber cords 142 and 144 might be made of a low denier nylon fibers with a tensile strength around 60,000 psi, while matrix 143 might be a polymer and/or elastomer based on polyurethane or other polymers having a maximum tensile strength of 4,000 psi, and an elastic modulus of 5,000 psi, which is significantly less than the cords. During wrapping onto the conduit, matrix 143 can have a lower melting temperature, and/or lower plastic deformation temperature and/or heat deflection temperature, and/or vicat softening point than the cords to allow the matrix material to deform without having to change the length nor heat damaging fiber cords 142 and 144. The diagonal angle of cords 142 and 144 along strip 140 allow the matrix to deform longitudinally while the cords shift with the stretching of matrix 143. After matrix 143 cools, cords 142 and 144 are locked into place and strip 140 becomes stiff in the plane of the cords, but can flex easily out of the plane of the strip. For the purposes of this patent, the reinforced polymer strips 140 can be used with other appropriate conduit making machines disclosed within this document. Polymer strip 140 is used extensively throughout this patent as an example, but the reader should understanding many of its properties are similar to strips 140a-h, and many other methods can be used to produce the basic bi-directionally reinforcement on a convoluted hose.

In this document, strips 140, 140a-k and 143a-b (and other strip materials) can stretch differentially in the longitudinal direction (in direction 145) because of the way cords 142 and 144 are oriented with respect to the longitudinal direction 145 of the strip. The orientation of the cords also provide bidirectional reinforcement so that both radial and longitudinal forces on the hose are supported. Cords 142 and 144 are oriented in these strips so that they can stretch longitudinally. For strips 140, 140c, and 140e-k cords 142 and 144 can be oriented with angles 148a-b (see FIG. 1) preferably being greater than forty degrees, but less than seventy-five degrees, to allow the woven fabric to stretch easily in the longitudinal direction 145, but not have the cords too close to being aligned transversely. This physical arrangement of diagonally angled fiber cords allows each transverse portion of strips 140, 140c, and 140e-k to stretch longitudinally at different rates than other transverse portions of the strip. For example, in FIGS. 1, 3, and 6 the transverse portions 152a and 152b of the differentially stretchable strips are stretched longitudinally considerably more in these examples than center transverse portion 154. In some configurations, a heating guard 159 can be used to protect the center portions of the strips and prevent that portion from reaching a high enough temperature to become easily stretchable (deformable), and thus providing a portion of the strip that will not easily stretch by the tension from rollers 150. With strip 140 having a cool center portion 154, in FIGS. 1, and 3, rollers 150 can provide sufficient resistance to the strips to stretch the side portions 152a-b

onto coiled wire 110 and lay the center portion at the bottom of valley 124. In general, rollers 150 will be set to a predetermined percentage of the speed of wire 110 so that strip 140 is continuously stretching the portion 152a-b of the strip that contacts wire 110 by that percentage. Portions 154 of strip 140 that go into valley portion 124 will stretch much less, or very little, and thus forms a smaller radius. In many example, the center of portion 154 may stretch only a small amount because it is protected from heating by heat guard 159 which is mounted between heater 151 and strip 140. Thus as strip 140 is wound onto wire 110, different transverse portions of strip 140 are being stretched at different rates and are actually is being wound onto conduit 158 at different speeds even though strip 140 is being fed into the system at a constant speed at rollers 150 before heating and stretching is performed. The other disclosed differentially stretchable strips disclosed in this document can operate in a similar manner.

In FIGS. 4 and 7, wear strip 141 comprises a polymer blend that is highly wear resistant. Because wear strip 141 is bonded adjacent wire 110, wear strip 141 does not stretch significantly as the hose extends and retracts. Thus wear strip 141 can comprise a metal alloy, hard wear resistant polymer(s), reinforced composite, or other highly wear resistant material that can be bonded to and/or crimped on the exterior ridge of bonded strip 140. Examples of materials that might be used for wear strip 141 include, but are not limited to, stainless steel strip, brass, other non-corrosive metals, and alloys Polyurethane (TPU or PU), PET, ABS, Nylon, HDPE, Polypropylene, and other wear resistant polymers, polymer composites and polymer combinations. During heating of strip 141, only the underside needs to be heated, or adhesive applied, so that bonding takes place between strip 141 and strip 140. If strips 140 and 141 are incompatible with heat fusing, then adhesives or intermediate layers can be used to bond the two strips together. Alternatively, the entire strip 141 can be heated so that roller 131 can also shape and mold the exterior and sides of strip 141 to the desired shape. One example of materials that can be used for strips 140 and 141 can comprise a polypropylene, or polyurethane, based polymer blend for matrix 143 in strip 140 and a polypropylene, or polyurethane, based composite for wear strip 141, respectfully, to allow thermal bonding (fusing) of the two strips. Another example of materials can comprise a polyurethane based blend for matrix 143 of strip 140 and a PET polymer for wear strip 141, with adhesive used to achieve bonding between the two strips. The reader should note that there is nearly an endless number of combinations for strip 140 and strip 141 materials that could be used with thermal and adhesive bonding since each family of polymers can have dozens of different formulations. In fact, wear strip 141 can be co-extruded and/or molded as part of polymer strip 140, eliminating the need for a separate strip 141. With this method, wear strip 141 and matrix 143 may be, or may not be made of the same material.

In FIG. 1, manufacturing equipment 100 shows multiple steps in building finished conduit 158. Specifically these steps comprise: 1) bending wire 110 into a coiled tension spring, 2) expanding the coils to the correct coil pitch, 3) wrapping reinforced strip 140 on coils 110, 4) bonding the strip together to form a conduit, and 5) bonding a valley reinforcement cord 155 in the valley of the hose. Notice that the construction of strip 140 and use of step 5) are the novel and unobvious components of making hose 158.

In FIGS. 1, 2, 4, 5, 7 and 8, valley reinforcement cord 155 is seen being wrapped onto its respective conduit near the center between the wire coils. Tension on cord 155 pulls the other hose structure toward the center of the valley (in toward the axis of the hose) to the desired radius. Because the radius

of cord **155** is significantly smaller than the radius of coiled wire **110**, cord **155** is effectively trapped in the valley of the conduit whether bonded or not bonded to the exterior of the hose. Cord **155** can be coated with a polymer or an adhesive to allow it to bond to matrix material **143** and **143a-b**, and thus integrate it with the conduit. In FIG. 1, cord **155** can be coated with polymer matrix **143**, or other compatible polymer, so that heater **151a** can melt the polymer and prepare cord **155** for thermal bonding to strip **140** in valley **124a**. Note that additional heaters can be used to heat strip **140** at the bottom of the valley for better bonding of reinforcement cord **155**. In FIG. 2, cord **155** is heated by heater **151a** to prepare cord **155** for bonding to strip **140c** at the bottom of v-shaped valley **124a**. In FIG. 4, cord **155** is heated by heater **151b** to prepare cord **155** for bonding to strip **143b** at the bottom of valley **124a**. In FIG. 5, cord **155** is heated by heater **151c** to prepare cord **155** for bonding between strips **143a** and **143b** with cord **155** wrapped over bidirectional reinforcement **140k**. In FIG. 7, cord **155** is heated by heater **151a** to prepare cord **155** for bonding to reinforced hose body **200** at the bottom of valley **124a**. In FIG. 8, cord **155** assists cords **252** and **254** in maintaining the valley shape, and providing additional radial support against internal pressure. While the use of adhesives is not shown in these drawings, the art of applying adhesive in continuously manufactured products is a well developed science, and can be used with any of the manufacturing processes discussed in this document.

In FIGS. 1, 2, 4, 5, 6, 7 and 8, valley reinforcement cord **155** provides a number of non-obvious benefits. First, cord **155** can create and stabilize the v-shaped valley. The advantages of the v-shape is not obvious at first, since most non-reinforced stretch hoses have a wide u-shape valley and work fine with this shape. However, when bidirectional reinforcement is integrated into a convoluted hose body, the hose body can no longer stretch like an unreinforced hose, and the wide u-shaped valley of prior art designs tend to cause more binding when retracting. Second, the wide u-shaped valley of prior art significantly increases stress in the reinforcement at the coiled wire due to the larger off-axis angle there. The sharp u-shaped or v-shaped valley created by the valley reinforcement **155**, reduces this angle and thus gives the bidirectional reinforcement (cords **142** and **144**) greater mechanical advantage against longitudinal forces (pulling on hose forces). Thus, the valley reinforcement also significantly increases the effective longitudinal strength of the hose. Third, reinforcement cord **155** also maintains the valley depth even when the hose is subjected to high temperatures where reinforcement fibers might shift and change the shape of the hose. Cord **155** insures that the valley is maintained both during and after use. And fourth, reinforcement cord **155** provides additional pressure strength for the hose by transferring some of the radial pressure tension in the bidirectional reinforcement (cords **142** and **144**) to cord **155**. Thus, valley reinforcement cord **155** provides many functions.

FIG. 1A shows a section of strip **140** before being heated and wrapped onto wire **110**. FIG. 1B, shows the approximate shape and orientation of the cords of the same section of strip **140** seen in FIG. 1A after it has been stretched onto wire **110** and mandrel **120**. Note that to actually be wrapped onto mandrel **120** and coiled wire **110**, the section of strip shown in FIG. 1B could not be laid flat anymore, thus FIG. 1B shows an approximation of what the section would look like if you could flatten it out. Notice that cords **142** and **144** change orientations to allow strip **140** to differentially stretch instead of actually stretching cords **142** and **144**. To effectively allow this shifting of the cords in a woven fabric, cord angles **148a** and **148b** of cords **142** and **144**, respectively, should be at least

thirty degrees to allow the desired indentation shape **124a** and no greater than eighty degrees so that enough strength is provided along the longitudinal axis **145** of the strip. Angles smaller than thirty degrees could be used for angles **148a** and **148b**, but the maximum depth possible for indentation **124a** would be reduced and this could adversely effect the retracting ability of finished conduit **158**. Optimally, angles **148a** and **148b** should be larger than forty degrees to provide a larger indentation (valley **124** or **124a**) between the coils of wire **110**. This provides the ability of the cords to tilt toward the longitudinal direction when the edge areas **152a** and **152b** are stretched (see FIG. 1B). Larger angles for **148a** and **148b** can be used, but as these angles grow larger than seventy degrees, cords **142** and **144** become more and more aligned transversely, and thus provide less and less reinforcing in the longitudinal direction **145** of the strip. Since the hoop stress on a cylindrical pressure conduit is twice the longitudinal stress for the same conduit, the hoop strength is very important. Thus, the longitudinal strength of strip **140** (direction **145**) could be compromised by making angles **148a-b** much larger than seventy degrees before stretching and sixty-five degrees after stretched on the conduit. Note that the longitudinal direction **145** for strip **140** when laid onto the conduit is oriented substantially in the direction of the hoop stress of finished conduit **158** (strip **140** laid substantially perpendicular to the longitudinal direction **147** of the finished hose **158**). Likewise, the transverse direction of strip **140** (perpendicular to direction **145**) is laid substantially in the longitudinal direction **147** of finished conduit **158**. This means that when strip **140** is wrapped on coiled wire **110**, cords **142** provide most of the hoop strength, and cords **144** provide most of the longitudinal strength.

In FIG. 1B, we see what the section of strip **140** seen in FIG. 1A might look like after it has been stretched onto coiled wire **110**. Note that the larger diameter sections of the conduit near the wire have been stretched longitudinally to compensate for the larger distance and larger circumference at that portion of the conduit. This is in contrast to the shorter distance around the circumference of the valley of the conduit near the center region of strip **140** and between the wire coils. Thus, after being stretched around mandrel **120** and coiled wire **110**, reinforced polymer strip **140** can be substantially un-stretched near the midline of the strip (center of transverse portion **154**), while the edges of strip **140** (transverse portion **152a-b**) are stretched significantly by the difference in linear velocity between the rotating coiled wire **110** and tensioning rollers **150**. In other words, the exterior speed of coiled wire **110** is set significantly larger than the exterior speed of tensioning rollers **150**, assuming strip **140** is not slipping as it passes through rollers **150**. Notice in FIG. 1B that strip **140** has stunk transversely as it has stretched. The dashed lines show the original width of strip **140**. The larger the cord angles **148a-b** the less transverse contraction that is needed to provide the shown stretch. As cord angles **148a-b** near thirty degrees the strip can stretch by less than ten percent, while an unreasonable amount of transverse shrinkage can occur. For deep valley portions **124**, angles **148a-b** can be made greater than forty-five degrees so that the needed longitudinal stretching can be achieved. These larger angles also reduce the changes in the transverse width of strip **140** while differentially stretching.

In FIG. 1C, we see polymer strip **140** in a section view, showing the cross-section along a line cut transversely through strip **140** (see FIG. 1). Fiber cords **142** and **144** are woven in and out of each other, but only their ends are shown in this section view. Matrix **143** is bonded to and/or surrounding fiber cords **142** and **144** to form a composite strip. Fiber

19

cords **142** and **144** form a woven fabric in this example, but may alternatively be layered as separately oriented sheets that are fused together (see FIG. 1C), or two layers each with one of the fiber cord orientations bonded together. The thickness of polymer strip **140** is exaggerated in FIG. 1C in order to show detail. In actual practice, strip **140** can be approximately 0.005 inches to 0.050 inches thick, and 0.5 inches to 1.5 inches wide for a single layer one inch diameter hose. The actual chosen dimensions for the strip depend on many factors including whether a single layer or double layer of strip is being wrapped, the operating conditions for the conduit (i.e. pressure rating), diameter of the conduit, the pitch between wire coils, and etc. The woven layer of cords **142** and **144** are shown here near the center of strip **140** (and matrix **143**) to provide maximum flexibility. This type of strip material can be used with any number of conduit making machines including, but not limited to, the conduit making machines shown in this document.

In FIG. 1D, we see a top view of the alternate knitted reinforced strip material **140a**. Strip **140a** comprises a weft knit fabric **142a** encapsulated in the matrix material **143**, with yarn (cord) reinforcement **142b** woven within or bonded to fabric **142a**. Knitted fabric **142a** and reinforcement **142b** can each comprise fiber cords similar to cords **142** and **144** discussed previously. Reinforcement **142b** is substantially aligned with the longitudinal direction **145** of strip material **140a**. Cords **142b** limit longitudinal stretch of fabric **142a** in the center portion of strip **140a** and provide valley reinforcement for the finished hose when used in a convoluted hose making machine, such as machine **100**. Strip **140a** is designed to be wrapped onto a convoluted hose with cords **142b** positioned in the center of the valley of the conduit. This type of strip material can be used with any number of conduit making machines including, but not limited to, the conduit making machines shown in this document.

In FIG. 1E, we see a top view of warp knitted reinforced strip material **140b**. Strip **140b** comprises a warp knit fabric **142c** encapsulated in the matrix material **143**. Section **142d** can be knitted as part of fabric **142c** and has significantly less stretch in the longitudinal direction **145** than other portions of knitted fabric **142c**. Knitted fabric **142c** and low-stretch reinforced section **142d** can each comprise fiber cords similar to cords **142** and **144**. Reinforcement section **142d** is substantially aligned with the longitudinal direction **145** of strip material **140b** and performs the valley reinforcement function similar to valley forming reinforcement cords **142b** and **155** because of the low stretch properties center section **142d**. Strip **140b** is designed to be wrapped onto a convoluted hose with section **142d** positioned in the center of the valley of the conduit. This type of strip material can be used with any number of conduit making machines including, but not limited to, the conduit making machines shown in this document. Example Conduit Making Machine **100a**—FIGS. 2 Through 2B

In FIG. 2, we see a second example of valley shaping reinforcement **155** used with a continuous conduit making machine **100a**. Conduit making machine **100a** is designed for making finished conduit **158a** by bonding fiber reinforced strip **140c** to itself at helical bonding zone **157**, which is positioned at the bottom of valley portion **124a** between the coils of wire **110**. In this example, valley shaping reinforcement **155** is wound in the valley on top of bonding zone **157**. The final hose **158a** is very similar to finished hose **158** seen in FIG. 1, except that the seam of the hose is in the valley instead of at the crest of the convoluted hose. In FIG. 2, reinforcement **155** serves the same function as it did in FIG. 1.

20

In FIG. 2, conduit making machine **100a** comprises wire bending machine **105**, roller mandrel **120a**, heaters **151** and **151a**, rollers **150** and **150a**, roller(s) **180**, and roller(s) **180a**. Heater **151** is used in this case instead of heater **161** because machine **100a** is using strip **140c** for conduit construction. Heater **151** can be used in FIG. 2, because strip **140c** is very similar in properties to strip **140**, with the only difference being that cords **142** and **144** are laid in two separate layers in strip **140c**, but are woven in strip **140**. The section view of strips **140** and **140c** can look identical. However, when tensioned, strip **140c** can behave quite differently than strip **140**. Thus, tensioning rollers **150** can be adjusted to provide the proper tensioning for strip **140c**. Heater **151** is adjusted to properly melt reinforced polymer strip **140c** so that it can be differentially stretched onto wire **110** and around mandrel **120a**. As mentioned before heater **151** can include heaters on both the bottom (shown) and top (not shown), and can comprise additional heaters near the actual overlap location.

In FIG. 2, rotating rod mandrel **120a** comprises, a center rod **123** with a straight portion **123a**, a valley forming portion **124a** and ridge forming portion **125**, and four rotatable rods **122a-d**. Center rod **123** is stationary and is mounted in the center of the four rotatable rods **122a-d**. Center rod **123** can be mounted to wire bending machine **105** or other solid structure. Rods **122a-d** are motor driven (not shown) and designed to rotate coiled wire **110** around mandrel **120a**, and provide a surface for applying pressure to hose strip **140c** for bonded at roller(s) **180** and **180a**. If FIG. 2, we see that center rod **123** can continue past the end of rods **122a-d** and take on a convoluted shape with a valley portion **124a** and a ridge portion **125** which allows v-shaped roller **185** on roller assembly **180** to help form the v-shaped valley and to bond cord **155** to the hose. Tension on reinforcement cord **155** from rollers **150a** also assist in shaping strip **140c** to form the desired v-shaped valley. The convoluted portion of center rod **123** is designed to provides a stable platform for shaping v-shaped valley. Also notice that rotating mandrel system **120a** can be used to make hose with the bond zone at the top of the ridge like hose **158** seen in FIG. 1, and is not limited to just the strip materials discussed within this document.

In FIG. 2 we see that strip **140c** is stretched differently than strip **140** seen in FIG. 1. Strip **140c** is stretched near its centerline (transverse portion **154**) while strip **140** is stretched near its edges (transverse portions **152a-b**). This is because wire **110** is aligned near the center of strip **140c** in this example (see FIGS. 1 and 2 for comparison). Because the center of strip **140c** is stretched onto wire **110**, the edges of strip **140c** must be bonded near the valley portion **124a** between the coils. Optional heat guards **159a-b** can be used to reduce heating to the edges of strip **140c** to prevent significant stretching of edge portions **152a-b**. Heat guards **159a-b** allow heating toward the end of heater **151**, to allow the outer surface of strip **140c** to be heated for bonding. Heater **151** can be placed closer to mandrel **120a** than shown to facilitate heating the inner surface of edge **152b** and outer surface of edge **152a** as it rotate around the mandrel. This helps heat the edge surfaces of strip **140c** while still allowing a heat bonded seam. Additional heaters can be used to heat the strip after it is stretched (i.e. rollers **184** can be heated). The overlap portion **157** of strip **140c** is shown in FIG. 2, and extends along a spiral path, the full length of the conduit. In alternative constructions, adhesives can be used to bond the edges of strip **140c** together. Also, strip **140c** can be replaced by many of the other differentially stretchable strips, such as, strips **140**, **140d**, **140e**, **140k**, **143a**, **143b**, as well as, extruded strips **143d**, or **143e**, depending on the final use of the hose.

In FIG. 2, roller assembly **180** comprises shaft **182** and rollers **183**, **184**, and **185** mounted on shaft **182**. The contact surface of rollers **183**, **184** and **185** can be textured to improve grip against strip **140c** and can be powered to turn at the same rate as strip **140c** to help motivate the strip to rotate with wire **110**. Additional roller assemblies similar to assembly **180** can be used, if needed, and may be mounted all the way around mandrel **120a**. After the second roller assembly **180a**, finished conduit **158a** is allowed to cool and then retract to its minimum length (retracted length). Conduit **158a** is shown fully retracted at section **170** after coming off of mandrel **120a**. Care must be taken to allow strip **140c** to cool sufficiently on the conduit before full retractions of the hose, otherwise the strip **140c** material could still be hot enough to bond to adjacent coils if pressed together by spring wire **110**. In an actual conduit making machine, pullers would keep conduit **158a** stretched for a distance after leaving mandrel **120a** to allow it to cool sufficiently to allow reinforced strip **140c** to stabilize its extended shape. The retracted section **170** of conduit **158a** is its normal relaxed state, with coiled spring wire **110** strongly tending to retract the conduit even when fully retracted as shown in section **170**. This retracting ability is common to all conduits made by the conduit making machines disclosed in this patent.

In FIG. 2A we see a portion of strip **140c** before being stretched onto wire **110**. In FIG. 2B we see the same portion of strip **140c** seen in FIG. 2A after it is stretched onto coiled wire **110** and forms a three-dimensional curved shape. Strip **140** would stretch in a similar manner if used on conduit making machine **100a**. Notice that the stretched strip portion shown in FIG. 2B only approximately shows the three-dimensional deformation that occurs in strip **140c** as it is stretched onto mandrel **120a** of conduit machine **100a**. Diagonal cords **142** and **144** do not stretch when matrix **143** stretches, but the angle of cords **142** and **144** changes to allow the central portion (transverse portion **154**) of strip **140c** to stretch while the edge portions (**152a-b**) stretch significantly less. Again, the new position of cords **142** and **144** seen in FIG. 2B is only approximate and is only designed to convey how the cords move to allow differential stretching of strip **140c** in this design.

In FIG. 2C, we see a top view of the alternate knitted reinforced strip material **140d**. Strip **140d** comprises a knit fabric **142e** encapsulated in the matrix material **143**. Within knitted fabric **142e** are reinforced knitted sections **142f** that have very low stretch in the longitudinal direction **145**. Knitted fabric **142e** and reinforced sections **142f** can each comprise fiber cords similar to cords **142** and **144**. Fabric **142e** and sections **142f** can be formed with the same cords (i.e. cords **142**) where section **142f** would be knitted with a different low stretch patterns compared to the rest of fabric **142e**. Strip **140d** is designed to be wrapped by hose making machine **100a** to form a convoluted hose with sections **142f** positioned substantially in the center of the valley of the conduit. Sections **142f** limit the longitudinal stretch of strip **140d** in those portions of the strip and assist conduit making machine **100a** in forming the needed valley at the edges of strip **140d**. Sections **142f** also serves as a valley reinforcement similar to valley reinforcement cord **155**, but is part of the knitted structure of fabric **142e**. Strip **140d** is another example of how valley reinforcement can be applied in alternate ways.

The reader should understand that the disclosed manufacturing example in FIGS. 1 and 2 can easily be extended to provide additional layering of material on the conduit being manufactured simply by extending the length of mandrel **120** and **120a** to providing space for additional sheet material(s) to

be rapped on the hose (i.e. extra wear strips, additional coverings or other applied layers, labeling, etc.).

In FIG. 2D we see a transverse section view of differentially stretchable strip **140e**, comprising a polymer matrix material surrounding diagonally woven cords **142** and **144**. The construction of cords **142** and **144** in strip **140e** can be identical to those seen in strip **140** or **140c**. Strip **140e** however is designed to wrap over two wire coil sections at time and is thus approximately twice as wide as strips **140** and **140c**. Strip **140e** can also be half as thick as strips **140** and **140c** since it will be wrapped onto the conduit in a double thickness. In this particular strip design, the woven cords **142** and **144** are bonded near the top surface of polymer layer **143**, but in other designs the cords can be placed in the middle of polymer matrix **143**. Cords **142** and **144** can also be replaced with cords that have half the density since two layers of cords will cover each section of hose (double layer with some overlap at edges for three layers in bond zone **156**, see FIG. 1). The double layer structure of the resulting hose provides greater resistance the seam between wrappings to come apart since the reinforcement cords **142** and **144** overlap an entire coil width on the hose. Strip **140e** can be used with the other conduit making machines just like strips **140** and **140c**.

Example Conduit Making Machine **100b**—FIG. 3

In FIG. 3, conduit making machine **100b** for making a double reinforce conduit **158b**. Conduit making machine **100b** shows an example of additional reinforcing cords **270a-d** being used to radially reinforce and shape hose **158b**, and using cords **270d** as valley reinforcement at the bottom of the valley. Cords **270a-d** are bonded over bonded strip **140** and longitudinal cords **272**. This example shows how the shape of the valley can be controlled by more than one valley reinforcement cord at the bottom of the valley. In alternate designs, additional polymer layer(s) may be bonded over reinforcing cords **270a-d** and **272** to hide this cord structure. In FIG. 3, longitudinal cords **272** and radial cords **270a-d** are positioned with a small space between them to provide added burst strength without significantly stiffening the body of the conduit. Machine **100b** comprises the previously mentioned conduit making machine **100**, with some modifications to the roller arrangement and of course the valley reinforcement. Note that the wear strip equipment (see FIG. 4) could have been easily added to an extended mandrel, but has been omitted to fit the drawing on the page.

In FIG. 3, conduit making machine **100b** comprises the previously discussed wire coiling machine **105**, mandrel **120**, two bonding roller assemblies **130**, tensioning rollers **150**, and heater **151**, along with the new components, heater **151b**, friction tensioning bar **150b**, radial cord guide **276**, which guide radial cords **270a-d**, and longitudinal cord guide **278** (sometimes called a nose ring) which guides longitudinal cords **272** onto the conduit. Notice that conduit making machine **100b** has the main components of conduit making machine **100** with the addition of a bonding system for bonding cords **270a-d** and **272** to the exterior of the conduit to provide added pressure strength and longitudinal strength without significant increasing the stiffness to the body of the conduit (strip **140**). Thus, cords **270a-d** and **272** still allow easy retraction and extension of the conduit. Cords **272** can be polymer coated fibers and/or uncoated fibers depending on the conduit construction. If uncoated yarn is used for cords **272** coated cords **270a-d** can have sufficient polymer to bond to strip **140** between cords **272**. Also notice that wire coil bending machine **105a** can easily be substituted for coil bending machine **105**. Cords **270d** provide the bottom valley rein-

forcement to provide a v-shaped valley. The other cords **270a-c** provide additional support and can be used to further define the shape of the valley.

In FIG. 3, the mechanism for applying reinforcing cords **270a-d** and **272** comprises friction tensioning bar **150b**, guide **276**, ring guide **278**, and heater **151b**. Reinforcing cords **270a-d** and **272** can comprise any high tensile strength fiber similar to those discussed for cords **142** and **144**. Cords **272** do not have to have the same composition as cords **270a-d**. In fact, each of the cords **270a-d** may all be different sizes and/or composition as needed for a particular conduit function. In particular designs, all of cords **272** and **270a-d** can be the same. In most examples, cords **270a-d** and **272** will only be a few thousandths of an inch thick and several times wider than it is thick after being laid on the hose. Thus, cords **270a-d** and **272** can have the shape of a flat strip after being wrapped onto the exterior of the conduit. Cords **270a-d** and **272** may have this flat profile before entering machine **100b**, as seen in FIG. 3A, or can be given this shape after heating and bonding to strip **140**. While a flat profile is desirable, the system will still work with more symmetric cords, such as, circular cross-section cords.

In FIG. 3A, we see the structure of cords **270a-d** in section view comprising many micro-fibers **274** bonded within a polymer matrix **275**. Fibers **274** and matrix **275** are chosen so that they can be bonded to each other. That is, fibers **274** do not easily delaminate from matrix **275**. Matrix **275** also holds micro fibers **274** together to form a single cord, and preferably bonds strongly to fibers **274**. Polymer matrix **275** is also chosen so that it can be strongly bonded to strip **140** (bond to polymer material **143** on the exterior of strip **140**), either by melt bonding, adhesive bonding, solvent bonding or other bonding methods.

In FIG. 3, circular guide **278** comprises a circular body that extends around mandrel **120** and can be attached to a hose wrapping machine (not shown) for rotating spools of cords **272** (not shown) around the mandrel in direction **146a**. Prior art spiral reinforcement wrapping machines are a standard component in the hose manufacturing industry for applying spiral wrapped reinforcement onto conduits. These prior art wrapping machines, however, are designed to wrap the reinforcement onto a non-rotating hose. In contrast conduit **158b** is rotated during manufacturing by conduit making machine **100b**, so that the wrapping angle can be controlled by the difference between the rotational speed **146** of hose **158b** and rotational speed **146a** of cords **272**. Arrows **273** show the direction of linear motion of cords **272** and arrow **146a** shows the rotational direction and relative rotational speed of cords **272**. Notice that in this example the rotational speed of cords **272** and hose **158b** are shown as approximately equal. With rotation speeds **146** and **146a** the same, cords **272** will be laid substantially lengthwise (longitudinally) along the hose as shown. Circular guide **278** can comprise individual guides for each cord **272** instead of notches. Alternatively, circular guide **278** can be a smooth stationary ring like guide ring **279** (see FIG. 6) so that cords **272** are guided by sliding along the inside surface of the smooth stationary ring. If cord guide **277** encompasses the conduit and is designed to guide cords **272** properly, then guide **278** could be eliminated. Similarly, the proper design of guide ring **278** can eliminate the need for guide **277**. In FIG. 3, guide **278** rotates with coiled wire **110** and strip **140** so that cords **272** are positioned (bonded) longitudinally onto the conduit formed by strip **140** (direction **147**). It can be desirable for cords **272** and guide **278** to rotate at speeds different than coiled wire **110** so that cords **272** can spiral around the finished conduit formed by polymer strip **140** at a predetermined rate and direction. For example, if

cords **272** are rotated faster than coiled wire **110**, cords **272** will wrap around the conduit with a right-handed spiral, which is in the opposite direction as wire coil **110**. This right-handed spiral, thus can provide a resistance against left-handed wire coil **110** to reduce twisting along the longitudinal axis of hose **158b** when pressurized. Rotating cords **272** faster than wire **110** can also place cords **272** closer to perpendicular to cords **270a-d**. Rotating cords **272** slower than wire **110** causes cords **272** to wrap around the conduit with a left-handed spiral (see cords **254** on wrapping machine **250b**).

In FIG. 3, stationary cord guide **276** comprises guide notches or eyelets for guiding cords **270a** through **270d** over cords **272** and strip **140**. Cords **270a-d** are fed from spindle or spools (not shown) and tensioning systems (not shown) as is normal for cord or yarn feeding and wrapping systems. Because guide **276** does not move, the cord feeding system can comprise an industry standard rack of spindles (spools) to feeding guide **276**. Friction tensioning bar **150b** is shown as a metal bar structure for providing friction and tension to cords **270a-d**, and can comprise one or more friction bars and/or eyelets for each cord to provide the desired individual friction and tension for each cord **270a-d**. Alternative tensioning systems can comprise a significantly more complex system than shown here with rollers and/or spring tensioning systems as is common in the textile industry. Cords **270a-d** are laid over cords **272** so that longitudinal tension in cords **272** does not cause them to tear away from the valley portion of strip **140**. Cords **270a-d** go onto the conduit at different speeds. Cord **270a** is the fastest, while cords **270b** are the next fastest, cords **270c** are the next fastest and cords **270d** are the slowest. The relative speed of each cord is shown approximately by the length of arrows **271** at the end of its respective cord. Notice that the left-most cord **270b** must compress all the cords **272** against strip **140**. Optionally, cord guide **277** can be positioned to follow near the path of the left-most cord **270b** and pre-compress cords **272** near the conduit surface to help relieve some of the stress on cord **270b**. Cord guide **277** is shown attached to guide **276**, but can be attached anywhere a stable mounting bracket is available, such as, on guide **278** and/or heater **151b**.

In FIG. 3, each radial cord **270a-d** is moving at a different rate to match the speed of strip **140** at that radius. Rollers can be used (see roller **160** in FIG. 8) to help press together these cords and strip material **140**. Special roller assemblies like roller assembly **160** can be used that have separate sections that can each rotate at a different rate to match the rate of its respective cord. Many additional cords, in both the longitudinal and radial directions, might be use if large hose diameters are created.

In FIG. 3A, we see a section view of cords **270a** through **270d**, which have similar construction. Multiple micro fibers **274** run longitudinally through cords **270a-d**, incased in a polymer matrix **275**. Cords **270a-d** have an elongated rectangular shape in this example to attach flat onto conduit strip material **140** and provide a low profile reinforcement. Polymer matrix material **275** can comprise any number of polymers including, but not limited to, the polymers discussed for matrix **143**, and **143a-b**. Fiber reinforcement strands **274** can comprise any number of high strength fibers, including, but not limited to, those fiber materials discussed for cords **142**, **144**, **142a-f**.

Example Conduit Making Machine **100c**—FIG. 4

In FIG. 4, we see conduit making machine **100c** using the disclosed valley reinforcement cord **155** with composite strip **140g**. Cord **155** is wrapped on top of elastomer layer **143b** with reinforcement layer **140f** and elastomer layer **143a**

below it. Reinforcement **140f** is thus, sandwiched between strips **143a** and **143b** with cord **155** on top in the finished hose. Through the application of heat and pressure elastomer layers **143a-b** are bonded together through the mesh layer **140f** to form a reinforced convoluted conduit. Cord **155** holds all these layers down in the valley of the hose and gives finished hose **158d** a stable v-shaped valley.

In FIG. 4, conduit making machine **100c** comprises wire coiling machine **105**, mandrel **120b**, tensioning rollers **150a** and **150c**, heaters **151a** and **151b**, heater shields **159** and **159c**, roller assembly **130**, roller assembly **130a** and forming roller **131** for making a finished conduit **158c**. Coiling machine **105**, mandrel **120b**, rollers **150a**, heater **151a**, and roller assemblies **130** and **130a** are substantially the same as seen in FIG. 1. Modifications to these systems can be done to optimize conduit making machine **100c** for wrapping composite strip **140g** onto mandrel **120b**. Rollers **150c**, and heater **151b** has been added to allow construction of conduit **158c** in this way. These components are designed to heat strips **143a-b** and **140f** at the same time so that it can differentially stretch as a unit over coiled wire **110** and mandrel **120b**. Strip **140g** is composed of three separate strips **143a**, **140f**, and **143b** that are bonded together prior to entering conduit making machine **100c**. Strip **140f** can be designed to extend across the entire width of composite strip **140g** so that the reinforcement in strip **140f** has a larger overlap region. Strips **143a-b** can be composed of the same polymer as matrix material **143** seen in strip **140**. Cords **142** and **144** in reinforcing strip **140f** can be made of the same materials as the cords **142** and **144** seen in strip **140**, but without matrix **143** molded around them or possibly a small amount of matrix **143** or other polymer molded around the cords. Cords **142** and **144** are embedded into the top surface of strip **143a** and the bottom surface of strip **143b**. In FIGS. 4 and 5, reinforcing mesh strip **140f** is shown with an open mesh structure which can be woven or non-woven. The density of cords **142** and **144** will depend on the type of conduit being made and what it will be used for. In many uses, strip **140f** can be a woven fabric to provide high strength. In other applications strip **140f** can be an open mesh as shown (either woven mesh or non-woven mesh).

Heat shields **159** are positioned between heater **151b** and the center of strips **143a** and **143b** to protect the transverse portion of those strips from heating to a temperature near their deflection temperature. Reinforcing strip **140f** may not require a heat guard since cords **142** and **144** have a much higher melting temperature than strips **143a-b**, but depending on the conduit being made and the density of cords **142** and **144** it may be required to protect the small cords from overheating during heating of strips **143a-b**.

Rollers **132** and **134** are used to press composite strip **140g** against itself to bond it into a sealed conduit. Specifically, the first roller **134** on the left is designed to press the right edge of strip **143a** against the left edge of itself (strip **143a**) to form the innermost layer of conduit **158c**. The second roller (roller **132**) is designed to press the left edge of strip **143b** against the left edge of strip **140f** and the right edge of strip **143a** below it. This places strip **140f** on top of strip **143a** and below strip **143b**, and places reinforcement strip **140f** sandwiched between strips **143a** and **143b**. Roller **132** is also designed to press the right edge of polymer strip **143b** down through strip **140f** and onto the right edge of strip **143a**, to create a bond between strip **143a** and **143b**. The first roller **132** on assembly **130a** is designed to press the left edge of strip **143b** again to insure strip **143b** is bonded to strip **143a** through the two edges of strip **140f**. The second roller **132** on assembly **130a** (right most roller **132**) is designed to continue pressing hot strip **143b** down through cords **142** and **144** and into strip

material **143a**, locking the two edges of reinforcing strip **140f** together at the seam **156** and provide a reinforcing layer within conduit **158c**. The right most roller **132** finishes the hose structure by pressing the right edge of strip **143b** against the left edge of strip **143b** to bond it to itself at bond zone **156** and forming a sealed exterior layer on conduit **158c**. The process is designed to provide the hose with distinct layers in the conduit: 1) An interior layer made of strip **143a**, 2) a central layer made of reinforcing strip **140f**, and 3) an exterior layer made of strip **143b**. Additional rollers can be used to provide better bonding of the layers by pressing the strips together in the v-shaped valley portion **124a** of mandrel **120b**. Valley forming cord **155** is wrapped on with strip **143b** and assists in pulling all three layers into the desired v-shape. Composite strip **140g** is shown here as formed separate from conduit making machine **100c**, but one could just as easily bring the three strips **143a**, **140f**, and **143a** together as they are wrapped onto mandrel **120b** (see FIG. 5, strips separately, not molded overlapping each other as in FIG. 4).

In FIG. 4A, we see a section view of composite strip **140i** with edge views of strips **143a**, **140j** and **143b**. Notice that strip **140i** is very similar to composite strip **140g** seen in FIG. 4. The only difference between strips **140g** and **140i** is that the center mesh **140j** in strip **140i** is coated with a polymer to hold the mesh cords **142** and **144** together. During manufacturing strips **140g** and **140i** behave approximately the same, though strip **140i** can be easier to bond together with strips **143a-b**. Strip materials **143a** and **143b** can be made of a flexible polymer similar to matrix **143**. Bidirectional reinforcement strip **140j** comprises woven or layered (see FIG. 5A) cords **142** and **144** that can be coated or encapsulated within a polymer matrix. Strip **140j** is bonded between strips **143a-b**. The angle of cords **142** and **144** within this arrangement can be the same as in strip **140** or any of the other bidirectional weave and knit reinforcement presented here to provide differential stretching of different transverse portions. A stabilizing reinforcement **155** can be bonded along the center of reinforcing strip **143b** as shown, or along the center of reinforcing strip **140j** to substantially prevent the center of strip **140j** from stretching during heating and molding of composite strip **140i**. Reinforcement **155** can be cords similar to cords **142** and **144** with matrix material **143**, or **143a-d**, binding the fibers within the cords together. In this way, reinforcement **155** can be coated to keep water way from the high-strength fibers within the cord. In alternate designs, cord **155** may be uncoated. With other bonding methods, such as adhesives, reinforcement **155** can be nearly any material that is somewhat flexible. Alternatively, reinforcement **155** can be made of the same materials as cords **142** and/or cords **144** and woven or bonded to strip **140j** near its center along its longitudinal axis (see FIG. 5). This causes the center portion of strip **140j** to be stretched down into valley **124a** and form the desired convoluted helical shape. Valley reinforcement **155** insures that the valley is properly formed in the bidirectional reinforcement formed on the hose and that the valley will not deform permanently from high temperature use.

In FIG. 4B, we see a transverse section view of strip **140h** comprising reinforcing cords **142** and **144** pressed into a double wide strip (two wire coils wide strip) of matrix **143** and valley forming reinforcement cord **155**. Cords **142** and **144** can be woven or non-woven depending on the final product desired. Strip **140h** would be wrap by conduit making machine **100c** the same way as strip **140g**. However, strip **140h** is designed to be wrapped two layers thick. Thus, strip **140h** wraps onto coiled wire **110** such that each side edge wraps over three wire coils, one coil on each end and one wire coil at its center. Guides can be used to guide strip **140h** onto

wire 110 so that it is aligned with the coils. Three heat guards (heat guards 159 and center heat guard 159c) can be used to protect the valley portions of matrix material 143 in strip 140h from heating to its deformation temperature. This protection reduces softening of matrix material 143 in the valley portions of reinforced strip 140h and thus helps form the v-shape of the valley portion of the conduit. Strip 140h when wrapped by conduit making machine 100c will produce a conduit substantially different in structure than the conduit made with reinforced strip 140g. Strip 140h will produce a double layer hose where each layer comprises a layer of matrix material 143 and a layer of woven cords 142 and 144. This provides a double layer structure except at the bond zone 156 (at the wire ridge area) where three layers are melted and bonded together. Reinforcement cord 155 is positioned in the valley portion of the strip and provides essentially no stretch when wrapped on mandrel 120b. Thus, cord 155 insures that strip 140h is pulled down into the v-shaped valley desired, and also insures that valley will not deform significantly over the life of the hose.

Strip 140h has reinforcing fibers 142 and 144 substantially along its entire top surface. Fibers 142 and 144 in strip 140h are preferably woven, but can be non-woven if desired. The dimensions of strip 140h is approximately twice the wide and half the thickness of strip 140. This allows strip 140h to be applied in two layers overlap to produce a conduit with at wall thickness that is approximately the same as conduit 158, which is made with strip 140 wrapped on as a single layer (see FIG. 1). If strip 140h were made three times as wide as strip 140 then a thickness of one-third might be used to produce similar wall thicknesses by wrapping three layers thick.

Notice that in FIGS. 4, 4A and 4B, strips 140g, 140i and 140h, respectively, can be constructed to have about one-half the thickness or less of the other strips presented in this patent (see strips 140, and 140c). Strips 140g and 140i produce a three-layer conduit, while strip 140h produces a substantially four-layer conduit (two layers of reinforcement/polymer 143). Even with this different structure, strips 140g and 140i can form a final conduit structure that is similar to conduits formed by strips 140 and 140c in FIGS. 1 and 2, respectively. Example Conduit Making Machine 100d—FIG. 5

In FIG. 5, we see conduit making machine 100d using valley forming reinforcement 155 to reinforce a conduit 158d by wrapping or bonding reinforcement 155 directly on top of bidirectional reinforcement strip 140k. Conduit making machine 100d, comprising wire coiling machine 105, mandrel 120b, three sets of tensioning rollers 150, heater 151c, three heat guards 159 and three sets of roller assemblies 130a for making a finished conduit 158d. Additional rollers and other guiding structures can be used to assist in guiding strips 143a, 140k, and 143a onto mandrel 120b and also assist in motivating them around the mandrel and also assist in insuring a consistent bond between strips 143a-b and mesh 140k. Conduit making machine 100d can also comprise strip guides if desired to help guide strips 143a, 140k, and 143a onto coiled wire 110. Strips 143a, 140k and 143a can be similar to the component strips 143a, 140f, and 143a seen in bonded strip 140g in FIG. 4. Notice that these three strips could be used with conduit making machine 100c in FIG. 4 to wrap the separate strips in the same positioning shown. The three strips bonded here form substantially the same conduit structure as conduit 158c in FIG. 4, minus wear strip 141. The reader should understand from the above description that the physical structure of finished conduit 158d can be substantially indistinguishable from conduit 158c seen in FIG. 4 except that reinforcement 155 is bonded under strip 143b instead of on top (wear strip 141 not considered). This is because strips

143a, 140k, and 143a are wrapped substantially in the same positions within conduit 158c as they are within conduit 158d by conduit making machines 100c and 100d, respectfully. Tensioning rollers 150, heat guards 159 and roller assemblies 130a have the same structure as in other examples presented here and provide similar functions. The tension on rollers 150 can be adjusted to a lower tension since strips 143a-b and 140k will generally be thinner than strip 140 for similar size conduits from other examples and will be easier to differentially stretch. Also the bonding zone can easily be moved to between the coils, with the use of different rollers (see roller 180 and 180a in FIG. 2).

In the process seen in both FIG. 4 and FIG. 5, the conduits produced have its layers (strip materials) bonded at the ridge at wire 110. In FIG. 4, valley reinforcement 155 is wrapped on top of strip material 143b providing a layer of polymer 143 between reinforcement 155 and bidirectional reinforcement strip 140f. This arrangement reduces wear between the fibers within reinforcement cord 155 and cords 142 and 144. In FIG. 5, valley reinforcement 155 is wrapped on top of bidirectional reinforcement 140k so that cord 155 lies almost directly on cords 142 and 144. This arrangement reduces the elastomer material between cords 142 and 144, and cord 155, making them act more as a single unit once strip 143b is bonded over and between them. In FIG. 5, strip 143b is wrapped on conduit 158d after valley forming reinforcement cord 155 is wrapped on and forms the desired valley. As such, strip 143b must wrap on and be formed close to the desired v-shaped valley without the aid of cord 155. Additional rollers like rollers 180 and 180a can be used to help form strip 143b into the valley formed by cord 155 and bond strip 143b through the reinforcements to strip 143a.

In FIG. 5A, we see a portion of an alternative non-woven reinforcing strip material 140k comprising fiber cords 142 and 144 and a thin layer of bonding matrix material 143c coating them and bonding them together. Material 143c can comprise the same materials that 143 is made of, or can be an adhesive, or be another polymer that can bond to both cords 142 onto 144, as well as, bond to strips 143a and 143b. Bonding matrix 143c can completely cover cords 142 and 144 as shown in FIG. 5A, or can be rolled on so that it exists mostly at the interface between cords 142 and 144. Non-woven strip 140k can substituted for woven mesh 140f in FIG. 4, with minor effect on the finished product. Matrix material 143c can be chosen to soften when heated by conduit making machine 100d, but not melt. In this way, strip reinforcement 140k can remain a structural mesh when heated and still easily differentially stretch. Matrix material 143c can also be used as an interface material to bond dissimilar cords within matrix material 143 or 143a-b. Thus, if one or both cords 142 and 144 can not be directly bond to matrix material 143 or 143a-b, coating them with matrix material 143c, as seen in reinforcement 140k, could allow them to be bonded. Valley forming reinforcement 155 can also be designed to bond to matrix material 143c to form a strong and stable bidirectional convoluted reinforcement.

The reader should understand that the design examples in FIGS. 1 through 8 can easily be modified to provide additional room for bonding additional layering of material(s) to the conduit. Specifically, a longer mandrel can provide space for additional wear strips and other coverings or other applied layers as desired.

Example Conduit Making Machine 100e—FIG. 6

In FIG. 6, we see conduit making machine 100e for making a bidirectionally reinforce conduit 158e with valley forming cords 142b acting to form a v-shaped valley similar to cord 155. In FIG. 6, conduit making machine 100e, comprises wire

coiling machine 105a, mandrel 120, shaping roller assemblies 130 and 160, heater 151, heat guard 159 and cross extrusion head 310, and circular cord guide 279 for making a finished conduit 158e. Wire coiling machine 105a comprises one or more drive rollers 106 and one or more rollers 108. Mandrel 120 and roller assemblies 130 are the same as those discussed in FIGS. 1 and 3. Roller assembly 160 comprises a support shaft 164, and five roller surfaces 162a-e. Roller surfaces 162a and 162e can rotate with shaft 164 to provide motivation to rotating conduit 158e. Roller surfaces 162b-d can rotate freely with strip material 143d. Because of radius differences at different places in the valley of the hose the roller surfaces can rotate at different speeds. Roller surface 162c would rotate the slowest at the bottom of the valley, roller surfaces 162b and 162d would rotate slightly faster, and roller surfaces 162a and 162e would rotate the fastest. In alternate designs, all or some of the roller surfaces 162a-e can be powered or free to rotate. Additional rollers similar to roller assemblies 130 and 160 can be used to achieve the desired bonding pressure and time for strip 143d to bond to strip 143a to bond to one another. Notice that cords 142 help cords 142b to force strip 143a into a v-shaped valley and also hold the side walls of that v-shape better under pressure than without radial cords 142. As in other hose making processes within this document, strip 143a can be pre-made as shown here or extruded directly onto coated coiled wire 111. If directly extruded, strip 143a would not need heater 151 since it would already be in a heated deformable state from the extruder. Elastomer strips like strip 143a are commonly extruded in the hose industry (see strip 143e in FIG. 8) and also allows continuous operation.

In FIG. 6, crosshead extrusion nozzle (or die) 310 comprises a crosshead extrusion die, customized for this particular application. Extrusion die 310 can comprise an inlet port 314 for mounting to a polymer extruder (not shown), and a plurality of yarn ports 312 for accepting cords 142 and 142b into the extrusion nozzle. Nozzle 310 is designed to extrude reinforced strip 143d and encapsulate reinforcement cords 142 and 142b within the elastomer entering through port 314 under pressure. Arrow vectors 271 show the relative velocity of each cord 142 and 142b as it is wrapped differentially onto conduit 158e. The velocities of cords 142 and 142b can be controlled by speed controlled feeders (not shown) that are common to the textile industry. The number of cords and their denier of cords 142 and 142b can be adjusted depending on the conduit design. Longitudinal cords 272 and radial cords 142 and 142b can be standard uncoated textile yarn to reduce costs (such as nylon and/or polyester fiber yarn), but other strong fiber cords can be used. Cords 272 can bond to strip 143a, but because the two polymer strips 143a and 143d can bond to each other and surround cords 272, cords 272 do not necessarily need to bond to the polymer matrix in strips 143a and 143d. Alternatively, cords 272 can be coated with a polymer or adhesive before application if desired to facilitate bonding to strips 143a and 143d. Cords 272 are designed to rotate in the same direction 146a as conduit 158e during manufacture, so that cords 272 are wrapped onto the conduit with a strong longitudinal component. By adjusting the rotation speed 146a of cords 272, the angle of cords 272 can be adjusted with respect with longitudinal direction 147. If cords 272 rotate faster than conduit 158e (wire coil 111) then cords 272 will have a right-hand twist on the conduit. If cords 272 rotate slower than conduit 158e, then cords 272 will have a left-handed twist on the conduit. If cords 272 rotate at the same rate as conduit 158e (rotation 146a is the same as rotation 146) then cords 272 will be aligned in the longitudinal direction 147 on conduit 158e. Cords 142 and 142b hold

cords 272 in place because of the geometry (cords 142 and 142b wrapped over cords 272), and also because strip 143a and strip 143d bond and trap the cords within the final convoluted structure. Roller surfaces 162a-e press on strip 143d to assist in pressing and bonding strip 143d to strip 143a beneath it.

In FIGS. 3 and 6, guide rings 278 and 279 can be stationary or rotating depending on the design. Since guide ring 279 is not rotating it is often called a nose ring, if it were rotating with cords 272 it is often called a yarn guide. Guide ring 279 is designed to guide cords 272 in toward conduit 158e for positioning the cords on the conduit. Normally, guide ring 279 will be stationary and cords 272 will slide around the guide ring during operation. Cords 272 can be rotated by standard reinforcement wrapping machine (not shown) which is common in the hose industry. Since guide ring 279 is not rotating it can be attached directly to extruder nozzle 310 if desired or to another support structure. If guide ring 279 were rotating it can be designed to rotate at the same speed as cords 272 and be attached to the same structure that holds the spools of rotating cords 272. Both rotating and non-rotating guide rings are common in the textile reinforcement industry. Example Conduit Making Machine 100f—FIG. 7

In FIG. 7, we see conduit making machine 100f for making a bidirectionally reinforce conduit 158f with cords 142 and 144 acting as bidirectional reinforcement and cord 155 providing valley forming reinforcement. In FIG. 7, conduit making machine 100f, comprising a mandrel 120c, and one removable end connector 190, and a wrapping system comprising tensioning rollers 150a and 150b, a bonding heater 151, two bonding heaters 151a, and a bonding heater 151c. Additional tensioning rollers and heaters similar to those seen in previous presented conduit making machines can be used as needed. The wrapping process can be similar to prior art mandrel wrapping systems where a platform moves up and back along the rotating mandrel as strip materials are wrapped on the mandrel.

In FIG. 7, the mandrel system comprises hose forming mandrel 120c and removable connector 190. Mandrel 120c comprises a rod with convoluted valley 124a, a convoluted ridge 125, a mandrel end 127 and a connector post 128. The shape of mandrel 120c is designed to form the interior shape of conduit 158f. A groove at ridge 125 allows the wire to be held there during the production process. Connector end 190 comprise a support mount 192 for connecting to a rotary support and connector socket 194 for attachment to mandrel connector end 128. The exterior of connector 190 is sized to produce the desired hose end size so that a standard connector end can be mounted on the end of the hose. The exterior of mandrel end 127 is sized to produce the desired hose end interior size and also to provide a large enough diameter to allow that end of the hose to pass over ridges 125 during removal of the hose from mandrel 120c. For most production hoses and conduits, mandrel end 127 and the exterior of connector end 190 will have the same outside diameter, but nothing prevents their diameters from being different. Connector end 190 is designed so that socket 194 slides over connector end 128 and can be designed to allow rotational torque to be imparted to mandrel 120c or designed to simply allow mandrel 120c to rotate. Socket 194 and connector 128 can have a non-round shape to provide this torque transfer during manufacture.

In FIG. 7, tensioning rollers 150a and 150b, bonding heaters 151, 151a and 151c, and wrapping materials 140, 141 and 155 can be mounted on a movable platform (not shown) which is designed to move along mandrel 120c at the correct speed to wrap the materials on mandrel 120c correctly. Many

configuration for such a movable platform are possible. Materials **140**, **141** and **155** can be spool mounted (not shown) where the spools can be mounted on the movable platform (not shown) along with rollers **150a** and **150b**, and heaters **151**, **151a** and **151c**. Additional guides and forming rollers can be used to shape the conduit as it is wrapped on mandrel **120c** and connector **190**. Rollers **150a** are designed to tension valley forming cord **155** and wear strip **141** to the correct tension, and heaters **151a** is designed to heat cord **155** and wear strip **141** to the correct temperature to bond to bidirectionally reinforced hose body **200** (adhesives can be used in place of heat bonding). Strip **140e** can be wrapped multiple times over the ends of conduit **158f** to form cuffs at both ends over the wire coils there. These cuffs can have several layers to provide a strong exterior for attachment of various hose connectors. In this example, valley forming cord **155**, wear strip **141**, and reinforced strip material **140** are all wrapped on at the same time, but are staggered to allow individual layers. With the wrapping platform moving from right to left in FIG. 7, strip material **140** goes on first, followed by valley reinforcement **155** and finally by wear strip **141**. Note that wear strip **141** and reinforcement **155** do not overlap so their order does not effect the hose structure. However, if additional layering is desired the wrapping platform can make more than one pass to form the hose. This type of hose wrapping system can make multiple passes along mandrel **120c** to produce nearly any hose with as many layers wrapped at different speeds and angles as desired. The shown hose **158f**, in FIG. 7, with valley reinforcement **155**, is only one possible example.

Using alternate materials and methods in FIG. 7, strip **140e** can be replaced by a polymer strip similar to strips **143a-b**, and **143e** to form the inner waterproof hose body. After the hose body is formed several reinforcement cords like cords **142**, **144** or **155** can be wrapped on the conduit from left to right and then from right to left to form a bidirectional reinforcement around conduit **158f**. This wrapping of reinforcement cords can be wrapped at predetermined angles by adjusting the rotation rate **129** of mandrel **120c** and/or the relative rate of linear motion of the wrapping equipment with respect to mandrel **120c**. The reinforcement can then be covered by an additional outer layer of polymer (not shown) and wear strip **141**. In alternate configurations the wrapping equipment (**150a**, **150b**, **151**, **151a**, and **151c**) and spools of strips **140**, **141**, and **155** can be stationary while mandrel **120c** and connector end **190** are moved pass the wrapping equipment to form the helical hose as shown.

#### Example Conduit Making Machine **100g**—FIG. 8

In FIG. 8, we see conduit making machine **100g** designed to make a bidirectionally reinforce conduit **158g**. Cords **252** and **254** are used to provide the bidirectional reinforcement and cord **155** providing valley forming reinforcement. In FIG. 7, conduit making machine **100g**, comprises a wire coiling machine **105a**, an air mandrel **120d**, an extruder nozzle **340**, a roller assembly **130**, wrapping machines **250a-b**, forming roller **160** and tensioning roller **150a**. Additional bonding and shaping rollers can be used as needed. Coiling machine **105a**, roller assembly **130**, and roller assembly **160** are the same as discussed previously. Air mandrel **120d** comprises a compressed air port **71**, an air channel **73**, a plurality of ridge air holes **77**, a plurality of valley air holes **79**, and a wire guide notch **125**. Compressed air line **61** is connected to connector **64** which is screwed into air port **71** to supply compressed air to air channel **73**. Compressed air within channel **73** escapes under pressure through air holes **77** and **79** to support conduit **158g** during manufacturing.

In FIG. 8, wire coiling machine **105a** bends wire **111** so that the wire rotates along helical wire guide notch **125** with

air holes **77** providing an air cushion under the wire to reduce friction. Air holes **79** provide compressed air to the underside of strip **143e** to provide a support air cushion while strip **143e** rotates around mandrel **120d**. A higher density of air holes **77** and **79** can be placed where rollers like roller assemblies **130** and **160** are placed to prevent friction between the interior of the rotating hose and mandrel **120d**.

Wrapping machines **250a** and **250b** can be standard hose wrapping equipment. In FIG. 8, only the nose rings **259a-b** of wrapping machines **250a-b** are shown. Wrapping machines can be purchased with two counter-rotating wrapping systems to wrap a hose in both directions at the same time. Knitting Machine Corporation of America in Cleveland Ohio makes a dual deck hose wrapping machine model KM-89-SS which wraps a hose with counter rotating yarn (cords). The model KM-89-SS can be modified to rotate both wrapping decks in the same direction so that it can be used as wrapping machines **250a** and **250b** to feed in cords **252** and **254**, to nose rings **259a** and **259b** along lines **253** and **255**, respectfully. Double direction wrapping machines are well known in the hose industry and can easily be modified to rotate the two decks in the same direction for use with the disclosed conduit making machine **100g**. Thus, with minor adjustments modern wrapping machines (spiral wrap machines) can be easily modified to rotate both decks in the same direction as wire coil **111** to provide the reinforcement wrapping function for cords **252** and **254**.

In FIG. 8, cords **252** are rotated by wrapping machine **250a** at a speed shown by arrow **256a** which is significantly faster than the rotation rate of wire coil **111** around the mandrel (see speed arrow **146**). This difference in rotational speeds puts a right-handed spiral on cords **252** around conduit **158g**. Similarly, cords **254** are rotated by wrapping machine **250b** at a speed shown by arrow **256b** which is significantly slower than the rotation rate of wire coil **111** around the mandrel. This difference in rotation rate puts a left-handed spiral on cords **254** around conduit **158g**. The rotation rates **256a** and **256b** are chosen to provide the desired right-handed and left-handed spiral angle for cords **252** and **254**, respectfully. In some designs it can be desirable for cords **252** and **254** to follow the convoluted v-shaped valley on mandrel **120d** by themselves (valley reinforcement **155** not needed). To do this the rotation rates of cords **252** and **254** relative to the rotation rate of conduit **158g** must be great enough to allow cords **252** and **254** to drop into the valleys between coils. If cords **252** rotate at the same rate as conduit **158g** cords **252** only touch the ridge peaks, but as this rotation rate is increased, cords **252** begin to wrap further and further into the valley between coil ridges. At a particular rotational speed difference between cords **252** and conduit **158g**, that depends on many factors, cords **252** will wrap onto conduit **158g** just right to touch the bottom of the valley. Additional increasing of rotation speed **256a** causes cords **252** to wrap more strongly in the valley. Similarly, if cords **254** rotate at the same rate as conduit **158g** cords **254** only touch the ridge peaks, but as this rate is slowed, cords **254** begin to drop down into the valley more and more as its rotation speed is decreased. At a particular speed, that depends on many factors, cords **254** will wrap onto conduit **158g** and just touch the bottom of the valley. Additional slowing of rotation speed **256b** causes cords **254** to wrap more strongly in the valley. Thus, cords **252** and **254** can be wrapped onto conduit **158g** as needed by choosing the rotational speeds of conduit **158g**, cords **252** and cords **254**.

In one example of rotational speed selection, it can be desirable for conduit making machine **100g**, in FIG. 8, to be adjusted to provide a mostly longitudinal cord reinforcement and a mostly radial cord reinforcement. The radial cord sup-

port can easily be provided by cords **252** being wrapped onto conduit **158g**, where the rotational speed (rotation **256a**) of cords **252** is approximately ten to fifteen percent faster than the rotation rate (rotation **146**) of conduit **158g** so that cords **252** lay generally in the longitudinal direction, but still has a strong right-handed twist that can counter the forces of coiled wire **111** that tend to cause twisting of conduit **158g** when it is pressurized. At this twist rate, cords **252** would still tend to wrap onto conduit **158g** from ridge peak to ridge peak. Cords **254** are wrapped on next and would be given a strong radial component to pull cords **252** down into the valley. Cords **254** might be given a rotation speed (rotation **256b**) that is twenty to seventy percent slower than the rotation speed (rotation **146**) of conduit **158g** so that cords **254** will wrap strongly into the bottom of the valley. As the rotational speed of cords **254** is reduced toward the lower end of these speeds, cords **254** might require some bonding of cords **254** to cords **252** and/or strip **143e** to prevent the cords from slipping out of position during use.

In FIG. 8, prior art heaters and adhesive applicators can be used to help form conduit **158g** like they are in other examples in this patent. The disclosed bonding methods in this patent and other prior art bonding methods can be used to bond strip **143e**, cords **252**, cords **254**, and/or valley forming cord **155** to each other. Roller assembly **160** can also be heated to help bond cords **252** and **254** and strip **143e** together. The high-temperature nature of extruded strip **143e** also tends to help bond these hose components together. In alternate examples, cords **252** and **254** can be coated with an adhesive or polymer so that these cords can bond strongly to each other where the cross, forming a bonded mesh that will hold its shape.

In FIG. 8, after cords **252** and **254** are positioned, valley forming cord **155** is guided and wrapped in the valley of conduit **158g**. This insures that cords **252** and **254**, and strip **143e** maintain the v-shaped valley during and after use. Tensioning rollers **150a** provide the proper tension or feed rate to cord **155** to produce the desired valley shape. Roller assembly **160** presses all these components together and bonds them into a finished conduit **158g**. Finally, additional polymer layers can be extruded over reinforcement cords **252** and **254** if mandrel **120d** is made longer and additional polymer extruders are added.

In FIG. 9, we see one possible example of for wrapping machines **250a** and **250b**. The KM-89-SS-HS (KM-89) dual wrapping machine can easily be modified to provide both wrappings by cords **252** and **254**. Two decks provide the support for cord spools **257** and **258**, for cords **252** and **254**, respectfully. The KM-89 can be modified to allow each deck of spools **257** and spools **258** rotate in the same direction and their speed controlled. This way the KM-89 can supply both sets of rotating cords **252** and **254** to nose rings **259a** and **259b**, respectfully.

#### OPERATION OF THE DISCLOSED CONDUIT MAKING MACHINES

##### Operation of Valley Reinforcement Cord **155**

Valley forming cord(s) **155** is wrapped near the bottom of the valley of a convoluted hose as shown in most of the examples presented here. Cord(s) **155** work when wrapped with any bidirectional reinforcement. Cord(s) **155** should be wrapped over any cords that are longitudinally oriented and wrapped around the convoluted hose in the same direction as the wire coil. Generally cord **155** can be bonded to the body of the hose by adhesives or thermal polymers. Valley forming and reinforcing cord(s) **155** provides a stabilizing effect on the bidirectional reinforcement within the hoses disclosed in

this document. Reinforcement cord(s) **155** can preferably be wrapped into the valley of a convoluted stretch hose over any bidirectional reinforcement. The tension in cord(s) **155** pulls other reinforcement down into the valley and prevents pressure within the hose from significantly forcing the valley portion outward radially. It also causes the side walls of the valley to form a somewhat v-shape with the walls substantially straight when not pressurized. When pressurized valley forming cord(s) **155** works with any bidirectional reinforcement to resist radial pressure within the hose. By maintaining the convoluted shape, cord(s) **155** assist in maintaining the proper shape of the hose during use so that it can easily retract and folding properly without binding during the retraction process. Valley reinforcement cords **270d** and **142b** can function essentially the same way as cord(s) **155**.

Operation of Differentially Stretchable Bidirectionally Reinforced Strips **140**, **140c**, **140f** and **140k**

Bidirectionally reinforced strips **140**, **140c**, **140e**, **140f**, **140j**, **140h** and **140k** each have diagonal cords **142** and **144** to provide a bidirectional reinforcement. Within strips **140**, **140c**, **140e**, **140f**, **140j**, **140h** and **140k** cords **142** and **144** can be locked together in either a woven structure (strip **140**), layered structure (strip **140c**) or a bonded joint structure (strip **140k**). Strips **140f**, **140j**, and **140h** can have any one of these structures. Cords **142** and **144** are angled in opposite directions at angles **148a** and **148b** from the strips' longitudinal axis **145**, respectfully (see FIG. 1). Having the cords woven in strip **140** at a diagonal angle allows longitudinal stretching because the longitudinal component of cords **142** and **144** can increase as the cords are angled more closely to the longitudinal direction **145**. Having the cords in strips **140f** and **140k** bonded together at their intersection (mesh design) allows cords **142** and **144** to angle more closely to direction **145** when stretched, especially when heated to allow the bonded joint to deform. Also note that there are many knitted mesh designs that can be used here as a replacement for strips **140f** and **140k**. Differential stretching is made possible in all three structures because the reinforcing cords are angled diagonally with respect to the longitudinal axis of the strip. If some of the cords were aligned with the longitudinal direction (**145**), the strip would not be able to stretch significantly at that point, because these cords would not allow it to stretch. For best operation, the angles **148a** and **148b** between the cords and the longitudinal direction **145** should be greater than thirty degrees, but less than eighty degrees before being stretched. The larger this cord angles is from the longitudinal, the greater percentage the longitudinal stretch that it can provide. Thus for conduits where the valley and ridge are nearly the same diameter, smaller cord angles near thirty degrees can be used and still produce the desired convoluted helical conduit. For designs where the valley radius is less than sixty-five percent the size of the ridge radius, angles greater than forty-five degrees give better results. The angle of cords **142** and **144** within the final hoses are substantially locked into position after cooling by the stiffness of matrix **143**.

Operation of Differentially Stretchable Bidirectionally Reinforced Strips **140a**, **140b** and **140d**

Bidirectional knit reinforced strips **140a**, **140b** and **140d** use one or more cords of cord(s) **142** to knit a bidirectionally reinforced fabric layer in a elastomer matrix **143**. Knitted fabrics **142a**, **142b** and **142d** are stretchable by the nature of knit structures, and can in general stretch in all directions. However, each knitted fabric **142a**, **142b** and **142d** is designed with a longitudinal portion that stretches much less than other portions of the knit. These low stretch areas acts as a valley forming reinforcement for the purposes of making

reinforced stretch hoses. In strip **140a**, longitudinal cords **142b** provide a very low stretch region along the center of strip **140a**. When strip **140a** is wrapped on a mandrel to form a hose conduit, with machines like those seen in FIGS. 1 through 8, cords **142b** can be pulled tight in the valley to prevent stretching there. At the same time the remainder of knitted fabric **142a** can stretch over the wire ridge to form a convoluted hose. Thus cords **142b** behave much like the valley reinforcement cords **155** and **270d** seen in other examples within this document.

In FIGS. 1E and 2C, strips **140b** and **140d**, incorporate valley forming reinforcement in the form of a special low stretch knitted portions **142d** and **142f**, respectfully. Note that the stretch of portions **142d** and **142f** can be further reduce by adding cords like **142b** seen in FIG. 1D to these longitudinal portions. Without this reduced stretch of reinforcement portions **142d** and **142f**, a typical knit like **142c** and **142e** would tend to stretch too much. Thus, portions **142d** and **142f** can be designed to stretch much less than the other portions of the knit reinforced strips **140b** and **140d**, respectfully. For example, when strip **140b** is heated and stretched onto a mandrel, portion **142d** might stretch twenty percent in the longitudinal direction **145**, while the other portions of knit **142c** might stretch sixty percent in the longitudinal direction. This difference between the twenty percent and sixty percent stretch would give an overall differential stretch of approximately forty percent for the strip material. Both the valley and the ridge reinforcement can be taught and able to support internal pressure. Thus, a properly designed knitted strip can shape itself into the convoluted shape of a stretch hose while at the same time providing a low-stretch valley reinforcement portion. Knitted portion **142d** in FIG. 1E can provide substantially the valley forming reinforcement properties as cords **142b** seen in FIG. 1D, with portion **142d** wrapped into the valley of the hose during manufacture. Knitted portions **142f** in FIG. 2C also provide the valley forming reinforcement properties similar to knitted portion **142d** seen in FIG. 1E. However, portions **142f** of strip **140d** are placed on each side of the strip and portions **142f** are pulled down into the valley and bonded together there. Thus, strip **140b** are designed to form the seam at the coiled wire ridge, and strip **140d** is designed to form the bond seam in the valley between the wire coils. Because typical knitted material can stretch in all directions it can be useful to use additional valley forming reinforcement, such as, cords **155**, **142b** and **270d** to maintain the shape of the knitted fabrics, especially when the conduit is used in a high temperature environments (temperatures that soften matrix materials **143**, **143a-d** and allow cords **142** and **144** to shift).

Operation of Differentially Stretchable Cross-Layered Reinforced Strip **140c**

In FIGS. 2, 2A and 2B, we see reinforced strip **140c** which comprises two separate fiber cords layers comprising cords **142** in one layer and cords **144** in the other layer. Both layers are bonded within matrix **143** near the mid-thickness of strip **140c**. The cords **142** and **144** are angled diagonally across the strip it opposite directions so that the cords reinforce strip **140c** along two dimensions, thus each providing a portion of both longitudinal and radial reinforcement. During production, strip **140c** is heated by heater **151** until it is deformable. Strip **140c** is then pulled by rotating wire **110** at the transverse location **154** of coiled wire **110** which causes strip **140c** to stretch differentially. As strip **140c** stretches longitudinally, fiber cords **142** and **144** will tend to orient toward the longitudinal direction **145** in those zones where the strip is stretched significantly. In zones of low or no stretching (zone **154** in FIG. 1, and zones **152a-b** in FIG. 2), fiber cords **142**

and **144** will tend to remain at their original angle. Also, if the cords are not woven, the natural limitation in stretch does not exist. Thus, strip **140c** can be stretched until fiber cords **142** and **144** delaminate from each other. Care must be taken to prevent over stretching of non-woven strips like strips **140c** when heated to its plastic state. Because strips with layers of fiber or cords can stretch no matter what the angle of the cords are, the user can choose angles that specifically meet their needs. After strip **140c** is stretched into a somewhat u-shaped cross-section, valley forming reinforcement cord **155** is wrapped at the bottom of the valley (on seam **157**) to increase the depth of the valley and force a more v-shape cross-section in the valley of the hose body. Rollers **150a** and heater **151a** provide the correct tension and temperature, respectfully, to create the correct v-shaped structure and bond cord **155** to strip **140c**.

Operation of Differentially Stretchable Multi-Layered Reinforced Strips **140g**, **140i**, and **140h**

In FIGS. 4, 4A and 4B, we see multi-layered reinforced strips **140g**, **140i** and **140h** which comprises strip material with bidirectional reinforcement cords **142** and **144** in a double wide strip (strip **140h**) and triple wide strip (strip **140g** and **140i**). Because the width of strips **140g**, **140i** and **140h** is wider than the distance between two coils (2 coil pitches), these strips will wrap around the conduit and create a hose is more than one layer thick. Strip **140g** and **140i** seen in FIGS. 4 and 4A, respectfully, are composite strips and comprise three separate strips bonded together to form a wide format strip. Each of these separate strips **143a**, **140f**, **140j** and **143b** are differentially stretchable when heated. Strips **143a** and **143b** have no reinforcement and are used to provide an inner and outer sealing layer when wrapped on a mandrel. Bidirectional reinforcement layers **140f** and **140j** are also differentially stretchable because of the diagonal orientation of cords **142** and **144** that is similar to strip material **140**. Strip **143b** is last to go on and cord **155** compresses all the layers to provide a v-shaped valley to finished conduit **158c**.

In FIG. 4B, we see a section view of strip material **140h**, which can be used in conduit making machines **100a-g**. In use with conduit making machine **100c**, strip **140h** would be fed into rollers **150c** in the same position as strips **143a** and **140f** seen in FIG. 4. After strip **140h** is heated by heater **151b**, it would be stretched over coiled wire **110**. Heat shield **159c** and right most heat shield **159** can reduce heating of the two transverse portions of strip **140h** corresponding to the valley portion **124a** of mandrel **120b** so that these portions will not significantly stretch. Rollers **132** would then press and bond strip **140h** to itself as strip **140h** would wrap over itself twice. Strip **140h** because of its double width will follow wire coil **110** and wrap twice over itself forming a double layer between the coils and a triple layer at the ridge of coiled wire **110**.

Operation of Conduit Making Machine **100**—FIG. 1

In FIG. 1, we see an example of a continuous conduit making machine **100**. Spring bending machine **105** comprises a standard spring coiling machine with drive rollers **106** (only one roller shown for drawing clarity). Drive rollers **106** are used to feed wire **110** under force into wire bending tool **107**. Bending tool **107** is often called a point tool because the wire contacts it at substantially a single point to cause it to bend. This point contact causes the wire to bend into a radius determined by how far the point tool is from the wire feeder guide, and at what angle it is oriented, and the type of wire being bent. Mandrel **120** is securely fastened to bending machine **105** or to another mechanical support structure fixed in position relative to bending machine **105**. Mandrel **120** is positioned so that as wire **110** loops around the mandrel after

it is bent. Tool 107 and spring bending machine 105 are adjusted to give wire 110 a pre-bias that tends to retract the coiled wire 110. Thus, wire 110 is formed into a tension spring. After wire 110 proceeds off the wire coiling machine's bending tool 107 it encounters wire guide 122 that slowly mechanically stretches the now coiled spring wire 110 as it rotates around the mandrel. Wire guide 122 extend the spring to the desired coil pitch before entering wire groove 122a. Notice that as the wire nears the area where strip 140 is laid onto coiled wire 110, the wire guides take on the form of a groove 122a that circles mandrel 120 along a spiral path. Coiled wire 110 rests in groove 122a with the groove edges aligning with wire 110 to provide a somewhat continuous surface. This is to allow wire 110 and mandrel 120 to combine to form the desired shape for the interior surface of strip 140 as it is formed into a final conduit or hose 158. In this way, the shape of the wire and the mandrel help determine the final shape of the finished conduit 158.

While wire 140 proceeds to revolve around mandrel 120 to the right, reinforced polymer strip 140 is pulled in toward mandrel 120 through a pair of tensioning rollers 150. After passing through rollers 150, heater 151 radiantly heats strip 140 to near the melting point of matrix 143 within strip 140. During heating, heat guard 159 reflects heat from the center portion of strip 140 preventing a small transverse portion of strip 140 from reaching a temperature that would allow easy deformation of matrix 143 within strip 140. Strip 140 is guided into position relative to rotating wire coils 110. Wire coils 110 are rotating at a linear speed significantly faster than the linear speed of strip 140 moving through tensioning rollers 150. This means that polymer strip 140 must stretch in order to continuously wrap onto wire 110. The center of strip 140 (center transverse portion 154) has not reached a temperature sufficiently high to become easily deformable so it stretches much less and forms the smaller radius portion of the conduit, which follows valley portion 124 of mandrel 120. Portions 152a and 152b of strip 140 are stretched significantly by the pull of wire 110 and rollers 132 and 134 on roller assembly 130. The actual stretching takes place before strip 140 actually wraps onto wire 110, since wire 110 and rollers 132 & 134 do not allow strip 140 to stretch significantly after contact. Friction from wire 110 and rollers 132 & 134 must be sufficient to provide the needed force to stretch strip 140 without it slipping off of coiled wire 110. During the stretching of strip 140 from heater 151 to rollers 132 and 134, the width of strip 140 narrows slightly as diagonal reinforcing fibers cords 142 and 144 are shifted to a slightly more longitudinal angle. Providing larger values for angles 148a-b will reduce the amount of shrinkage in the transverse direction because of the geometry of fiber cords 142 and 144. The needed width of strip 140 is also effected by the depth the strip indentation at valley 124. The deeper the indentation the more strip material 140 is needed to bridge the gap between adjacent coils of wire 110. This is because fiber cords 142 and 144 have a higher melting temperature than matrix 143 and do not lengthen or shorten significantly during this heating and stretching process. This means that shaping strip 140 into the u-shape valley 124 requires strip 140 to be significantly wider than the pitch between coils of wire 110. For example, if the spacing (pitch) between wire coils 110 is 0.65 inches where strip 140 is wrapped onto wire 110, and a 0.20 inch overlap is needed on each side, and the u-shaped indentation requires thirty-five percent additional width to form that shape, then 0.90 inches of material will be needed to go between wire coils plus 0.10 inches overlap on each side, for a total strip width of 1.10 inches. The final v-shaped valley is formed when valley forming cord 155 is wrapped in the valley and

pulls cords 142 and 144 tight within strip 140. This tightening of cords 142 and 144 tend to straighten the walls of the valley and form the desired v-shaped cross-section for the valley. Wrapping of cord 155 in the valley also shifts cords 142 and 144 in toward the valley slightly. Thus, sufficient overlap at seam 156 should be provided to allow for this shifting of the cords.

After strip 140 has been wrapped onto wire 110, rollers 132 and 134 motivate strip 140 around mandrel 120 until it makes one complete revolution. At that point the left edge of strip 140 meets the right edge of itself being wrapped onto wire 110. Thus the right edge of incoming strip 140 is laid on top of the left edge of strip 140 that has traveled one revolution around mandrel 120. Because strip 140 is hot and partially melted, strip 140 sticks to itself forming a bond. Roller 132 at the same time applies pressure to this overlap portion of strip 140 to force the soft polymer matrix 143 of the strip together and permanently fuse strip 140 to itself. In this way a continuous conduit of reinforce polymer is formed over coiled wire 110 which has a convoluted helical shape. Roller assembly 130a provides shaping and pressing of bond zone 156 a second and third time to insure complete water tight fusing of strip 140 to itself. Valley forming reinforcement cord 155 is tensioned by rollers 150a and heated to a tacky state by heater 151a. Cord 155 is then wrapped onto the hose near the center of the valley and tension in the cord pulls the bottom of the valley to the desired radius. This action also tends to straighten the walls of the valley to form a somewhat v-shaped cross-section to the valley. The still tacky cord 155 bonds to strip 140 to permanently hold cord 155 in place.

After this the finish conduit 158 rotates off mandrel 120 to the left (direction 147, see FIG. 1). Pullers can keep conduit 158 extended while it cools and then allow coiled spring wire 110 to retract the hose into its full retracted position for further cooling. Care must be taken to allow sufficient cooling before retracting the hose. Note that coiled wire 110 will cause conduit 158 to retract fully unless other forces keep it extended (either groove 122a or a puller beyond the right end of mandrel 120). This is because when the conduit is retracted, the outside of strip 140 is forced together by spring wire 110, which can cause the outside of strip 140 to bond to itself if it is too hot. Thus, proper cooling of conduits 158a-g is important because the conduits need to cool before conduit body retracts against itself (see section 170 in FIG. 2) to prevent bonding the exterior portions of the hose.

In FIG. 1D, we see a top view of warp knitted reinforced strip material 140a designed for use with conduit making machines like 100, 100a, 100b, 100c, 100d, 100e, 100f or 100g seen in FIGS. 1 through 8, respectfully. As an example, when strip 140a is used with conduit making machine 100, knitted section 142a is stretched and can easily differentially stretch to form a convoluted structure. As strip 140a is heated by heater 151, matrix material 143 softens and the strip can be stretched over the wire coils. However, because valley forming cords 142b are knitted longitudinally into strip 140a, tension on rollers 151 causes the center portion of strip 140a to be pulled into the valley and form the desired shape for valley between the wire coils. When using strip 140a with conduit making machine 100, heat guard 159 can be optional since cords 142b will not stretch significantly even when heated because they are oriented in longitudinal direction 145. Thus, even if matrix 143 softens, cords 142b can prevent the center portion of strip 140a from stretching.

In FIG. 1E, we see a top view of warp knitted reinforced strip material 140b designed for use with conduit making machines like 100, 100a, 100b, 100c, 100d, 100e, 100f or 100g seen in FIGS. 1 through 8, respectfully. As an example,

when strip 140b is used with conduit making machine 100, knitted section 142d is much less stretchable than the other portions of knitted fabric 142c. As strip 140b is heated by heater 151, matrix material 143 softens and the strip can be stretched over the wire coils. However, because section 142d has a knitted structure that limits its longitudinal stretch, tension on rollers 150 causes the center portion of strip 140b to be pulled to the valley and form the desired shape for the valley between the wire coils. When using strip 140b with conduit making machine 100, heat guard 159 is not needed since section 142d will generally not stretch significantly more even when heated because the knit there cannot stretch as much as the rest of fabric 142c. Thus, even if matrix 143 softens, section 142d can prevent the center portion of strip 140b from stretching excessively.

In FIG. 2C, alternate knitted reinforced strip material 140d is designed specifically for use with conduit making machines 100a seen in FIG. 2, but could be used with any conduit making machine within this document with slight modification. Strip 140d differs from the other strips disclosed in this document in that strip 140d is designed so the center of the strip lands on the coil ridge and the low-stretch knitted edges 142f are bonded in the valley. During production strip 140d is centered on coiled wire 110 and stretched on to wire 110. The center portion of strip 140d stretches while the edge sections 142f resist stretching because of they way fabric 142e is knitted there. Heating of strip 140d by heater 151 allows matrix polymer 143 to soften and fabric 142e to stretch. Sections 142f have limited stretch so that tensioning rollers 150 can pull strip 140d down into the valley on each side of the wire coil and form the proper valley shape. With low stretch sections 142f, the need for cord 155 becomes optional, since sections 142f acting as the valley forming reinforcement and maintains the depth of the valley.

Operation of Conduit Making Machine 100a—FIGS. 2 Through 2C

In FIG. 2 we see conduit making machine 100a using mandrel 120a to produce convoluted hose. Conduit making machine 100a operates quite differently than conduit making machines 100, but can produce substantially the same hose from the same materials, and can be substituted for mandrels 120 and 120b shown within this document with only minor modifications. Conduit making machine 100a comprises four rotating rods 122a through 122d which are used to assist in rotating wire 110 and provide a moving surface to compress and bond the seam 157. Wire 110 can be coiled slightly differently than in FIG. 1 because the rotating rods 122a-d can assist in bending the wire around the mandrel. In this example, and strip 140c is fed through rollers 150 and heated by heater 151. Each side of strip 140c is limited from stretching by heat guards 159a and 159b. However portions 152a and 152b must be heated to allow bonding at bond zone 157. Roller assembly 180 can also help reduce the pull on edge portions 152a-b by forcing the desired shape and to limit the amount of stretching that occurs. After strip 140c makes on loop around mandrel 120a, roller surface 184 then presses the two edges of strip 140c together against the rotating rod 122c on the interior of the hose and fuses matrix material 143 within the edges of strip 140c together. Additional rollers and guides can further shape and bond the conduit before it exits mandrel 120a to the right (direction 147). As finished conduit 158a rotates off of mandrel 120a, coiled wire 110 is no longer supported by mandrel 120a. This causes conduit 158a to retract to its natural state 170 which is the fully retracted position for conduit 158a. Additional mandrel length can be used to keep conduit 158a stretched while cooling it, or rotating pullers common to the industry can keep conduit

158a stretched after exiting mandrel 120a. Both of these methods can be used to set the shape of strip 140c in an extended convoluted shape. Note that strips 140, 140a-b, and 140f-h in many instances can be used in place of strip 140c.

In FIG. 2C we see knit reinforce strip 140d which can be substituted for strip 140c. With this substitution, conduit making machine 100a can optionally use valley forming cord 155 and heat guards 159a and 159b. Strip 140d does not need valley reinforcement 155 because low stretch portions 142f serve this purpose. Also Strip 140d does not need heat guards 159a and 159b because the stretch of knitted portions 142f are not significantly effected by softening matrix material 143 and can be compensated for in the design pattern of portion 142f.

15 Operation of Conduit Making Machine 100b—FIG. 3

FIG. 3 show a conduit making machine 100b is shown providing a v-shaped valley reinforcement where the entire wall of the valley is shaped by multiple radial cords 270a through 270d. By applied to valley reinforcement across the entire surface of the valley, convoluted stretch hose 158b can be assured to maintain its shape even at elevated temperatures. As with the conduit making machine 100 seen in FIG. 1, conduit making machine 100b, starts by coiling spring wire 110 around mandrel 120. After stretching coiled spring 110 to the desired coil pitch, strip 140 is wrapped onto the wire and bonded to itself as previously discussed. After roller 132 presses bond seam 156 to fuse the two edges of strip 140, additional layers and reinforcement can be added. In FIG. 3, this additional reinforcement takes the form of many matrix coated fiber cords 270a-d and 272 (see FIG. 3A), that are heated and then bonded to the exterior of strip 140 after it is in the form of a finished conduit 158b.

In FIG. 3, additional reinforcing cords 270a-d can be bonded over the new conduit made from strip 140. After the conduit is formed by strip 140 and continues to move to the right for application of a second layer of bidirectional reinforcement. Heater 151b can reheat the outside surface of strip 140 and also heats the underside of radial cords 270a-d. Additional heaters may also heat longitudinal cords 272 (if heat bonding is the bonding process). Longitudinal cords 272 can be optional in this example because of the bidirectional reinforcement in strip 140. Cords 272 can be fed off of spools (not shown) through ring-shaped cord guide 278 in the direction 273 toward mandrel 120 while simultaneously rotating around mandrel 120 as shown by arrow 146a. At the same time, seven radial cords 270a-d are fed off of spools (not shown) and directed to tensioning bar 150b and then through cord guide 276. Guides 276 and 278 are drawn in a simplified manner, and are representative of the many types of cord guides that are possible. For example, heated rollers could be used instead of the static guides shown in conduit making machine 100b. Also note that guides 276 and 278 are shown far from mandrel 120 to improve the clarity of the drawing. In an actual system, guides 276 and 278 could be placed very close to the actual bonding area and roller(s) used to press cords 272 and 270a-d, and strip 140 together. Cords 272 and 270a-d can be non-coated yarn made of nylon and/or polyester fibers if additional matrix material or adhesives are used (see FIG. 6). Coating and bonding of the non-coated yarn to hose 158b can comprise adding another layer of strip material similar to strips 140, 140c and 140f over the reinforcement or coating hose 158b with a liquid polymer adhesives which is commercially available, or other methods. The reader should understand here are many alternative combinations of the disclosed technology with present manufacturing processes.

In FIG. 3, as cords 272 get close to strip 140, an optional guide bar 277 helps force cords 272 into close proximity with

strip **140** just prior to wrapping radial cords **270a-d**. In this way, the left most cord **270b** can wrap over cords **272** and force cords **272** against strip **140** for bonding without the left most cord **270b** slipping significantly from its desired bonding location on finished conduit **158b**. Rollers **135a-g** make contact with cords **270a-d** just prior to pressing these cords against strip **140**. Rollers **135a-g** can be offset from each other so that the rightmost cords are pressed against strip **140** before the leftmost cords. Each radial cord **270a-d** is wrapped around conduit **158b** at a different rate to desired radius of that portion of conduit **158b** and thus shape the valley into whatever cross-sectional shape is desired. Rollers can be used to help press and shape cords **170a-d** into strip material strip **140**. After cords **272** are guided onto strip **140** and cords **270a-d** are wrapped over them, the entire conduit rotates around mandrel **120** to be heated again by heater **151b**, where additional rollers can insure these cords are securely bonded to the exterior of strip **140** and to themselves. After cooling, finished conduit **158b** can be allowed to retract back to its natural state.

Operation of Conduit Making Machine **100c**—FIGS. **4**, **4A** and **4B**

In FIG. **4**, we see conduit making machine **100c** which is very similar to conduit making machine **100**, however, strips **140g**, **140i** and **140h** which can be wrapped by machine **100c** are substantially wider than strip **140** used with machine **100**. In FIGS. **4** and **4A**, strips **140g** and **140i** are slightly more than three coils wide so that when wrapped on wire **110** a three layer structure is formed. In FIG. **4B**, strip **140h** is slightly more than two coils wide and thus wraps on in two layers. Thus, these wider strip covers two or three coil lengths at a time. Looking at FIG. **4** as the example, roller assemblies **130** and **130a** help motivate strips **140g** around mandrel **120b** with wire **110**, and helps bond the strip to itself at the ridge formed by coiled wire **110**. Rollers **132** apply force to the edges of strips **143a**, and **143b** to achieve bonding. strip **140g** passes through rollers **150c** their speed is controlled by the speed at which rollers **150c** are turning. Heater **151b** heats strips **143a-b** to their deformation temperature. Heat shields **159** protect the center of strips **143a-b** so that the center portion deform significantly less during stretching. Stretching of the strips is accomplished by the greater linear speed of wire **110** compared with the linear speed of rollers **150c**. Since the center portion of strip **143b** is not heated to its deformation temperature it can apply tension to the center portion of mesh **140f** and push it down into the valley between the coils. Stabilizing polymer reinforcement cord **155** can be applied to reinforcing mesh **140f** to insure that mesh **140f** shapes itself to mandrel **120b** during stretching. However, even without stabilizing reinforcement **155**, strip **143b** will tend to press mesh **140f** into the valley portion of mandrel **120b** forming a v-shaped valley as it is wrapped on top of mesh **140f**. However, this v-shaped valley might not maintain its shape during operation without valley reinforcement **155**, especially at elevated temperatures. After the conduit portion (strip **143a**, **140f** and **143b**) are bonded by heat and pressure by rollers **132**, wear strip **141** can be bonded onto the outer ridge of the conduit through either heat bonding, adhesives, or other bonding methods. Pressure from roller **131** assists in the bonding. Finished conduit **158c** can leave mandrel **120b** and be pulled a short distance while cooling, before the conduit is allowed to relax into its retracted length. This allows conduit **158c** to set in the shape of the extended position of the conduit when pressurized. This is done to provide a smooth even shape for the conduit when pressurized, so there is no high stress points. When conduit **158c** is relaxed and retracted, it might have creases or folds in its reinforced strip materials,

but there is no pressure on the strips in this position and little damage can be done. Additional rollers can be added to insure a good bond between strips **143a** and **143b** through mesh **140f**, for an airtight conduit. Conduit making machine **100c** can similarly be used to wrap and bond strip materials **140i** and **140h** into a similar stretch hose conduit shape.

Operation of Conduit Making Machine **100d**—FIGS. **5** and **5A**

Operation of conduit making machine **100d** is very similar to the other conduit making machines presented here, but has three separate strip feeding systems for wrapping and creating a finished conduit. In this particular example, three separate strips **143a**, **140k** and **143a** are fed through their own tensioning rollers **150**. Each tensioning roller may be adjusted for its particular strip material, but can be essentially identical to each other. Rollers **150** may provide a predetermined linear speed for feeding the three strips each which can be a different speed. Heater **151c** then heats all three strip **143a-b** and **140k** to the deformation temperature or deflection temperature of the material of which strips **143a-b** are composed. The two heat guards **159** protect the center portion of strips **143a-b**. If valley reinforcement **155** is made from a low temperature polymer the center heat shield **159** can protect valley reinforcement **155** so that it can maintain a tension for forming the valley. Reinforcing strip **140k** could be replaced with a reinforced strip like strip **140**, but with just enough polymer matrix **143** to hold the reinforcing cords **142** and **144** in place (see strip **140j** in FIG. **4A**, an optional way to make strip **140k**). Such a coated strip would differentially deform onto mandrel **120b** similar to strip **140**. In FIG. **5**, bonding roller assemblies **130a** are shown for rolling and bonding the ridge portion of conduit **158d**. Additional rollers can be used to bond the strip as needed. The inner layer formed by strip **143a** is bonded to itself and forms a air tight conduit before it reaches the position where reinforcing strip **140k** is wrapped over it. Finally, strip **143b** is stretched over reinforcing strip **140k** and strip **143a** and bonded through mesh **140k** to strip **143a**. After bonding at the ridge an additional wear ridge can be added as shown in other examples (i.e. wear strip **141** in FIG. **4**).

Operation of Conduit Making Machine **100e**—FIG. **6**

In FIG. **6**, conduit making machine **100e** is very similar to conduit making machine **100d** seen in FIG. **3**. The difference is that the radial cords **142** and **142b** are coated by an extruder just prior to being wrapped onto conduit **158e**. This eliminates the need for pre-coating the reinforcement cords and also provides the outer sealing layer at the same time. Cords **142b** provide the valley forming reinforcement, while cords **142** assist in maintaining the v-shaped valley even when pressurized.

In FIG. **6**, the operation of conduit making machine **100e** starts by bending a coiled tension spring with coated wire **111**. As coiled coated wire **111** rotates around mandrel **120** it is stretched to the correct coil pitch by mandrel guides **122** and **126** so that polymer strip **143a** can be stretched over the rotating coiled wire. After roller **132** presses the two edges of strip **143a** together and bonds them a convoluted stretch hose structure is formed. This hose structure continues rotating to the right on mandrel **120** where it reaches a reinforcing section comprising a plurality of longitudinal cords **272**, guide ring **279**, extruder nozzle **310**, and a plurality of cords **142** and **142b**. Longitudinal cords **272** can rotate slightly faster in the direction **146a** than the conduit (wire **111** and coiled strip **143a**) so that cords **272** wrap onto strip **143a** in a right-hand spiral (opposite the left-handed spiral of coiled wire **111**). This right-hand spiral of cords **272** creates an opposing force to the left-hand spiral of coiled wire **111** to resist the natural

tendency for the convoluted hose to rotate along its axis when pressurized. That is, the expansion of coiled wire **111** from internal pressure will tend to cause significant rotation of conduit **158e** along its axis. The opposite spiral of the reinforcement counters the axial rotation caused by the spiraled coiled wire **111**.

As cords **272** rotate, stationary guide ring **279** forces cords **272** in alignment with the surface of the conduit formed by strip **143a**. This way extruded strip **143d** can effectively cover and bond cords **142**, **142b** and **272** to the conduit formed by strip **143a**. Tension within cords **142** and **142b**, inside extruded strip **143d** help pull cords **272** against the conduit formed by strip **143a**. Then cords **142** and **142b** are used to press elastomer **143** in outer layer strip **143d** through reinforcing cords **272** and into inner layer strip **143a**, thus bond all the layers together. Additional rollers can be used to insure desired bonding. Mandrel **120** provides some support for the interior surface of conduit **158e** as it is pressed by cords **142** and **142b**.

Crosshead extruder die **310** extrudes melted elastomer **143** for extrusion at port **314** where the elastomer surrounds cords **142** entering die **310** at openings **312**. Cords **142** are infused with melted elastomer **143** within extrusion die **310** and are encapsulated within extruded strip **143d**. The drawing of extrusion die **310** is only for representation of components and actual crosshead extrusion dies can comprise various designs.

Operation of Conduit Making Mandrel **100f**—FIG. 7

In FIG. 7 we see a conduit making mandrel **100f** which uses a rotating mandrel **120c** to form the desired conduit shape. While the other examples of conduit making machines in this document show continuous conduit making processes, FIG. 7 shows a process that is designed to build one conduit **158f** on mandrel **120c** at a time. During production of hose **158f**, mandrel **120c** and connector end **190** are rotated in direction **129** while various layers of strip materials are wrapped and bonded around mandrel **120c**. Many different combinations of layering is possible, two examples will be discussed here. First, the arrangement in FIG. 7 will be discussed where a single pass wrapping process is used. Second, we will consider a multi-pass wrapping process with continuous bidirectional reinforcement.

In FIG. 7 we see one example of how conduit **158f** can be layered on mandrel **120c** and connector **190** using strip material similar to strip **140**. After wire **111** is coiled onto mandrel **120c**, a strip similar to strip material **140** can be wrapped over wire **111** from right to left on rotating mandrel **120c** and bonded at its seam similar to other conduits seen in this document. Following behind the bonding of strip **140** would be the wrapping on of wear strip **141** and the bonding of valley reinforcement cord **155**. This style of mandrel hose construction with cylindrical mandrels is common in the hose industry, but the use of a convoluted mandrel is new.

A second example of how conduit **158f** can be formed using the conduit making machine seen in FIG. 7 would be to have a three pass construction. Reinforced strip material **140** would be replaced by a plain polymer strip material like strip **143a** or **143b**, though some single direction reinforcement could be used. Also single cord **155** would be replaced by several radial reinforcement cords similar to cords **270a-d** seen in FIG. 3. The first pass would start with the wrapping platform (rollers **150** and **150a**, and heaters **151**, **151a**, and **151c** and strip material and cords) moving from right to left and both coiling wire **111** and bonding a layer of strip material **143a** over the wire and wrapping a first set of cords **270a-d** over the bonded strip material. The wire coiling portion on the wrapping platform is not shown in this drawing to keep the

drawing less cluttered, but can be placed next to the other wrapping and heating components. The second pass with the wrapping platform moving from left to right wraps on a second set of cords **270a-d** with the opposite twist as the first layer so that they form a bidirectional reinforcement. Also during the second pass a second layer of polymer strip **143a** is wrapped over the bidirectional reinforcement and bonded together at the seam using a number of different methods (i.e. thermal bonding, adhesives, etc.). Note that this second layer of both the cords **270a-d** and polymer strip **143a** is spiraled in the opposite direction as coiled wire **111** and thus the cords and strip seam crosses the valley and ridge many times along the length of conduit **158f**. If the first and second layers of strip materials need to be different, two polymer strips such as **143a** and **143b** can be used for the separate passes. The third pass from right to left could lay down a valley reinforcement **155** and bond a wear strip **141** to conduit **158f** as desired. The formed conduit would be similar in layer construction but the bidirectional cords would be continuous in this example and have slightly different orientations within conduit **158f** than when using strip material **140**. Many other layering options and positioning of layers are possible with this general type of platform. For example, valley reinforcement cord **155** can be wrapped on to the conduit after the wrapping of cords **270a-d**, but before bonding the second layer of polymer strip over the conduit to seal in cord **155**. Or cord **155** can be left off entirely and rely instead on the radially wrapped cords **270a-d** to provide valley reinforcement. Many additional layers of materials can be added within the conduit construction and between the bidirectional reinforcement and the valley forming reinforcement if desired.

Operation of Conduit Making Machine **100g**—FIG. 8

In FIG. 8, conduit making machine **100g** produces a hose that is very similar to the other conduit making machines in this patent, but because it uses two cord wrapping machines **259a-b** the angle of cords **252** and **254** can be chosen as desired. Wire coiling machine **105a** bends coated wire **111** around air mandrel **120d** as previously discussed, and wire **111** is guided by groove **125** at the ridge of mandrel **120d**. Compressed air from compressed air line **61** enters channel **73** and forces compressed air out of the plurality of holes **77** and **79**. Air exiting holes **77** produce an air cushion in groove **125** for wire **111** to float on. Compressed air exiting holes **79** produce an air cushion in the valley of the mandrel for strip **143e** to float on. Thus, the compressed air exiting holes **77** and **79** greatly reduce the friction of conduit **158g** against mandrel **120d** and it is allowed to rotate freely. Extra air holes, and/or larger air holes, are placed near the area where rollers **132** and **134** contact conduit **158g** to provide greater cushion against the forces created by the rollers. Similarly, extra air holes, and/or larger air holes, are provided in the area roller assembly **160** will be pressing against conduit **158g** to provide enhanced additional air cushion there. Extruded strip **143e** is wrapped onto wire **111** while still hot and the strip is pressed into itself by roller **132** to bond the edges of the strip together to form a watertight and airtight conduit.

In FIG. 8, after strip **143e** is formed into a conduit, reinforcement cords **252** and **254** are wrapped onto the conduit by standard wrapping machines **250a** and **250b**, respectively. Rotation direction arrows **146**, **256a**, and **256b** show the direction of rotation for conduit **158g**, cords **252**, and cords **254**, respectively. The length of direction arrows **146**, **256a**, and **256b** show the relative speed at which that item is rotating. Thus, in this design example, cords **252** are rotating the fastest so that they are wrapped with a right-handed twist onto conduit **158g**, and cords **254** are rotating the slowest so that they are wrapped with a left-handed twist onto conduit **158g**.

45

The rotation speed of conduit **158g** is between these two speeds. Nose rings **259a** and **259b** guide cords **252** and **254**, respectfully, onto conduit **158g** and properly place the cords on the conduit. The rotational speeds **146**, **256a**, and **256b** can be selected so that cords **252** and **254** naturally form a valley 5 between the coils of the desired depth. Thus, with the correct ratio of speeds cords **252** and **254** can provide valley reinforcement to help hold the valley in place against internal hose pressure. To increase resistance to internal hose pressure, reinforcement cord **155** is wrapped over cords **252** and **254** to insure a stable v-shaped valley. Additional layer can then be extruded or sprayed on to waterproof the exterior of the hose, and/or bond cords **252**, **254** and **155** in permanently in place. Additional air holes, and/or larger air holes **77** and **79** can be placed on mandrel **120d** where cords **252**, **254** and **155** are wrapped onto conduit **158g**. This provided added air cushion at the locations where the cords tension tend to press the conduit against the mandrel and reduces friction that might be caused by the added pressure of the cords. 10 15 20

#### RAMIFICATIONS, and SCOPE

The disclosed examples of a valley forming reinforcement and manufacturing processes that it can be used with to produce reinforced convoluted stretch hoses has several advantages over prior art hoses and systems. First, the valley forming reinforcement helps shape the valley portion of a helical convoluted stretch hose with bidirectional reinforcement which cannot form the valley on its own. Second, valley reinforcement helps form and maintain a v-shaped cross-section which reduces the reinforcement angles at the wire and the valley to improve longitudinal strength. Third, the valley forming reinforcement helps provide additional radial pressure strength by partially supporting the hose body in the radial direction. Fourth, valley reinforcement reduces the tendency of the hose body to permanently expand and deform radially during use at elevated temperatures. This is especially true with stretchable knit reinforcements which can stretch in all directions under force. 25 30 35

Although the above description of the invention contains many specifications, these should not be viewed as limiting the scope of the invention. Instead, the above example descriptions should be considered illustrations of some of the presently preferred embodiments of this invention. For example, the of differentially stretchable strips for the construction of the conduits is only presented as examples of conduit construction that be used with valley forming reinforcement, and other convoluted hose reinforcement structures will work equally well with valley forming reinforcement to improve internal pressure strength and prevent permanent radial deformation of the hose body, which can prevent retraction of the stretch hose. Also, many mandrel designs and styles exist that can be used with the disclosed hose manufacturing systems. For example, the mandrel design is not limited to just solid rods mandrels (FIGS. **1**, **3**, **4**, **5**, **6**), multiple rotating rods mandrels (FIG. **2**), rotating mandrels (FIG. **7**), with internal rollers or bearings that provide low-friction surfaces for the rotating hose (FIG. **8**), and other prior art mandrel styles and designs. 40 45 50 55

Thus, the scope of this invention should not be limited to the above examples but should be determined from the following claims. 60

I claim:

1. An extendable reinforced convoluted pressure hose having an extended length and a retracted length, comprising: 65
  - a) a convoluted stretch hose body having a valley portion and a ridge portion;

46

- b) a valley reinforcement cord comprising one or more of high strength fibers with a tensile strength greater than 15,000 psi;
- c) a metal biasing spring having a tendency to return the hose from the extended length to the retracted length; wherein:
  - A) the valley reinforcement cord is wound in a helical path along the valley portion of the convoluted stretch hose body, whereby the valley reinforcement cord stabilizes the valley portion of the convoluted stretch hose body and substantially maintains the radial position of the valley portion at the extended length;
  - B) the biasing spring is located along the ridge portion of the convoluted stretch hose body, whereby the biasing spring supports the ridge portion of the stretch hose body at both the extended length and the retracted length; and
  - C) the stretch hose body is between the valley reinforcement cord and the biasing spring, with the biasing spring disposed on the stretch hose body's interior, and the valley reinforcement cord disposed on the stretch hose body's exterior;
  - D) the extended length is at least twice the retracted length.

2. The reinforced convoluted hose in claim **1**, wherein the valley reinforcement cord is coated with a polymer matrix material, wherein the coated valley reinforcement cord can be bonded to the valley portion of the convoluted stretch hose body. 25

3. The reinforced convoluted hose in claim **2**, wherein the convoluted stretch hose body comprises a thermoplastic and/or an elastomer. 30

4. The reinforced convoluted hose in claim **1**, further including a means of bonding the valley reinforcement cord to the convoluted stretch hose body for further stabilizing the valley portion of the convoluted hose. 35

5. The reinforced convoluted hose in claim **4**, wherein convoluted stretch hose body comprises a thermoplastic and/or an elastomer. 40

6. The reinforced convoluted hose in claim **1**, further including one or more valley shaping cords positioned along the walls of the valley portion. 45

7. The reinforced convoluted hose in claim **1**, wherein the convoluted stretch hose body comprises bidirectional fiber reinforcement. 50

8. The reinforced convoluted hose in claim **1**, further including a plurality of longitudinal reinforcement cords positioned on convoluted stretch hose body under the valley reinforcement cord. 55

9. The reinforced convoluted hose in claim **8**, wherein the plurality of longitudinal reinforcement cords are oriented so that they spiral around the convoluted stretch hose opposite the direction of the valley portion spiral. 60

10. An extendable reinforced convoluted pressure hose having an extended length and a retracted length, comprising:

- a) a convoluted stretch hose body having a valley portion and a ridge portion;
- b) a metal biasing spring disposed along the ridge portion of the convoluted stretch hose body and adapted to:
  - i) allow the reinforced convoluted hose to extend to the extended length when pressurized;
  - ii) automatically retract the convoluted hose to the retracted length when depressurized; and
  - iii) support the ridge portion of the convoluted stretch hose body at both the extended length and the retracted length;

- c) a valley reinforcement cord disposed along the valley portion of the convoluted stretch hose body, and adapted to maintain the valley portion's radial position at the extended length;
- wherein:
- A) at both the extended length and the retracted length, the ridge portion of the convoluted stretch hose body has an inside diameter which is:
    - I) greater than or equal to an outside diameter of the biasing spring; and
    - II) greater than any other portion of the convoluted stretch hose body's inside diameter;
  - B) at the extended length, the valley portion of the convoluted stretch hose body has an outside diameter which is:
    - I) less than or equal to an inside diameter of the valley reinforcement cord; and
    - II) less than any other portion of the convoluted stretch hose body's outside diameter;
12. The reinforced convoluted hose of claim 10, wherein:
- a) the outside diameter of the valley portion of the convoluted stretch hose body is substantially equal to the inside diameter of the valley reinforcement cord; and
  - b) the inside diameter of the ridge portion of the convoluted stretch hose body is substantially equal to the outside diameter of the biasing spring.
13. A method of using an extendable reinforced convoluted pressure hose, the method comprising:
- a) extending the reinforced convoluted pressure hose from a retracted length to an extended length by pressurizing the convoluted pressure hose;

- b) while the reinforced convoluted pressure hose is at the extended length, using it to transport a fluid from a fluid source at a first end of the reinforced convoluted pressure hose to a second end of the reinforced convoluted pressure hose from which it is discharged;
  - c) after using the reinforced convoluted pressure hose to transport the fluid, allowing the reinforced convoluted pressure hose to self-retract while maintaining a convoluted shape by:
    - i) depressurizing the convoluted pressure hose such that a natural tendency of a metal biasing spring adapted to support a ridge portion of the reinforced convoluted pressure hose at both the extended length and the retracted length returns the reinforced convoluted pressure hose from the extended length to the retracted length; and
    - ii) stabilizing a valley portion of the of the reinforced convoluted pressure hose with a valley reinforcement cord which is disposed along the valley portion of the reinforced convoluted pressure hose and is adapted to maintain the valley portion's radial position at the extended length;
- wherein the extended length is at least twice the retracted length.
14. The method of claim 13, wherein:
- a) the valley portion and the ridge portion are both helical in shape; and
  - b) in a longitudinal cross section of the reinforced convoluted pressure hose, the ridge portion comprises a plurality of peaks, and the valley portion comprises a plurality of troughs;
  - c) maintaining the valley portion's radial position comprises, for each trough from the plurality of troughs having two neighboring peaks from the plurality of peaks, maintaining that trough at a position where the bottom of that trough is equidistant from the tops of each of its neighboring peaks.
15. The method of claim 13, wherein the reinforced convoluted pressure hose comprises a convoluted stretch hose body between the valley reinforcement cord and the biasing spring, with the biasing spring disposed on the stretch hose body's interior, and the valley reinforcement cord disposed on the stretch hose body's exterior.

\* \* \* \* \*