




(22) 1991/06/11

(43) 1991/12/14

(45) 2001/04/24

(72) Borzatta, Valerio, IT

(72) Carrozza, Primo, IT


(73) CIBA SPECIALTY CHEMICALS HOLDING INC., CH

(51) Int.Cl.⁵ C07D 401/14, C07D 413/14, C08L 39/08, C08F 226/06


(30) 1990/06/13 (20631A/90) IT

(54) **CO-OLIGOMERES PIPERIDINE-TRIAZINE UTILISES COMME
AGENTS STABILISANTS DE MATIERES ORGANIQUES**


(54) **PIPERIDINE-TRIAZINE CO-OLIGOMERS FOR USE AS
STABILIZERS FOR ORGANIC MATERIALS**




(Ia)



(Ib)



(Ic)




(II)

(57) The present invention relates to novel co-oligomers containing recurring units of the formulae (Ia) (Ib) (Ic) (see formulae Ia, Ib and Ic) which have a molecular weight of e.g. from 1,000 to 5,000 and a (Ia):(Ib) ratio of e.g. 1:1, and in which R₁ and R₅ are e.g. N-(2,2,6,6-tetramethyl-4-piperidyl)-n-butylamino, R₂ is e.g. 2,2,6,6-tetramethyl-4-piperidyl, R₃ is e.g. hexamethylene, R₄ is e.g. hydrogen and X is e.g. a group (see formula II) These compounds are particularly suitable for stabilizing organic materials against light, heat and oxidation.


A-18121/A/CHM 53

Novel piperidine-triazine co-oligomers for use as stabilizers for organic materialsAbstract of the disclosure

The present invention relates to novel co-oligomers containing recurring units of the formulae (Ia) and (Ib)



(Ia)



(Ib)

which have a molecular weight of e.g. from 1,000 to 5,000 and a (Ia):(Ib) ratio of e.g. 1:1, and in which R_1 and R_5 are e.g. N-(2,2,6,6-tetramethyl-4-piperidyl)-n-butylamino, R_2 is e.g. 2,2,6,6-tetramethyl-4-piperidyl, R_3 is e.g. hexamethylene, R_4 is e.g. hydrogen and X is e.g. a group $\text{—N—CH}_2\text{CH}_2\text{—O—}$.




These compounds are particularly suitable for stabilizing organic materials against light, heat and oxidation.

A-18121/A/CHM 53Novel piperidine-triazine co-oligomers for use as stabilizers for organic materials

The present invention relates to novel piperidine-triazine compounds, to their use as light stabilizers, heat stabilizers and oxidation stabilizers for organic materials, in particular synthetic polymers, and to organic materials thus stabilized.

It is known to use triazine oligomers and co-oligomers containing 2,2,6,6-tetramethylpiperidyl groups, as described in US patents 4,086,204, 4,331,586, 4,412,020, 4,459,395, 4,547,548 and 4,696,961, as stabilizers for synthetic polymers.

The present invention relates to novel co-oligomers containing recurring units of the formulae (Ia) and (Ib)




(Ia)

(Ib)

which have a molecular weight of from 1,000 to 20,000 and a (Ia):(Ib) ratio of from 4:1 to 1:4, and in which R₁ and R₅ which can be identical or different are a group -OR₆, -SR₆ or $\begin{array}{c} \text{---N---} \\ | \\ \text{R}_7 \end{array}$ R₈ in which R₆ is hydrogen, C₁-C₁₈alkyl, C₅-C₁₂cycloalkyl unsubstituted or


mono-, di- or tri-substituted by C₁-C₄alkyl; C₃-C₁₈alkenyl, C₇-C₉phenylalkyl unsubstituted or mono-, di- or tri-substituted on the phenyl by C₁-C₄alkyl; phenyl which is unsubstituted or mono-, di- or tri-substituted by C₁-C₄alkyl or C₁-C₄alkoxy; or a group of the formula (II)

- 2 -




in which R_9 is hydrogen, C_1 - C_8 alkyl, O , OH , NO , CH_2CN , C_1 - C_{18} alkoxy, C_5 - C_{12} cycloalkoxy, C_3 - C_6 alkenyl, C_7 - C_9 phenylalkyl unsubstituted or mono-, di- or tri-substituted on the phenyl by C_1 - C_4 alkyl; or C_1 - C_8 acyl, and R_7 and R_8 which can be identical or different are as defined above for R_6 or are C_2 - C_4 alkyl substituted in the 2-, 3- or 4-position by C_1 - C_8 alkoxy or by di- $(C_1$ - C_4 alkyl)-amino; or $\begin{array}{c} \text{---N---} \\ | \\ R_7 \end{array} R_8$ is a 5-membered to 7-membered

heterocyclic group, R_2 is hydrogen, C_1 - C_{18} alkyl, C_5 - C_{12} cycloalkyl unsubstituted or mono-, di- or tri-substituted by C_1 - C_4 alkyl; C_7 - C_9 phenylalkyl unsubstituted or mono-, di- or tri-substituted on the phenyl by C_1 - C_4 alkyl; or a group of the formula (III)



R_4 being as defined for R_9 , R_3 is C_2 - C_{12} alkylene, C_4 - C_{12} alkylene interrupted by 1, 2 or 3 oxygen atoms or by 1 or 2 $>N-R_{10}$ groups with R_{10} being as defined above for R_2 ; cyclohexylene, cyclohexylenedimethylene, methylenedicyclohexylene, isopropylidene-dicyclohexylene or xylylene, and X is one of the groups of the formulae (IVa)-(IVc)



in which R_{11} is hydrogen or C_1 - C_8 alkyl, R_{12} is C_2 - C_6 alkylene, n is zero or 1, R_{13} is as defined for R_7 and R_8 , and R_{14} is C_2 - C_6 alkylene or C_4 - C_{12} alkylene interrupted by 1, 2 or 3 oxygen atoms.

Examples of alkyl having not more than 18 carbon atoms are methyl, ethyl, propyl, isopropyl, butyl, 2-butyl, isobutyl, t-butyl, pentyl, 2-pentyl, hexyl, heptyl, octyl, 2-ethylhexyl, t-octyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, hexadecyl and octadecyl.

Examples of C_2 - C_4 alkyl substituted by C_1 - C_8 alkoxy, preferably C_1 - C_4 alkoxy, especially methoxy or ethoxy, are 2-methoxyethyl, 2-ethoxyethyl, 3-methoxypropyl, 3-ethoxypropyl, 3-butoxypropyl, 3-octoxypropyl and 4-methoxybutyl.

Examples of C_2 - C_4 alkyl substituted by di- $(C_1$ - C_4 alkyl)-amino, preferably by dimethylamino or diethylamino, are 2-dimethylaminoethyl, 2-diethylaminoethyl, 3-dimethylaminopropyl, 3-diethylaminopropyl, 3-dibutylaminopropyl and 4-diethylaminobutyl.

Representative examples of C_1 - C_{18} alkoxy R_4 and R_9 are methoxy, ethoxy, propoxy, isopropoxy, butoxy, isobutoxy, pentoxy, isopentoxy, hexoxy, heptoxy, octoxy, decyloxy, dodecyloxy, tetradecyloxy, hexadecyloxy and octadecyloxy. C_6 - C_{12} Alkoxy, in particular heptoxy or octoxy, is preferred.

Examples of the various C_5 - C_{12} cycloalkyl substituents which are unsubstituted or mono-, di- or tri-substituted by C_1 - C_4 alkyl are cyclopentyl, methylcyclopentyl, dimethylcyclopentyl, cyclohexyl, methylcyclohexyl, dimethylcyclohexyl, trimethylcyclohexyl, t-butylcyclohexyl, cyclooctyl, cyclodecyl and cyclododecyl; unsubstituted or C_1 - C_4 alkyl-substituted cyclohexyl is preferred.

Representative examples of C_5 - C_{12} cycloalkoxy R_4 and R_9 are cyclopentoxy, cyclohexoxy, cycloheptoxy, cyclooctoxy, cyclodecyloxy and cyclododecyloxy. Cyclopentoxy and cyclohexoxy are preferred.

Examples of alkenyl having not more than 18 carbon atoms are allyl, 2-methylallyl, hexenyl, decenyl, undecenyl and oleyl. Alkenyl groups in which the carbon atom in the 1-position is saturated are preferred; allyl is particularly preferred.

Examples of substituted phenyl are methylphenyl, dimethylphenyl, trimethylphenyl, t-butylphenyl, di-t-butylphenyl, 3,5-di-t-butyl-4-methylphenyl, methoxyphenyl and ethoxyphenyl.

Examples of the various C₇-C₉phenylalkyl substituents which are unsubstituted or mono-, di- or tri-substituted on the phenyl by C₁-C₄alkyl are benzyl, methylbenzyl, dimethylbenzyl, trimethylbenzyl, t-butylbenzyl and 2-phenylethyl. Benzyl is preferred.

Acyl R₄ and R₉ having not more than 8 carbon atoms can be an aliphatic or aromatic group. Representative examples are formyl, acetyl, propionyl, butyryl, pentanoyl, hexanoyl, heptanoyl, octanoyl, benzoyl, acryloyl or crotonoyl. C₁-C₈Alkanoyl, C₃-C₈-alkenoyl and benzoyl are preferred. Acetyl is particularly preferred.

A 5-membered to 7-membered heterocyclic group $\begin{array}{c} \text{---N---R}_8 \\ | \\ \text{R}_7 \end{array}$ can contain a further

heteroatom, for example nitrogen or oxygen; representative examples are 1-pyrrolidyl, 1-piperidyl, 4-morpholinyl, 4-methyl-1-piperazinyl and 1-hexahydroazepinyl. 4-Morpholinyl is preferred.

Examples of alkylene having not more than 12 carbon atoms are ethylene, propylene, trimethylene, tetramethylene, pentamethylene, 2,2-dimethyltrimethylene, hexamethylene, trimethylhexamethylene, octamethylene, decamethylene and dodecamethylene.

Examples of C₄-C₁₂alkylene interrupted by 1, 2 or 3 oxygen atoms are 3-oxapentane-1,5-diyl, 4-oxaheptane-1,7-diyl, 3,6-dioxaoctane-1,8-diyl, 4,7-dioxadecane-1,10-diyl, 4,9-dioxadodecane-1,12-diyl and 3,6,9-trioxaundecane-1,11-diyl.

Representative examples of C₄-C₁₂alkylene R₃ interrupted by 1 or 2 >N-R₁₀ groups are the groups $\begin{array}{c} \text{---(CH}_2\text{)}_{2-6}\text{---N---(CH}_2\text{)}_{2-6}\text{---} \\ | \\ \text{R}_{10} \end{array}$ and $\begin{array}{c} \text{---(CH}_2\text{)}_{2-3}\text{---N---(CH}_2\text{)}_{2-3}\text{---N---(CH}_2\text{)}_{2-3}\text{---} \\ | \qquad \qquad | \\ \text{R}_{10} \qquad \qquad \text{R}_{10} \end{array}$.

The preferred definitions of R₄ and R₉ are hydrogen, C₁-C₄alkyl, OH, C₆-C₁₂alkoxy, C₅-C₈cycloalkoxy, allyl, benzyl or acetyl, in particular hydrogen or methyl.

Those co-oligomers are preferred which contain recurring units of the formulae (Ia) and (Ib) and have a molecular weight of from 1,000 to 15,000 and a (Ia):(Ib) ratio of from 4:1 to 1:4, and in which R₁ and R₅ which can be identical or different are a group -OR₆, -SR₆

or $\begin{array}{c} \text{---N---R}_8 \\ | \\ \text{R}_7 \end{array}$, R_6 is $\text{C}_1\text{-C}_{14}$ alkyl, $\text{C}_5\text{-C}_8$ cycloalkyl unsubstituted or mono-, di- or

tri-substituted by $\text{C}_1\text{-C}_4$ alkyl; $\text{C}_3\text{-C}_{12}$ alkenyl, benzyl, phenyl or a group of the formula (II), R_7 and R_8 which can be identical or different are as defined above for R_6 or are hydrogen or $\text{C}_2\text{-C}_3$ alkyl substituted in the 2- or 3-position by $\text{C}_1\text{-C}_4$ alkoxy or by di- $(\text{C}_1\text{-C}_4\text{alkyl})$ -amino; or the group $\begin{array}{c} \text{---N---R}_8 \\ | \\ \text{R}_7 \end{array}$ is 1-pyrrolidyl, 1-piperidyl, 4-morpholinyl,

4-methyl-1-piperazinyl or 1-hexahydroazepinyl, R_2 is hydrogen, $\text{C}_1\text{-C}_{12}$ alkyl, $\text{C}_5\text{-C}_8$ cycloalkyl unsubstituted or mono-, di- or tri-substituted by $\text{C}_1\text{-C}_4$ alkyl; benzyl or a group of the formula (III), R_3 is $\text{C}_2\text{-C}_{10}$ alkylene, $\text{C}_4\text{-C}_{10}$ alkylene interrupted by 1, 2 or 3 oxygen atoms or by 1 or 2 $>\text{N-CH}_3$ groups; cyclohexylene, cyclohexylenedimethylene, methylenedicyclohexylene, isopropylidenedicyclohexylene or xylylene, and X is one of the groups of the formulae (IVa)-(IVc) in which R_{11} is hydrogen or $\text{C}_1\text{-C}_4$ alkyl, R_{12} is $\text{C}_2\text{-C}_6$ alkylene, n is zero or 1, R_{13} is as defined for R_7 and R_8 , and R_{14} is $\text{C}_2\text{-C}_6$ alkylene or $\text{C}_4\text{-C}_{10}$ alkylene interrupted by 1, 2 or 3 oxygen atoms.

Those co-oligomers are particularly preferred which contain recurring units of the formulae (Ia) and (Ib) and have a molecular weight of from 1,000 to 10,000 and a (Ia):(Ib) ratio of from 3:1 to 1:3, and in which R_1 and R_5 which can be identical or different are a group $-\text{OR}_6$, $-\text{SR}_6$ or $\begin{array}{c} \text{---N---R}_8 \\ | \\ \text{R}_7 \end{array}$, R_6 is $\text{C}_1\text{-C}_{12}$ alkyl, cyclohexyl which is unsubstituted or

mono-, di- or tri-substituted by $\text{C}_1\text{-C}_4$ alkyl; allyl, undecenyl, benzyl, phenyl or a group of the formula (II), R_7 and R_8 which can be identical or different are as defined for R_6 or are hydrogen or $\text{C}_2\text{-C}_3$ alkyl substituted in the 2- or 3-position by $\text{C}_1\text{-C}_4$ alkoxy, by dimethylamino or by diethylamino; or the group $\begin{array}{c} \text{---N---R}_8 \\ | \\ \text{R}_7 \end{array}$ is 4-morpholinyl, R_2 is hydrogen,

$\text{C}_1\text{-C}_8$ alkyl, cyclohexyl which is unsubstituted or mono-, di- or tri-substituted by $\text{C}_1\text{-C}_4$ alkyl; benzyl or a group of the formula (III), R_3 is $\text{C}_2\text{-C}_8$ alkylene, $\text{C}_6\text{-C}_{10}$ alkylene interrupted by 2 or 3 oxygen atoms; cyclohexylenedimethylene, methylenedicyclohexylene or xylylene, and X is one of the groups of the formulae (IVa)-(IVc) in which R_{11} is hydrogen or methyl, R_{12} is $\text{C}_2\text{-C}_4$ alkylene, n is zero or 1, R_{13} is as defined for R_7 and R_8 , and R_{14} is $\text{C}_2\text{-C}_4$ alkylene or $\text{C}_4\text{-C}_8$ alkylene interrupted by 1 or 2 oxygen atoms.

Those co-oligomers are of special interest which contain recurring units of the formulae

(Ia) and (Ib) and have a molecular weight of from 1,000 to 8,000 and a (Ia):(Ib) ratio of from 2:1 to 1:2, and in which R_1 and R_5 which can be identical or different are a group $-OR_6$ or $-\overset{\text{R}_7}{\underset{|}{\text{N}}}-R_8$, R_6 is C_1 - C_8 alkyl, cyclohexyl, allyl, benzyl, phenyl or a group of the

formula (II), R_7 and R_8 which can be identical or different are as defined above for R_6 or are hydrogen or C_2 - C_3 alkyl substituted in the 2- or 3-position by methoxy, by ethoxy, by dimethylamino or by diethylamino; or the group $-\overset{\text{R}_7}{\underset{|}{\text{N}}}-R_8$ is 4-morpholinyl, R_2 is

hydrogen, C_1 - C_4 alkyl, cyclohexyl or a group of the formula (III), R_3 is C_2 - C_6 alkylene, C_6 - C_{10} alkylene interrupted by 2 or 3 oxygen atoms; cyclohexylenedimethylene, methylenedicyclohexylene or xylylene, and X is one of the groups of the formulae (IVa)-(IVc) in which R_{11} is hydrogen or methyl, R_{12} is C_2 - C_3 alkylene, n is zero or 1, R_{13} is as defined for R_7 and R_8 , and R_{14} is C_2 - C_4 alkylene or C_4 - C_8 alkylene interrupted by 1 or 2 oxygen atoms.


Those co-oligomers are of particular interest which contain recurring units of the formulae (Ia) and (Ib) and have a molecular weight of from 1,000 to 5,000 and a (Ia):(Ib) ratio of from 2:1 to 1:1, and in which R_1 and R_5 are a group $-OR_6$ or $-\overset{\text{R}_7}{\underset{|}{\text{N}}}-R_8$, R_6 is C_1 - C_4 alkyl,

2,2,6,6-tetramethyl-4-piperidyl or 1,2,2,6,6-pentamethyl-4-piperidyl, R_7 and R_8 which can be identical or different are C_1 - C_8 alkyl, cyclohexyl, 2,2,6,6-tetramethyl-4-piperidyl or 1,2,2,6,6-pentamethyl-4-piperidyl, or R_7 can also be hydrogen, or the group $-\overset{\text{R}_7}{\underset{|}{\text{N}}}-R_8$ is


4-morpholinyl, R_2 is hydrogen, methyl, 2,2,6,6-tetramethyl-4-piperidyl or 1,2,2,6,6-pentamethyl-4-piperidyl, R_3 is C_2 - C_6 alkylene or C_8 - C_{10} alkylene interrupted by 2 or 3 oxygen atoms, R_4 is hydrogen or methyl and X is one of the groups of the formulae (IVa)-(IVc) in which R_{11} is hydrogen, R_{12} is ethylene, n is zero or 1, R_{13} is as defined for R_7 and R_8 , and R_{14} is C_2 - C_3 alkylene or C_4 - C_6 alkylene interrupted by one oxygen atom.

The novel compounds of the present invention can be prepared by processes known per se, for example as reported in US patent 4,459,395, by reacting, in the appropriate molar ratios, dichlorotriazines of the formulae (Va) and (Vb)

- 7 -




(Va)



(Vb)

with the compounds of the formulae (VIa) and (VIb)




(VIa)



(VIb)

The two reagents (VIa) and (VIb) can be reacted with the dichlorotriazines (Va) and (Vb) simultaneously or separately, using an excess, preferably of not more than 20 %, of the reagents (VIa) and (VIb) for controlling the molecular weight. If $R_1 = R_5$ and the (Ia):(Ib) ratio = 1:1, it is possible to prepare co-oligomers having a regular alternation of the recurring units (Ia) and (Ib), first preparing the compound of the formula (VII)



(VII)

as an intermediate and then reacting it with the compound (VIb).

The reactions are preferably carried out in an aromatic hydrocarbon solvent, for example toluene, xylene or trimethylbenzene, operating at a temperature of e.g. between 40° and 200°C, preferably between 50° and 180°C.

The hydrogen chloride set free in the reaction is preferably neutralized with an inorganic base, for example sodium or potassium hydroxide or carbonate in a quantity at least equivalent to the acid set free.


The dichlorotriazines (Va) and (Vb) can be prepared by known processes by reacting e.g. cyanuric chloride with compounds R_1-H and R_5-H in equimolar ratio.

If $R_1 = R_5$, the dichlorotriazine thus obtained can be used directly, without isolation from the reaction mixture, for the subsequent reaction with the compounds of the formulae (VIa) and (VIb).

The compounds (VIa) can be prepared, for example, as described in US patent 4,104,248.

The compounds (VIb) are commercially available or can easily be prepared by known processes.


Depending on the type and the molar ratios of the starting materials (monomers) used, the compounds of the present invention can have different end groups. In particular, the end groups bound to the triazine radical (formulae Ia and Ib) are, for example, $-Cl$, $-OH$, $-ONa$, $-OK$, a group R_1 or R_5 , with R_1 and R_5 being as defined above, a group $-X-Z$ or a group



where Z is hydrogen, methyl, C_1-C_8 acyl or $(C_1-C_4$ alkoxy)-carbonyl. The end group attached to the polyalkylpiperidylimino group (formula (Ia)) and the terminal group attached to the oxygen atom (X of formula (Ib)) are e.g. Z which is as defined above.

If R_4 and $R_9 = CH_3$, the co-oligomers of the present invention can preferably be prepared by reacting the corresponding compounds where R_4 and $R_9 = H$ with formaldehyde and formic acid or with formaldehyde and hydrogen in the presence of a hydrogenation catalyst such as palladium or platinum.

A preferred embodiment of the instant invention is also a co-oligomer containing recurring units of the formulae (Ia) and (Ib), which has a (Ia):(Ib) ratio of 1:1 and a regular alternation of the recurring units (Ia) and (Ib) characterized in that the co-oligomer contains recurring units of the formula (Ic)



wherein R_1 and R_5 are identical.

As mentioned in the outset, the novel compounds of the present invention are highly effective in improving the light stability, heat stability and oxidation stability of organic materials, in particular synthetic polymers and copolymers.

Examples of such organic materials which can be stabilized are:

1. Polymers of monoolefins and diolefins, for example polypropylene, polyisobutylene, polybutene-1, polymethylpentene-1, polyisoprene or polybutadiene, as well as polymers of cycloolefins, for instance of cyclopentene or norbornene, polyethylene (which optionally can be crosslinked), for example high-density polyethylene (HDPE), low-density polyethylene (LDPE) and linear low-density polyethylene (LLDPE).
2. Mixtures of the polymers mentioned under 1), for example mixtures of polypropylene with polyisobutylene, polypropylene with polyethylene (for example PP/HDPE, PP/LDPE) and mixtures of different types of polyethylene (for example LDPE/HDPE).
3. Copolymers of monoolefins and diolefins with each other or with other vinyl monomers, such as, for example, ethylene/propylene, linear low-density polyethylene (LLDPE) and its mixtures with low-density polyethylene (LDPE), propylene/butene-1, ethylene/hexene, ethylene/ethylpentene, ethylene/heptene, ethylene/octene, propylene/isobutylene, ethylene/butene-1, propylene/butadiene, isobutylene/isoprene, ethylene/alkyl acrylates, ethylene/alkyl methacrylates, ethylene/vinyl acetate or

ethylene/acrylic acid copolymers and their salts (ionomers) and terpolymers of ethylene with propylene and a diene, such as hexadiene, dicyclopentadiene or ethylidenenorbornene; as well as mixtures of such copolymers and their mixtures with polymers mentioned in 1) above, for example polypropylene/ethylene-propylene copolymers, LDPE/EVA, LDPE/EAA, LLDPE/EVA and LLDPE/EAA.

3a. Copolymers of α -olefins with carbon monoxide, with regular or random alternation.

3b. Hydrocarbon resins (for example C₅-C₉) and hydrogenated modifications thereof (for example tackifiers).

4. Polystyrene, poly-(p-methylstyrene), poly-(α -methylstyrene).

5. Copolymers of styrene or α -methylstyrene with dienes or acrylic derivatives, such as, for example, styrene/acrylonitrile, styrene/alkyl methacrylate, styrene/maleic anhydride, styrene/butadiene/ethyl acrylate, styrene/acrylonitrile/methyl acrylate; mixtures of high impact strength from copolymers of styrene and other polymers, such as, for example, from a polyacrylate, a diene polymer or an ethylene/propylene/diene terpolymer and block copolymers of styrene, such as, for example, styrene/butadiene/styrene, styrene/isoprene/styrene, styrene/ethylene/butylene/styrene or styrene/ethylene/propylene/styrene.

6. Graft copolymers of styrene or α -methylstyrene such as, for example, styrene on polybutadiene; styrene on polybutadiene-styrene or polybutadiene-acrylonitrile; styrene and acrylonitrile (or methacrylonitrile) on polybutadiene; styrene and maleic anhydride or maleimide on polybutadiene; styrene, acrylonitrile and maleic anhydride or maleimide on polybutadiene; styrene, acrylonitrile and methyl methacrylate on polybutadiene; styrene and alkyl acrylates or methacrylates on polybutadiene; styrene and acrylonitrile on ethylene/propylene/diene terpolymers; styrene and acrylonitrile on polyacrylates or polymethacrylates; styrene and acrylonitrile on acrylate/butadiene copolymers, as well as mixtures thereof with the copolymers listed under 5), for instance the mixtures known as ABS, MBS, ASA and AES polymers.

7. Halogen-containing polymers, such as polychloroprene, chlorinated rubbers, chlorinated or sulfochlorinated polyethylene, epichlorohydrin homo- and copolymers, polymers from halogen-containing vinyl compounds, such as for example polyvinyl chloride,

polyvinylidene chloride, polyvinyl fluoride, polyvinylidene fluoride, as well as copolymers thereof, for example vinyl chloride/vinylidene chloride, vinyl chloride/vinyl acetate or vinylidene chloride/vinyl acetate copolymers.

8. Polymers which are derived from α,β -unsaturated acids and derivatives thereof, such as polyacrylates and polymethacrylates, polyacrylamide and polyacrylonitrile.

9. Copolymers from the monomers mentioned under 8) with each other or with other unsaturated monomers, such as, for instance, acrylonitrile/butadiene, acrylonitrile/alkyl acrylate, acrylonitrile/alkoxyalkyl acrylate or acrylonitrile/vinyl halide copolymers or acrylonitrile/alkyl methacrylate/butadiene terpolymers.

10. Polymers which are derived from unsaturated alcohols and amines, or acyl derivatives thereof or acetals thereof, such as polyvinyl alcohol, polyvinyl acetate, polyvinyl stearate, polyvinyl benzoate, polyvinyl maleate, polyvinyl butyral, polyallyl phthalate or polyallylmelamine; as well as their copolymers with olefins mentioned in 1) above.

11. Homopolymers and copolymers of cyclic ethers, such as polyalkylene glycols, polyethylene oxide, polypropylene oxide or copolymers thereof with bis-glycidyl ethers.

12. Polyacetals, such as polyoxymethylene and polyoxymethylenes which contain ethylene oxide as a comonomer; polyacetals modified with thermoplastic polyurethanes, acrylates or MBS.

13. Polyphenylene oxides and sulfides, and mixtures of polyphenylene oxides with polystyrene and polyamides.

14. Polyurethanes which are derived from polyethers, polyesters or polybutadiene with terminal hydroxyl groups on the one hand and aliphatic or aromatic polyisocyanates on the other hand, as well as precursors thereof (polyisocyanates, polyols or prepolymers).

15. Polyamides and copolyamides which are derived from diamines and dicarboxylic acids and/or from aminocarboxylic acids or the corresponding lactams, such as polyamide 4, polyamide 6/6, polyamide 6/10, 6/9, 6/12 and 4/6, polyamide 11, polyamide 12, aromatic polyamides obtained by condensation of m-xylenediamine and adipic acid; polyamides prepared from hexamethylenediamine and isophthalic and/or terephthalic acid and

optionally an elastomer as modifier, for example poly-2,4,4-trimethyl-hexamethylene-terephthalamide or poly-m-phenylene-isophthalamide. Further, copolymers of the aforementioned polyamides with polyolefins, olefin copolymers, ionomers or chemically bonded or grafted elastomers; or with polyethers, as, for instance, with polyethylene glycols, polypropylene glycols or polytetramethylene glycols. Polyamides or copolyamides modified with EPDM or ABS. Polyamides condensed during processing (RIM-polyamide systems).

16. Polyureas, polyimides and polyamide-imides.

17. Polyesters which are derived from dicarboxylic acids and diols and/or from hydroxycarboxylic acids or the corresponding lactones, such as polyethylene terephthalate, polybutylene terephthalate, poly-1,4-dimethylolcyclohexane terephthalate, poly-[2,2-(4-hydroxyphenyl)-propane] terephthalate and polyhydroxybenzoate as well as block copolyether-esters derived from polyethers having hydroxyl end groups.

18. Polycarbonates and polyester-carbonates.

19. Polysulfones, polyether-sulfones and polyether-ketones.

20. Crosslinked polymers which are derived from aldehydes on the one hand and phenols, ureas and melamines on the other hand, such as phenol/formaldehyde resins, urea/formaldehyde resins and melamine/formaldehyde resins.

21. Drying and non-drying alkyd resins.

22. Unsaturated polyester resins which are derived from copolyesters of saturated and unsaturated dicarboxylic acids with polyhydric alcohols and vinyl compounds as crosslinking agents, and also halogen-containing modifications thereof of low flammability.

23. Thermosetting acrylic resins, derived from substituted acrylic esters, such as epoxy-acrylates, urethane-acrylates or polyester-acrylates.

24. Alkyd resins, polyester resins or acrylate resins in admixture with melamine resins, urea resins, polyisocyanates or epoxide resins as crosslinking agents.

25. Crosslinked epoxide resins which are derived from polyepoxides, for example from bis-glycidyl ethers or from cycloaliphatic diepoxides.

26. Natural polymers, such as cellulose, rubber, gelatine and derivatives thereof which are chemically modified in a polymer-homologous manner, such as cellulose acetates, cellulose propionates and cellulose butyrates, or cellulose ethers, such as methylcellulose; rosins and their derivatives.

27. Mixtures of the polymers mentioned above, for example PP/EPDM, polyamide 6/EPDM or ABS, PVC/EVA, PVC/ABS, PVC/MBS, PC/ASA, PC/PBT, PVC/CPE, PVC/acrylates, POM/thermoplastic PUR, PC/thermoplastic PUR, POM/acrylate, POM/MBS, PPE/HIPS, PPE/PA 6/6 and copolymers, PA/HDPE, PA/PP, PA/PPE.

28. Naturally occurring and synthetic organic materials which are pure monomeric compounds or mixtures of such compounds, for example mineral oils, animal and vegetable fats, oil and waxes, or oils, fats and waxes based on synthetic esters (e.g. phthalates, adipates, phosphates or trimellitates) and also mixtures of synthetic esters with mineral oils in any weight ratio, which materials may be used as plasticizers for polymers or as textile spinning oils, as well as aqueous emulsions of such materials.

29. Aqueous emulsions of natural or synthetic rubbers, for example natural latex or latexes of carboxylated styrene/butadiene copolymers.

The instant co-oligomers are particularly suitable for improving the light stability, heat stability and oxidation stability of polyolefins, especially polyethylene and polypropylene.

The co-oligomers of the present invention can be used in mixtures with organic materials in various proportions depending on the nature of the material to be stabilized, on the end use and on the presence of other additives.

In general, it is appropriate to use, for example, 0.01 to 5 % by weight of the instant co-oligomers, relative to the weight of the material to be stabilized, preferably 0.05 to 1 %.

In general, the instant co-oligomers can be added to the polymeric materials before, during or after the polymerization or crosslinking of the said materials.

The instant co-oligomers can be incorporated in the polymeric materials by various processes, such as dry mixing in the form of powder, or wet mixing in the form of solutions or suspensions or also in the form of a masterbatch; in such operations, the polymer can be used in the form of powder, granules, solutions, suspensions or in the form of latices. It is possible to incorporate the instant co-oligomers into the material to be stabilized in a pure form or encapsulated in waxes, oils or polymers.

The materials stabilized with the instant co-oligomers can be used for the production of mouldings, films, tapes, monofilaments, fibres, surface coatings and the like.

If desired, other conventional additives for synthetic polymers, such as antioxidants, UV absorbers, nickel stabilizers, pigments, fillers, plasticizers, antistatic agents, flameproofing agents, lubricants, corrosion inhibitors and metal deactivators, can be added to the mixtures of the instant co-oligomers with the organic materials.

Particular examples of additives which can be used in admixture with the instant co-oligomers are:

1. Antioxidants

1.1. Alkylated monophenols, for example 2,6-di-tert-butyl-4-methylphenol, 2-tert-butyl-4,6-dimethylphenol, 2,6-di-tert-butyl-4-ethylphenol, 2,6-di-tert-butyl-4-n-butylphenol, 2,6-di-tert-butyl-4-isobutylphenol, 2,6-dicyclopentyl-4-methylphenol, 2-(α -methylcyclohexyl)-4,6-dimethylphenol, 2,6-dioctadecyl-4-methylphenol, 2,4,6-tricyclohexylphenol, 2,6-di-tert-butyl-4-methoxymethylphenol, 2,6-dinonyl-4-methylphenol.

1.2. Alkylated hydroquinones, for example 2,6-di-tert-butyl-4-methoxyphenol, 2,5-di-tert-butylhydroquinone, 2,5-di-tert-amylhydroquinone, 2,6-diphenyl-4-octadecyloxyphenol.

1.3. Hydroxylated thiodiphenyl ethers, for example 2,2'-thiobis(6-tert-butyl-4-methylphenol), 2,2'-thiobis(4-octylphenol), 4,4'-thiobis(6-tert-butyl-3-methylphenol), 4,4'-thiobis(6-tert-butyl-2-methylphenol).

1.4. Alkylidenebisphenols, for example 2,2'-methylenebis(6-tert-butyl-4-methylphenol), 2,2'-methylenebis(6-tert-butyl-4-ethylphenol), 2,2'-methylenebis[4-methyl-6-(α -methylcyclohexyl)phenol], 2,2'-methylenebis(4-methyl-6-cyclohexylphenol), 2,2'-methylenebis(6-nonyl-4-methylphenol), 2,2'-methylenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(4,6-di-tert-butylphenol), 2,2'-ethylidenebis(6-tert-butyl-4-isobutylphenol), 2,2'-methylenebis[6-(α -methylbenzyl)-4-nonylphenol], 2,2'-methylenebis[6-(α,α -dimethylbenzyl)-4-nonylphenol], 4,4'-methylenebis(2,6-di-tert-butylphenol), 4,4'-methylenebis(6-tert-butyl-2-methylphenol), 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 2,6-bis(3-tert-butyl-5-methyl-2-hydroxybenzyl)-4-methylphenol, 1,1,3-tris(5-tert-butyl-4-hydroxy-2-methylphenyl)butane, 1,1-bis(5-tert-butyl-4-hydroxy-2-methylphenyl)-3-n-dodecylmercaptobutane, ethylene glycol bis[3,3-bis(3'-tert-butyl-4'-hydroxyphenyl)butyrate], bis(3-tert-butyl-4-hydroxy-5-methylphenyl)-dicyclopentadiene, bis[2-(3'-tert-butyl-2'-hydroxy-5'-methylbenzyl)-6-tert-butyl-4-methylphenyl] terephthalate.

1.5. Benzyl compounds, for example

1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl)-2,4,6-trimethylbenzene, bis(3,5-di-tert-butyl-4-hydroxybenzyl) sulfide, isooctyl 3,5-di-tert-butyl-4-hydroxybenzylmercaptoacetate, bis(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl) dithiolterephthalate, 1,3,5-tris(3,5-di-tert-butyl-4-hydroxybenzyl) isocyanurate, 1,3,5-tris(4-tert-butyl-3-hydroxy-2,6-dimethylbenzyl) isocyanurate, dioctadecyl 3,5-di-tert-butyl-4-hydroxybenzylphosphonate, calcium salt of monoethyl 3,5-di-tert-butyl-4-hydroxybenzylphosphonate, 1,3,5-tris(3,5-dicyclohexyl-4-hydroxybenzyl) isocyanurate.

1.6. Acylaminophenols, for example lauric acid 4-hydroxyanilide, stearic acid

4-hydroxyanilide, 2,4-bis(octylmercapto)-6-(3,5-di-tert-butyl-4-hydroxyanilino)-s-triazine, octyl N-(3,5-di-tert-butyl-4-hydroxyphenyl)-carbamate.

1.7. Esters of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid with mono- or

polyhydric alcohols, e.g. with methanol, diethylene glycol, octadecanol, triethylene glycol,

1,6-hexanediol, pentaerythritol, neopentyl glycol, tris(hydroxyethyl) isocyanurate, thiodiethylene glycol, N,N'-bis(hydroxyethyl)oxamide.

1.8. Esters of β -(5-tert-butyl-4-hydroxy-3-methylphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, diethylene glycol, octadecanol, triethylene glycol, 1,6-hexanediol, pentaerythritol, neopentyl glycol, tris(hydroxyethyl) isocyanurate, thiodiethylene glycol, N,N'-bis(hydroxyethyl)oxamide.

1.9. Esters of β -(3,5-dicyclohexyl-4-hydroxyphenyl)propionic acid with mono- or polyhydric alcohols, e.g. with methanol, diethylene glycol, octadecanol, triethylene glycol, 1,6-hexanediol, pentaerythritol, neopentyl glycol, tris(hydroxyethyl) isocyanurate, thiodiethylene glycol, N,N'-bis(hydroxyethyl)oxamide.

1.10. Amides of β -(3,5-di-tert-butyl-4-hydroxyphenyl)propionic acid e.g. N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hexamethylenediamine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)trimethylenediamine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazine.

2. UV absorbers and light stabilizers

2.1. 2-(2'-Hydroxyphenyl)benzotriazoles, for example the 5'-methyl, 3',5'-di-tert-butyl, 5'-tert-butyl, 5'-(1,1,3,3-tetramethylbutyl), 5-chloro-3',5'-di-tert-butyl, 5-chloro-3'-tert-butyl-5'-methyl, 3'-sec-butyl-5'-tert-butyl, 4'-octoxy, 3',5'-di-tert-amyl and 3',5'-bis(α,α -dimethylbenzyl) derivatives.

2.2. 2-Hydroxybenzophenones, for example the 4-hydroxy, 4-methoxy, 4-octoxy, 4-decyloxy, 4-dodecyloxy, 4-benzyloxy, 4,2',4'-trihydroxy and 2'-hydroxy-4,4'-dimethoxy derivatives.

2.3. Esters of variously substituted benzoic acids, for example 4-tert-butylphenyl salicylate, phenyl salicylate, octylphenyl salicylate, dibenzoylresorcinol, bis(4-tert-butylbenzoyl)resorcinol, benzoylresorcinol, 2,4-di-tert-butylphenyl 3,5-di-tert-butyl-4-hydroxybenzoate and hexadecyl 3,5-di-tert-butyl-4-hydroxybenzoate.

2.4. Acrylates, for example ethyl α -cyano- β,β -diphenylacrylate, isooctyl α -cyano- β,β -diphenylacrylate, methyl α -carbomethoxycinnamate, methyl

α -cyano- β -methyl-p-methoxycinnamate, butyl α -cyano- β -methyl-p-methoxycinnamate, methyl α -carbomethoxy-p-methoxycinnamate and N-(β -carbomethoxy- β -cyanovinyl)-2-methylindoline.

2.5. Nickel compounds, for example nickel complexes of 2,2'-thiobis[4-(1,1,3,3-tetramethylbutyl)phenol], such as the 1:1 or 1:2 complex, with or without additional ligands such as n-butylamine, triethanolamine or N-cyclohexyldiethanolamine, nickel dibutyldithiocarbamate, nickel salts of 4-hydroxy-3,5-di-tert-butylbenzylphosphonic acid monoalkyl esters, e.g. of the methyl or ethyl ester, nickel complexes of ketoximes, e.g. of 2-hydroxy-4-methylphenyl undecyl ketoxime, nickel complexes of 1-phenyl-4-lauroyl-5-hydroxypyrazole, with or without additional ligands.

2.6. Sterically hindered amines, for example bis(2,2,6,6-tetramethylpiperidyl) sebacate, bis(1,2,2,6,6-pentamethylpiperidyl) sebacate, bis-(1,2,2,6,6-pentamethylpiperidyl) n-butyl-3,5-di-tert-butyl-4-hydroxybenzylmalonate, the condensation product of 1-hydroxyethyl-2,2,6,6-tetramethyl-4-hydroxypiperidine and succinic acid, the condensation product of N,N'-bis(2,2,6,6-tetramethyl-4-piperidyl)hexamethylenediamine and 4-tert-octylamino-2,6-dichloro-1,3,5-triazine, tris(2,2,6,6-tetramethyl-4-piperidyl) nitrilotriacetate, tetrakis(2,2,6,6-tetramethyl-4-piperidyl) 1,2,3,4-butanetetracarboxylate, 1,1'-(1,2-ethanediyl)-bis(3,3,5,5-tetramethylpiperazinone).

2.7. Oxalic acid diamides, for example, 4,4'-dioctyloxyoxanilide, 2,2'-dioctyloxy-5,5'-di-tert-butyloxanilide, 2,2'-didodecyloxy-5,5'-di-tert-butyloxanilide, 2-ethoxy-2'-ethyloxanilide, N,N'-bis(3-dimethylaminopropyl)oxamide, 2-ethoxy-5-tert-butyl-2'-ethyloxanilide and its mixtures with 2-ethoxy-2'-ethyl-5,4'-di-tert-butyloxanilide and mixtures of ortho- and para-methoxy-disubstituted oxanilides and mixtures of o- and p-ethoxy-disubstituted oxanilides.

2.8 2-(2-Hydroxyphenyl)-1,3,5-triazines, for example 2,4,6-tris(2-hydroxy-4-octyloxyphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2,4-dihydroxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine, 2,4-bis(2-hydroxy-4-propyloxyphenyl)-6-(2,4-dimethylphenyl)-1,3,5-triazine, 2-(2-hydroxy-4-octyloxyphenyl)-4,6-bis(4-methylphenyl)-1,3,5-triazine,

2-(2-hydroxy-4-dodecyloxyphenyl)-4,6-bis(2,4-dimethylphenyl)-1,3,5-triazine.

3. Metal deactivators, for example N,N'-diphenyloxamide, N-salicylal-N'-salicyloylhydrazine, N,N'-bis(salicyloyl)hydrazine, N,N'-bis(3,5-di-tert-butyl-4-hydroxyphenylpropionyl)hydrazine, 3-salicyloylamino-1,2,4-triazole, bis(benzylidene)oxalodihydrazide.

4. Phosphites and phosphonites, for example triphenyl phosphite, diphenyl alkyl phosphites, phenyl dialkyl phosphites, tris(nonylphenyl) phosphite, trilauryl phosphite, trioctadecyl phosphite, distearyl pentaerythritol diphosphite, tris(2,4-di-tert-butylphenyl) phosphite, diisodecyl pentaerythritol diphosphite, bis(2,4-di-tert-butylphenyl) pentaerythritol diphosphite, tristearyl sorbitol triphosphite, tetrakis(2,4-di-tert-butylphenyl) 4,4'-biphenylenediphosphonite, 3,9-bis(2,4-di-tert-butylphenoxy)-2,4,8,10-tetraoxa-3,9-diphosphaspiro[5.5]undecane.

4a. Hydroxylamines, for example dibenzylhydroxylamine, dioctylhydroxylamine, didodecylhydroxylamine, ditetradecylhydroxylamine, dihexadecylhydroxylamine, dioctadecylhydroxylamine, 1-hydroxy-2,2,6,6-tetramethyl-4-piperidyl benzoate or bis-(1-hydroxy-2,2,6,6-tetramethyl-4-piperidinyl) sebacate.

5. Peroxide scavengers, for example esters of β -thiodipropionic acid, for example the lauryl, stearyl, myristyl or tridecyl esters, mercaptobenzimidazole or the zinc salt of 2-mercaptobenzimidazole, zinc dibutyldithiocarbamate, dioctadecyl disulfide, pentaerythritol tetrakis(β -dodecylmercapto)propionate.

6. Polyamide stabilizers, for example copper salts in combination with iodides and/or phosphorus compounds and salts of divalent manganese.

7. Basic co-stabilizers, for example melamine, polyvinylpyrrolidone, dicyandiamide, triallyl cyanurate, urea derivatives, hydrazine derivatives, amines, polyamides, polyurethanes, alkali metal salts and alkaline earth metal salts of higher fatty acids, for example calcium stearate, zinc stearate, magnesium stearate, sodium ricinoleate and potassium palmitate, antimony pyrocatecholate or zinc pyrocatecholate.

8. Nucleating agents, for example 4-tert-butyl-benzoic acid, adipic acid, diphenylacetic acid.

9. Fillers and reinforcing agents, for example calcium carbonate, silicates, glass fibres, asbestos, talc, kaolin, mica, barium sulfate, metal oxides and hydroxides, carbon black, graphite.

10. Other additives, for example plasticizers, lubricants, emulsifiers, pigments, optical brighteners, flameproofing agents, antistatic agents and blowing agents.

Several examples of the preparation and use of the co-oligomers containing recurring units of the formulae (Ia) and (Ib) are reported for more detailed illustration of the present invention; these examples are given solely for illustrative purposes and do not imply any restriction. An especially preferred example of the instant invention is example 4.


Example 1: A solution of 63.7 g (0.3 mol) of 4-butylamino-2,2,6,6-tetramethylpiperidine in 60 ml of water is added slowly, maintaining the temperature between 0° and 5°C, to a solution of 55.3 g (0.3 mol) of cyanuric chloride in 400 ml of xylene, cooled to 0°C. After 30 minutes, a solution of 12.4 g (0.31 mol) of sodium hydroxide in 30 ml of water is added slowly, maintaining the temperature between 0° and 5°C.

The mixture is stirred for 1 hour at between 5° and 10°C, the aqueous phase is separated off, 59.2 g (0.15 mol) of N,N'-bis-(2,2,6,6-tetramethyl-4-piperidyl)-1,6-hexanediamine and 12 g (0.3 mol) of sodium hydroxide are added, and the whole is heated for 4 hours at 90°C.

40.3 g (0.2 mol) of 1-(2-hydroxyethyl)-2,2,6,6-tetramethyl-4-piperidinol and 24 g (0.6 mol) of ground sodium hydroxide are then added and the mixture is heated for 16 hours under reflux, the water of reaction being separated off azeotropically.

After cooling to about 70°C, the reaction mixture is filtered for separating off the inorganic products, and the filtrate is evaporated under reduced pressure. The product obtained melts at 161-170°C and has a molecular weight of $M_n = 3,000$.

Examples 2-6: Following the procedure described in Example 1 and using the respective reagents in the appropriate molar ratios, the following compounds containing recurring units of the formula



are prepared:.

Example	R	R'	m.p.(°C)	Mn
2	$n - C_4H_9 - N -$ 	$-N - \text{piperidine ring} - CH_2CH_2O -$	149-158	2100
3	$n - C_4H_9 - N -$ 	$-OCH_2CH_2 - N - \text{piperidine ring} - CH_2CH_2O -$	130-139	4300
4	$n - C_4H_9 - N -$ 	$-N - CH_2CH_2O -$ $ $ C_2H_5	140-147	1900
5	$O - \text{piperidine ring} - N -$		170-177	2300
6	$O - \text{piperidine ring} - N -$	$-N - CH_2CH_2O -$ 	170-175	2000

Example 7: 70.5 g (0.3 mol) of 2,4-dichloro-6-morpholino-1,3,5-triazine, 78.9 g (0.2 mol) of N,N'-bis-(2,2,6,6-tetramethyl-4-piperidyl)-1,6-hexanediamine and 16 g (0.4 mol) of sodium hydroxide in 400 ml of xylene are heated for 4 hours at 70°C.

30.2 g (0.15 mol) of 1-(2-hydroxyethyl)-2,2,6,6-tetramethyl-4-piperidinol and 16 g (0.4

mol) of ground sodium hydroxide are then added, and the mixture is heated for 16 hours under reflux, with the water being separated off azeotropically.

After cooling to about 70°C, the reaction mixture is filtered for separating off the inorganic products, and the filtrate is evaporated under reduced pressure. The product obtained melts at 160-169°C and has a molecular weight of $M_n = 2,600$.

In the examples, the number-average molecular weight is determined by means of a vapour pressure osmometer ([®]Gonotec) as described in EP-A-255,990, from page 18, line 54, to page 19, line 15.

Example 8 (light-stabilizing action in polypropylene tapes): 1 g of each of the compounds indicated in Table 1, 1.0 g of tris-(2,4-di-t-butylphenyl) phosphite, 0.5 g of pentaerythritol tetrakis-[3-(3,5-di-t-butyl-4-hydroxyphenyl)-propionate] and 1 g of calcium stearate are mixed in a slow mixer with 1,000 g of polypropylene powder of melt index = 2 g/10 minutes (measured at 230°C and 2.16 kg).

The mixtures are extruded at 200-230°C to give polymer granules which are then converted into stretched tapes of 50 µm thickness and 2.5 mm width, using a pilot-type apparatus ([®]Leonard-Sumirago (VA) Italy) operating under the following conditions:

extruder temperature	:	210-230°C
head temperature	:	240-260°C
stretch ratio	:	1:6

The tapes thus prepared are exposed, mounted on a white card, in a 65 WR Weather-O-Meter (ASTM D 2565-85) with a black panel temperature of 63°C. The residual tenacity is measured on samples taken after various times of exposure to light by means of a constant-speed tensometer; the exposure time (in hours) (T_{50}) needed to halve the initial tenacity is then calculated.

Tapes prepared under the same conditions as indicated above, but without addition of stabilizer are exposed for comparison.

The results obtained are shown in Table 1.

TABLE 1

Stabilizer	T ₅₀ (hours)
none	300
compound from Example 1	1600
compound from Example 2	1800

Example 9 (light-stabilizing action in polypropylene fibres): 2.5 g of each of the products indicated in Table 2, 0.5 g of tris-(2,4-di-t-butylphenyl) phosphite, 0.5 g of calcium monoethyl 3,5-di-t-butyl-4-hydroxybenzylphosphonate, 1 g of calcium stearate and 2.5 g of titanium dioxide are mixed in a slow mixer with 1,000 g of polypropylene powder of melt index = 12 g/10 minutes (measured at 230°C and 2.16 kg).

The mixtures are extruded at 200-230°C to give polymer granules which are then converted into fibres, using a pilot-type apparatus ([®]Leonard-Sumirago (VA), Italy), operating under the following conditions:

extruder temperature	:	200-230°C
head temperature	:	255-260°C
stretch ratio	:	1:3.5
count	:	11 dtex per filament.

The fibres thus prepared are exposed, after mounting on a white card, in a model 65 WR Weather-O-Meter (ASTM D 2565-85) with a black panel temperature of 63°C.

The residual tenacity is measured on samples taken after various times of exposure to light by means of a constant-speed tensometer, and the exposure time in hours (T₅₀) need to halve the initial tenacity is then calculated.

Fibres prepared under the same conditions as indicated above, but without the addition of compounds according to the invention, are exposed for comparison.

The results obtained are shown in Table 2:

TABLE 2

Stabilizer	T ₅₀ (hours)
none	150
compound from Example 1	1060
compound from Example 3	1050
compound from Example 5	1030
compound from Example 7	1160

Example 10 (antioxidant action in polypropylene plaques):

1 g of the compound whose preparation is described in example 4, 0.5 g of octadecyl 3-(3,5-di-t-butyl-4-hydroxyphenyl) propionate, 1 g of tris-(2,4-di-t-butylphenyl) phosphite and 1 g of calcium stearate are mixed in a slow mixer with 1,000 g of polypropylene powder of melt index = 2 g/10 minutes (measured at 230°C and 2.16 kg).

The mixture is extruded twice at 200-230°C to give polymer granules which are then converted into plaques of 1 mm thickness by compression-moulding for 6 minutes at 230°C.

The plaques are then punched by means of a DIN 53451 mould, and the specimens obtained are exposed in a forced-circulation air oven maintained at a temperature of 135°C.

The specimens are checked at intervals by folding them by 180°, in order to determine the time (in hours) needed to cause fracture. Specimens prepared under the conditions indicated above, but without addition of the compound of the present invention, are also exposed for comparison.

The results obtained are shown in table 3.

- 24 -


TABLE 3

<u>Stabilizer</u>	<u>Time to fracture (hrs)</u>
none	550
compound from example 4	2160


The compounds of the invention can also be used as stabilizers, especially as light stabilizers, for almost all materials known in the art of photographic reproduction and other reproduction techniques as e.g. described in Research Disclosure 1990, 31429 (pages 474 to 480).

WHAT IS CLAIMED IS:

1. A co-oligomer containing recurring units of the formulae (Ia) and (Ib)




(Ia)



(Ib)

which has a molecular weight of from 1,000 to 20,000 and a (Ia):(Ib) ratio of from 4:1 to 1:4, and in which R_1 and R_5 which can be identical or different are a group $-OR_6$, $-SR_6$ or $-N(R_7)-R_8$ in which R_6 is hydrogen, C_1 - C_{18} alkyl, C_5 - C_{12} cycloalkyl unsubstituted or

mono-, di- or tri-substituted by C_1 - C_4 alkyl; C_3 - C_{18} alkenyl, C_7 - C_9 phenylalkyl unsubstituted or mono-, di- or tri-substituted on the phenyl by C_1 - C_4 alkyl; phenyl which is unsubstituted or mono-, di- or tri-substituted by C_1 - C_4 alkyl or C_1 - C_4 alkoxy; or a group of the formula (II)




(II)

in which R_9 is hydrogen, C_1 - C_8 alkyl, O-, OH, NO, CH_2CN , C_1 - C_{18} alkoxy, C_5 - C_{12} cycloalkoxy, C_3 - C_6 alkenyl, C_7 - C_9 phenylalkyl unsubstituted or mono-, di- or tri-substituted on the phenyl by C_1 - C_4 alkyl; or C_1 - C_8 acyl, and R_7 and R_8 which can be identical or different are as defined above for R_6 or are C_2 - C_4 alkyl substituted in the 2-, 3- or 4-position by C_1 - C_8 alkoxy or by di- $(C_1$ - C_4 alkyl)-amino; or $-N(R_7)-R_8$ is a 5-membered

to 7-membered heterocyclic group, R_2 is hydrogen, C_1 - C_{18} alkyl, C_5 - C_{12} cycloalkyl unsubstituted or mono-, di- or tri-substituted by C_1 - C_4 alkyl; C_7 - C_9 phenylalkyl unsubstituted or mono-, di- or tri-substituted on the phenyl by C_1 - C_4 alkyl; or a group of the formula (III)



R_4 being as defined for R_9 , R_3 is C_2 - C_{12} alkylene, C_4 - C_{12} alkylene interrupted by 1, 2 or 3 oxygen atoms or by 1 or 2 $>N-R_{10}$ groups with R_{10} being as defined above for R_2 ; cyclohexylene, cyclohexylenedimethylene, methylenedicyclohexylene, isopropylidene-dicyclohexylene or xylylene, and X is one of the groups of the formulae (IVa)-(IVc)



in which R_{11} is hydrogen or C_1 - C_8 alkyl, R_{12} is C_2 - C_6 alkylene, n is zero or 1, R_{13} is as defined for R_7 and R_8 , and R_{14} is C_2 - C_6 alkylene or C_4 - C_{12} alkylene interrupted by 1, 2 or 3 oxygen atoms.

2. A co-oligomer containing recurring units of the formulae (Ia) and (Ib) according to claim 1, in which R_4 and R_9 which can be identical or different are hydrogen, C_1 - C_4 alkyl, OH, C_6 - C_{12} alkoxy, C_5 - C_8 cycloalkoxy, allyl, benzyl or acetyl.

3. A co-oligomer containing recurring units of the formulae (Ia) and (Ib) according to claim 1, which has a molecular weight of from 1,000 to 15,000 and a (Ia):(Ib) ratio of from 4:1 to 1:4, and in which R_1 and R_5 which can be identical or different are a group $-OR_6$, $-SR_6$ or $-N(R_7)-R_8$, R_6 is C_1 - C_{14} alkyl, C_5 - C_8 cycloalkyl unsubstituted or mono-, di-

or tri-substituted by C_1 - C_4 alkyl; C_3 - C_{12} alkenyl, benzyl, phenyl or a group of the formula

(II), R_7 and R_8 which can be identical or different are as defined above for R_6 or are hydrogen or C_2 - C_3 alkyl substituted in the 2- or 3-position by C_1 - C_4 alkoxy or by di- $(C_1$ - C_4 alkyl)-amino; or the group $\begin{array}{c} \text{---N---} R_8 \\ | \\ R_7 \end{array}$ is 1-pyrrolidyl, 1-piperidyl, 4-morpholinyl,

4-methyl-1-piperazinyl or 1-hexahydroazepinyl, R_2 is hydrogen, C_1 - C_{12} alkyl, C_5 - C_8 cycloalkyl unsubstituted or mono-, di- or tri-substituted by C_1 - C_4 alkyl; benzyl or a group of the formula (III), R_3 is C_2 - C_{10} alkylene, C_4 - C_{10} alkylene interrupted by 1, 2 or 3 oxygen atoms or by 1 or 2 $>N$ - CH_3 groups; cyclohexylene, cyclohexylenedimethylene, methylenedicyclohexylene, isopropylidenedicyclohexylene or xylylene, and X is one of the groups of the formulae (IVa)-(IVc) in which R_{11} is hydrogen or C_1 - C_4 alkyl, R_{12} is C_2 - C_6 alkylene, n is zero or 1, R_{13} is as defined for R_7 and R_8 , and R_{14} is C_2 - C_6 alkylene or C_4 - C_{10} alkylene interrupted by 1, 2 or 3 oxygen atoms.

4. A co-oligomer containing recurring units of the formulae (Ia) and (Ib) according to claim 1, which has a molecular weight of from 1,000 to 10,000 and a (Ia):(Ib) ratio of from 3:1 to 1:3, and in which R_1 and R_5 which can be identical or different are a group $-OR_6$, $-SR_6$ or $\begin{array}{c} \text{---N---} R_8 \\ | \\ R_7 \end{array}$, R_6 is C_1 - C_{12} alkyl, cyclohexyl which is unsubstituted or mono-,

di- or tri-substituted by C_1 - C_4 alkyl; allyl, undecenyl, benzyl, phenyl or a group of the formula (II), R_7 and R_8 which can be identical or different are as defined for R_6 or are hydrogen or C_2 - C_3 alkyl substituted in the 2- or 3-position by C_1 - C_4 alkoxy, by dimethylamino or by diethylamino; or the group $\begin{array}{c} \text{---N---} R_8 \\ | \\ R_7 \end{array}$ is 4-morpholinyl, R_2 is

hydrogen, C_1 - C_8 alkyl, cyclohexyl which is unsubstituted or mono-, di- or tri-substituted by C_1 - C_4 alkyl; benzyl or a group of the formula (III), R_3 is C_2 - C_8 alkylene, C_6 - C_{10} alkylene interrupted by 2 or 3 oxygen atoms; cyclohexylenedimethylene, methylenedicyclohexylene or xylylene, and X is one of the groups of the formulae (IVa)-(IVc) in which R_{11} is hydrogen or methyl, R_{12} is C_2 - C_4 alkylene, n is zero or 1, R_{13} is as defined for R_7 and R_8 , and R_{14} is C_2 - C_4 alkylene or C_4 - C_8 alkylene interrupted by 1 or 2 oxygen atoms.

5. A co-oligomer containing recurring units of the formulae (Ia) and (Ib) according to claim 1, which has a molecular weight of from 1,000 to 8,000 and a (Ia):(Ib) ratio of from 2:1 to 1:2, and in which R_1 and R_5 which can be identical or different are a group $-OR_6$ or

$\begin{array}{c} \text{---N---R}_8 \\ | \\ \text{R}_7 \end{array}$, R₆ is C₁-C₈alkyl, cyclohexyl, allyl, benzyl, phenyl or a group of the formula

(II), R₇ and R₈ which can be identical or different are as defined above for R₆ or are hydrogen or C₂-C₃alkyl substituted in the 2- or 3-position by methoxy, by ethoxy, by dimethylamino or by diethylamino; or the group $\begin{array}{c} \text{---N---R}_8 \\ | \\ \text{R}_7 \end{array}$ is 4-morpholinyl, R₂ is


hydrogen, C₁-C₄alkyl, cyclohexyl or a group of the formula (III), R₃ is C₂-C₆alkylene, C₆-C₁₀alkylene interrupted by 2 or 3 oxygen atoms; cyclohexylenedimethylene, methylenedicyclohexylene or xylylene, and X is one of the groups of the formulae (IVa)-(IVc) in which R₁₁ is hydrogen or methyl, R₁₂ is C₂-C₃alkylene, n is zero or 1, R₁₃ is as defined for R₇ and R₈, and R₁₄ is C₂-C₄alkylene or C₄-C₈alkylene interrupted by 1 or 2 oxygen atoms.

6. A co-oligomer containing recurring units of the formulae (Ia) and (Ib) according to claim 1, which has a molecular weight of from 1,000 to 5,000 and a (Ia):(Ib) ratio of from 2:1 to 1:1, and in which R₁ and R₅ are a group -OR₆ or $\begin{array}{c} \text{---N---R}_8 \\ | \\ \text{R}_7 \end{array}$, R₆ is C₁-C₄alkyl,

2,2,6,6-tetramethyl-4-piperidyl or 1,2,2,6,6-pentamethyl-4-piperidyl, R₇ and R₈ which can be identical or different are C₁-C₈alkyl, cyclohexyl, 2,2,6,6-tetramethyl-4-piperidyl or 1,2,2,6,6-pentamethyl-4-piperidyl, or R₇ can also be hydrogen, or the group $\begin{array}{c} \text{---N---R}_8 \\ | \\ \text{R}_7 \end{array}$ is


4-morpholinyl, R₂ is hydrogen, methyl, 2,2,6,6-tetramethyl-4-piperidyl or 1,2,2,6,6-pentamethyl-4-piperidyl, R₃ is C₂-C₆alkylene or C₈-C₁₀alkylene interrupted by 2 or 3 oxygen atoms, R₄ is hydrogen or methyl and X is one of the groups of the formulae (IVa)-(IVc) in which R₁₁ is hydrogen, R₁₂ is ethylene, n is zero or 1, R₁₃ is as defined for R₇ and R₈, and R₁₄ is C₂-C₃alkylene or C₄-C₆alkylene interrupted by one oxygen atom.

7. A co-oligomer containing recurring units of the formulae (Ia) and (Ib) according to claim 1, which has a (Ia):(Ib) ratio of 1:1 and a regular alternation of the recurring units (Ia) and (Ib) characterized in that the co-oligomer contains recurring units of the formula (Ic)




wherein R_1 and R_5 are identical.


8. A co-oligomer according to claim 7, which has a molecular weight of from 1,000 to 5,000 and in which R_1 and R_5 are N-(2,2,6,6-tetramethyl-4-piperidyl)-n-butylamino, R_2 is 2,2,6,6-tetramethyl-4-piperidyl, R_3 is hexamethylene, R_4 is hydrogen and X is a group




9. A composition which contains an organic material susceptible to degradation induced by light, heat and oxidation and a co-oligomer containing recurring units of the formulae (Ia) and (Ib) according to claim 1.
10. A composition according to claim 9, wherein the organic material is a synthetic polymer.
11. A composition according to claim 10, which contains other conventional additives for synthetic polymers, in addition to the co-oligomer containing recurring units of the formulae (Ia) and (Ib).
12. A composition according to claim 9, wherein the organic material is a polyolefin.
13. A composition according to claim 9, wherein the organic material is polyethylene or polypropylene.
14. A method for stabilizing an organic material against degradation induced by light, heat and oxidation, which comprises incorporating in said organic material a co-oligomer containing recurring units of the formulae (Ia) and (Ib) according to claim 1.




(Ia)



(Ib)



(Ic)



(II)