



(12) **EUROPEAN PATENT APPLICATION**

(43) Date of publication:
26.04.2017 Bulletin 2017/17

(51) Int Cl.:
G01K 7/02 (2006.01) **G01K 7/04** (2006.01)
F01D 17/08 (2006.01) **F01D 5/28** (2006.01)
G01K 13/02 (2006.01)

(21) Application number: **16200727.2**

(22) Date of filing: **01.07.2009**

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO PL PT RO SE SI SK SM TR

(30) Priority: **01.08.2008 US 85645 P**
01.08.2008 US 85654 P
03.12.2008 US 327058

(62) Document number(s) of the earlier application(s) in accordance with Art. 76 EPC:
09790020.3 / 2 310 819

(71) Applicant: **Siemens Energy, Inc.**
Orlando, FL 32826-2399 (US)

(72) Inventors:
• **Kulkarni, Anand A.**
Charlotte, 28277 (US)
• **Mitchell, David J.**
Oviedo, 32765 (US)
• **Roesch, Edward R.**
Orlando, 32833 (US)

(74) Representative: **Maier, Daniel Oliver**
Siemens AG
Postfach 22 16 34
80506 München (DE)

Remarks:

This application was filed on 25-11-2016 as a divisional application to the application mentioned under INID code 62.

(54) **THERMOCOUPLE FOR GAS TURBINE ENVIRONMENTS**

(57) An instrumented gas turbine component comprising: a metal substrate (22) thermally insulated by a thermal barrier coating (20); a layer of electrically insulating material (34) that maintains a resistance greater than 0.5 mega ohms above 1100°C deposited on an exposed surface of the thermal barrier coating (20), the layer of electrically insulating material (34) comprising yttrium aluminum garnet; and a thermocouple (12) formed on the layer of electrically insulating material (34), the thermocouple (12) comprising a first leg (26') comprising a first pure metal and a second leg (28') making ohmic contact with the first leg (26').




Fig. 4A

Description

[0001] This application claims benefit of the 01 August 2008 filing dates of United States Provisional Application 61/085,645 and United States Provisional Application 61/085,654.

FIELD OF THE INVENTION

[0002] The present invention generally relates to thermocouples and their method of manufacture, and in particular to thin-film monoelemental thermoelectric elements and structure forming thermocouples that may be deposited on non-planar surfaces and are efficient at ultra high temperatures.

BACKGROUND OF THE INVENTION

[0003] There is an increasing demand for real-time measurement of the structural integrity of critical moving components in modern gas turbines, which operate at ultra high temperatures. Moreover, requirements for gas turbines in the future call for ever higher operating temperatures. However, the harsh turbine environment encountered in these turbines along with the lack of long-term demonstrated sensor functionality, make it difficult to meet these objectives. The materials exposed to the hot gas path are being operated more closely to their design margins, which require the development of accurate and reliable sensors for monitoring the materials' condition during operation. While life prediction tools utilize laboratory generated data, active monitoring with embedded sensors enable a better understanding of the physics of material failure, loss of functionality due to material degradation, and coating delamination or cracking or spalling. The turbine typically includes a wide range of component materials with varied exposure to high temperatures and high centrifugal forces on rotating elements, and it is often surrounded by highly conductive metallic materials.

[0004] A temperature sensor with demonstrated reliability is a thermocouple. In principle, when two conductors made of dissimilar metals are joined at both ends, a thermoelectric circuit is formed. When one of the ends of this circuit is heated, there is a continuous current that flows in the thermoelectric circuit. Thomas Seebeck made this discovery in 1821. If this circuit is broken at the center, the hot open circuit voltage (the Seebeck voltage) is a function of the junction temperature and the composition of the two metals. Such a circuit is known as a thermocouple.

[0005] Most prior art thermocouples are made of wire. For example, a standard thermocouple, such as a Type S thermocouple, is made of a pure platinum wire for one wire leg and an alloy of approximately 90% platinum and 10% rhodium for the second wire leg. Another example of a standard prior art thermocouple is a Type R thermocouple, which has one wire leg made of an alloy consist-

ing of 95% platinum and 5% rhodium, while the second wire leg is made of an alloy consisting of 87% platinum and 13% rhodium. These alloy combinations work well when the thermocouples are made of wire wherein the percent of the constituents along the length of the wire are consistent. This is not necessarily the case when the thermocouple legs are deposited in thin-film structures. For example, when an alloy (e.g., platinum-10% rhodium) is deposited, compositional variations along the length of the thermocouple leg will occur. That is to say, the 10% rhodium will not be evenly distributed everywhere, which will cause a deviation in the performance of the thermocouple.

[0006] Accordingly, there is a need for a thermocouple that is reliable and that can withstand the harsh environment of a gas turbine. While the thermocouple needs to function in a turbine hot gas path section where temperatures may be greater than 1300°C, it is also desired that the thermocouple has minimal impact on the performance or life of the component.

BRIEF DESCRIPTION OF THE DRAWINGS

[0007] The invention is explained in the following description in view of the drawings that show:

FIG. 1 is a perspective view of a turbine blade having a sensor, such as a thermocouple, formed thereon. FIG. 2 is cross-sectional view of a portion of the turbine blade showing a thin-film thermocouple in accordance with the present invention formed on the thermal barrier coating on the blade.

FIG. 3 is a planar view of the thin-film thermocouple in accordance with the present invention.

FIG. 4A is a cross-sectional view of a portion of the turbine blade showing a thermocouple in accordance with an embodiment of the present invention formed over a high temperature dielectric on the thermal barrier coating (TBC) on the blade.

FIG. 4B is a cross-sectional view of a portion of the turbine blade showing a thermocouple in accordance with an embodiment of the present invention formed over a high temperature dielectric deposited directly onto the blade's substrate and beneath the TBC layer.

FIG. 4C is a cross-sectional view of a portion of the turbine blade showing a thermocouple in accordance with an embodiment of the present invention formed within the TBC layer.

FIG. 5 is a planar view of the thin-film thermocouple deposited over the high temperature dielectric over or beneath the TBC layer in accordance with the present invention.

FIG. 6 is a graph showing the performance of the monoelemental thermocouple as temperature increases.

FIG. 7 is a graph showing the performance of the monoelemental thermocouple compared with a

standard Type S type thermocouple.

DETAILED DESCRIPTION OF THE INVENTION

[0008] With the development of thin-film techniques it is recognized that there are several advantages of thin-film thermocouples over the standard wire thermocouples for measuring solid surface temperatures. Their low mass provides a very rapid response, the thinness of the film does not disturb the convective heat transfer characteristics of the surface compared to a wire sensor, and the small size is quite compatible with complex electronic fabrication techniques. Moreover, the low mass of the thin-film sensor, when attached to a turbine component, does not create problems with centrifugal forces placed on the thermocouple by turbine rotation. Furthermore, the thin-film sensor allows conformance to the non-planar surfaces of turbine components. Additionally, thin-film sensor implementation on critical moving components in the harsh turbine environment provides an excellent source of data for condition-based monitoring during operation. These thermocouples provide a real-time temperature profile that enables reliability monitoring of the part in service. One such family of thin-film sensors is the monoelemental thermocouple. A mono-elemental thermocouple has two legs each made of a different single-element material (e.g., precious metals like platinum, palladium, rhodium, or iridium). In other words, a monoelemental thermocouple does not use legs of alloyed wire as in the Type S and Type R wire thermocouples.

[0009] Pure platinum and pure palladium metals for the two legs of the thermocouple may be used due to the minimal mismatch of their CTE with that of an underlying ceramic thermal barrier coating (TBC) deposited on the turbine component (i.e., blade). Also, due to the purity of these metals (i.e., they are monoelemental), there is very little chemical variation along the length of the deposited thermocouple lines to contribute to a variation in the performance of the thermocouple. The term "pure" or "monoelemental" as used herein means a purity level of at least 99 wt. percent. Additional advantages of using these metals include their excellent oxidation properties and high melting point (e.g., platinum is 1769°C), which allows the thermocouple to be deposited on the top surface of the TBC where it may be exposed directly to the hot combustion gas path environment.

[0010] One instrumented moving turbine component that would enable collection of real-time temperature data is shown in FIG. 1, wherein a turbine blade 10 of a gas turbine 11 has mounted thereon a thermocouple 12 and conductors 14 leading to circuitry 16, which processes and transmits data derived from the thermocouple 12 to a receiver circuit (not shown) external the turbine 11. An effective solution to the circuitry 16 is disclosed in published U.S. Patent Application Publication No US 2005/0198967 A1 entitled SMART COMPONENT FOR USE IN AN OPERATING ENVIRONMENT.

[0011] Referring now to FIG. 2, a cross-sectional view

of a portion of the turbine blade 10 is shown having mounted thereon a thin-film thermocouple 12 in accordance with one embodiment of the present invention, which is formed atop the TBC 20 covering the metal blade. The underlying substrate 22 of the blade 10 has first formed thereon a bond coat 24, which separates the TBC 20 from the substrate and ensures a good bond between the two. FIG. 3 is a plan view of the thermocouple 12, where in accordance with one embodiment, a first leg 26 is formed of pure platinum and a second leg 28 is formed of pure palladium. First ends of the two legs 26 and 28 are joined together at a point 30, which makes ohmic contact between these two legs and forms a hot junction for conversion of heat into an electrical signal (i.e., the Seebeck voltage). Bonding pads 32A and 32B are formed on the other ends of the legs 26 and 28, respectively, which allow for the making of electrical contact with the conductors 14 in order to transmit the electrical signal (i.e., Seebeck voltage) to the circuitry 16.

[0012] Another consideration in a high-temperature turbine environment (e.g., greater than 800°C) is the dielectric/ionic conductivity of the TBC material. The standard TBC, which is made from yttria stabilized zirconia, loses its dielectric strength above 800°C. Accordingly, there may be a need for a ceramic insulator coating 34 (FIG. 4A) to separate the thermocouple 12 from the TBC 20, which insulator coating typically has a dielectric strength (high temperature resistance of greater than 0.5 mega ohms) above 1100°C. Various oxides are capable of retaining such strength at high temperatures. One composition of interest is yttrium aluminum garnet ("YAG"), which has been deposited in thickness within a range of 50 - 250 microns and has demonstrated excellent performance of the thermocouple at high temperature (e.g., above 1100°C). A cross-sectional view of the dielectric insulator coating 34 on the TBC 20 is shown in FIG. 4A. In particular, the dielectric insulator coating 34 physically and electrically separates the thermocouple 12 from the TBC 20. An alternate embodiment of the invention is shown in FIG. 4B which illustrates another portion of the turbine blade wherein the dielectric insulator coating 34 is deposited directly onto the substrate 22 and the thermocouple 12 is deposited over this dielectric insulator coating. Also, another dielectric insulator coating 35 (such as of the same material and thickness) may be deposited over the thermocouple 12 if needed. Finally, the TBC layer 20 is deposited over the dielectric insulator coating 35 (or directly over the thermocouple). Accordingly, the thermocouple 12 is embedded in the structure and senses directly the temperature of the component substrate 22. FIG. 4C is an embodiment which illustrates yet another portion of the turbine blade wherein the thermocouple 12 is embedded within the TBC layer 20 and is electrically insulated from contact with the TBC material 20 by layers of electrically insulating material 34, 35 in order to provide a measurement of the temperature within the TBC layer 20. Such structures may be formed by thermally spraying the respective materials as the

TBC layer 20 is formed in a conventional manner.

[0013] FIG. 5 is a plan view of the thermocouple 12 of FIG. 4A, wherein in accordance with an embodiment a first leg 26' is formed of pure platinum and a second leg 28' is formed of pure palladium. The two legs 26' and 28' are joined together at a point 30', which makes ohmic contact between the two legs. Bonding pads 32A' and 32B' are formed on the other end of the legs 26' and 28', respectively, which allows for making electrical contact with the conductors 14.

[0014] FIG. 6 is a graph showing the performance (curve 40) of the monoelemental thermocouple. As temperature increases, the thermocouple voltage (Seebeck voltage in mv) increases substantially linearly. The performance of these thermocouples is shown in FIG. 7 by curve 41, with comparison to standard Type S thermocouples (curve 43). In this configuration, the monoelemental thermocouple performance is within 3 degrees of the Type S thermocouple, which exhibits an excellent correlation.

[0015] The legs 32A and 32B (or 32A' and 32B') and the conductors 14 may be deposited on the blade 10 by plasma spraying, EB PVD, CVD, pulsed laser deposition, mini-plasma, direct write, mini hvof or solution plasma spraying, for example. In one embodiment the legs of the thermocouple 12 are deposited at a thickness within the range of 50 - 100 microns, which thickness may be necessary for endurance in the harsh environment of a gas turbine.

[0016] It is noted that the scale of the cross-sectional illustrations of FIGS. 2, 4A 4B and 4C are such that they may be considered to show either a planar substrate or curved or non-planar surface as found on most turbine components.

[0017] In accordance with an alternate embodiment of the invention the second leg 28 or 28' may be replaced with a transparent conducting oxide (TCO), while the first leg 26 or 26' remains pure platinum. Such TCO provides a good thermoelectric response with platinum as the first leg, mainly due to their excellent electrical conductivity. Another advantage is their chemical stability. Examples of such oxides are CuAlO_2 , $\text{In}_2\text{O}_3\text{-SnO}_2$, $\text{In}_2\text{O}_3\text{-SnO}_2$ doped with ZnO , Ga_2O_3 , CdIn_2O_4 , Cd_2SnO_4 , and ZnO . This alternate embodiment would be optimum for environments where the temperature exceeds 1550°C because pure palladium begins to soften and oxidize above this temperature. The performance curve for a pure platinum-oxide thermocouple is depicted by curve 42 in FIG. 6.

[0018] A method of manufacturing a thin film thermocouple on a non-planar surface of a turbine component may include the steps of: laser cutting a first mask and shaping the first mask to conform with a non-planar surface, the first mask including a pattern opening defining a first element of the thermocouple; depositing a first conductor in the pattern opening of the first mask; laser cutting a second mask and shaping the second mask to conform with the non-planar surface, the second mask

including a pattern opening defining a second element of the thermocouple; and depositing a second conductor in the pattern opening of the second mask.

[0019] While various embodiments of the present invention have been shown and described herein, it will be obvious that such embodiments are provided by way of example only. Numerous variations, changes and substitutions may be made without departing from the invention herein. Accordingly, it is intended that the invention be limited only by the spirit and scope of the appended claims.

Claims

1. An instrumented gas turbine component comprising:
 - a metal substrate (22) thermally insulated by a thermal barrier coating (20);
 - a layer of electrically insulating material (34) that maintains a resistance greater than 0.5 mega ohms above 1100°C deposited on an exposed surface of the thermal barrier coating (20), the layer of electrically insulating material (34) comprising yttrium aluminum garnet; and
 - a thermocouple (12) formed on the layer of electrically insulating material (34), the thermocouple (12) comprising a first leg (26') comprising a first pure metal and a second leg (28') making ohmic contact with the first leg (26').
2. The component of claim 1, wherein the second leg (28') comprises a second pure metal different than the first pure metal.
3. The component of claim 1, wherein the first leg (26') comprises platinum and the second leg (28') comprises palladium, rhodium or iridium.
4. The component of claim 1, wherein the second leg (28') comprises one of the group consisting of CuAlO_2 , $\text{In}_2\text{O}_3\text{-SnO}_2$, $\text{In}_2\text{O}_3\text{-SnO}_2$ doped with ZnO , Ga_2O_3 , CdIn_2O_4 , Cd_2SnO_4 , and ZnO .




Fig. 1




Fig. 2




Fig. 3




Fig. 4A




Fig. 4B




Fig. 4C




Fig. 5




Fig. 6




Fig. 7



EUROPEAN SEARCH REPORT

Application Number
EP 16 20 0727

5

10

15

20

25

30

35

40

45

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (IPC)
A,D	US 2005/198967 A1 (SUBRAMANIAN) 15 September 2005 (2005-09-15) * abstract; figures 1,10,11 * * paragraphs [0003] - [0009], [0068] - [0080] *	1-4	INV. G01K7/02 G01K7/04 F01D17/08 F01D5/28 G01K13/02
A	PRAKASH S ET AL: "Development of thin film temperature sensors for high performance turbo-jet engines", MATERIALS RESEARCH BULLETIN, ELSEVIER, KIDLINGTON, GB, vol. 23, no. 2, February 1988 (1988-02), pages 187-195, XP022794350, ISSN: 0025-5408 [retrieved on 1988-02-01] * abstract * * pages 188-190 *	1-4	
A	JIH-FEN LEI ET AL: "Advances in Thin Film Sensor Technologies for Engine Applications", NASA TECHNICAL MEMORANDUM , 29 December 2006 (2006-12-29), pages 1-6, XP002548388, Retrieved from the Internet: URL:http://web.archive.org/web/20061229011456/http://gltrs.grc.nasa.gov/reports/1997/TM-107418.pdf [retrieved on 2009-10-01] * the whole document *	1-4	TECHNICAL FIELDS SEARCHED (IPC) G01K F01D H01L
A	GB 2 439 389 A (SOUTHSIDE THERMAL SCIENCES LT) 27 December 2007 (2007-12-27) * abstract; figures * * pages 1-2 *	1-4	
The present search report has been drawn up for all claims			
Place of search Munich		Date of completion of the search 16 March 2017	Examiner Barthélemy, Matthieu
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			

 2
 EPO FORM 1503 03.82 (P04C01)

50

55

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 16 20 0727

5

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

16-03-2017

10

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2005198967 A1	15-09-2005	US 2005198967 A1	15-09-2005
		WO 2006007056 A1	19-01-2006

GB 2439389 A	27-12-2007	NONE	

15

20

25

30

35

40

45

50

55

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 61085645 B [0001]
- US 61085654 B [0001]
- US 20050198967 A1 [0010]