

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
11 June 2009 (11.06.2009)

PCT

(10) International Publication Number
WO 2009/073483 A1

- (51) International Patent Classification:
C08G 64/30 (2006.01)
- (21) International Application Number:
PCT/US2008/084713
- (22) International Filing Date:
25 November 2008 (25.11.2008)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/991,698 30 November 2007 (30.11.2007) US
- (71) Applicant (for all designated States except US): **E. I. DU PONT DE NEMOURS AND COMPANY** [US/US]; 1007 Market Street, Wilmington, Delaware 19898 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **CORBIN, David, Richard** [US/US]; 600 Swallow Lane, West Chester, Pennsylvania 19380 (US). **DICOSIMO, Robert** [US/US]; 1607 Masters Way, Chadds Ford, Pennsylvania 19317-9720 (US). **DRYSDALE, Neville, Everton** [JM/US]; 227 Welsh Tract Road, Newark, Delaware 19702 (US). **SUNKARA, Hari, Babu** [US/US]; 3 Fritze Court, Hockessin, Delaware 19707 (US).
- (74) Agent: **TANZER, Gail, D.**; E. I. du Pont de Nemours and Company, Legal Patent Records Center, 4417 Lancaster Pike, Wilmington, Delaware 19805 (US).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:
— with international search report



WO 2009/073483 A1

(54) Title: HYDROTALCITE CATALYZED POLYMERIZATION OF A TRIMETHYLENE CARBONATE

(57) Abstract: The present invention relates to the use of hydrotalcites as catalysts for the polymerization of unsubstituted or substituted trimethylene carbonate.

TITLEHYDROTALCITE CATALYZED POLYMERIZATION OF A
TRIMETHYLENE CARBONATE

5

FIELD OF THE INVENTION

The present invention relates to the use of hydrotalcites as catalysts for the polymerization of unsubstituted or substituted trimethylene carbonates.

10

BACKGROUND

Poly(trimethylene carbonate) glycols find use in a variety of materials. These diols have been prepared by the polymerization of trimethylene carbonate (TMC, 1,3-dioxan-2-one), generally using
15 catalysts containing organometallic compounds such as zinc, tin and alkali metal compounds, as described in Hyun, H.; et. al. J. Polym. Sci. Part A: Polym. Chem.: Vol.44 (2006). Also, it has been reported that TMC can be polymerized via various alcohol and HCl initiator systems, as described in Shibasaki, Y.; et al., Macromol. Rapid Commun. 20,
20 532 (1999) and Macromolecules 2000, 33, 4316. These methods necessitate the removal of the catalyst used, especially when the resulting diols are to be used in biomedical applications. Hydrotalcites can act as heterogeneous catalysts for polymerization reactions (see, for example, F. Cavani, et al., Catalysis today, 11 (1991) 173-301).

25

There exists a need to produce catalyst-free poly(1,3-propanediol carbonate) diol oligomers via polymerization of trimethylene carbonate (TMC, 1,3-dioxan-2-one).

SUMMARY OF THE INVENTION


30

One aspect of the present invention is a process for producing unsubstituted or R-substituted poly(trimethylene carbonate) glycols, comprising contacting unsubstituted or R-substituted trimethylene carbonate with a hydrotalcite catalyst in the presence of one or more solvents at a temperature of about 40 to about 120 degrees Celsius, to

form a reaction mixture, the reaction mixture comprising unsubstituted or R-substituted poly(1,3-propanediol carbonate) diol oligomers.

DETAILED DESCRIPTION

5 The present invention relates to a process to make unsubstituted or R-substituted poly(trimethylene carbonate) glycols from trimethylene carbonate (TMC, 1,3-dioxan-2-one) at elevated temperatures (generally between about 40 and 120 degrees Celsius) in the presence of a solvent utilizing a hydrotalcite as a catalyst. This
 10 reaction can be represented by the equation below:



The unsubstituted trimethylene carbonate can be derived
 15 from 1,3-propanediol, which is also known as PO3G, and available from DuPont, Wilmington, DE.

In the structure above, each R substituent is independently selected from the group consisting of H, C₁-C₂₀ alkyl, particularly C₁-C₆ alkyl, C₃-C₂₀ cyclic alkyl, C₃-C₆ cyclic alkyl, C₅-C₂₅ aryl, particularly C₅-
 20 C₁₁ aryl, C₆-C₂₀ alkaryl, particularly C₆-C₁₁ alkaryl, and C₆-C₂₀ arylalkyl, particularly C₆-C₁₁ arylalkyl, and each R substituent can optionally form a cyclic structural group with adjacent R substituents. Typically such cyclic structural groups are C₃-C₈ cyclic groups, e.g., cyclopropane, cyclobutane, cyclopentane, cyclohexane, cycloheptane,
 25 and cyclooctane. In the structure above, n is an integer of about 2 to 100, and particularly about 2 to 50; and z is an integer of about 1 to about 20, particularly about 1 to 7, more particularly about 1 to 5.

The unsubstituted or substituted poly(trimethylene carbonate) glycols can be isolated using known methods.

30 Trimethylene carbonate (TMC) is prepared by any of the various chemical or biochemical methods known to those skilled in the art.

Chemical methods for the preparation of TMC include, but are not limited to, a) reacting 1,3-propanediol with diethylcarbonate in the presence of zinc powder, zinc oxide, tin powder, tin halide or an organotin compound at elevated temperature, b) reacting 1,3-propanediol and phosgene or bis-chloroformates to produce a polycarbonate intermediate that is subsequently depolymerized using heat and, optionally, a catalyst, c) depolymerizing poly(trimethylene carbonate) in a wiped film evaporator under vacuum, d) reacting 1,3-propanediol and urea in the presence of metal oxides, e) dropwise addition of triethylamine to a solution of 1,3-propanediol and ethylchloroformate in THF, and f) reacting 1,3-propanediol and phosgene or diethylcarbonate. Biochemical methods for the preparation of TMC include, but are not limited to, a) lipase catalyzed condensation of diethylcarbonate or dimethylcarbonate with 1,3-propanediol in an organic solvent, and b) lipase-catalyzed depolymerization of poly(trimethylene carbonate) to produce TMC. The 1,3-propanediol and/or trimethylene carbonate (TMC) can be obtained biochemically from a renewable source ("biologically-derived" 1,3-propanediol).

Preferably the 1,3-propanediol used as the reactant or as a component of the reactant has a purity of greater than about 99%, and more preferably greater than about 99.9%, by weight as determined by gas chromatographic analysis

The purified 1,3-propanediol preferably has the following characteristics:

- (1) an ultraviolet absorption at 220 nm of less than about 0.200, and at 250 nm of less than about 0.075, and at 275 nm of less than about 0.075; and/or
- (2) a composition having CIELAB "b*" color value of less than about 0.15 (ASTM D6290), and an absorbance at 270 nm of less than about 0.075; and/or
- (3) a peroxide composition of less than about 10 ppm; and/or

(4) a concentration of total organic impurities (organic compounds other than 1,3-propanediol) of less than about 400 ppm, more preferably less than about 300 ppm, and still more preferably less than about 150 ppm, as measured by gas chromatography.

The process employs one or more hydrotalcite(s) as a catalyst. These materials are available from a number of sources. These catalysts are generally added to the reactants to form a reaction mixture. As shown in the examples below, conveniently small amounts of these catalysts afford high conversion rates (approaching 100 percent) within about 25 hours.

Examples of suitable hydrotalcites include Pural® MG materials, available from Sasol, Lake Charles, LA. Generally, these hydrotalcites are of the formula $Mg_{2x}Al_2(OH)_{4x+4}CO_3 \cdot nH_2O$ wherein n represents the number of water molecules associated with the magnesium aluminum compound, and is typically an integer of 1 to 4. In the compound as purchased and used in the Examples herein, n is 4.

The process of the present invention employs one or more solvents. Generally, any solvent can be used, as long as it is substantially non-reactive with the reactants and/or catalyst so that unwanted materials are not formed. Examples of solvents useful in the process described herein include but are not limited to methylene chloride, toluene and dioxane. As shown in the examples below, lower amounts of solvent generally provide for higher conversion rates.

The process described herein is carried out at elevated temperature, generally about 40 to 120 degrees Celsius. Once the reactants are added together, they may be mixed by any convenient method. The process can be done in batch, semi-batch or continuous mode, and generally take place in an inert atmosphere (i.e., under nitrogen).

Once the reactants have been contacted with the catalyst in the presence of one or more solvents, the reaction is allowed to continue for the desired time. Generally, at least 6 percent of the TMC polymerizes to give the desired poly(1,3-propanediol carbonate) diol

oligomers after about 6 hours, with greater than about 75 percent conversion achieved within about 25 hours. As shown in the examples below, 100 percent conversion can be achieved by the proper selection of solvent and catalyst, and amounts thereof.

5 Additionally, the desired degree of polymerization, n , can be achieved by selection of solvent and catalyst, and amounts thereof. As shown in the examples below, the use of toluene and hydrotalcites afford a diol oligomer with an n of approximately 6 to about 20.

10 The resulting poly(1,3-propanediol carbonate) diol oligomers can be separated from the unreacted starting materials and catalyst by any convenient means, such as filtration, including filtration after concentration.

15 The process presented in the invention allows for the degree of polymerization to be selected based on the solvent and/or catalyst chosen, and the amount of those materials used. This is advantageous as the materials resulting from the process can vary in properties including viscosity. The diol oligomers, particularly poly(1,3-propanediol carbonate) n' diol oligomers with n' less than or equal to 20, can find wide uses in products such as biomaterials, engineered
20 polymers, personal care materials, coatings, lubricants and polycarbonate/polyurethanes (TPUs).

EXAMPLES

Example 1

25 Trimethylene carbonate (10.00 g, 0.098 mol) and toluene (25 mL) were placed in four round bottom flasks equipped with stirrers, reflux condensers and under nitrogen. To each respective flask was added 1.00 g of Hydrotalcite Pural® MG30, Pural® MG50, Pural® MG70 and Pural® MG61 HT. The flasks were placed in oil baths
30 maintained at 100 °C and stirred. Aliquots were withdrawn periodically, concentrated at reduced pressure and analyzed via Proton NMR. The table below tabulates the results:

Example	Hydrotalcite (1.0 g)	Conversion (5 Hr) (%)	Conversion (22 Hr) (%)	n (22 Hr)
1A	Pural® MG30	84.63	97.97	14.20
1B	Pural® MG50	60.64	95.43	13.39
1C	Pural® MG70	97.72	98.72	12.37
1D	Pural® MG61HT	50.10	96.42	19.46

Example 2Concentration Effect

Trimethylene carbonate (10.00 g 0.098 mol) and Hydrotalcite Pural® MG70 (1.0 g) were placed in three oven dried flasks equipped with a stirrer, reflux condenser and under nitrogen. Toluene (25, 50 and 100 mL) was added separately to each flask. The flasks were placed and stirred in oil baths maintained at ~100 °C. Aliquots were withdrawn periodically, concentrated at reduced pressure and analyzed via Proton NMR. The table below tabulates the results:

10

Example	Toluene (mL)	Conversion (3 Hr) (%)	Conversion (5 Hr) (%)	Conversion (22 Hr) (%)
2A	25	88.01	97.65	97.69
2B	50	73.17	95.96	97.80
2C	100	46.24	49.11	96.77

Example 3Lower Temperature

Trimethylene carbonate (10.00 g, 0.098 mol) and toluene (25 mL) were placed in three RB flasks equipped with stirrers, reflux condensers and under nitrogen. To each repective flask was added Hydrotalcite Pural® MG70 (2.00, 3.00 and 4.00 g). The flasks were placed in oil baths maintained at 50 °C and stirred. Aliquots were withdrawn periodically, concentrated at reduced pressure and analyzed via Proton NMR. The table below tabulates the results:

20

Example	Hydrotalcite Pural® MG70 (g)	Conversion (3 Hr) (%)	n (3 Hr)	Conversion (22 Hr) (%)	n (22 Hr)
3A	2.00	98.99	9.44	98.69	7.02
3B	3.00	96.29	7.84	98.40	6.88
3C	4.00	197.44	7.03	98.93	6.32

CLAIMS

What is claimed is:

1. A process for producing unsubstituted or R-substituted poly(trimethylene carbonate) glycols, comprising contacting
5 unsubstituted or R-substituted trimethylene carbonate with a hydrotalcite catalyst in the presence of one or more solvents at a temperature of about 40 to about 120 degrees Celsius, to form a reaction mixture, the reaction mixture comprising unsubstituted or R-
10 substituted poly(1,3-propanediol carbonate) diol oligomers.
2. The process of Claim 1, wherein the hydrotalcite catalyst is of formula $Mg_{2x}Al_2(OH)_{4x+4}CO_3 \bullet nH_2O$, wherein n represents the number of water molecules associated with the magnesium aluminum
15 compound an integer of 1 to 4.
3. The process of Claim 1, wherein the solvent is substantially non-reactive.
- 20 4. The process of Claim 3, wherein the substantially non-reactive solvent is toluene.
5. The process of Claim 1, further comprising isolating the unsubstituted or R-substituted poly(trimethylene carbonate) glycols.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2008/084713

A. CLASSIFICATION OF SUBJECT MATTER INV. C08G64/30		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols) C08G		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used) EPO-Internal, WPI Data, CHEM ABS Data		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 721 305 A (ESHUIS JOHAN JAN W [NL] ET AL) 24 February 1998 (1998-02-24)	
A	ALBERTSSON A-C ET AL: "HOMOPOLYMERIZATION OF 1,3-DIOXAN-2-ONE TO HIGH MOLECULAR WEIGHT POLY(TRIMETHYLENE CARBONATE)" JOURNAL OF MACROMOLECULAR SCIENCE : PART A - CHEMISTRY, MARCEL DEKKER, NEW YORK, NY, US, vol. A29, no. 1, 1 January 1992 (1992-01-01), pages 43-54, XP001041001 ISSN: 0022-233X	
A	EP 0 600 417 A (NIPPON PAINT CO LTD [JP]; DAICEL CHEM [JP]) 8 June 1994 (1994-06-08)	
A	WO 01/64771 A (SHELL INT RESEARCH [NL]) 7 September 2001 (2001-09-07)	
<input type="checkbox"/> Further documents are listed in the continuation of Box C.		
<input checked="" type="checkbox"/> See patent family annex.		
* Special categories of cited documents :		
A document defining the general state of the art which is not considered to be of particular relevance		
E earlier document but published on or after the international filing date		
L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)		
O document referring to an oral disclosure, use, exhibition or other means		
P document published prior to the international filing date but later than the priority date claimed		
T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention		
X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone		
Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.		
& document member of the same patent family		
Date of the actual completion of the international search	Date of mailing of the international search report	
3 March 2009	11/03/2009	
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer Lohner, Pierre	

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2008/084713

Patent document cited in search report	A	Publication date	Patent family member(s)	Publication date
US 5721305	A	24-02-1998	AU 1108795 A	03-07-1995
			DE 69413710 D1	05-11-1998
			DE 69413710 T2	18-02-1999
			WO 9516723 A1	22-06-1995
			ES 2121333 T3	16-11-1998
			JP 3759952 B2	29-03-2006
			JP 9506596 T	30-06-1997
EP 0600417	A	08-06-1994	CA 2110359 A1	02-06-1994
			JP 7010920 A	13-01-1995
WO 0164771	A	07-09-2001	AU 5617701 A	12-09-2001
			CA 2401493 A1	07-09-2001
			CN 1449422 A	15-10-2003
			EP 1259559 A2	27-11-2002
			JP 2003532750 T	05-11-2003
			MX PA02008406 A	12-02-2003