

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
26 March 2009 (26.03.2009)

PCT

(10) International Publication Number
WO 2009/037103 A1

(51) International Patent Classification:
C08F 10/02 (2006.01) *F16L 9/12* (2006.01)
C08L 23/08 (2006.01)

BERTRAND, Christine [BE/BE]; 1C Rue Champtaine,
B-1325 Chaumont-Gistoux (BE).

(21) International Application Number:
PCT/EP2008/061539

(22) International Filing Date:
2 September 2008 (02.09.2008)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
07116898.3 21 September 2007 (21.09.2007) EP
07121863.0 29 November 2007 (29.11.2007) EP

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for all designated States except US*): **TOTAL PETROCHEMICALS RESEARCH FELUY** [BE/BE]; Zone Industrielle C, B-7181 Seneffe (feluy) (BE).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **BELLOIR, Pierre** [BE/BE]; 78 Rue Jules Hans, B-1420 Braine-l'alleud (BE).

Published:
— with international search report

(54) Title: PIPES FOR TRANSPORTING WATER CONTAINING CHLORAMINE

(57) Abstract: This invention is related to the preparation of polyethylene pipe resins suitable for transporting hot and cold water containing chloramine.

WO 2009/037103 A1

PIPES FOR TRANSPORTING WATER CONTAINING CHLORAMINE.

This invention is related to the preparation of polyethylene pipe resins suitable for transporting cold and/or hot water containing chloramine.

Polymer materials are frequently used for preparing pipes that are suitable for transporting fluid such as liquid or gas. The fluid may be pressurised and its temperature may range between 0 and 90 °C. These pipes were usually prepared from medium or high density monomodal or multimodal polyethylene.

For example, WO00/01765 discloses the use of a multimodal polyethylene resin having a density of 0.930 to 0.965 g/cc and a MI5 of from 0.2 to 1.2 dg/min for transporting cold, pressurised water.

The transport of hot water requires other types of resin than conventional polyethylene as the service life of a typical polyethylene pipe decreases by about 50 % when the temperature of the transported fluid increases by 10 °C and as it is subject to stress cracking at elevated temperature.

Several multimodal polyethylene resins were disclosed for the transport of hot fluid. For example, EP-A-1448702 discloses a polyethylene resin useful for the preparation of hot water pipes. That polyethylene resin is multimodal with a high molecular weight fraction having a density of at least 0.920 g/cc and a low molecular weight fraction. Its density ranges between 0.921 and 0.950 g/cc. Its time to failure at a temperature of 95 °C and at a pressure of 3.6 MPa is of at least 165 h and its modulus of elasticity is of at most 900 MPa.

EP-A-1425344 also discloses a multimodal polyethylene resin that can be used for hot water pipes. It has a density of from 0.925 to 0.950 g/cc and a MI2 of from 0.1 to 5 dg/min. It comprises a high molecular weight fraction having a density of from 0.910 to 0.935 g/cc and a MI2 of at most 1 dg/min and a low molecular weight fraction having a density of from 0.945 to 0.965 g/cc and a MI2 of from 2 to 200 dg/min.

Water for domestic use also transports disinfectants such as for example chlorine dioxide. The service life of pipes prepared from the prior art polyethylene resins was substantially decreased by the addition of chloramine.

Cross-linked polyethylene resins have also been used to improve the performances of the pipes. The cross linking was achieved either chemically with silanes or peroxides or physically by irradiation.

WO2005/056657 discloses the use of a high density polyethylene resin comprising a combination of at least two antioxidant additives to prepare pipes for transporting water containing chlorine.

There is thus a need for polyethylene pipes that are able to transport hot or cold water containing such aggressive chemical compound that do not require the addition of specific combinations of antioxidants.

It is an aim of the present invention to prepare polyethylene pipe resins suitable for transporting hot or cold water containing chloramine.

It is also an aim of the present invention to prepare polyethylene pipe resins that have good mechanical properties.

It is another aim of the present invention, to prepare polyethylene pipe resins that can be processed easily.


Any one of these aims is at least partially fulfilled by the present invention.

Accordingly, the present invention discloses the use for transporting water containing chloramine of a pipe characterised in that is prepared from a polyethylene resin produced by one or more single site catalyst systems.

The pipe of the present invention is preferably prepared from a bi- or multi-modal polyethylene resin produced either by two or more single site catalyst systems in a single reactor or by a single site catalyst system in two serially connected reactors,

wherein at least one of the single site catalyst systems is a metallocene catalyst system comprising a bisindenyl or a bis tetrahydroindenyl catalyst component of formula $R'' (Ind)_2 MQ_2$ wherein Ind is a substituted or unsubstituted indenyl or tetrahydroindenyl group, R'' is a structural bridge imparting stereorigidity to the complex, M is a metal Group 4 of the Periodic Table and Q is a hydrocarbyl having from 1 to 20 carbon atom or a halogen.

The one or more single site catalyst systems are preferably metallocene catalyst systems and more preferably comprise a bridged bis-indenyl or bistetrahydro-indenyl catalyst component described by general formula



wherein Ind is a substituted or unsubstituted indenyl or tetrahydroindenyl group, R'' is a structural bridge imparting stereorigidity to the complex, M is a metal Group 4 of the Periodic Table and Q is a hydrocarbyl having from 1 to 20 carbon atom or a halogen.

If Ind is an indenyl group it is preferably unsubstituted or substituted at position 4 with a bulky substituent and at position 2 with a small substituent. A bulky substituent is at least as bulky as t-butyl. A small substituent is preferably methyl.

If Ind is a tetrahydroindenyl group, it is preferably unsubstituted.

M is preferably Ti or Zr, more preferably Zr.

Each Q is preferably selected from aryl, alkyl, alkenyl, alkylaryl or arylalkyl having at most 6 carbon atoms, or halogen. More preferably both Q are the same and are chlorine.

Structural bridge R'' is selected from C_1 - C_4 alkylene radical, a dialkyl germanium or silicon or siloxane, or an alkyl phosphine or amine radical, which bridge is substituted or unsubstituted. Preferably it is ethylene, isopropylidene, dimethylsilyl or diphenyl.

The most preferred catalyst component is ethylene bistetrahydroindenyl zirconium dichloride. The metallocene catalyst component used in the present invention can be prepared by any known method. A preferred preparation method is described in J. Organomet. Chem. 288, 63-67 (1985).

The catalyst system also comprises an activating agent having an ionising action and optionally an inert support. The activating agent is preferably selected from aluminoxane or boron-containing compound and the inert support is preferably selected from mineral oxide, more preferably, silica. Alternatively, the activating agent is a fluorinated activating support.

The polyethylene resin that can be used in the present invention is either monomodal or bi- or multi-modal and is prepared by any method known in the art, with the restriction that the catalyst system comprises at least one single site component. Its density preferably ranges from 0.915 to 0.965 g/cc.

In a more preferred embodiment according to the present invention the polyethylene resin is a bi- or multi-modal resin prepared in two or more serially connected loop reactors. It comprises a high molecular weight (HMW), low density fraction and a low molecular weight (LMW), high density fraction.

The high molecular weight, low density fraction has a density of at least 0.908 g/cc, preferably of at least 0.912 g/cc and of at most 0.928 g/cc, more preferably of at most 0.926 g/cc. Most preferably it is of about 0.922 g/cc. It has a high load melt index HLMI of at least 2 dg/min, more preferably of at least 5 dg/min and most preferably of at least 7 dg/min and of at most 12 dg/min, more preferably of at most 10 dg/min. Most preferably, it is of 8 to 9 dg/min. The melt index MI2 is of from 0.05 to 2 dg/min, more preferably of from 0.1 to 0.5 dg/min and most preferably of about 0.2 dg/min.

The low molecular weight, high density fraction has a density of at least 0.930 g/cc, more preferably of at least 0.940 g/cc, and of at most 0.975 g/cm³, more preferably of at most 0.962 g/cc. Most preferably it is of about 0.945 to 0.955 g/cc. It has a melt index MI2 of at least 0.5 dg/min, more preferably of at least 1 dg/min, and of at most

10 dg/min, more preferably of at most 6 dg/min. Most preferably, it is of from 2 to 3 dg/min.

The final resin comprises 50 to 60 wt% of HMW fraction, preferably from 50 to 55 wt%, more preferably from 52 to 53 wt% and from 40 to 50 wt% of LMW fraction, preferably from 45 to 50 wt% and most preferably from 47 to 48 wt%. It has a broad or multimodal molecular weight distribution of from 2 to 5, a density of from 0.930 to 0.949 g/cc and a melt index MI2 of from 0.3 to 1 dg/min. The most preferred polyethylene resin according to the present invention has a density of about 0.935 g/cc, a melt index MI2 of 0.6 dg/min and a polydispersity of about 3.

The molecular weight distribution is fully described by the polydispersity index D defined by the ratio M_w/M_n of the weight average molecular weight M_w to the number average molecular weight M_n as determined by gel permeation chromatography (GPC).

The density is measured according to the method of standard test ASTM 1505 at a temperature of 23 °C. The melt index and high load melt indices are measured by the method of standard test ASTM D 1238 respectively under a load of 2.16 kg and 21.6 kg and at a temperature of 190 °C.

The polyethylene resins according to the invention can be prepared by any method suitable therefore. They can be prepared by physically blending the high density and the low density polyethylene fractions, prepared separately, or they can be prepared by polymerising ethylene in the presence of a mixture of catalysts. Preferably, the high density and low density fractions are produced in two serially connected loop reactors with the same catalyst system. In such a case, the LMW, high density fraction is preferably prepared in the first reactor, so that the HMW, low density fraction is prepared in the presence of the high density fraction. Preferably, the same catalyst system is used in both steps of the cascade polymerisation process to produce a chemical blend of the high and low molecular weight fractions. The catalyst system may be employed in a solution polymerisation process, which is homogeneous, or in a slurry process, which is heterogeneous or in a gas phase

process. Preferably a slurry process is used. The most preferred polymerisation process is carried out in two serially connected slurry loop reactors.

In a preferred arrangement, the product of a first cascade reaction zone, including the olefin monomer, is contacted with the second co-reactant and the catalyst system in a second cascade reaction zone to produce and mix the second polyolefin with the first polyolefin in the second reaction zone. The first and second reaction zones are conveniently interconnected reactors such as interconnected loop reactors. It is also possible to introduce into the second reaction zone fresh olefin monomer as well as the product of the first reaction zone.

Because the second polyolefin is produced in the presence of the first polyolefin a multimodal or at least bimodal molecular weight distribution is obtained.

In one embodiment of the invention, the first co-reactant is hydrogen, to produce the LMW fraction and the second co-reactant is the comonomer to produce the HMW fraction. Typical comonomers include hexene, butene, octene or methylpentene, preferably hexene.

In an alternative embodiment, the first co-reactant is the comonomer, preferably hexene. Because the metallocene catalyst components of the present invention exhibit good comonomer response as well as good hydrogen response, substantially all of the comonomer is consumed in the first reaction zone in this embodiment. Homopolymerisation takes place in the second reaction zone with little or no interference from the comonomer.

The temperature of each reactor may be in the range of from 60°C to 110°C, preferably from 70°C to 90°C.

The present invention further provides the use of such a polyethylene resin for the manufacture of pipes for cold or hot water, especially for hot water containing chloramine.

The polyethylene resins according to the invention, having such a specific composition, molecular weight and density, can lead to a marked improvement of the processing properties when the resin is used as a pipe resin, while conserving or improving mechanical behaviour as compared to known pipe resins.

In particular, the polyethylene resins in accordance with the invention have impact resistance and slow crack resistance at least equivalent, often higher than current available pipe resins.

The resins of the invention are endowed with excellent rheological behaviour.

The resin in accordance with the invention is characterised by a high shear-thinning behaviour. This means good injection-moulding capability for the resins when used to produce injection-moulded pipes and pipe fittings.

Generally, the pipes are manufactured by extrusion or by injection moulding, preferably by extrusion in an extruder. The pipes made of the multimodal polyethylene resin according to the present invention may be single layer pipes or be part of multilayer pipes that include further layers of other resins.

In another embodiment according to the present invention, the pipe is a multilayer pipe comprising at least one layer of polyethylene pipe resin prepared by any method known in the art and at least one other layer of polyethylene resin prepared with a single site catalyst system, wherein said other polyethylene resin may or may not be a pipe resin.

The pipe resin may also be compounded, for example with black or blue pigments.

The pipes of the present invention offer an excellent resistance to corrosion when used for transporting hot or cold water containing chloramine. The water temperature ranges from 0 to 90 °C and the amount of chlorine dioxide in the water is of from the smallest detectable amount, typically of from 0.1 mg/L, up to the existing upper tolerance of 4 mg per litre of water, typically it is of 0.3 to 0.6 mg/L. It must be noted

that the pipes according to the present invention could sustain higher percentage of chlorine dioxide than the upper limit of 4 mg/L tolerated for domestic water.

Examples.

Three different resins have been formed into pipes that were tested for transporting water containing chloramine.

Resin R1, according to the present invention, was prepared with ethylene bistetrahydroindenyl zirconium dichloride catalyst component in a double slurry loop reactor. The density was of 0.935 g/cc and the melt flow rate MI2 was of 0.7 dg/min. It was additivated with black pigment resulting in a density of 0.945 g/cc.

Resin R2 is a commercial resin sold by Total Petrochemicals under the name XS10B. It was prepared with a Ziegler-Natta catalyst system.

Resin R3 is a commercial resin sold by Total Petrochemicals under the name 3802B. It was prepared with a chromium-based catalyst system.

Resins R2 and R3 were also additivated with the same amount of black pigments as resin R1.

These pipes were tested following the standard procedures of JANALAB under the following conditions:

- pH : 6.8
- chloramine: 4 ppm
- fluid temperature : 80 °C
- stress : 1.9 MPa
- flow rate : 0.1 USGPM

The results of time to failure are summarised in Table I

TABLE I.

Resin	Average time to failure (h)
R1	> 10000
R2	7500
R3	3500

As can be seen from Table I the resin according to the present invention resists for a longer time than those prepared with Ziegler-Natta or chromium catalyst systems.

CLAIMS.

1. Use for transporting water containing chloramine of a pipe characterised in that it is prepared from a bi- or multi-modal polyethylene resin produced either with two or more single site catalyst systems in a single reactor or with a single site catalyst system in two serially connected reactors, wherein at least one of the single site catalyst systems is a metallocene catalyst system comprising a bisindenyl or a bis tetrahydroindenyl catalyst component of formula $R''(Ind)_2MQ_2$ wherein Ind is a substituted or unsubstituted indenyl or tetrahydroindenyl group, R'' is a structural bridge imparting stereorigidity to the complex, M is a metal Group 4 of the Periodic Table and Q is a hydrocarbyl having from 1 to 20 carbon atom or a halogen.
2. The use of claim 1 or claim 2 wherein the polyethylene resin has a density of from 0.915 to 0.965 g/cc.
3. The use of claim 1 or claim 2 wherein the bi- or multi-modal resin is prepared by physical blending.
4. The use of claim 1 or claim 2 wherein the bi- or multi-modal resin is prepared by chemical blending in a solution polymerisation process or in a slurry polymerisation process or in a gas phase process.
5. The use of claim 4 wherein the bimodal resin is prepared in two or more serially connected slurry loop reactors.
6. The use of any one of the preceding claims wherein the bimodal resin has a density of from 0.930 to 0.949 g/cc and a melt index MI2 of from 0.3 to 1 dg/min and comprises a high molecular weight, low density fraction having a density of from 0.908 to 0.928 g/cc and a high load melt index HLMI of from 2 to 12 dg/min and a low molecular weight, high density fraction having a density of from 0.930 to 0.975 g/cc and a melt index MI2 of from 0.5 to 10 dg/min.

7. The use of any one of the preceding claims wherein the bimodal resin comprises from 50 to 60 wt% of HMW fraction and 40 to 50 wt% of LMW fraction.
8. The use of any one of the preceding claims wherein the pipe is a single layer pipe.
9. The use of any one of claims 1 to 7 wherein the pipe is a multi-layer pipe wherein at least one of the layers is prepared with the resin of the invention.
10. The use of any one of the preceding claims wherein the amount of chloramine is of from the smallest detectable amount, up to the existing upper tolerance of 4 mg per litre of water.
11. The use of any one of the preceding claims wherein the water temperature is of from 0 to 90 °C.

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2008/061539

A. CLASSIFICATION OF SUBJECT MATTER

INV. C08F10/02 C08L23/08 F16L9/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C08F C08L F16L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 2005/228139 A1 (LEE KI S [KR] ET AL LEE KI SOO [KR] ET AL) 13 October 2005 (2005-10-13) paragraphs [0003], [0005], [0012], [0015], [0017], [0019], [0021], [0022], [0064], [0071] claims 1,2,5,6,8	1-11
Y	EP 1 650 230 A (TOTAL PETROCHEMICALS RES FELUY [BE]) 26 April 2006 (2006-04-26) paragraphs [0008], [0038], [0039], [0101], [0102]	1-11
	----- -/-- -----	

☒ Further documents are listed in the continuation of Box C.

☒ See patent family annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

28 October 2008

Date of mailing of the international search report

05/11/2008

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Lippert, Sigrid

INTERNATIONAL SEARCH REPORT

International application No

PCT/EP2008/061539

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 03/020821 A (DOW GLOBAL TECHNOLOGIES INC [US]; SCHRAMM DETLEF [CH]; QUACK WOLFGANG) 13 March 2003 (2003-03-13) claims 1-10 page 1, line 1 - page 2, line 28 page 7, line 7 - line 15 -----	1-11
A	EP 1 764 390 A (UNION CARBIDE CHEM PLASTIC [US]) 21 March 2007 (2007-03-21) the whole document -----	1-11
A	WO 2005/056657 A (DOW GLOBAL TECHNOLOGIES INC [US]; HO THOI H [US]; CHAM PAK-MENG [US];) 23 June 2005 (2005-06-23) the whole document -----	1-11
A	WO 99/33752 A (KAAS POVL [DK]) 8 July 1999 (1999-07-08) page 1, line 12 - line 17 -----	1-11

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/EP2008/061539

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 2005228139	A1	13-10-2005	CN 1906220 A	31-01-2007
			EP 1732958 A1	20-12-2006
			JP 2007517087 T	28-06-2007
			WO 2006001588 A1	05-01-2006
			KR 20050098663 A	12-10-2005
EP 1650230	A	26-04-2006	WO 2006045737 A1	04-05-2006
WO 03020821	A	13-03-2003	AT 287924 T	15-02-2005
			BR 0212631 A	24-08-2004
			CA 2457430 A1	13-03-2003
			CN 1545536 A	10-11-2004
			DE 60202780 D1	03-03-2005
			DE 60202780 T2	30-06-2005
			EP 1425344 A1	09-06-2004
			ES 2232767 T3	01-06-2005
			JP 2005501951 T	20-01-2005
			KR 20080068916 A	24-07-2008
			MX PA04001928 A	23-07-2004
EP 1764390	A	21-03-2007	NONE	
WO 2005056657	A	23-06-2005	AR 047136 A1	11-01-2006
			AU 2004297227 A1	23-06-2005
			BR PI0417262 A	06-03-2007
			CA 2547157 A1	23-06-2005
			CN 101068868 A	07-11-2007
			EP 1692222 A2	23-08-2006
			MX PA06006271 A	23-08-2006
WO 9933752	A	08-07-1999	AT 209611 T	15-12-2001
			AU 1869399 A	19-07-1999
			CA 2316222 A1	08-07-1999
			DE 69802716 D1	10-01-2002
			DE 69802716 T2	08-05-2002
			DK 1042237 T3	02-04-2002
			EP 1042237 A1	11-10-2000
			NO 20003376 A	25-08-2000
			US 6451209 B1	17-09-2002