

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 520 465 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:

27.12.1996 Bulletin 1996/52

(51) Int Cl.⁶: **C22C 29/16**

(21) Application number: **92110770.2**

(22) Date of filing: **26.06.1992**

(54) **Sintered alloy of golden color**

Goldfarbige gesinterte Legierung

Alliage fritté de couleur dorée

(84) Designated Contracting States:
CH DE LI

(30) Priority: **27.06.1991 JP 157204/91**
27.06.1991 JP 157205/91
27.06.1991 JP 157206/91
09.08.1991 JP 200339/91
11.05.1992 JP 117659/92

(43) Date of publication of application:
30.12.1992 Bulletin 1992/53

(73) Proprietor: **KYOCERA CORPORATION**
Yamashina-ku Kyoto-shi (JP)

(72) Inventors:
• **Nagato, Yoshio, c/o Kyocera Corporation**
Kokubu-shi, Kagoshima-ken (JP)
• **Hamashima, Hiroshi, c/o Kyocera Corporation**
Sendai-shi, Kagoshima-ken (JP)

(74) Representative: **Alber, Norbert et al**
Patent- und Rechtsanwälte
Hansmann, Vogeser, Dr. Boecker,
Alber, Dr. Strych, Liedl
Albert-Rosshaupter-Strasse 65
81369 München (DE)

(56) References cited:
US-A- 4 589 917

- **CHEMICAL ABSTRACTS**, vol. 99, no. 14, October 03, 1983, Columbus, Ohio, USA **TOSHIBA TUNGALOY CO.** "Ornamental golden-colored titanium monoxide-base composites" page 252, column 2, abstract-no. 109 451t; & Jpn. Kokai Tokkyo Koho JP 58 91,145
- **CHEMICAL ABSTRACTS**, vol. 95, no. 2, July 13, 1981, Columbus, Ohio, USA **MITSUBISHI METAL CORP.** "Ornamental hard sintered alloys" page 250, column 2, abstract-no. 11 128k; & Jpn. Kokai Tokkyo Koho 81 09, 352
- **CHEMICAL ABSTRACTS**, vol. 80, no. 16, April 22, 1974, Columbus, Ohio, USA **YONEYA KATSUTOSHI et al.** "Hard alloy for ornament" page 233, column 2, abstract-no. 86 647c; & Japan. Kokai 73 94, 607

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 520 465 B1

Description

BACKGROUND OF THE INVENTION

5 The present invention relates to a sintered alloy which exhibits gold color and is used for ornamental purposes.

As materials for ornamental purposes exhibiting gold color, there have heretofore been used a variety of metals such as pure gold, alloys thereof, brass and the like, as well as those metals of which the surfaces are plated with gold. However, these metals all have small hardnesses and get scratched on the surfaces or cracked when they come into contact with hard substances. In order to prevent the surfaces from being scratched, furthermore, a variety of metals
10 have been coated with hard layers that exhibit gold color. However, these layers have different properties and tend to be peeled off because of their insufficient strength.

In order to overcome the above-mentioned defects in recent years, therefore, there have been used in many cases sintered alloys of gold color obtained by bonding a metal such as nickel or cobalt to the nitride of a metal such as titanium nitride (Japanese Laid-Open Patent Publication No. 58335/1990).

15 However, the aforementioned gold-color sintered alloys are usually sintered poorly. In order to improve such sintering property, therefore, the sintering must be carried out by adding various additives such as carbides or carbonitrides of elements of the Groups 4a, 5a and 6a of periodic table.

In fact, however, such additives cause the color tone of the sintered products to greatly change from their gold color into other colors. In particular, when carbides or carbonitrides of elements of the Groups 4a, 5a and 6a of periodic
20 table are added, the color tone of the sintered product changes into a red copper color making it difficult to obtain a vivid and favorable gold color, though the sintering property is improved.

Furthermore, an increase in the amounts of additives results in a remarkable increase in the dropped-out particles of the sintered product during the grinding and an increase in the voids in the sintered product, causing the strength and hardness to decrease and making it difficult to obtain a mirror surface despite the effort of polishing.

25 Moreover, an increase in the amounts of additives results in a decrease in the corrosion resistance against the human sweat and sea water.

Further, the sintered products exhibit poor anti-chipping property, easily develop dropped-out particles at the time of machining for making ornaments, and make it difficult to carry out sharp-edge machining.

The object of the present invention therefore is to provide a sintered alloy of gold color having vivid and favorable
30 gold color tone, high strength and hardness, excellent corrosion resistance, excellent anti-chipping property, and which permits the sharp-edge machining to be easily carried out.

According to the present invention, there is provided a sintered alloy of gold color comprising a nitride of titanium or a carbonitride of titanium and metals, wherein titanium is contained in an amount of 55 to 75% by weight with respect to the whole amount, metals of the iron family and elements of the Group 6a of periodic table including at least chromium
35 are contained in an amount of 3 to 30% by weight with respect to the whole amount, and the remainder being non-metallic elements consisting of nitrogen or nitrogen and carbon, and wherein the ratio of carbon with respect to said non-metallic elements is not greater than 10% by weight, and the ratio of chromium in the metal elements excluding titanium is not smaller than 35% by weight.

According to a preferred embodiment of the present invention, there is provided a sintered alloy in which metals
40 of the iron family and elements of the Group 6a of periodic table including at least chromium are contained in an amount of 10 to 30% by weight with respect to the whole amount, the ratio of carbon is not greater than 0.7% by weight with respect to the whole amount, and the brightness index L^* and chromaticness indexes a^* , b^* in the $L^*a^*b^*$ color display system stipulated under JIS Z 8730 are $L^* \geq 10$, $a^* \leq +0.4$ and $b^* \geq +8.0$.

According to another preferred embodiment of the present invention, there is provided a sintered alloy having an
45 average crystalline particle size of not greater than $3\ \mu\text{m}$.

According to the present invention, metals of the iron family include nickel, iron and cobalt, elements of the Group 6a of periodic table include chromium, molybdenum and tungsten, and non-metallic elements include nitrogen and carbon.

Titanium is contained in an amount of 55 to 75% by weight with respect to the whole amount. If this amount is
50 smaller than 55% by weight, the gold color tone becomes faint. If this amount becomes greater than 75% by weight, on the other hand, the sintering property is lost and the strength decreases. It is desired that titanium is contained in an amount of 60 to 70% by weight and, particularly, in an amount of 60 to 68% by weight. In the sintered product, titanium exists chiefly in the forms of TiN and TiCN that constitute hard phases.

Metals of the iron family and elements of the Group 6a of periodic table are contained in an amount of 3 to 30%
55 by weight with respect to the whole amount. This is because, if this amount is smaller than 3% by weight, it becomes difficult to carry out the sintering and besides the sintered product loses strength. If the amount exceeds 30% by weight, on the other hand, the hardness of the sintered product is remarkably lost and the corrosion resistance is lost, too.

In order to further improve the color tone of the sintered alloy, it is desired that the metals are contained in an

amount of 10 to 30% by weight and, particularly, in an amount of 12 to 23% by weight. The metals of the iron family form a binder phase in the sintered product, and elements of the Group 6a of periodic table form a hard phase or a bonding phase. Concretely speaking, it is desired that the metals of the iron family exist at a ratio of 5 to 18% by weight and the elements of the Group 6a of periodic table exist at a ratio of 3 to 12% by weight.

The ratio of carbon with respect to the non-metallic elements is selected to be not greater than 10% by weight. This is because if this ratio is greater than 10% by weight, the color tone tends to become reddish rather than the gold color, and the color changes from red copper color into greyish brown with an increase in the ratio of carbon. In order to maintain vivid and favorable gold color tone, therefore, the ratio of carbon with respect to the non-metallic elements must be selected to be not greater than 10% by weight. In particular, it is desired that the ratio of carbon with respect to the non-metallic elements is not greater than 8% by weight.

According to a particularly preferred embodiment of the present invention, the ratio of carbon is selected to be not greater than 0.7% by weight with respect to the whole amount. If this ratio is greater than 0.7% by weight with respect to the whole amount, the chromaticness indexes a^* and b^* become $a^* > +0.4$ and $b^* < +8.0$, and the color tone tends to become reddish from its original gold color, and the color changes from red copper color into greyish brown with an increase in the ratio of carbon. In particular, the chromaticness index a^* changes with a change in the ratio of carbon. In order to maintain vivid and favorable gold color tone, therefore, the ratio of carbon must be not greater than 0.7% by weight with respect to the whole amount. In particular, it is desired that the ratio of carbon is not greater than 0.5% by weight with respect to the whole amount. In order that the amount of carbon in the sintered product is not greater than 0.7% by weight, it is recommended that the starting powder of carbide should be added in an amount as small as possible. Or, when the carbide is added in a large amount, oxides such as TiO_2 and the like should be added, such that carbon in the carbide is diffused during the baking.

The ratio of chromium in the metal elements excluding titanium is larger than 35% by weight and, particularly, larger than 40% by weight. If this ratio is smaller than 35% by weight, voids easily develop in the sintered product, and dropped-out particles develop remarkably during the machining such as grinding and polishing causing the strength to decrease and the corrosion resistance to decrease, too. Further, if the ratio of chromium is smaller than 35% by weight, the brightness index L in the $L^*a^*b^*$ color display system tends to be decreased. If the ratio of chromium with respect to the bonded metals in the sintered product is not smaller than 35% by weight, on the other hand, the sintering property is improved and the above-mentioned problems do not take place. This is attributed to that the addition of chromium improves wettability between the hard phase and the binding phase.

It is desired that the sintered alloy of gold color has an average crystalline particle size of not greater than $8\ \mu m$ and, particularly, not greater than $3\ \mu m$. If the particle size is greater than $8\ \mu m$, cracks develop remarkably and chipping develops during the grinding to such an extent that makes it difficult to carry out the sharp-edge machining. If the average crystalline particle size is not greater than $3\ \mu m$, on the other hand, it is allowed to easily carry out the sharp-edge machining. This is attributed to that the ceramic material is brittle and is weak against impact and easily develops cracks. If the average crystalline particle size is not greater than $3\ \mu m$, however, reduced stress acts upon each particle in case stress is produced by the grinding and the dropped-out particle takes place little. The remainder inevitably includes small amounts of impurities.

The sintered alloy of gold color of the present invention is obtained by mixing a nitride of titanium and a carbonitride of titanium as starting powders together with metals of the iron family and elements of the Group 6a of periodic table. The mixture is then pulverized in an organic solvent such as acetone for a predetermined period of time. Then, an organic binder is added thereto in a predetermined amount, and the mixture is molded into a desired shape by the press molding, injection molding or extrusion molding. The molded article is then placed in a non-oxidizing atmosphere heated at a temperature of $250^\circ C$ to $500^\circ C$ to remove the binder therefrom, followed by baking at a predetermined temperature. For instance, a nitride of titanium and a carbonitride of titanium having a particle size of 0.5 to $3.0\ \mu m$, nickel and cobalt having a particle size of 0.1 to $1.0\ \mu m$ which are metals of the iron family, as well as chromium, WC, Cr_3C_2 and $Mo(Mo_2C)$ having a particle size of 1.0 to $10.0\ \mu m$ which are elements of the Group 6a of periodic table, are weighed and mixed, and are pulverized in an organic solvent such as acetone for about 20 to 100 hours and, particularly, for 48 to 72 hours. The mixture is then molded into a desired shape by the press molding, injection molding or extrusion molding. The molded article is placed in a non-oxidizing atmosphere at a predetermined temperature to remove the organic binder, followed by vacuum-baking in a vacuum heating furnace at a predetermined temperature to obtain the sintered alloy of gold color. It is desired that the vacuum-baking is carried out for 0.5 to 5 hours. Here, tungsten and chromium are added as starting carbide powders but do not stay as metallic chromium or metallic tungsten in the form of solid solution in the bonded metals, or do not stay in the form of solid solution in TiN or TiCN, or do not exist in the form of WC or Cr_3O_2 in the step of baking.

The baking is carried out at a temperature of 1300° to $1800^\circ C$ in an atmosphere of a degree of vacuum of 10^{-1} to 10^{-4} Torr or in various atmosphere of reduced pressure or without pressure. The baking is continued for 0.5 to 5 hours though it may vary depending upon the size of the sample. After the baking, the surface of the sintered product is polished like a mirror surface using a diamond paste or the like to obtain vivid and favorable gold color with luster.

According to the present invention as described above in detail, there is obtained a sintered alloy of gold color having practically sufficient hardness and strength, excellent corrosion resistance, and mirror-like surface of elegant gold color owing to markedly improved sintering property, and which enables sharp-edge machining to be easily carried out, without permitting corrosion or scratches to develop even after used for extended periods of time. Therefore, the sintered alloy can be used for ornamental purposes such as of watch cases, watch bands, necklaces, brooches, memorial medals and buttons, and for cutlery, fishing tools and printing tools.

Example 1

TiN having a particle size of 2 μm , TiCN having a particle size of 2 μm , chromium having a particle size of 3 μm , molybdenum having a particle size of 4 μm , nickel having a particle size of 1 μm and cobalt having a particle size of 1 μm were used as starting material powders, and were weighed and mixed in a manner that the ratios of amount of the metals in the final sintered products were as shown in Table 1. The mixtures were pulverized in an organic solvent such as acetone for about 68 hours and, after paraffin was added thereto in an amount of 4 to 5% by weight, were molded under the application of pressure of 1.5 tons/cm² into a desired shape. The molded articles were placed in a non-oxidizing atmosphere heated at a temperature of 300°C to remove the organic binder, and were then baked in vacuum in a vacuum heating furnace having a degree of vacuum of 10⁻² Torr at a temperature of 1450°C for one hour. Compositions of the thus obtained final sintered products were analyzed by the ICP emission spectroanalysis. The results were as shown in Table 1.

Table 1

Sample No.	Analytical ratio of sintered product (% by wt.)						Ratio of chromium (% by wt.)	
	Ti	Group 6a	Iron+family metal		C	N		
#1	75.3	Mo	2.7	Ni	3.0	1.2	17.8	0.0
#2	71.2	Cr	2.7	Co	1.0	0.3	20.8	35.1
				Ni	4.0			
3	70.0	Cr	4.0	Co	1.0	0.3	19.7	40.0
				Ni	5.0			
#4	69.7	Cr	3.0	Ni	6.0	0.8	19.5	30.0
				Fe	1.0			
5	68.1	Cr	4.7	Ni	6.0	0.3	19.9	40.2
		Mo	1.0					
6	68.0	Cr	5.0	Ni	7.0	0.4	19.6	41.7
7	67.5	Cr	5.0	Ni	7.5	0.2	19.8	40.0
8	65.8	Cr	7.0	Ni	7.0	0.6	19.6	50.0
#9	65.8	Cr	3.0	Ni	7.0	0.2	19.2	20.0
				Co	5.0			
#10	65.8	Cr	4.7	Co	6.0	1.3	19.0	34.3
				Fe	3.0			
11	65.8	Cr	9.5	Ni	5.0	0.5	19.2	65.6
#12	62.1	Cr	1.0	Ni	20.0	0.8	16.1	4.8
13	61.0	Cr	8.7	Ni	15.0	0.7	18.6	36.7
14	60.0	Cr	10.0	Ni	10.4	0.4	17.2	44.6
		Mo	2.0					
15	55.7	Cr	9.8	Ni	18.0	0.6	15.9	35.3
#16	54.7	Cr	7.3	Ni	20.0	0.9	17.1	26.7
#17	53.5	Cr	15.0	Ni	15.0	0.8	15.7	50.0

Samples marked with # lie outside the scope of the invention.

The surfaces of the sintered products were ground and polished like a mirror. The samples were then tested for their color tone, bending strength, Vickers' hardness (Hv), anti-chipping property and corrosion resistance. The bending strength was measured in accordance with the three-point bending test stipulated under JIS R 1601, the Vickers' hardness was measured in compliance with the testing method of JIS Z 2244, and the anti-corrosion testing was carried out by using human sweat (pH 4.7) in compliance with the standards of the ISO (International Standardization Organ-

ization) as a corrosive solution, immersing the lower half of the mirror surface-polished sample in the human sweat maintained at 40°C + 2°C for 24 hours, and the conditions of the polished surfaces of the samples after immersed were observed. The color tone was measured and evaluated by using an L*a*b* optical color difference meter (manufactured by Minolta Co.), i.e., by using a high-functional-color color difference meter (in compliance with JIS Z 8722) of the 45° ring illumination vertical light-receiving system. The anti-chipping property was evaluated in terms of a maximum chipping width of when the mirror surface-polished sample was creep-ground. The results were as shown in Table 2 and 3.

Table 2

Sample No.	Color difference		
	L* (Brightness)	a* (+red, -green)	b* (+yellow, -blue)
#1	4.2	+0.8	+27.4
#2	9.0	-0.4	+18.1
3	24.0	-0.3	+15.0
#4	18.2	+0.6	+12.4
5	20.4	-0.4	+16.2
6	39.0	-0.1	+12.6
7	33.8	-2.0	+13.7
8	40.0	+0.2	+11.8
#9	8.9	-2.0	+9.4
#10	8.1	+1.3	+9.6
11	45.1	-0.6	+9.9
#12	7.0	+0.6	+5.2
13	12.4	+0.4	+8.0
14	34.3	-0.2	+8.4
15	30.5	+0.1	+8.0
#16	10.8	+0.5	+7.2
#17	21.5	+0.6	

The samples marked with # lie outside the scope of the invention.

Table 3

Sample No.	Deflective strength (kg/mm ²)	Vickers' hardness	Corrosion resistance	Anti-chipping property	Color tone	remarks
#1	30	1500	Δ	○	-	poorly sintered poor mirror surface
#2	55	1250	○	○	-	
3	90	1380	○	○	gold color	
#4	90	1050	○	Δ	orange	
5	95	1350	○	○	gold color	
6	120	1150	○	○	gold color	poor mirror surface
7	105	1050	○	○	gold color	
8	115	1100	○	○	gold color	
#9	105	1050	Δ	Δ	-	
#10	90	1000	Δ	X	reddish gold color	
11	125	1050	○	○	gold color	poorly sintered
#12	50	940	X	X	-	

Table 3 (continued)

Sample No.	Deflective strength (kg/mm ²)	Vickers' hardness	Corrosion resistance	Anti-chipping property	Color tone	remarks
13	135	1050	○	○	gold color	
14	115	1100	○	○	gold color	
15	140	980	○	○	gold color	
#16	70	850	X	○	orange	
#17	120	970	Δ	○	reddish white	

Samples marked with # lie outside the scope of the invention.

Sample numbers indexed with marks in Tables 1, 2 and 3 indicate being outside of the scope of the invention. As to the results of anticorrosion tests circle mark ○ represent no discoloration, triangular mark Δ represents discoloration and cross mark X represents discoloration and corrosion. As to the antichipping property, circle mark ○ indicate good for sharp edge working, triangular mark Δ indicates not suitable for sharp edge working as sporadic chippings in sizes of 1 to 5 μm appear and cross mark X indicates unfit for sharp edge working as chippings in sizes of larger than 5 μm occur in a great number.

It will be understood from the above Tables 1, 2 and 3 that the samples that lie within the scope of the present invention have very excellent bending strength, Vickers' hardness, corrosion resistance and anti-chipping property, and exhibit elegant gold color.

Example 2

TiN having a particle size of 1.2 μm, TiCN having a particle size of 1.5 μm, Cr₃C₂ having a particle size of 7.0 μm, WC having a particle size of 9.0 μm, nickel having a particle size of 3.0 μm, and cobalt having a particle size of 4.0 μm were used as starting material powders, and were weighed and mixed in a manner that the ratios of amounts of the metals in the final sintered products were as shown in Table 1. The mixtures were pulverized in an organic solvent such as acetone for about 68 hours and, after paraffin was added thereto in an amount of 4 to 5% by weight, were molded under the application of pressure of 1.5 tons/cm² into a desired shape. The molded articles were placed in a non-oxidizing atmosphere heated at a predetermined temperature to remove the organic binder, and were then baked in vacuum in a vacuum heating furnace having a degree of vacuum of 10⁻² Torr at a temperature of 1450°C for one hour. The thus obtained final sintered products were analyzed by the ICP emission spectroanalysis. The results were as shown in Table 4.

Table 4

Sample No.	Analytical ratio of sintered product (% by weight)							C/C+N (wt%)	Ratio of chromium (wt%)
	Ti	Group 6a		Iron-family metal		C	N		
#1	75.8	Cr	0.9	Ni	1.0	0.1	22.2	0.4	47.4
2	74.5	Cr	2.0	Ni	1.4	0.3	21.8	1.4	58.8
3	69.6	Cr	4.3	Ni	3.5	0.8	20.3	3.8	46.2
		W	1.5						
4	68.1	Cr	5.0	Ni	7.0	1.0	18.9	5.0	41.7
5	67.7	Cr	5.0	Ni	7.5	0	19.8	0	40.0
6	65.8	Cr	6.5	Ni	7.5	1.0	19.2	5.0	46.4
7	58.0	Cr	10.7	Ni	5.0	0	19.2	0	66.7
#8	58.0	Cr	8.7	Ni	15.0	1.3	17.0	7.1	36.7
9	58.0	Cr	10.4	Ni	10.0	1.6	17.0	8.6	44.4
				Co	3.0				
#10	56.5	Cr	13.0	Ni	12.0	2.0	16.5	10.8	52.0
#11	54.0	Cr	14.5	Ni	9.5	2.2	15.8	12.2	51.8
				Co	4.0				
#12	50.3	Cr	21.7	Ni	10.0	3.3	14.7	18.3	68.5

Samples marked # lie outside the scope of the invention.

The surfaces of the sintered products were ground and polished like a mirror. The samples were then tested for their color tone, bending strength, Vickers' hardness (Hv), porosity, average crystalline size, anti-chipping property and corrosion resistance. The bending strength was measured in accordance with the three-point bending test stipulated under JIS R 1601, the Vickers' hardness was measured in compliance with the testing method of JIS Z 2244, and the porosity was measured according to the Archimedes' method. The anti-corrosion testing was carried out by using human sweat (pH 4.7) in compliance with the standards of the ISO (International Standardization Organization) as a corrosive solution, immersing the lower half of the mirror surface-polished sample in the human sweat maintained at 40°C + 2°C for 24 hours, and the conditions of the polished surfaces of the samples after immersed were observed. The average crystalline particle size was calculated from an S.E.M photograph of the sintered product. The anti-chipping property was indicated in terms of a maximum chipping width of when the mirror surface-polished sample was creep-ground. The results were as shown in Table 5.

Table 5

Sample No.	Average particle diameter (μm)	Porosity	Deflective strength (kg/mm ²)	Vickers' hardness Hv (kg/mm ²)	Corrosion resistance	Anti-chipping property	Color tone
#1	2.5	X	-	-	-	X	poorly sintered
2	2.8	○	90	1600	○	○	gold color
3	1.3	○	110	1400	○	○	gold color
4	1.5	○	150	1300	○	○	gold color
5	1.8	○	125	1350	○	○	gold color
6	2.3	○	125	1350	○	○	gold color
7	2.3	○	115	1400	○	○	gold color
#8	1.8	○	120	1150	X	○	gold color
9	2.2	○	140	1150	○	○	gold color
#10	2.5	○	140	1200	○	○	reddish golden color
#11	3.3	○	130	950	○	X	dark gold color
#12	3.5	○	135	1050	○	X	red copper color

The samples marked with # lie outside the scope of the invention.

In Tables 4 and 5, the samples marked with # lie outside the scope of the present invention. Concerning the porosity in Table 5, furthermore, an open circle ○ represents high-density products with the porosity of smaller than 5% and a mark X represents low-density products with the porosity of greater than 5%. As for the anti-corrosion testing, an open circle ○ represents the products without any discoloration or corrosion, and a mark X represents the products that were discolored and corroded. As for the anti-chipping property, an open circle ○ represents the products that could be favorably sharp-edge machined, and a mark X represents the products that developed chipping and could not be sharp-edge machined.

It will be understood from the above Tables 4 and 5 that the samples Nos. 2 to 7 and 9 that lie within the scope of the present invention have very excellent porosity, bending strength, Vickers' hardness, corrosion resistance and anti-chipping property, and exhibit elegant gold color.

Claims

1. A sintered alloy of gold color comprising a nitride of titanium or a carbonitride of titanium and metals, wherein titanium is contained in an amount of 55 to 75% by weight with respect to the whole amount, metals of the iron family and elements of the Group 6a of periodic table including at least chromium are contained in an amount of 3 to 30% by weight with respect to the whole amount, and the remainder being non-metallic elements consisting of nitrogen or nitrogen and carbon, and wherein the ratio of carbon with respect to said non-metallic elements is not greater than 10% by weight, and the ratio of chromium in the metal elements excluding titanium is not smaller

than 35% by weight.

2. A sintered alloy of gold color according to claim 1, wherein metals of the iron family and elements of the Group 6a of periodic table including at least chromium are contained in an amount of 10 to 30% by weight with respect to the whole amount, the ratio of carbon is not greater than 0.7% by weight with respect to the whole amount, and the brightness index L^* and chromaticness indexes a^* , b^* in the $L^*a^*b^*$ color display system stipulated under JIS Z 8730 are $L^* \geq 10$, $a^* \leq +0.4$ and $b^* \geq +8.0$.
3. A sintered alloy of gold color according to claim 2, wherein titanium exists in an amount of 60 to 68% by weight with respect to the whole amount.
4. A sintered alloy of gold color according to claim 2, wherein metals of the iron family and elements of the Group 6a of periodic table exist in amounts of 12 to 23% by weight with respect to the whole amount.
5. A sintered alloy of gold color according to claim 2, wherein metals of the iron family exist at a ratio of 5 to 18% by weight and elements of the Group 6a of periodic table exist at a ratio of 3 to 12% by weight with respect to the whole amount.
6. A sintered alloy of gold color according to claim 1, wherein the sintered alloy has a average crystalline particle size which is not greater than $3 \mu\text{m}$.
7. A sintered alloy of gold color according to claim 6, wherein the ratio of chromium in the metal elements excluding titanium is not smaller than 40% by weight.
8. A sintered alloy of gold color according to claim 6, wherein titanium exists in an amount of 60 to 70% by weight with respect to the whole amount.
9. A sintered alloy of gold color according to claim 6, wherein the ratio of carbon with respect to the non-metallic elements is not greater than 8% by weight.

Patentansprüche

1. Ein Titanitrid oder Titancarbonitrid und Metalle enthaltende goldfarbige gesinterte Legierung, worin Titan in einer Menge von 55 bis 75 Gew.-%, bezogen auf die Gesamtmenge, Metalle der Eisenfamilie und Elemente der Gruppe 6a des Periodensystems einschließlich zumindest Chrom in einer Menge von 3 bis 30 Gew.-%, bezogen auf die Gesamtmenge enthalten, und der Rest aus Stickstoff oder Stickstoff und Kohlenstoff enthaltende nichtmetallische Elemente sind und worin das Kohlenstoffverhältnis hinsichtlich der nichtmetallischen Elemente nicht größer als 10 Gew.-% und das Chromverhältnis in den Metallelementen ausschließlich Titan nicht kleiner als 35 Gew.-% ist.
2. Goldfarbige gesinterte Legierung nach Anspruch 1, worin die Metalle der Eisenfamilie und die Elemente der Gruppe 6a des Periodensystems einschließlich zumindest Chrom in einer Menge von 10 bis 30 Gew.-%, bezogen auf die Gesamtmenge, enthalten, das Kohlenstoffverhältnis nicht größer als 0,7 Gew.-%, bezogen auf die Gesamtmenge, und der Helligkeitsindex L und die Chromatizitätsindizes a^* , b^* in dem gemäß JIS Z 8730 festgelegten $L^*a^*b^*$ -Farbdisplaysystem $L^* \geq 10$, $a^* \leq +0,4$ und $b^* \geq +8,0$ sind.
3. Goldfarbige gesinterte Legierung nach Anspruch 2, worin Titan in einer Menge von 60 bis 68 Gew.-%, bezogen auf die Gesamtmenge, vorliegt.
4. Goldfarbige gesinterte Legierung nach Anspruch 2, worin die Metalle der Eisenfamilie und die Elemente der Gruppe 6a des Periodensystems in Mengen von 12 bis 23 Gew.-%, bezogen auf die Gesamtmenge, vorliegen.
5. Goldfarbige gesinterte Legierung nach Anspruch 2, worin die Metalle der Eisenfamilie in einem Verhältnis von 5 bis 18 Gew.-% und die Elemente der Gruppe 6a des Periodensystems in einem Verhältnis von 3 bis 12 Gew.-%, bezogen auf die Gesamtmenge, vorliegen.
6. Goldfarbige gesinterte Legierung nach Anspruch 1, worin die gesinterte Legierung eine durchschnittliche Teilchengröße von nicht größer als $3 \mu\text{m}$ hat.

7. Goldfarbige gesinterte Legierung nach Anspruch 6, worin das Chromverhältnis in den Metallelementen ausschließlich Titan nicht kleiner als 40 Gew.-% ist.
8. Goldfarbige gesinterte Legierung nach Anspruch 6, worin Titan in einer Menge von 60 bis 70 Gew.-%, bezogen auf die Gesamtmenge, vorliegt.
9. Goldfarbige gesinterte Legierung nach Anspruch 6, worin das Kohlenstoffverhältnis bezüglich der nichtmetallischen Elemente nicht größer als 8 Gew.-% ist.

Revendications

1. Alliage fritté de couleur dorée comprenant un nitrure de titane ou un carbonitrure de titane et des métaux, dans lequel le titane est contenu selon une quantité de 55 à 75 % en poids par rapport au poids total, les métaux de la famille du fer et les éléments du groupe 6a de la classification périodique incluant au moins du chrome selon une quantité de 3 à 30% en poids par rapport au poids total, et le reste étant des éléments non métalliques consistant en azote ou azote et carbone, la teneur en carbone par rapport auxdits éléments non-métalliques n'étant pas supérieure à 10% en poids, et la teneur en chrome par rapport aux éléments métalliques autres que le titane n'étant pas inférieure à 35 % en poids.
2. Alliage fritté de couleur dorée suivant la revendication 1, dans lequel les métaux de la famille du fer et les éléments du groupe 6a de la classification périodique incluant au moins du chrome représentent une quantité de 3 à 30% en poids par rapport au poids total, la teneur en carbone n'est pas supérieure à 0,7% par rapport au poids total, et l'indice de luminosité L^* et les indices de chromie ("chromacticness") a^* , b^* dans le système couleur $L^*a^*b^*$ selon la norme JIS Z 8730 sont $L^* \geq 10$, $a^* \leq +0,4$ et $b^* \geq +8,0$.
3. Alliage fritté de couleur dorée suivant la revendication 2, dans lequel le titane est présent selon une quantité de 60 à 68% en poids par rapport au poids total.
4. Alliage fritté de couleur dorée suivant la revendication 2, dans lequel les métaux de la famille du fer et les éléments du groupe 6a de la classification périodique sont présents selon une quantité de 12 à 23 % en poids par rapport au poids total.
5. Alliage fritté de couleur dorée suivant la revendication 2, dans lequel les métaux de la famille du fer sont présents selon une teneur de 5 à 18% en poids et les éléments du groupe 6a de la classification périodique sont présents selon une teneur de 3 à 12% en poids par rapport au poids total.
6. Alliage fritté de couleur dorée suivant la revendication 1, dans lequel l'alliage fritté a une taille moyenne de particules cristallines qui n'est pas supérieure à 3 μm .
7. Alliage fritté de couleur dorée suivant la revendication 6, dans lequel la teneur en chrome dans les éléments métalliques autres que le titane n'est pas inférieure à 40 % en poids.
8. Alliage fritté de couleur dorée suivant la revendication 6, dans lequel le titane est présent selon une quantité de 60 à 70% en poids par rapport au poids total.
9. Alliage fritté de couleur dorée suivant la revendication 6, dans lequel la teneur en carbone par rapport aux éléments non-métalliques n'est pas supérieure à 8% en poids.