



(86) Date de dépôt PCT/PCT Filing Date: 2009/04/06
(87) Date publication PCT/PCT Publication Date: 2009/10/08
(45) Date de délivrance/Issue Date: 2015/06/23
(85) Entrée phase nationale/National Entry: 2010/09/29
(86) N° demande PCT/PCT Application No.: US 2009/039655
(87) N° publication PCT/PCT Publication No.: 2009/124311
(30) Priorité/Priority: 2008/04/04 (US61/042,470)


(51) Cl.Int./Int.Cl. *A61K 8/21* (2006.01),
A61K 33/16 (2006.01), *A61K 8/98* (2006.01),
A61P 1/02 (2006.01), *A61Q 11/00* (2006.01)

(72) Inventeurs/Inventors:
BLANVALET, CLAUDE, BE;
LAMBERT, PIERRE, BE;
TACK, VIVIANE, BE

(73) Propriétaire/Owner:
COLGATE-PALMOLIVE COMPANY, US

(74) Agent: SMART & BIGGAR

(54) Titre : COMPOSITIONS ORALES COMPRENANT DE LA CIRE DE GOMME-LAQUE ET GOMME-LAQUE
DESTINEE A ETRE UTILISEE EN STOMATOLOGIE ET POUR LES SOINS DENTAIRE
(54) Title: ORAL COMPOSITIONS COMPRISING SHELLAC WAX AND BLEACHED SHELLAC FOR USE IN
STOMATOLOGY AND DENTAL CARE



(57) Abrégé/Abstract:

An oral composition comprising an active component and an adhesive film forming component comprising bleached shellac and shellac wax for the treatment of teeth.

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
8 October 2009 (08.10.2009)(10) International Publication Number
WO 2009/124311 A1

(51) International Patent Classification:

A61K 8/21 (2006.01) *A61Q 11/00* (2006.01)
A61K 8/98 (2006.01) *A61P 1/02* (2006.01)
A61K 33/16 (2006.01)

(21) International Application Number:

PCT/US2009/039655

(22) International Filing Date:

6 April 2009 (06.04.2009)

(25) Filing Language:

English

(26) Publication Language:


English

(30) Priority Data:

61/042,470 4 April 2008 (04.04.2008) US

(71) **Applicant** (for all designated States except US): **COLGATE-PALMOLIVE COMPANY** [US/US]; 300 Park Avenue, New York, NY 10022 (US).(72) **Inventors; and**(75) **Inventors/Applicants** (for US only): **BLANVALET, Claude** [BE/BE]; Rue Bossy, 61, B-4031 Liege (BE). **LAMBERT, Pierre** [BE/BE]; Rue Du Mat'pays 4, B-4621 Fleron (BE). **TACK, Viviane** [BE/BE]; Rue Baudrihay, 17, B-4630 Soumagne (BE).(74) **Agent:** **LEE, Michael, U.**; Colgate-Palmolive Company, Patent Department, 909 River Road, Piscataway, NJ 08855 (US).(81) **Designated States** (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.(84) **Designated States** (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).**Published:**

- with international search report (Art. 21(3))
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments (Rule 48.2(h))

(54) **Title:** ORAL COMPOSITIONS COMPRISING SHELLAC WAX AND BLEACHED SHELLAC FOR USE IN STOMATOLOGY AND DENTAL CARE(57) **Abstract:** An oral composition comprising an active component and an adhesive film forming component comprising bleached shellac and shellac wax for the treatment of teeth.

TITLE OF THE INVENTION

ORAL COMPOSITIONS COMPRISING SHELLAC WAX AND BLEACHED SHELLAC FOR USE IN STOMATOLOGY AND DENTAL CARE

BACKGROUND OF THE INVENTION

[0001] Dental caries is a major dental disease that affects the majority of the population. In the early part of the 20th century, investigators discovered that fluoride was effective in reducing the incidence of caries. Since that time, fluoride research has developed, and it is now well accepted that fluoride treatments benefit dental health.

[0002] Fluoride compositions are routinely applied to teeth by any number of methods and compositions, the most common methods by utilizing fluoride containing dentifrice compositions, such as toothpastes and mouthwashes. However, there are certain situations where it is desirable to have prolonged contact of the fluoride compositions with teeth, and to use amounts of fluoride that exceed fluoride amounts present in dentifrice compositions. For example, it may be desirable to treat xerostomia (dry mouth), tooth hypersensitivity, dental caries with high levels of fluoride for prolonged periods of time. This may be accomplished by the use of a dental tray, wherein a composition is applied to the dental tray, and then the composition and tray are applied to the teeth to be treated; however, this method is inconvenient, as the user is forced to retain the tray in their mouth during use, and thus the treatment time is limited by how long the user may retain the tray in their mouth. Thus, tooth varnish compositions have been developed to be applied directly to the tooth with a brush. The use of tooth varnish compositions are well known in the art, and the varnish compositions allow for a longer exposure time (e.g., about or greater than 2 hours) before the composition is worn away.

[0003] Existing tooth varnish compositions generally contain an active component, e.g., to treat caries, provide fluoride therapy, treat xerostomia, tooth sensitivity, and/or whiten or bleach teeth, and an adhesive film forming component to cause the active material to adhere to the tooth. However, due to the colour of the adhesive film forming component, the varnish may cause a temporary change in the surface colour of teeth, e.g., creating a yellow color. A color difference may be desirable in that it aids the user in identifying tooth surfaces on which the varnish has been applied; however, excessive color is undesirable, as yellow teeth suggest an unhygienic oral cavity, regardless of how

62301-2975

temporary the varnish is. Additionally, the discoloration may cause embarrassment to the user, as others may realize that the user is utilizing a tooth varnish. Thus, there is a need to develop tooth varnish compositions which do not adversely affect the colour of a tooth.

- 5 **[0004]** Another disadvantage with tooth varnishes is that the varnishes tend to be multiphase, e.g., as the active component is insoluble in the adhesive film forming phase, and the varnish may separate out into distinct phases. Additionally, components of the adhesive film forming phase, may also separate into distinct phases over time. Users typically need to stir the varnish in order to mix the phases,
10 which is time consuming and wasteful, as the varnish adheres to the mixing apparatus and is then discarded. Thus, there exists a need to develop tooth varnish compositions with greater stability, wherein the phases do not readily separate.

BRIEF SUMMARY OF THE INVENTION

- [0005]** In accordance with the present invention, it has been surprisingly
15 discovered that a tooth varnish comprising an active component, and an adhesive film forming component comprising shellac wax and a bleached shellac imparts less color when applied to a tooth, and has greater stability, e.g., the phases tend not to separate; moreover, the use of such compositions does not cause a reduction of activity of the active component. The varnish may be easily applied by brush, e.g.,
20 dipping a brush into the composition, and then applying it to a tooth surface, preferably a dry tooth surface. The varnish is temporary, and wears off of the tooth surface after a period of time, e.g., within 48 hours of application, within 24 hours of application, within 12 hours of application, within 6 hours of application, or within 2 hours of application.

- 25 **[0006]** Thus, the present invention is directed to composition 1.0, an oral composition comprising an active component, and adhesive film forming component comprising a bleached shellac and shellac wax.

62301-2975

[0006a] The present invention may also relate to an oral composition comprising an active component, and adhesive film forming component comprising a bleached shellac and shellac wax, wherein the oral composition is a tooth varnish and the active component comprises a fluoride ion source, an antibacterial agent, an
5 antisensitivity agent, a tooth whitening agent, or combinations thereof, and wherein shellac wax comprises from about 0.5% to 15% weight of the composition.

[0007] Additional compositions of the present invention include compositions:

1.1 Composition 1.0 wherein the bleached shellac is a dewaxed bleached shellac;

10 1.2 Composition 1.0 or 1.1 wherein the bleached shellac comprises from about 5% to about 70% weight of the composition, e.g., from about 5% to about 40%, from about 10% to about 30%, or about 20%, or wherein the bleached shellac comprises from

- about 10% to about 50% by weight of the adhesive film forming component, e.g., from about 15% to about 35%, or about 25% by weight of the component;
- 1.3 Any of the preceding compositions wherein the shellac wax comprises from about 0.1% to about 20% weight of the composition, e.g., from about 0.5% to about 15%, from about 1% to about 10%, or about 1%, 4%, 6%, 8%, or 10%, or wherein the shellac wax comprises from about 0.1 to about 10% by weight of the adhesive film forming component, e.g., from about 0.5% to about 8%, from about 1% to about 5%, or about 2, 3, or 4%;
- 1.4 Any of the preceding compositions wherein the active component comprises from about 3% to about 50% by weight of the composition, e.g., from about 5% to about 30%, from about 10% to about 20%, or about 14% or 15%;
- 1.5 Any of the preceding compositions wherein the adhesive film forming component further comprises beeswax, colophonium, mastic, a water-insoluble alkyl cellulose, and combinations thereof;
- 1.6 Any of the preceding compositions wherein the adhesive film forming component comprises from about 5% to about 97% weight of the composition, e.g., from about 50% to about 95%, from about 60% to about 90%, from about 70% to about 85%, or about 80%;
- 1.7 Any of the preceding compositions further comprises a solvent, e.g., wherein the composition comprises from about 5% to about 50% weight of the solvent, e.g., from about 10% to about 40%, from about 25% to about 30%, or about 27%;
- 1.8 Any one of the preceding compositions wherein the active component comprises a solvent, e.g., wherein the solvent is from about 20% to about 60% by weight of the active component, e.g., from about 30% to about 50%, from about 35% to about 45%, or about 40% or 43%;
- 1.9 Compositions 1.7 or 1.8 wherein the solvent is selected from methanol, ethanol, ethyl acetate, acetone, isopropyl alcohol, or combinations thereof;
- 1.10 Any of the preceding compositions wherein the active component comprises colophonium, e.g., wherein the active component comprises from about 5% to 40%

colophonium by weight, e.g., from about 10% to about 30%, from about 15% to about 25%, or about 20 or 22%;

- 1.11 Any of the preceding compositions wherein the active component comprises a fluoride ion source, e.g., present in an amount of about 0.5% to about 15% by weight of the total composition, e.g., from about 1% to about 10%, from about 2% to about 7%, or about 5%;
- 1.12 Any of the preceding compositions comprising a fluoride ion source sufficient to provide from about 1,000 ppm to about 50,000 ppm fluoride ions in the composition, e.g., about 22,000 ppm, or 23, 000 ppm;
- 1.13 Any of the preceding compositions comprising a fluoride ion source selected from sodium fluoride, potassium fluoride, calcium fluoride, zinc fluoride, zinc ammonium fluoride, lithium fluoride, ammonium fluoride, stannous fluoride, stannous fluorozirconate, sodium monofluorophosphate, potassium monofluorophosphate, laurylamine hydrofluoride, diethylaminoethyloctoylamide hydrofluoride, didecyldimethylammonium fluoride, cetylpyridinium fluoride, dilaurylmorpholinium fluoride, sarcosine stannous fluoride, glycine potassium fluoride, glycine hydrofluoride, amine fluoride, or combinations thereof;
- 1.14 Any of compositions wherein the active component comprises a tooth desensitizing agent;
- 1.15 Any of the preceding compositions comprising a tooth desensitizing agent selected from a potassium salt, capsaicin, eugenol, a strontium salt, a zinc salt, a chloride salt, or combinations thereof;
- 1.16 Any of the preceding compositions wherein the active component comprises an effective amount of a antibacterial agent;
- 1.17 Any of the preceding compositions wherein the active component comprises a tooth whitening compound;
- 1.18 Any of the preceding compositions substantially free of water, e.g., less than 1% by weight water;
- 1.19 Any of the preceding compositions comprising stannous ion agent, triclosan, triclosan monophosphate, chlorhexidine, alexidine, hexetidine, sanguinarine,

62301-2975

benzalkonium chloride, salicylanilide, arginate esters, ethyl lauryl arginate, bisphenols, domiphen bromide, tetradecylpyridinium chloride, N-tetradecyl-4-ethylpyridinium chloride, octenidine, delmopinol, octapinol, nisin, zinc ion agent, copper ion agent, essential oils, furanones, bacteriocins, a basic amino acid, or
 5 combinations thereof;

1.19.1 Any of the preceding compositions wherein the active component comprises a halogenated diphenyl ether.

1.20 Any of the preceding compositions which is a tooth varnish.

1.20.1 Any of the preceding compositions wherein the composition is applied
 10 to a plurality of teeth to treat the teeth with fluoride.

[0008] The present invention is also directed to a method for treating a tooth with an active component comprising applying any one of compositions 1.0 - 1.20 to the tooth in the oral cavity, e.g., by a brush, swab, or syringe. The present invention is also directed to methods to treat dental caries, xerostomia, tooth hypersensitivity,
 15 or dental stains comprising applying any one of compositions 1.0 - 1.20 to the tooth in the oral cavity. The compositions of the present invention may be applied to the enamel, dentin or cementum of the tooth and can be used to help prevent and/ or treat tooth decay, remineralize the tooth surface, and hypersensitivity. Preferably, the composition remains adhered to the tooth surface for 0.5 hours to 48 hours following
 20 application, e.g., for 2, 4, 6, 12, or 14 hours following application.

BRIEF DESCRIPTION OF THE DRAWINGS

[0009] FIG. 1 details results as described in Example 2;

[0010] FIG. 2 details results as described in Example 3; and

[0011] FIG. 3 details results as described in Example 4.

62301-2975

DETAILED DESCRIPTION OF THE INVENTION

[0012] Throughout the present disclosure, ranges are used as a shorthand for describing each and every value that is within the range. Any value within the range can be selected as the terminus of the range.

5 **[0013]** The active component of the present invention may be any oral active which is known in the art, e.g., fluoride ion sources, antibacterials, tooth whitening and/or bleaching agents, and antisensitivity agents.

[0014] The adhesive film forming component of the present invention is used to facilitate adhesion of the active component to the dental surface, and to form a
10 substantially continuous film over the surface to which the present invention is applied.

The adhesive film forming component contains shellac wax, bleached shellac, and optionally other adhesive or film forming materials which are known in the art.

[0015] Shellac is a processed resinous secretion from the lac insect *Kerria lacca*. Methods of manufacturing shellac are known in the art. Although shellac has previously been used in tooth varnishes, the inventors have discovered that by using a bleached shellac in a tooth varnish, the stability of the varnish is improved, and the color tooth when the varnish is applied to the tooth is also improved.

[0016] Methods of producing shellac wax are known in the art. Generally, unprocessed shellac is dissolved in an alkali solution or an alcohol, and subject to solvent extraction, optionally using activated carbon. The shellac wax is then recovered from the solvent phase. Shellac wax may be obtained from Renshel Exports Pvt. Ltd. (Kolata, India), or Sitaram Saraf (Kolkata, India).

[0017] Methods of producing bleached shellac (which may be dewaxed) are also known in the art. Generally, the solvent extracted alkali solution (produced from manufacturing shellac wax) is treated with a bleaching agent, e.g., sodium hypochlorite. The bleached shellac is precipitated from solution with a strong acid, e.g., sulphuric acid and dried. See also US Pat. No. 6,348,217. Bleached shellac may be obtained from Renshel Exports Pvt. Ltd. as type 101 (Kolata, India), or Sitaram Saraf (Kolkata, India)

[0018] Other film forming materials may also be added to the film forming component. For example, white wax, beeswax, white beeswax, colophonum (also known as rosin), mastic, polybutene, and water insoluble alkyl cellulose as described in DE 20 2004 000 552 U1 may be incorporated into the adhesive film forming component. Colophonum may be obtained from Willers Engels & Co. GMBH (Hamburg, Germany).

[0019] The compositions of the present invention comprise an active component, which is selected depending on the intended purpose of the tooth varnish. For example, an active component may be a fluoride ion source for fluoride treatments, treatment of caries, hypersensitivity, or xerostomia. An active component may be an antisensitivity agent for treatment of tooth hypersensitivity. An active component may be a tooth whitening or bleaching composition for tooth whitening or bleaching, e.g., for treating

62301-2975

stains and discolorations. The active component preferably does not react with the adhesive film forming component.

[0020] Fluoride ion sources are known in the art, and may be anything that is capable of releasing fluoride ion in an aqueous environment. Typical sources include soluble salts of the fluoride ion; such as, for example: sodium fluoride, potassium fluoride, calcium fluoride, zinc fluoride, zinc ammonium fluoride, lithium fluoride, ammonium fluoride, stannous fluoride, stannous fluoro-zirconate, and complex fluorides, monofluorophosphates and salts thereof such as, e.g., sodium monofluorophosphate or potassium monofluorophosphate, laurylamine hydrofluoride, diethylaminoethyloctylamide hydrofluoride, didecyl-dimethylammonium fluoride, cetylpyridinium fluoride, dilaurylmorpholinium fluoride, sarcosine stannous fluoride, glycine potassium fluoride, glycine hydrofluoride, and amine fluorides. See, e.g., U.S. Patents Nos. 3,538,230, 3,689,637, 3,711,604, 3,911,104, 3,935,306 and 4,040,858. The fluoride ion source may be presented as a salt or a silane preparation. Preferably, the fluoride ion source is in the form of a salt, and a preferred fluoride ion source is sodium fluoride.

[0021] The fluoride ion source is most preferably in an amount such that it is capable of providing a high level of fluoride ion in the composition, that is at least about 5,000 ppm, and in some instances up to as much as 50,000 ppm, e.g., from about 7,000 ppm to about 40,000 ppm, from about 15,000 ppm to about 30,000 ppm, or about 22,000 or 23,000 ppm. In order to provide such a concentration in the optimal ppm range, the exact weight percentage of the fluoride ion source in the composition may vary, depending upon the stoichiometric properties of different fluoride ion sources.

[0022] Preferably, the antibacterial agents may be utilized as an active component if reduction of microorganisms is desired. Antibacterial agents are known in the art, and include benzoic acid, sodium benzoate, potassium benzoate, boric acid, and phenolic compounds such as betanaphthol, chlorothymol, thymol, anethole, eucalyptol, carvacrol, menthol, phenol, amylphenol, hexylphenol, heptylphenol, octylphenol, hexylresorcinol, laurylpyridinium chloride, myristylpyridinium chloride, cetylpyridinium fluoride, cetylpyridinium chloride, cetylpyridinium bromide, and halogenated diphenyl ethers,

such as triclosan. Compositions of the present invention may also include one or more basic amino acids, e.g., arginine, in free base or salt form. Such agents may be added in effective amounts, e.g., from about 1% to about 20% by weight based on the total weight of the composition, depending on the agent chosen.

[0023] The compositions of the present invention may incorporate one or more antisensitivity agents, e.g., potassium salts such as potassium nitrate, potassium bicarbonate, potassium chloride, potassium citrate, and potassium oxalate; capsaicin; eugenol; strontium salts; zinc salts; chloride salts and combinations thereof. Such agents may be added in effective amounts, e.g., from about 1% to about 20% by weight based on the total weight of the composition, depending on the agent chosen. The compositions of the present invention may also be used to treat hypersensitivity by blocking dentin tubules when applied to a tooth.

[0024] The active component of the present invention may also be a tooth whitening or tooth bleaching composition, which are known in the art. Suitable whitening and bleaching composition include peroxides, metal chlorites, persulfates. Peroxides include hydroperoxides, hydrogen peroxide, peroxides of alkali and alkaline earth metals, organic peroxy compounds, peroxy acids, and mixtures thereof. Peroxides of alkali and alkaline earth metals include lithium peroxide, potassium peroxide, sodium peroxide, magnesium peroxide, calcium peroxide, barium peroxide, and mixtures thereof. Other peroxides include perborate, urea peroxide, and mixtures thereof. Suitable metal chlorites may include calcium chlorite, barium chlorite, magnesium chlorite, lithium chlorite, sodium chlorite, and potassium chlorite. Such agents may be added in effective amounts, e.g., from about 1% to about 20% by weight based on the total weight of the composition, depending on the agent chosen.

[0025] The present invention may optionally include a solvent, which rapidly evaporates when the compositions of the present invention are applied to the teeth. Suitable solvents may include methanol, ethanol, ethyl acetate, acetone, or isopropanol. Preferably, the solvent is non-toxic, and a preferred solvent is ethanol. The solvent may also function as a viscosity modifier, and to ensure even deposition of the film forming component.

[0026] Preferably the composition has a viscosity of between about 100 and 5000 centipoise. In addition, the composition may also be thixotropic so that it is more easily spread during application. Due to the high viscosity and thixotropic characteristics of the composition, any tendency of the composition to otherwise run or drip once applied is minimized and/or prevented.

[0027] The oral care composition is preferably in the form of a tooth varnish, thus the compositions may be substantially free of water, e.g., 0% water, or less than 1% water by weight. It is to be understood that some ingredients in the composition, e.g., bleached shellac or ethanol, may contain trace amounts of water.

[0028] Flavors, e.g., sweeteners, may be used in the oral care compositions of the present invention if desired. Suitable sweeteners include but are not limited to: saccharins and derivatives thereof, cyclamates and derivatives thereof, acesulfane-K, thaumatin, neohesperidin dihydrochalcone, ammoniated glycyrrhizin, dextrose, levulose, sucrose, mannose, glucose, xylitol, and any other suitable sweeteners. Other flavorings are known in the art, and may include artificial flavors, or plant extracts.

[0029] The invention will now be described with respect to the following non-limiting examples:

EXAMPLE 1

[0030] A tooth varnish active component comprising 42.5% weight ethanol, 22.9% weight colophonium, and 34.6% weight sodium fluoride. The materials are mixed until homogenous.

[0031] Five different adhesive film forming components are prepared in accordance with Table 1. The ingredients are mixed until homogenous. Unless otherwise indicated, the numbers expressed as percent weight.

[0032] TABLE 1

	Adhesive A	Adhesive W	Adhesive X	Adhesive Y	Adhesive Z
Shellac	25.7				
Bleached shellac		24.7	24.2	23.7	23.2
Shellac Wax		1	1.5	2	2.5
Ethanol	24.2	24.2	24.2	24.2	24.2
Colophonium	34.5	34.5	34.5	34.5	34.5
Beeswax	0.6	0.6	0.6	0.6	0.6
Mastic	14.2	14.2	14.2	14.2	14.2
Flavor	0.8	0.8	0.8	0.8	0.8

[0033] Tooth varnish compositions are then prepared by admixing the active component and adhesive film forming component. Additional ethanol and flavorings are also added to the composition. The final tooth varnish composition contains 84.3% by weight of the adhesive component, and 14.1% by weight of the active component. The final tooth varnish compositions are presented in Table 2.

TABLE 2

	Varnish A	Varnish W	Varnish X	Varnish Y	Varnish Z
Shellac	21.8				
Bleached Shellac		20.8	20.4	20	19.6
Shellac Wax		1	1.4	1.8	2.2
Ethanol	27	27	27	27	27
Colophonium	32.3	32.3	32.3	32.3	32.3
Sodium fluoride	4.9	4.9	4.9	4.9	4.9
White beeswax	0.5	0.5	0.5	0.5	0.5
Mastic	11.9	11.9	11.9	11.9	11.9
Flavoring	1.6	1.6	1.6	1.6	1.6

EXAMPLE 2

[0034] The varnish compositions of Example 1 are spun in a 15ml centrifuge tube for 15 minutes up to 360 hours, at 3000 rpm and 35 °C to determine their stability and tendency to separate into different phases. During centrifugation, a clear phase is

62301-2975

produced at the top of the varnish, indicating that the phases have separated. The length of the clear phase is measured, and presented in Figure 1.

EXAMPLE 3

[0035] Varnishes W, X, Y and Z of Example 1 are subjected to increasing temperatures until a 0.1 cm phase separation is observed. The results are presented in Figure 2, which indicates that compositions having a higher shellac wax component are stable at higher temperatures. 4%, 6%, 8%, and 10% represent varnishes W, X, Y and Z respectively.

EXAMPLE 4

[0036] Varnishes A and X are applied to teeth at varying thicknesses, and the color of the teeth are evaluated according to the Hunter L, a, b Color Scale with an Ultrascan XE spectrophotometer. Specifically, the b value of blue to yellow is evaluated. Results are presented in Figure 3. It will be determined that varnish A contains a greater yellow color component than varnish X.

EXAMPLE 5

[0037] Varnishes A and X are applied by dental professionals to patient teeth to determine the degree of adhesion. It will be determined that the dental professionals found varnish X has superior adhesion properties compared to varnish A.

EXAMPLE 6

[0038] Varnishes A and X are applied by dental professionals to patient teeth to determine the ease of application. It will be found that dental professionals found that varnish X easier to apply to teeth than composition A.

[0039] It will be appreciated by those skilled in the art that changes and alterations may be made to the embodiments described above without departing from the broad inventive concept thereof. It is understood, therefore, that this invention is not limited to the particular embodiments disclosed, but it is intended to cover modifications within the scope of the present invention as defined by the appended claims.

62301-2975

CLAIMS:

1. An oral composition comprising an active component, and adhesive film forming component comprising a bleached shellac and shellac wax, wherein the oral composition is a tooth varnish and the active component comprises a fluoride ion source, an
5 antibacterial agent, an antisensitivity agent, a tooth whitening agent, or combinations thereof, and wherein the shellac wax comprises from about 0.5% to 15% weight of the composition.
2. The composition of claim 1 wherein the bleached shellac is a dewaxed bleached shellac.
3. The composition of claim 1 or 2 wherein the bleached shellac comprises from
10 5% to 70% weight of the composition.
4. The composition of any one of claims 1 to 3 wherein the active component comprises from 3% to 50% by weight of the composition.
5. The composition of any one of claims 1 to 4 wherein the adhesive film forming component further comprises beeswax, colophonium, mastic, a water-insoluble alkyl
15 cellulose, or combinations thereof.
6. The composition of any one of claims 1 to 5 wherein the adhesive film forming component comprises from 5% to 97% weight of the composition.
7. The composition of any one of claims 1 to 6 wherein the composition comprises from 5% to 50% weight of a solvent.
- 20 8. The composition of any one of claims 1 to 7 wherein the active component comprises colophonium and a solvent which is methanol, ethanol, ethyl acetate, acetone, isopropyl alcohol, or combinations thereof.
9. The composition of claim 8, wherein the solvent is ethanol.
10. The composition of any one of claims 1 to 9, wherein the fluoride ion source is
25 present in an amount sufficient to provide from 1,000 ppm to 50,000 ppm fluoride ions in the

62301-2975

composition, or wherein the fluoride ion source selected from the group consisting of sodium fluoride, potassium fluoride, calcium fluoride, zinc fluoride, zinc ammonium fluoride, lithium fluoride, ammonium fluoride, stannous fluoride, stannous fluorozirconate, sodium monofluorophosphate, potassium monofluorophosphate, laurylamine hydrofluoride,
 5 diethylaminoethyloctoylamide hydrofluoride, didecyldimethylammonium fluoride, cetylpyridinium fluoride, dilaurylmorpholinium fluoride, sarcosine stannous fluoride, glycine potassium fluoride, glycine hydrofluoride, amine fluoride, and combinations thereof.

11. The composition of claim 10, wherein the fluoride ion source comprises sodium fluoride.

10 12. The composition of any one of claims 1 to 11 wherein the active component comprises a halogenated diphenyl ether.

13. The composition of any one of claims 1 to 12 which is substantially free of water.

14. The oral composition of any one of claims 1 to 13, in which the active
 15 component comprises a fluoride ion source, for use in the treatment of a tooth with fluoride.

1/2

Figure 1





FIGURE 2



2/2




Figure 3

