




(72) FORD, RANDAL RAY, US

(72) STUART, RICHARD KINGSLEY JR., US

(71) EASTMAN CHEMICAL COMPANY, US

(51) Int.Cl.⁷ C08F 10/00

(30) 1998/10/27 (60/105,786) US

(30) 1999/08/31 (09/386,547) US

(54) **TECHNIQUE DE POLYMERISATION D'OLEFINES,
NOUVEAUX POLYETHYLENES, FILMS ET ARTICLES
PRODUITS A L'AIDE DE CES POLYETHYLENES**

(54) **PROCESS FOR THE POLYMERIZATION OF OLEFINS; NOVEL
POLYETHYLENES, AND FILMS AND ARTICLES PRODUCED
THEREFROM**

(57) Ce nouveau procédé de polymérisation d'oléfines consiste à mettre au moins une oléfine en contact avec un catalyseur du type Ziegler-Natta en présence d'un composé précis, ce qui donne des produits polymères à répartition plus étroite du poids moléculaire. L'invention concerne également un procédé permettant de rendre plus étroite la répartition du poids moléculaire d'une polyoléfine, lequel procédé consiste à mettre en contact une oléfine, un catalyseur Ziegler-Natta et un composé précisé dans le descriptif. Elle porte, de surcroît, sur de nouveaux polyéthylènes ainsi que sur des films et des articles produits à l'aide de ceux-ci.

(57) A novel process for the polymerization of olefins is provided. The process involves contacting at least one olefin with a Ziegler-Natta type catalyst in the presence of a specified compound that results in the production of polymeric products having a narrower molecular weight distribution. Also provided is a process for narrowing the molecular weight distribution of a polyolefin comprising contacting an olefin, a Ziegler-Natta catalyst and a compound specified herein. Further provided are novel polyethylenes, and films and articles produced therefrom.

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08F 10/00	A2	(11) International Publication Number: WO 00/24790 (43) International Publication Date: 4 May 2000 (04.05.00)
(21) International Application Number: PCT/US99/24240 (22) International Filing Date: 14 October 1999 (14.10.99) (30) Priority Data: 60/105,786 27 October 1998 (27.10.98) US 09/386,547 31 August 1999 (31.08.99) US (71) Applicant: EASTMAN CHEMICAL COMPANY [US/US]; 100 North Eastman Road, Kingsport, TN 37660 (US). (72) Inventors: FORD, Randal, Ray; 3013 Latonia, Longview, TX 75605-1505 (US). STUART, Richard, Kingsley, Jr.; 719 Oakwood Drive, Longview, TX 75604-3112 (US). (74) Agent: GRAVES, Bernard, J., Jr.; P.O. Box 511, Kingsport, TN 37662-5075 (US).		(81) Designated States: BR, CA, CN, CZ, IN, JP, KR, MX, RU, SG, UA, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: PROCESS FOR THE POLYMERIZATION OF OLEFINS; NOVEL POLYETHYLENES, AND FILMS AND ARTICLES PRODUCED THEREFROM (57) Abstract A novel process for the polymerization of olefins is provided. The process involves contacting at least one olefin with a Ziegler-Natta type catalyst in the presence of a specified compound that results in the production of polymeric products having a narrower molecular weight distribution. Also provided is a process for narrowing the molecular weight distribution of a polyolefin comprising contacting an olefin, a Ziegler-Natta catalyst and a compound specified herein. Further provided are novel polyethylenes, and films and articles produced therefrom.		

TITLE OF THE INVENTION

**Process For The Polymerization of Olefins; Novel Polyethylenes, and Films
and Articles Produced Therefrom**

5

FIELD OF INVENTION

The present invention relates to a process for the polymerization of olefins having narrowed molecular weight distribution (MWD) values. Polyethylenes produced in accordance with the process of the present invention are generally characterized further by having a reduced n-hexane soluble polymeric fraction. Additionally, this invention relates to novel polyethylenes, and films and articles of manufacture produced therefrom.

15

BACKGROUND OF INVENTION

Catalyst systems for the polymerization of olefins are well known in the art and have been known at least since the issuance of U.S. Patent No. 3,113,115. Thereafter, many patents have been issued relating to new or improved Ziegler-Natta type catalysts. Exemplary of such patents are U.S. Patents Nos. 3,594,330; 3,676,415; 3,644,318; 3,917,575; 4,105,847; 4,148,754; 4,256,866; 4,298,713; 4,311,752; 4,363,904; 4,481,301 and Reissue 33,683.

These patents disclose Ziegler-Natta type catalysts that are well known as typically consisting of a transition metal component and a co-catalyst that is typically an organoaluminum compound. Optionally, used with the catalyst are activators such as halogenated hydrocarbons and activity modifiers such as electron donors.

The use of halogenated hydrocarbons with titanium-based Ziegler-Natta type polymerization catalysts in the production of polyethylene is disclosed in European Patent Applications EP A 0 529 977 A1 and EP 0 703 246 A1. As

30

disclosed, the halogenated hydrocarbons may reduce the rate of ethane formation, improve catalyst efficiency, or provide other effects. Typical of such halogenated hydrocarbons are monohalogen and polyhalogen substitutes of saturated or unsaturated aliphatic, alicyclic, or aromatic hydrocarbons having 1 to 12 carbon atoms. Exemplary aliphatic compounds include methyl chloride, methyl bromide, methyl iodide, methylene chloride, methylene bromide, methylene iodide, chloroform, bromoform, iodoform, carbon tetrachloride, carbon tetrabromide, carbon tetraiodide, ethyl chloride, ethyl bromide, 1,2-dichloroethane, 1,2-dibromoethane, methylchloroform, perchloroethylene and the like. Exemplary alicyclic compounds include chlorocyclopropane, tetrachlorocyclopentane and the like. Exemplary aromatic compounds include chlorobenzene, hexabromobenzene, benzotrichloride and the like. These compounds may be used individually or as mixtures thereof.

It is also well known, in the polymerization of olefins, particularly where Ziegler-Natta type catalysts are employed, to utilize, optionally, electron donors. Such electron donors often aid in increasing the efficiency of the catalyst and/or in controlling the stereospecificity of the polymer when an olefin, other than ethylene, is polymerized. Electron donors, typically known as Lewis Bases, can be employed during the catalyst preparation step, referred to as internal electron donors, or during the polymerization reaction when the catalyst comes into contact with the olefin or olefins, referred to as external electron donors.

The use of electron donors in the field of propylene polymerization is well known and is primarily used to reduce the atactic form of the polymer and increase the production of the isotactic polymers. However, while improving the production of isotactic polypropylene, electron donors tend, generally, to reduce the productivity of the Ziegler-Natta type catalyst.

In the field of ethylene polymerization, where ethylene constitutes at least about 50% by weight of the total monomers present in the polymer, electron donors are utilized to control the molecular weight distribution (MWD) of the polymer and the activity of the catalyst in the polymerization medium. Exemplary patents

describing the use of internal electron donors in producing polyethylene are U.S. Patents Nos. 3,917,575; 4,187,385, 4,256,866; 4,293,673; 4,296,223; Reissue 33,683; 4,302,565; 4,302,566; and 5,470,812. The use of an external electron donor to control molecular weight distribution is shown in U.S. Patent no. 5,055,535; and the use of external electron donors to control the reactivity of catalyst particles is described in U.S. Patent No. 5,410,002.

Illustrative examples of electron donors include carboxylic acids, carboxylic acid esters, alcohols, ethers, ketones, amines, amides, nitriles, aldehydes, alcoholates, thioethers, thioesters, carbonic esters, organosilicon compounds containing oxygen atoms, and phosphorus, arsenic or antimony compounds connected to an organic group through a carbon or oxygen atom.

The above is a partial listing of suitable electron donors. For the present invention, it is possible to use any electron donor that is suitable in a process for the polymerization of olefins.

SUMMARY OF THE INVENTION

The process of the present invention comprises polymerizing at least one olefin in the presence of both at least one Ziegler-Natta catalyst comprised of a component comprising at least one transition metal and a co-catalyst comprising at least one organometallic compound, and a sufficient amount of a specified compound to obtain an olefin homopolymer or interpolymer having a narrower molecular weight distribution than would be obtained in the absence of the specified compound. The specified compound added to the polymerization process is selected from the following:

- 1) An oxide of germanium, tin and lead;
- 2) Cyanogen (C_2N_2);
- 3) An oxide or imide of carbon of formula CE or C_3E_2 where $E = O$ and NR , R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen

- atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 5
- 4) A sulfur, selenium, or tellurium containing chalcogenide of carbon, silicon, germanium, tin and lead;
- 5) A chalcogenide of carbon, silicon, germanium, tin and lead containing more than one chalcogen;
- 10
- 6) A chalcogenide imide of carbon, silicon, germanium, tin and lead having the formula $C(E)(X)$ where $E = O, S, Se, Te, \text{ or } NR$; $X = NR'$ where R and/or R' is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 15
- 7) A chalcogenyl halide or imidohalide of carbon, silicon, germanium, tin and lead of the formula $C(E)X_2$ where $E = O, S, Se, Te, \text{ and } NR$; R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms; and X is a halogen;
- 20
- 8) An elemental form of phosphorus, arsenic, antimony and bismuth;
- 9) An oxide of nitrogen, phosphorus, arsenic, antimony and bismuth;
- 25
- 10) A nitrogen oxoacid or salt containing the anion thereof;
- 11) A halide of the formula E_nX_m , where E is nitrogen, phosphorus, arsenic, antimony or bismuth and X is a halogen or pseudohalogen, $n = 1 \text{ to } 10$, and $m = 1 \text{ to } 20$;
- 30
- 12) A chalcogenide or imide of nitrogen, phosphorus, arsenic, antimony and bismuth of the general formula E_nY_m , where $E = N, P, As, Sb, \text{ and }$

- Bi; Y = S, Se, Te, Po and NR; n = 1 to 10; m = 1 to 40; and R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 5
- 13) A chalcogenyl or imido compound of nitrogen, phosphorus, arsenic, antimony and bismuth having the formula $E_n Y_m X_q$, where E = N, P, As, Sb and Bi; Y = O, S, Se, Te and NR; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms; n = 1 to 20; m = 1 to 40; q = 1 to 40; and R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 10
- 15
- 20
- 14) An interpnictogen;
- 15) A phosphazene of the general formula $(NPR_2)_x$ wherein R = halogen, or alkyl or aryl group containing up to 50 non-hydrogen atoms, and x is at least 2;
- 25
- 16) A compound of the general formula $A(E)X_3$ where A = P, As, Sb, and Bi; E = NR or CR_2 , R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen
- 30

- atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms; and X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 10 atoms;
- 17) A pnictogen hydride;
- 18) An elemental form of oxygen, sulfur, selenium, and tellurium;
- 19) An interchalcogen;
- 20) A compound containing one or more chalcogens and one or more halogens of formula E_nX_m where E = O, S, Se, and Te; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms, n = 1 to 10, m = 1 to 20;
- 21) A compound of general formula EOX_2 where E = O, S, Se, and Te; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;

- 22) A compound of general formula EOX_4 where E = S, Se, and Te; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 23) A compound of general formula EO_2X_2 where E = S, Se, and Te; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 24) A Sulfur-Nitrogen compound;
- 25) A compound of the formula $\text{S}(\text{NR})_n\text{X}_m$ where $n = 1$ to 3 ; $m = 0$ to 6 ; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms; and R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen

- atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 26) A sulfur oxoacid, peroxyacid, and salts containing the anions thereof;
- 27) A selenium oxoacid, peroxyacid, and salts containing the anions thereof;
- 28) A tellurium oxoacid, peroxyacid, and salts containing the anions thereof;
- 29) A chalcogen hydride;
- 30) An elemental form of fluorine, chlorine, bromine, iodine, and astatine;
- 31) An interhalogen, salts containing their cations, and salts containing the anions thereof;
- 32) A salt containing polyhalide cations and/or anions;
- 33) A homoleptic or heteroleptic halogen oxide, salts containing the cations thereof, and salts containing the anion thereof;
- 34) An oxoacid and salts containing the anions thereof;
- 35) A hydrogen halide;
- 36) NH_4F , SF_4 , SbF_3 , AgF_2 , KHF_2 , ZnF_2 , AsF_3 , and salts containing the HF_2^- anion;
- 37) A hydrohalic acid;
- 38) A He, Ne, Ar, Kr, Xe, and Rn oxide, salts containing the cations thereof, and salts containing the anions thereof;
- 39) A He, Ne, Ar, Kr, Xe, and Rn halide, salts containing the cations thereof, and salts containing the anions thereof;
- 40) A He, Ne, Ar, Kr, Xe, and Rn chalcogenyl halide, salts containing the cations thereof, and salts containing the anions thereof;
- 41) A product obtained by reacting a material selected from the group consisting of water, alcohol, hydrogen sulfide and a thiol with any of the above compounds and salts thereof containing the corresponding anion;
- 42) An organic peroxide;

43) Water; and

44) Mixtures thereof.

Also provided is a process for narrowing molecular weight distribution of a polymer comprising at least one or more olefin(s) comprising contacting under
5 polymerization conditions, at least one or more olefin(s) with at least one Ziegler-Natta catalyst comprised of a component comprising at least one transition metal and a co-catalyst comprising at least one organometallic compound, and at least one of the specified compounds, wherein the specified compound is present in an amount sufficient that the molecular weight distribution of the resulting polymeric
10 product is narrower than would be obtained in the absence of the specified compound. The specified compounds are listed hereinabove.

All mention herein to elements of Groups of the Periodic Table are made in reference to the Periodic Table of the Elements, as published in "Chemical and Engineering News", 63(5), 27, 1985. In this format, the Groups are numbered 1 to
15 18.

In carrying out the novel polymerization process of the present invention, there may optionally be added any electron donor(s) and/or any halogenated hydrocarbon compound(s).

Also, the present invention comprises novel polyethylene homopolymers and
20 interpolymers. Further, the present invention comprises films and articles of manufacture produced from the novel polyethylene homopolymers and interpolymers.

DETAILED DESCRIPTION OF THE INVENTION

25

The present invention relates to a process for polymerizing at least one olefin in the presence of both at least one Ziegler-Natta catalyst comprised of a component comprising at least one transition metal and a co-catalyst comprising at least one organometallic compound, and a sufficient amount of a specified
30 compound to obtain a polyolefin homopolymer or interpolymers characterized by

having a molecular weight distribution (MWD) narrower than would be obtained in the absence of the specified compound. The specified compounds are listed hereinabove.

Also provided is a process for narrowing molecular weight distribution of a polymer comprising at least one or more olefin(s) comprising contacting under polymerization conditions, at least one or more olefin(s) with at least one Ziegler-Natta catalyst comprised of a component comprising at least one transition metal and a co-catalyst comprising at least one organometallic compound, and at least one of the specified compounds, wherein the specified compound is present in an amount sufficient that the molecular weight distribution of the resulting polymeric product is narrower than would be obtained in the absence of the specified compound. The specified compounds are listed hereinabove.

The polymerization of the at least one olefin herein may be carried out using any suitable process. For example, there may be utilized polymerization in suspension, in solution or in the gas phase media. All of these polymerization processes are well known in the art.

A particularly desirable method for producing polyethylene polymers according to the present invention is a gas phase polymerization process. This type process and means for operating the polymerization reactor are well known and completely described in U.S. Patents Nos. 3,709,853; 4,003,712; 4,011,382; 4,012,573; 4,302,566; 4,543,399; 4,882,400; 5,352,749; 5,541,270; Canadian Patent No. 991,798 and Belgian Patent No. 839,380. These patents disclose gas phase polymerization processes wherein the polymerization zone is either mechanically agitated or fluidized by the continuous flow of the gaseous monomer and diluent. The entire contents of these patents are incorporated herein by reference.

In general, the polymerization process of the present invention may be effected as a continuous gas phase process such as a fluid bed process. A fluid bed reactor for use in the process of the present invention typically comprises a reaction zone and a so-called velocity reduction zone. The reaction zone comprises a bed of

growing polymer particles, formed polymer particles and a minor amount of catalyst particles fluidized by the continuous flow of the gaseous monomer and diluent to remove heat of polymerization through the reaction zone. Optionally, some of the recirculated gases may be cooled and compressed to form liquids that increase the heat removal capacity of the circulating gas stream when readmitted to the reaction zone. A suitable rate of gas flow may be readily determined by simple experiment. Make up of gaseous monomer to the circulating gas stream is at a rate equal to the rate at which particulate polymer product and monomer associated therewith is withdrawn from the reactor and the composition of the gas passing through the reactor is adjusted to maintain an essentially steady state gaseous composition within the reaction zone. The gas leaving the reaction zone is passed to the velocity reduction zone where entrained particles are removed. Finer entrained particles and dust may be removed in a cyclone and/or fine filter. The said gas is passed through a heat exchanger wherein the heat of polymerization is removed, compressed in a compressor and then returned to the reaction zone.

In more detail, the reactor temperature of the fluid bed process herein ranges from about 30°C to about 150°C. In general, the reactor temperature is operated at the highest temperature that is feasible taking into account the sintering temperatures of the polymer product within the reactor.

The process of the present invention is suitable for the polymerization of at least one or more olefins. The olefins, for example, may contain from 2 to 16 carbon atoms. Included herein are homopolymers, copolymers, terpolymers, and the like of the olefin monomeric units. Particularly preferred for preparation herein by the process of the present invention are polyethylenes. Such polyethylenes are defined as homopolymers of ethylene and interpolymers of ethylene and at least one alpha-olefin wherein the ethylene content is at least about 50% by weight of the total monomers involved. Exemplary alpha-olefins that may be utilized herein are propylene, 1-butene, 1-pentene, 1-hexene, 1-heptene, 1-octene, 4-methyl-1-pentene, 1-decene, 1-dodecene, 1-hexadecene and the like. Also utilizable herein are non-conjugated dienes and olefins formed in situ in the polymerization

medium. When olefins are formed in situ in the polymerization medium, the formation of polyethylenes containing long chain branching may occur.

The polymerization reaction of the present invention is carried out in the presence of a Ziegler-Natta catalyst. In the process of the invention, the catalyst
5 can be introduced in any manner known in the art. For example, the catalyst can be introduced directly into the fluidized bed reactor in the form of a solution, a slurry or a dry free flowing powder. The catalyst can also be used in the form of a deactivated catalyst, or in the form of a prepolymer obtained by contacting the catalyst with one or more olefins in the presence of a co-catalyst.

10 The Ziegler-Natta catalysts utilized herein are well known in the industry. The Ziegler-Natta catalysts in the simplest form are comprised of a component comprising at least one transition metal and a co-catalyst comprising at least one organometallic compound. The metal of the transition metal component is a metal selected from Groups 4, 5, 6, 7, 8, 9 and/or 10 of the Periodic Table of the
15 Elements, as published in "Chemical and Engineering News", 63(5), 27, 1985. In this format, the groups are numbered 1-18. Exemplary of such transition metals are titanium, zirconium, vanadium, chromium, manganese, iron, cobalt, nickel, and the like, and mixtures thereof. In a preferred embodiment the transition metal is selected from the group consisting of titanium, zirconium, vanadium and
20 chromium, and in a still further preferred embodiment, the transition metal is titanium. The Ziegler-Natta catalyst can optionally contain magnesium and/or chlorine. Such magnesium and chlorine containing catalysts may be prepared by any manner known in the art.

The co-catalyst used in the process of the present invention can be any
25 organometallic compound, or mixtures thereof, that can activate the transition metal component in a Ziegler-Natta catalyst in the polymerization of olefins. In particular, the organometallic co-catalyst compound that is reacted with the transition metal component contains a metal selected from Groups 1, 2, 11, 12, 13 and/or 14 of the above described Periodic Table of the Elements. Exemplary of

such metals are lithium, magnesium, copper, zinc, boron, silicon and the like, or mixtures thereof.

Preferred for use herein are the organoaluminum compounds such as the trialkylaluminum compounds and dialkylaluminum monohalides. Examples
5 include trimethylaluminum, triethylaluminum, trihexylaluminum, dimethylaluminum chloride, and diethylaluminum chloride.

The transition metal component, with or without co-catalyst, may be deposited on a carrier. In so doing, there may be used as the carrier any catalyst carrier compound known in the art. Exemplary carriers are magnesium oxides,
10 magnesium oxyhalides and magnesium halides, particularly magnesium chloride. The catalyst, with or without the carrier, may be supported on a solid porous support, such as silica, alumina and the like.

The catalyst system may contain conventional components in addition to the transition metal component and the organometallic co-catalyst component. For
15 example, there may be added any internal or external electron donor(s) known in the art, any halogenated hydrocarbon(s), and the like.

The Ziegler-Natta catalyst may be prepared by any method known in the art. The catalyst can be in the form of a solution, a slurry or a dry free flowing powder. The amount of Ziegler-Natta catalyst used is that which is sufficient to
20 allow production of the desired amount of polymeric material.

The polymerization reaction is carried out in the presence of a specified compound selected from the following. It is essential that the specified compound be utilized in an amount that will be sufficient to result in the production of polyolefins characterized by having a molecular weight distribution narrower than
25 would be obtained in the absence of utilizing the specified compound in the specified amount. The molecular weight distribution of the polyolefins herein is evidenced by the melt flow ratio (MFR) values of the polyolefins.

The compounds that are used, in amounts effective to narrow the molecular weight distribution (MWD) of the polyolefins of the present process, are as follow:

- a) A compound containing an element of Group 14 (carbon, silicon, germanium, tin and lead) selected from the following:
- i) An oxide of germanium, tin and lead such as GeO, GeO₂, SnO, SnO₂, PbO, PbO₂, Pb₂O₃ and Pb₃O₄;
 - 5 ii) Cyanogen (C₂N₂);
 - iii) An oxide or imide of carbon of formula CE or C₃E₂ where E = O and NR, R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms, such as CO, C₃O₂, CNH, CNF, CNPh, CNMe, CNSiMe₃, CNBt₂, and CN-cyclohexyl;
 - 10
 - 15 iv) A sulfur, selenium, or tellurium containing chalcogenide of carbon, silicon, germanium, tin and lead such as CS, CS₂, CSe, CTe, SiS₂, GeS₂, SnS₂, CSe₂, and CTe₂;
 - v) A chalcogenide of carbon, silicon, germanium, tin and lead containing more than one chalcogen such as COS, COSe, CSSe, COTe, CSt₂, CSeTe;
 - 20
 - vi) A chalcogenide imide of carbon, silicon, germanium, tin and lead having the formula C(E)(X) where E = O, S, Se, Te, or NR; X = NR' where R and/or R' is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms, such as C(N-cyclohexyl)₂, CO(NMe), CS(NPh), CSe(NCSiMe₃), and CTe(NBt₂);
 - 25
 - vii) A chalcogenyl halide or imidohalide of carbon, silicon, germanium, tin and lead of the formula C(E)X₂ where E = O, S, Se, Te, and NR; R
 - 30

- is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms; and X is a halogen, such as COF_2 , COCl_2 , $\text{C}_2\text{O}_2\text{Cl}_2$, $\text{C}_2\text{O}_2\text{F}_2$, GeOCl_2 , $\text{C}(\text{NCMe}_3)\text{Cl}_2$, $\text{C}(\text{NCl})\text{Br}_2$, $\text{C}_2\text{O}(\text{NSiMe}_3)\text{Cl}_2$, $\text{C}_2(\text{N-cyclohexyl})_2\text{Cl}_2$, $\text{Si}(\text{NPh})\text{Cl}_2$, and $\text{Ge}(\text{NPh})\text{F}_2$;
- b) A pnictogen containing compound (a pnictogen is an element of Group 15) selected from the following:
- i) Elemental forms of phosphorus, arsenic, antimony and bismuth;
 - ii) An oxide of nitrogen, phosphorus, arsenic, antimony and bismuth such as NO , NO_2 , N_2O , N_2O_3 , N_2O_4 , N_2O_5 , P_4O_n where $n = 6-10$, AsO , As_4O_6 or As_2O_3 , As_4O_{10} or As_2O_5 , Sb_2O_3 , Sb_2O_4 , Sb_2O_5 , Bi_2O_5 , and Bi_2O_3 . Preferred for use herein is dinitrogen monoxide (N_2O);
 - iii) A nitrogen oxoacid or salt containing the anion thereof, such as HNO_2 , HNO_3 , NO_2^- , NO_3^- ;
 - iv) A halide of the formula E_nX_m , where E is nitrogen, phosphorus, arsenic, antimony or bismuth and X is a halogen or pseudohalogen, $n = 1$ to 10, and $m = 1$ to 20, such as NF_3 , N_2F_4 , NCl_3 , PF_3 , PF_5 , P_2F_4 , PCl_3 , PCl_5 , P_2Cl_4 , PBr_5 , AsF_3 , AsF_5 , AsCl_5 , As_2I_2 , SbF_3 , SbF_5 , SbCl_5 , BiF_3 , BiF_5 , BiBr_3 , BiI_2 , and BiI_3 ;
 - v) A chalcogenide or imide of nitrogen, phosphorus, arsenic, antimony and bismuth of the general formula E_nY_m , where $\text{E} = \text{N}, \text{P}, \text{As}, \text{Sb}, \text{and Bi}$; $\text{Y} = \text{S}, \text{Se}, \text{Te}, \text{and NR}$; $n = 1$ to 10; $m = 1$ to 40; and R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms, such as P_4S_3 , P_4S_5 , P_4Se_5 , $\text{P}_4(\text{NCMe}_3)_n$ where $n = 6$ to 10, $\text{P}_4(\text{NPh})_n$ where $n = 6$ to 10, As_4S_3 , As_4S_4 , As_4S_5 , As_4Se_3 and As_4Se_4 ;

- vi) A chalcogenyl or imido compound of nitrogen, phosphorus, arsenic, antimony and bismuth having the formula $E_n Y_m X_q$, where E = N, P, As, Sb and Bi; Y = O, S, Se, Te and NR; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms; $n = 1$ to 20; $m = 1$ to 40; $q = 1$ to 40; and R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms, such as NOF, NOCl, NOBr, F_3NO , POF_3 , $POCl_3$, $POBr_3$, $PSCl_3$, $PO(OCN)_3$, $PO(CN)_3$, $P(NPh)Cl_3$, $P(NSiMe_3)Cl_3$, $P(NPh)F_3$, $P(NPh)Br_3$, $P(NBEt_2)Cl_3$, $PSCl_3$, $AsOF_3$, PO_2Cl , $P(NCMe_3)_2Cl$, $P(NCMe_3)_2Me$, $As_2O_3Cl_4$, $POCl$, $P(NCMe_3)Cl$, $P(NPh)Cl$, $P(NSiMe_3)Me$, $PSeCl$, $BiOCl$ and $SbOCl$;
- vii) An interpnictogen (compounds containing at least 2 elements of Group 15) such as PN, AsN;
- viii) A phosphazene of the general formula $(NPR_2)_x$ wherein R = halogen, or alkyl or aryl group containing up to 50 non-hydrogen atoms, and x is at least 2;
- ix) A compound of the general formula $A(E)X_3$ where A = P, As, Sb, and Bi; E = NR or CR_2 , R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-

- hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms; and X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms, such as $P(CH_2)Ph_3$, $P(CH_2)Me_3$, $P(CH_2)(OPh)_3$, $P(CH_2)(NMe_2)_3$, $P(CHSiMe_3)Me_3$, $P(CHBEt_2)Me_3$, $P(CHMe)Ph_3$, $P(CHPh)Ph_3$, $P(CHMe)Me_3$, $P(NCMe_3)Ph_3$, $P(NPh)Ph_3$, $P(NSiMe_3)Me_3$, $P(NCMe_3)Me_3$, $P(NCMe_3)Ph_3$, $P(NCMe_3)Cl_3$, $P(NCMe_3)Br_2Me$, $P(NBPh_2)Cl_3$, $P(NBPr_2)Et_3$, $P(NCMe_3)(OCMe_3)_3$, $As(CHMe)Ph_3$, $Sb(CHMe)Ph_3$, $As(NCMe_3)Ph_3$;
- x) A pnictogen hydride such as H_3N , H_3P , H_3As , H_3Sb , H_3Bi ;
- c) A chalcogen containing compound (a chalcogen is an element of Group 16) selected from the following:
- i) An elemental form of oxygen, sulfur, selenium, and tellurium such as O_2 , O_3 , S_n where $n = 1$ to 30 , Se_2 , Se_8 , and Te_2 . Other allotropes of these elements may also be used;
- ii) An interchalcogen (compounds containing at least 2 Group 16 elements) such as SO , SO_2 , SO_3 , SeO_2 , SeO_3 , TeO_2 , S_nO_2 , where $n = 5$ to 8);
- iii) A compound containing one or more chalcogens and one or more halogens of formula E_nX_m where $E = O, S, Se, \text{ and } Te$; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50

- non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms, $n = 1$ to 10, $m = 1$ to 20, such as SOCl_2 , SO_2Cl_2 , SOF_2 , Se_2F_2 , S_2Cl_2 , S_2F_4 , S_4Cl_4 , S_4F_4 , Se_2Br_2 , S_2F_{10} , OF_2 , SF_2 , SF_4 , SF_6 , SeF_2 , SeF_4 , SeF_3 , TeF_4 , TeF_6 , SCl_4 , TeI_4 and mixed halides such as SF_5Cl , SF_3Cl , SO_2SbF_5 ;
- iv) A compound of general formula EOX_2 where $\text{E} = \text{O}, \text{S}, \text{Se},$ and Te ; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms, such as SOF_2 , SOCl_2 , SOBr_2 , SOFCl , SeOF_2 , SeOCl_2 , SeOBr_2 , SOMe_2 , SO_2Me_2 , SO_2Ph_2 , $\text{SO}_2(\text{OEt})_2$, $\text{SO}_2(\text{SPh})_2$, and $\text{SO}(\text{SiMe}_3)_2$;
- v) A compound of general formula EOX_4 where $\text{E} = \text{S}, \text{Se},$ and Te ; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms, such as SOF_4 , SeOF_4 , and TeOF_4 ;
- vi) A compound of general formula EO_2X_2 where $\text{E} = \text{S}, \text{Se},$ and Te ; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50

- non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms, such as SO_2F_2 , SO_2Cl_2 , SO_2FCl , SO_2FBr , SeO_2F_2 ;
- vii) A Sulfur-Nitrogen compound such as NS , NSCl , $\text{S}_3\text{N}_2\text{Cl}_2$, S_4N_4 , $\text{S}_4\text{N}_3\text{Cl}$, S_2N_2 , $\text{S}_4\text{N}_4\text{H}_2$, $\text{N}_4\text{S}_4\text{F}_4$, $\text{S}_3\text{N}_3\text{Cl}_3$, S_4N_2 , NSF , S_7NH , SF_5NF_2 , $(\text{SN})_x$ where x is greater than 1;
- viii) A compound of the formula $\text{S}(\text{NR})_n\text{X}_m$ where $n = 1$ to 3 ; $m = 0$ to 6 ; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms; and R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms, such as $\text{CF}_3\text{N}=\text{SF}_2$, $\text{RCF}_2\text{N}=\text{SF}_2$, $\text{S}(\text{NSiMe}_3)_2$, $\text{S}(\text{NSiMe}_3)_3$, $\text{S}(\text{NCMe}_3)_2$, $\text{S}(\text{NCMe}_3)_3$, $\text{S}(\text{NSO}_2\text{-C}_6\text{H}_4\text{-Me})_2$, $\text{S}(\text{NSO}_2\text{-C}_6\text{H}_4\text{-Me})_3$, and $\text{S}(\text{NCH}(\text{CF}_3)_2)_3$;
- ix) A sulfur oxoacid, peroxyacid, and salts containing the anions thereof, such as H_2SO_3 , HSO_3^- , SO_3^{2-} , H_2SO_4 , HSO_4^- , SO_4^{2-} , $\text{H}_2\text{S}_2\text{O}_3$, HS_2O_3^- , $\text{S}_2\text{O}_3^{2-}$, $\text{H}_2\text{S}_2\text{O}_4$, HS_2O_4^- , $\text{S}_2\text{O}_4^{2-}$, $\text{H}_2\text{S}_2\text{O}_5$, HS_2O_5^- , $\text{S}_2\text{O}_5^{2-}$, $\text{H}_2\text{S}_2\text{O}_6$, HS_2O_6^- , $\text{S}_2\text{O}_6^{2-}$, $\text{H}_2\text{S}_2\text{O}_7$, HS_2O_7^- , $\text{S}_2\text{O}_7^{2-}$, $\text{H}_2\text{S}_{n+2}\text{O}_6$ where n is greater than 0, $\text{HS}_{n+2}\text{O}_6^-$ where n is greater than 0, $\text{S}_{n+2}\text{O}_6^{2-}$ where n is greater than 0, H_2SO_5 , HSO_5^- , SO_5^{2-} , $\text{H}_2\text{S}_2\text{O}_8$, HS_2O_8^- , $\text{S}_2\text{O}_8^{2-}$;

- 20 -

- x) A selenium oxoacid, peroxyacid, and salts containing the anions thereof, such as H_2SeO_3 , HSeO_3^- , SeO_3^{2-} , HSeO_3^- , H_2SeO_4 , HSeO_4^- , SeO_4^{2-} ;
- xi) A tellurium oxoacid, peroxyacid, and salts containing the anions thereof, such as H_2TeO_3 , HTeO_3^- , TeO_3^{2-} , H_2TeO_4 , HTeO_4^- , TeO_4^{2-} ;
- 5 xii) A chalcogen hydride, such as SH_2 , SeH_2 , TeH_2 , SOH_2 , SeOH_2 , and SSeH_2 ;
- d) A halogen containing compound (a halogen is an element of Group 17) selected from the following:
- i) Elemental forms of fluorine, chlorine, bromine, iodine, and astatine, such as F_2 , Cl_2 , Br_2 , I_2 , and At_2 or any other allotrope;
- 10 ii) An interhalogen (compounds containing at least 2 Group 17 elements), salts containing their cations, and salts containing the anions thereof, such as ClF , ClF_3 , ClF_5 , BrF , BrF_3 , BrF_5 , IF , IF_3 , IF_5 , IF_7 , BrCl_3 , ICl , ICl_3 , I_2Cl_6 , IF_4^+ , BrF_2^+ , BrF_4^+ , IF_2^+ , IF_6^+ , Cl_2F^+ , ClF_2^- , ClF_4^- , BrF_2^- , BrF_4^- , BrF_6^- , IF_2^- , IF_4^- , IF_3^- , IF_6^- , IF_8^{2-} ;
- 15 iii) A salt containing polyhalide cations and/or anions, such as Br_2^+ , I_2^+ , Cl_3^+ , Br_3^+ , I_3^+ , Cl_3^- , Br_3^- , I_3^- , Br_2Cl^+ , BrCl_2^+ , ICl_4^+ , IBrCl_3^+ , $\text{I}_2\text{Br}_2\text{Cl}^+$, I_4Cl^+ , I_5^+ , ICl_2^+ , IBrCl^+ , IBr_2^+ , I_2Cl^+ , I_2Br^+ , I_2Cl^- , IBr_2^- , ICl_2^- , IBCl^{2-} , IBrF^- , I_5^- ;
- 20 iv) A homoleptic or heteroleptic halogen oxide, salts containing the cations thereof, and salts containing the anion thereof, such as FClO_2 , ClO_2^+ , F_2ClO_2^- , F_3ClO , FClO_3 , F_3ClO_2 , FBrO_2 , FBrO_3 , FIO_2 , F_3IO , FIO_3 , F_3IO_2 , F_5IO , ClF_3O , $\text{I}_2\text{O}_4\text{F}_5$, F_2O , F_2O_2 , Cl_2O , ClO_2 , Cl_2O_4 , Cl_2O_6 , Cl_2O_7 , Br_2O , Br_3O_8 or BrO_3 , BrO_2 , I_2O_4 , I_4O_9 , I_2O_5 , Br_2O_3 ;
- 25 v) An oxoacid and salts containing the anions thereof, such as HOF , OF^- , HOCl , HClO_2^- , HClO_3 , ClO^- , ClO_2^- , ClO_3^- , HBrO , HBrO_2 , HBrO_3 , HBrO_4 , BrO^- , BrO_2^- , BrO_3^- , BrO_4^- , HIO , HIO_3 , HIO_4 , IO^- , IO_3^- , IO_4^- , HAtO , HAtO_3 , HAtO_4 , AtO_3^- , AtO_4^- , AtO^- ;
- vi) A hydrogen halide, such as HF , HCl , HBr , HI , HAt ;

- vii) NH_4F , SF_4 , SbF_3 , AgF_2 , KHF_2 , ZnF_2 , AsF_3 , and salts containing the HF_2^- anion;
- viii) A hydrohalic acid, such as $\text{HF}_{(\text{aq})}$, $\text{HCl}_{(\text{aq})}$, $\text{HBr}_{(\text{aq})}$, $\text{HI}_{(\text{aq})}$, $\text{HAt}_{(\text{aq})}$;
- e) A noble gas containing compound (a noble gas is an element of Group 18) selected from the following:
- 5 i) A He, Ne, Ar, Kr, Xe, and Rn oxide, salts containing the cations thereof, and salts containing the anions thereof, such as XeO_3 , XeO_2 , XeO_4 , XeO_4^{2-} , and XeO_6^{4-} ;
- 10 ii) A He, Ne, Ar, Kr, Xe, and Rn halide, salts containing the cations thereof, and salts containing the anions thereof, such as KrF_2 , XeF_2 , XeCl_2 , XeF_4 , XeF_6 , KrF^+ , Kr_2F_3^+ , XeF^+ , XeF_5^+ , Xe_2F_3^+ , XeF_7^- , XeF_8^{2-} , $\text{Xe}_2\text{F}_{11}^+$;
- 15 iii) A He, Ne, Ar, Kr, Xe, and Rn chalcogenyl halide, salts containing the cations thereof, and salts containing the anions thereof, such as XeOF_4 , XeO_2F_2 , XeO_3F_2 , XeO_3F^- , XeOF_3^+ , XeO_2F^+ ;
- f) A product obtained by reacting a material selected from the group consisting of water, alcohol, hydrogen sulfide and a thiol with any compound selected from a) i – vii; b) i – x; c) i – xii; d) i – viii; e) i – iii; and salts thereof containing the corresponding anion;
- 20 g) An organic peroxide;
- h) Water; and
- i) Mixtures thereof.

In the process of the present invention it has been found suitable to add, generally, to the polymerization medium the compound(s) in an amount from about 1 ppm to about 10,000 ppm by molar ratio in the fluid phase(s) of the polymerization medium, in order to produce polyolefins having narrowed molecular weight distributions. The fluid phase may be gas or liquid phase.

In a further embodiment of the present invention it has been found suitable to add, generally, to the gas phase polymerization medium the compound(s) in an

amount from about 1 ppm to about 10,000 ppm by volume, in order to produce polyolefins having narrowed molecular weight distributions.

Polyethylenes produced by the present process are not only characterized by narrower molecular weight distribution, but also, generally, a reduced n-hexane
5 soluble polymeric fraction.

In carrying out the polymerization reaction of the present process there may be added other conventional additives generally utilized in processes for polymerizing olefins. Specifically there may be added any halogenated hydrocarbon, including those mentioned hereinbefore, and preferably, chloroform.
10 Further, there may be added any external or internal electron donor, or mixtures of electron donors, such as those mentioned hereinbefore, and preferably, tetrahydrofuran.

There are also provided herein novel polyethylenes. These polyethylenes are homopolymers of ethylene and copolymers of ethylene and at least one or more
15 alpha-olefins having 3 to 16 carbon atoms wherein ethylene comprises at least about 50% by weight of the total monomers involved.

The novel copolymers of ethylene and 1-hexene of the present invention, wherein ethylene comprises at least about 50% by weight of the copolymer, are further characterized by having a differential scanning calorimetry (DSC) melt
20 transition temperature, T_m , of about 116°C to about 123°C, a density of about 0.880g/cc to about 0.930g/cc, a n-hexane extractable of from 0 to about 6 weight percent, and a melt flow ratio of about 26 to about 34.

In a further embodiment the novel copolymers of ethylene and 1-hexene of the present invention are further characterized by having a DSC melt transition
25 temperature, T_m , of about 119°C to about 121°C, a density of about 0.905g/cc to about 0.920g/cc, a n-hexane extractable of from 0 to about 3 weight percent, and a melt flow ratio of about 26 to about 32.

In a further embodiment, there are provided herein novel copolymers of ethylene and an olefin having from 3 to 16 carbon atoms, wherein ethylene

comprises at least 99% by weight of the copolymer, and the copolymer has a melt flow ratio of from about 22 to about 26.

In a still further embodiment herein, there are provided novel copolymers of ethylene and at least one or more olefin(s) having 5 to 16 carbon atoms, wherein
5 ethylene comprises at least about 50% by weight of the copolymer, characterized by having a DSC melt transition temperature of about 116°C to about 123°C, a density of from about 0.880g/cc to about 0.930g/cc, a n-hexane extractable of from 0 to about 6 weight percent, and a melt flow ratio of from about 26 to about 34.

Any conventional additive may be added to the polyolefins obtained by the
10 present invention. Examples of the additives include nucleating agents, heat stabilizers, antioxidants of phenol type, sulfur type and phosphorus type, lubricants, antistatic agents, dispersants, copper harm inhibitors, neutralizing agents, foaming agents, plasticizers, anti-foaming agents, flame retardants, crosslinking agents, flowability improvers such as peroxides, ultraviolet light absorbers, light
15 stabilizers, weathering stabilizers, weld strength improvers, slip agents, anti-blocking agents, antifogging agents, dyes, pigments, natural oils, synthetic oils, waxes, fillers and rubber ingredients.

The novel polyethylenes of the present invention may be fabricated into films by any technique known in the art. For example, films may be produced by
20 the well known cast film, blown film and extrusion coating techniques.

Further, the novel polyethylenes may be fabricated into other articles of manufacture, such as molded articles, by any of the well known techniques.

The invention will be more readily understood by reference to the following examples. There are, of course, many other forms of this invention which will
25 become obvious to one skilled in the art, once the invention has been fully disclosed, and it will accordingly be recognized that these examples are given for the purpose of illustration only, and are not to be construed as limiting the scope of this invention in any way.

In the following examples the test procedures listed below were used in evaluating the analytical properties of the polyolefins herein and in evaluating the physical properties of the films of the examples.

- 5 a) Dart Impact is determined according to ASTM D-1709, Method A; with a 38.1 mm dart, and a drop height of 0.66 meter. Film thickness of about 1 mil;
- b) Density is determined according to ASTM D-4883 from a plaque made according to ASTM D1928;
- 10 c) Melt Index (MI), I_2 , is determined in accord with ASTM D-1238, condition E, measured at 190°C, and reported as decigrams per minute;
- d) High Load Melt Index (HLMI), I_{21} , is measured in accord with ASTM D-1238, Condition F, measured at 10.0 times the weight used in the melt index test above;
- 15 e) Melt Flow Ratio (MFR) = I_{21}/I_2 or High Load Melt Index/Melt Index; and
- f) n-Hexane Extractable – is determined in accordance with 21 CFR 177.1520 (Option 2). More particularly, an approximately 1 square inch film test specimen having a thickness ≤ 4 mils weighing 2.5 ± 0.05 grams is placed into a tared sample basket and accurately weighed to the
20 nearest 0.1 milligram. The sample basket containing the test specimen is then placed in a 2-liter extraction vessel containing approximately 1 liter of n-hexane. The basket is placed such that it is totally below the level of n-hexane solvent. The sample resin film is extracted for 2 hours at $49.5 \pm 0.5^\circ\text{C}$ and then the basket is raised above the solvent level to
25 drain momentarily. The basket is removed and the contents are rinsed by immersing several times in fresh n-hexane. The basket is allowed to dry between rinsing. The excess solvent is removed by briefly blowing the basket with a stream of nitrogen or dry air. The basket is placed in the vacuum oven for 2 hours at $80 \pm 5^\circ\text{C}$. After 2 hours, it is removed
30 and placed in a desiccator to cool to room temperature (about 1 hour).

- 25 -

After cooling, the basket is reweighed to the nearest 0.1 milligram. The percent n-hexane extractables content is then calculated from the weight loss of the original sample.

- 5 g) DSC Melt Transition Temperature (T_M) was determined according to ASTM D-3418-97. The transition, T_M , was measured on the second heat cycle.

The Ziegler-Natta catalyst used in Examples 1-7 herein was prepared in accordance with Example 1-a of European Patent Application EP 0 703 246 A1.

- 10 The prepolymer used in Examples 1-7 herein was prepared in accordance with Example 1-b of European Patent Application EP 0 703 246 A1. A prepolymer containing about 34 grams of polyethylene per millimole of titanium, with a tri-n-octylaluminum (TnOA) to titanium molar ratio of about 1.1, was thus obtained.

- 15 The polymerization process utilized in Examples 1-7 herein was carried out in a fluidized-bed reactor for gas-phase polymerization, consisting of a vertical cylinder of diameter 0.74 meters and height 7 meters and surmounted by a velocity reduction chamber. The reactor is provided in its lower part with a fluidization grid and with an external line for recycling gas, which connects the top of the velocity reduction chamber to the lower part of the reactor, at a point below the fluidization grid.
- 20 The recycling line is equipped with a compressor for circulating gas and a heat transfer means such as a heat exchanger. In particular the lines for supplying ethylene, 1-hexene, hydrogen and nitrogen, which represent the main constituents of the gaseous reaction mixture passing through the fluidized bed, feed into the recycling line.

- 25 Above the fluidization grid, the reactor contains a fluidized bed consisting of about 800 pounds of a low-density polyethylene powder made up of particles with a weight-average diameter of about 0.7 mm. The gaseous reaction mixture, which contains ethylene, 1-hexene, hydrogen, nitrogen and minor amounts of other components, passes through the fluidized bed under a pressure of about 295 psig
- 30 with an ascending fluidization speed of about 1.9 ft/s.

A catalyst is introduced intermittently into the reactor, the said catalyst comprising magnesium, chlorine and titanium and having been converted beforehand to a prepolymer, as described above, containing about 34 grams of polyethylene per millimole of titanium and an amount of tri-n-octylaluminum (TnOA) such that the molar ratio, Al/Ti, is equal to about 1.1. The rate of introduction of the prepolymer into the reactor is adjusted to achieve the desired production rate. During the polymerization, a solution of trimethylaluminum (TMA) in n-hexane, at a concentration of about 2 weight percent, is introduced continuously into the line for recycling the gaseous reaction mixture, at a point situated downstream of the heat transfer means. The feed rate of TMA is expressed as a molar ratio of TMA to titanium (TMA/Ti), and is defined as the ratio of the TMA feed rate (in moles of TMA per hour) to the prepolymer feed rate (in moles of titanium per hour). Simultaneously, a solution of chloroform (CHCl_3) in n-hexane, at a concentration of about 0.5 weight percent, is introduced continuously into the line for recycling the gaseous reaction mixture. The feed rate of CHCl_3 is expressed as a molar ratio of CHCl_3 to titanium (CHCl_3/Ti), and is defined as the ratio of the CHCl_3 feed rate (in moles of CHCl_3 per hour) to the prepolymer feed rate (in moles of titanium per hour). Likewise, a solution of tetrahydrofuran (THF) in n-hexane, at a concentration of about 1 weight percent, can be introduced continuously into the line for recycling the gaseous reaction mixture. The feed rate of THF is expressed as a molar ratio of THF to titanium (THF/Ti), and is defined as the ratio of the THF feed rate (in moles of THF per hour) to the prepolymer feed rate (in moles of titanium per hour). Furthermore, the compound added to narrow the molecular weight distribution of the polyolefin, depending on its physical state, can be added as a gas, liquid or as a solution in a suitable solvent into the line for recycling the gaseous reaction mixture or directly into the reactor. In Examples 3-7 herein, dinitrogen monoxide (N_2O) was added as a gas to the line for recycling the gaseous reaction mixture in amounts to narrow the molecular weight distribution of the polyethylene. The concentration of N_2O in the gas phase polymerization medium is expressed in units of parts per million (ppm) by volume. Polyethylenes

of ethylene and 1-hexene, having densities of 0.917 g/cc, were manufactured at a rate of about 150 to about 200 pounds per hour in the following examples.

The productivity of the prepolymer (Productivity) is the ratio of pounds of polyethylene produced per pound of prepolymer added to the reactor. The activity of the catalyst is expressed as grams of polyethylene per millimole titanium per hour per 100 psia of ethylene pressure.

EXAMPLE 1

The gas phase process conditions are given in Table 1 and the resin properties are given in Table 2. The molar ratio of trimethylaluminum (TMA) to titanium (TMA/Ti) was 3. The molar ratio of chloroform (CHCl_3) to titanium (CHCl_3/Ti) was 0.03. The operation was conducted without the addition of an external electron donor. 1-Hexene was used as comonomer. Under these conditions a polyethylene free from agglomerate was withdrawn from the reactor at a rate of 150 lb/h (pounds per hour). The productivity of the prepolymer was 375 pounds of polyethylene per pound of prepolymer which corresponds to an activity of 2311 grams of polyethylene per millimole of titanium per hour per 100 psia of ethylene partial pressure $[\text{gPE}/(\text{mmoleTi}\cdot\text{h}\cdot 100\text{P}_{\text{C}_2})]$.

The polyethylene had a density of 0.917 g/cc and a melt index $\text{MI}_{2.16, I_2}$ of 0.9 dg/min. The Melt Flow Ratio, I_{21}/I_2 , was 33 and the n-hexane extractables were 2.6 % by weight. The DSC melt transition temperature (T_m) was 124.5 °C.

EXAMPLE 2

The gas phase process conditions are given in Table 1 and the resin properties are given in Table 2. The molar ratio TMA/Ti was 7. The molar ratio CHCl_3/Ti was 0.06. The molar ratio of tetrahydrofuran (THF) to titanium (THF/Ti) was 1. 1-Hexene was used as comonomer. Under these conditions a polyethylene free from agglomerate was withdrawn from the reactor at a rate of 192 lb/h. The productivity of the prepolymer was 231 pounds of polyethylene per pound of prepolymer which corresponds to an activity of 1800 $[\text{gPE}/(\text{mmoleTi}\cdot\text{h}\cdot 100\text{P}_{\text{C}_2})]$.

The polyethylene had a density of 0.917 g/cc and a melt index $MI_{2.16}$, I_2 , of 0.9 dg/min. The Melt Flow Ratio, I_{21}/I_2 , was 31 and the n-hexane extractables were 2.0 % by weight. The DSC melt transition temperature (T_m) was 123.9 °C.

5

EXAMPLE 3

The gas phase process conditions are given in Table 1 and the resin properties are given in Table 2. The molar ratio TMA/Ti was 7. The molar ratio $CHCl_3$ /Ti was 0.06. The molar ratio THF/Ti was 1. The concentration of dinitrogen monoxide (N_2O) in the polymerization medium was 70 ppm by volume. 10 1-Hexene was used as comonomer. Under these conditions a polyethylene free from agglomerate was withdrawn from the reactor at a rate of 180 lb/h. The productivity of the prepolymer was 79 pounds of polyethylene per pound of prepolymer which corresponds to an activity of 609 [gPE/(mmoleTi·h·100P_{C2})].

The polyethylene had a density of 0.917 g/cc and a melt index $MI_{2.16}$, I_2 , of 15 0.9 dg/min. The Melt Flow Ratio, I_{21}/I_2 , was 28 and the n-hexane extractables were 1.1 % by weight. The DSC melt transition temperature (T_m) was 122.3 °C.

EXAMPLE 4

The gas phase process conditions are given in Table 1 and the resin properties are given in Table 2. The molar ratio TMA/Ti was 7. The molar ratio 20 $CHCl_3$ /Ti was 0.06. The molar ratio THF/Ti was 0. The concentration of N_2O in the polymerization medium was 130 ppm by volume. 1-Hexene was used as comonomer. Under these conditions a polyethylene free from agglomerate was withdrawn from the reactor at a rate of 211 lb/h. The productivity of the 25 prepolymer was 121 pounds of polyethylene per pound of prepolymer which corresponds to an activity of 1116 [gPE/(mmoleTi·h·100P_{C2})].

The polyethylene had a density of 0.917 g/cc and a melt index $MI_{2.16}$, I_2 , of 0.9 dg/min. The Melt Flow Ratio, I_{21}/I_2 , was 28 and the n-hexane extractables were 1.6 % by weight. The DSC melt transition temperature (T_m) was 122.7 °C.

30

EXAMPLE 5

The gas phase process conditions are given in Table 1 and the resin properties are given in Table 2. The molar ratio TMA/Ti was 7. The molar ratio CHCl_3/Ti was 0.06. The molar ratio THF/Ti was 0. The concentration of N_2O in the polymerization medium was 210 ppm by volume. 1-Hexene was used as comonomer. Under these conditions a polyethylene free from agglomerate was withdrawn from the reactor at a rate of 194 lb/h. The productivity of the prepolymer was 124 pounds of polyethylene per pound of prepolymer which corresponds to an activity of 1038 $[\text{gPE}/(\text{mmoleTi}\cdot\text{h}\cdot 100\text{P}_{\text{C}_2})]$.

The polyethylene had a density of 0.917 g/cc and a melt index $\text{MI}_{2.16}$, I_2 , of 0.9 dg/min. The Melt Flow Ratio, I_{21}/I_2 , was 28 and the n-hexane extractables were 1.1 % by weight. The DSC melt transition temperature (T_m) was 122.2 °C.

EXAMPLE 6

The gas phase process conditions are given in Table 1 and the resin properties are given in Table 2. The molar ratio TMA/Ti was 7. The molar ratio CHCl_3/Ti was 0.06. The molar ratio THF/Ti was 0.3. The concentration of N_2O in the polymerization medium was 300 ppm by volume. 1-Hexene was used as comonomer. Under these conditions a polyethylene free from agglomerate was withdrawn from the reactor at a rate of 192 lb/h. The productivity of the prepolymer was 83 pounds of polyethylene per pound of prepolymer which corresponds to an activity of 471 $[\text{gPE}/(\text{mmoleTi}\cdot\text{h}\cdot 100\text{P}_{\text{C}_2})]$.

The polyethylene had a density of 0.917 g/cc and a melt index $\text{MI}_{2.16}$, I_2 , of 0.9 dg/min. The Melt Flow Ratio, I_{21}/I_2 , was 27 and the n-hexane extractables were 0.8% by weight. The DSC melt transition temperature (T_m) was 120.0 °C.

EXAMPLE 7

The gas phase process conditions are given in Table 1 and the resin properties are given in Table 2. The molar ratio TMA/Ti was 7. The molar ratio CHCl_3/Ti was 0.06. The molar ratio THF/Ti was 0.3. The concentration of N_2O in

the polymerization medium was 300 ppm by volume. 1-Hexene was used as comonomer. Under these conditions a polyethylene free from agglomerate was withdrawn from the reactor at a rate of 174 lb/h. The productivity of the prepolymer was 91 pounds of polyethylene per pound of prepolymer which
5 corresponds to an activity of 470 [gPE/(mmoleTi·h·100P_{C2})].

The polyethylene had a density of 0.917 g/cc and a melt index MI_{2.16}, I₂, of 0.6 dg/min. The Melt Flow Ratio, I₂₁/I₂, was 28 and the n-hexane extractables were 0.5% by weight. The DSC melt transition temperature (T_m) was 119.5 °C.

Table 1: Reactor Conditions for Examples 1 through 7

		Example						
5		1	2	3	4	5	6	7
	Reactor Pressure (psig)	290	296	295	294	295	297	296
	Reactor Temperature (°C)	84	84	84	84	84	86	86
	Fluidization Velocity (ft/sec)	1.8	1.9	1.9	1.9	1.9	1.8	1.8
10	Fluidized Bulk Density (lb/ft ³)	17.0	17.8	17.1	17.5	16.7	15.2	14.9
	Reactor Bed Height (ft)	9.4	10.2	10.2	10.0	10.4	12.8	12.9
	Ethylene (mole%)	38	32	32	32	32	41	41
	H ₂ /C ₂ (molar ratio)	0.178	0.157	0.140	0.113	0.110	0.080	0.063
	C ₆ /C ₂ (molar ratio)	0.191	0.153	0.138	0.128	0.124	0.115	0.112
15	TMA/Ti (molar ratio)	3	7	7	7	7	7	7
	CHCl ₃ /Ti	0.03	0.06	0.06	0.06	0.06	0.06	0.06
	THF/Ti (molar ratio)	0	1	1	0	0	0.3	0.3
	N ₂ O (ppm by volume)	0	0	70	130	210	300	300
	Prepolymer Rate (lb/h)	0.4	0.83	2.29	1.74	1.56	2.30	1.92
20	Production Rate (lb/h)	150	192	180	211	194	192	174
	Productivity (mass ratio)	375	231	79	121	124	83	91
	Space Time Yield (lb/h-ft ³)	3.6	4.0	3.8	4.6	4.0	3.2	2.9
	Activity*	2311	1800	609	1116	1038	471	470
25	Residual Titanium (ppm)	3.8	5.9	17.5	11.3	11.0	16.9	15.6
* units of grams PE/(mmoleTi-h-100P _{C2})								

* units of grams PE/(mmoleTi-h-100P_{C2})

Table 2: Resin Properties for LLDPE prepared in Examples 1 through 7

30	Example							
	1	2	3	4	5	6	7	
35	Density (g/cc)	0.917	0.917	0.917	0.917	0.917	0.917	0.917
	Melt Index, I ₂ (dg/min)	0.9	0.9	0.9	0.9	0.9	0.9	0.6
	Melt Flow Ratio (I ₂₁ /I ₂)	33	31	28	28	28	27	28
	n-Hexane Extractable (wt%)	2.9	2.0	1.1	1.6	1.1	0.8	0.5
	DSC Melt Trans., T _M (°C)	124.5	123.9	122.3	122.7	122.2	120.0	119.5
40	Dart Impact (g/mil)	200	330	380	400	580	1750	>2000

From the above data in the Examples and Tables 1 and 2 the following observations may be made. The addition of N₂O caused a narrowing of the molecular weight distribution as evidenced by the reduction in the melt flow ratio (I₂₁/I₂) values, caused a reduction in the n-hexane soluble polymeric fraction (wt% extractable), and caused a reduction in the DSC melt transition temperature (T_m) of the polyethylenes.

The combination of narrowed molecular weight distribution, reduced n-hexane extractables, and reduced DSC melt transition temperature (T_m) is indicative of a reduction of the compositional heterogeneity in the polyethylene.

Films prepared from the polyethylenes of the present invention are
5 generally characterized as having improved optical properties and improved strength properties which are particularly shown by the values of Dart Impact in Table2.

Articles such as molded items can also be prepared from the polyethylenes of the present invention.

10 In similar fashion polyolefins may be produced using any of the other compounds described herein. It is expected that the resultant polyolefins will likewise exhibit narrowed molecular weight distributions.

It is also expected that the activity of a given Ziegler-Natta catalyst can either increase or decrease upon the addition of the compounds described herein
15 depending on the transition metal, the co-catalyst type, the olefin type, the polymerization medium, the polymerization conditions, and the particular compound added to narrow the molecular weight distribution.

It should be clearly understood that the forms of the invention herein described are illustrative only and are not intended to limit the scope of the
20 invention. The present invention includes all modifications falling within the scope of the following claims.

CLAIMS

We claim:

1. A process for polymerizing at least one or more olefin(s) comprising
5 contacting, under polymerization conditions, the at least one or more olefin(s)
with at least one Ziegler-Natta catalyst comprised of a component comprising at
least one transition metal and a co-catalyst comprising at least one
organometallic compound, and a compound selected from the group consisting
of
 - 10 (a) An oxide of germanium, tin and lead;
 - (b) Cyanogen (C_2N_2);
 - (c) An oxide or imide of carbon of formula CE or C_3E_2 where $E = O$
and NR , R is hydrogen, a halogen, an alkyl group containing up to
15 50 non-hydrogen atoms, an aryl group containing up to 50 non-
hydrogen atoms, a silyl group containing up to 50 non-hydrogen
atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an
amino group containing up to 50 non-hydrogen atoms, a thiolato
group containing up to 50 non-hydrogen atoms, or a boryl group
containing up to 50 non-hydrogen atoms;
 - 20 (d) A sulfur, selenium, or tellurium containing chalcogenide of carbon,
silicon, germanium, tin and lead;
 - (e) A chalcogenide of carbon, silicon, germanium, tin and lead
containing more than one chalcogen;
 - (f) A chalcogenide imide of carbon, silicon, germanium, tin and lead
25 having the formula $C(E)(X)$ where $E = O, S, Se, Te$, or NR ; $X = NR'$
where R and/or R' is hydrogen, a halogen, an alkyl group containing
up to 50 non-hydrogen atoms, an aryl group containing up to 50
non-hydrogen atoms, a silyl group containing up to 50 non-
hydrogen atoms, or a boryl group containing up to 50 non-hydrogen
30 atoms;

- 34 -

- 5 (g) A chalcogenyl halide or imido halide of carbon, silicon, germanium, tin and lead of the formula $C(E)X_2$ where $E = O, S, Se, Te,$ and NR ; R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms; and X is a halogen;
- (h) An elemental form of phosphorus, arsenic, antimony and bismuth;
- (i) An oxide of nitrogen, phosphorus, arsenic, antimony and bismuth;
- 10 (j) A nitrogen oxoacid or salt containing the anion thereof;
- (k) A halide of the formula E_nX_m , where E is nitrogen, phosphorus, arsenic, antimony or bismuth and X is a halogen or pseudohalogen, $n = 1$ to 10, and $m = 1$ to 20;
- 15 (l) A chalcogenide or imide of nitrogen, phosphorus, arsenic, antimony and bismuth of the general formula E_nY_m , where $E = N, P, As, Sb,$ and Bi ; $Y = S, Se, Te$ and NR ; $n = 1$ to 10; $m = 1$ to 40; and R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 20 (m) A chalcogenyl or imido compound of nitrogen, phosphorus, arsenic, antimony and bismuth having the formula $E_nY_mX_q$, where $E = N, P, As, Sb$ and Bi ; $Y = O, S, Se, Te$ and NR ; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms; $n = 1$ to 20; $m = 1$ to 40; $q = 1$ to 40; and R is
- 25
- 30

- hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- (n) An interpnictogen;
- (o) A phosphazene of the general formula $(\text{NPR}_2)_x$ wherein R = halogen, or alkyl or aryl group containing up to 50 non-hydrogen atoms, and x is at least 2;
- (p) A compound of the general formula $\text{A}(\text{E})\text{X}_3$ where A = P, As, Sb, and Bi; E = NR or CR_2 , R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms; and X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- (q) A pnictogen hydride;
- (r) An elemental form of oxygen, sulfur, selenium, and tellurium;
- (s) An interchalcogen;

- 36 -

- 5 (t) A compound containing one or more chalcogens and one or more halogens of formula E_nX_m where $E = O, S, Se, \text{ and } Te$; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms, $n = 1$ to 10 , $m = 1$ to 20 ;
- 10 (u) A compound of general formula EOX_2 where $E = O, S, Se, \text{ and } Te$; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 15 (v) A compound of general formula EOX_4 where $E = S, Se, \text{ and } Te$; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 20 (w) A compound of general formula EO_2X_2 where $E = S, Se, \text{ and } Te$; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 25 (w) A compound of general formula EO_2X_2 where $E = S, Se, \text{ and } Te$; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 30 (w) A compound of general formula EO_2X_2 where $E = S, Se, \text{ and } Te$; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;

- 37 -

- group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- (x) A Sulfur-Nitrogen compound;
- 5 (y) A compound of the formula $S(NR)_nX_m$ where $n = 1$ to 3 ; $m = 0$ to 6 ; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms; and R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 10
- 15
- 20 (z) A sulfur oxoacid, peroxyacid, and salts containing the anions thereof;
- (aa) A selenium oxoacid, peroxyacid, and salts containing the anions thereof;
- (bb) A tellurium oxoacid, peroxyacid, and salts containing the anions thereof;
- 25
- (cc) A chalcogen hydride;
- (dd) An elemental form of fluorine, chlorine, bromine, iodine, and astatine;
- (ee) An interhalogen, salts containing their cations, and salts containing the anions thereof;
- 30

- 38 -

- (ff) A salt containing polyhalide cations and/or anions;
- (gg) A homoleptic or heteroleptic halogen oxide, salts containing the cations thereof, and salts containing the anion thereof;
- (hh) An oxoacid and salts containing the anions thereof;
- 5 (ii) A hydrogen halide;
- (jj) NH_4F , SF_4 , SbF_3 , AgF_2 , KHF_2 , ZnF_2 , AsF_3 , and salts containing the HF_2^- anion;
- (kk) A hydrohalic acid;
- (ll) A He, Ne, Ar, Kr, Xe, and Rn oxide, salts containing the cations thereof, and salts containing the anions thereof;
- 10 (mm) A He, Ne, Ar, Kr, Xe, and Rn halide, salts containing the cations thereof, and salts containing the anions thereof;
- (nn) A He, Ne, Ar, Kr, Xe, and Rn chalcogenyl halide, salts containing the cations thereof, and salts containing the anions thereof;
- 15 (oo) A product obtained by reacting a material selected from the group consisting of water, alcohol, hydrogen sulfide and a thiol with any of the above compounds and salts thereof containing the corresponding anion;
- (pp) An organic peroxide;
- 20 (qq) Water; and
- (rr) Mixtures thereof,

wherein the compound is present in an amount sufficient that the molecular weight distribution of the resulting polymeric product is narrower than would be obtained in the absence of the compound.

- 25 2. The process according to Claim 1 wherein the at least one transition metal is selected from Groups 4, 5, 6, 7, 8, 9 and 10 of the Periodic Table of the Elements, as defined herein.
- 3. The process according to Claim 1 wherein the metal of the at least one organometallic compound is selected from Groups 1, 2, 11, 12, 13 and 14 of the
- 30 Periodic Table of the Elements, as defined herein.

4. The process according to Claim 3 wherein the at least one organometallic compound is selected from the group consisting of trialkylaluminums, dialkylaluminum halides and alkylaluminum sesquihalides.
5. The process according to Claim 1 wherein the compound is a nitrogen oxide selected from the group consisting of nitrogen monoxide, nitrogen dioxide, dinitrogen monoxide, dinitrogen trioxide, dinitrogen tetroxide and dinitrogen pentoxide.
6. The process according to Claim 5 wherein the nitrogen oxide is dinitrogen monoxide.
- 10 7. The process according to Claim 1 wherein the compound is selected from the group consisting of CO, C₃O₂, COS, SO₂, and SO₃.
8. The process according to Claim 1 wherein the compound is selected from dioxygen and ozone.
9. The process according to Claim 1 further comprising the presence of at least one electron donor.
- 15 10. The process according to Claim 9 wherein at least one of the electron donors is tetrahydrofuran.
11. The process according to Claim 1 further comprising the presence of at least one halogenated hydrocarbon.
- 20 12. The process according to Claim 11 wherein at least one of the halogenated hydrocarbons is chloroform.
13. The process according to Claim 2 further comprising the presence of at least one electron donor and at least one halogenated hydrocarbon.
14. The process according to Claim 13 wherein the organometallic co-catalyst compound is trimethylaluminum, the electron donor is tetrahydrofuran, the halogenated hydrocarbon is chloroform and the compound is dinitrogen monoxide.
- 25 15. The process according to Claim 14 wherein the metal of the transition metal compound is titanium.

16. The process according to Claim 1 wherein the compound is present in the polymerization medium in an amount ranging from about 1 ppm to about 10,000 ppm by molar ratio in the fluid phase(s) of the polymerization medium.
17. The process according to Claim 1 wherein the polymerization conditions are gas phase.
18. The process according to Claim 17 wherein the compound is present in the gas phase polymerization medium in an amount ranging from about 1 ppm by volume to about 10,000 ppm by volume.
19. A process for narrowing molecular weight distribution of a polymer comprising at least one or more olefin(s) comprising contacting under polymerization conditions, the at least one or more olefin(s) with at least one Ziegler-Natta catalyst comprised of a component comprising at least one transition metal and a co-catalyst comprising at least one organometallic compound, and a compound selected from the group consisting of
- (a) An oxide of germanium, tin and lead;
 - (b) Cyanogen (C_2N_2);
 - (c) An oxide or imide of carbon of formula CE or C_3E_2 where $E = O$ and NR , R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
 - (d) A sulfur, selenium, or tellurium containing chalcogenide of carbon, silicon, germanium, tin and lead;
 - (e) A chalcogenide of carbon, silicon, germanium, tin and lead containing more than one chalcogen;
 - (f) A chalcogenide imide of carbon, silicon, germanium, tin and lead having the formula $C(E)(X)$ where $E = O, S, Se, Te, \text{ or } NR$; $X = NR'$

where R and/or R' is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;

5

(g) A chalcogenyl halide or imidohalide of carbon, silicon, germanium, tin and lead of the formula $C(E)X_2$ where $E = O, S, Se, Te, \text{ and } NR$; R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms; and X is a halogen;

10

(h) An elemental form of phosphorus, arsenic, antimony and bismuth;

(i) An oxide of nitrogen, phosphorus, arsenic, antimony and bismuth;

15

(j) A nitrogen oxoacid or salt containing the anion thereof;

(k) A halide of the formula E_nX_m , where E is nitrogen, phosphorus, arsenic, antimony or bismuth and X is a halogen or pseudohalogen, $n = 1 \text{ to } 10$, and $m = 1 \text{ to } 20$;

(l) A chalcogenide or imide of nitrogen, phosphorus, arsenic, antimony and bismuth of the general formula E_nY_m , where $E = N, P, As, Sb, \text{ and } Bi$; $Y = S, Se, Te \text{ and } NR$; $n = 1 \text{ to } 10$; $m = 1 \text{ to } 40$; and R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;

20

25

(m) A chalcogenyl or imido compound of nitrogen, phosphorus, arsenic, antimony and bismuth having the formula $E_nY_mX_q$, where $E = N, P, As, Sb \text{ and } Bi$; $Y = O, S, Se, Te \text{ and } NR$; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group

30

- containing up to 50 non-hydrogen atoms, an alkoxy group
 containing up to 50 non-hydrogen atoms, an amino group containing
 up to 50 non-hydrogen atoms, a thiolato group containing up to 50
 non-hydrogen atoms, or a boryl group containing up to 50 non-
 hydrogen atoms; $n = 1$ to 20; $m = 1$ to 40; $q = 1$ to 40; and R is
 hydrogen, a halogen, an alkyl group containing up to 50 non-
 hydrogen atoms, an aryl group containing up to 50 non-hydrogen
 atoms, a silyl group containing up to 50 non-hydrogen atoms, an
 alkoxy group containing up to 50 non-hydrogen atoms, an amino
 group containing up to 50 non-hydrogen atoms, a thiolato group
 containing up to 50 non-hydrogen atoms, or a boryl group
 containing up to 50 non-hydrogen atoms;
- (n) An interpnictogen;
- (o) A phosphazene of the general formula $(NPR_2)_x$ wherein R =
 halogen, or alkyl or aryl group containing up to 50 non-hydrogen
 atoms, and x is at least 2;
- (p) A compound of the general formula $A(E)X_3$ where A = P, As, Sb,
 and Bi; E = NR or CR_2 , R is hydrogen, a halogen, an alkyl group
 containing up to 50 non-hydrogen atoms, an aryl group containing
 up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-
 hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen
 atoms, an amino group containing up to 50 non-hydrogen atoms, a
 thiolato group containing up to 50 non-hydrogen atoms, or a boryl
 group containing up to 50 non-hydrogen atoms; and X is hydrogen,
 a halogen, an alkyl group containing up to 50 non-hydrogen atoms,
 an aryl group containing up to 50 non-hydrogen atoms, a silyl group
 containing up to 50 non-hydrogen atoms, an alkoxy group
 containing up to 50 non-hydrogen atoms, an amino group containing
 up to 50 non-hydrogen atoms, a thiolato group containing up to 50

- non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 5 (q) A pnictogen hydride;
- (r) An elemental form of oxygen, sulfur, selenium, and tellurium;
- (s) An interchalcogen;
- (t) A compound containing one or more chalcogens and one or more halogens of formula E_nX_m where $E = O, S, Se, \text{ and } Te$; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms, $n = 1$ to 10, $m = 1$ to 20;
- 10 15 (u) A compound of general formula EOX_2 where $E = O, S, Se, \text{ and } Te$; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 20 (v) A compound of general formula EOX_4 where $E = S, Se, \text{ and } Te$; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 25 30

- 5 (w) A compound of general formula EO_2X_2 where E = S, Se, and Te; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 10 (x) A Sulfur-Nitrogen compound;
- 15 (y) A compound of the formula $S(NR)_nX_m$ where $n = 1$ to 3 ; $m = 0$ to 6 ; X is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms; and R is hydrogen, a halogen, an alkyl group containing up to 50 non-hydrogen atoms, an aryl group containing up to 50 non-hydrogen atoms, a silyl group containing up to 50 non-hydrogen atoms, an alkoxy group containing up to 50 non-hydrogen atoms, an amino group containing up to 50 non-hydrogen atoms, a thiolato group containing up to 50 non-hydrogen atoms, or a boryl group containing up to 50 non-hydrogen atoms;
- 20
- 25 (z) A sulfur oxoacid, peroxyacid, and salts containing the anions thereof;
- (aa) A selenium oxoacid, peroxyacid, and salts containing the anions thereof;
- 30 (bb) A tellurium oxoacid, peroxyacid, and salts containing the anions thereof;

- (cc) A chalcogen hydride;
- (dd) An elemental form of fluorine, chlorine, bromine, iodine, and
astatine;
- 5 (ee) An interhalogen, salts containing their cations, and salts containing
the anions thereof;
- (ff) A salt containing polyhalide cations and/or anions;
- (gg) A homoleptic or heteroleptic halogen oxide, salts containing the
cations thereof, and salts containing the anion thereof;
- (hh) An oxoacid and salts containing the anions thereof;
- 10 (ii) A hydrogen halide;
- (jj) NH_4F , SF_4 , SbF_3 , AgF_2 , KHF_2 , ZnF_2 , AsF_3 , and salts containing the
 HF_2^- anion;
- (kk) A hydrohalic acid;
- (ll) A He, Ne, Ar, Kr, Xe, and Rn oxide, salts containing the cations
thereof, and salts containing the anions thereof;
- 15 (mm) A He, Ne, Ar, Kr, Xe, and Rn halide, salts containing the cations
thereof, and salts containing the anions thereof;
- (nn) A He, Ne, Ar, Kr, Xe, and Rn chalcogenyl halide, salts containing
the cations thereof, and salts containing the anions thereof;
- 20 (oo) A product obtained by reacting a material selected from the group
consisting of water, alcohol, hydrogen sulfide and a thiol with any of
the above compounds and salts thereof containing the corresponding
anion;
- (pp) An organic peroxide;
- 25 (qq) Water; and
- (rr) Mixtures thereof,

wherein the compound is present in an amount sufficient that the molecular
weight distribution of the resulting polymeric product is narrower than would
be obtained in the absence of the compound.

20. The process according to Claim 19 wherein the at least one transition metal is selected from Groups 4, 5, 6, 7, 8, 9 and 10 of the Periodic Table of the Elements, as defined herein.
21. The process according to Claim 19 wherein the metal of the at least one
5 organometallic compound is selected from Groups 1, 2, 11, 12, 13 and 14 of the Periodic Table of the Elements, as defined herein.
22. The process according to Claim 21 wherein the at least one organometallic compound is selected from the group consisting of trialkylaluminums, dialkylaluminum halides and alkylaluminum sesquihalides.
- 10 23. The process according to Claim 19 wherein the compound is a nitrogen oxide selected from the group consisting of nitrogen monoxide, nitrogen dioxide, dinitrogen monoxide, dinitrogen trioxide, dinitrogen tetroxide and dinitrogen pentoxide.
24. The process according to Claim 23 wherein the nitrogen oxide is dinitrogen
15 monoxide.
25. The process according to Claim 19 wherein the compound is selected from the group consisting of CO, C₃O₂, COS, SO₂, and SO₃.
26. The process according to Claim 19 wherein the compound is selected from dioxygen and ozone.
- 20 27. The process according to Claim 19 further comprising the presence of at least one electron donor.
28. The process according to Claim 27 wherein at least one of the electron donors is tetrahydrofuran.
29. The process according to Claim 19 further comprising the presence of at least
25 one halogenated hydrocarbon.
30. The process according to Claim 29 wherein at least one of the halogenated hydrocarbons is chloroform.
31. The process according to Claim 20 further comprising the presence of at least one electron donor and at least one halogenated hydrocarbon.

32. The process according to Claim 31 wherein the organometallic co-catalyst compound is trimethylaluminum, the electron donor is tetrahydrofuran, the halogenated hydrocarbon is chloroform and the compound is dinitrogen monoxide.
- 5 33. The process according to Claim 32 wherein the metal of the transition metal compound is titanium.
34. The process according to Claim 19 wherein the compound is present in the polymerization medium in an amount ranging from about 1 ppm to about 10,000 ppm by molar ratio in the fluid phase(s) of the polymerization medium.
- 10 35. The process according to Claim 19 wherein the polymerization conditions are gas phase.
36. The process according to Claim 35 wherein the compound is present in the gas phase polymerization medium in an amount ranging from about 1 ppm by volume to about 10,000 ppm by volume.
- 15 37. The process according to Claim 1 wherein the polymerization conditions are solution phase.
38. The process according to Claim 1 wherein the polymerization conditions are slurry phase.
39. The process according to Claim 1 wherein at least one olefin is ethylene.
- 20 40. A copolymer of ethylene and 1-hexene, wherein ethylene comprises at least about 50% by weight of the copolymer, characterized by having a DSC melt transition temperature of about 116 °C to about 123 °C, a density of from about 0.880 g/cc to about 0.930 g/cc, a n-hexane extractable of from 0 to about 6 weight percent, and a melt flow ratio of from about 26 to about 34.
- 25 41. The copolymer according to Claim 40 wherein the DSC melt transition temperature is from about 119 °C to about 121 °C, the density is from about 0.905 g/cc to about 0.920 g/cc, the n-hexane extractable is from 0 to about 3 weight percent, and the melt flow ratio is from about 26 to about 32.

42. A copolymer of ethylene and an olefin having 3-16 carbon atoms wherein ethylene comprises at least 99% by weight of the copolymer, having a melt flow ratio of from about 22 to about 26.
43. A copolymer of ethylene and at least one or more olefin(s) having 5 to 16
5 carbon atoms, wherein ethylene comprises at least about 50% by weight of the copolymer, characterized by having a DSC melt transition temperature of about 116 °C to about 123 °C, a density of from about 0.880 g/cc to about 0.930 g/cc, a n-hexane extractable of from 0 to about 6 weight percent, and a melt flow ratio of from about 26 to about 34.
- 10 44. A film fabricated from the copolymer according to claim 40.
45. A film fabricated from the copolymer according to claim 43.
46. An article fabricated from the copolymer according to claim 40.
47. An article fabricated from the copolymer according to claim 43.