



(22) Date de dépôt/Filing Date: 2015/07/13

(41) Mise à la disp. pub./Open to Public Insp.: 2016/02/13

(45) Date de délivrance/Issue Date: 2018/01/02

(30) Priorité/Priority: 2014/08/13 (US14/458,961)

(51) Cl.Int./Int.Cl. *G01N 3/02* (2006.01),
B32B 38/10 (2006.01), *B32B 5/12* (2006.01),
G01N 3/62 (2006.01)


(72) Inventeurs/Inventors:
ESPOSITO, JACK J., US;
DUSTIN, JOSHUA S., US

(73) Propriétaire/Owner:
THE BOEING COMPANY, US

(74) Agent: SMART & BIGGAR

(54) Titre : SPECIMEN DE TEST COMPOSITE

(54) Title: COMPOSITE TEST SPECIMEN



(57) Abrégé/Abstract:

A particular composite test specimen includes a first tab, a second tab, and a gage section between the first tab and the second tab. The first tab, the second tab, and the gage section are machined from a composite test blank. The composite test blank includes a plurality of plies arranged with first ply layers having fibers oriented in a first direction and second ply layers having fibers oriented in a second direction, where the first direction is different than the second direction.

ABSTRACT OF THE DISCLOSURE

A particular composite test specimen includes a first tab, a second tab, and a gage section between the first tab and the second tab. The first tab, the second tab, and the gage section are machined from a composite test blank. The composite test
5 blank includes a plurality of plies arranged with first ply layers having fibers oriented in a first direction and second ply layers having fibers oriented in a second direction, where the first direction is different than the second direction.

COMPOSITE TEST SPECIMEN

FIELD OF THE DISCLOSURE

5 **[0001]** The present disclosure is generally related to composite test specimens.

BACKGROUND

10 **[0002]** To reliably predict a failure response of composite materials, ply level progressive failure analysis using material properties of the composite material may be used. Material properties of composite materials may be determined using standardized methodologies. For example, the ASTM D695-10 standard describes a methodology for testing the compressive property of rigid plastics. However, ply level progressive failure analysis tends to be sensitive to fiber direction material properties, and current standardized methodologies are not able to provide

15 sufficiently reliable fiber direction material property information. For example, current test methodologies for measurement of fiber direction strength and strain tend to produce spurious failure modes leading to underestimation of critical compressive material properties.

20 **[0003]** Some causes of the spurious failure modes may be related to the manner in which composite test specimens are prepared. Composite test specimens used for compressive testing are typically prepared by bonding end tabs onto a sample of a material to be tested. The bonded end tabs can introduce problems, which may lead to premature failure of the composite test specimen. For example, the bonded ends tabs may lead to brooming of fibers. As a result, even with use of standard test

25 methods, actual compressive failure limits of fibers of a composite test specimen may be underestimated. Additionally, spacing constraints (e.g., an amount of distance between the end tabs), may prevent performing direct strain measurements on the composite test specimen during testing. Accordingly, valuable information that could be gained by direct strain measurement is not available.

30

SUMMARY

[0004] In a particular embodiment, a composite test specimen includes a first tab, a second tab, and a gage section between the first tab and the second tab. The first tab, the second tab, and the gage section are machined from a composite test blank.

5 The composite test blank includes a plurality of plies arranged with first ply layers having fibers oriented in a first direction and second ply layers having fibers oriented in a second direction, where the first direction is different than the second direction.

[0005] In another particular embodiment, a method includes using a plurality of plies to form a composite assembly by arranging first ply layers to have fibers oriented in
10 a first direction and arranging second ply layers to have fibers oriented in a second direction, where the first direction is different than the second direction. The composite assembly has a first face and a second face opposite the first face. The method includes cutting the composite assembly to form a first section and a second section. The first section has a third face corresponding to the first face of the
15 composite assembly and a fourth face corresponding to the second face of the composite assembly, and the second section has a fifth face corresponding to the first face of the composite assembly and a sixth face corresponding to the second face of the composite assembly. The method also includes coupling the third face of the first section to the fifth face of the second section to form a composite panel and
20 forming one or more composite test blanks from the composite panel.

[0006] In another particular embodiment, a composite test blank includes a first stack of plies and a second stack of plies. The first stack of plies and the second stack of plies are sections of a single composite assembly. The single composite assembly includes first ply layers having fibers oriented in a first direction and second ply
25 layers having fibers oriented in a second direction. The single composite assembly has a first face and a second face opposite the first face. The first stack of plies has a third face corresponding to the first face of the single composite assembly and a fourth face corresponding to the second face of the single composite assembly. The second stack of plies has a fifth face corresponding to the first face of the single
30 composite assembly and a sixth face corresponding to the second face of the single

composite assembly. The third face of the first stack of plies is coupled to the fifth face of the second stack of plies.

[0006a]In another embodiment, there is provided a composite test specimen comprising: a first tab including a plurality of plies arranged with first ply layers
 5 having first fibers oriented in a first direction and second ply layers having second fibers oriented in a second direction, the first direction different from the second direction; a second tab including the first ply layers and the second ply layers; and a gage section positioned between the first tab and the second tab, the gage section including the first ply layers and the second ply layers, wherein a number of plies in
 10 the gage section is less than a number of plies of the first tab and a number of plies of the second tab.

[0006b]In another embodiment, there is provided a method comprising: forming a composite layup by arranging first ply layers to have first fibers oriented in a first direction and arranging second ply layers to have second fibers oriented in a second
 15 direction, the first direction different from the second direction, wherein the composite layup has a first face and a second face opposite the first face; cutting the composite layup to form a first section and a second section, the first section having a third face corresponding to the first face of the composite layup and a fourth face corresponding to the second face of the composite layup, and the second section
 20 having a fifth face corresponding to the first face of the composite layup and a sixth face corresponding to the second face of the composite layup; coupling the third face of the first section to the fifth face of the second section to form a composite panel; and forming one or more composite test blanks from the composite panel.

[0006c]In another embodiment, there is provided a composite test blank comprising:
 25 a first stack of plies; and a second stack of plies, wherein the first stack of plies and the second stack of plies are sections of a single composite layup. The single composite layup includes: first ply layers having first fibers oriented in a first direction; and second ply layers having second fibers oriented in a second direction, the first direction different than the second direction. The single composite layup has
 30 a first face and a second face opposite the first face. The first stack of plies has a

third face corresponding to the first face of the single composite layup and a fourth face corresponding to the second face of the single composite layup. The second stack of plies has a fifth face corresponding to the first face of the single composite layup and a sixth face corresponding to the second face of the single composite layup. The third face of the first stack of plies is coupled to the fifth face of the second stack of plies.

[0007] The features, functions, and advantages described can be achieved independently in various embodiments or may be combined in other embodiments, further details of which are disclosed with reference to the following description and drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0008] FIGs. 1A, 1B, 1C and 1D are diagrams illustrating a particular embodiment of a method of forming a composite assembly;

[0009] FIG. 2 is a diagram of a top view of a particular embodiment of the composite panel formed from the composite assembly of FIG. 1;

[0010] FIG. 3 is a diagram of multiple views of a particular embodiment of a composite test blank formed from the composite panel of FIG. 2;

[0011] FIG. 4 is a diagram of multiple views of a particular embodiment of a composite test specimen formed from the composite test blank of FIG. 3;

[0012] FIG. 5 is a diagram of detailed side view of a particular embodiment of the composite test specimen of FIG. 4; and

[0013] FIG. 6 is a flow chart illustrating a particular embodiment of a method of forming a composite test specimen.

DETAILED DESCRIPTION

[0014] By forming a test specimen from a composite material (e.g., a composite test specimen) using methods described herein, compressive properties of the composite material may be measured more accurately (e.g., by avoiding early failure of the test specimen). In a particular embodiment, a test specimen is prepared from (e.g., milled from) a single composite blank rather than by bonding end tabs to a sample of a material to be tested. To illustrate, a composite panel (formed using methods described herein) is cut or otherwise machined to provide one or more composite test blanks. A composite test blank may be machined (e.g., milled, ground, cut, etc.) to remove material (e.g., portions of ply layers) to form a gage

section between tabs. Thus, the gage section and tabs are each integral to and formed from a single composite assembly. The composite test specimen may include additional features that reduce premature failure mechanisms, such as premature buckling between the gage section and the tabs and brooming of ends of the tabs. Further, a cross-ply layup may be used to form the composite assembly to reduce or restrict premature transverse tension failures of **0-degree** plies.

[0015] FIGs. **1A-1D** are diagrams illustrating a particular embodiment of a method of forming a composite assembly **140**. The composite assembly **140** may be cured to form a composite panel (such as the composite panel **200** of FIG. **2**), which may be used to form one or more composite test blanks. The composite assembly **140** may be formed by arranging a plurality of plies (e.g., plies **121-128**) to form a composite layup **102**. The plies **121-128** may be arranged in a cross-ply layup. In the cross-ply layup, first ply layers (e.g., plies **121**, **122**, **124**, **125**, **126**, and **127**) have fibers arranged in a first direction, and second ply layers (e.g., plies **123** and **128**) have fibers oriented in a second direction, where the second direction is different than the first direction. For example, an angle between the second direction and the first direction may be approximately **90-degrees**. In the example provided in FIGs. **1A-1D**, the first ply layers (e.g., plies **121**, **122**, **124**, **125**, **126**, and **127**) have fibers oriented in a **0-degree** direction, and the second ply layers (e.g., plies **123** and **128**) have fibers oriented in a **90-degree** direction (as indicated by a fiber orientation key in FIG. **1D**).

[0016] The cross-ply arrangement of the composite layup **102** enables placement of **0-degree** plies (plies with fibers oriented in the **0-degree** direction) away from areas of high stress concentration (such as at reentrant corners, as described with reference to FIGs. **4** and **5**) by surrounding the **0-degree** plies with **90 degree** plies (plies with fibers oriented in the **90-degree** direction). The cross-ply arrangement of the composite layup **102** also results in use of a relatively small number (e.g., **2** to **3**) of **0-degree** plies in a gage section of a composite test specimen (as illustrated in FIG. **5**) to reduce a load required to cause compressive failure. This reduction in load reduces the risk of inducing a premature end failure during compressive testing.

The specific arrangement of plies be changed somewhat from one composite layup **102** to another arrangement of plies (not shown) based on the cured ply thickness of the material used. For example, more ply layers or fewer ply layers may be used. As another example, a different proportion or arrangement of **0**-degree plies to **90**-
 5 degree plies may be used.

[0017] The composite layup **102** may be formed using a plurality of pre-impregnated (“pre-preg”) plies that are stacked or otherwise arranged as illustrated in FIG. **1A**. After debulking and possibly performing some machining steps (such as cutting down, squaring or otherwise treating edges, corners or faces of the composite layup
 10 **102**), and before curing, the composite layup **102** may be divided into sections, e.g., along section line **106**.

[0018] Referring to FIG. **1B**, a first section **131** and a second section **130** of the composite layup **102**, divided along the section line **106**, are shown. The first section **131** has a third face **133** corresponding to a first face **110** of the composite
 15 layup **102**. Additionally, the first section **131** has a fourth face **135** corresponding to a second face **112** of the composite layup **102**. Likewise, the second section **130** has a fifth face **132** corresponding to the first face **110** of the composite layup **102** and has a sixth face **134** corresponding to the second face **112** of the composite layup **102**. It is noted that the figures are not to scale. Accordingly, although the
 20 sections **130** and **131** are illustrated in FIG. **1B** as having approximately the same size and shape, the sections **130** and **131** may have the same size and shape or different sizes and/or shapes, depending on particular design constraints or preferences.

[0019] Referring to FIG. **1C**, the first section **131** may be flipped over and coupled to the second section **130**. For example, the third face **133** of the first section **131** may
 25 be coupled to the fifth face **132** of the second section **130** to form a composite assembly **140** (shown in FIG. **1D**). Thus, the composite assembly **140** includes multiple stacks of plies including a first stack of plies corresponding to the first section **131** and a second stack of plies corresponding to the second section **130**,
 30 where both the first stack of plies and the second stack of plies are formed from a

single composite layup (e.g., the composite layup **102** of FIG. 1A). Although the first stack of plies corresponding to the first section **131** and the second stack of plies corresponding to the second section **130** are illustrated, in other embodiments more than two stacks of plies may be formed from a single composite layup.

5 **[0020]** Referring to FIG. 1D, after the composite assembly **140** is formed, the composite assembly **140** may be cured to form a composite panel (such as the composite panel **200** of FIG. 2). Curing may be performed with the composite assembly **140** placed on a relatively flat surface **154**. Additionally, a caul plate **150** may be applied to the composite assembly **140** during curing. The caul plate **150**
 10 and the flat surface **154** enable the composite layup **102** to cure with a relatively smooth first face **152** and a relatively smooth second face **156**.

[0021] FIG. 2 is a diagram of a top view of a particular embodiment of a composite panel **200** formed by curing the composite assembly **140** of FIG. 1D. The composite panel **200** may be divided (e.g., cut or milled) into a plurality of composite test
 15 blanks, such as composite test blanks **210-221**. For example, edges **230** and **232** of the composite panel **200** may be cut away (or otherwise removed), and a central portion of the composite panels **200** may be used to form the composite test blanks **210-221**. Each composite test blank **210-221** may have a length oriented along the
 0-degree direction described with reference to FIG. 1A-1D and a width oriented
 20 along the 90-degree direction. Although the composite panel **200** is divided into twelve composite test blanks in FIG. 2, in other embodiments the composite panel **200** may be divided into more than twelve composite test blanks or fewer than twelve composite test blanks.

[0022] FIG. 3 is a diagram of multiple views of a particular embodiment of a
 25 composite test blank formed from the composite panel **200** of FIG. 2. FIG. 3 shows a particular composite test blank **210** in more detail via a top-view, a front-view, a side-view, and a perspective-view. The composite test blank **210** has a first end **304** and a second end **306**. Between the first end **304** and the second end **306**, the composite test blank **210** has a length L_b . The composite test blank **210** also has a
 30 first side **308** and a second side **310**. Between the first side **308** and second side

310, the composite test blank **210** has a width W_b . The composite test blank **210** also has a first face **312** and a second face **314**. Between the first face **312** and second face **314**, the composite test blank **210** has a thickness T_b .

[0023] The composite test blank **210** may be formed of a plurality of ply layers as described with reference to FIGs. **1A-1D**. The plurality of ply layers may include two or more stacks of plies, such as a first stack of plies **320** and a second stack of plies **322**. The first stack of plies **320** and the second stack of plies **322** may be formed during a single composite layup. For example, as described with reference to FIG. **1A-1D**, the single composite layup (e.g., the composite layup **102**) may be formed to have a first face (e.g., the first face **110** of FIG. **1A**) and a second face (e.g., the second face **112** of FIG. **1A**) opposite the first face. Before curing, the single composite layup may be divided into sections such that a first section (e.g., the first section **131** of FIG. **1B**) has a third face (e.g., the third face **133** of FIG. **1B**) and a fourth face (e.g., the fourth face **135** of FIG. **1B**), and a second section (e.g., the second section **130** of FIG. **1B**) has a fifth face (e.g., the fifth face **132** of FIG. **1B**) and a sixth face (e.g., the sixth face **134** of FIG. **1B**). The first section may correspond to the first stack of plies **320** and the second section may correspond to the second stack of plies **322**. For example, the third face of the first section may be coupled to the fifth face of the second section to form a composite assembly (such as the composite assembly **140** of FIG. **1D**). The composite assembly may be cured to form a composite panel, which may be cut into composite test blanks (as described with reference to FIG. **2**).

[0024] The composite test blank **210** may be used to form a composite test specimen. For example, the composite test blank **210** may be machined (e.g., cut, milled, ground, or otherwise acted upon using a subtractive manufacturing process) to form the composite test blank.

[0025] FIGs. **4** and **5** are diagrams of various views of a particular embodiment of a composite test specimen **402** formed from the composite test blank **210** of FIG. **3**. In FIG. **4**, the composite test specimen **402** has a first end **404** and a second end **406**. Between the first end **404** and second end **406**, the composite test specimen has a

length L_s . Additionally, the composite test specimen **402** has a first side **408** and a second side **410**. Between the first side **408** and second side **410**, the composite test specimen **402** has a width W_s . Further, the composite test specimen **402** has a first face **412** and a second face **414**. Between the first face **412** and second face **414**, the composite test specimen **402** has a thickness of T_s . In a particular embodiment, the length L_s , the width W_s , and the thickness T_s may be selected to enable use of the composite test specimen **402** with a testing apparatus (e.g., a testing apparatus as described in the ASTM D695-10 standard). For example, the length L_s may be about **3.10** inches (within a tolerance of ± 0.03 inches), the width W_s may be about **0.500** inches (within a tolerance of ± 0.005 inches), and the thickness T_s may be about **0.135** inches. The thickness T_s may vary from one composite test specimen to another as a result of how the composite assembly cures in various areas, as well as for other reasons (such as differences in materials being tested).

[0026] To form the composite test specimen **402** from the composite test blank **210** the length, the width, the thickness, or a combination thereof, of the composite test blank **210** may be reduced. For example, the width W_s of the composite test specimen **402** may be less than the width W_b of the composite test blank **210**. To illustrate, the composite test blank **210** may be machined (e.g., milled, cut, ground or otherwise acted upon using a subtractive manufacturing process) to reduce the width W_b to the width W_s . The machining may also shape other dimensions of the composite test specimen **402**, such as squaring the sides **408**, **410** relative to the ends **404**, **406** and/or relative to the faces **412**, **414**. Further, the machining may shape the composite test specimen **402** such that the sides **408**, **410** are each substantially parallel to fibers oriented in the 0-degree direction.

[0027] The composite test blank **210** may also, or in the alternative, be machined (e.g., milled, cut, ground or otherwise acted upon using a subtractive manufacturing process) to reduce the length L_b to the length L_s . The machining may also shape other dimensions of the composite test specimen **402**, such as squaring the ends **404**, **406** relative to the sides **408**, **410** and/or relative to the faces **412**, **414**.

[0028] The composite test specimen **402** may include a first tab **422** and a second tab **424**. Between the first tab **422** and the second tab **424**, the composite test specimen **402** may include a gage section **420**. The first tab **422** and second tab **424** may be integral with (as opposed to adhered to) the gage section **420**. The gage section **420** has a thickness T_g corresponding to a first number of ply layers, the first tab **422** includes a second number of ply layers, and the second tab **424** includes a third number of ply layers. The first number of ply layers (corresponding to the gage section **420**) is less than the second number of ply layers and is less than the third number of ply layers. The gage section **420** may be formed by reducing a thickness of the composite test blank **210** from both faces **412** and **414** of the composite test blank **210** (e.g., by reducing a number of plies of the gage section **420** relative to a number of plies of the composite test blank **210**). To illustrate, as shown in the side-view and perspective-view of FIG. 4, the gage section **420** may correspond to a portion of the composite test specimen **402** where the thickness T_s is reduced to the thickness T_g , which is less than the thickness T_s . In a particular embodiment, the thickness T_g is about **0.075** inches. Approximately half of the material that is removed to reduce the thickness of the gage section **420** from the thickness T_s to the thickness T_g is removed from each face. To illustrate, if the thickness T_s is about **0.135** inches and the thickness T_g is about **0.075** inches, about **0.060** inches of material needs to be removed to go from T_s to T_g . Approximately half of the **0.060** inches of material (i.e., about **0.030** inches of material) is removed from the first face **412**, and approximately half of the **0.060** inches of material (i.e., about **0.030** inches of material) is removed from the second face **414**. Thus, the gage section **420** may be formed by machining (e.g., cutting, milling, grinding, etc.) the composite test blank **210** in a direction that is perpendicular to the stacks of plies (e.g., a direction normal to the first face **312**, the second face **314**, or both) to reduce the number of plies in the stack in the gage section **420** and to reduce the thickness of the gage section to a predetermined amount.

[0029] As illustrated in FIG. 4, the tabs **422**, **424** and the gage section **420** are formed as integral portions of the original composite panel. Accordingly, the tabs

422, **424** and the gage section **420** are similarly affected by environmental condition (e.g., temperature, humidity, etc.). Thus, the composite test specimen **402** may be less prone to disbond during extreme environment testing than traditional test coupons (e.g., test coupons that use bonded end-tabs on a sample of test material).

5 Additionally while bonding tabs to a test material to form a traditional test coupon uses a special bonding fixture, no such fixture is used to form tabs **422** and **424**, which reduces time and resources that would be used to manufacture the traditional test coupons. The tabs **422**, **424** also help to maintain very high tolerances in the coupon geometry because they can be precisely machined while forming the

10 composite test specimen (e.g., without worrying about debonding a bonded end tab from a sample of test material).

[0030] In a particular embodiment, the gage section **420** is formed by machining (e.g., milling, cutting, grinding or otherwise acting upon using a subtractive manufacturing process) the faces **412** and **414** of the composite test blank **210**. The

15 machining process may also form a curved reentrant corner between the gage section **420** and each of the tabs **422** and **424**. For example, each reentrant corner of the gage section **420** may have a radius of curvature R as illustrated in FIG. 4. In a particular embodiment, the radius of curvature R of each reentrant corner is about **0.020** inches (within a tolerance of ± 0.005 inches). The curvature of the reentrant

20 corners may reduce stress concentration at the corners, thereby reducing risk of early failures at the interface between the gage section **420** and each tab **422**, **424** during testing.

[0031] A length L_g of the gage section **420** may be sized such that a strain gage can be directly adhered to the gage section **420**. For example, the length L_g may be

25 about **0.30** inches in order to accommodate a **0.25** inch strain gage. In FIG. 4, a first strain gage **430** is coupled to (e.g., adhered to) the gage section **420** at a first face of the gage section **420**, and a second strain gage **432** is coupled to the gage section **420** at a second face of the gage section **420**. Thus, the strain gages **430**, **432** enable direct measurement of strain during compressive testing, providing more

30 detailed information than can be gathered using conventional test specimens.

[0032] The composite test specimen **402** may also include a first cap plate **440** coupled to the first end **404** of the first tab **422** and a second cap plate **442** coupled to the second end **406** of the second tab **424**. The first cap plate **440** may cover the first end **404** of the first tab **422** and may cover at least a portion of one or more sides **408, 410**, at least a portion of one or more faces **412, 414** of the first tab **422**, or a combination thereof. For example, the first cap plate **440** may include a metal piece that is formed or machined with a groove, slot or opening to fit over the first end **404** of the first tab **422**. Likewise, the second cap plate **442** may cover the second end **406** of the second tab **424** and may cover at least a portion of one or more sides **408, 410**, at least a portion of one or more faces **412, 414** of the second tab **424**, or a combination thereof. For example, the second cap plate **442** may include a metal piece that is formed or machined with a groove, slot or opening to fit over the second end **406** of the second tab **424**. The cap plates **440, 442** may inhibit brooming of ends of respective tabs **422, 424** when the ends are subject to end-loaded compression testing.

[0033] FIG. **5** is a diagram of a detailed side view of a particular embodiment of the composite test specimen **402** of FIG. **4**. In particular, FIG. **5** illustrates a more detailed view of the gage section **420** and an area connecting the gage section **420** to the first tab **422** and to the second tab **424**. FIG. **5** also illustrates orientations of fibers of the ply layers and provides further illustration of the radius of curvature **R** of the reentrant corners and attachment of the strain gages **430, 432** to the composite test specimen **402**.

[0034] In FIG. **5**, the strain gages **430, 432** are directly adhered to the gage section **420**. Leads **434, 436** of the strain gages **430, 432** may protrude from the gage section **420** to enable measurement of strain during testing. Each reentrant corner may have the radius of curvature **R** to reduce strain at the reentrant corner during testing. As illustrate in FIG. **5**, a majority of plies of the composite test specimen have a **90-degree** fiber orientation with remaining plies having a **0-degree** fiber orientation. The **0-degree** fiber orientation plies reduce the risk of premature transverse tension failures.

[0035] FIG. 6 is a flow chart illustrating a particular embodiment of a method **600** of forming a composite test specimen. The method **600** may be used to form the composite test specimen **402** of FIGs. 4 and 5. Further, portions of the method **600** may be used to form the composite test blank **210** of FIG. 3.

5 **[0036]** The method **600** includes, at **602**, using a plurality of plies to form a composite layup by arranging first ply layers to have fibers oriented in a first direction and arranging second ply layers to have fibers oriented in a second direction, where the first direction is different than the second direction. The composite layup has a first face and a second face opposite the first face. For example, the plurality of
10 plies **121-128** of FIG. 1 may be arranged to form the composite layup **102** of FIG. 1A.

[0037] The method **600** may also include, at **604**, cutting the composite assembly to form a first section and a second section. For example, the composite layup **102** of FIG. 1A may be divided into the first section **131** and the second section **130** of FIG.
15 **1B**.

[0038] As described with reference to FIG. 1B, the first section **131** has the third face **133**, which corresponds to the first face **110** of the composite layup **102**, and the first section **131** has the fourth face **135**, which corresponds to the second face **112** of the composite layup **102**. Additionally, the second section **130** has the fifth face **132**,
20 which corresponds to the first face **110** of the composite layup **102**, and has the sixth face **134**, which corresponds to the second face **112** of the composite layup **102**. The method **600** also includes, at **606**, coupling the third face of the first section to the fifth face of the second section and to form a composite assembly. The composite assembly may be cured to form a composite panel, such as the
25 composite panel **200** of FIG. 2.

[0039] The method **600** may also include, at **608**, forming one or more composite test blanks from the composite panel. For example, the composite panel **200** of FIG. 2 may be machined (e.g., cut, milled, ground, etc.) to form the composite test blanks **210-221**.

[0040] The method **600** may also include, at **610**, machining a particular composite test blank of the one or more composite test blanks to form a composite test specimen. For example, the composite test blank **210** of FIGs **2** and **3** may be machined (e.g., milled, cut, ground, etc.) to form the composite test specimen **402** of FIGs. **4** and **5**. To illustrate, machining the particular composite test blank to form the composite test specimen may include machining the gage section perpendicular to the first direction and perpendicular to the second direction to reduce a number of plies in the gage section relative to a number of plies of the particular composite test blank. As described with reference to FIG. **4**, the composite test specimen may have a first tab, a second tab, and a gage section between the first tab and the second tab. Thus, the composite test specimen is formed from a single composite layup (e.g., corresponding to the composite layup **102** of FIG. **1A**) rather than including multiple parts (e.g., a sample of a material to be tested with bonded end tabs).

[0041] The method **600** may also include, at **612**, coupling a first cap plate to an end of the first tab and, at **614**, coupling a second cap plate to an end of the second tab. Each cap plate may cover an end of the respective tab and cover at least a portion of one or more sides, at least a portion of one or more faces of the respective tab, or a combination thereof. For example, the first cap plate **440** of FIG. **4** covers the first end **404** of the first tab **422** and extends to cover at least a portion of a side and/or a portion of a face of the first tab **422**. Likewise, the second cap plate **442** covers the second end **406** of the second tab **424** and extends to cover at least a portion of a side and/or and a portion of a face of the second tab **424**.

[0042] The method **600** may also include, at **616**, adhering a strain gage to the gage section of the composite test specimen. For example, the strain gages **430** and **432** may be coupled to the gage section **420**, as in FIGs. **4** and **5**. Leads of the strain gages **430**, **432** may be routed to monitoring equipment to enable real-time monitoring of strain during compressive testing of the composite test specimen.

[0043] After the composite test specimen is formed, the composite test specimen may be used to perform testing to gather information regarding compressive

properties of materials used to form the composite test specimen. For example, the ASTM D695-10 standard methodology or a modified version thereof may be used to test the composite test specimen. In the modified version, a test fixture described in the ASTM D695-10 standard may be modified to accommodate the composite test specimen. For example, an additional lower load plate may be added to the test fixture to prevent premature end failure by eliminating the space between an out-of-plane buckling guide of the test fixture and a bottom load plate of the test fixture. Addition of the lower load plate may result in the composite test specimen being supported to the end of the buckling guide. As another example, out-of-plane buckling guides of the test fixture may be flipped such that smooth surfaces of the out-of-plane buckling guides contact the composite test specimen (rather than allowing V-notched surfaces of the out-of-plane buckling guides to contact the composite test specimen as prescribed in the ASTM D695-10 standard). Flipping the out-of-plane buckling guides may reduce end buckling failure of the composite test specimen due to contact with the V-notched surfaces. As a further example, support bolts of the test fixture may be torqued to 1 in-lb, which may reduce friction between the test fixture and the composite test specimen.

[0044] Thus, after the composite test specimen is prepared (e.g., machined from a composite test blank and coupled to cap plates and strain gages), the composite test specimen may be secured in the modified test fixture and 1 in-lb of torque may be applied to the support bolts. The composite test specimen is secured to the modified test fixtures such that the composite test specimen is centered in the test fixture and such that ends of the composite test specimen squarely contact the test fixture. An end cap is placed on a top end of the composite test specimen and a load platen is moved so that it comes in contact with the end cap. The composite test specimen is loaded to failure while the load/strain response is monitored.

[0045] In a test using a composite test specimen formed of a particular composite material using the methods described herein, ultimate fiber compressive strain in excess of 21000 μ -strain at room temperature dry test conditions and 24000 μ -strain at cold temperature dry test conditions were measured. These results are in

contrast to results generated for the same particular composite material using a bonded end tab test specimen, which provided measured ultimate fiber compressive strains of **7000** μ -strain at room temperature dry test conditions and **8000** μ -strain at cold temperature dry test conditions.

5 **[0046]** Embodiments described above are illustrative and do not limit the disclosure. It is to be understood that numerous modifications and variations are possible in accordance with the principles of the present disclosure.

10 **[0047]** The illustrations of the embodiments described herein are intended to provide a general understanding of the structure of the various embodiments. The illustrations are not intended to serve as a complete description of all of the elements and features of apparatus and systems that utilize the structures or methods described herein. Many other embodiments may be apparent to those of skill in the art upon reviewing the disclosure. Other embodiments may be utilized and derived from the disclosure, such that structural and logical substitutions and changes may
15 be made without departing from the scope of the disclosure. For example, method steps may be performed in a different order than is shown in the figures or one or more method steps may be omitted. Accordingly, the disclosure and the figures are to be regarded as illustrative rather than restrictive.

20 **[0048]** Moreover, although specific embodiments have been illustrated and described herein, it is to be appreciated that any subsequent arrangement designed to achieve the same or similar results may be substituted for the specific embodiments shown. This disclosure is intended to cover any and all subsequent adaptations or variations of various embodiments. Combinations of the above embodiments, and other embodiments not specifically described herein, will be
25 apparent to those of skill in the art upon reviewing the description.

30 **[0049]** The Abstract of the Disclosure is submitted with the understanding that it will not be used to interpret or limit the scope or meaning of the claims. In addition, in the foregoing Detailed Description, various features may be grouped together or described in a single embodiment for the purpose of streamlining the disclosure. This disclosure is not to be interpreted as reflecting an intention that the claimed

embodiments require more features than are expressly recited in each claim. Rather, as the following claims reflect, the claimed subject matter may be directed to fewer than all of the features of any of the disclosed embodiments.

EMBODIMENTS IN WHICH AN EXCLUSIVE PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. A composite test specimen comprising:

5 a first tab including a plurality of plies arranged with first ply layers having first fibers oriented in a first direction and second ply layers having second fibers oriented in a second direction, the first direction different from the second direction;

10 a second tab including the first ply layers and the second ply layers; and

15 a gage section positioned between the first tab and the second tab, the gage section including the first ply layers and the second ply layers, wherein a number of plies in the gage section is less than a number of plies of the first tab and a number of plies of the second tab.

20 **2.** The composite test specimen of claim 1, wherein the first tab, the second tab, and the gage section are machined from a composite test blank, the composite test blank includes at least two stacks of plies formed from a single composite layup, the at least two stacks of plies including:

a first stack of plies from a first section of the single composite layup; and

25 a second stack of plies from a second section of the single composite layup.

3. The composite test specimen of claim 2, wherein the first stack of plies is coupled to the second stack of plies before the single composite layup was

cured, and wherein the second section is adjacent the first section in the single composite layup.

- 5 **4.** The composite test specimen of claim **2** or **3**, wherein the single composite layup has a first face and a second face opposite the first face, wherein the first stack of plies has a third face corresponding to the first face of the single composite layup and a fourth face corresponding to the second face of the single composite layup, wherein the second stack of plies has a fifth face corresponding to the first face of the single composite layup and a sixth face corresponding to the second face of the single composite layup, and wherein the third face of the first stack of plies is coupled to the fifth face of the second stack of plies to form the composite test blank.
- 15 **5.** The composite test specimen of any one of claims **2** to **4**, wherein the first direction is rotated approximately **90** degrees relative to the second direction, and wherein the first ply layers include a fewer number of layers than the second ply layers.
- 20 **6.** The composite test specimen of claim **5**, wherein the first direction is along a length of the composite test blank, the length corresponding to a direction from the first tab toward the second tab, and wherein the second direction is across a width of the composite test blank.
- 25 **7.** The composite test specimen of any one of claims **2** to **6**, wherein sides of the first tab and the second tab are substantially parallel to the first direction, and wherein the gage section is formed by removal of material from both faces of the composite test blank to reduce a thickness of the composite test blank, and wherein a portion of the gage section proximate a center of the thickness of the composite test blank is curved.

30

8. The composite test specimen of any one of claims 1 to 7, further comprising a strain gage coupled to the gage section.

9. The composite test specimen of any one of claims 1 to 8, further comprising:

5

a first cap plate coupled to an end of the first tab, the first cap plate covering the end of the first tab and covering at least a portion of one or more sides, at least a portion of one or more faces of the first tab, or a combination thereof; and

10

a second cap plate coupled to an end of the second tab, the second cap plate covering the end of the second tab and covering at least a portion of one or more sides, at least a portion of one or more faces of the second tab, or a combination thereof,

15

wherein the first cap plate and the second cap plate are configured to inhibit brooming of ends of respective tabs when the ends are subject to end-loaded compression testing.

20 10. A method comprising:

forming a composite layup by arranging first ply layers to have first fibers oriented in a first direction and arranging second ply layers to have second fibers oriented in a second direction, the first direction different from the second direction, wherein the composite layup has a first face and a second face opposite the first face;

25

cutting the composite layup to form a first section and a second section, the first section having a third face corresponding to the first face of the composite layup and a fourth face corresponding to the

30

second face of the composite layup, and the second section having a fifth face corresponding to the first face of the composite layup and a sixth face corresponding to the second face of the composite layup;

5 coupling the third face of the first section to the fifth face of the second section to form a composite panel; and

forming one or more composite test blanks from the composite panel.

10 **11.** The method of claim **10**, further comprising machining a particular composite test blank of the one or more composite test blanks to form a composite test specimen, the composite test specimen having a first tab, a second tab, and a gage section positioned between the first tab and the second tab, the gage section including the first ply layers and the second ply layers, wherein a
15 number of plies in the gage section is less than a number of plies of the first tab and a number of plies of the second tab.

12. The method of claim **11**, wherein machining the particular composite test blank to form the composite test specimen includes machining the gage
20 section perpendicular to the first direction and perpendicular to the second direction, and wherein the number of plies in the gage section is less than a number of plies of the particular composite test blank.

13. The method of claim **11** or **12**, further comprising:

25 coupling a first cap plate to an end of the first tab, the first cap plate covering the end of the first tab and covering at least a portion of one or more sides, at least a portion of one or more faces of the first tab, or a combination thereof; and

30

coupling a second cap plate to an end of the second tab, the second cap plate covering the end of the second tab and covering at least a portion of one or more sides, at least a portion of one or more faces of the second tab, or a combination thereof,

5

wherein the first cap plate and the second cap plate inhibit brooming of ends of respective tabs when the composite test specimen is subject to end-loaded during compression testing.

- 10 **14.** The method of any one of claims **11** to **13**, wherein machining the particular composite test blank to form the composite test specimen includes:

milling sides of the particular composite test blank to be substantially parallel to the first direction; and

15

forming the gage section by removing material from both faces of the particular composite test blank to reduce a thickness of the particular composite test blank, wherein a portion of the gage section proximate a center of the thickness of the particular composite test blank is curved.

20

- 15.** The method of any one of claims **10** to **14**, wherein the plurality of plies used to form the composite layup include pre-impregnated (pre-preg) plies, and further comprising curing the pre-preg plies while the first face of the composite layup contacts a substantially smooth surface and while the second face of the composite layup contacts a substantially smooth caul plate.

25

- 16.** The method of any one of claims **10** to **15**, wherein the first section and the second section are adjacent to one another in the composite layup.

30

17. The method of any one of claims **10** to **16**, wherein the first direction is rotated approximately **90** degrees relative to the second direction and wherein the first ply layers include fewer layers than the second ply layers.
- 5 18. The method of claim **17**, wherein the first direction is along a length of the one or more composite test blanks and wherein the second direction is across a width of the one or more composite test blanks.
- 10 19. A composite test blank comprising:
- a first stack of plies; and
- a second stack of plies, wherein the first stack of plies and the second stack of plies are sections of a single composite layup,
- 15 wherein the single composite layup includes:
- first ply layers having first fibers oriented in a first direction; and
- 20 second ply layers having second fibers oriented in a second direction, the first direction different than the second direction, and
- wherein the single composite layup has a first face and a second face opposite the first face,
- 25 wherein the first stack of plies has a third face corresponding to the first face of the single composite layup and a fourth face corresponding to the second face of the single composite layup,

30

wherein the second stack of plies has a fifth face corresponding to the first face of the single composite layup and a sixth face corresponding to the second face of the single composite layup, and

- 5 wherein the third face of the first stack of plies is coupled to the fifth face of the second stack of plies.

1/6




FIG. 1A




FIG. 1B




FIG. 1C





FIG. 1D



3/6




FIG. 3

4/6




FIG. 4

5/6




FIG. 5

6/6




FIG. 6

