

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
1 March 2007 (01.03.2007)

PCT

(10) International Publication Number
WO 2007/024564 A1

(51) International Patent Classification:
C08K 5/10 (2006.01) *C01B 33/44* (2006.01)

(21) International Application Number:
PCT/US2006/031839

(22) International Filing Date: 15 August 2006 (15.08.2006)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/710,015 19 August 2005 (19.08.2005) US

(71) Applicant (for all designated States except US): **CRYOVAC, INC.** [US/US]; Post Office Box 464, Duncan, SC 29334 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **GRAH, Michael, D.** [US/US]; 10 Lebar Court, Greenville, SC 29615 (US). **BE-CRAFT, Michael, L.** [US/US]; 5 Avens Hill Drive, Greer, SC 29651 (US). **SPEER, Drew, V.** [US/US]; 204 English Oak Road, Simpsonville, SC 29681 (US). **BEALL, Gary, W.** [US/US]; 805 Valley View West, San Marcos, TX 78666 (US).

(74) Agents: **RUBLE, Daniel, Bi** et al.; CRYOVAC, INC., SEALED AIR CORPORATION, Post Office Box 464, 100 Rogers Bridge Rd., Duncan, SC 29334 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LV, LY, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, LV, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: INTERCALATED LAYERED SILICATE

(57) Abstract: An intercalated layered silicate comprises a layered silicate and an intercalating agent sorbed between the silicate layers of the layered silicate. The amount of intercalating agent is effective to provide an average interlayer spacing between the silicate layers of at least about 20Å. The intercalating agent comprises one or more of fatty acid esters of sorbitan, ethoxylated fatty esters of sorbitan, fatty acid esters of glycerol, fatty acid esters of polyglycerol, fatty acid amide waxes, variants of amide waxes, and variants of amides. The intercalated layered silicate may be exfoliated by mixing it with a matrix medium and adding sufficient energy to form a dispersed-particle composition. A packaging film, such as a food packaging film, may comprise the dispersed-particle composition.



WO 2007/024564 A1

INTERCALATED LAYERED SILICATE

This application claims the benefit of U.S. Provisional Application No. 60/710,015 filed August 19, 2005, which is incorporated herein in its entirety by reference.

5BACKGROUND

The present invention relates to intercalated layered silicates and to dispersed-particle compositions comprising silicate platelets exfoliated from intercalated layered silicates.

10 Intercalated clays may be made using a quaternary ammonium-based intercalating agent. However, it may be difficult to obtain government agency approval to utilize quaternary ammonium-based intercalating agents in some end-use applications, such as food-contacting materials. Further, quaternary ammonium-based intercalating agents may show an unacceptably high amount of decomposition at the processing resident times and temperatures desired for processing a matrix medium incorporating the quaternary
15 ammonium-based intercalating agent.

SUMMARY

One or more embodiments of the present invention may address one or more of the aforementioned problems.

20 An intercalated layered silicate comprises a layered silicate and an intercalating agent sorbed between the silicate layers of the layered silicate. The amount of intercalating agent is effective to provide an average interlayer spacing between the silicate layers of at least about 20Å. The intercalating agent may comprise compounds selected from one or more of fatty acid esters of sorbitan, ethoxylated fatty esters of sorbitan, fatty acid
25 esters of glycerol, fatty acid esters of polyglycerol, fatty acid amide waxes, variants of amide waxes, variants of amides, and lecithin.

The intercalated layered silicate may be exfoliated by mixing it with a matrix medium and adding sufficient energy to form a dispersed-particle composition. A packaging film, such as a food packaging film, may comprise the dispersed-particle composition.

30 Additional aspects and embodiments of the invention will be more readily understood and appreciated by reference to the detailed description below.

DETAILED DESCRIPTION

An intercalated layered silicate comprises a layered silicate comprising a plurality of silicate layers. An intercalating agent is sorbed between the silicate layers in an amount effective to provide an average interlayer spacing between the silicate layers of at least about 20Å.

Layered Silicate

The intercalated layered silicate comprises a layered silicate. The layered silicate (i.e., phyllosilicate) may be naturally occurring or synthetically derived. Exemplary layered silicates include:

1. Natural clays such as smectite clays, for example, bentonite clays (e.g., montmorillonite, hectorite), mica, vermiculite, nontronite, beidellite, volkonskoite, and saponite;
2. Layered polysilicates (e.g., layered silicic acid), such as kanemite, makatite, ilerite, octosilicate, magadiite, and kenyaite; and
3. Synthetic clays, such as, synthetic silicates, synthetic mica, synthetic saponite, synthetic laponite, and synthetic hectorite.

Layered silicates comprise a plurality of silicate layers, that is, a laminar structure having a plurality of stacked silicate sheets or layers with a variable interlayer distance between the layers. For example, the layered silicate may have a 2:1 layer structure typified by an octahedral layer, comprising aluminum or magnesium, sandwiched between two tetrahedral silicate layers. The layers of the layered silicate may be turbostratic relative to each other, such that the layered silicate may be swellable, for example, in water. The average thickness of the silicate layers may be at least about any of the following: 3, 5, 8, 10, 15, 20, 30, 40, and 50 Å; and at most about any of the following: 60, 50, 45, 35, 25, 20, 15, 12, 10, 8, and 5 Å. For example, many layered silicates have a silicate layer thickness ranging from 8 to 11 Å.

The average interlayer spacing of the layered silicate at 60% relative humidity before intercalation with the intercalating agent may be at least about any of the following: 1,

2, 3, 4, 5, 6, 8, and 10 Å; and may be at most about any of the following: 20, 15, 10, 8, 6, 5, 3, and 2 Å.

5 The average interlayer spacing (i.e., the gallery spacing) of a layered silicate (including an intercalated layered silicate) refers to the distance between the internal faces of the non-exfoliated, adjacent layers of representative samples of the layered silicate. The interlayer spacing may be calculated using standard powder wide angle X-ray diffraction techniques generally accepted in the art in combination with Bragg's law equation, as is known in the art.

10 Useful layered silicates are available from various companies including Nanocor, Inc., Southern Clay Products, Kunimine Industries, Ltd., and Rheox.

Intercalating Agent

15 The intercalated layered silicate comprises an intercalating agent sorbed between the silicate layers of the layered silicate. The term "sorbed" in this context means inclusion within the layered silicate (for example, by adsorption and/or absorption) without covalent bonding. An intercalating agent that is sorbed between silicate layers may be held to the interlayer surface of a silicate layer by one or more of ionic complexing, electrostatic complexing, chelation, hydrogen bonding, ion-dipole interaction, dipole-dipole interaction, and van der Waals forces.

20 The intercalating agent may comprise one or more compounds selected from any of the following:

- 25 1) Fatty acid esters of sorbitan, for example, sorbitan monostearate, sorbitan tristearate, sorbitan monolaurate, sorbitan monopalmitate, sorbitan monooleate, and sorbitan trioleate. Fatty acid esters of sorbitan are available, for example, from Uniquema Corporation (New Castle, DE) under the SPAN 20, SPAN 40, and SPAN 60 trade names.
- 2) Ethoxylated fatty esters of sorbitan, for example, ethoxylated sorbitan monostearate, ethoxylated sorbitan monolaurate, ethoxylated sorbitan monooleate, and ethoxylated sorbitan monopalmitate. Ethoxylated fatty esters of sorbitan are available, for example, from Uniquema Corporation (New Castle, DE) under the Tween 20, Tween 40, and 30 Tween 60 trade names.
- 3) Fatty acid esters of glycerol, for example, glycerol monostearate, glycerol distearate, glycerol palmitate, glycerol oleate, glycerol dioleate, glycerol dipalmitate, glycerol

monolaurate, glycerol dilaurate, glycerol monomyristate, glycerol monobehenate, glycerol monohydroxystearate, glycerol dihydroxystearate, glycerol monoricinoleate, and glycerol diricinoleate; and fatty acid esters of polyglycerol, for example, polyglycerol-3 stearate, polyglycerol-6 stearate, and polyglycerol-10 stearate. Fatty acid esters of glycerol and fatty acid esters of polyglycerol are available, for example, from Akzo Nobel Polymer Chemicals Company (Chicago, IL) under the Armostat 1000 trade name and from Lonza Inc. (Allendale, NJ) under the Glycolube 180 trade name.

4) Fatty acid amide waxes, for example, lauric diethanol amide, myristic diethanol amide, oleic diethanol amide, palmitic diethanol amide, stearic diethanol amide, and behenic diethanol amide. Fatty acid amide waxes are available, for example, from Chemax Performance Products, a division of Rutgers Organics Corporation (State College, PA), under the Chemstat LD-100 and the Chemid ODA 100 trade names, and from Akzo Nobel Polymer Chemicals Company (Chicago, IL) under the Armostat 2000 trade name.

5) Variants of amide waxes, for example, N,N' ethylene bis-stearamide, ethylene bis-oleamide, N-(2-hydroxyethyl)-12-hydroxystearamide, and N,N'-ethylene-bis(12-hydroxystearamide). Amide wax variants are available, for example, from Crompton Corporation (Middlebury, CT) under the Kemamide W-20 and Kemamide W-40 trade names.

6) Variants of amides, for example, oleyl palmityl amide, stearyl erucamide, and stearyl stearamide. Amide variants are available, for example, from Crompton Corporation (Middlebury, CT) under the Kemamide P-181 trade name and from Croda Inc. (Arlington, TX) under the Crodamide 212 trade name.

7) Lecithin and hydrogenated lecithin.

Suitable methods for the synthesis of the above compounds are known to those of skill in the art, and may be found, for example, in *Advanced Organic Chemistry*, 3rd Ed., Jerry March, John Wiley & Sons, New York, 1985, which is incorporated herein in its entirety by reference. Many of these compounds are commercially available, for example, as noted above.

The intercalating agent may be a nonionic intercalating agent, that is, an intercalating agent that does not tend to form or exchange ions, for example, in intercalating a layered silicate.

The average interlayer spacing between the silicate layers of the intercalated layered silicate may be at least about any of the following: 20, 30, 40, 50, 60, 70, 80, and

90Å; and/or may be at most about any of the following: 100, 90, 80, 70, 60, 50, 40, 30, 25Å.

The amount of intercalating agent sorbed between the silicate layers may be effective to provide any of the forgoing average interlayer spacing between the silicate layers. The measurement of the average interlayer spacing of the intercalated layered silicate may be
5 made at a relative humidity of 60%.

The amount of intercalating agent sorbed in the intercalated layered silicate per 100 weight parts layered silicate may be at least about and/or at most about any of the following: 5, 10, 20, 30, 50, 70, 90, 110, 150, 200, and 300 weight parts.

The intercalated layered silicate may be essentially free of intercalating agent
10 comprising onium functionality. The intercalated silicate may be essentially free of any one, or of all, or of any combination of the following compounds: ammonium compounds, quaternary ammonium compounds, tertiary ammonium compounds, secondary ammonium compounds, primary ammonium compounds, phosphonium compounds, quaternary phosphonium compounds, tertiary phosphonium compounds, secondary phosphonium
15 compounds, primary phosphonium compounds, arsonium compounds, stibonium compounds, oxonium compounds, and sulfonium compounds.

Exemplary ammonium compounds from which the intercalated layered silicate may be essentially free include any one or any combination of the following: alkyl ammonium compounds, such as tetramethyl ammonium compounds, hexyl ammonium
20 compounds, butyl ammonium compounds, bis(2-hydroxyethyl) dimethyl ammonium compounds, bis(2-hydroxyethyl) octadecyl methyl ammonium compounds, octadecyl trimethyl ammonium compounds, octadecyl benzyl dimethyl ammonium compounds, hexyl benzyl dimethyl ammonium compounds, benzyl trimethyl ammonium compounds, butyl benzyl dimethyl ammonium compounds, tetrabutyl ammonium compounds, dodecyl
25 ammonium compounds, di(2-hydroxyethyl) ammonium compounds, and polyalkoxylated ammonium compounds.

Exemplary phosphonium compounds from which the intercalated layered silicate may be essentially free include any one or any combination of the following: alkyl phosphonium compounds, such as tetrabutyl phosphonium compounds, trioctyl octadecyl
30 phosphonium compounds, tetraoctyl phosphonium compounds, octadecyl triphenyl phosphonium compounds.

The intercalated layered silicate may be essentially free of any intercalating agent comprising a compound selected from any or all of the compounds listed in the previous three paragraphs.

5

Manufacture of the Intercalated Layered Silicate

To make the intercalated layered silicate, a layered silicate is mixed with the intercalating agent to effect the inclusion (i.e., sorption) of the intercalating agent in the interlayer space between the silicate layers of the layered silicate. In doing so, the resulting intercalated layered silicate may be rendered organophilic (i.e., hydrophobic) and show an enhanced attraction to an organic matrix medium.

10

In making the intercalated layered silicate, the intercalating agent may first be mixed with a carrier, for example, a carrier comprising one or more solvents such as water and/or organic solvents such as ethanol to disperse or solubilize the intercalating agent in the carrier. The intercalating agent/carrier blend may subsequently be mixed with the layered silicate. Alternatively, the layered silicate may be mixed with the carrier to form a slurry, to which the intercalating agent may be added. Also, the intercalating agent may be mixed directly with the layered silicate without the benefit of a carrier. Intercalation may be enhanced by addition of one or more of heat, pressure, high shear mixing, ultrasonic cavitation, and microwave radiation to any of the above systems.

15

The inclusion of the intercalation agent within the interlayer spaces between the silicate layers of the layered silicate increases the interlayer spacing between adjacent silicate layers. This may disrupt the tactoid structure of the layered silicate to enhance the dispersibility of the intercalated layered silicate in the matrix medium, as discussed below.

20

The intercalating agent sorbed between the silicate layers may be an amount and/or type effective to increase the interlayer spacing between the silicate layers – relative to the spacing before the sorption of the intercalating agent -- by at least about any of the following: 5, 6, 7, 8, 10, 12, 14, 15, 18, 20, 30, 40, 50, 60, 70, 80, and 90 Å; and/or by at most about any of the following: 100, 90, 80, 70, 60, 50, 40, 30, 25, 20, 18, 15, 12, 10, 8, and 7 Å.

25

The intercalated layered silicate may be further treated to aid dispersion and/or exfoliation in a matrix medium and/or improve the strength of a resulting polymer/silicate interface. For example, the intercalated layered silicate may be treated with a surfactant to

30

enhance compatibility with the matrix medium. Also by way of example, the intercalated layered silicate may be further intercalated with a compatibilizer, such as a polyolefin oligomer having polar groups. An example is maleic anhydride modified olefin oligomer or maleic anhydride modified ethylene vinyl acetate oligomer. An oligomer may be modified (e.g., grafted) with unsaturated carboxylic acid anhydride (i.e., anhydride-modified oligomer) to incorporate anhydride functionality, which promotes or enhances the adhesion characteristics of the oligomer. Examples of unsaturated carboxylic acid anhydrides include maleic anhydride, fumaric anhydride, and unsaturated fused ring carboxylic acid anhydrides. Anhydride-modified polymer may be made by grafting or copolymerization, as is known in the art. Useful anhydride-modified oligomers may contain anhydride group in an amount (based on the weight of the modified polymer) of at least about any of the following: 0.1%, 0.5%, 1%, and 2%; and/or at most about any of the following: 10%, 7.5%, 5%, and 4%.

The intercalated layered silicate may have a peak degradation temperature of at least about any of the following: 360, 380, 390, 395, 400, 405, 410, 420, 430, and 440°C; and/or at most about any of the following: 380, 390, 395, 400, 405, 410, 420, 430, 440, and 450°C. The intercalated layered silicate may have an onset temperature of degradation of at least about any of the following: 200, 210, 220, 230, 240, 250, and 280°C; and/or at most about any of the following: 220, 230, 240, 250, 280, and 300°C. The peak degradation temperature and onset temperature of degradation may be determined by thermogravimetric analysis (TGA) of the sample operating at a 20°C per minute scan rate from room temperature to 800°C in an argon purged atmosphere, and utilizing first derivative of weight loss analysis. A useful TGA machine for such analysis is the TGA Q50 model available from TA Instruments, Inc.

25 Dispersed-Particle Composition

The intercalated layered silicate may be exfoliated to form a dispersed-particle composition comprising a plurality of dispersed particles comprising exfoliated silicate platelets dispersed within a matrix medium. The dispersed particles may comprise silicate platelets having sorbed intercalating agent of the type previously discussed.

30 The matrix medium may comprise one or more polymers, for example, one or more thermoplastic polymers, such as one or more polymers selected from polyolefin,

ethylene/vinyl alcohol copolymer, ionomer, vinyl plastic, polyamide, polyester, and polystyrene.

The matrix medium may comprise one or more energy curable polymer precursors, for example, one or more energy curable precursors selected from multifunctional
5 acrylates or methacrylates, thiol-ene systems, epoxy/amine or epoxy polyol systems, and polyurethane precursors such as isocyanates and polyols.

The matrix medium may comprise one or more compounds useful in the formulation of paints, coatings, varnishes, greases, cosmetics, or pharmaceutical excipients (either topical or internal).

10

Polyolefins

The matrix medium may comprise one or more polyolefins. Exemplary polyolefins include ethylene homo- and co-polymers and propylene homo- and co-polymers. The term "polyolefins" includes copolymers that contain at least 50 mole % monomer units
15 derived from olefin. Ethylene homopolymers include high-density polyethylene ("HDPE") and low density polyethylene ("LDPE"). Ethylene copolymers include ethylene/alpha-olefin copolymers ("EAOs"), ethylene/unsaturated ester copolymers, and ethylene/(meth)acrylic acid. ("Copolymer" as used in this application means a polymer derived from two or more types of monomers, and includes terpolymers, etc.)

20 EAOs are copolymers of ethylene and one or more alpha-olefins, the copolymer having ethylene as the majority mole-percentage content. The comonomer may include one or more C₃-C₂₀ α-olefins, one or more C₄-C₁₂ α-olefins, and one or more C₄-C₈ α-olefins. Useful α-olefins include 1-butene, 1-hexene, 1-octene, and mixtures thereof.

25 Exemplary EAOs include one or more of the following: 1) medium density polyethylene ("MDPE"), for example having a density of from 0.926 to 0.94 g/cm³; 2) linear medium density polyethylene ("LMDPE"), for example having a density of from 0.926 to 0.94 g/cm³; 3) linear low density polyethylene ("LLDPE"), for example having a density of from 0.915 to 0.930 g/cm³; 4) very-low or ultra-low density polyethylene ("VLDPE" and "ULDPE"), for example having density below 0.915 g/cm³, and 5) homogeneous EAOs.
30 Useful EAOs include those having a density of less than about any of the following: 0.925, 0.922, 0.92, 0.917, 0.915, 0.912, 0.91, 0.907, 0.905, 0.903, 0.9, and 0.898 grams/cubic

centimeter. Unless otherwise indicated, all densities herein are measured according to ASTM D1505.

5 The polyethylene polymers may be either heterogeneous or homogeneous. As is known in the art, heterogeneous polymers have a relatively wide variation in molecular weight and composition distribution. Heterogeneous polymers may be prepared with, for example, conventional Ziegler-Natta catalysts.

10 On the other hand, homogeneous polymers are typically prepared using metallocene or other single-site catalysts. Such single-site catalysts typically have only one type of catalytic site, which is believed to be the basis for the homogeneity of the polymers resulting from the polymerization. Homogeneous polymers are structurally different from heterogeneous polymers in that homogeneous polymers exhibit a relatively even sequencing of comonomers within a chain, a mirroring of sequence distribution in all chains, and a similarity of length of all chains. As a result, homogeneous polymers have relatively narrow molecular weight and composition distributions. Examples of homogeneous polymers include 15 the metallocene-catalyzed linear homogeneous ethylene/alpha-olefin copolymer resins available from the Exxon Chemical Company (Baytown, TX) under the EXACT trademark, linear homogeneous ethylene/alpha-olefin copolymer resins available from the Mitsui Petrochemical Corporation under the TAFMER trademark, and long-chain branched, metallocene-catalyzed homogeneous ethylene/alpha-olefin copolymer resins available from 20 the Dow Chemical Company under the AFFINITY trademark.

25 Another exemplary ethylene copolymer is ethylene/unsaturated ester copolymer, which is the copolymer of ethylene and one or more unsaturated ester monomers. Useful unsaturated esters include: 1) vinyl esters of aliphatic carboxylic acids, where the esters have from 4 to 12 carbon atoms, and 2) alkyl esters of acrylic or methacrylic acid (collectively, "alkyl (meth)acrylate"), where the esters have from 4 to 12 carbon atoms.

Representative examples of the first ("vinyl ester") group of monomers include vinyl acetate, vinyl propionate, vinyl hexanoate, and vinyl 2-ethylhexanoate. The vinyl ester monomer may have from 4 to 8 carbon atoms, from 4 to 6 carbon atoms, from 4 to 5 carbon atoms, and preferably 4 carbon atoms.

30 Representative examples of the second ("alkyl (meth)acrylate") group of monomers include methyl acrylate, ethyl acrylate, isobutyl acrylate, n-butyl acrylate, hexyl acrylate, and 2-ethylhexyl acrylate, methyl methacrylate, ethyl methacrylate, isobutyl

methacrylate, n-butyl methacrylate, hexyl methacrylate, and 2-ethylhexyl methacrylate. The alkyl (meth)acrylate monomer may have from 4 to 8 carbon atoms, from 4 to 6 carbon atoms, and preferably from 4 to 5 carbon atoms.

5 The unsaturated ester (i.e., vinyl ester or alkyl (meth)acrylate) comonomer content of the ethylene/unsaturated ester copolymer may range from about 6 to about 18 weight %, and from about 8 to about 12 weight %, based on the weight of the copolymer. Useful ethylene contents of the ethylene/unsaturated ester copolymer include the following amounts: at least about 82 weight %, at least about 85 weight %, at least about 88 weight %, no greater than about 94 weight %, no greater than about 93 weight %, and no greater than
10 about 92 weight %, based on the weight of the copolymer.

Representative examples of ethylene/unsaturated ester copolymers include ethylene/methyl acrylate, ethylene/methyl methacrylate, ethylene/ethyl acrylate, ethylene/ethyl methacrylate, ethylene/butyl acrylate, ethylene/2-ethylhexyl methacrylate, and ethylene/vinyl acetate.

15 Another useful ethylene copolymer is ethylene/(meth)acrylic acid, which is the copolymer of ethylene and acrylic acid, methacrylic acid, or both.

Useful propylene copolymer includes: 1) propylene/ethylene copolymers ("EPC"), which are copolymers of propylene and ethylene having a majority weight % content of propylene, such as those having an ethylene comonomer content of less than 15%,
20 less than 6%, and at least about 2% by weight and 2) propylene/butene copolymers having a majority weight % content of propylene.

EVOH

Ethylene/vinyl alcohol copolymer ("EVOH") is another useful thermoplastic.
25 EVOH may have an ethylene content of about 32 mole %, or at least about any of the following values: 20 mole %, 25 mole %, and 30 mole %. EVOH may have an ethylene content of below about any of the following values: 50 mole %, 40 mole %, and 33 mole %. As is known in the art, EVOH may be derived by saponifying or hydrolyzing ethylene/vinyl acetate copolymers, for example, to a degree of hydrolysis of at least about any of the following
30 values: 50%, 85%, and 98%.

Ionomer

Another useful thermoplastic is ionomer, which is a copolymer of ethylene and an ethylenically unsaturated monocarboxylic acid having the carboxylic acid groups partially neutralized by a metal ion, such as sodium or zinc. Useful ionomers include those in which sufficient metal ion is present to neutralize from about 10% to about 60% of the acid groups in the ionomer. The carboxylic acid is preferably “(meth)acrylic acid” – which means acrylic acid and/or methacrylic acid. Useful ionomers include those having at least 50 weight % and preferably at least 80 weight % ethylene units. Useful ionomers also include those having from 1 to 20 weight percent acid units. Useful ionomers are available, for example, from Dupont Corporation (Wilmington, DE) under the SURLYN trademark.

Vinyl Plastics

Useful vinyl plastics include polyvinyl chloride (“PVC”), vinylidene chloride polymer (“PVdC”), and polyvinyl alcohol (“PVOH”). Polyvinyl chloride (“PVC”) refers to a vinyl chloride-containing polymer or copolymer – that is, a polymer that includes at least 50 weight percent monomer units derived from vinyl chloride ($\text{CH}_2 = \text{CHCl}$) and also, optionally, one or more comonomer units, for example, derived from vinyl acetate. One or more plasticizers may be compounded with PVC to soften the resin and/or enhance flexibility and processibility. Useful plasticizers for this purpose are known in the art.

Another exemplary vinyl plastic is vinylidene chloride polymer (“PVdC”), which refers to a vinylidene chloride-containing polymer or copolymer – that is, a polymer that includes monomer units derived from vinylidene chloride ($\text{CH}_2 = \text{CCl}_2$) and also, optionally, monomer units derived from one or more of vinyl chloride, styrene, vinyl acetate, acrylonitrile, and $\text{C}_1 - \text{C}_{12}$ alkyl esters of (meth)acrylic acid (e.g., methyl acrylate, butyl acrylate, methyl methacrylate). As used herein, “(meth)acrylic acid” refers to both acrylic acid and/or methacrylic acid; and “(meth)acrylate” refers to both acrylate and methacrylate. Examples of PVdC include one or more of the following: vinylidene chloride homopolymer, vinylidene chloride/vinyl chloride copolymer (“VDC/VC”), vinylidene chloride/methyl acrylate copolymer (“VDC/MA”), vinylidene chloride/ethyl acrylate copolymer, vinylidene chloride/ethyl methacrylate copolymer, vinylidene chloride/methyl methacrylate copolymer, vinylidene chloride/butyl acrylate copolymer, vinylidene chloride/styrene copolymer, vinylidene chloride/acrylonitrile copolymer, and vinylidene chloride/vinyl acetate copolymer.

Useful PVdC includes that having at least about 75, at most about 95, and at most about 98 weight % vinylidene chloride monomer. Useful PVdC (for example, as applied by latex emulsion coating) includes that having at least about any of 5%, 10%, and 15% -- and/or at most about any of 25%, 22%, 20%, and 15 weight % -- comonomer with the vinylidene chloride monomer.

A layer that includes PVdC may also include a thermal stabilizer (e.g., a hydrogen chloride scavenger such as epoxidized soybean oil) and a lubricating processing aid (e.g., one or more acrylates).

10

Polyamide


Useful polyamides include those of the type that may be formed by the polycondensation of one or more diamines with one or more diacids and/or of the type that may be formed by the polycondensation of one or more amino acids and/or of the type formed by the ring opening of cyclic lactams. Useful polyamides include aliphatic polyamides and aliphatic/aromatic polyamides.

Representative aliphatic diamines for making polyamides include those having the formula:



where n has an integer value of 1 to 16. Representative examples include trimethylenediamine, tetramethylenediamine, pentamethylenediamine, hexamethylenediamine, octamethylenediamine, decamethylenediamine, dodecamethylenediamine, hexadecamethylenediamine. Representative aromatic diamines include p-phenylenediamine, 4,4'-diaminodiphenyl ether, 4,4' diaminodiphenyl sulphone, 4,4'-diaminodiphenylethane. Representative alkylated diamines include 2,2-dimethylpentamethylenediamine, 2,2,4-trimethylhexamethylenediamine, and 2,4,4-trimethylpentamethylenediamine. Representative cycloaliphatic diamines include diaminodicyclohexylmethane. Other useful diamines include heptamethylenediamine, nonamethylenediamine, and the like.

Representative diacids for making polyamides include dicarboxylic acids, which may be represented by the general formula:



where Z is representative of a divalent aliphatic or cyclic radical containing at least 2 carbon atoms. Representative examples include aliphatic dicarboxylic acids, such as adipic acid, sebacic acid, octadecanedioic acid, pimelic acid, suberic acid, azelaic acid, dodecanedioic acid, and glutaric acid; and aromatic dicarboxylic acids, such as isophthalic acid and terephthalic acid.

The polycondensation reaction product of one or more of the above diamines with one or more of the above diacids may form useful polyamides. Representative polyamides of the type that may be formed by the polycondensation of one or more diamines with one or more diacids include aliphatic polyamides such as poly(hexamethylene adipamide) (“nylon-6,6”), poly(hexamethylene sebacamide) (“nylon-6,10”), poly(heptamethylene pimelamide) (“nylon-7,7”), poly(octamethylene suberamide) (“nylon-8,8”), poly(hexamethylene azelamide) (“nylon-6,9”), poly(nonamethylene azelamide) (“nylon-9,9”), poly(decamethylene azelamide) (“nylon-10,9”), poly(tetramethylenediamine-co-oxalic acid) (“nylon-4,2”), the polyamide of n-dodecanedioic acid and hexamethylenediamine (“nylon-6,12”), the polyamide of dodecamethylenediamine and n-dodecanedioic acid (“nylon-12,12”).

Representative aliphatic/aromatic polyamides include poly(tetramethylenediamine-co-isophthalic acid) (“nylon-4,I”), polyhexamethylene isophthalamide (“nylon-6,I”), polyhexamethylene terephthalamide (“nylon-6,T”), poly(2,2,2-trimethyl hexamethylene terephthalamide), poly(m-xylylene adipamide) (“nylon-MXD,6”), poly(p-xylylene adipamide), poly(hexamethylene terephthalamide), poly(dodecamethylene terephthalamide), and polyamide-MXD,I.

Representative polyamides of the type that may be formed by the polycondensation of one or more amino acids include poly(4-aminobutyric acid) (“nylon-4”), poly(6-aminohexanoic acid) (“nylon-6” or “poly(caprolactam)”), poly(7-aminoheptanoic acid) (“nylon-7”), poly(8-aminooctanoic acid) (“nylon-8”), poly(9-aminononanoic acid) (“nylon-9”), poly(10-aminodecanoic acid) (“nylon-10”), poly(11-aminoundecanoic acid) (“nylon-11”), and poly(12-aminododecanoic acid) (“nylon-12” or “poly(lauryllactam)”).

Representative copolyamides include copolymers based on a combination of the monomers used to make any of the foregoing polyamides, such as, nylon-4/6, nylon-6/6, nylon-6/9, nylon-6/12, caprolactam/hexamethylene adipamide copolymer (“nylon-6,6/6”),

hexamethylene adipamide/caprolactam copolymer (“nylon-6/6,6”), trimethylene adipamide/hexamethylene azelaamide copolymer (“nylon-trimethyl 6,2/6,2”), hexamethylene adipamide-hexamethylene-azelaamide caprolactam copolymer (“nylon-6,6/6,9/6”), hexamethylene adipamide/hexamethylene-isophthalamide (“nylon-6,6/6,I”),
5 hexamethylene adipamide/hexamethyleneterephthalamide (“nylon-6,6/6,T”), nylon-6,T/6,I, nylon-6/MXD,T/MXD,I, nylon-6,6/6,10, and nylon-6,I/6,T.

Conventional nomenclature typically lists the major constituent of a copolymer before the slash (“/”) in the name of a copolymer; however, in this application the constituent listed before the slash is not necessarily the major constituent unless specifically
10 identified as such. For example, unless the application specifically notes to the contrary, “nylon-6/6,6” and “nylon-6,6/6” may be considered as referring to the same type of copolyamide.

Polyamide copolymers may include the most prevalent polymer unit in the copolymer (e.g., hexamethylene adipamide as a polymer unit in the copolymer nylon-6,6/6)
15 in mole percentages ranging from any of the following: at least about 50%, at least about 60%, at least about 70%, at least about 80%, and at least about 90%, and the ranges between any of the forgoing values (e.g., from about 60 to about 80%); and may include the second most prevalent polymer unit in the copolymer (e.g., caprolactam as a polymer unit in the copolymer nylon-6,6/6) in mole percentages ranging from any of the following: less than
20 about 50%, less than about 40%, less than about 30%, less than about 20%, less than about 10%, and the ranges between any of the forgoing values (e.g., from about 20 to about 40%).

Useful polyamides include those that are approved by the controlling regulating agency (e.g., the U.S. Food and Drug Agency) for either direct contact with food and/or for use in a food packaging film, at the desired conditions of use.
25

Polyesters

Useful polyesters include those made by: 1) condensation of polyfunctional carboxylic acids with polyfunctional alcohols, 2) polycondensation of hydroxycarboxylic acid, and 3) polymerization of cyclic esters (e.g., lactone).

30 Exemplary polyfunctional carboxylic acids (and their derivatives such as anhydrides or simple esters like methyl esters) include aromatic dicarboxylic acids and

derivatives (e.g., terephthalic acid, isophthalic acid, dimethyl terephthalate, dimethyl isophthalate) and aliphatic dicarboxylic acids and derivatives (e.g., adipic acid, azelaic acid, sebacic acid, oxalic acid, succinic acid, glutaric acid, dodecanoic diacid, 1,4-cyclohexane dicarboxylic acid, dimethyl-1,4-cyclohexane dicarboxylate ester, dimethyl adipate). Useful 5 dicarboxylic acids also include those discussed above in the polyamide section. As is known to those of skill in the art, polyesters may be produced using anhydrides and esters of polyfunctional carboxylic acids.

Exemplary polyfunctional alcohols include dihydric alcohols (and bisphenols) such as ethylene glycol, 1,2- propanediol, 1,3-propanediol, 1,3 butanediol, 1,4-butanediol, 10 1,4-cyclohexanedimethanol, 2,2-dimethyl-1,3-propanediol, 1,6-hexanediol, poly(tetrahydroxy-1,1'-biphenyl, 1,4-hydroquinone, and bisphenol A.

Exemplary hydroxycarboxylic acids and lactones include 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, pivalolactone, and caprolactone.

Useful polyesters include homopolymers and copolymers. These may be 15 derived from one or more of the constituents discussed above. Exemplary polyesters include poly(ethylene terephthalate) ("PET"), poly(butylene terephthalate) ("PBT"), and poly(ethylene naphthalate) ("PEN"). If the polyester includes a mer unit derived from terephthalic acid, then such mer content (mole %) of the diacid component of the polyester may be at least about any the following: 70, 75, 80, 85, 90, and 95 %.

20 The polyester may be thermoplastic. The polyester (e.g., copolyester) of the film may be amorphous, or may be partially crystalline (semi-crystalline), such as with a crystallinity of at least about, or at most about, any of the following weight percentages: 10, 15, 20, 25, 30, 35, 40, and 50 %.

25 Polystyrene
The matrix medium may comprise polystyrene. Exemplary polystyrene includes styrene homo- and co-polymers. Polystyrene may be substantially atactic, syndiotactic or isotactic. The term "polysytrene" includes copolymer that contains at least 50 mole % monomer units derived from styrene. Styrene may be copolymerized with alkyl acrylates, maleic 30 anhydride, isoprene, or butadiene. Styrene copolymers with isoprene and butadiene may be further hydrogenated.

Energy Curable Polymer Precursors

The matrix medium may comprise one or more energy curable polymer precursors. An energy curable polymer precursor is a compound (e.g., monomer or oligomer) that is intended for transformation to a cured polymer by the application of energy in the form of heat and/or radiation (e.g., light), and may also involve an initiator and/or catalyst. The resulting energy cured polymer may be a thermoset polymer or a thermoplastic polymer. A single energy curable polymer precursor may react to form a polymer, or two or more energy curable polymer precursors may react together to form a polymer. The energy curable polymer precursor may be multifunctional, that is, adapted to form crosslinked polymer when cured. The energy curable chemical reaction may be induced by heat, catalyst interaction, radiation (e.g., light), or mixing of the energy curable polymer precursors.

Useful energy curable polymer precursors may include one or more of the energy curable polymer precursors that are precursors to one or more of the following polymers: polyester resins (e.g., alkyd resin), allyl resins (e.g., diallyl phthalate, diallyl isophthalate, diallyl maleate, and diallyl chloroendate), amino resins (e.g., urea resins, melamine resins, and their copolymers with formaldehyde), epoxy resins, furan resins, phenolic resins (e.g., phenol-alkyl resins, phenol-formaldehyde resins), polyacrylic ester resins, polyamide resins, polyurethane resins, polyacrylamide resins, polyimide resins, and acrylamide resins.

Exemplary energy curable polymer precursors may include (meth)acrylates (i.e., methacrylates and/or acrylates), multifunctional (meth)acrylates, thiol-ene systems, and maleimides.

Exemplary energy curable polymer precursors, for example, with respect to polyurethane polymer precursors, may include polyols and polyisocyanates (e.g., toluene diisocyanate and diphenyl-methanediisocyanate).

With respect to the polyurethane and epoxy resin precursors, for example, the intercalated layered silicate may be mixed with the polyol precursor component rather than the more reactive component to help minimize premature reaction.

Additional Matrix Medium

The matrix medium may comprise one or more compounds useful in the formulation of one or more of any of the following: coatings (i.e., paints and/or varnishes), inks, greases, cosmetics, and pharmaceutical dosage forms.

5 The matrix medium may comprise one or more materials selected from coating (i.e., paint and/or varnish) solvents, coating binders, and coating resins. Useful coating solvents, coating binders, and coating resins are known to those of skill in the art; see, for example, those discussed in *Paints and Coatings*, Ullmann's Encyclopedia of Industrial Chemistry, Volume 24, pages 591-790 (2003 Wiley-VCH), of which pages 591-790 are
10 incorporated herein by reference. Examples include mineral spirits, toluene, and linseed oil.

The matrix medium may comprise one or more materials selected from ink solvents and ink resins (e.g., ink binders and/or ink vehicles). Useful ink solvents and ink resins are known to those of skill in the art; see, for example, those discussed in Leach and Pierce, *The Printing Ink Manual* (5th edition 1993), which is incorporated herein in its
15 entirety.

The matrix medium may comprise one or more materials selected from grease lubricating oils and grease gelling agents. Useful grease lubricating oils and grease gelling agents are known to those of skill in the art; see, for example, those discussed in *Kirk-Othmer Encyclopedia of Chemical Technology*, Volume 15, pages 493-98 (4th edition 1995), of
20 which pages 493-98 are incorporated herein by reference.

The matrix medium may comprise one or more materials useful in the formulation of cosmetics, for example, one or more materials selected from lipids, emollients, humectants, film formers, binders, surfactants, and solvents. Useful cosmetic lipids, emollients, humectants, film formers, binders, surfactants, and solvents are known to those of
25 skill in the art; see, for example, those discussed in *Kirk-Othmer Encyclopedia of Chemical Technology*, Volume 7, pages 572-619 (4th edition 1993), of which pages 572-619 are incorporated herein by reference, and *CTFA International Cosmetic Ingredient Handbook*, 2nd edition (CTFA Washington DC 1992), which is incorporated herein in its entirety by
reference.

30 Compounds useful in the formulation of pharmaceutical dosage forms include pharmaceutical (e.g., medical) excipients (e.g., carriers). The matrix medium may comprise one or more pharmaceutical excipients, for example, one or more excipients adapted for an

internal pharmaceutical dosage form and/or adapted for an external pharmaceutical dosage form. Useful pharmaceutical excipients are known to those of skill in the art; see, for example, those discussed in Pharmaceutical Dosage Forms, Ullmann's Encyclopedia of Industrial Chemistry, Volume 25, pages 515-547 (2003 Wiley-VCH), of which pages 515-
5 547 are incorporated herein by reference.

The matrix medium may comprise one or more of water, an oil-in-water emulsion, and a water-in-oil emulsion.

Dispersed Particles

10 The dispersed particles in the dispersed-particle composition may have an average size of less than about 100 nm in at least one dimension. The particles may have an average aspect ratio (i.e., the ratio of the average largest dimension to the average smallest dimension of the particles) of from about 10 to about 30,000. Typically, the aspect ratio for particles comprising silicate platelets exfoliated from an intercalated layered silicate may be
15 taken as the length (largest dimension) to the thickness (smallest dimension) of the platelets. For a particle having a fiber configuration, the aspect ratio may be taken as the length (largest dimension) to the diameter (smallest dimension) of the particle.

Useful aspect ratios for the dispersed particles include at least about any of the following values: 10; 20; 25; 200; 250; 1,000; 2,000; 3,000; and 5,000; and at most about any
20 of the following values: 25,000; 20,000; 15,000; 10,000; 5,000; 3,000; 2,000; 1,000; 250; 200; 25; and 20.

The dispersed particles may have an average size in the shortest dimension of at least about any of the following values: 0.5 nm, 0.8 nm, 1 nm, 2 nm, 3 nm, 4 nm, and 5 nm; and at most about any of the following values: 100 nm, 60 nm, 30 nm, 20 nm, 10 nm, 8
25 nm, 5 nm, and 3 nm, as estimated from transmission electron microscope ("TEM") images. The particles may have an average dimension small enough to maintain optical transparency of the matrix medium in which the particles are dispersed.

The amount of exfoliated particles dispersed in the dispersed-particle composition may be at least about any of the following values 0.1, 0.5, 1, 1.5, 2, 2.5, 3, 4, 5,
30 and 10 weight %; and/or may be at most about any of the following values: 50, 40, 30, 20, 15, 10, 8, 6, 5, 4, 3, 2, and 1 weight %, based on the weight of the dispersed-particle composition. Also, the amount of exfoliated particles dispersed in the dispersed-particle composition may

be at least about any of the following values: 0.1, 0.5, 1, 1.5, 2, 2.5, 3, 4, 5, and 10 weight parts; and/or may be at most about any of the following values: 100, 80, 60, 50, 40, 30, 20, 15, 10, 8, 6, 5, 4, 3, 2, and 1 weight parts, based on 100 weight parts of matrix medium, for example, based on 100 weight parts of the one or more polymers discussed above.

5 The dispersed-particle composition may comprise at least about any of the following: 50, 60, 70, 80, 90, 95, and 98 weight %; and at most about any of the following: 99, 98, 95, 90, 80, 70, and 60 weight %, based on the weight of the dispersed-particle composition of any of the following: 1) the matrix medium, or 2) the one or more polymers, or 3) the energy curable polymer precursors, or 4) the coating solvents, coating binders, or
10 coating resins, or 5) the ink solvents or ink resins, or 6) the grease lubricating oils or grease gelling agents, or 7) the cosmetic lipids, cosmetic emollients, cosmetic humectants, cosmetic film formers, cosmetic binders, cosmetic surfactants, or cosmetic solvents, or 8) pharmaceutical excipients.

15 The particles may comprise silicate platelets derived from the intercalated layered silicate and an intercalating agent sorbed to the silicate platelets. Exemplary intercalating agents are discussed above. The dispersed-particle composition may be essentially free of intercalating agent comprising onium functionality, such as any one, or of all, or of any combination of the onium compounds discussed above.

20 The amount of intercalating agent sorbed to the silicate platelets may be at least about and/or at most about any of the following: 1, 5, 10, 20, 30, 50, 70, 90, 110, 150, 200, and 300 weight parts per 100 weight parts silicate platelets.

25 It is believed that exfoliated particles result when individual silicate layers of a layered silicate are no longer close enough to interact significantly with the adjacent layers via ionic or van der Waals attractions or to form strongly correlated systems due to the large aspect ratios of the platelets. An exfoliated layered silicate has lost its registry and may be relatively uniformly and randomly dispersed in a continuous matrix medium. It is believed that the dispersion in a matrix medium occurs when the interlayer spacing of the layered silicate is at or greater than the average radius of gyration of the molecules comprising the matrix medium.

A dispersing aid may be used to enhance exfoliation of the intercalated layered silicate into the matrix medium. Exemplary dispersing aids may include one or more of water, alcohols, ketones, aldehydes, chlorinated solvents, hydrocarbon solvents, and aromatic solvents.

5

Manufacture of the Dispersed-Particle Composition

The intercalated layered silicate may be exfoliated in a matrix medium to form the dispersed-particle composition. The intercalated layered silicate may be added to the matrix medium under conditions effective to exfoliate at least a portion of the intercalated layered silicate into particles comprising silicate platelets dispersed in the matrix medium. An amount of intercalated layered silicate mixed with the matrix medium may be at least about any of the following: 0.1, 0.5, 1, 1.5, 2, 2.5, 3, 4, 5, and 10 weight parts intercalated layered silicate; and/or may be at most about any of the following values: 100, 80, 60, 50, 40, 30, 20, 15, 10, 8, 6, 5, 4, 3, 2, and 1 weight parts intercalated layered silicate, based on 100 weight parts of matrix medium, for example, based on 100 weight parts of the one or more polymers discussed above.

101520

At least about any of the following amounts of the intercalated layered silicate added to the matrix medium may be dispersed as exfoliated particles having an average size of less than about 100 nm in at least one dimension: 50, 60, 70, 80, 90, 95, 98, and 99 weight parts exfoliated particles per 100 weight parts added intercalated layered silicate. The exfoliated silicate platelets may have the average thickness of the individual layers of the layered silicate, or may have as an average thickness multiples of less than about any of 10, 5, and 3 layers of the layered silicate. TEM images may be used to estimate the amount and size and characteristics of the exfoliated particles.

25

The effective exfoliation conditions may include the addition of mixing and/or shearing energy to the mixture of the intercalated layered silicate and the matrix medium. The process variables for exfoliating the intercalated layered silicate in the matrix medium include time, temperature, geometry of the mixing apparatus, and the shear rate, and generally requires a balance of these variables, as is known to those of skill in the art. The balancing of these variables may take into account the desire to minimize the physical degradation or decomposition of the matrix medium and/or the intercalating agent, for

30

example, by limiting the upper temperature of the processing and/or the amount of time at a selected temperature during processing.

An increase in temperature generally provides more thermal energy to enhance exfoliation. A decrease in temperature may lower the viscosity of the mixture while
5 increasing the shear rate. An increase in shear rate generally enhances exfoliation. Shear rates of at least about any of the following may be applied to the mixture of the intercalated layered silicate and the matrix medium: 1 sec⁻¹, 10 sec⁻¹, 50 sec⁻¹, 100 sec⁻¹, and 300 sec⁻¹.

Illustrative methods or systems for applying shear to effect exfoliation of the intercalated layered silicate in the matrix medium include mechanical systems, thermal
10 shock, pressure alternation, and ultrasonics. A flowable mixture may be sheared by mechanical methods, such as the use of stirrers, blenders, Banbury type mixers, Brabender type mixers, long continuous mixers, injection molding machines, and extruders. Twin screw extruders may be useful, for example, for mixing the intercalated layered silicate with a thermoplastic matrix medium. A thermal shock method achieves shearing by alternatively
15 raising and lowering the temperature of the mixture to cause thermal expansions and contractions to induce internal stresses that cause shear. Sudden and alternating pressure changes may also be used to apply shear to the mixture. Ultrasonic methods induce shear by cavitation or resonant vibrations, which cause varying portions of the mixture to vibrate and become excited at different phases.

20 The effective exfoliation conditions may comprise raising the temperature of the matrix medium, for example a matrix medium comprising one or more thermoplastic polymers, so that the matrix medium is thermally processible at a reasonable rate in the mechanical system either before, while, or after adding the intercalated layered silicate to the matrix medium. During processing, the mixture of the intercalated layered silicate and the
25 matrix medium may be at a temperature, for example, of at least about and/or at most about any of the following temperatures: 100°C, 150°C, 200°C, 240°C, 280°C, 300°C, 320°C, 350°C, 380°C, and 400°C. The amount of residence time that the mixture of the intercalated layered silicate and the matrix medium may reside at any of these temperatures may be at least about and/or at most about any of the following times: 2, 4, 5, 8, 10, 12, 15, and 20
30 minutes.

Before effecting exfoliation, the layered silicate may be reduced in size by methods known in the art, including, but not limited to, grinding, pulverizing, hammer milling, jet milling, and their combinations, so that the average particle diameter of the layered silicate may be, for example, less than about any of 100, 50, and 20 microns.

5

Use of the Intercalated Layered Silicate and Dispersed-Particle Composition

The dispersed particles may be used to enhance the physical and/or performance properties of the matrix medium in which they are dispersed. For example, the dispersed particles may improve one or more of the modulus, strength, permeability, rheological, and surface adhesion properties of the matrix medium incorporating the particles relative to the matrix medium without the particles.

10

Several types of products may benefit from incorporation of the dispersed-particle composition to improve, for example, performance properties. Exemplary products that may comprise the dispersed-particle composition include:

15

sheets and panels, which, for example, may be further shaped by pressing, molding, and/or thermoforming to form useful objects;

coatings (i.e., paints and/or varnishes);

lubricants, for example, food-grade lubricants;

greases;

20

personal care products, such as cosmetics (e.g., antiperspirants, deodorants, facial makeup, decorative makeup, toothpastes, shampoos, soaps, skin conditioners, skin moisturizers, and sunscreens);

25

pharmaceuticals, such as topical medicinal compositions (e.g., anti-fungal compositions, anti-bacterial compositions, anesthetics, anti-inflammatory compositions, pain-relief ointments, and rash/itch/irritation ointments) and internal medicinal compositions (e.g., pills, tablets, capsules, powders, and solutions);

dental articles, such as fillings, crowns, inlays, veneer, prosthesis, sealants, implants, dentures, bridges, bonding agents, and impression patterns; and

30

packaging materials, such as packaging films (e.g., shrink films, stretch films, and food packaging films), bottles, trays, and containers.

A packaging film may comprise one or more layers comprising any of the dispersed-particle compositions discussed above. The film may have any total thickness as

long as it provides the desired properties (e.g., free shrink, shrink tension, flexibility, Young's modulus, optics, strength, barrier) for the given application of expected use. The film may have a thickness of less than about any of the following: 20 mils, 10 mils, 5 mils, 4 mils, 3 mils, 2 mils, 1.5 mils, 1.2 mils, and 1 mil. The film may also have a thickness of at least
5 about any of the following: 0.25 mils, 0.3 mils, 0.35 mils, 0.4 mils, 0.45 mils, 0.5 mils, 0.6 mils, 0.75 mils, 0.8 mils, 0.9 mils, 1 mil, 1.2 mils, 1.4 mils, 1.5 mils, 2 mils, 3 mils, and 5 mils.

The film may be monolayer or multilayer. The film may comprise at least any of the following number of layers: 1, 2, 3, 4, 5, 6, 7, 8, and 9. The film may comprise at most
10 any of the following number of layers: 20, 15, 10, 9, 7, 5, 3, 2, and 1. The term "layer" refers to a discrete film component which is coextensive with the film and has a substantially uniform composition. Any of the layers of the film may have a thickness of at least about any of the following: 0.05, 0.1, 0.2, 0.5, 1, 2, and 3 mil. Any of the layers of the film may have a thickness of at most about any of the following: 20, 10, 5, 2, 1, and 0.5 mils. Any of the layers
15 of the film may have a thickness as a percentage of the total thickness of the film of at least about any of the following values: 1, 3, 5, 7, 10, 15, 20, 30, 40, 50, 60, 70, 80, and 90 %. Any of the layers of the film may have a thickness as a percentage of the total thickness of the film of at most about any of the following values: 90, 80, 50, 40, 35, 30, 25, 20, 15, 10, and 5 %.

A layer of the film may comprise at least about and/or at most about any of the
20 following amounts of dispersed-particle composition based on the layer weight: 0.1, 0.5, 1, 3, 5, 10, 20, 50, 60, 70, 80, 90, 95, 99, and 100 weight %. A layer of the film comprising any of the foregoing amounts of dispersed-particle composition may also have a thickness of at least about, and/or at most about, any of the following percentages based on the total thickness of the film: 90, 80, 70, 60, 50, 40, 30, 20, 15, 10, and 5%.

25 A layer comprising the dispersed-particle composition may be an outer layer of the film. An outer layer may be an "outside layer" of the film (i.e., an outer layer adapted or designed to face to the outside of a package incorporating the film) or an "inside layer" of the film (i.e., an outer layer adapted or designed to face the inside of a package incorporating the film). If the film comprises only one layer, then the one layer may be considered an
30 "outer layer." A layer comprising the dispersed-particle composition may be an inner or interior layer of the film. An inner or interior layer of the film is between two outer layers of the film.

For example, an internal tie layer of a film, such as disclosed in U.S. Patent Application Serial No. 10/452892 filed June 2, 2003 by Grah et al, which is incorporated herein in its entirety by reference, may comprise the dispersed-particle composition discussed above.

5 The film comprising the dispersed-particle composition may be formed into a package (e.g., bag or casing) for packaging (e.g., enclosing) an object such as a food product (e.g., coffee, nuts, snack foods, cheese, ground or processed meat products, fresh red meat products, and more specifically, meats such as poultry, pork, beef, sausage, lamb, goat, horse, and fish).

10 The package may be formed by sealing the film to itself, or by sealing the film to a support member (e.g., a tray, cup, or tub), which supports the product (e.g., a food product) that may be disposed on or in the support member. Seals may be made by adhesive or heat sealing, such as bar, impulse, radio frequency ("RF") or dielectric sealing. Suitable package configurations include end-seal bag, side-seal bag, L-seal bag, pouch, and seamed casing 15 (e.g., back-seamed tubes by forming an overlap or fin-type seal). Such configurations are known to those of skill in the art. The support member (e.g., tray) may also comprise any of the dispersed-particle compositions discussed above. The support member may also comprise a thermoformed web comprising a thermoplastic.

The package may also be formed by laminating or sealing the film comprising 20 the dispersed-particle composition to another substrate. Suitable substrates may comprise: 1) a film comprising one or more of the following materials: polyester (e.g., PET), metalized polyester (e.g., metalized PET), PVdC-coated PET, polypropylene (e.g., biaxially oriented polypropylene or BOPP), metalized BOPP, PVdC, and coated BOPP, 2) paper, 3) paperboard, and 4) metal foil. A composite packaging structure may also be formed by extrusion coating of 25 one or more polymer layers, any or all of which may comprise the dispersed-particle composition, to any of the above substrates.

Also by way of example, once a film comprising the dispersed-particle composition has been placed in a tube or casing configuration, one end of the tube may be closed by tying, clipping (e.g., metal clips), or sealing. The tube may then be filled through the 30 remaining open end with an uncooked food product (e.g., a sausage emulsion or another flowable meat product). The remaining open end may then be closed by tying, clipping, or sealing to form a package enclosing a food product. This filling procedure may take place, for

example, by vertical form-fill-seal or horizontal form-fill-seal processes known to those of skill in the art.

5 The packaged food product enclosed within the package comprising the film comprising the dispersed-particle composition may be processed (e.g., cooked, retorted, or pasteurized) for example, by immersing the packaged food in a liquid hot water bath, exposing the packaged food to steam, or exposing the packaged food to hot air, for an effective amount of time and at an effective temperature and pressure. This exposure may also shrink the package tightly about the enclosed food product by heat shrinking the film. The packaged food may also be exposed to an amount of radiation such as microwave radiation effective to cook the 10 packaged food. After the food product has been processed (e.g., cooked or retorted) to a desired level, the packaged food may be sold in the packaged form, or the package may be stripped from the cooked food so the food may be processed further or consumed.

A film comprising the dispersed-particle composition may be manufactured by thermoplastic film-forming processes known in the art. The film may be prepared by 15 extrusion or coextrusion utilizing, for example, a tubular trapped bubble film process or a flat film (i.e., cast film or slit die) process. The film may also be prepared by extrusion coating. Alternatively, the film may be prepared by adhesively or extrusion laminating the various layers. These processes are known to those of skill in the art. A combination of these processes may also be employed.

20 A film comprising the dispersed-particle composition may be non-oriented. Alternatively, a film comprising the dispersed-particle composition may be oriented in either the machine (i.e., longitudinal), the transverse direction, or in both directions (i.e., biaxially oriented), in order to reduce the permeability and/or to enhance the strength, optics, and durability of the film. The orientation of the film may also enhance the orientation of the 25 silicate platelets of the dispersed-particle composition, so that generally the major plane through the platelets is substantially parallel to the major plane through the film. The film may be oriented in at least one direction by at least about any of the following ratios: 2.5:1, 3:1, 3.5:1, and 3.7:1; and/or by at most about 10:1.

30 A film comprising the dispersed-particle composition may be non-heat shrinkable – for example, having a free shrink in any direction at 185°F (85°C) of less than about any of the following: 4%, 3%, 1%, and 0.5%. A film comprising the dispersed-particle composition may be heat shrinkable (i.e., has a shrink characteristic), which as used herein,

means that the film has a free shrink at 185°F (85°C) in at least one direction of at least about 5% at 185°F. For example, the film comprising the dispersed-particle composition may have a free shrink at 185°F (85°C) in either of the machine or transverse directions (or both directions) of at least about, and/or at most about, any of the following: 7%, 10%, 15%, 25%, 30%, 40%,
5 45%, 50%, 55%, 60%, 70%, and 80%. Further, the film may have any of the preceding free shrink values measured at a temperature selected from any of 200°F, 220°F, 240°F, 260°F, and 280°F.

The film may have unequal free shrink in both directions, that is differing free shrink in the machine and transverse directions. For example, the film may have a free shrink
10 (185°F) in the machine direction of at least 40% and a free shrink (185°F) in the transverse direction of at least 25%. The film may not have a heat shrink characteristic in both directions. For example, the film may have a free shrink at 185°F in one direction of less than about any of the following: 5%, 4%, 3%, 2% and 1%; or the film may have 0% free shrink at 185°F in one direction. The free shrink of the film is determined by measuring the percent dimensional
15 change in a 10 cm x 10 cm film specimen when subjected to selected heat (i.e., at a specified temperature exposure) according to ASTM D 2732, which is incorporated herein in its entirety by reference. All references to free shrink in this application are measured according to this standard.

As is known in the art, a heat-shrinkable film shrinks upon the application of heat
20 while the film is in an unrestrained state. If the film is restrained from shrinking to some extent - - for example by a packaged product around which the film shrinks -- then the tension of the heat-shrinkable film increases upon the application of heat. Accordingly, a heat-shrinkable film that has been exposed to heat so that at least a portion of the film is either reduced in size (unrestrained) or under increased tension (restrained) is considered a heat-shrunk (i.e., heat-
25 contracted) film.

A film comprising the dispersed-particle composition may exhibit a shrink tension at 185°F in at least one direction of at least about, and/or at most about, any of the following: 100 psi, 150 psi, 175 psi, 200 psi, 225 psi, 250 psi, 275 psi, 300 psi, 325 psi, 350 psi, 400 psi, 450 psi, 500 psi, 550 psi, and 600 psi. Further, the film may have any of the
30 preceding shrink tensions measured at a temperature selected from any of 200°F, 220°F, 240°F, 260°F, and 280°F. The film may have unequal shrink tension in both directions, that is,

differing shrink tension in the machine and transverse directions. The film may not have a shrink tension in one or both directions. Shrink tension is measured at a specified temperature (e.g., 185°F) in accordance with ASTM D 2838 (Procedure A), which is incorporated herein in its entirety by reference. All references to shrink tension in this application are by this
5 standard.

A film comprising the dispersed-particle composition may be annealed or heat-set to reduce the free shrink slightly, substantially, or completely; or the film may not be heat set or annealed once the oriented film has been quenched in order that the film will have a high
10 level of heat shrinkability.

10

Appearance Characteristics

A film comprising the dispersed-particle composition may have low haze characteristics. Haze is a measurement of the transmitted light scattered more than 2.5° from the axis of the incident light. Haze is measured against the outside layer of the film. As
15 previously discussed, the "outside layer" is the outer layer of the film that will be adjacent the area outside of the package comprising the film. Haze is measured according to the method of ASTM D 1003, which is incorporated herein in its entirety by reference. All references to "haze" values in this application are by this standard. The haze of the film may be no more than about any of the following values: 30%, 25%, 20%, 15%, 10%, 8%, 5%, and 3%.

20 A film comprising the dispersed-particle composition may have a gloss, as measured against the outside layer of at least about any of the following values: 40%, 50%, 60%, 63%, 65%, 70%, 75%, 80%, 85%, 90%, and 95%. These percentages represent the ratio of light reflected from the sample to the original amount of light striking the sample at the designated angle. All references to "gloss" values in this application are in accordance
25 with ASTM D 2457 (60° angle), which is incorporated herein in its entirety by reference.

A film comprising the dispersed-particle composition may be transparent (at least in the non-printed regions) so that a packaged article may be visible through the film. "Transparent" means that the film transmits incident light with negligible scattering and little

absorption, enabling objects (e.g., the packaged article or print) to be seen clearly through the film under typical viewing conditions (i.e., the expected use conditions of the material). The transparency (i.e., clarity) of the film may be at least about any of the following values: 65%, 70%, 75%, 80%, 85%, and 90%, as measured in accordance with ASTM D1746.

5 The measurement of optical properties of plastic films, including the measurement of total transmission, haze, clarity, and gloss, is discussed in detail in Pike, LeRoy, "Optical Properties of Packaging Materials," Journal of Plastic Film & Sheeting, vol. 9, no. 3, pp. 173-80 (July 1993), of which pages 173-80 is incorporated herein by reference.

10 Any numerical value ranges recited herein include all values from the lower value to the upper value in increments of one unit provided that there is a separation of at least 2 units between any lower value and any higher value. As an example, if it is stated that the amount of a component or a value of a process variable (e.g., temperature, pressure, time) may range from any of 1 to 90, 20 to 80, or 30 to 70, or be any of at least 1, 20, or 30 and/or at most 90, 80, or 70, then it is intended that values such as 15 to 85, 22 to 68, 43 to 51, and 15 30 to 32, as well as at least 15, at least 22, and at most 32, are expressly enumerated in this specification. For values that are less than one, one unit is considered to be 0.0001, 0.001, 0.01 or 0.1 as appropriate. These are only examples of what is specifically intended and all possible combinations of numerical values between the lowest value and the highest value enumerated are to be considered to be expressly stated in this application in a similar manner.

20 The above descriptions are those of various aspects and embodiments of the invention. Various alterations and changes can be made without departing from the spirit and broader aspects of the invention as defined in the claims, which are to be interpreted in accordance with the principles of patent law, including the doctrine of equivalents. Except in the claims and the specific examples, or where otherwise expressly indicated, all numerical 25 quantities in this description indicating amounts of material, reaction conditions, use conditions, molecular weights, and/or number of carbon atoms, and the like, are to be understood as modified by the word "about" in describing the broadest scope of the invention. Any reference to an item in the disclosure or to an element in the claim in the

singular using the articles "a," "an," "the," or "said" is not to be construed as limiting the item or element to the singular unless expressly so stated. The definitions and disclosures set forth in the present Application control over any inconsistent definitions and disclosures that may exist in an incorporated reference. All references to ASTM tests are to the most recent, 5 currently approved, and published version of the ASTM test identified, as of the priority filing date of this application. Each such published ASTM test method is incorporated herein in its entirety by this reference.

CLAIMS

What is claimed is:

1. An intercalated layered silicate comprising:
5 a layered silicate comprising a plurality of silicate layers; and
an intercalating agent sorbed between the silicate layers in an amount effective to provide an average interlayer spacing between the silicate layers of at least about 20Å, wherein the intercalating agent is selected from one or more of ethoxylated fatty esters of sorbitan and fatty acid esters of polyglycerol.
- 10 2. The intercalated layered silicate of claim 1 wherein the intercalating agent comprises one or more ethoxylated fatty esters of sorbitan.
3. The intercalated layered silicate of claim 1 wherein the intercalating agent comprises
15 one or more ethoxylated fatty esters of sorbitan selected from one or more of ethoxylated sorbitan monostearate, ethoxylated sorbitan monolaurate, ethoxylated sorbitan monooleate, and ethoxylated sorbitan monopalmitate.
4. The intercalated layered silicate of claim 1 wherein the intercalating agent comprises
20 one or more fatty acid esters of polyglycerol.
5. The intercalated layered silicate of claim 1 wherein the intercalating agent comprises one or more fatty acid esters of polyglycerol selected from one or more of polyglycerol-3 stearate, polyglycerol-6 stearate, and polyglycerol-10 stearate.
25
6. The intercalated layered silicate of any of the preceding claims wherein the intercalated layered silicate is essentially free of an intercalating agent comprising an ammonium compound.
- 30 7. The intercalated layered silicate of any of the preceding claims wherein the intercalated layered silicate is essentially free of an intercalating agent comprising onium functionality.

8. The intercalated layered silicate of any of the preceding claims wherein the amount of sorbed intercalating agent is at least about 5 weight parts per 100 weight parts layered silicate.

5 9. The intercalated layered silicate of any of the preceding claims wherein the average interlayer spacing between the silicate layers is at least about 30Å.

10. The intercalated layered silicate of any of the preceding claims wherein the layered silicate is a bentonite clay.

10

11. The intercalated layered silicate of any of the preceding claims having a peak degradation temperature of at least about 360°C.

12. A method of exfoliating a layered silicate comprising:

15 mixing from about 0.1 to about 100 weight parts of the intercalated layered silicate of any of the preceding claims with 100 weight parts of a matrix medium to form a mixture; and adding sufficient energy to the mixture to form a dispersed-particle composition comprising at least about 0.1 weight parts exfoliated particles per 100 weight parts matrix medium.

20

13. The method of claim 12 wherein the exfoliated particles have an average dimension in the shortest dimension of at most about 100 nm.

25 14. The method of any of claims 12 to 13 wherein the matrix medium comprises one or more polymers selected from polyolefin, ethylene/vinyl alcohol copolymer, ionomer, vinyl plastic, polyamide, polyester, and polystyrene.

15. The method of any of claims 12 to 13 wherein the matrix medium comprises one or more energy curable polymer precursors.

30

16. The method of any of claims 12 to 13 wherein the matrix medium comprises one or more materials selected from coating solvents, coating binders, and coating resins.

17. The method of any of claims 12 to 13 wherein the matrix medium comprises one or more materials selected from ink solvents and ink resins.
- 5 18. The method of any of claims 12 to 13 wherein the matrix medium comprises one or more materials selected from grease lubricating oils and grease gelling agents.
19. The method of any of claims 12 to 13 wherein the matrix medium comprises one or more materials selected from cosmetic lipids, cosmetic emollients, cosmetic humectants,
10 cosmetic film formers, cosmetic binders, cosmetic surfactants, and cosmetic solvents.
20. The method of any of claims 12 to 13 wherein the matrix medium comprises one or more pharmaceutical excipients.
- 15 21. The method of any of claims 12 to 13 wherein the matrix medium comprises an emulsion selected from an oil-in-water emulsion and a water-in-oil emulsion.
22. The method of any of claims 12 to 13 comprising mixing from about 1 to about 10 weight parts of the intercalated layered silicate with 100 weight parts of a matrix medium.
20
23. The method of any of claims 12 to 13 comprising adding sufficient energy to the mixture to form a dispersed-particle composition comprising at least about 1 weight parts exfoliated particles per 100 weight parts matrix medium.
- 25 24. A dispersed-particle composition comprising:
at least about 50 weight % of a matrix medium; and
from at least about 0.1 to at most about 50 weight % of particles dispersed in the matrix medium, the particles having an average size in the shortest dimension of at most about 100 nm, the particles comprising:
30 silicate platelets; and

an intercalating agent sorbed to the silicate platelets, wherein the intercalating agent is selected from one or more of ethoxylated fatty esters of sorbitan and fatty acid esters of polyglycerol.

5 25. The dispersed-particle composition of claim 24 wherein the matrix medium comprises one or more polymers selected from polyolefin, ethylene/vinyl alcohol copolymer, ionomer, vinyl plastic, polyamide, polyester, and polystyrene.

10 26. The dispersed-particle composition of claim 24 wherein the matrix medium comprises one or more energy curable polymer precursors.

27. A packaged food comprising:
a package comprising the dispersed-particle composition of any of claims 24 to 26;
and
15 a food enclosed in the package.

28. A packaging film comprising the dispersed-particle composition of any of claims 24 to 25, wherein the matrix medium comprises one or more polymers, wherein the one or more polymers are thermoplastic.
20

29. A method of packaging a food comprising:
enclosing a food in a package comprising the packaging film of claim 28.

25 30. A method of exfoliating a layered silicate comprising:
mixing from about 0.1 to about 100 weight parts of an intercalated layered silicate with 100 weight parts of a matrix medium to form a mixture, wherein:
the intercalated layered silicate comprises:
a layered silicate comprising a plurality of silicate layers; and
an intercalating agent sorbed between the silicate layers in an amount effective
30 to provide an average interlayer spacing between the silicate layers of at least about 20Å, wherein the intercalating agent is selected from one or more of fatty acid esters

of sorbitan, fatty acid esters of glycerol, fatty acid amide waxes, variants of amide waxes, and variants of amides; and

the matrix medium comprises one or more materials selected from:

polymer selected from one or more of ethylene/vinyl alcohol

5 copolymer, ionomer, vinyl plastic, polyamide, polyester, and polystyrene;

energy curable polymer precursors;

coating solvents, coating binders, and coating resins;

ink solvents and ink resins;

grease lubricating oils and grease gelling agents;

10 cosmetic lipids, cosmetic emollients, cosmetic humectants, cosmetic film formers, cosmetic binders, cosmetic surfactants, and cosmetic solvents;

pharmaceutical excipients;

emulsions selected from an oil-in-water emulsion and a water-in-oil

emulsion; and

15 adding sufficient energy to the mixture to form a dispersed-particle composition comprising at least about 0.1 weight parts exfoliated particles per 100 weight parts matrix medium.

20 31. The method of claim 30 wherein the exfoliated particles have an average dimension in the shortest dimension of at most about 100 nm.

32. The method of any of claims 30 to 31 wherein the matrix medium comprises one or more polymers selected from ethylene/vinyl alcohol copolymer, ionomer, vinyl plastic, polyamide, polyester, and polystyrene.

25 33. The method of any of claims 30 to 31 wherein the matrix medium comprises one or more energy curable polymer precursors.

30 34. The method of any of claims 30 to 31 wherein the matrix medium comprises one or more materials selected from coating solvents, coating binders, and coating resins.

35. The method of any of claims 30 to 31 wherein the matrix medium comprises one or more materials selected from ink solvents and ink resins.

5 36. The method of any of claims 30 to 31 wherein the matrix medium comprises one or more materials selected from grease lubricating oils and grease gelling agents.

37. The method of any of claims 30 to 31 wherein the matrix medium comprises one or more materials selected from cosmetic lipids, cosmetic emollients, cosmetic humectants, cosmetic film formers, cosmetic binders, cosmetic surfactants, and cosmetic solvents.

10 38. The method of any of claims 30 to 31 wherein the matrix medium comprises one or more pharmaceutical excipients.

15 39. The method of any of claims 30 to 31 wherein the matrix medium comprises an emulsion selected from an oil-in-water emulsion and a water-in-oil emulsion.

40. The method of any of claims 30 to 39 comprising mixing from about 1 to about 10 weight parts of the intercalated layered silicate with 100 weight parts of the matrix medium.

20 41. The method of any of claims 30 to 40 comprising adding sufficient energy to the mixture to form a dispersed-particle composition comprising at least about 1 weight parts exfoliated particles per 100 weight parts matrix medium.

25 42. A dispersed-particle composition comprising:
at least about 50 weight % of a matrix medium comprising one or more materials selected from:

polymer selected from one or more of ethylene/vinyl alcohol copolymer, ionomer, vinyl plastic, polyamide, polyester, and polystyrene;
energy curable polymer precursors;
30 coating solvents, coating binders, and coating resins;
ink solvents and ink resins;
grease lubricating oils and grease gelling agents;

cosmetic lipids, cosmetic emollients, cosmetic humectants, cosmetic film formers, cosmetic binders, cosmetic surfactants, and cosmetic solvents; pharmaceutical excipients; and emulsions selected from an oil-in-water emulsion and a water-in-oil emulsion;

5

and

from at least about 0.1 to at most about 50 weight % of particles dispersed in the matrix medium, the particles having an average size in the shortest dimension of at most about 100 nm, the particles comprising:

silicate platelets; and

10

an intercalating agent sorbed to the silicate platelets, wherein the intercalating agent is selected from one or more of fatty acid esters of sorbitan, fatty acid esters of glycerol, fatty acid amide waxes, variants of amide waxes, and variants of amides.

15 43. The dispersed-particle composition of claim 42 wherein the matrix medium comprises one or more polymers selected from ethylene/vinyl alcohol copolymer, ionomer, vinyl plastic, polyamide, polyester, and polystyrene.

44. The dispersed-particle composition of claim 42 wherein the matrix medium comprises ethylene/vinyl alcohol copolymer.

20

45. The dispersed-particle composition of claim 42 wherein the matrix medium comprises ionomer.

25 46. The dispersed-particle composition of claim 42 wherein the matrix medium comprises vinyl plastic.

47. The dispersed-particle composition of claim 42 wherein the matrix medium comprises vinyl plastic.

30 48. The dispersed-particle composition of claim 42 wherein the matrix medium comprises polyamide.

49. The dispersed-particle composition of claim 42 wherein the matrix medium comprises polyester.
50. The dispersed-particle composition of claim 42 wherein the matrix medium comprises
5 polystyrene.
51. The dispersed-particle composition of claim 42 wherein the matrix medium comprises one or more energy curable polymer precursors.
- 10 52. The dispersed-particle composition of any of claims 42-51 wherein the intercalating agent comprises fatty acid esters of sorbitan.
53. The dispersed-particle composition of any of claims 42-51 wherein the intercalating agent comprises fatty acid esters of glycerol.
- 15 54. The dispersed-particle composition of any of claims 42-51 wherein the intercalating agent comprises fatty acid amide waxes.
55. The dispersed-particle composition of any of claims 42-51 wherein the intercalating
20 agent comprises variants of amide waxes.
55. The dispersed-particle composition of any of claims 42-51 wherein the intercalating agent comprises variants of amides.
- 25 56. The dispersed-particle composition of any of claims 42-51 wherein the intercalating agent comprises one or more fatty acid esters of sorbitan selected from one or more of sorbitan monostearate, sorbitan tristearate, sorbitan monolaurate, sorbitan monopalmitate, sorbitan monooleate, and sorbitan trioleate.
- 30 57. The dispersed-particle composition of any of claims 42-51 wherein the intercalating agent comprises one or more fatty acid esters of glycerol selected from one or more of glycerol monostearate, glycerol distearate, glycerol palmitate, glycerol oleate, glycerol

dioleate, glycerol dipalmitate, glycerol monolaurate, glycerol dilaurate, glycerol monomyristate, glycerol monobehenate, glycerol monohydroxystearate, glycerol dihydroxystearate, glycerol monoricinoleate, and glycerol diricinoleate.

- 5 58. The dispersed-particle composition of any of claims 42-51 wherein the intercalating agent comprises one or more fatty acid amide waxes selected from one or more of lauric diethanol amide, myristic diethanol amide, oleic diethanol amide, palmitic diethanol amide, stearic diethanol amide, and behenic diethanol amide.
- 10 59. The dispersed-particle composition of any of claims 42-51 wherein the intercalating agent comprises one or more variants of amide waxes selected from one or more of N,N' ethylene bis-stearamide, ethylene bis-oleamide, N-(2-hydroxyethyl)-12-hydroxystearamide, and N,N'-ethylene-bis(12-hydroxystearamide).
- 15 60. The dispersed-particle composition of any of claims 42-51 wherein the intercalating agent comprises one or more variants of amides selected from one or more of oleyl palmityl amide, stearyl erucamide, and stearyl stearamide.
- 20 61. The dispersed-particle composition of any of claims 42-60 wherein the dispersed-particle composition is essentially free of an intercalating agent comprising an ammonium compound.
62. The dispersed-particle composition of any of claims 42-60 wherein the dispersed-particle composition is essentially free of an intercalating agent comprising onium
- 25 functionality.
63. A packaged food comprising:
a package comprising the dispersed-particle composition of any of claims 43 to 62;
and
30 a food enclosed in the package.
64. A packaging film comprising the dispersed-particle composition of any of claims 43 to 62.

65. A method of packaging a food comprising:
enclosing a food in a package comprising the packaging film of claim 64.

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2006/031839

A. CLASSIFICATION OF SUBJECT MATTER
INV. C08K5/10 C01B33/44

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
C08K C01B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)
EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2003/232912 A1 (ROSENTHAL JAY S [US] ET AL) 18 December 2003 (2003-12-18) paragraphs [0012], [0014], [0027], [0037], [0049] claims 1,6-9	1
A	US 2004/223990 A1 (MONDET JEAN [FR] ET AL) 11 November 2004 (2004-11-11) paragraphs [0054], [0062], [0067] claim 32	1

Further documents are listed in the continuation of Box C.

See patent family annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

Date of mailing of the international search report

5 December 2006

12/12/2006

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Von Kuzenko, Michael

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No PCT/US2006/031839

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 2003232912 A1	18-12-2003	AU 2003238617 A1 BR 0305093 A CA 2456954 A1 EP 1511798 A2 WO 03106549 A2 JP 2005530002 T	31-12-2003 21-09-2004 24-12-2003 09-03-2005 24-12-2003 06-10-2005
US 2004223990 A1	11-11-2004	NONE	