



(86) Date de dépôt PCT/PCT Filing Date: 2001/10/01  
 (87) Date publication PCT/PCT Publication Date: 2002/04/11  
 (85) Entrée phase nationale/National Entry: 2003/04/01  
 (86) N° demande PCT/PCT Application No.: SE 2001/002120  
 (87) N° publication PCT/PCT Publication No.: 2002/028665  
 (30) Priorité/Priority: 2000/10/03 (0003550-1) SE

(51) Cl.Int.<sup>7</sup>/Int.Cl.<sup>7</sup> B44C 5/04, B32B 31/20, B29C 59/02  
 (71) Demandeur/Applicant:  
PERGO AB, SE  
 (72) Inventeurs/Inventors:  
NILSSON, MAGNUS N., SE;  
OHLSSON, LARS, SE;  
CHRISTIANSSON, MADGALENA, SE;  
HANSSON, KRISTER, SE;  
ERICSSON, JAN, SE  
 (74) Agent: FETHERSTONHAUGH & CO.

(54) Titre : PROCEDE DE FABRICATION D'ELEMENTS DE SURFACE  
 (54) Title: A PROCESS FOR THE MANUFACTURE OF SURFACE ELEMENTS

(57) **Abrégé/Abstract:**

A process for the manufacture of a decorative surface element, which element comprises a base layer, a decor and a wear layer of a UV or electron beam curing lacquer. One or more structured surfaces, forming embossing surfaces of one or more rollers or moulds, are positioned on top of the decorative lacquered surface, possibly after having cured the lacquer to a desired viscosity, and are continuously or discontinuously pressed on to this. The lacquer will be provided with a surface structure which enhances the decorative effect of the decor. The wear layer is then completely cured.

## (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
11 April 2002 (11.04.2002)

PCT

(10) International Publication Number  
**WO 02/28665 A1**

- (51) International Patent Classification<sup>7</sup>: **B44C 5/04**, B29C 59/02, B32B 31/20 (74) Agent: **STENBERG, Yngve**; c/o Perstorp AB, S-284 80 Perstorp (SE).
- (21) International Application Number: PCT/SE01/02120 (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.
- (22) International Filing Date: 1 October 2001 (01.10.2001)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
0003550-1 3 October 2000 (03.10.2000) SE (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (71) Applicant: **PERGO AB** [SE/SE]; Strandridaregatan 8, S-231 25 Trelleborg (SE).
- (72) Inventors: **NILSSON, Magnus, N.**; Järnvägsgatan 19, S-231 44 Trelleborg (SE). **OHLSSON, Lars**; Brors Lundsv. 37A, S-236 34 Höllviken (SE). **CHRISTIANS-SON, Madgalena**; Frans Malmrosq. 38B, S-231 54 Trelleborg (SE). **HANSSON, Krister**; Frans Malmros-gatan 56, S-231 54 Trelleborg (SE). **ERICSSON, Jan**; Röamöllagatan 83, S-254 43 Helsingborg (SE).

**Published:**

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



**WO 02/28665 A1**

(54) Title: A PROCESS FOR THE MANUFACTURE OF SURFACE ELEMENTS

(57) Abstract: A process for the manufacture of a decorative surface element, which element comprises a base layer, a decor and a wear layer of a UV or electron beam curing lacquer. One or more structured surfaces, forming embossing surfaces of one or more rollers or moulds, are positioned on top of the decorative lacquered surface, possibly after having cured the lacquer to a desired viscosity, and are continuously or discontinuously pressed on to this. The lacquer will be provided with a surface structure which enhances the decorative effect of the decor. The wear layer is then completely cured.

**A process for the manufacturing of surface elements.**

The present invention relates to a process for the manufacture of decorative surface elements with a surface structure matching the decor of the upper surface.

Products coated with simulated versions of materials such as wood and marble are frequent today. They are foremost used where a less expensive material is desired, but also where resistance towards abrasion, indentation and different chemicals and moisture is required. As an example of such products floors, floor beadings, table tops, work tops and wall panels can be mentioned.

As an example of an existing product can be mentioned the thermosetting laminate which mostly consists of a number of base sheets with a decor sheet placed closest to the surface. The decor sheet can be provided with a desired decor or pattern. Frequently used patterns usually represent the image of different kinds of wood or minerals such as marble or granite. The surface of the laminate can, at the laminating procedure, be provided with a structure, which will make the decor more realistic. Press plates with structure or structure foils are here frequently used during the pressing of the laminate. A negative reproduction of the structure in the press plate or the foil will be embossed into the laminate surface during the laminating procedure.

The structure suitably represents features characteristic for the pattern the decor represents. The structure can be made coarse to simulate for example rough planed stone, or smooth with randomly placed pits and micro cracks to simulate polished marble. When the surface of wood is simulated the surface is provided with randomly placed thin oblong indentations which imitate pores.

It has for a long time been a great need to be able to manufacture simulated materials where a lacquer is used as a top coat on a decor. The only way, so far, to achieve a surface structure in lacquer is casting or abrasive moulding which both are time consuming and expensive processes.

According to the present invention the above mentioned needs have been met and a surface element with a decorative surface with a surface structure has been achieved. The invention relates to a process for the manufacture of a decorative surface element. The element comprises a base layer, a decor and a wear layer of a UV or electron beam curing lacquer. The invention is characterised in that one or more structured surfaces forming embossing surfaces of or more rollers or moulds are positioned on top of the decorative lacquered surface, possibly after having cured the lacquer to a desired viscosity, and are continuously or discontinuously pressed on to this. The lacquer will hereby be provided with a surface structure which enhances the decorative effect of the decor. The wear layer is then completely cured. The lacquer preferably consists of a UV-curing or electron beam curing acrylic or maleimide lacquer. The wear layer is preferably applied in several steps with intermediate partial curing. The wear layer preferably also includes hard particles with an average particle size in the range 50nm - 150µm. The base layer may suitably consist of a particle board or a fibre board but may also be made of a material which mainly consist of a polymer such as polyurethane.

In order to make the structuring process run smoother, the surface element preferably contains a layer which is elastic at least before the complete curing. The elastic layer is selected from the group consisting of; the base layer, a primer layer, the decor layer and the wear layer.

The structuring process will most often result in undesirable raised sections in the surface. These sections can be planed out by pressing one or more glazing rollers towards the surface structured wear layer before the complete curing stage.

The structured rollers are preferably heated to a surface temperature above 40°C, preferably in the range 50°C - 150°C. This will minimise the risk for forming of cracks. The glazing rollers are preferably also heated to a surface temperature above 30°C, preferably in the range 35°C - 100°C for the same reason.

According to an alternative embodiment of the invention the structuring is achieved by means of a mould. The structured surface of the mould is heated to a surface temperature above 40°C, preferably in the range 50°C - 150°C. The

pressure exercised by the structured mould surface is 50 - 200 Bar, preferably 65 - 100 Bar.

The glazing process will result in a surface which is easier to clean. It is also possible to achieve such a surface by applying a thin top coat on top of the structured wear layer. Such a thin top coat may of course be applied on top of the structured wear layer after the glazing stage as well. A thin top coat may advantageously also be applied on top of the structured wear layer before the glazing stage. The top coat is then partially cured before the glazing. The top coat is suitably comprised of acrylic, epoxy or maleimide lacquer and does possibly have an additive in the form of hard particles with an average particle size in the range 50nm - 10 $\mu$ m.

Each structured roller is provided with a counter stay roller between which the surface element is passed. Each glazing roller is preferably also provided with a counter stay roller between which the surface element is passed. The surface element has a thickness T and the distance between each structured roller and corresponding counter stay is preferably set in the range T minus 0.5mm to 1.2mm, preferably 0.7mm - 0.9mm. The pressure between each structured roller and its corresponding counter stay is then 50 - 200 Bar, preferably 65 - 100 Bar.

The surface element has a thickness T and that the distance between each glazing roller and corresponding counter stay is set in the range T minus 0.7mm - 1.2mm, preferably 0.7mm - 0.9mm. The pressure between each glazing roller and its corresponding counter stay is suitably in the range 0.1 - 10 Bar, preferably 0.5 - 5 Bar.

The hard particles added to the lacquer consists of for example silicon oxide,  $\alpha$ -aluminium oxide or silicon carbide. According to one embodiment of the invention the main part of the hard particles consists of for example silicon oxide,  $\alpha$ -aluminium oxide or silicon carbide while a smaller amount of the hard particles consist of diamond. The hard particles consisting of diamond is then in the average particle size range 50nm - 2 $\mu$ m and is placed close to the upper surface of the wear layer.

The rollers may, when more than one structured roller is used, be provided with different surface structures. This will make it possible to achieve a surface structure with a variation that corresponds to the visible decor.

AMENDED SHEET

## CLAIMS

1. A process for the manufacture of a decorative surface element, which element comprises a base layer, a decor and a wear layer of a UV or electron beam curing lacquer and hard particles with an average particle size in the range 50nm - 150µm, characterised in that one or more structured surfaces, forming embossing surfaces of one or more rollers or moulds, which are heated to a surface temperature above 40°C, preferably in the range 50°C - 150°C are positioned on top of the decorative lacquered surface, possibly after having cured the lacquer to a desired viscosity, and are continuously or discontinuously pressed on to this with a pressure of 50 - 200 Bar, preferably 65 - 100 Bar, whereby the lacquer will be provided with a surface structure which enhances the decorative effect of the decor, whereupon the wear layer is completely cured.
2. A process according to claim 1, characterised in that the lacquer consists of an acrylic, epoxy or a maleimide lacquer.
3. A process according to claim 1 or 2, characterised in that the wear layer is applied in several steps with intermediate partial curing.
4. A process according to claim 1, characterised in that the base layer consists of a particle board or a fibre board.
5. A process according to claim 1, characterised in that the base layer consists mainly of a polymer such as polyurethane.
6. A process according to any of the claims 1 - 5, characterised in that the surface element contains a layer which is elastic at least before the complete curing, the elastic layer being selected from the group; the base layer, a primer layer, the decor layer and the wear layer.
7. A process according to any of the claims 1 - 6, characterised in that one or more glazing rollers is pressed towards the surface structured wear layer before the complete curing stage.

8. A process according to any of the claims 7, characterised in that the glazing rollers are heated to a surface temperature above 30°C, preferably in the range 35°C - 100°C.
9. A process according to any of the claims 1 - 6 or 8, characterised in that a thin top coat is applied on top of the structured wear layer.
10. A process according to any of the claims 7 or 8, characterised in that a thin top coat is applied on top of the structured wear layer after the glazing stage.
11. A process according to any of the claims 7 or 8, characterised in that a thin top coat is applied on top of the structured wear layer before the glazing stage and that the top coat is partially cured before the glazing.
12. A process according to any of the claims 9 - 11, characterised in that the top coat is comprised of acrylic, epoxy or maleimide lacquer and possibly an additive in the form of hard particles with an average particle size in the range 50nm - 10µm.
13. A process according to any of the claims 1 - 12, characterised in that each structured roller is provided with a counter stay roller between which the surface element is passed.
14. A process according to any of the claims 7 - 13, characterised in that each glazing roller is provided with a counter stay roller between which the surface element is passed.
15. A process according to claim 13, characterised in that the surface element has a thickness T and that the distance between each structured roller and corresponding counter stay is set in the range T minus 0.5mm - 1.2mm, preferably 0.7mm - 0.9mm.
16. A process according to claim 14, characterised in that the surface element has a thickness T and that the distance between each glazing roller and corresponding counter stay is set in the range T minus 0.7mm - 1.2mm, preferably 0.7mm - 0.9mm.



17. A process according to claim 16, characterised in that the pressure between each glazing roller and its corresponding counter stay is 0.1 - 10 Bar, preferably 0.5 - 5 Bar.
18. A process according to any of the claims 1 - 17, characterised in that the hard particles consists of for example silicon oxide,  $\alpha$ -aluminium oxide or silicon carbide.
19. A process according to any of the claims 1 - 17, characterised in that the main part of the hard particles consists of for example silicon oxide,  $\alpha$ -aluminium oxide or silicon carbide while a smaller amount of the hard particles consist of diamond.
20. A process according to claim 19, characterised in that the hard particles consisting of diamond is in the average particle size range 50nm - 2 $\mu$ m and is placed close to the upper surface of the wear layer.