



(86) Date de dépôt PCT/PCT Filing Date: 2004/01/21
(87) Date publication PCT/PCT Publication Date: 2004/08/12
(85) Entrée phase nationale/National Entry: 2005/07/22
(86) N° demande PCT/PCT Application No.: US 2004/001519
(87) N° publication PCT/PCT Publication No.: 2004/067783
(30) Priorités/Priorities: 2003/01/24 (60/442,334) US;
2003/01/31 (60/444,261) US

(51) Cl.Int.⁷/Int.Cl.⁷ C22C 38/22, C22C 38/46, C22C 38/44,
C22C 38/24, C21D 9/00

(71) Demandeur/Applicant:
ELLWOOD NATIONAL FORGE COMPANY, US

(72) Inventeurs/Inventors:
RUHLMAN, JAMES D., US;
DILMORE, MORRIS, US

(74) Agent: RIDOUT & MAYBEE LLP

(54) Titre : ACIER « EGLIN », COMPOSITION HAUTE RESISTANCE FAIBLEMENT ALLIEE
(54) Title: EGLIN STEEL - A LOW ALLOY HIGH STRENGTH COMPOSITION

(57) **Abrégé/Abstract:**

The present invention relates to a low to medium carbon content, high strength, and high ductility steel composition. The present invention contains relatively low nickel content, yet exhibits high performance characteristics and is manufactured at a substantially lower cost than alloy compositions containing high levels of nickel.



(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
12 August 2004 (12.08.2004)

PCT

(10) International Publication Number
WO 2004/067783 A3

(51) International Patent Classification⁷: **C22C 38/22**,
38/24, 38/44, 38/46, C21D 9/00

(21) International Application Number:
PCT/US2004/001519

(22) International Filing Date: 21 January 2004 (21.01.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/442,334 24 January 2003 (24.01.2003) US
60/444,261 31 January 2003 (31.01.2003) US

(71) Applicant (for all designated States except US): **ELLWOOD NATIONAL FORGE COMPANY** [US/US];
One Front Street, Irvine, PA 16329 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **RUHLMAN, James, D.** [US/US]; 35 Blue Bayou Drive, Santa Rosa Beach, FL 32459-7120 (US). **DILMORE, Morris** [US/US]; 5948 Jack Stokes Road, Baker, FL 32531 (US).

(74) Agents: **SUPERKO, Colleen_ et al.**; Hale and Dorr LLP, 60 State Street, Boston, MA 02109 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM,

AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(88) Date of publication of the international search report:
7 October 2004

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: EGLIN STEEL - A LOW ALLOY HIGH STRENGTH COMPOSITION

(57) Abstract: The present invention relates to a low to medium carbon content, high strength, and high ductility steel composition. The present invention contains relatively low nickel content, yet exhibits high performance characteristics and is manufactured at a substantially lower cost than alloy compositions containing high levels of nickel.



WO 2004/067783 A3

EGLIN STEEL - A LOW ALLOY HIGH STRENGTH COMPOSITION

Related Application

This application claims benefit to U.S. Provisional Application, Serial No. 60/442,334, entitled "Eglin Steel – A Low Alloy High Strength Composition," filed January 24, 2003 and to U.S. Provisional Application, Serial No. 60/444,261, also entitled "Eglin Steel – A Low Alloy High Strength Composition," filed January 31, 2003 with the U.S. Patent and Trademark Office, the contents of which are hereby incorporated by reference in their entirety.

10 Government Interests

The present invention was made in the course of a contract with the Department of the Air Force, and may be manufactured and used by or for the Government of the United States for all governmental purposes without the payment of a royalty. The Government may have rights in this invention.

15

Technical Field

The present invention relates to a low alloy, high strength steel composition having a low to medium carbon content and high ductility.

20 Background of the Invention

There is a need in the art for a low cost, high strength, high performance steel composition. Such high strength, high performance steels have various applications in both the commercial and military industries. For example, commercial applications of high strength, high performance steels include the following: pressure vessels; hydraulic and mechanical press components; commercial aircraft frame and landing gear components; locomotive, automotive, and truck components, including die block steels for manufacturing of components; and bridge structural members. Exemplary military applications of high strength, high performance steels include hard target penetrator warhead cases, missile components including frames, motors, and ordnance components including gun components, armor plating, military aircraft frame and landing gear components.

One major disadvantage in the use of high strength, high performance steels in such applications is the relatively high cost of the steel, which is the result of the high

alloy content and expensive related manufacturing processes associated with such high strength steels. To produce a high strength steel, prior art compositions have included high levels of nickel, which is an expensive element and contributes to the high overall cost of the final steel product. One prior art composition commonly
5 designated as AF-1410, described in U.S. Patent No. 4,076,525 hereby incorporated by reference, provides a high strength, high performance steel at an expensive cost due to the high weight percentage of nickel, which comprises about 9.5 to about 10.25 percent by weight of the entire AF-1410 steel composition. A need, therefore, exists for an improved low alloy, high strength, high performance steel composition that can
10 be produced relatively inexpensively.

The present invention overcomes the existing need in the prior art by providing a low alloy, low to medium carbon content, and low nickel content steel composition, which exhibits the same desirable high performance characteristics of high strength steel compositions known in the prior art and which can be produced according to
15 current "state-of-the-art" production techniques at substantially lower cost (ladle melting and refining versus vacuum melting and refining). The low carbon and low alloy content makes the steel composition of the present invention more easily welded and more easily heat-treated. Current bomb case materials are not generally weldable, whereas the bomb case material disclosed herein welds very easily. Weldability will
20 increase the options for manufacturing bomb cases and, as a result, should significantly reduce overall production costs for this type of application.

The steel composition of the present invention has utility wherever high strength, high performance steel is desired. The low alloy, high strength steel composition of the present invention is particularly useful in projectile penetrator
25 applications wherein high impact velocities, such as those greater than 1000 feet per second, are imparted to the projectile to cause deep penetration of rock and concrete barriers. The strength, toughness and wear resistance of the steel produced according to the present invention provides enhanced penetrator performance, while at the same time reduces manufacturing costs by using less of the more costly alloy materials such
30 as nickel.

Summary of the Invention

The present invention relates to a high strength and high ductility steel composition called "Eglin steel," having a low alloy and a low to medium carbon content. The Eglin steel composition of the present invention includes relatively low levels of nickel, yet maintains the high strength and high performance characteristics associated with steel compositions that contain high levels of nickel.

It is an object of the present invention to provide a low alloy, high strength steel composition that has a relatively low nickel content.

It is another object of the present invention to provide a low alloy, high strength steel composition that is manufactured by certain specific thermal processes to exhibit optimum mechanical properties.

It is yet another object of the present invention to provide a high performance steel composition that avoids the high production costs associated with high alloys.

It is still further an object of the present invention to produce a bomb case material that is weldable, so as to increase the options for manufacturing bomb cases and, consequently, significantly reduce overall production costs.

The foregoing and other features and advantages of the present invention will become more apparent in light of the following detailed description of the preferred embodiments thereof. While the invention will be described in connection with one or more preferred embodiments, it will be understood that it is not intended to limit the invention to those embodiments. On the contrary, it is intended that the invention cover all alternatives, modifications and equivalents as may be included within its spirit and scope as defined by the appended claims.

25 Detailed Description of the Invention

The present invention is directed to a low alloy, low to medium carbon content, high strength, and high ductility steel composition termed "Eglin steel." Eglin steel contains a relatively low nickel content, yet exhibits high performance characteristics. Eglin steel, furthermore, is manufactured at a substantially lower cost than alloy compositions containing high levels of nickel.

The low alloy, Eglin steel of the present invention has the following weight percentages, as set forth in Table 1, below:

Table 1

	<u>Element</u>	<u>Weight %</u>
	Carbon (C)	0.16-0.35%
5	Manganese (Mn)	0.85% Maximum
	Silicon (Si)	1.25% Maximum
	Chromium (Cr)	1.50-3.25%
	Nickel (Ni)	5.00% Maximum
	Molybdenum (Mo)	0.55% Maximum
10	Tungsten (W)	0.70-3.25%
	Vanadium (V)	0.05-0.30%
	Copper (Cu)	0.50% Maximum
	Phosphorous (P)	0.015% Maximum
	Sulfur (S)	0.012% Maximum
15	Calcium (Ca)	0.02% Maximum
	Nitrogen (N)	0.14% Maximum
	Aluminum (Al)	0.05% Maximum
	Iron (Fe)	Balance

20 Certain alloying elements of Eglin steel provide desirable properties. Silicon
is included to enhance toughness and stabilize austenite. Chromium is included to
enhance strength and hardenability. Molybdenum is included to enhance
hardenability. Calcium is included as a sulfur control agent. Vanadium and nickel are
included to increase toughness. Tungsten is included to enhance strength and wear
25 resistance.

The alloy of the present invention can be manufactured by the following
processes: (i) Electric Arc, Ladle Refined and Vacuum Treated; (ii) Vacuum
Induction Melting; (iii) Vacuum Arc Re-Melting; and/or (iv) Electro Slag Re-Melting.
The use of the end item will dictate the manufacturing process that should be applied.
30 As an example, a limited use and low liability item is manufactured by using only the
Electric Arc, Ladle Refined and Vacuum Treated manufacturing process. In another
example, a medium use and medium liability item is manufactured by using either the
Electric Arc, Ladle Refined and Vacuum Treated process or the Electric Arc, Ladle
Refined, Vacuum Treated plus Vacuum Arc Re-Melting process. The Electric Arc,
35 Ladle Refined, Vacuum Treated plus Electro Slag Re-Melting may also be included.
In yet another example, a high use and high liability item such as an airframe
component requires the Vacuum Induction Melting process, the Vacuum Arc Re-
Melting process, or the Vacuum Induction Melting process, Vacuum Arc Re-Melting
process and the Electro Slag Re-Melting manufacturing process. As the liability and

number of manufacturing processes increase, the cost also increases. End products made from Eglin steel can be produced using open die forging, close die forging, solid or hollow extrusion methods, static or centrifugal castings, continuous casting, plate rolling, bar rolling or other conventional methods.

5 The present invention is explained and illustrated more specifically by the following non-limiting example.

EXAMPLE 1

10 Five sample heats (*e.g.*, compositional variants termed ES-1 through ES-5) of the Eglin steel alloy composition of the present invention were produced according to the composition ranges in Table 1 above. The typical chemistry to obtain desired properties is listed below in Table 2 in the following weight percentages:

Table 2

Element	C	Mn	P	S	Ni	Cr	Al	W	Si	Mo	N	V	Cu	Ca
Weight %	.28	.74	.012	.003	1.03	2.75	.011	1.17	1.00	.36	.0073	.06	.10	.02

15 The samples were rolled into 1" thick plates and thermal processed according to the following process. First, the samples were normalized by: (i) charging the samples into a furnace below 500°F; (ii) heating the samples at 125°F maximum per hour to about 1725-1775°F; (iii) holding the samples at 1750°F for 1 hour per inch of section size; and (iv) allowing the samples to cool in air at room temperature. Second,
 20 the samples were austenitized by (i) charging the samples into a furnace below 500°F; (ii) heating the samples at 125°F maximum per hour to about 1675-1725°F; and (iii) holding the samples at 1700°F for 1 hour per inch of section size. Next, the samples were oil quenched to below 125°F. Lastly, the samples were tempered by (i) charging
 25 the samples into a furnace below 500°F; (ii) heating the samples at 100°F maximum per hour to about 490-510°F; (iii) holding the samples at 500°F for 1 hour per inch of section size; and (iv) allowing the samples to cool in air at room temperature.

 The following tests were conducted: tensile strength, yield strength, elongation, reduction of area, Charpy V-Notch Impact, and the Hardness Rockwell C-scale. The results of these tests are depicted in Table 3, below.

Table 3
Mechanical Properties Table for Eglin Steel Test Series

Composition	HR UTS ksi	HR YTS ksi	HR STF %	HRHT UTS ksi	HRHT YTS ksi	HRHT STF %	LR UTS ksi	LR YTS ksi	LR STF %	Hardness Rc	CI RT ft. lbs	CI - 40°F ft. lb.
ES-1	263.7	224.5	16.6	215.7	191.4	15.9	246.7	193.9	18.4	45.6	56.2	42.7
std. dev.	3.1	4.0	0.3	3.6	7.0	0.7	1.4	2.2	0.4	0.1	2.6	0.3
ES-2	261.2	231.9	15.5	216.1	197.4	15.1	244.4	201.9	17.5	46.6	27.3	20.0
std. dev.	2.0	3.3	0.3	7.1	6.0	0.6	1.0	0.2	0.3	0.2	1.9	1.0
ES-3	247.5	218.4	16.6	202.6	187.8	16.0	233.6	186.4	18.0	45.4	44.8	21.3
std. dev.	3.4	3.5	0.5	2.0	2.7	1.0	0.7	1.1	0.2	0.2	2.8	3.9
ES-4	264.3	229.0	16.3	218.4	198.0	16.0	248.3	199.1	17.5	46.5	39.6	24.2
std. dev.	1.6	4.5	0.4	1.2	2.1	0.8	1.4	0.6	0.4	0.2	0.6	3.6
ES-5	291.9	244.8	15.1	233.3	210.6	15.2	270.2	216.0	16.6	48.3	26.2	22.3
std. dev.	0.8	5.5	0.5	2.1	0.5	0.3	1.1	1.6	0.3	0.18	2.2	0.8

HR UTS – High Rate Ultimate Tensile Strength
 HR YTS – High Rate Yield Tensile Strength
 HR STF – High Rate Strain-To-Failure
 HRHT UTS – High Rate High Temperature (900°F) Ultimate Tensile Strength
 HRHT YTS – High Rate High Temperature (900°F) Yield Tensile Strength
 HRHT STF – High Rate High Temperature (900°F) Strain-To-Failure
 LR UTS – Low Rate Ultimate Tensile Strength
 LR YTS – Low Rate Ultimate Yield Strength
 LR STF – Low Rate Strain-To-Failure

Hardness Rockwell “C”

CI, RT – Charpy “V” Notch Impact @ Room Temperature

CI, -40°F – Charpy “V” Notch Impact @ -40°F

EXAMPLE 2- 5

Sample heats of the Eglin steel alloy composition of the present invention were produced according to the composition ranges in Table 1 above. The samples were thermal processed according to the following processes.

EXAMPLE 2

First, the samples were normalized by: (i) charging the samples into a furnace below 500°F; (ii) heating the samples at 900°F maximum per hour to about 1725-1775°F; (iii) holding the samples at 1750°F for 1 hour per inch of section size; and (iv) allowing the samples to cool in air at room temperature. Second, the samples were austenitized by (i) charging the samples into a furnace below 500°F; (ii) heating the samples at 900°F maximum per hour to about 1675-1725°F; and (iii) holding the samples at 1700°F for 1 hour per inch of section size. Next, the samples were helium or nitrogen gas quenched to below 125°F. Lastly, the samples were tempered by (i) charging the samples into a furnace below 500°F; (ii) heating the samples at 100°F per hour to about 490-510°F; (iii) holding the samples at 500°F for 1 hour per inch of section size; and (iv) allowing the samples to cool in air at room temperature.

EXAMPLE 3

First, the samples were normalized by: (i) charging the samples into a furnace below 500°F; (ii) heating the samples at 125°F maximum per hour to about 1725-1775°F; (iii) holding the samples at 1750°F for 1 hour per inch of section size; and (iv) allowing the samples to cool in air at room temperature. Second, the samples were austenitized by (i) charging the samples into a furnace below 500°F; (ii) heating the samples at 125°F maximum per hour to about 1675-1725°F; and (iii) holding the samples at 1700°F for 1 hour per inch of section size. Next, the samples were quenched by (i) still air cooling the samples to about 975-1025°F; and (ii) oil quenching the samples to below 125°F. Lastly, the samples were tempered by (i) charging the samples into a furnace below 500°F; (ii) heating the samples at 100°F maximum per hour to about 490-510°F; (iii) holding the samples at 500°F for 1 hour per inch of section size; and (iv) allowing the samples to cool in air at room temperature.

EXAMPLE 4

First, the samples were normalized by: (i) charging the samples into a furnace below 500°F; (ii) heating the samples at 900°F maximum per hour to about 1725-

1775°F; (iii) holding the samples at 1750°F for 1 hour per inch of section size; and (iv) allowing the samples to cool in air at room temperature. Second, the samples were austenitized by (i) charging the samples into a furnace below 500°F; (ii) heating the samples at 900°F maximum per hour to about 1675-1725°F; and (iii) holding the samples at 1700°F for 1 hour per inch of section size. Next, the samples were quenched by (i) simulating air-cooling the samples with helium or nitrogen to about 975-1025°F; and (ii) helium or nitrogen gas quenching the samples to below 125°F. Lastly, the samples were tempered by (i) charging the samples into a furnace below 500°F; (ii) heating the samples at 100°F maximum per hour to about 490-510°F; and (iii) holding the samples at 500°F for 1 hour per inch of section size.

EXAMPLE 5

First, the samples were normalized by: (i) charging the samples into a furnace below 500°F; (ii) heating the samples at 125°F maximum per hour to about 1725-1775°F; (iii) holding the samples at 1750°F for 1 hour per inch of section size; and (iv) allowing the samples to cool in air at room temperature. Second, the samples were austenitized by (i) charging the samples into a furnace below 500°F; (ii) heating the samples at 125°F maximum per hour to about 1675-1725°F; and (iii) holding the samples at 1700°F for 1 hour per inch of section size. Next, the samples were quenched by (i) still air cooling the samples to about 975-1025°F; and (ii) water quenching the samples to below 125°F. Lastly, the samples were tempered by (i) charging the samples into a furnace below 500°F; (ii) heating the samples at 100°F maximum per hour to about 490-510°F; (iii) holding the samples at 500°F for 1 hour per inch of section size; and (iv) cooling the samples in air at room temperature.

In addition to the specific examples noted above, it has been found that improved mechanical properties and/or process efficiencies can be realized by one or more of the following: (i) eliminating the normalizing operation, (ii) varying austenitization times and temperatures, (iii) quenching in a variety of media, including water, polymer solutions oil, pressurized nitrogen or helium, and air, (iv) varying tempering temperatures from about 300-600°F, and (v) varying tempering times.

Various modifications of the present invention in addition to those shown and described herein will be apparent to those skilled in the art from the foregoing description. Such modifications are also intended to fall within the scope of the appended claims.

We claim:

1. An alloy steel in weight percentage consisting essentially of from about 0.16% to about 0.35% carbon, about 0.85% maximum manganese, about 1.25% maximum silicon, about 1.50% to about 3.25% chromium, about 5.00% maximum nickel, about 5 0.55% maximum molybdenum, about 0.70% to about 3.25% tungsten, about 0.05% to about 0.30% vanadium, about 0.50% maximum copper, about 0.015% maximum phosphorous, about 0.012% maximum sulfur, about 0.02% maximum calcium, about 0.14% maximum nitrogen, about 0.05% maximum aluminum, and balance essentially iron.
- 10 2. The alloy steel as in claim 1, consisting essentially of about 0.28% carbon, about 0.74% manganese, about 0.012% phosphorus, about 0.003% sulfur, about 1.03% nickel, about 2.75% chromium, about 0.011% aluminum, about 1.17% tungsten, about 1% silicon, about 0.36% molybdenum, about 0.0073% nitrogen, about 0.06% vanadium, about 0.1% copper, about 0.02% calcium, and balance essentially
15 iron.
3. A method of thermally processing an alloy steel comprising:
 - a) normalizing;
 - b) austenitizing;
 - c) oil quenching; and
 - 20 d) tempering.
4. The method as in claim 3, wherein normalizing further comprises:
 - a) charging the alloy steel into a furnace below 500°F;
 - b) heating the alloy steel at 125°F maximum per hour to about 1725-
25 1775°F;
 - c) maintaining the alloy steel at 1750°F for 1 hour per inch of section size; and
 - d) cooling the alloy steel in air at room temperature.
5. The method as in claim 3, wherein austenitizing further comprises:
 - a) charging the alloy steel into a furnace below 500°F;
 - 30 b) heating the alloy steel at 125°F maximum per hour to about 1675-1725°F; and
 - c) maintaining the alloy steel at 1700°F for 1 hour per inch of section size.
6. The method as in claim 3, wherein the alloy steel is oil quenched to below 125°F.
- 35 7. The method as in claim 6, wherein the alloy steel is still air-cooled to about 975-1025°F prior to oil quenching.
8. The method as in claim 3, wherein tempering further comprises:
 - a) charging the alloy steel into a furnace below 500°F;
 - b) heating the alloy steel at 100°F maximum per hour to about 490-510°F;
 - 40 c) maintaining the alloy steel at 500°F for 1 hour per inch of section size; and
 - d) cooling the alloy steel in air at room temperature.
9. A method of thermally processing an alloy steel comprising:

- a) normalizing;
 - b) austenitizing;
 - c) gas quenching; and
 - d) tempering.
- 5 10. The method as in claim 9, wherein normalizing further comprises:
- a) charging the alloy steel into a furnace below 500°F;
 - b) heating the alloy steel at 900°F maximum per hour to about 1725-1775°F;
 - c) maintaining the alloy steel at 1750°F for 1 hour per inch of section
 - 10 size; and
 - d) cooling the alloy steel in air at room temperature.
11. The method as in claim 9, wherein austenitizing further comprises:
- a) charging the alloy steel into a furnace below 500°F;
 - b) heating the alloy steel at 900°F maximum per hour to about 1675-1725°F; and
 - 15 c) maintaining the alloy steel at 1700°F for 1 hour per inch of section size.
12. The method as in claim 9, wherein the alloy steel is helium or nitrogen gas quenched to below 125°F.
13. The method as in claim 12, wherein stimulating air-cooling the alloy steel with helium or nitrogen to about 975-1025°F occurs prior to gas quenching.
- 20 14. The method as in claim 9, wherein tempering further comprises:
- a) charging the alloy steel into a furnace below 500°F;
 - b) heating the alloy steel at 100°F per hour to about 490-510°F;
 - c) maintaining the alloy steel at 500°F for 1 hour per inch of section size;
 - 25 and
 - d) cooling the alloy steel in air at room temperature.
15. The method as in claim 9, wherein tempering further comprises:
- a) charging the alloy steel into a furnace below 500°F;
 - b) heating the alloy steel at 100°F maximum per hour to about 490-510°F;
 - 30 and
 - c) maintaining the alloy steel at 500°F for 1 hour per inch of section size.
16. A method of thermally processing an alloy steel comprising:
- a) normalizing;
 - b) austenitizing;
 - 35 c) water quenching; and
 - d) tempering.
17. The method as in claim 16, wherein normalizing further comprises:
- a) charging the alloy steel into a furnace below 500°F;
 - b) heating the alloy steel at 125°F maximum per hour to about 1725-1775°F;
 - 40 c) maintaining the alloy steel at 1750°F for 1 hour per inch of section size; and
 - d) cooling the alloy steel in air at room temperature.

18. The method as in claim 16, wherein austenitizing further comprises:
a) charging the alloy steel into a furnace below 500°F;
b) heating the alloy steel at 125°F maximum per hour to about 1675-
5 1725°F; and
c) maintaining the alloy steel at 1700°F for 1 hour per inch of section size.
19. The method as in claim 16, wherein quenching comprises:
a) still air cooling the alloy steel to about 975-1025°F; and
b) water quenching the alloy steel to below 125°F.
- 10 20. The method as in claim 16, wherein tempering further comprises:
a) charging the alloy steel into a furnace below 500°F;
b) heating the alloy steel at 100°F maximum per hour to about 490-510°F;
c) maintaining the alloy steel at 500°F for 1 hour per inch of section size;
and
15 d) cooling the alloy steel in air at room temperature.
21. A bomb casing material comprising the alloy steel in weight percentage as in claim 1.
22. A bomb casing material comprising the alloy steel in weight percentage as in claim 2.

20