



(11)

EP 3 517 580 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
25.12.2024 Bulletin 2024/52

(21) Application number: **19160988.2**(22) Date of filing: **04.05.2006**

(51) International Patent Classification (IPC):
C09C 1/00 (2006.01) **C09D 11/02 (2014.01)**
C09D 5/36 (2006.01)

(52) Cooperative Patent Classification (CPC):
C09C 1/0015; B42D 25/324; B42D 25/36;
B42D 25/425; B42D 25/445; C09C 1/04;
C09D 5/36; C09D 7/61; C09D 7/70; C09D 11/037;
C01P 2004/20; C01P 2006/40; C08K 3/10;
C09C 2200/1054; C09C 2200/301; (Cont.)

(54) **OPAQUE PIGMENT FLAKES CONTAINING SYMBOLS FOR COVERT SECURITY APPLICATIONS**

OPAKE PIGMENTFLOCKEN MIT SYMBOLEN FÜR VERBORGENE
SICHERHEITSANWENDUNGEN

FLOCONS DE PIGMENT OPAQUES CONTENANT DES SYMBOLES POUR APPLICATIONS DE
SÉCURITÉ FURTIVES

(84) Designated Contracting States:
AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
HU IE IS IT LI LT LU LV MC NL PL PT RO SE SI SK
TR

(30) Priority: **05.07.2005 US 69659305 P**
04.10.2005 US 24312205

(43) Date of publication of application:
31.07.2019 Bulletin 2019/31

(62) Document number(s) of the earlier application(s) in accordance with Art. 76 EPC:
06252357.6 / 1 741 757

(73) Proprietor: **Viavi Solutions Inc.**
Chandler, AZ 85286 (US)

(72) Inventor: **ARGOITIA, Alberto**
Santa Rosa, CA California 95405 (US)

(74) Representative: **Murgitroyd & Company**
165-169 Scotland Street
Glasgow G5 8PL (GB)

(56) References cited:
EP-A1- 1 239 307 **EP-A2- 0 978 373**
EP-A2- 1 353 197 **WO-A2-2005/017048**
US-A1- 2002 182 383

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

(52) Cooperative Patent Classification (CPC): (Cont.)
C09C 2210/30; C09C 2220/20

Description

[0001] The present invention relates generally to thin-film pigment flakes for use in a coating composition.

BACKGROUND OF THE INVENTION

[0002] Specialty pigments have been developed for use in security applications, such as anti-counterfeiting devices printed on banknotes, packaging of high-value items, seals for containers, and even for direct application to commercial items. For example, the U.S. twenty-dollar Federal Reserve Note currently uses optically variable ink. The number "20" printed in the lower-right corner of the face of the note changes color as the viewing angle changes. This is an overt anti-counterfeiting device. The color-shifting effect is not reproducible by ordinary color photocopiers, and someone receiving a note can observe whether it has the color-shifting security feature to determine the note's authenticity.

[0003] Other high-value documents and objects use similar measures. For example, iridescent pigments or diffractive pigments are used in paints and inks that are applied directly to an article, such as a stock certificate, passport, original product packaging, or to seals that are applied to an article. Security features that are more difficult to counterfeit are desirable as counterfeiters continue to become more sophisticated.

[0004] One anti-counterfeiting approach uses microscopic symbols on multi-layer color-shifting pigment flakes. The symbols are formed on at least one of the layers of the multi-layer color-shifting pigment flakes by a local change of an optical property(s), such as reflectivity. The multi-layer color-shifting pigment flakes generally include a Fabry Perot-type structure having an absorbing layer separated from a reflective layer by a spacer layer. The reflective layer is typically a layer of metal, which renders the pigment flake essentially opaque. If a large portion of these types of pigment flakes are mixed with other pigment, the resultant color might be significantly different from the pigment, and if too few of these flakes are mixed with other pigment, they might be difficult to find.

[0005] Another technique uses epoxy-encapsulated shaped flakes of polyethylene terephthalate ("PET"). A reflective layer is deposited on a roll of PET, and then the PET is cut into pieces. The flakes are coated or encapsulated with epoxy to improve the durability of the reflective layer. These flakes are available in a variety of shapes, such as square, rectangle, hexagon, and "apostrophe," and a selection of reflective metallic tints, such as silver, pewter, gold, and copper. However, the epoxy layer and the relatively thick PET substrate (which typically has a minimum thickness of about 13 microns (0.5 mils) for use in vacuum deposition processes) result in a relatively thick flake, typically greater than 14 microns. Unfortunately, such a thick flake is not desirable for use in covert applications where the thickness is substantially

greater than the base pigment. Similarly, such thick flakes do not flow well in inks, and create lumps in paint. When paint includes a thick flake that creates a rough surface, a relatively thick clear topcoat is typically applied over the rough surface.

[0006] It is desirable to mark objects with covert anti-counterfeiting devices that overcome the limitations of the techniques discussed above. US2002/0182383A1 and EP1239307A are useful in understanding such techniques.

[0007] This invention relates to providing flakes which have taggents or covert symbols stamped or embossed or etched therein by mechanical means or formed by laser means, wherein the covert symbols can be seen

with a microscope. In order to preserve the integrity of the symbols, a frame is provided around all of or part of covert symbols so that when the individual flakes are removed from the support structure they are deposited on, the majority of flakes break along the frame lines provided

instead of breaking in a less controlled un-predictable manner wherein break lines would otherwise occur with greater frequency through and about the symbols. In some instances, parallel frame lines may be provided so that the flakes break into a ribbon; in a preferred

embodiment of this invention, flakes and more particularly one or more symbols within a flake will have a framed grooved border on four or fewer sides about the one or more symbols, so that the flakes break in uniform rectangles along the same lines. A conventional release layer is provided so that the flakes can easily be removed from their backing or support layer and so that upon removal, the flakes break up along the framing lines. Frames can be made in a similar manner in which the symbols are made; using a laser, etching or stamping of the film that is upon the substrate; in a preferred embodiment, the frames are provided in the same process along with the formation of the symbols.

[0008] It is therefore an object of this invention, to provide flakes having symbols thereon, and wherein the symbols have or had, frames or borders embossed, etched or laseried into the flake for protecting the symbols during the process of separating flakes from their temporary support backing.

45 SUMMARY OF THE INVENTION

[0009] In accordance with the invention there is provided a plurality of covert flakes as defined in Claim 1.

[0010] A coating composition may include the covert opaque flakes of the present invention, being less than about 10 microns thick with identifying indicia. Examples of identifying indicia include selected flake shape(s) and/or compositions. The covert flakes are typically dispersed in a carrier, such as a varnish base, paint vehicle or ink vehicle, to form a coating composition. The covert flakes are dispersed in sufficiently dilute concentration so that the covert flakes are not easily detectable in the coating composition by casual observation and are co-

lored to match the color of a base pigment or have a different optical characteristic, such as being highly reflective ("bright" or "silver"). The shapes of selectively shaped covert flakes are not discerned by unaided human vision, but can be seen under about 50 X to 300 X magnification. In one embodiment, the covert flakes appear to be essentially identical to base pigment flakes in the composition, but are made of different thin-film layers that are detectable using standard analytical methods.

[0011] In a particular embodiment the covert flakes are a single layer of a shaped inorganic dielectric material, such as ZnS. The thickness of the single layer of inorganic dielectric material is selected to provide a covert flake that has color to match mica-based nacreous base pigment.

[0012] A composition using flakes of the present invention could be applied to an object to provide a covert security feature. A pigmented composition may be used to print a field (e.g. an image) on the object, and a varnish composition with a low concentration of opaque security flakes may be used to overprint an existing image on the object. In an embodiment of the invention, covert flake is mixed with base pigment to provide a covert security feature to images printed with the composition that look substantially similar to images printed with only the base pigment.

BRIEF DESCRIPTION OF THE DRAWINGS

[0013]

Fig. 1 is a plan view of a portion of a document with a security feature using an embodiment of the present invention.

Fig. 2A is a simplified view of a portion of a deposition substrate having an embossed portion and a non-embossed portion.

Fig. 2B is a simplified view of a portion of an other deposition substrate 11' having an embossed portion 13' and a non-embossed portion 15'

Fig. 3A is a simplified plan view of a portion 14A of the security feature 14 shown in Fig. 1.

Fig. 3B is a simplified cross section of a bright pigment flake 20 according to an embodiment of the present invention.

Fig. 3C is a simplified cross section of a bright flake 20' providing an elemental fingerprint.

Fig. 3D is a simplified cross section of a color-shifting pigment flake 30 according to another embodiment of the present invention.

Fig. 4 is a cross section of a varnish with opaque covert flakes according to an embodiment of the present invention dispersed in a carrier.

Fig. 5 is a cross section of base flakes and opaque covert flakes according to another embodiment of the present invention dispersed in a binder.

Fig. 6 is a flow chart of a method of making pigment flake according to an embodiment of the present

invention.

Fig. 12 is an embodiment in accordance with this invention wherein a flake has color shifting properties, magnetic properties, and bears a covert feature within the flake.

Fig. 13 is a photograph of security features wherein covert flakes are aligned to provide an overt security feature bearing the covert feature within flakes.

10 DETAILED DESCRIPTION OF THE INVENTION

I. Introduction

[0014] Flakes for covert security applications are not typically seen by casual observation. Some sort of inspection technique, such as inspection under a microscope or analytical technique, such as elemental analysis, is used. In one embodiment, opaque flakes containing indicia, such as a particular shape, substantially match the visual characteristics of a bulk pigment or other substance they are mixed with. In a particular embodiment, a single-layer inorganic opaque flake having a selected shape is mixed with an iridescent mica-based flake or other base pigment. For the purpose of this discussion, a "single layer" of inorganic material includes multiple layers of the same inorganic material built up upon each other.

[0015] Inorganic covert flakes are particularly desirable in applications where heat, solvents, sunlight, or other factors may degrade organic flakes. For example, an inorganic covert flake used in an explosive is detectable even after exposure to high temperatures and/or pressures, and is persistent in the environment. Flakes according to embodiments of the present invention also are substantially thinner, typically less than about 10 microns, than conventional shaped flakes, enabling their use in ink and produce a smooth surface finish in paints without having to use a clear topcoat. Thin, inorganic flakes according to embodiments of the present invention also have a density closer to the density of base pigment flakes made using similar techniques. Thick flakes incorporating organic substrates often have a different density than thin-film base pigment flake, and may segregate, either before or during application while the carrier is fluid. Flake segregation is undesirable because it can result in an inconsistent ratio of covert and base flakes in a composition, and may degrade the covert nature of the covert flakes if segregation results in an unduly high concentration of covert flakes

II. Exemplary Opaque Flake

[0016] Fig. 1 is a plan view of a portion of a document 10 with a security feature 12 according to an embodiment of the present invention. At least a portion 14 of the security feature 12 is printed with ink or paint including opaque flakes having indicia (hereinafter "covert flakes") mixed with bulk pigment, such as bulk pigment flakes. In one

embodiment, the covert flakes have a particular shape, being rectangular. Preferably, the selected shape is provided by embossing, etching or using a laser to create frames or borders along which the flakes will fracture upon removal from their temporary supporting substrate. In a particular embodiment, the grating pattern has a grating spacing that is not optically active in the visible range of the spectrum. That is, these grating patterns do not form a visible diffraction grating. Covert flakes are also sometimes referred to as taggent flakes, although not all taggent flakes are necessarily covert flakes.

[0017] Generally, bulk pigment particles, including bulk pigment flakes, have an irregular shape. In one embodiment, the covert flakes are distinguishable from bulk pigment flakes by their shape. Alternatively, bulk pigment flakes have a first selected shape, and the covert flakes have a rectangular shape. Production of shaped pigment flakes is accomplished by a variety of techniques, such as using a patterned substrate to deposit the flake material on the substrate and then separating the flake from the substrate to obtain the pattern such as a frame or border, or using a laser or other means to cut the patterned flakes from a sheet of flake material. The shape of the covert flakes may be associated with a manufacturing facility, date of manufacture, or other aspect of the document 10, or ink used in producing the document, for example.

[0018] A roll coater is one type of apparatus that can be used to produce shaped covert flakes according to embodiments of the invention. A roll of a sheet of polymer substrate material (also known as a "web") is passed through a deposition zone(s) and coated with one or more thin film layers. Multiple passes of the roll of polymer substrate back and forth through the deposition zone(s) may be made. The thin film layer(s) is then separated from the polymer substrate and processed into flake. Other apparatus and techniques may be used.

[0019] It is generally desirable to limit the total thickness of thin film layers deposited (and hence removed) from a roll of polymer film substrate to less than about 10 microns. PET is one type of polymer film substrate used in roll coaters, and the PET film substrate is usually at least about 13 microns thick. Thinner PET film tends to thermally deform during vacuum deposition processes. Both the heat in the deposition zone and the heat of condensation of the deposited thin-film layer(s) increase the temperature of the polymer substrate as it passes through a deposition zone. Thus, the minimum thickness of flake cut from and incorporating PET film is about 13 microns.

[0020] In addition to flakes having a rectangular shape preferably realized by embossing frames into the substrate, along which the flakes will separate and break apart, the covert flakes preferably include a one or more symbols, other forms of indicia within and bordered by the frames, and/or a grating pattern. The grating pattern is embossed on a substrate used in a roll coater prior to depositing thin film layers that are processed into flakes, or otherwise formed. In a further embodiment, a selected

amount (percentage) of the deposition substrate surface area is embossed with a grating pattern or shape pattern to obtain a selected amount of covert flakes when the thin film layers are stripped from the deposition substrate and processed into flakes. This technique provides covert flakes with the same optical design (thin film layer composition and thickness) as the base flake. For example, embossing 10% of the deposition substrate surface area with a grating pattern and/or shape pattern would result in

5 a pigment mixture having about 10% covert flakes as is shown in Fig. 10. Different rolls of deposition substrate are produced with different percentages of embossed surface area to obtain pigment mixtures having different amounts covert flake, or are embossed with different 10 patterns to obtain different shapes and/or grating patterns.

[0021] Fig. 2A is a simplified view of a portion of a deposition substrate 11 having an embossed portion 13 and a non-embossed portion 15. The embossed portion 20 has a frame, which is exaggerated for purposes of illustration, and alternatively or optionally has a grating or symbol, for example, and the non-embossed portion is essentially smooth. Alternatively, the non-embossed portion is embossed with a different frame, grating, or symbol. The ratio of the surface area of the embossed portion 13 to the non-embossed portion 15 produces a selected 25 amount of taggent flake (produced from the embossed portion) having the same thin-film structure as the base flake (produced from the non-embossed portion). The deposition substrate 11 travels from one roll 17 to another 30 19 through a deposition zone (not shown) in a roll coater, but alternative embodiments use different types of substrates and deposition systems. Fig. 2B is a simplified view of a portion of another deposition substrate 11' having an embossed portion 13' and a non-embossed portion 15'.

[0022] A pigment flake with identifying indicia provides a security feature even if it is easily observable; however, if a pigment flake with identifying indicia is not easily 40 observable, a counterfeiter might not even be aware that a covert flake is present. One embodiment of the present invention uses covert pigment flake that has the same optical characteristics as the base pigment. The covert pigment flakes are not seen by unaided human vision, but 45 are visible under magnification of about 50 X to 300 X. Covert pigment flakes having essentially the same visual characteristics can be mixed with base pigment in a wide range of proportions without significantly affecting the color of the composition. In some embodiments, covert 50 pigment flakes are readily identifiable in compositions having 5-10 weight % covert pigment flakes and 95-90 weight % base pigment flakes having similar appearance (e.g. color and/or color travel). Often, shaped opaque covert flakes are easily identifiable in the field using hand-held microscopes (e.g. "shirt-pocket" microscopes), and require less magnification to identify than similar sized flakes having symbols.

[0023] Another approach is to use an opaque covert

flake with a rectangular shape that is a different color than the base flake. In one embodiment, the opaque covert flake is a bright metallic ("silver") flake having a thin-film layer of aluminium or other reflector between layers of a dielectric material, such as MgF₂. Bright flake is generally highly reflective over a wide range of visible wavelengths, and often does not have a characteristic color. Bright flake made with gold and copper may appear yellowish and reddish, for example. It has been found that between about 0.25 weight % to about 5 weight % of shaped (e.g. "diamond" shaped) bright flake in colored base pigments can be added without causing a noticeable change in color, but are still easily identifiable under illuminated magnification of about 50 X (i.e. 50 times magnification). Under illuminated magnification, both the shape and high brightness of the flake distinguish it from the base flake. When less than about 0.25% of shaped bright flake is used the covert flakes become difficult to detect because dilution with the base flake results in fewer shaped bright flakes in the field of view.

[0024] When the amount of bright flake exceeds about 5 weight %, the color (e.g. hue) of certain types of flakes, particularly dark colored flakes, changes. In these instances, too much bright flake essentially "dilutes" the color of the base pigment. However, using shaped bright flake in compositions having color-shifting pigment is highly desirable because a single type of shaped bright flake is added in small quantities to many different types (color and/or color travel) of pigment flake, and a relatively small amount of shaped bright flake provides a covert security feature. Similarly, dilution of color is not critical in applications where compositions containing pigment and bright flake are not intended to replace or otherwise be indistinguishable from compositions containing 100% pigment flake.

[0025] Pigments are often mixed in carriers to form paint or ink. Examples of carriers include polyvinyl alcohol, polyvinyl acetate polyvinylpyrrolidone, poly(ethoxyethylene), poly(methoxyethylene), poly(acrylic) acid, poly(acrylamide), poly(oxyethylene), poly(maleic anhydride), hydroxyethyl cellulose, cellulose acetate, poly(saccharides) such as gum arabic and pectin, poly(acetals) such as polyvinylbutyral, poly(vinyl halides) such as polyvinyl chloride and polyvinylene chloride, poly(dienes) such as polybutadiene, poly(alkenes) such as polyethylene, poly(acrylates) such as polymethyl acrylate, poly(methacrylates) such as poly methylmethacrylate, poly(carbonates) such as poly(oxycarbonyl oxyhexamethylene, poly(esters) such as polyethylene terephthalate, poly(urethanes), poly(siloxanes), poly(sulphides), poly(sulphones), poly(vinyl nitriles), poly(acrylonitriles), poly(styrene), poly(phenylenes) such as poly(2,5 dihydroxy-1,4-phenyleneethylene), poly(amides), natural rubbers, formaldehyde resins, other polymers and mixtures of polymers and polymers with solvents.

[0026] Fig. 3A is a simplified plan view of a portion 14A of the security feature 14 shown in Fig. 1. The portion 14A of the security feature is viewed under magnification,

typically about 20 X-300 X, in order to see the shape of the flakes, which are typically about 5-100 microns across, more typically about 20-40 microns across. The security feature was printed using ink including base pigment particles 16 and a covert pigment flake 18 having a selected shape, in this case a "diamond" shape. The optical characteristics and concentration of the covert pigment flake is chosen so as to not disturb the visual appearance of a composition made with the base pigment particles.

[0027] The base pigment particles 16 are illustrated as being irregularly shaped flakes. Alternatively, base pigment flakes have a selected (i.e. regular) shape. Similarly, the covert pigment flake 18 could have a grating. The addition of a grating further increases the difficulty of counterfeiting. In some embodiments, the covert pigment flake 18 has generally the same optical characteristics as the base pigment particles. Alternatively, the covert pigment flake 18 has different optical characteristics as the base pigment particles but is present in sufficiently small quantities so as not to disturb the visual appearance of a composition made with the base pigment particles.

[0028] To assist understanding of the present invention, "diamond- shaped" covert flakes were provided as bright flakes about 25 microns by 35 microns across. The shaped flakes were made by embossing a diamond pattern into a roll of PET deposition substrate material, and then depositing a standard thin-film design for bright flake (e.g. about 100-60 nm of Al between layers of MgF₂ that are each about 400 nm thick). The total thickness for this bright flake is about 900 nm, which is about one micron. The embossed pattern is also known as a "frame" (as opposed to a grating which is intended to produce a pattern in or on the flake), and is positive in some embodiments and negative in other embodiments. Aside from the diamond flakes themselves offering some measure of a covert feature when distributed in some predetermined ratio with other irregular shaped flakes, the diamond-shaped flakes may be embossed with additional covert symbols, thereby providing two levels of covert features available to protect a device.

[0029] To assist understanding of the present invention, the combination of a metal layer with one or more dielectric layers facilitates removal of the flake from the deposition substrate. A thin film stack having only dielectric layers is brittle and often has residual stresses from the deposition process. Such thin film stacks tend to break more randomly, resulting in fewer shaped flakes. An all-metal stack or single layer is difficult to process into patterned flakes according to the frame of the deposition substrate because the metal is relatively ductile. A dielectric-metal-dielectric flake having a total thickness of between about 0.5 microns and about 3 microns provides a good combination of ductile and brittle characteristics that result in good patterning of the flake when it is removed from the substrate and processed. In a particular embodiment, shaped bright flake having a total thickness of about one micron of a ductile metal layer

between brittle dielectric layers yielded about 90% diamond-shaped flakes from an embossed deposition substrate.

[0030] The thin-film layers were stripped from the deposition substrate and processed into flake using conventional techniques. The embossed diamond pattern provided lines along which the thin-film layers broke into flakes having the selected diamond shape. In another embodiment, the diamond-shaped flakes were about 12 microns by 16 microns and included a grating on the major surface of the flakes. The grating was nominally 2000 lines/mm and did not produce a noticeable diffractive effect in a composition when used as a taggent. The shape of the 12-by-16-micron flake was easily seen at 100 X magnification; however, the grating was not easily seen at this magnification. The grating was readily apparent at 400 X magnification. In other embodiments, a grating is coarser, and is easily seen at the same magnification (e.g. 50 X to 100 X) that is used to discern the shape of the taggent flakes. Thus, gratings used to provide a security feature to taggent flakes do not have to be optically active in the visible portion of the spectrum.

[0031] In a particular embodiment, the base pigment particles are flakes of mica coated with a layer of TiO₂ or other dielectric material. The coating material typically has a relatively high index of refraction. Mica is a naturally occurring mineral that is relatively inexpensive and easily processed into flake substrate. When mica flake substrate is coated with a layer of high-index material of a selected thickness, a nacreous pigment flake is obtained. Mica flake substrate can be coated with several alternative materials using a variety of processes. Such pigments are commonly known as "mica-based" pigments. A photocopy of an image printed with such nacreous pigment does not look like the original, thus mica-based pigment flakes are desirable for use to provide overt security features. However, shaping mica flake substrate or providing a symbol on mica flake substrate is impractical. Covert flake according to an embodiment of the present invention is mixed with the mica-based pigment to enable a covert security feature to be included in images printed with mica-based pigment flakes. Shaped pigment flakes made of a single layer of inorganic dielectric material, such as TiO₂ or ZnS, have an appearance similar to a mica-based pigment if the covert pigment flake has a thickness about five times the quarter-wave optical thickness ("QWOT") at a wavelength in the visible spectrum. Typically, a single-layer covert flake of ZnS intended to match the appearance of a mica-based pigment has a thickness of about 60 nm to about 600 nm. Processing all-dielectric flake from a deposition substrate having an embossed diamond-shaped pattern tends to have a lower yield than a counterpart metal-dielectric flake.

[0032] Fig. 3B is a simplified cross section of a bright pigment flake 20 that assists understanding of the present invention. A reflective layer 22 is between two dielectric thin-film layers 24, 26. The dielectric thin-film

layers 24, 26, provide stiffness to the bright pigment flake and facilitate removal of the pigment flake from the roll coater substrate. It is desirable to keep the bright pigment flake less than 10 microns thick to provide a composition that dries or cures to a smooth surface. In particular embodiments, the thickness of the flake is between about 1 micron and about 3 microns. Thinner flakes tend to be more difficult to process and handle because they weigh so little, and thicker flakes are stronger, and hence more difficult to break along the frame pattern.

[0033] The reflective layer 22 is a thin-film layer of a highly reflective metal being aluminium. The reflective layer 22 is sufficiently thick to be opaque (reflective) in the visible portion of the spectrum, but not so thick as to interfere with separation of the thin-film layers from the substrate and subsequent processing into flake. In other words, a metal reflective layer that was too thick would provide a ductile layer between the relatively brittle dielectric layers 24, 26 and tend to interfere with processing the deposited layers into flakes. Suitable materials for the dielectric layers include ZnS, MgF₂, SiO₂, Al₂O₃, TiO₂, NbZOs, and TazOs, among others. In some embodiments, the dielectric thin film layers 24, 26 also provide environmental protection for the reflective layer 22.

[0034] The bright flake 20 has a selected shape, and optionally or alternatively has other indicia, such as a surface (grating) pattern or an elemental fingerprint. In sufficiently low concentrations, the bright flake 20 is added to colored pigment and colored compositions (e.g. inks and paints). Shaped bright flake can be added to base (i.e. randomly shaped or alternatively shaped) bright flake as a covert security feature.

[0035] Fig. 3C is a simplified cross section of a bright flake 20' with an elemental indicator layer 28. The bright flake 20' has reflective layers 22', 22" between dielectric layers 24', 26', and a layer 28 providing an elemental indicator. The elemental indicator layer 28 is a layer of material that is not found in a base pigment that the bright flake will be used with, and that is readily detectable using elemental analysis techniques, such as secondary ion mass spectrometry ("SIMS"), energy dispersive X-ray ("EDX") and Auger analysis. Furthermore, the elemental indicator is present in the covert flake but not in the base flake, and micro-SIMS, micro-EDX or micro-Auger analysis easily detects this difference. Merely adding the indicating element to the pigment mixture (e.g. adding a small amount of a compound containing the indicating element to the carrier) would not overcome this security feature.

[0036] The elemental indicator layer 28 is not optically active because it is between the two opaque reflective layers 22', 22". The reflective layers 22', 22" are selected to be of the same material used in the base flake, i.e. aluminium. Suitable materials for an elemental indicator include platinum, iridium, osmium, vanadium, cobalt, and tungsten, among others. Those of skill in the art appreciate that the elemental indicator material chosen depends on the base pigment it will be used with. In an alternative

embodiment, the reflective layer of bright pigment is of an elemental indicator material (see Fig. 3B, ref. num. 22). For example, covert bright or colored pigment flake using platinum as the reflective layer is mixed with base bright flake or colored pigment flake using aluminium as the reflective layer. In a further embodiment, the amount of flake having the elemental indicator incorporated into a pigment mixture or composition is chosen to provide a selected elemental ratio (e.g. aluminium to platinum) in the pigment mixture. In an alternative or further embodiment, the material of the dielectric thin-film layers 24', 26' (Fig. 3B, ref. numerals. 24, 26) is chosen to provide an elemental indicator.

[0037] Fig. 3D is a simplified cross section of a color-shifting pigment flake 30 according to an embodiment of the present invention. The color-shifting pigment flake 30 is generally known as a symmetrical 5-layer Fabry-Perot interference flake. A thin film stack 32 includes a reflective metal layer 34, two spacer layers 36A, 36B, and two absorber layers 38A, 38B. The absorber layers are typically very thin, semi-opaque layers of chromium, carbon, or other material. The reflector, spacer, and absorber layers are all optically active, that is, they contribute to the optical performance of the color-shifting pigment flake. Each side of the flake provides similar Fabry-Perot interference structures to incident light, and hence the flake is optically symmetrical.

[0038] The color and color travel of the color-shifting pigment flake is determined by the optical design of the flake, namely the material and thicknesses of the layers in the thin film stack 32, as is well-known in the art of optically variable pigments. The optical design of the color-shifting pigment flake 30 is typically chosen to match the optical properties of the base pigment flake that it will be mixed with. The color-shifting pigment flake is shaped (see Fig. 3A, ref. num. 18), and optionally or alternatively includes other indicia, such as a surface grating pattern and/or elemental indicator.

[0039] For example, the reflective layer includes an elemental indicator, either a reflective metal that is different than the base pigment flakes, or includes an additional elemental indicator layer(s), which may or may not be optically active (see Fig. 3C, ref. num. 28). Alternatively or additionally, the spacer layers 36A, 36B and/or the absorber layers 38A, 38B include an elemental indicator. For example, if the base pigment flake uses MgF_2 , SiO_2 , or Al_2O_3 as a spacer layer material, the covert pigment flake 30 uses different spacer layer material, such as TiO_2 or ZnS . Spacer and/or absorber indicator materials include elements that are easily detected using elemental analysis.

[0040] In some embodiments, using a different spacer material and/or reflector material results in a covert pigment flake 30 that has different optical properties than the base flake. For example, even if the covert and base flakes have similar color at normal incidence, the color travel might be different. Generally, low-index spacer materials (such as MgF_2 and SiO_2) provide more color

travel ("fast shifting" pigments) than high-index spacer materials (such as ZnS and TiO_2). However, such covert flakes can be added in relatively high concentrations to the base pigment flake, even if the color travel does not precisely match that of the base flake, because most casual observers cannot detect the difference between a mixture according to an embodiment of the invention and 100% base flake.

[0041] Fig. 4 is a cross section of a varnish 40 with covert flakes 42 dispersed in a carrier 44 according to an embodiment of the present invention. The carrier is clear or tinted, and the covert flakes 42 are at a concentration selected to avoid casual visual detection. An optional color coat or bright (e.g. "chromed") coating 46 has been applied to an object 48 underneath the varnish 40. The varnish 40 provides a covert security feature to the object without disturbing its appearance. In a particular embodiment, the optional color coat 46 is an image printed with nacreous or color-shifting pigment to provide an overt security feature to the object. The object is a document, product, packaging, or seal, for example. The varnish 40 enables providing a covert security feature to an object that already has a covert security feature without significantly altering the appearance of the object. For example, if stock certificates have been printed with overt security features and it subsequently becomes desirable to provide a covert security feature to the stock certificates, the overt security feature is over-printed with the varnish 40 or a similar ink composition (i.e. an essentially clear ink composition containing covert flakes). In another embodiment, an additional covert security feature is provided to an object already having one or more covert security features. In a particular embodiment, the covert flakes make up not more than 2% of the varnish.

[0042] Fig. 5 is a cross section of a composition 50 (e.g. ink or paint) including base pigment flakes 16 and shaped covert flakes 18 dispersed in a binder or carrier 52 to assist understanding of the present invention. The covert flakes 18 have a rectangular shape. The composition 50 has been applied to an object 48, such as a label, product packaging, bank note, or consumer item.

[0043] Adding covert flake to an existing ink or paint composition provides a covert security feature to images made of the ink or paint. For example, ink with color-shifting pigment is used to provide a color-shifting image as an overt security feature on a bank note or other object. Covert flake according to an embodiment of the present invention is added to the ink, and the resultant mixture is used to print images that appear substantially similar as those printed with the original ink. Thus, a casual observer of the bank note does not notice a change in the appearance of the overt security feature (i.e. color-shifting image) after the covert security feature is added. The indicia of the covert flake indicates a date-of-manufacture, a printing location, and/or the source (manufacturer) of the ink, for example.

III. Experimental Results

[0044] A test standard using 100% magenta-to-green optically variable intaglio ("OVI") pigment flake was produced and measured. Both bright and optically variable taggent samples had a grating pattern of 2000 lines/mm, which made the taggent flakes easier to distinguish from the base pigment flake (i.e. locate) and more difficult to counterfeit. The grating pattern was clearly visible at about 400 X, and did not induce visible diffractive properties to images printed with the test compositions. It is believed that the low portion of the taggent flakes in combination with not being well oriented to the viewer avoided a diffractive effect from occurring. In an alternative embodiment, a finer grating pattern is included on shaped taggent flakes. The shapes are identifiable under a microscope at a first magnification, but the grating pattern is not easily seen at this first magnification. The grating pattern is seen at a higher magnification. It is believed that including such a grating pattern to taggent flake having a selected shape or symbol further enhances the covert nature of the taggent flake because a counterfeiter might see the shape or a symbol under microscopic examination, but not see the grating pattern, and hence not include it in a counterfeit article.

[0045] The first test sample ("sample 1") contained 90% (by weight) of the conventional (base) magenta-to-green pigment flake mixed with 10% magenta-to-green OVI pigment flake with a grating ("taggent flake"). The taggent flakes were easy to detect by routine microscopic inspection, and the color performance of the mixture was the same as the test standard because the color of the taggent flake was well matched to the color of the base flake. Close color matching involves careful monitoring of the production of the taggent flake and a new optical design for each color of taggent flake would generally be used to match each color of base flake.

[0046] Another approach is to use a standard taggent flake design that can be used with many different colors of base flake. Bright taggent flake using an aluminium reflector layer (giving the flake a "silver" appearance) was also evaluated. Fabrication of bright flake is relatively simple and these flakes were very easy to detect at a concentration of 5% when mixed with colored base pigment flakes. Bright taggent flakes are used with many colors of base pigment to provide covert security features. The amount of bright taggent flakes in the composition depends on the desired result. For example, the color performance of an intaglio blend containing 5% bright taggent flake mixed with the magenta-to-green OVI base is distinguishable in a side-by-side comparison from a composition of 100% magenta-to-green OVI flake. A composition essentially indistinguishable from 100% magenta-to-green OVI flake uses less than 5% bright flake, such as compositions with concentrations between about 0.25 weight % and 3 weight % of bright taggent flake in magenta-to-green OVI flake. It is believed that bright flake in concentrations greater than 5% may be

added to pigment flake providing lighter or less saturated color without noticeably changing the appearance of the composition. Bright taggent flakes are easy to detect under modest magnification, even at concentrations below 1%, because of the combination of having a selected shape and of being a different color (e.g. "silver" instead of magenta).

IV. Exemplary Methods

[0047] Fig. 6 is a flow chart of a method 600 of making pigment flake according to an embodiment of the present invention. A roll substrate having a non-embossed ("smooth") portion and an embossed portion in a selected ratio of the deposition surface area of the roll substrate is provided (step 602). In one embodiment, the embossed portion is embossed with a frame for producing flakes having a selected shape. In an alternative embodiment, the embossed portion is embossed with a grating pattern or symbol. In an alternative embodiment, the substrate is patterned using a process other than embossing, such as laser ablation. At least one thin film layer is deposited on the roll substrate (step 604), and the deposited thin film layer(s) is processed into flake (step 606) to result in a flake mixture having a selected amount of taggent flakes. The yield of taggent flake depends on factors such as the type of thin-film layers being processed, the nature of the frame, grating pattern, or symbol, and processing parameters.

[0048] For example, referring to Figs. 2A and 2B, if 10% of the surface of the roll substrate is embossed with a grating or symbol, then a yield of approximately 10% taggent flake having the grating pattern or symbol is expected. If 10% of the surface of the roll substrate is embossed with a diamond-shaped frame, then a yield of about 9% is expected for dielectric-metal-dielectric flake because of the 10% yield loss processing the patterned portion of the thin film stack into shaped flakes. Similarly, a yield of about 5% is expected for shaped all-dielectric flake because of the 50% yield loss processing the patterned portion of the thin film stack into shaped flakes.

[0049] Fig. 12 illustrates an embodiment in accordance with this invention wherein a flake has color shifting properties, magnetic properties, and bears a covert feature within the flake. Preferably the flake is also bordered by a frame to preserve its shape.

[0050] Turning now to Fig. 12, a pigment flake is shown having a magnetic layer sandwiched between two aluminium reflective layers. Each of the aluminium layers in addition to an absorber and dielectric layer provide color shifting layers on each side. Within the flake is stamped a covert "euro" symbol thereon which can be seen with suitable magnification. The embodiment shown in Fig. 13 utilizes a plurality of the flakes shown in Fig. 12 to provide a security features that are both covert and overt.

[0051] The covert and overt features are illustrated in the photograph which is a compilation of 3 photographs depicted by figure 13 where a large Euro symbol and a

map of the continents are shown on the upper right in the photograph and wherein a globe is shown on the upper left of the photograph printed by silk screen in the presence of magnetic fields to create different visual contrasts (rolling bar effect) in addition to the standard green to magenta color shifting.

[0052] In this instance the covert framed square flakes of about 30 microns in size bear a Euro symbol about 17 microns across.

[0053] Of course other optical designs, magnetic or non-magnetic, shapes or symbols can be created as desired. By using the layer structure of the flake in Fig. 12, optically variable, special magnetically alignable, and covert feature can be provided within a same security device.

[0054] By using frames in accordance with the teachings of this invention, preferential side benefits may be utilized. As the flakes are rectangular in shape, instead of being square, preferentially orientation of the symbols can be achieved, using magnetic shape anisotropy inherent of elongated flakes. Thus by providing a magnetic layer, for example of Ni, and ensuring that the flakes separate as elongate flakes due to the frames being designed in this manner, the flakes can be aligned as a function of their shape, and the symbols may have a preferential orientation, or be more likely to orient by this process.

[0055] Although preferred embodiments of the invention relate to pigment flakes, it is possible to use a non-symmetrical flake having features on one side such as optically variable features. In this instance, approximately half of the flakes when examined will show the covert feature and other optical features, and the other half will not appear the same due to a lack of symmetry within a flake. Notwithstanding, this may still offer a reasonable covert security feature which can be used to authenticate.

9% is expected for dielectric-metal-dielectric flake because of the 10% yield loss processing the patterned portion of the thin film stack into shaped flakes. Similarly, a yield of about 5% is expected for shaped all-dielectric flake because of the 50% yield loss processing the patterned portion of the thin film stack into shaped flakes.

[0056] While the invention has been described above in terms of various specific embodiments, an aspect of the invention which provides significant advantages will now be described.

[0057] For example an embodiment of this invention which offers significant advantages is the aspect of using frames or borders framing symbols or indicia framed by these borders on a substrate material used to form a coating upon.

[0058] Turning now to Fig. 7, a photograph is shown of sheet bearing a plurality of Euro symbols wherein each € symbol on the sheet has an embossed border around it. This is generally accomplished by embossing an organic substrate, such as a PET substrate with the framed € symbols, and subsequently coating the substrate with a

removable coating. Fig. 8 is a photograph of the flakes after separation from their backing or substrate. This photograph clearly shows most of the symbols to be intact with few cracks appearing into or through the

5 symbols. By using this invention, a very small portion of the flakes in the figure are broken in such a manner as to obscure the € symbol. However, what is shown is that the frames are not present along all sides of all flakes after the flakes break apart from the substrate they were deposited on. Some flakes have no borders and others may have one and up to four borders. However, this is understandable. Since a frame border separates the flake from its nearest neighbour, when the flakes separate the border generally remains attached to one flake 10 and not its adjacent flake on the other side of that frame border. However, the existence of the frame or border results in most of the flakes breaking upon frame lines, on one side of the frame or the other providing relatively uniform flakes with relatively straight edges. More often 15 than not, each flake bearing a symbol will have at least one border or frame segment attached to it after separating from the web or substrate it was deposited on.

[0059] Fig. 9 is a photograph of a plurality of Mg-Gn flakes bearing € symbols wherein the flakes have broken 20 randomly preserving some symbols and destroying others, due to stress cracks and resulting apparently random fracture lines as a result of the absence of frames. Fig. 9 illustrates stress cracks throughout the flakes causing the flakes to separate as a function of 25 these cracks. Furthermore, cracks continue to appear within flakes thereby obscuring symbols. The provision of frames in accordance with this invention does not entirely prevent stress cracks, however provides a means in which these cracks can be controlled to a greater extent, 30 so as to occur or be preferentially routed along the frame lines. In contrast to Fig. 9, the embodiment of this invention shown in conjunction with Figs. 7 and 8 offers a manner in which the flakes can be separated along 35 predetermined borders thereby preserving the shape and integrity of the symbols on the flakes to a much higher degree and generally does obscure the covert symbol within the flake.

[0060] The cracks that do appear in the non-framed 40 symbols appear and propagate in the more fragile, glass-like, dielectric material but are stopped and rerouted to 45 continue their propagation along the frame lines provided in the sheet of framed symbols shown in Fig. 7. The provision of frames produces the preferential rupture of the 50 flakes along frame lines. Most of the cracks observed in the flakes of Figure 8 do not go all the way through the total thickness of the flakes, but are stopped at the level of the more elastic metallic core (Al/Ni/Al) of the flakes 55 producing a shadowing effect detrimental to the readability of the originally embossed symbols.

[0061] The flakes in both Figs 8 and 9 are about 1300 nm or 1.3 microns in thickness and have a layer structure of 10nm Cr/ 480 nm MgF₂/ 80 nm Al/ 50 nm Ni/ 80 nm Al 480 nm MgF₂ / 10 nm Cr. Ni is present to provide the

magnetic layer for overt features.

[0062] Turning now to Fig. 10 is a photograph of a plurality of framed symbols within a greater number of flakes absent any covert symbols or frames where a ratio of framed symbols to other flakes is 1:10. There are two interesting aspects of this embodiment. On a first level of detection, one, equipped with a 100 x hand held microscope can detect the presence of covert flakes with a Euro symbol thereon, and furthermore, one can also quickly approximate that the ratio of covert to non-covert symbols is about 1:10. Yet still further, one can compare the ratio of square symbols to randomly shaped flakes to provide some measure of authentication. Therefore, shape, distribution, and identification of the symbols with-in framed shapes can be used to determine if the coating is authentic within some range of assurance.

[0063] Fig. 11 is a close-up detailed photograph of a plurality of μ symbols some of which are cracked through the symbols and some of which have plural symbols on a single flake; the great distribution in particle size is evidenced here in this photograph due to the absence of providing frames or borders about the symbols.

[0064] Fig. 12 illustrates an embodiment in accordance with this invention wherein a flake has color shifting properties, magnetic properties, and bears a covert feature within the flake. Preferably the flake is also bordered by a frame to preserve its shape.

[0065] Turning now to Fig. 12, a pigment flake is shown having a magnetic layer sandwiched between two aluminium reflective layers. Each of the aluminium layers in addition to an absorber and dielectric layer provide color shifting layers on each side. Within the flake is stamped a covert "euro" symbol thereon which can be seen with suitable magnification. The embodiment shown in Fig. 13 utilizes a plurality of the flakes shown in Fig. 12 to provide a security features that are both covert and overt.

[0066] The covert and overt features are illustrated in the photograph which is a compilation of 3 photographs depicted by figure 13 where a large Euro symbol and a map of the continents are shown on the upper right in the photograph and wherein a globe is shown on the upper left of the photograph printed by silk screen in the presence of magnetic fields to create different visual contrasts (rolling bar effect) in addition to the standard green to magenta color shifting.

[0067] In this instance the covert framed square flakes of about 30 microns in size bear a Euro symbol about 17 microns across.

[0068] Of course other optical designs, magnetic or non-magnetic, shapes or symbols can be created as desired. By using the layer structure of the flake in Fig. 12, optically variable, special magnetically alignable, and covert feature can be provided within a same security device.

[0069] By using frames in accordance with the teachings of this invention, particular shapes having preferential side benefits may be utilized. For example, if the flakes are rectangular in shape, instead of being square,

preferentially orientation of the symbols can be achieved, using magnetic shape anisotropy inherent of elongated flakes. Thus by providing a magnetic layer, for example of Ni, and ensuring that the flakes separate as elongate flakes due to the frames being designed this manner, the flakes can be aligned as a function of their shape, and the symbols may have a preferential orientation, or be more likely to orient by this process.

[0070] Thus, the embodiments described above illustrate the invention.

[0071] Although preferred embodiments of the invention relate to pigment flakes, it is possible to use a non-symmetrical flake having features on one side such as optically variable features. In this instance, approximately half of the flakes when examined will show the covert feature and other optical features, and the other half will not appear the same due to a lack of symmetry within a flake. Notwithstanding, this may still offer a reasonable covert security feature which can be used to authenticate.

Claims

25. 1. A plurality of pigment flakes having color shifting properties, magnetic properties, and bearing a covert feature within the flakes; comprising:
30. a magnetic layer sandwiched between two aluminium reflective layers, in addition to an absorber layer and dielectric layer to provide color shifting layers on each side;
35. wherein the shape of a flake of the plurality of pigment flakes is rectangular.
2. A plurality of pigment flakes as claimed in claim 1, wherein the magnetic layer comprises Ni.
3. A plurality of pigment flakes as claimed in claim 1, 40. wherein the plurality of pigment flakes are used to create an overt feature.
4. A plurality of pigment flakes as claimed in claim 1, 45. wherein the covert symbol is selected from one of a Euro symbol or a globe.
5. A plurality of pigment flakes as claimed in claim 1, 50. wherein the overt feature created with the plurality of pigment flakes comprises an optically variable effect.
6. A plurality of pigment flakes as claimed in claim 5, 55. wherein the optically variable effect is a visual contrast.
7. A plurality of pigment flakes as claimed in claim 1, wherein the rectangular shape of a flake achieves a preferential orientation of the flake and a preferential orientation of the covert symbol disposed on the

flake.

Patentansprüche

1. Eine Vielzahl von Pigmentplättchen, die Farbverschiebungseigenschaften, magnetische Eigenschaften aufweisen und ein verdecktes Merkmal innerhalb der Plättchen tragen; beinhaltend:

eine magnetische Schicht, die sandwichartig zwischen zwei Aluminium-Reflexionsschichten angeordnet ist, zusätzlich zu einer Absorberschicht und einer dielektrischen Schicht, um Farbverschiebungsschichten auf jeder Seite bereitzustellen;
wobei die Form eines Plättchens der Vielzahl von Pigmentplättchen rechteckig ist.

2. Vielzahl von Pigmentplättchen gemäß Anspruch 1, wobei die magnetische Schicht Ni beinhaltet.

3. Vielzahl von Pigmentplättchen gemäß Anspruch 1, wobei die Vielzahl von Pigmentplättchen verwendet wird, um ein offensichtliches Merkmal zu erzeugen.

4. Vielzahl von Pigmentplättchen gemäß Anspruch 1, wobei das verdeckte Symbol aus einem Euro-Symbol oder einer Weltkugel ausgewählt ist.

5. Vielzahl von Pigmentplättchen gemäß Anspruch 1, wobei das offensichtliche Merkmal, das mit der Vielzahl von Pigmentplättchen erzeugt wurde, einen optisch variablen Effekt beinhaltet.

6. Vielzahl von Pigmentplättchen gemäß Anspruch 5, wobei der optisch variable Effekt ein visueller Kontrast ist.

7. Vielzahl von Pigmentplättchen gemäß Anspruch 1, wobei die rechteckige Form eines Plättchens eine bevorzugte Ausrichtung des Plättchens und eine bevorzugte Ausrichtung des verdeckten Symbols, das auf dem Plättchen angeordnet ist, bewirkt.

Revendications

1. Une pluralité de paillettes de pigment présentant des propriétés de changement de couleur, des propriétés magnétiques, et portant un élément caché au sein des paillettes ; comprenant :

une couche magnétique prise en sandwich entre deux couches réfléchissantes en aluminium, en plus d'une couche d'absorbeur et d'une couche diélectrique afin de fournir des couches à changement de couleur sur chaque côté ;

où la forme d'une paillette de la pluralité de paillettes de pigment est rectangulaire.

2. Une pluralité de paillettes de pigment telle que revendiquée dans la revendication 1, où la couche magnétique comprend du Ni.

3. Une pluralité de paillettes de pigment telle que revendiquée dans la revendication 1, la pluralité de paillettes de pigments étant utilisées pour créer un élément patent.

4. Une pluralité de paillettes de pigment telle que revendiquée dans la revendication 1, où le symbole caché est sélectionné parmi soit un symbole de l'euro, soit un globe.

5. Une pluralité de paillettes de pigment telle que revendiquée dans la revendication 1, où l'élément patent créé avec la pluralité de paillettes de pigment comprend un effet optiquement variable.

6. Une pluralité de paillettes de pigment telle que revendiquée dans la revendication 5, où l'effet optiquement variable est un contraste visuel.

7. Une pluralité de paillettes de pigment telle que revendiquée dans la revendication 1, où la forme rectangulaire d'une paillette permet d'obtenir une orientation privilégiée de la paillette et une orientation privilégiée du symbole caché disposé sur la paillette.

35

45

50

55




FIG. 1




FIG. 2A




FIG. 2B




FIG. 3A




FIG. 3B




FIG. 3C




FIG. 3D




FIG. 4




FIG. 5




FIG. 6




FIG. 7




FIG. 8



FIG. 9



FIG. 10




FIG. 11



FIG. 12



Fig. 13

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- US 20020182383 A1 [0006]
- EP 1239307 A [0006]