




(86) **Date de dépôt PCT/PCT Filing Date:** 2013/04/15
(87) **Date publication PCT/PCT Publication Date:** 2013/10/31
(45) **Date de délivrance/Issue Date:** 2019/04/09
(85) **Entrée phase nationale/National Entry:** 2014/10/23
(86) **N° demande PCT/PCT Application No.:** JP 2013/061158
(87) **N° publication PCT/PCT Publication No.:** 2013/161599
(30) **Priorités/Priorities:** 2012/04/26 (JP2012-101614);
2012/11/28 (JP2012-260286)

(51) **Cl.Int./Int.Cl.** **C22B 3/08** (2006.01),
B01D 11/02 (2006.01), **B01F 15/02** (2006.01),
B01F 7/22 (2006.01), **B01J 3/02** (2006.01),
C22B 23/00 (2006.01)

(72) **Inventeurs/Inventors:**
MATSUBARA, SATOSHI, JP;
NAKAI, OSAMU, JP;
KYODA, YOJI, JP;
SAKAMOTO, TAKASHI, JP;
MAKI, KOICHIRO, JP;
KITAHARA, MASAKI, JP;
ISHIKAWA, HARUO, JP

(73) **Propriétaire/Owner:**

(54) **Titre : PROCEDE D'ADDITION D'UNE SUSPENSION DE MATERIAU DE DEPART ET D'ACIDE SULFURIQUE DANS UN AUTOCLAVE DANS UN PROCEDE DE LIXIVIATION ACIDE A HAUTE PRESSION ET AUTOCLAVE**
(54) **Title: METHOD FOR ADDING STARTING MATERIAL SLURRY AND SULFURIC ACID TO AUTOCLAVE IN HIGH PRESSURE ACID LEACHING PROCESS AND AUTOCLAVE**



(57) **Abbrégé/Abstract:**

In an autoclave 100 in a high pressure acid leaching process in which heated and pressurized starting material slurry and sulfuric acid are stirred by stirring machines 30A, 30B ... provided in each of compartments 20A, 20B ... in the autoclave partitioned into

(73) **Propriétaires(suite)/Owners(continued)**:SUMITOMO METAL MINING CO., LTD., JP

(74) **Agent**: SMART & BIGGAR

(57) **Abrégé(suite)/Abstract(continued)**:

plurality by partition walls 10A, 10B ... to proceed leaching, and slurry is transferred from a compartment on an upstream side to a compartment on a downstream side to sequentially proceed leaching, wherein starting material slurry supply tubes 41 and 42 having the starting material slurry discharge ports 41A and 42A alternately disposed and sulfuric acid supply tubes 51 and 52 having sulfuric acid discharge ports 51A and 52A are alternately disposed on a perimeter of stirring blades 31A of the stirring machine 30A provided in the compartment 20A at an upstream end, and the starting material slurry and sulfuric acid are added to the compartment 20A at the upstream end from the starting material slurry discharge ports 41A and 42A and the sulfuric acid discharge ports 51A and 52A positioned at positions higher than an uppermost part of the stirring blades 31A and lower than a contained liquid surface L. With this, mixing of the starting material slurry and sulfuric acid is promoted, and control values of concentrations of free sulfuric acid after discharge are reduced.

ABSTRACT

In an autoclave 100 in a high pressure acid leaching process in which heated and pressurized starting material slurry and sulfuric acid are stirred by stirring machines 30A, 30B ... provided in each of compartments 20A, 20B ... in the autoclave partitioned into plurality by partition walls 10A, 10B ... to proceed leaching, and slurry is transferred from a compartment on an upstream side to a compartment on a downstream side to sequentially proceed leaching, wherein starting material slurry supply tubes 41 and 42 having the starting material slurry discharge ports 41A and 42A alternately disposed and sulfuric acid supply tubes 51 and 52 having sulfuric acid discharge ports 51A and 52A are alternately disposed on a perimeter of stirring blades 31A of the stirring machine 30A provided in the compartment 20A at an upstream end, and the starting material slurry and sulfuric acid are added to the compartment 20A at the upstream end from the starting material slurry discharge ports 41A and 42A and the sulfuric acid discharge ports 51A and 52A positioned at positions higher than an uppermost part of the stirring blades 31A and lower than a contained liquid surface L. With this, mixing of the starting material slurry and sulfuric acid is promoted, and control values of concentrations of free sulfuric acid after discharge are reduced.

DESCRIPTION

METHOD FOR ADDING STARTING MATERIAL SLURRY AND SULFURIC ACID TO AUTOCLAVE IN HIGH PRESSURE ACID LEACHING PROCESS AND AUTOCLAVE

Field of the Invention

[0001]

This invention relates to a method for adding starting material slurry and sulfuric acid to an autoclave in a high pressure acid leaching process in which the starting material slurry is leached by the autoclave (high pressure reaction vessel) under high temperature and high pressure and the slurry after leaching are lowered to normal temperature and normal pressure in a flash vessel (temperature and pressure lowering vessel). The present application asserts priority rights based on JP Patent Application 2012-101614 filed in Japan on April 26, 2012 and JP Patent Application 2012-260286 filed in Japan on November 28, 2012.

[0002]

In recent years, with the development of a material with anti-corrosion characteristics under high temperature and high pressure, a High Pressure Acid Leach (HPAL) method using sulfuric acid has attracted attention as a wet smelting

method for nickel oxide ore. Unlike a dry smelting method, which is a conventional general smelting method for nickel oxide ore, this method does not include a dry process such as a reducing and drying process but includes consistent wet processes, and therefore is advantageous in energy and cost. That is, in the above-described high pressure acid leaching method, by controlling the oxidation-reaction potential and temperature of a leachate in a pressuring and leaching reaction vessel in a leaching process, iron as main impurities is fixed in leaching residues in a form of hematite (Fe_2O_3). Thus, nickel and cobalt can be selectively leached with respect to iron, which is an enormous merit.

[0003]

For example, as a wet smelting method for nickel oxide ore, a high pressure acid leaching method using an autoclave is adopted.

[0004]

The high pressure acid leaching method for obtaining nickel-cobalt mixed sulfide includes, for example, as depicted in Figure 19, a pre-processing process (1), a high pressure acid leaching process (2), a solid-liquid separating process (3), a neutralizing process (4), a dezincifying process (5), and a sulfurizing process (6), and a detoxifying process (7) (for example, refer to PTL 1).

[0005]

In the pre-processing process (1), nickel oxide ore is crushed and classified by using a pulverizing facility and a sorting facility to prepare starting material

slurry with a predetermined slurry concentration including ores 2 mm or less. The starting material slurry is supplied to the next high pressure acid leaching process (2).

[0006]

In the high pressure acid leaching process (2), the temperature and pressure of the starting material slurry obtained in the pre-processing process (1) are increased by a preheater (temperature and pressure increasing facility) in a stepwise manner, and the resulting starting material slurry is then supplied to the autoclave. In the autoclave, sulfuric acid with its temperature and pressure increased in a similar manner is added to the starting material slurry, stirring is performed at 220 degrees Celsius to 280 degrees Celsius for high pressure acid leaching of valuable metal, and the temperature and pressure of the obtained leached slurry are lowered to normal temperature and normal pressure in a flash vessel.

[0007]

In the solid-liquid separating process (3), the leached slurry of the valuable metal obtained in the leaching process (2) is subjected to solid-liquid separation to obtain a leachate containing nickel and cobalt as valuable metals (crude nickel sulfate aqueous solution) and leaching residues.

[0008]

In the neutralizing process (4), the leachate obtained in the solid-liquid separating process (3) is neutralized.

[0009]

In the dezincifying process (5), hydrogen sulfide gas is added to the leachate neutralized in the neutralizing process (4) to precipitate and remove zinc as zinc sulfide.

[0010]

In the sulfurizing process (6), hydrogen sulfide gas is added to the dezincified finish solution obtained in the dezincifying process (5) to obtain a nickel-cobalt complex sulfide and nickel barren solution.

[0011]

In the detoxifying process (7), the leaching residues generated in the solid-liquid separating process (3) and the nickel barren solution generated in the sulfurizing process (6) are detoxified.

[0012]

Here, in the autoclave in the high pressure acid leaching process (2), the heated and pressurized starting material slurry and sulfuric acid, are supplied to a first compartment in the autoclave partitioned into plurality by partition walls, and are stirred by a stirring machine provided to the first compartment to proceed leaching. The slurry is transferred to a second compartment onward by overflow, thereby further promoting leaching sequentially in a similar method.

[0013]

Meanwhile, to supply the above-described starting material slurry and

sulfuric acid to the autoclave, expensive piping resistant to pressure and corrosion is required, and many valves for operation are also provided. In view of reduction in cost and in order to ensure favorable operability, the shortest and simple arrangement is generally adopted.

[0014]

For example, the structure of the first compartment in the conventional autoclave is schematically depicted in Figure 20A, Figure 20B, and Figure 20C as a cross-section, a longitudinal section, and a side section, respectively. In a compartment 210 of an autoclave 200, stirring blades 231 of a stirring machine 230 is installed at the center, and starting material slurry addition pipes 241 and 242 and sulfuric acid addition pipes 251 and 252 are disposed at positions closest to both sides of an autoclave body when viewed in the cross-section of Figure 20A.

[0015]

As such, by setting positions closest to the both sides of the autoclave body as adding positions, pipes to these positions can be shortened, and the pipes do not cross or overlap with each other. Therefore, easy recognition by an operator and favorable operability can be ensured.

[0016]

However, even with many partitions, the leaching ratio in the autoclave is not 100%, and excessive sulfuric acid more than appropriate to valuable metals in the starting material slurry is fed into the autoclave. The sulfuric acid amount of this

excessive portion is controlled with the amount of free sulfuric acid (unreacted sulfuric acid remaining in the above-described leachate) to maintain a predetermined leaching ratio in operation (normally 90% to 95%), and normally has a value on the order of 50 g/L to 55 g/L.

[0017]

Also, since the leachate obtained in the solid-liquid separating process (3) is neutralized in the next neutralizing process (4), free sulfuric acid is neutralized without contributing to leaching, which is wasteful. Moreover, since cost of a neutralizer for neutralization is also required, the amount of free sulfuric acid is desired to be decreased no matter to how small a degree. Under present circumstances, however, the above-described amount of free sulfuric acid has to be used to maintain a predetermined leaching ratio.

[0018]

For example, a technique has been suggested in which an optimum temperature condition is maintained in the first compartment in the autoclave by a contrivance, such as maintaining reactive slurry with a capacity larger by 50% to 200% than the capacity of reactive slurry in any compartment on a downstream side, without external heating or cooling (for example, refer to PTL 2).

[0019]

A technique has also been suggested in which sulfuric acid is regenerated by performing successive two or more leaching stages in a composite manner

including a normal pressure leaching stage and a pressurized leaching stage to reduce a great deal of the added sulfuric acid amount (for example, refer to PTL 3).

[0020]

However, since the disclosed technique of the above-described PTL 2 is targeted for a sulfide material and the disclosed technique of PTL 3 requires a normal pressure leaching process, these techniques cannot be applied to the above-described problems.

Prior-Art Documents

Patent Documents

[0021]

PTL 1: Japanese Patent Application Laid-Open No. 2005-350766

PTL 2: Japanese Examined Patent Publication No. 07-084623

PTL 3: Japanese Translation of PCT International Application

Publication No. 2009-515044

Summary of the Invention

[0022]

In view of the conventional problems as described above, an object of the present invention is to provide a method for adding starting material slurry and sulfuric acid to an autoclave capable of promoting mixing of the starting material

slurry and sulfuric acid and reducing a control value of concentration of free sulfuric acid after discharge in a high pressure acid leaching process.

[0023]

Other objects of the present invention and specific advantages obtained by the present invention will become more apparent from description of an embodiment, which will be described below.

[0024]

To achieve the above-described object, the inventors have studied a mixing state of starting material slurry and sulfuric acid in an autoclave for use in high pressure acid leaching of nickel oxide ore without sticking to only piping cost or operability, and thereby found specific effective adding positions and completed the present invention.

[0025]

That is, by defining positions of adding starting material slurry and sulfuric acid, a leaching ratio similar to a conventional one can be maintained even a free acid amount, which is a control value of autoclave finish solution, is reduced.

[0026]

The present invention provides a method for adding starting material slurry and sulfuric acid to an autoclave in a high pressure acid leaching process in which the starting material slurry and the sulfuric acid are heated and pressurized and stirred by a stirring machine provided in each of compartments in the autoclave

partitioned into plurality by partition walls to proceed leaching, and slurry is transferred from a compartment on an upstream side to a compartment on a downstream side to sequentially proceed leaching, wherein via starting material slurry supply tubes having the starting material slurry discharge ports and sulfuric acid supply tubes having sulfuric acid discharge ports alternately disposed on a perimeter of stirring blades of the stirring machine provided in a compartment at an upstream end of the autoclave, the starting material slurry and the sulfuric acid are added to the compartment at the upstream end from the starting material slurry discharge ports and the sulfuric acid discharge ports positioned at positions higher than an uppermost part of the stirring blades and lower than a contained liquid surface.

[0027]

Also, the present invention provides an autoclave in a high pressure acid leaching process in which heated and pressurized starting material slurry and sulfuric acid are stirred by a stirring machine provided in each of compartments in the autoclave partitioned into plurality by partition walls to proceed leaching, and slurry is transferred from a compartment on an upstream side to a compartment on a downstream side to sequentially proceed leaching, wherein starting material slurry supply tubes having the starting material slurry discharge ports and sulfuric acid supply tubes having sulfuric acid discharge ports are alternately disposed on a perimeter of stirring blades of the stirring machine provided in a compartment at an

upstream end, and the starting material slurry discharge ports and the sulfuric acid discharge ports are positioned at positions higher than an uppermost part of the stirring blades and lower than a contained liquid surface, and via the starting material slurry supply tubes and the sulfuric acid supply tubes, the starting material slurry and the sulfuric acid are added to the compartment at the upstream end from the starting material slurry discharge ports and the sulfuric acid discharge ports alternately positioned on the perimeter of the stirring blades and at positions higher than the uppermost part of the stirring blades of the stirring machine and lower than the contained liquid surface.

[0028]

In the present invention, the starting material slurry and the sulfuric acid can be added to the compartment at the upstream end from the starting material slurry discharge ports and the sulfuric acid discharge ports, with the starting material slurry discharge ports and the sulfuric acid discharge ports being positioned at planar positions, the starting material slurry discharge ports being positioned in a range of a distance of $0.25D$ from, as centers, apex positions at both ends of a bottom side of a regular triangle with a height being any diameter D of a circle formed by tips of the stirring blades, the regular triangle moved by distance of $0D$ to $0.5D$ so that the regular triangle has a midpoint of the bottom side positioned in a length direction of the bottom side of the regular triangle and on a downstream side of a rotating direction of the stirring blades, and the sulfuric acid discharge ports

being positioned in a range of a distance of $0.25 D$ of the diameter from, as centers, the midpoint position of the bottom side and the remaining apex position of the regular triangle.

[0029]

The length direction of the bottom side of the regular triangle can be, for example, parallel to a side wall of the autoclave.

[0029a]

There is further provided a method for adding starting material slurry and sulfuric acid to an autoclave in a high pressure acid leaching process in which heated and pressurized starting material slurry and the sulfuric acid are stirred by a stirring machine provided in each of compartments in the autoclave partitioned into plurality by partition walls to proceed leaching of the starting material slurry, and slurry is transferred from a compartment on an upstream side to a compartment on a downstream side to sequentially proceed leaching, wherein via starting material slurry supply tubes having starting material slurry discharge ports and sulfuric acid supply tubes having sulfuric acid discharge ports alternately disposed in a circumference around stirring blades of the stirring machine provided in a compartment at an upstream end of the autoclave, the starting material slurry and the sulfuric acid are added to the compartment at the upstream end from the starting material slurry discharge ports and the sulfuric acid discharge ports positioned at positions higher than an uppermost part of the stirring blades and lower than a contained liquid surface, wherein the starting material slurry and the sulfuric acid are added to the compartment at the upstream end from the starting material slurry discharge ports and the sulfuric acid discharge ports, with the starting material slurry discharge ports and the sulfuric acid discharge ports being positioned at planar positions, the starting material slurry discharge ports being positioned in a range of a distance of $0.25D$ from, as centers, apex positions at both ends of a bottom side of a regular triangle with a height being any diameter D of a circle formed by tips of the stirring blades, the regular triangle moved by a distance of $0D$ to $0.5D$ so that the regular triangle has a midpoint of the bottom side positioned in a length direction of the bottom side of the regular triangle and on a downstream side of a rotating direction of the stirring blades, and the sulfuric acid discharge

ports being positioned in a range of a distance of 0.25 of the diameter from, as centers, the midpoint position of the bottom side and the remaining apex position of the regular triangle.

[0029b]

There is further provided an autoclave in a high pressure acid leaching process in which heated and pressurized starting material slurry and sulfuric acid are stirred by a stirring machine provided in each of compartments in the autoclave partitioned into plurality by partition walls to proceed leaching of the starting material slurry, and slurry is transferred from a compartment on an upstream side to a compartment on a downstream side to sequentially proceed leaching of the starting material slurry, wherein starting material slurry supply tubes having starting material slurry discharge ports and sulfuric acid supply tubes having sulfuric acid discharge ports are alternately disposed in a circumference around stirring blades of the stirring machine provided in a compartment at an upstream end, and the starting material slurry discharge ports and the sulfuric acid discharge ports are positioned at positions higher than an uppermost part of the stirring blades and lower than a contained liquid surface, and via the starting material slurry supply tubes and the sulfuric acid supply tubes, the starting material slurry and the sulfuric acid are added to the compartment at the upstream end from the starting material slurry discharge ports and the sulfuric acid discharge ports alternately positioned in a circumference around the stirring blades and at positions higher than the uppermost part of the stirring blades of the stirring machine and lower than the contained liquid surface, wherein with the starting material slurry discharge ports and the sulfuric acid discharge ports being positioned at planar positions, the starting material slurry discharge ports are positioned in a range of a distance of $0.25D$ from, as centers, apex positions at both ends of a bottom side of a regular triangle with a height being any diameter of a circle formed by tips of the stirring blades, the regular triangle moved by a distance of $0D$ to $0.5D$ so that the regular triangle has a midpoint of the bottom side positioned in a length direction of the bottom side of the regular triangle and on a downstream side of a rotating direction of the stirring blades, and the sulfuric acid discharge ports are positioned in a range of a distance of $0.25 D$ from, as centers, the midpoint position of the bottom side and the remaining apex position of the regular triangle.

Effects of Invention

[0030]

According to the present invention, it is possible to provide a method for adding starting material slurry and sulfuric acid to an autoclave capable of promoting mixing of the starting material slurry and sulfuric acid and reducing a control value of concentration of free sulfuric acid after discharge in a high pressure acid leaching process, and also possible to provide the autoclave.

Brief Description of Drawings

[0031]

Figure 1 depicts an example of structure of main parts of an autoclave to which the present invention is applied, in which Figure 1A is a plan view schematically depicting the inner structure of the autoclave as being horizontally cut, Figure 1B is a side view schematically depicting the inner structure of the

autoclave as being vertically cut, and Figure 1C is a front view schematically depicting the inner structure of the autoclave as being vertically cut.

Figure 2 schematically depicts a procedure of determining positions of starting material slurry discharge ports and acid discharge ports in the above-described autoclave, in which Figure 2A, Figure 2B, Figure 2C, Figure 2D schematically depict each position in the course of the procedure.

Figure 3 is a schematic view of stirring simulation results regarding a conventional autoclave before improvement.

Figure 4 is a schematic view of stirring simulation results regarding an autoclave to which the present invention is applied.

Figure 5 depicts simulation models of arrangement of slurry supply tubes, in which Figure 5A is a plan view of a model A in which two slurry supply tubes are arranged along a side wall and Figure 5B is a plan view of a model B in which two slurry supply tubes are arranged along a direction orthogonal to the side wall.

Figure 6 depicts results of simulations indicated by flow lines which visualize flows created only by rotational force of stirring blades in the above-described autoclave, in which Figure 6A depicts a state of flows in a compartment at an upstream end viewed from the oblique above and Figure 6B depicts the state viewed from straight above.

Figure 7 depicts results of a simulation indicated by flow lines which visualize flows in an autoclave provided with slurry supply tubes, in which Figure

7A depicts a state of flows in the compartment at the upstream end viewed from the oblique above and Figure 7B depicts the state viewed from straight above.

Figure 8 depicts results of a simulation indicated by flow lines which visualize flows of slurry in the compartment at the upstream end, in which Figure 8A depicts a state in which slurry is let flow from a slurry supply tube on a partition wall side and Figure 8B depicts a state in which slurry is let flow from a slurry supply tube on a hemisphere side.

Figure 9 is a schematic view of results of a simulation indicated by flow lines which visualize flows of slurry in the compartment at the upstream end.

Figure 10 depicts residence time distribution curves of slurry in the above-described models A and B, in which Figure 10A depicts results obtained by calculating residence time distribution curves of slurry in the above-described model A, and Figure 10B depicts results obtained by calculating residence time distribution curves of slurry in the above-described model B.

Figure 11 depicts residence time distribution curves of sulfuric acid in the above-described models A and B, in which Figure 11A depicts results obtained by calculating residence time distribution curves of sulfuric acid in the above-described model A, and Figure 11B depicts results obtained by calculating residence time distribution curves of sulfuric acid in the above-described model B.

Figure 12 depicts results obtained by performing a simulation indicated by flow lines which visualize flows in the compartment at the upstream end and

comparing residence times of slurry near the partition wall, in which Figure 12A depicts residence times of slurry near the partition wall of the above-described model A and Figure 12B depicts residence times of slurry near the partition wall of the above-described model B.

Figure 13 is a vector diagram obtained as a result of a simulation of flows at a section where the sulfuric acid supply tube is installed.

Figure 14 depicts results of a simulation in which flow lines near the partition wall are colored with sulfuric acid concentrations for comparison, in which Figure 14A depicts sulfuric acid concentrations near the partition wall in the above-described model A and Figure 14B depicts sulfuric acid concentrations near the partition wall in the above-described model B.

Figure 15 depicts results of simulations of flows of sulfuric acid in a model C including long sulfuric acid supply tubes and in a model D including short sulfuric acid supply tubes, with the number of revolutions of stirring blades being set at 60.5 rpm, in which Figure 15A depicts flows of sulfuric acid in the model C and Figure 15B depicts flows of sulfuric acid in the model D.

Figure 16 is a diagram depicting results of a simulation of flows of sulfuric acid in a model E including sulfuric acid supply tubes slightly longer than the short sulfuric acid supply tubes, with the number of revolutions of the stirring blades being set at 60.5 rpm.

Figure 17 depicts temperature contours of baffles and stirring blades

depending on the length of sulfuric acid supply tubes, in which Figure 17A depicts temperature contours of the baffles and the stirring blades with the number of revolutions of the stirring blades being set at 42.4 rpm in the model C and Figure 17B depicts temperature contours of the baffles and the stirring blades with the number of revolutions of the stirring blades being set at 42.4 rpm in the model D.

Figure 18 is a diagram depicting temperature contours of the baffles and the stirring blades with the number of revolutions of the stirring blades being set at 60.5 rpm in the model E including the sulfuric acid tubes slightly longer than the short sulfuric acid supply tubes.

Figure 19 is a process diagram depicting a procedure of leaching nickel and cobalt by a high pressure acid leaching method for nickel oxide ore.

Figure 20 depicts a schematic structure of a general autoclave, in which Figure 20A is a plan view schematically depicting the inner structure of the autoclave as being horizontally cut, Figure 20B is a side view schematically depicting the inner structure of the autoclave as being vertically cut, and Figure 20C is a front view schematically depicting the inner structure of the autoclave as being vertically cut.

Detailed Description of the Invention

[0032]

An embodiment of the present invention is described in detail below with

reference to the drawings.

[0033]

<Structure of Autoclave>

The present invention is implemented by an autoclave 100 with a structure depicted in Figure 1, for example.

[0034]

Figure 1 depicts the structure of main parts of the autoclave 100, in which Figure 1A is a plan view schematically depicting the inner structure of the autoclave 100 as being horizontally cut, Figure 1B is a side view schematically depicting the inner structure of the autoclave 100 as being vertically cut, and Figure 1C is a front view schematically depicting the inner structure of the autoclave 100 as being vertically cut.

[0035]

This autoclave 100 is an autoclave in a high pressure acid leaching process in which heated and pressurized starting material slurry and sulfuric acid are stirred to perform high temperature pressurized acid leaching of valuable metal, a plurality of compartments 20A, 20B ... partitioned by partition walls 10A, 10B, ... are provided in the autoclave, and stirring machines 30A, 30B ... are installed in each of the compartments 20A, 20B, ... In addition, in this autoclave 100, with stirring by the stirring machines 30A, 30B ... provided to the respective compartments 20A, 20B ... partitioned by partition walls 10A, 10B, leaching is proceeded to

transfer slurry from a compartment on an upstream side to a compartment on a downstream side, and thereby leaching is sequentially proceeded.

[0036]

Here, the compartment 20A at an upstream end has a shape as coupling a hemisphere and a cylinder, and the compartment 20B in the middle is in a cylindrical shape.

[0037]

In this autoclave 100, two starting material slurry supply tubes 41 and 42 having starting material slurry discharge ports 41A and 42A, respectively, and two sulfuric acid supply tubes 51 and 52 having sulfuric acid discharge ports 51A and 52A, respectively, are alternately disposed on the perimeter of stirring blades 31A of the stirring machine 30A provided in the compartment 20A at the upstream end. In addition, the above-described starting material slurry discharge ports 41A and 42A and sulfuric acid discharge ports 51A and 52A are positioned higher than an uppermost part of the above-described stirring blades 31A and lower than a contained liquid surface L.

[0038]

Note that each pipe is inserted from above into the inside of the autoclave 100, and has a vapor pipe at any position for maintaining temperature. Also, in this autoclave 100, the stirring blades 31A provided in the compartment 20A at the upstream end rotate in a clockwise direction to form a downward flow.

[0039]

Here, in this autoclave 100, the positions of the above-described starting material slurry discharge ports 41A and 42A and sulfuric acid discharge ports 51A and 52A are determined as depicted in Figure 2, for example.

[0040]

That is, at planar positions at height positions of the above-described starting material slurry discharge ports 41A and 42A and sulfuric acid discharge ports 51A and 52A, apex positions P1, P2, and P3 and a midpoint position P4 of a bottom side of a regular triangle T with a height being any diameter D of a circle formed by tips of the above-described stirring blades 31A as depicted in Figure 2A are determined, the regular triangle T moved by a distance of 0 to 0.5D so that the regular triangle T has the above-described midpoint positioned in a length direction of the bottom side and on a downstream side of a rotating direction of the above-described stirring blades 31A as depicted in Figure 2B. The above-described starting material slurry discharge ports 41A and 42A are positioned in ranges S1 and S2 a distance of 0.25D away from the apex positions P1 and P2, respectively, at both ends of the above-described bottom side as centers, as depicted in Figure 2C. In addition, the above-described sulfuric acid discharge ports 51A and 52A are positioned in ranges S3 and S4 a distance of 0.25D away from the remaining apex position P3 and the midpoint position P4, respectively, at the above-described bottom side of the above-described regular triangle T as centers, as depicted in Figure 2D.

[0041]

Also, the above-described starting material slurry discharge ports 41A and 42A and sulfuric acid discharge ports 51A and 52A are positioned higher than the uppermost part of the above-described stirring blades 31A and lower than the contained liquid surface L.

[0042]

In addition, in this this autoclave 100, starting material slurry and sulfuric acid are added to the above-described compartment 20A at the upstream end via two starting material slurry supply tubes 41 and 42 having the starting material slurry discharge ports 41A and 42A and two sulfuric acid sulfuric supply tubes 51 and 52 having sulfuric acid discharge ports 51A and 52A, these tubes alternately disposed on the perimeter of the stirring blades 31A of the stirring machine 31 provided in the compartment 20A at the upstream end.

[0043]

For the above-structured autoclave 100, a simulation of stirring was performed. As a result, it can be found that while slurry high concentration portions a1 and a2 and sulfuric acid high concentration portions b1 and b2 were widely present in a conventional autoclave before improvement as depicted in Figure 3 and the autoclave was in a diffusion failure state, the slurry high concentration portions a1 and a2 and the sulfuric acid high concentration portions b1 and b2 were small and effectively diffused in the autoclave 100 to which the

present invention is applied, as the simulation result is depicted in Figure 4.

[0044]

<Study of Installation Positions of Starting Material Slurry Supply Tubes and Sulfuric Acid Supply Tubes>

Here, to perform a stable autoclave operation, the installation positions of the starting material slurry supply tubes 41 and 42 having the starting material slurry discharge ports 41A and 42A and the sulfuric acid supply tubes 51 and 52 having the sulfuric acid discharge ports 51A and 52A in the above-described autoclave 100 are determined based on the following simulation so as to satisfy three conditions of:

- (1) maintaining favorable mixture properties;
- (2) ensuring a constant residence time for leaching reaction in a reaction tank; and
- (3) avoiding damage to facilities due to acid.

Specific description is as follows.

[0045]

(Regarding Installation Position of Starting Material Slurry Supply Tube)

In the above-structured autoclave 100, for sufficient advancement of a leaching reaction, maintaining favorable mixing and predetermined residence time are required in the compartment 20A at the upstream end in a shape obtained by coupling a hemisphere and a cylinder. Also, since the flow rate of slurry is larger

than those of sulfuric acid or vapor, kinetic energy of the flow of slurry by rotational force of the stirring blades 31A determines a tendency of the flows in the autoclave 100.

[0046]

Thus, firstly, to maintain favorable mixing, flows in the compartment 20A at the upstream end in the autoclave 100 were analyzed by simulations regarding a model A in which the two slurry supply tubes 41 and 42 are arranged along the side wall as depicted in Figure 5A and a model B in which two slurry supply tubes 43 and 44 are arranged along a direction orthogonal to the side wall as depicted in Figure 5B.

[0047]

First, Figure 6A and Figure 6B depict results of simulations indicated by flow lines which visualize flows created only by rotational force of the stirring blades, with all slurry supply tubes eliminated. As depicted in Figure 6, two vertically rotating axial flows F1 and F2 are formed, and a plane S formed by a downward flow is positioned slightly close to a hemisphere side by the rotation axis of the stirring blades 31A.

[0048]

By adding slurry supply tubes to this model, simulations indicated by flow lines which visualize flows in the compartment 20A were performed. The results are depicted in Figure 7A and Figure 7B. As depicted in Figure 7, it can be found

that, with a baffle-like effect of the pipes, the plane S formed by a downward flow is moved near a plane including the rotation axis of the stirring blades 31A.

[0049]

Therefore, from this, it is required to stabilize the two large axial flows F1 and F2 occurring on the hemisphere side and a partition wall side.

[0050]

The above-described Figure 6A and Figure 6B and Figure 7A and Figure 7B depict a state of flows in the compartment 20A at the upstream end viewed from the oblique above (A) and the state viewed from straight above (B). Also, a tendency of the flows of slurry is substantially determined by the positions where the slurry supply tubes are arranged.

[0051]

Next, for the model A depicted in Figure 5A described above, a simulation was performed as indicated by a flow line which visualizes a flow of slurry in the compartment 20A. The results are depicted in Figure 8A and Figure 8B.

[0052]

As depicted in Figure 8A, in the case of the model A, when slurry is let flow from the slurry supply tube 41 on the partition wall 10A side, a large flow passing through a space between the stirring blades 31A and baffles and heading for a portion near a baffle 62 of the hemisphere part. Also, as depicted in Figure 8B, the slurry supply tube 42 on the hemisphere side creates a rotational flow in the

hemisphere portion. Slurry let flow from this slurry supply tube 42 appears to stay in the hemisphere part, and the strong axial flow F2 is present on its perimeter as depicted in Figure 6A and Figure 6B described above. Therefore, stable flows of slurry can be obtained by adjusting the position of the slurry supply tube 42.

[0053]

By contrast, the results of a simulation indicated by flow lines which visualize flows in the compartment 20A for the model B depicted in Figure 5B described above are depicted in Figure 9. As depicted in Figure 9, a slurry supply tube 44 interposed on an opposite side of the side wall where the above-described slurry supply tubes 41 and 42 creates a flow of slurry heading for the partition wall 10A side. Slurry let flow from this slurry supply tube 44 becomes a flow that approaches and then directly collide with the partition wall 10A, thereby leading to a short path of slurry. Therefore, it is not preferable to arrange the slurry supply pipe 44 as in the model B.

[0054]

Next, in the autoclave 100 structured as described above, a simulation was performed as follows regarding a residence time in the compartment 20A at the upstream end required for sufficient advancement of a leaching reaction.

[0055]

That is, as for the models A and B depicted in Figure 5A and Figure 5B described above, a colored fluid for a predetermined time (here, one second) was let

flow, and residence time distribution curves obtained by plotting concentrations of the fluid which reached a tank exit were calculated. The calculation results are depicted in Figure 10A, Figure 10B, Figure 11A, and Figure 11B.

[0056]

Note that Figure 10A depicts a residence time distribution from an entrance to an exit of slurry in the model A. In this Figure 10A, a distribution curve AP1 indicates logical values of a residence time distribution of slurry predicted in a complete mixing model, a distribution curve AB1 indicates a residence time distribution of slurry when the sulfuric acid supply tubes are short, and a distribution curve AG1 indicates a residence time distribution of slurry when the sulfuric acid supply tubes are long. Also, Figure 10B depicts a residence time distribution from the entrance to the exit of slurry in the model B by using a distribution curve BB1. Note that a distribution curve BP1 indicates logical values of a residence time distribution predicted in the complete mixing model.

[0057]

Also, Figure 11A depicts a residence time distribution from an entrance to an exit of sulfuric acid in the model A. In this Figure 11A, a distribution curve AP2 indicates logical values of a residence time distribution of sulfuric acid predicted in the complete mixing model, a distribution curve AB2 indicates a residence time distribution of sulfuric acid when the sulfuric acid supply tubes are short, and a distribution curve AG2 indicates a residence time distribution of sulfuric acid when

the sulfuric acid supply tubes are long. Also, Figure 11B depicts a residence time distribution from the entrance to the exit of sulfuric acid in the model B by using a distribution curve BB2. Note that a distribution curve BP2 indicates logical values of a residence time distribution predicted in the complete mixing model.

[0058]

As depicted in Figure 10A and Figure 10B and Figure 11A and Figure 11B, compared with the logical values of the residence time distributions predicted in the complete mixing model indicated by the distribution curves AP1, BP1, AP2, and BP2, high concentration is observed in both of slurry and sulfuric acid in an early time zone (10 seconds to 30 seconds) in the model B. By contrast, in the model A, a concentration higher than the above-described logical values is not observed in an early time zone.

[0059]

Also, as for the models A and B, simulations indicated by flow lines which visualize flows in the compartment 20A were performed, the flow lines were colored according to elapsed time of the flows of slurry, and residence times of slurry near the partition wall were compared. The results are depicted in Figure 12A and Figure 12B.

[0060]

Note that Figure 12A depicts residence times of slurry near the partition wall 10A of the model A. Also, Figure 12B depicts residence times of slurry near the

partition wall 10A of the model B. Furthermore, in Figure 12A and Figure 12B, red r indicates a residence time equal to or shorter than fifteen seconds, and blue b indicates a residence time equal to or longer than thirty seconds.

[0061]

As depicted in Figure 12A and Figure 12B, it can be found that Figure 12B has a red portion larger than that of Figure 12A, meaning that there is a relatively lot of slurry approaching a partition wall 10A portion fifteen seconds or shorter in the model B.

[0062]

Also from these simulation results, it can be found the arrangement of the slurry supply tube 44 in the model B where there is a possibility that slurry directly flows near the partition wall is not preferable.

[0063]

Furthermore, Figure 13 depicts a vector diagram obtained as a result of a simulation of flows at a cross-section where the sulfuric acid supply tube 51 is installed.

[0064]

As depicted in the vector diagram of Figure 13, it can be found that while a small swirl crosses each other in an area AR1 near the opening, a stable flow toward the direction of the partition wall 10A is viewed in an upper area AR2 of the opening.

[0065]

(Regarding Installation Positions of Sulfuric Acid Supply Tubes)

Next, the installation positions of a sulfuric acid supply tubes is studied. For this study, in view of the possibility of damage to the partition wall 10A by sulfuric acid supplied from the sulfuric acid supply tubes, a simulation was performed for the above-described models A and B in which flow lines near the partition wall 10A were colored by sulfuric acid concentration for comparison.

[0066]

The simulation results are depicted in Figure 14A and Figure 14B. Note that Figure 14A depicts sulfuric acid concentrations near the partition wall 10A in the above-described model A. Figure 14B depicts sulfuric acid concentrations near the partition wall 10A in the above-described model B.

[0067]

As depicted in Figure 14A and Figure 14B, although there is a slight difference in concentration, it has been revealed from the results of this simulation that the model A is superior to the model B regarding the installation position of the sulfuric acid supply tube.

[0068]

Thus, in the above-described autoclave 100, with the above-described starting material slurry discharge ports 41A and 42A arranged as in the above-described model B and the sulfuric acid discharge ports 51A and 52A

arranged as in the model A, these ports are alternately disposed on the perimeter of the stirring blades 31A of the stirring machine provided to the above-described compartment 20A, thereby causing starting material slurry and sulfuric acid to be alternately drawn toward the stirring blades 31A to increase the possibility of a contact and proceed mixing more efficiently than ever.

[0069]

(Regarding Length of Sulfuric Acid Supply Tubes)

Next, the length of the sulfuric acid supply tubes is studied. First, simulations of flows of sulfuric acid were performed in a model C including long sulfuric acid supply tubes 51L and 52L and in a model D including short sulfuric acid supply tubes 51S and 52S, with the number of revolutions of the stirring blades 31A being set at 60.5 rpm. The results are depicted in Figure 15A and Figure 15B.

[0070]

As depicted in Figure 15A, it has been revealed that sulfuric acid stays in a swirl shape near the exits of the sulfuric acid supply tubes 51L and 52L in the model C with the long sulfuric acid supply tubes 51L and 52L and sulfuric acid smoothly flows in the direction of the partition wall 10A in the model D with the short sulfuric acid supply tubes 51S and 52S as depicted in Figure 15B.

[0071]

And, it has been revealed that flows of sulfuric acid in a model E including the sulfuric acid supply tubes 51 and 52 slightly longer than the short sulfuric acid

supply tubes 51S and 51S can be improved as depicted in Figure 16 by arranging the sulfuric acid discharge ports 51A and 52A of the sulfuric acid supply tubes 51 and 52 at slurry-stable downstream positions.

[0072]

Also, it has been conventionally confirmed that the flow of sulfuric acid moves as approaching a baffle or a tank wall due to fluctuations in the flow of sulfuric acid with the rotation of the stirring blades 31A. Therefore, influences of fluctuations in the flow of sulfuric acid were verified. However, since a non-stationary analysis required to reproducing fluctuations in the flow takes extremely long time, increases in temperature at a relevant portion were observed with stationary calculation as approximate calculation.

[0073]

While there were no problems in a normal operation state, when stability with respect to fluctuations in flow rate conditions and operation conditions were investigated, a decrease was observed in which a baffle temperature was increased in the model D including short sulfuric acid supply tubes 51S and 52S when the number of revolutions of the stirring blades 31A was small.

[0074]

Here, temperature contours of the baffles and the stirring blades 31A depending on the length of the sulfuric acid supply tubes 51 and 52 are depicted in Figure 17A, Figure 17B, and Figure 18. Note that Figure 17A depicts temperature

contours of the baffles 61 to 63 and the stirring blades 31A with the number of revolutions of the stirring blades 31A being set at 42.4 rpm in the model C including the long sulfuric acid supply tubes 51L and 52L. Also, Figure 17B depicts temperature contours of the baffles 61 to 63 and the stirring blades 31A with the number of revolutions of the stirring blades 31A being set at 42.4 rpm in the model D including the short sulfuric acid supply tubes 51S and 52S.

[0075]

As depicted in Figure 17A and Figure 17B, in the model D with the short sulfuric acid supply tubes 51S and 52S described above, even when the number of revolution of the stirring blades 31A is 60.5 rpm, part of sulfuric acid is directly drawn to an upper part of the stirring blades, and a slight increase in temperature is observed at the baffle of the hemisphere part. Therefore, as for the model E with the sulfuric acid supply tubes 51 and 52 slightly longer than the short sulfuric acid supply tubes 51S and 52S so that the supply ports of sulfuric acid were positioned near the upper surface of the upper part of the stirring blades, baffle temperatures of the hemisphere part with the number of revolutions of the stirring blades being set at 60.5 rpm were checked. As a result, the results as depicted in Figure 18 were obtained. That is, compared with the model with the short sulfuric acid supply tubes 51S and 52S depicted in Figure 15B, it has been revealed that an increase in temperature of the baffle in the hemisphere part was decreased and sulfuric acid was not directly drawn to the upper part of the stirring blades.

[0076]

Thus, in the above-described autoclave 100, starting material slurry and sulfuric acid are added to the above-described compartment 20A at the upstream end from the above-described starting material slurry discharge ports 41A and 42A and the sulfuric acid discharge ports 51A and 52A positioned at positions higher than the uppermost part of the above-described stirring blades 31A and lower than the contained liquid surface L via the two starting material slurry supply tubes 41 and 42 having the starting material slurry discharge ports 41A and 42A, respectively, and the two sulfuric acid supply tubes 51 and 52 having sulfuric acid discharge ports 51A and 52A, respectively, alternately disposed on the perimeter of the stirring blades 31A of the stirring machine 31 provided in the compartment 20A at the upstream end as described above.

[0077]

As such, in the autoclave 100 in which starting material slurry and sulfuric acid are added from the above-described starting material slurry discharge ports 41A and 42A and sulfuric acid discharge ports 51A and 52A to the compartment 20A at the upstream end, in particular, in the case of a nickel oxide ore process, due to mixture of conditions such as solid contents and viscosity of starting material slurry and the temperature of the autoclave, starting material slurry and sulfuric acid are alternately drawn toward the stirring blades 31A to increase the possibility of a contact. Therefore, mixing is proceeded more efficiently than ever to improve a

leaching ratio. Also, a contact of high-concentration sulfuric acid with a wall surface can be prevented to decrease damage to the wall surface due to a contact of high-concentration sulfuric acid.

[0078]

Conventionally, a predetermined leaching ratio of 90% to 95% cannot be maintained unless the concentration of free sulfuric acid of the leachate is set at 50 g/L to 55 g/L. By contrast, in the above-described autoclave 100, the predetermined leaching ratio can be maintained even if the concentration of free sulfuric acid of the leachate is set at 45 g/L to 50 g/L.

[0079]

Here, the relation of the positions of the above-described starting material slurry discharge ports 41A and 42A and sulfuric acid discharge ports 51A and 52A with the autoclave 100 is not particularly limited, and any positions can be selected by rotation based on the center of the stirring blades 31A of the stirring machine 30A provided in the compartment 20A at the upstream end.

[0080]

Note that while the above-described starting material slurry discharge ports 41A and 42A and the above-described sulfuric acid discharge ports 51A and 52A are alternately drawn in a similar manner when they are positioned outside the above-described defined ranges S1, S2, S3, and S4, their dense flows are too close to or too far away from each other, thereby causing decreased mixing efficiency,

which is undesirable.

[0081]

Also, in this autoclave 100, the direction of the bottom side of the above-described regular triangle T is set parallel with the side wall of the autoclave 100. With this, since the starting material slurry discharge ports 41A and 42A are positioned in parallel with the side wall of the autoclave, relatively short piping suffices. Furthermore, since the degree of crossing and overlapping at the time of piping installation is minimum, operation is simple, which is preferable.

Examples

[0082]

(Example 1)

Operation was performed with a pressure in the autoclave of 5.5 MPaG, a temperature of 250 degrees Celsius, an Ni grade in crystal of 1.0% to 1.4%, and an amount of slurry influx to the autoclave of 300 m³ to 700 m³ per hour. Here, ore slurry and sulfuric acid were supplied by applying the present invention.

[0083]

As a result, the leaching ratio of nickel was 92.5%. Also, operation was possible herein with the concentration of free sulfuric acid of the leachate being managed at 45 g/L to 50 g/L.

[0084]

(Comparative Example 1)

Without applying the present invention, operation was performed similarly to that of Example 1 except that present invention was not applied and ore slurry and sulfuric acid were supplied in conventional method in the conventional autoclave depicted in Figure 20.

[0085]

As a result, the leaching ratio of nickel was 92.0%. However, the above-described leaching ratio was not able to be maintained unless the concentration of free sulfuric acid of the leachate was managed at 50 g/L to 55 g/L.

Reference Signs List

[0086]

10A, 10B ... partition wall; 20A, 20B ... compartment; 30A, 30B ... stirring machine; 31A stirring blade; 41, 42 ... starting material slurry supply tube; 41A, 42A ... starting material slurry discharge port; 51, 52 ... sulfuric-acid supply tube; 51A, 52A ... sulfuric-acid discharge port; 100 autoclave

CLAIMS:

1. A method for adding starting material slurry and sulfuric acid to an autoclave in a high pressure acid leaching process in which heated and pressurized starting material slurry and the sulfuric acid are stirred by a stirring machine provided in each of compartments in the autoclave partitioned into plurality by partition walls to proceed leaching of the starting material slurry, and slurry is transferred from a compartment on an upstream side to a compartment on a downstream side to sequentially proceed leaching, wherein

via starting material slurry supply tubes having starting material slurry discharge ports and sulfuric acid supply tubes having sulfuric acid discharge ports alternately disposed in a circumference around stirring blades of the stirring machine provided in a compartment at an upstream end of the autoclave, the starting material slurry and the sulfuric acid are added to the compartment at the upstream end from the starting material slurry discharge ports and the sulfuric acid discharge ports positioned at positions higher than an uppermost part of the stirring blades and lower than a contained liquid surface, wherein

the starting material slurry and the sulfuric acid are added to the compartment at the upstream end from the starting material slurry discharge ports and the sulfuric acid discharge ports, with the starting material slurry discharge ports and the sulfuric acid discharge ports being positioned at planar positions, the starting material slurry discharge ports being positioned in a range of a distance of $0.25D$ from, as centers, apex positions at both ends of a bottom side of a regular triangle with a height being any diameter D of a circle formed by tips of the stirring blades, the regular triangle moved by a distance of $0D$ to $0.5D$ so that the regular triangle has a midpoint of the bottom side positioned in a length direction of the bottom side of the regular triangle and on a downstream side of a rotating direction of the stirring blades, and the sulfuric acid discharge ports being positioned in a range of a distance of 0.25 of the diameter from, as centers, the midpoint position of the bottom side and the remaining apex position of the regular triangle.

2. The method for adding starting material slurry and sulfuric acid to the autoclave according to claim 1, wherein

the length direction of the bottom side of the regular triangle is parallel to a side wall of the autoclave.

3. An autoclave in a high pressure acid leaching process in which heated and pressurized starting material slurry and sulfuric acid are stirred by a stirring machine provided in each of compartments in the autoclave partitioned into plurality by partition walls to proceed leaching of the starting material slurry, and slurry is transferred from a compartment on an upstream side to a compartment on a downstream side to sequentially proceed leaching of the starting material slurry, wherein

starting material slurry supply tubes having starting material slurry discharge ports and sulfuric acid supply tubes having sulfuric acid discharge ports are alternately disposed in a circumference around stirring blades of the stirring machine provided in a compartment at an upstream end, and the starting material slurry discharge ports and the sulfuric acid discharge ports are positioned at positions higher than an uppermost part of the stirring blades and lower than a contained liquid surface, and

via the starting material slurry supply tubes and the sulfuric acid supply tubes, the starting material slurry and the sulfuric acid are added to the compartment at the upstream end from the starting material slurry discharge ports and the sulfuric acid discharge ports alternately positioned in a circumference around the stirring blades and at positions higher than the uppermost part of the stirring blades of the stirring machine and lower than the contained liquid surface, wherein

with the starting material slurry discharge ports and the sulfuric acid discharge ports being positioned at planar positions, the starting material slurry discharge ports are positioned in a range of a distance of $0.25D$ from, as centers, apex positions at both ends of a bottom side of a regular triangle with a height being any diameter of a circle formed by tips of the stirring blades, the regular triangle moved by a distance of $0D$ to $0.5D$ so that the regular triangle has a midpoint of the bottom side positioned in a length direction of the bottom side of the regular triangle and on a downstream side of a rotating direction of the stirring blades, and the sulfuric acid discharge ports are positioned in a range of a distance of $0.25 D$ from, as centers, the midpoint position of the bottom side and the remaining apex position of the regular triangle.

4. The autoclave according to claim 3, wherein
the length direction of the bottom side of the regular triangle is parallel to a side wall of
the autoclave.




FIG. 1A




FIG. 1B






FIG. 1C






FIG.3




FIG.4




FIG. 5A




FIG. 5B




FIG. 6B




FIG. 6A




FIG.7B

FIG.7A




FIG. 8A




FIG. 8B




FIG.9

10/20




FIG.10A




FIG.10B




FIG.11A




FIG.11B




FIG.12B





FIG.12A






FIG.13




FIG. 14B




FIG. 14A




FIG. 15A




FIG. 15B




FIG.16




FIG.17A




FIG.17B





FIG.18

**FIG.19 - Prior Art**

