



US 20060210736A1

(19) **United States**

(12) **Patent Application Publication**  
**Wycech**

(10) **Pub. No.: US 2006/0210736 A1**

(43) **Pub. Date: Sep. 21, 2006**

(54) **METHOD FOR FORMING A TANGIBLE ITEM AND A TANGIBLE ITEM WHICH IS MADE BY A METHOD WHICH ALLOWS THE CREATED TANGIBLE ITEM TO EFFICIENTLY ABSORB ENERGY**

**Related U.S. Application Data**

(60) Provisional application No. 60/598,830, filed on Aug. 5, 2004.

**Publication Classification**

(76) Inventor: **Joseph S. Wycech**, Gross Pointe Shores, MI (US)

(51) **Int. Cl.**  
**B31B 45/00** (2006.01)  
(52) **U.S. Cl.** ..... **428/34.1**


Correspondence Address:  
**John G. Chupa**  
**Law Offices of John Chupa and Associates, P.C.**  
**Suite 50**  
**28535 Orchard Lake Rd.**  
**Farmington Hills, MI 48334 (US)**

(57) **ABSTRACT**

A method for creating a tangible item (such as an "A" pillar garnishment **18**) which increases the capacity of the item to absorb energy by the incorporation and/or addition of a plurality of adhesive-covered beads **25**, and which utilizes the method and/or type of energy used to normally form the item to incorporate and/or add the adhesive-covered beads **25**, thereby increasing efficiency while reducing cost. A new and novel tangible item, such as "A" pillar garnishment **18**, having programmed energy absorption characteristics is also disclosed.

(21) Appl. No.: **11/170,863**

(22) Filed: **Jun. 30, 2005**






FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG. 6  25




FIG. 7




FIG. 9




FIG. 10




FIG. 8

**METHOD FOR FORMING A TANGIBLE ITEM  
AND A TANGIBLE ITEM WHICH IS MADE BY A  
METHOD WHICH ALLOWS THE CREATED  
TANGIBLE ITEM TO EFFICIENTLY ABSORB  
ENERGY**

**BACKGROUND**

**[0001]** 1. Field of the Invention

**[0002]** The present invention generally relates to a method for forming a tangible item and to a tangible item which is made by a method which allows the created tangible item to efficiently absorb energy and, more particularly, to a new and novel method for increasing the amount of energy which may be absorbed by a tangible item, without appreciably increasing the amount of energy used to normally form the item, and which further allows the produced tangible item to have disparate energy absorption portions in an intentional and programmable manner.

**[0003]** 2. Background of the Invention

**[0004]** It is relatively common to see traffic accidents and/or other mishaps which involve a vehicle and/or other type of selectively movable assembly. In these circumstances, a passenger (e.g., an individual residing within the vehicle or within other types of selectively movable assemblies) may be “thrown” within and/or otherwise jostled or moved within the vehicle or other type of selectively movable assembly by the force of the circumstances, in a manner which is dangerous and injurious to the passenger (e.g., the passenger forcibly contacts a portion of the interior of the vehicle or selectively movable assembly and is injured or killed).

**[0005]** It is therefore desirable to construct and/or adapt certain automotive and/or other types of parts and/or components (e.g., respectively forming or representing “tangible items”) which readily absorb this impact-type of force and/or energy and “cushion the blow” to the passenger, thereby reducing the likelihood of injury and death. While current tangible items do absorb some energy, they do so in a relatively inefficient manner, are relatively costly to manufacture, and are not “programmable”, (i.e., they do not have intentionally disparate energy absorption portions where contact is most likely to occur).

**[0006]** Further, it is desirable to achieve such a capacity without expending substantially more energy than is already being utilized and/or expended to create the part and/or component (e.g., the “tangible item”), and it is frequently and additionally desirable to cause only a portion of a part and/or component to be constructed and/or adapted to efficiently absorb energy (e.g., the portion which is readily contacted by the passenger), thereby reducing the overall cost in producing such an energy absorbing item while concomitantly achieving the desired energy absorption characteristics where they are most likely to be needed.

**[0007]** Further, it is desirable that, if these desirable energy-absorption enhancement characteristics are made within a tangible item, they be made in a manner which substantially utilizes only the type and the amount of energy which is currently used to form the item, thereby further not appreciably increasing the amount of energy already used to produce the item.

**[0008]** There is therefore a need for a new and novel method of forming an automotive part and/or other tangible item which can absorb a relatively high and/or relatively large amount of energy, for a tangible item which has enhanced energy absorption properties, and further for a method which does not substantially increase the amount of energy already expended in forming and/or otherwise creating a part and/or other tangible item but which allows the formed item to have enhanced energy absorption characteristics. There is therefore also a need for a new and improved tangible item having enhanced energy-absorption properties and which may have selectively and intentionally disparate energy-absorbing properties, thereby tailoring and/or “programming” the characteristics of the produced item to the needs of the environment in which it is placed. The present invention provides these and other novel benefits.

**SUMMARY OF THE INVENTION**

**[0009]** It is a first non-limiting object of the present invention to provide a method for creating a tangible item which overcomes some or all of the previously delineated drawbacks associated with prior and/or current methods or strategies.

**[0010]** It is a second non-limiting object of the present invention to provide a method for creating a tangible item which overcomes some or all of the previously delineated drawbacks associated with prior and/or current methods or strategies and which allows a tangible item to be produced which readily and efficiently absorbs energy in a cost-effective manner.

**[0011]** It is a third non-limiting object of the present invention to provide a method for creating a tangible item which overcomes some or all of the previously delineated drawbacks associated with prior and/or current methods or strategies, which allows a tangible item to be produced which readily and efficiently absorbs energy in a cost-effective manner, and which does not substantially increase the amount of energy required to produce the item without these enhanced energy-absorbing characteristics.

**[0012]** It is a fourth non-limiting object of the present invention to provide a method for creating a tangible item which overcomes some or all of the previously delineated drawbacks associated with prior and/or current methods or strategies, which allows a tangible item to be produced which readily and efficiently absorbs energy in a cost-effective manner, which does not substantially increase the amount of energy required to produce the item without these enhanced energy-absorbing characteristics, and which allows for selectively disparate energy absorption properties to be created within the created tangible item.

**[0013]** According to a first non-limiting aspect of the present invention, a method of forming a tangible item is provided which comprises the steps of forming a pre-part; forming a plurality of adhesive coated beads; and causing said adhesive coated beads to adhere to at least a portion of the pre-part, thereby forming the tangible item.

**[0014]** According to a second non-limiting aspect of the present invention, a method of forming a tangible item is provided which comprises the steps of forming a pre-part which includes at least one pocket; placing adhesive coated beads within the at least one pocket; and compressing the

adhesive coated beads, thereby causing said adhesive coated beads to adhere to the pre-part and thereby forming the tangible item.

[0015] According to a third non-limiting aspect of the present invention, a method of forming a tangible item is provided which comprises the steps of forming a pre-part which includes at least one pocket; placing adhesive coated beads within the at least one pocket; generating heated air; and directing the heated air to contact the adhesive coated beads, thereby causing the adhesive coated beads to adhere to the pre-part and thereby forming the tangible item.

[0016] According to a fourth non-limiting aspect of the present invention, a method of forming a tangible item is provided which comprises the steps of forming a pre-part which includes at least one pocket; placing adhesive coated beads within the at least one pocket; and causing the adhesive coated beads to be placed within a substantially anaerobic environment for a certain amount of time, thereby causing the adhesive coated beads to adhere to the pre-part and thereby forming said tangible item.

[0017] According to a fifth non-limiting aspect of the present invention, a method of forming a tangible item is provided which comprises the steps of providing a mold; placing a first material within the mold; placing a second material within the mold, wherein the second material comprises a plurality of adhesive coated beads; and using the mold to create the tangible item comprising a body which is substantially formed from said first material and wherein the body includes an enhanced energy absorption portion which is formed from the plurality of adhesive coated beads which are integrally formed and reside within a certain portion of the body.

[0018] According to a sixth non-limiting aspect of the present invention, a method of increasing the amount of energy which may be absorbed by a tangible item is provided wherein the tangible item is normally formed by the use of a process which requires a certain amount of energy, the method comprising the steps of providing beads; placing a certain amount of adhesive material upon the beads, thereby substantially coating the beads with the adhesive material; and causing the coated beads to be adhered to the tangible item only by the use of said certain amount of energy.

[0019] According to a seventh non-limiting aspect of the present invention, a method of increasing the amount of energy which may be absorbed by a tangible item is provided which comprises the steps of selecting only a portion of said tangible item; providing adhesive coated beads; and placing the adhesive coated beads only upon said selected portion of said tangible item, thereby programmably providing enhanced energy absorption properties to a selected portion of the produced tangible item.

[0020] According to an eighth non-limiting aspect of the present invention, a tangible item is provided which comprises at least one pocket; and a plurality of adhesive coated beads which are resident within said at least one pocket.

[0021] These and other objects, aspects and advantages of the present invention will become apparent to one of ordinary skill in the art by reading the following detailed description of the preferred embodiment of the invention and by reference to the following drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

[0022] FIG. 1 is an environmental perspective view of a portion of a selectively movable assembly which has been created according to the teachings of preferred embodiment of the present invention and which includes a pair of energy-absorbing tangible items which are made in accordance with the teachings of the preferred embodiment of the present invention.

[0023] FIG. 2 is a partial back view of one of the tangible items which is made in accordance with the teachings of an alternate embodiment of the present invention and which is shown in FIG. 1.

[0024] FIG. 3 is a top and partial schematic view of an assembly which is used to apply a plurality of adhesive-coated beads to a finished pre-part which is made in accordance to the teachings of an alternate embodiment of the present invention and which is shown in FIG. 2.

[0025] FIG. 4 is a side sectional view of an assembly which is used to form a tangible item in accordance with the teachings of another alternate embodiment of the present invention.

[0026] FIG. 5 is a side sectional side view of an assembly which is used to cure a tangible item made in accordance with the teachings of an alternate embodiment of the present invention.

[0027] FIG. 6 is a front view of an adhesive-covered bead which is used to create the tangible items according to the various non-limiting methodologies of the present invention.

[0028] FIG. 7 is a side sectional view of an assembly which is used to form a tangible item in accordance with the teachings of another alternate embodiment of the present invention.

[0029] FIG. 8 is a block diagram of a tangible item creation methodology of the various non-limiting methodologies of the present invention.

[0030] FIG. 9 is a cross-sectional view of a tangible item created according to one of the various methodologies of the present invention.

[0031] FIG. 10 is a perspective view of an energy-absorbing item which is formed in accordance with the teachings of an alternate embodiment of the invention shown being placed upon a pre-part.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT OF THE INVENTION

[0032] Referring now to FIGS. 1-8, there is cooperatively shown various new and novel methods and strategies for selectively, cost-effectively, and efficiently creating energy-absorbing tangible items which may even have disparate energy-absorption properties at various locations within the created item, thereby causing the created energy-absorbing tangible items to be highly "programmable" (e.g., having enhanced energy-absorption characteristics only at certain "pre-programmed" locations). It should be appreciated that the present invention is not limited to the production of a certain tangible item, but that various tangible items, of many types, of many shapes, and of many sizes may be selectively created and selectively used within a wide vari-

ety of assemblies. Further, it should be realized that various diverse assemblies may utilize these created items and that nothing in this description limits the assembly in which the created "energy absorption-enhanced" item is employed to a vehicle or selectively movable assembly, and that the created tangible items may be formed from plastic, metal, a composite material, or substantially any other desired material and/or blend of materials.

[0033] Particularly, as will be abundantly apparent from the following discussion, the present inventions provide these energy-absorption benefits by the use of a plurality of coated or "adhesive-covered" beads **25** which, as is best shown in **FIG. 6**, may each comprise a generally circular or spherical body portion **24** which may be evacuated, partially evacuated, or which may be substantially solid, and is substantially covered by a certain adhesive coating material **30**. Particularly, the body portion **24** may be comprised of substantially any material which efficiently absorbs a relatively large amount of energy and such material includes, but is not limited to, glass and semi-solid ceramic type material. Some non-limiting examples of such material or beads are those which may be purchased from The Kinetico Corporation of Cayahoga Falls, Ohio and which are commercially referred to by the trademarks Macrolyte® 714, Macrolyte® 1430 or Macrolyte® 357. Other commercially available beads and/or other energy-absorbing material may also be used. Generally, high temperature ceramic beads may be utilized by the various methodologies of the inventions.

[0034] The adhesive coating **30** may be comprised of substantially any type of adhesive, including but not limited to a "sticky" adhesive (i.e., a glue-like adhesive or an adhesive activated by room-temperature conditions), a heat-activated adhesive or an anaerobic type adhesive (i.e., adhesives which respectively become active or "sticky" in the presence of heat or in the absence of air and/or oxygen), or a moisture-activated or catalyst-activated type of adhesive. Additionally, the material used for the adhesive coating may be selected from (but is not limited to) several general classes of material such as, by way of example and without limitation, thermoplastic material (hot melt types of material), thermoset material (substantially solid epoxy types of material), thermoset material (liquid resin types of thermoset material and/or water-based liquid types of thermoset material), and/or to various blends of the foregoing.

[0035] The process used to create and/or coat the body portion **24** with the selected adhesive material **30** varies depending upon the characteristic of the adhesive **30** which is selected for use and depending upon the pre-part forming process which is utilized as part of the energy enhancement methodologies and/or strategies of the present invention.

[0036] For example and without limitation, if a thermoplastic hot melt adhesive and/or a thermoset solid epoxy is used, as the adhesive **30**, the beads **24** will be heated beyond the melting point of the adhesive within a heated mixer. The hot melted material is then heated and dispensed at a maximum of about twenty-five percent of the weight of the beads into the heated mixer. The beads are then continuously moved or "tumbled" within the mixer, thereby coating the beads, and the coated beads are then slowly brought to room temperature as they are continuously rotated.

[0037] However, if a thermoset liquid resin material and/or a water-based liquid resin material (such as epoxy,

polyester, vinyl ester, urethanes, or various blends thereof) is used as the adhesive **30**, then the chosen material, such as a flexible, polyester, acrylic or epoxy resin with no more than 1000 centipose viscosity, is catalyzed with a room temperature curing agent, and the catalyzed, flexible resin (or other chosen material) is then poured into the mixer containing the beads at a maximum of about twenty-five percent of the weight of the contained beads. The beads are then continuously tumbled at room temperature. If the thermoset water-based liquid resin is used as the adhesive **30**, the additional step of heating the coated and contained beads until the water is driven off the beads and the beads have a drier coat is added to the foregoing process. Once the beads are formed in one of the foregoing manners, they may be selectively dispensed as part of one of the energy enhancement methodologies or strategies of the present invention.

[0038] In one non-limiting embodiment of the invention, it is desirable that a portion of a selectively movable assembly, such as the garnishment and/or trim member **18** of an "A" pillar of a vehicle, or the "headliner" and/or roof portion **14** of a vehicle or other type of selectively movable assembly as best shown in **FIG. 1**, be able to efficiently and "programmably" absorb a relative high and/or large amount of energy (i.e., more than the energy which is capable of being absorbed by an "unenhanced part" and/or member or item made in a "prior" manner would characteristically and typically have).

[0039] It should be understood that the term "pre-part", as used within this description, means a tangible item which is created in a customary or "prior" manner without having the enhanced energy-absorbing characteristics of the present invention.

[0040] According to one non-limiting embodiment of the invention, the beads **25** may be placed upon a finished pre-part while it remains within the production assembly (i.e., the tool or apparatus which is used to create the pre-part) or after the finished pre-part has been created and subsequently removed from the production assembly, or during and as a part of the "normal" pre-part production process (e.g., the beads may be "sandwiched" between pre-part layers during the process by which the "finished" pre-part is created), or the beads may be selectively and separately formed into a separate part and/or item and selectively coupled to a part and/or pre-part. It should be realized that the type of adhesive and the method for placing the beads **25** on the tangible item may be chosen so as to not appreciably increase the amount of energy used by the conventional methodology of creating the pre-part, and further that the beads may only be located on a certain pre-selected portion of the pre-part **22**, thereby causing this single portion to have a disparate energy absorption property and/or characteristic from the other portions, thereby "pre-programming" the created tangible item to provide enhanced energy absorption at certain locations.

[0041] In one non-limiting embodiment of the invention as best shown in **FIG. 2**, a pre-part **22** (e.g., an "A" pillar garnishment) is formed within a production assembly (such as assembly **35** shown in **FIG. 4**) by any desired methodology (e.g., injection molding or male-female compression molding). The beads **25** are dispensed into the production assembly through a desired dispenser **37**, after a pocket **21** is formed within at least one surface **11** of the pre-part **22** and

the pocket **21** has a size, shape and location which allows the dispensed and subsequently received energy absorption beads to cooperatively provide a desired amount of energy-absorption. It should be realized that the material which is used to form the pre-part **22** is different from the material used to construct the beads **25**.

[0042] The beads may be additionally and/or selectively shaped and formed with a separate tool (for example, if the pre-part is formed by vacuum forming). The heat and/or other type of energy which is produced by the production assembly **35** is effective, in the most preferred embodiment of the invention, to “cure” (i.e., bond and/or otherwise attach) the adhesive-coated beads **25** to the desired discrete area and/or the entire surface of the finished pre-part (e.g., upon surface **11** and within the pocket **21**), thereby creating a tangible item (e.g., an garnishment and/or trim member for an “A” pillar **18**), which has the desired and enhanced energy-absorbing characteristics, at least within the formed pocket **21**.

[0043] By way of example and without limitation, the pocket **21** is formed nearest the head or other member of a driver or passenger of a selectively movable assembly (e.g., when the member **18** is deployed in the selectively movable assembly the pocket **21** is close to the head of a passenger or driver). In this manner, the member **18** has a programmably increased amount of energy absorption only within pocket **21** (which is the most likely portion of the member **18** to be contacted by a passenger), thereby protecting the passenger’s head or other member.

[0044] In another non-limiting embodiment of the invention, as best shown in **FIG. 3**, a substantially finished pre-part **22** may be formed by any substantially desirable process (e.g., injection molding, male-female compression molding, and/or vacuum molding) and removed from the production assembly (such as production assembly **35**). In one alternate embodiment of the invention, the conventionally or normally “finished” pre-part is formed by spraying a substance, such as polyurea. The finished pre-part **22** is then placed into a fixture (such as a holding apparatus) or into a tray such as tray **160** which encompasses the entire finished pre-part **22**.

[0045] A small, open mold **155** and top forming tool **158** are then applied to the “finished” pre-part **22** in a manner which shapes and locates a plurality of the beads **25** over the whole finished pre-part **22** or in a discrete local area on the “finished” pre-part. The “finished” pre-part **22** may then be subjected to conditions such as heat (e.g., from a microwave and/or convection oven), pressure, and/or other conditions (e.g., anaerobic conditions) which activate the adhesive **30** which was selected to coat the beads **25** (including room-temperature conditions), thereby bonding (i.e., curing) the beads **25** to the finished pre-part **22** which has the desired enhanced energy-absorbing characteristics.

[0046] In one non-limiting embodiment, as best shown in **FIG. 5**, the conventionally or normally “finished” pre-part **22** and the selected beads **25** (which reside within the pocket **21** of the pre-part **22**) are placed into a curing apparatus **80** having a first reception or support portion **82** and a second vent portion **84** which has a plurality of vent channels **44**. The adhesive on the beads **25** is then activated and/or “cured” (e.g., bonded and/or otherwise attached to the surface of the “finished” pre-part **22**) by the addition of hot

air in the direction of arrow **110** through the vents **44** or by the evacuation of air in the direction of the arrow **120** through the vents **44** (depending upon the selected adhesive **30** used to coat the beads **25**), or by any other desirable chemical process which has the effect of bonding the beads **25** to the finished pre-part **22**, thereby creating a part (such as the “A” pillar garnishment **18**) which has the desired and enhanced energy-absorption characteristics.

[0047] In another non-limiting embodiment of the invention as shown in **FIG. 7**, a tangible item such as “headliner” **14** may be formed in a “sandwich-layer” type process from at least two pre-part (or “sandwich substrate”) layers **72, 74**. In operation, the first “layer” or pre-part **72** is formed and/or molded (e.g., by compression molding,) in a production assembly such as assembly **62**. In one non-limiting embodiment of the invention, assembly **62** realizes a molding and/or forming process (e.g., the assembly **62** is a production tool used to conventionally or normally produce a “finished” pre-part) such as by compression member **79**, which is coupled to a motor or other driving assembly which propels the compression member **79** in the direction of the arrows **130**, effective to mold and/or otherwise form the layers **72, 74**. When it is desirable to have an enhanced energy-absorption characteristic within the “sandwich” item (e.g., a “headliner” such as **14**), the beads **25** are dispensed and/or deployed onto a prescribed and desired area on the back surface **73** of layer **72** in an intermediate layer **78**. A second pre-part or layer **74** is the placed on top of the intermediate layer **78**, thereby completing the forming and/or production process, as best shown in **FIGS. 7 and 9**. Alternately, the “uncured” layers **72, 74** and the intermediate layer **78** may be placed in a male-female type forming tool, heated, and subjected to a final forming process (e.g., vacuum), thereby creating a part and/or tangible item (such as “headliner” **14**) which has the desired and enhanced energy-absorption characteristics. It should be realized that material layers **72, 74** may comprise substantially similar or dissimilar materials and that each of the layers **72, 74** has a material which is different from the material used to form the beads **25**.

[0048] In yet another non-limiting embodiment of the invention as best shown in **FIG. 10**, the beads **25** are selectively and remotely pre-formed (i.e., molded and/or shaped and cured) into a desired item and/or assembly **8**. The item and/or assembly **8** may then be selectively placed onto a “finished” pre-part such as pre-part **22** and selectively glued, coupled, and/or otherwise attached to the pre-part **22**.

[0049] Referring now to **FIG. 8**, there is shown a block diagram of the methodology or energy enhancement strategy **200** which may be used, in one non-limiting embodiment of the invention, to create a tangible item (such as “A” pillar garnishment member **18** or “headliner” **14**) having a substantially increased capacity for energy absorption. Particularly, the method **200** includes the step **201** of providing a plurality of the beads **24** and the step **203** of providing a plurality of the adhesive coating **30**. The beads **24** and the selected adhesive coating **30** are then selectively mixed (step **205**) and/or continuously and selectively rotated (step **210**) (e.g., within a “cement-mixer” type apparatus) until the adhesive coating **30** substantially covers the surface of each unique one of the plurality of beads **24**, thereby creating a desired plurality of adhesive-coated beads **25**. The adhesive-coated beads **25** are then selectively dispensed (step **215**) by

a device (e.g., an auger type pump and or a progressive cavity pump, or an open molding tool such as tool **155** and a top forming tool such as tool **158**). It should be realized that the created adhesive-covered beads **25** may be selectively dispensed directly onto a finished pre-part such as finished pre-part **22** either within the production assembly (step **228**) or after the finished pre-part **22** has been removed from the production assembly (step **220**), during a pre-part creation process (such as the foregoing “sandwich-layer” production process, step **224**), or directly into a mold which shapes the beads **25** as desired independent of a part or pre-part (step **230**). Each of these processes has been described above.

[0050] It should further be appreciated that, when the beads **25** are cured and/or bonded together, a chemical-type bond forms between each molecule of the adhesive **30** and interstices and/or “spaces” **250** between the deployed beads **25** are formed (i.e., the beads cure into a “honeycomb” type arrangement). Since a relatively small amount of energy is required to form these bonds and thereby “cure” the beads **25**, this “quick-curing” operation reduces cycle time and reduces costs while increasing overall efficiency. It should further be appreciated that, once cured, the semi-solid ceramic beads are adapted to absorb energy upon being subjected to an impact- or dynamic-type force (i.e., not a static-type force) through several mechanisms including, by way of example and without limitation, the breaking of the chemical bonds which couple and/or attach the beads **25**, the crushing and/or other deforming of the semi-solid ceramic beads **25**, and the compression of the beads **25** into the interstices **250**.

[0051] It is to be understood that the invention is not limited to the exact methods which have been illustrated, but that various changes and modifications may be made without departing from the spirit and the scope of the invention as delineated in the following claims. From the foregoing it should be apparent that the adhesive-covered beads **25** may be applied to an automotive and/or other type of part and/or component, such as “A” pillar garnishment and/or member **18**, in a manner which increases the capacity of the item to programmably absorb energy and which utilizes the method and/or energy used to form the item to apply the beads **25**.

What is claimed is:

1) A method of forming a tangible item comprising the steps of forming a pre-part; forming a plurality of adhesive coated beads; and causing said adhesive coated beads to adhere to at least a portion of a pre-part.

2) The method of claim 1 wherein said tangible item comprises an automotive component.

3) The method of claim 2 wherein said automotive component comprises a pillar garnishment.

4) The method of claim 3 wherein said pillar garnishment comprises an “A” pillar garnishment.

5) The method of claim 2 wherein said component comprises a headliner.

6) The method of claim 2 wherein said component comprises a door trim panel.

7) The method of claim 1 wherein said beads comprise glass beads.

8) The method of claim 1 wherein said beads comprise ceramic semi-solid beads.

9) The method of claim 1 wherein said adhesive comprises an anaerobic adhesive.

10) The method of claim 1 wherein said adhesive comprises a thermoplastic hot melt adhesive.

11) The method of claim 1 wherein said adhesive comprises a thermoset adhesive.

12) A method for creating a tangible item comprising the steps of forming a pre-part which includes at least one pocket; placing adhesive coated beads within said at least one pocket; and compressing said adhesive coated beads, thereby causing said adhesive coated beads to adhere to said pre-part and forming said tangible item.

13) The method of claim 12 wherein said tangible item comprises an automotive component.

14) The method of claim 12 wherein said beads comprise glass beads.

15) The method of claim 12 wherein said beads comprise ceramic semi-solid beads.

16) A method for creating a tangible item comprising the steps of forming a pre-part which includes at least one pocket; placing adhesive coated beads within said at least one pocket; generating heated air; and directing said heated air to contact said adhesive coated beads, thereby causing said adhesive coated beads to adhere to said pre-part and forming said tangible item.

17) The method of claim 16 wherein said tangible item comprises an automotive component.

18) The method of claim 16 wherein said beads comprise glass beads.

19) The method of claim 16 wherein said beads comprise ceramic semi-solid beads.

20) The method of claim 16 wherein said adhesive comprises a thermoplastic hot melt adhesive.

21) The method of claim 16 wherein said adhesive comprises a thermoset adhesive.

22) A method for creating a tangible item comprising the steps of forming a pre-part which includes at least one pocket; placing adhesive coated beads within said at least one pocket; and causing said adhesive coated beads to be placed within a substantially anaerobic environment for a certain amount of time, thereby causing said adhesive coated beads to adhere to said pre-part and forming said tangible item.

23) The method of claim 22 wherein said tangible item comprises an automotive component.

24) The method of claim 22 wherein said beads comprise glass beads.

25) The method of claim 22 wherein said beads comprise ceramic semi-solid beads.

26) The method of claim 22 wherein said adhesive comprises an anaerobic adhesive.

27) A method for forming a tangible item comprising the steps of providing a mold; placing a first material within said mold; placing a second material within said mold, wherein said second material comprises a plurality of adhesive coated beads; and using said mold to create said tangible item comprising a body which is substantially formed from said first material and wherein said body includes an enhanced energy absorption portion which is formed from said plurality of adhesive coated beads which are integrally formed and reside within a certain portion of said body.

28) The method of claim 27 wherein said tangible item comprises an automotive component.

29) The method of claim 27 wherein said beads comprise glass beads.

**30)** The method of claim 27 wherein said beads comprise ceramic semi-solid beads.

**31)** A method of increasing the amount of energy which may be absorbed by a tangible item wherein said tangible item is normally formed by the use of a process which requires a certain amount of energy, said method comprising the steps of providing beads; placing a certain amount of adhesive material upon said beads, thereby substantially coating said beads with said adhesive material; and causing said coated beads to be adhered to said tangible item only by the use of said certain amount of energy.

**32)** The method of claim 31 wherein said tangible item comprises an automotive component.

**33)** The method of claim 31 wherein said beads comprise glass beads.

**34)** The method of claim 31 wherein said beads comprise ceramic semi-solid beads.

**35)** A method for increasing the amount energy which may be absorbed by a tangible item, said method comprising the steps of selecting only a portion of said tangible item; providing adhesive coated beads; and placing said adhesive coated beads only upon said selected portion of said tangible item.

**36)** The method of claim 35 wherein said tangible item comprises an automotive component.

**37)** The method of claim 35 wherein said beads comprise glass beads.

**38)** The method of claim 35 wherein said beads comprise ceramic semi-solid beads.

**39)** The method of claim 35 wherein said tangible item is normally formed by the use of a process which requires a certain amount of energy, and wherein said coated beads to be adhered to said tangible item are adhered only by the use of said certain amount of energy.

**40)** A tangible item comprising at least one pocket; and a plurality of adhesive coated beads which are resident within said at least one pocket.

**41)** The tangible item of claim 40 wherein said tangible item comprises an automotive component.

**42)** The tangible item of claim 40 wherein said beads comprise glass beads.

**43)** The tangible item of claim 40 wherein said beads comprise ceramic semi-solid beads.

\* \* \* \* \*