

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 260 823 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication of patent specification: **09.06.93** (51) Int. Cl.⁵: **G03F 7/004**

(21) Application number: **87307437.1**

(22) Date of filing: **21.08.87**

(54) **Improvements in or relating to printing plate precursors.**

(30) Priority: **16.09.86 GB 8622266**

(43) Date of publication of application:
23.03.88 Bulletin 88/12

(45) Publication of the grant of the patent:
09.06.93 Bulletin 93/23

(84) Designated Contracting States:
AT BE CH DE ES FR GB IT LI LU NL SE

(56) References cited:
EP-A- 0 053 749
US-A- 3 840 369

(73) Proprietor: **E.I. du Pont de Nemours and Company (a Delaware corporation)**
1007 Market Street
Wilmington Del. 19898(US)

(72) Inventor: **Etherington, Terrence**
50 Belle Vue Avenue
Roundhay Leeds, LS8 2NN(GB)
Inventor: **Fletcher, Keith Malcolm**
10 Oakwell Oval
Oakwood Leeds LS8 4AL(GB)
Inventor: **Potts, Rodney Martin**
43 St. Helens Way
Adel Leeds, LS16 8LP(GB)
Inventor: **Wade, John Robert**
7 Kings Close
Otley, LS21 1RO(GB)

(74) Representative: **Overbury, Richard Douglas et al**
HASELTINE LAKE & CO Hazlitt House 28
Southampton Buildings Chancery Lane
London WC2A 1AT (GB)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid (Art. 99(1) European patent convention).

Description

This invention relates to printing plate precursors and is concerned with such precursors which comprise a substrate coated with a radiation sensitive composition. Whilst being particularly concerned with lithographic plate precursors, the invention is also applicable to precursors for flexographic plates.

In use of such precursors, the radiation sensitive composition is image-wise exposed to radiation so that parts are struck by the radiation and parts are not. The radiation struck parts and the non-radiation struck parts have differing solubilities in developer liquids. Thus the more soluble of these parts can be selectively removed by the application of such a developer liquid to leave a printing image on the substrate constituted by the less soluble parts.

As is well known, printing plate precursors and similar radiation sensitive articles are considered to be either negative working or positive working depending on the effect of actinic radiation on the radiation sensitive composition.

In the past, most negative-working compositions for printing plate precursors have been based on photocrosslinkable compounds (e.g. cinnamate type materials) or on the so-called "diaz resins". The former type have the disadvantage of needing to be developed in an organic solvent developer liquid and the latter have the disadvantage of having a shorter printing life. Both types are also limited as regards their exposure speed.


More recently, there has been a trend towards using radiation sensitive compositions based on compounds containing ethylenic unsaturation (hereafter referred to as prepolymers), which polymerise on exposure to actinic radiation. Precursors using such compounds have the advantage that, whilst having the potential to be developed in aqueous-based developer liquids in a similar manner to diazo resin based precursors, they are also capable of much longer printing life than photo-crosslinkable or diazo resin based precursors and, moreover, they have exposure speeds which are many times greater. However, there are drawbacks to the use of such prepolymers. Commonly, the unsaturated groups are in the form of low molecular weight acrylates which can involve health and safety problems. Also, highly sensitive pre-polymer based precursors can have problems in respect of the storage life necessary for a presensitised precursor in that if they are stored for any length of time before exposure and development they cannot be developed using aqueous-based developers.

It is an object of the present invention to provide printing plate precursors which, whilst retaining high sensitivity, have improved aqueous developability characteristics after storage and pose less risks in terms of health and safety.

US Patent No. 3,840,369 describes printing plate precursors including a radiation-sensitive composition based on an isocyanate-modified polyethylenically unsaturated ester and a photoinitiator. The ester is formed by reacting a polyhydric alcohol with (meth)acrylic acid and the like. Many suitable polyhydric alcohols are mentioned including trimethylol propane and pentaerythritol. However, there is no suggestion to use propoxylated pentaerythritol as the polyhydric alcohol and the isocyanate-modified unsaturated ester preferably includes residual hydroxyl groups.

EP-A-0053749 describes the production of radiation-sensitive compositions suitable for various diverse purposes including impregnating, coating, reinforcing and priming textile materials, wood, plastics, non-woven materials and leather and also for the production of relief (letter press) printing plates. The radiation-sensitive composition comprises (A) a polyisocyanate, (B) an ethylenically-unsaturated partial ester formed from an alkoxyolated trimethylol propane and (meth)acrylic acid, and (C) optionally a hydroxy alkyl (meth)acrylate.


According to one aspect of the present invention, there is provided a printing plate precursor comprising a substrate coated with a radiation sensitive composition which composition comprises at least one photoinitiator and at least one photopolymerisable compound which is an acrylic or methacrylic ester of a tetra functional polyol having the general formula:



wherein the average degree of propoxylation n is from 3 to 6, from 50% to 90% of the available hydroxy groups have been converted to acrylate or methacrylate groups, and the remaining hydroxy groups have been reacted with a di-isocyanate or a polyisocyanate.

According to another aspect of the present invention there is provided a method of producing a printing plate precursor which method comprises

- (i) forming a urethane acrylate or urethane methacrylate by converting from 50 to 90% of the available hydroxy groups of a tetra functional polyol having the general formula:



wherein the average degree of propoxylation n is from 3 to 6, into acrylate or methacrylate groups and reacting the remaining available hydroxy groups with a diisocyanate or polyisocyanate;

(ii) admixing the urethane acrylate or urethane methacrylate with a photoinitiator to form a radiation sensitive composition, and

(iii) forming a coating of the composition on a substrate.

The polyol may be obtained by reacting pentaerythritol with an oxypropylating agent, for example propylene oxide and/or propylene carbonate. The (meth)acrylation may be carried out by an acid catalysed (e.g. sulphuric acid) azeotropic esterification reaction in the presence of a product to inhibit premature polymerisation of the (meth)acrylate groups (for example copper oxide). Reaction of the remaining hydroxy groups of the resultant hydroxy poly(meth)acrylate with the isocyanate may be effected by treating the poly(meth)acrylate with the isocyanate in the presence of a suitable catalyst, for example an alkyl tin compound and/or a tertiary amine. Optionally, an organic, non-protonic solvent, such as toluene or butanone, may also be present.

In accordance with an embodiment of the invention, the di-isocyanate or polyisocyanate is reacted, either simultaneously or successively, with both a compound having at least two active hydrogen containing groups and also the hydroxy poly(meth)acrylate described above.

The active hydrogen-containing group may be a hydroxy group, a carboxy group, a mercapto group or an amino group and particularly preferred compounds containing such groups are polyethylene glycol, polypropylene glycol, 2-(ethylamino)ethanol, butan-1,3-diol, polycaprolactone based diols, 3,6-dithiaoctan-1,8-diol, lactic acid or thiosalicylic acid.

Whilst any di- or poly-isocyanate can be used, 2, 4 and 2, 6 toluene diisocyanate, diphenyl methane diisocyanate, hexamethylene diisocyanate, isophorone diisocyanate and isophorone diisocyanate trimer are particularly suitable.

Preferred photoinitiators for the radiation sensitive composition are triazines such as 2,4,6-tris(trichloromethyl)-s-triazine; ketones such as benzoin, benzoin ethers, benzophenone or Michler's ketone; peresters as referred to in European Patent (EP) Specification No. 125140, such as 4-benzoyl-t-butyl perbenzoate; (trichloromethyl)phenacylidene N-heterocyclic derivatives as referred to in EP No.135348, such as 1,3,3-trimethyl-2-(4'-trichloromethylbenzoyl)methylene 5-chloroindoline; acridine compounds such as 9-phenyl acridine; and polynuclear quinones such as 2-ethyl anthraquinone and 2-isopropyl thioxanthone. The photoinitiator may be present in an amount of from 0.01-50% (preferably 0.1-15%) by weight of the urethane (meth)acrylate).

If required an optical sensitiser may be included in the composition to broaden or alter its spectral response. Examples of suitable optical sensitisers are coumarins and bis coumarins (GB Patent No.1 578 662, US Patent No.4 147 552 and EP No.22188); α,β -unsaturated ketones (GB Patent No.1 553 823, US Patent Nos.3 652 275, 4 162 161 and 4 268 667 and GB Published Application No.2 006 775); methine dyes (GB Patent No.1 566 405, US Patent No.2 732 301 and GB published patent Application No.2 064 546); and pyrylium dyes (GB Patent Nos.1 023 377 and 1 566 405 and US Patents Nos.3 907 561 and 900 031). The sensitiser may be present in an amount of from 0.01 to 50% (preferably 0.1 to 15%) by weight of the urethane (meth)acrylate).

If required, a binder resin may be incorporated in the radiation sensitive composition to provide greater strength and improve the adherence of the composition to the substrate. Typical binders are acrylic polymers, vinyl acetate polymers, polyurethanes, novolak resins, polyamides, polyvinyl esters, polyvinyl acetals, polyvinyl ethers, epoxide resins, styrene maleic anhydride copolymers, polymethacrylates, polyesters, alkyd resins, polyacrylamides, polyvinyl alcohol, polyethylene oxide, polydimethylacrylamide, polyvinylpyrrolidone, polyvinylmethylformamide and polyvinylmethyl-acetamide. It is particularly preferred to use binder resins which are at least swellable in aqueous-alkaline solutions. Many other examples of suitable binders are listed in the patent literature and reference may be made, for example, to US Patent Nos.3 652 275, 4 268 667, 4 458 007 and GB published patent application No.2 006 775. The binder resin may be present in an amount of from 0-500% (preferably 0-250%) by weight of the urethane (meth)acrylate).

The substrate may be any substrate conventionally used for printing plate precursors, such as paper, plastics material, or metal. A substrate formed of grained and anodised aluminium is particularly preferred for a lithographic plate precursor and a substrate formed of polyfibron, steel or aluminium is preferred for a flexographic plate precursor.

The radiation sensitive composition may also include a substance which exhibits a colour change when the composition is exposed to radiation. Thus the substance may be a dye, a dye precursor, an indicator

which becomes bleached or otherwise changes colour in the presence of acid, or a leuco dye which is caused to become coloured by oxidation as a consequence of the exposure of the composition to radiation.

Such colour changes are particularly important in the production of lithographic and flexographic printing plates from radiation sensitive plates since they provide a visible distinction between the image and the non-image area after image-wise exposure and this allows defects to be noticed before the plate is developed.

The polymerisation of ethylenically unsaturated compounds is inhibited by the presence of oxygen. It is, therefore, desirable to overcoat the radiation sensitive composition with a barrier layer which is transparent to radiation and also impervious to oxygen. A layer of polyvinyl alcohol is particularly suitable for this purpose and it may be applied by a roller coater.

The following Examples illustrate the invention.

EXAMPLE 1

An electrolytically grained and anodised aluminium sheet was whirler coated with a solution, in ethyl methyl ketone, of a radiation sensitive composition comprising:

2 parts by weight of Prepolymer A

1 part by weight of a vinyl acetate/crotonic acid copolymer

0.15 parts by weight of 2,4,6-tris(trichloromethyl)-s-triazine

0.15 parts by weight Ethyl Michler's Ketone, and

0.15 parts by weight Leuco Crystal Violet

The coating weight was 1 g/sq.metre. After drying, an overcoating of poly(vinyl alcohol) was applied by roller coater to prevent oxygen inhibition. The resultant radiation sensitive plate was exposed through a continuous tone Stouffer step-wedge to ultraviolet light (30 units) from a Berkey Ascor printing down frame and developed with an aqueous solution containing sodium propionate, sodium benzoate and a surfactant. The developed image of the resultant lithographic printing plate had a step-wedge of solid 4 tail 9.

Prepolymer A is the reaction product of toluene diisocyanate and a polyol of the above general formula wherein $n = 3.7$ and approximately 75% of the free hydrogen groups have been acrylated. It may be prepared as follows:

A mixture of 122 g of pentaerythritol, 193.5 g of propylene oxide and 3 g of triethylamine was heated in an autoclave to 90 degC. The temperature was controlled between 90 °C and 105 °C until essentially all the propylene oxide had reacted, as evidenced by a significant reduction in pressure. A pale coloured transparent liquid of low viscosity was obtained.

A mixture of 40 g of the above propoxylated pentaerythritol, 30.2 g acrylic acid, 0.4 g of copper (I) oxide and 1.2 cm³ conc. H₂SO₄ in toluene (150 cm³) was heated with stirring in the presence of a Dean and Stark trap. The reaction was allowed to continue until 6.1 cm³ of water had been liberated. The mixture was then cooled and washed with 20% w/v aqueous sodium chloride (2 x 50 cm³ aliquots), then with 15% w/v aqueous potassium bicarbonate (2 x 100 cm³ aliquots) and finally a further wash with 20% w/v aqueous sodium chloride (2 x 50 cm³ aliquots). The resulting solution was then filtered and dried over anhydrous sodium sulphate. The solvent was then removed leaving the polyacrylate product as a colourless oil to which 0.2% w/w of 4-methoxyphenol, a polymerisation inhibitor, was then added.

A mixture of 68.9 g of the polyacrylate, 8.7 g of commercial quality toluene di-isocyanate, 0.1 g dibutyl tin dilaurate and 0.1 g triethylene diamine were heated with stirring to 50 degC in a moisture-free atmosphere. The reaction was allowed to proceed until all the isocyanate had reacted as determined by IR spectroscopy. The product, Prepolymer A, was a transparent, viscous liquid.

EXAMPLE 2

Using the method described in Example 1 and altering the proportion of propylene oxide relative to pentaerythritol (to vary the degree of propoxylation), altering the amount of (meth)acrylic acid, continuing the reaction until the correct degree of esterification has been achieved as indicated by the amount of water liberated (to vary the ester group and the degree of esterification) and utilising an appropriate isocyanate, prepolymers B to J were prepared as shown in Table I. The prepolymers were then incorporated in radiation sensitive compositions and radiation sensitive plates were prepared and processed as in Example 1. The compositions and the resulting sensitivities thereof are shown in Table II.

TABLE I

Prepolymer	Degree of Propoxylation	Ester Group	Degree of Esterification	Isocyanate
A	3.7	Acrylate	75%	I
B	3.7	Methacrylate	75%	I
C	4.7	Acrylate	75%	I
D	4.7	Methacrylate	75%	I
E	4.7	Acrylate	90%	II
F	4.7	Acrylate	50%	III
G	4.7	Acrylate	75%	IV
H	5.5	Acrylate	75%	I
I	5.5	Methacrylate	90%	II
J	5.5	Acrylate	75%	V

The isocyanate used were as follows:

I = Toluene diisocyanate

II = Poly[methylene(poly phenyl isocyanate)]

III = Phenyl isocyanate

IV = Isophorone diisocyanate

V = Hexamethylene diisocyanate

TABLE II

Formulation	67%	Prepolymer	Binder Resin	33%	Photoinitiator	5%	Sensitiser	5%	Sensitivity
1	A		I	I	I	I	I	I	4,9
2	A		I	I	II	-	-	-	6,11
3	A		I	I	I	I	II	II	2,6
3	A		I	I	I	I	III	III	1,5
5	A		I	I	III	I	I	I	5,11
6	A		I	I	IV	I	I	I	0,4
7	A		III	III	II	-	-	-	7,12
8	B		III	III	II	-	-	-	6,10
9	C		III	III	II	-	-	-	7,13
10	D		III	III	II	-	-	-	6,12
11	E		III	III	II	-	-	-	5,9
12	F		III	III	II	-	-	-	8,13
13	G		III	III	II	-	-	-	6,10
14	H		III	III	II	-	-	-	7,12
15	I		III	III	II	-	-	-	5,11
15	J		III	III	II	-	-	-	4,9
17	C		II	II	II	-	-	-	8,14
18	C		II	II	III	I	I	I	7,13
19	C		IV	IV	III	I	I	I	6,12
20	C		V	V	III	I	I	I	3,7
21	C		VI	VI	III	I	I	I	5,10

The binder resins, photoinitiators and sensitisers used were as follows:

- I = Vinyl acetate/crotonic acid copolymer (acid value 80)
 II = Phthaloylated poly(vinyl butyral) (acid value 80)
 III = N-t-Octylacrylamide/acrylic acid/methyl methacrylate/hydroxypropyl methacrylate/t-butylaminomethacrylate polymer
 IV = n-hexylmethacrylate/methacrylic acid/styrene terpolymer (Acid value 120)
 V = styrene maleic anhydride ester co-polymer (acid value 200)
 VI = p-tolylsulphonyl carbamate modified poly(vinyl butyral)

Photoinitiators

- I = 2,4,6-tris(trichloromethyl)-s-triazine
 II = 4'-trichloromethyl phenacrylidene-1,3,3-trimethyl-5-chloro indolenine
 5 III = Benzophenone-4-t-butyl benzoate
 IV = 9-phenyl acridine

Sensitisers

- 10 I = Ethyl Michler's ketone
 II = 2-benzoylmethylene-3-methyl benzo thiazole
 III = 3-methyl-7-diethylamino coumarin

EXAMPLE 3

15 Example 1 was repeated except that the Prepolymer A was replaced by Prepolymer K in which the free hydroxy groups were reacted with toluene diisocyanate end-capped polypropylene glycol.

Similar results were obtained.

20 Prepolymer K may be prepared in the same way as Prepolymer A except that in the final reaction, 26.5 g of the polyacrylate is used and 10.62 g of polypropylene glycol 425 is added to the reaction mixture.

EXAMPLE 4

25 Example 1 was again repeated using as the prepolymer Prepolymer L which may be prepared by further reacting the polyacrylate as follows.

A mixture of 68.9 g of the polyacrylate, 10.0 g of commercial toluene diisocyanate and 0.1 g of dibutyl tin dilaurate were heated to 90 °C for 16 hours in a moisture free atmosphere. 1.15 g of thiosalicylic acid were then added and the reaction continued at 90 °C until all the isocyanate had reacted as determined by i/r spectroscopy. The product was a highly viscous liquid.

30 Similar results were obtained.

EXAMPLE 5

35 A polyfibron substrate was curtain coated with a solution in ethyl methyl ketone of a radiation sensitive composition comprising:

- 0.75 parts by weight Prepolymer A
 1 part by weight of a vinyl acetate/crotonic acid copolymer
 0.05 parts by weight of 2,4,6-tris(trichloromethyl)-s-triazine, and
 0.01 parts by weight Ethyl Michler's Ketone.

40 The coating weight was 300 g/sq.metre. After coating with poly(vinyl alcohol), the plate was exposed through a line negative to ultra-violet light and developed as in Example 1.

A flexographic plate having a 300 micron relief image was obtained.

EXAMPLE 6


45 A plate based on Formulation 18 of Table II (containing Prepolymer C) was subjected to a rapid ageing test by being stored at 30 °C and 90% relative humidity in a cabinet. The plate was removed at intervals of 1 week from the cabinet and processed as in Example 1 until it failed to develop cleanly. The experiment was repeated with Prepolymer C replaced with various other commercially available prepolymers. The results are shown in Table III as a percentage of the stability of Formulation 18.

50 Further identical plates were made and press tested on a web-offset printing press. The results obtained are also shown in Table III as a percentage of the run length of Formulation 18.

Prepolymer	Type	Stability (% of Formulation 18)	Run length (% of Formulation 18)
Ebecryl 220	Hexa functional aromatic urethane acrylate	33	80
Genomer T1200	Trifunctional polyester based urethane acrylate	40	85
Synocure E2778	Epoxyacrylate	70	65
Laromer PE55F	Polyester acrylate	40	80
-	Glyceryl diacrylate/Desmodur-N urethane tetra acrylate	35	95

Claims

1. A printing plate precursor comprising a substrate coated with a radiation sensitive composition which composition comprises at least one photoinitiator and at least one photopolymerisable compound characterised in that the photopolymerisable compound is an acrylic or methacrylic ester of a tetra functional polyol having the general formula:



wherein the average degree of propoxylation n is from 3 to 6, from 50% to 90% of the available hydroxy groups have been converted to acrylate or methacrylate groups, and the remaining hydroxy groups have been reacted with a di-isocyanate or a polyisocyanate.


2. A printing plate precursor as claimed in claim 1 wherein the photoinitiator is a triazine, a ketone, a perester, an acridine or a polynuclear quinone.

3. A printing plate precursor as claimed in claim 1 or 2 wherein the composition comprises an acrylic polymer, a vinyl acetate polymer, a styrene-maleic anhydride copolymer, or a poly(vinyl acetal) as a binder resin.

4. A printing plate precursor as claimed in claim 1, 2 or 3, wherein the composition includes a coumarin or bis coumarin, an α,β -unsaturated ketone, a methine dye or a pyrilium dye as an optical sensitiser.

5. A printing plate precursor as claimed in any one of claims 1 to 4 wherein the substrate is formed of aluminium.

6. A method of producing a printing plate precursor by admixing at least one photopolymerisable compound with at least one photoinitiator to form a radiation sensitive composition and coating the substrate with the composition characterised in that the photopolymerisable compound is a urethane acrylate or urethane methacrylate formed by converting from 50 to 90% of the available hydroxy groups of a tetra functional polyol having the general formula:



wherein the average degree of propoxylation n is from 3 to 6, into acrylate or methacrylate groups and reacting the remaining available hydroxy groups with a diisocyanate or polyisocyanate.


7. A method according to claim 6 wherein the diisocyanate or polyisocyanate is additionally reacted with a compound having at least two groups which contain an active hydrogen atom.

8. A method according to claim 7 wherein said compound is polyethylene glycol; polypropylene glycol; 2-ethylamino ethanol; butan-1,3-diol; a polycaprolactone based diol; 3,6-dithiaoctan-1,8-diol, lactic acid or thiosalicylic acid.

9. A method according to claim 6, 7 or 8 wherein the diisocyanate or polyisocyanate is 2,4 toluene diisocyanate; 2,6 toluene diisocyanate, diphenyl methane diisocyanate; hexamethylene diisocyanate; isophorone diisocyanate, or isophorone diisocyanate trimer.

5 Patentansprüche

1. Vorläufer für Druckplatten (Druckformenmaterial), welcher ein mit einer strahlungsempfindlichen Mischung beschichtetes Substrat aufweist, wobei die strahlungsempfindliche Mischung zumindest einen Photoinitiator und zumindest eine photopolymerisierbare Verbindung enthält, dadurch gekennzeichnet, daß die photopolymerisierbare Verbindung ein Acrylsäure- oder Methacrylsäureester eines tetrafunktionellen Polyols der allgemeinen Formel



- mit einem durchschnittlichen Propoxylierungsgrad n von 3 bis 6 ist, wobei 50% bis 90% der zur Verfügung stehenden Hydroxygruppen zu Acrylat- oder Methacrylatgruppen umgewandelt und die verbleibenden Hydroxygruppen mit einem Diisocyanat oder einem Polyisocyanat umgesetzt worden sind.


2. Vorläufer für Druckplatten nach Anspruch 1, worin der Photoinitiator ein Triazin, ein Keton, ein Perester, ein Acridin oder ein mehrkerniges Chinon ist.

3. Vorläufer für Druckplatten nach Anspruch 1 oder 2, worin die strahlungsempfindliche Mischung ein Acrylpolymer, ein Vinylacetatpolymer, ein Styrol/Maleinsäureanhydrid-Copolymer oder ein Poly(vinylacetal) als Bindeharz enthält.

4. Vorläufer für Druckplatten nach Anspruch 1, 2 oder 3, worin die strahlungsempfindliche Mischung ein Cumarin oder Biscumarin, ein α,β -ungesättigtes Keton, einen Methinfarbstoff oder einen Pyriliumfarbstoff als optischen Sensibilisator enthält.

5. Vorläufer für Druckplatten nach irgendeinem der Ansprüche 1 bis 4, worin das Substrat von Aluminium gebildet ist.

6. Verfahren zum Herstellen eines Vorläufers für Druckplatten durch Vermischen zumindest einer photopolymerisierbaren Verbindung mit zumindest einem Photoinitiator zwecks Ausbildung einer strahlungsempfindlichen Mischung und durch Beschichten des Substrats mit dieser Mischung, dadurch gekennzeichnet, daß die photopolymerisierbare Verbindung ein Urethanacrylat oder Urethanmethacrylat ist, welches durch Umwandeln von 50 bis 90% der zur Verfügung stehenden Hydroxygruppen eines tetrafunktionellen Polyols der allgemeinen Formel



- mit einem durchschnittlichen Propoxylierungsgrad n von 3 bis 6 in Acrylat- oder Methacrylatgruppen und durch Umsetzen der restlichen zur Verfügung stehenden Hydroxygruppen mit einem Diisocyanat oder einem Polyisocyanat hergestellt worden ist.


7. Verfahren nach Anspruch 6, worin das Diisocyanat oder Polyisocyanat zusätzlich mit einer Verbindung umgesetzt wird, welche zumindest zwei, ein aktives Wasserstoffatom enthaltende Gruppen aufweist.

8. Verfahren nach Anspruch 7, worin die erwähnte Verbindung Polyäthylenglykol, Polypropylenglykol, 2-Äthylaminoäthanol, Butan-1,3-diol, ein Polycaprolacton auf Basis eines Diols, 3,6-Dithiaoctan-1,8-diol, Milchsäure oder Thiosalicylsäure ist.

9. Verfahren nach Anspruch 6, 7 oder 8, worin das Diisocyanat oder Polyisocyanat 2,4-Toluoldiisocyanat, 2,6-Toluoldiisocyanat, Diphenylmethandiisocyanat, Hexamethylendiisocyanat, Isophorondiisocyanat oder das Trimere von Isophorondiisocyanat ist.

Revendications

1. Précurseur pour plaques d'impression comprenant un substrat revêtu avec une composition sensible au rayonnement, composition qui comprend au moins un photoinitiateur et au moins un composé photopolymérisable, caractérisé en ce que le composé photopolymérisable est un ester acrylique ou méthacrylique d'un polyol tétrafonctionnel ayant la formule générale :



dans laquelle le degré moyen de propoxylation n vaut de 3 à 6, 50% à 90% des groupes hydroxy disponibles ayant été convertis en groupes acrylate ou méthacrylate, et les groupes hydroxy restants ayant réagis avec un diisocyanate ou un polyisocyanate.


2. Précurseur pour plaques d'impression selon la revendication 1, dans lequel le photoinitiateur est une triazine, une cétone, un perester, une acridine ou une quinone polynucléaire.

3. Précurseur pour plaques d'impression selon la revendication 1 ou 2, dans lequel la composition comprend un polymère acrylique, un polymère d'acétate de vinyle, un copolymère anhydride maléique-styrène, ou un poly(acétal vinylique) comme résine liante.

4. Précurseur pour plaques d'impression selon la revendication 1, 2 ou 3, dans lequel la composition comprend une coumarine ou une bis-coumarine, une cétone α -insaturée, un colorant méthine ou un colorant pyrilium comme sensibilisateur optique.

5. Précurseur pour plaques d'impression selon l'une quelconque des revendications 1 à 4, dans lequel le substrat est formé d'aluminium.

6. Procédé pour la production d'un précurseur pour plaques d'impression consistant à mélanger au moins un composé photopolymérisable avec au moins un photoinitiateur pour former une composition sensible au rayonnement, et à revêtir le substrat avec la composition, caractérisé en ce que le composé photopolymérisable est un acrylate d'uréthane ou un méthacrylate d'uréthane formé en convertissant de 50 à 90% des groupes hydroxy disponibles d'un polyol tétrafonctionnel ayant la formule générale :



dans laquelle le degré moyen de propoxylation n vaut de 3 à 6, en groupes acrylate ou méthacrylate, et en faisant réagir les groupes hydroxy disponibles restants avec un diisocyanate ou un polyisocyanate.

7. Procédé selon la revendication 6, dans lequel on fait réagir de plus le diisocyanate ou le polyisocyanate avec un composé ayant au moins deux groupes qui contiennent un atome d'hydrogène actif.

8. Procédé selon la revendication 7, dans lequel ledit composé est le polyéthylèneglycol; le polypropylèneglycol; le 2-éthylamino éthanol; le butane-1,3-diol; un diol à base de polycaprolactone; le 3,6-dithiaoctane-1,8-diol, l'acide lactique ou l'acide thiosalicylique.

9. Procédé selon la revendication 6, 7 ou 8, dans lequel le diisocyanate ou le polyisocyanate est le 2,4-diisocyanate de toluène; le 2,6-diisocyanate de toluène; le diisocyanate de méthane diphényle; le diisocyanate d'hexaméthylène; le diisocyanate d'isophorone, ou le trimère de diisocyanate d'isophorone.