



(51) International Patent Classification:

C09J 7/20 (2018.01) C09D 11/30 (2014.01)  
C09J 7/40 (2018.01)

(21) International Application Number:

PCT/IB2019/060447

(22) International Filing Date:

04 December 2019 (04.12.2019)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

62/778,616 12 December 2018 (12.12.2018) US

(71) Applicant: **3M INNOVATIVE PROPERTIES COMPANY** [US/US]; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(72) Inventors: **KOBE, Taylor J.**; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US). **GETSCHEL, Joel A.**; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US). **FANSLER, Duane D.**; 3M Center, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(74) Agent: **HAN, Qiang** et al.; 3M Center, Office of Intellectual Property Counsel, Post Office Box 33427, Saint Paul, Minnesota 55133-3427 (US).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME,

MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available):

ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a patent (Rule 4.17(ii))
- as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii))

Published:

- with international search report (Art. 21(3))
- in black and white; the international application as filed contained color or greyscale and is available for download from PATENTSCOPE

(54) Title: RELEASE INKJET PRINTING INK ARTICLES




FIG. 1

(57) Abstract: An article and a method of making thereof. The article includes a polymeric film having a first major surface and a second major surface; and a plurality of discrete domains of an inkjet printing ink comprising a low adhesion backsize coating composition deposited on the first major surface of the polymeric film; wherein the low adhesion backsize coating composition has a viscosity between 1 to 30 cp at a printing temperature between 20 to 70 degrees Celsius.



## RELEASE INKJET PRINTING INK ARTICLES

### FIELD OF THE INVENTION

This invention relates to inkjet printing inks, articles using inkjet printing inks and method  
5 thereof.

### BACKGROUND

Repositionable note pads, tapes and linerless labels typically consist of sheets of stock (paper,  
films, etc.) coated with pressure sensitive adhesive (“PSA”) (and optionally a primer) on one side of the  
10 sheet and a release coating (also referred to as “low adhesion backsize” or “LAB”) on the other side. In  
either pad (stacked sheets) or roll form, the release coating is in contact with the adhesive.

Lithographic, flexographic, or gravure printing processes are often used to prepare printed  
repositionable notes, tapes and linerless labels. Often, the printing process is separate from and  
subsequent to the process that applies the adhesive and release coating. In such situations, a roll of stock  
15 that has been pre-coated with adhesive and a release material is routed through a printing press, ink is  
printed on top of the release coating, and the printed material is immediately either rolled back up or cut  
into a stack of discrete sheets. Printing of ink over the release coating renders the release coating  
ineffective. Undesirable adhesive-ink interactions are also formed which results in poor release (high  
unwind, tear outs, poor dispensing) and transfer of ink from the printed stock to the adhesive. Such “ink  
20 transfer” damages the printed image and contaminates the adhesive. There is a need for inkjet printing  
inks with LAB coating.

### SUMMARY

Briefly in one aspect of the present invention, an article is provided comprising: a polymeric film  
25 having a first major surface and a second major surface; and a plurality of discrete domains of an inkjet  
printing ink comprising a low adhesion backsize coating composition deposited on the first major surface  
of the polymeric film. The low adhesion backsize coating composition has a viscosity between 1 to 30 cp  
at a printing temperature between 20 to 70 degrees Celsius.

Inkjet printing ink comprising a low adhesion backsize coating composition can be advantageously  
30 used in products that have pressure sensitive adhesives (PSAs) in contact with the printed inks in order to  
reduce undesirable PSA/ink interactions. The Inkjet printing ink can add unlimited colors, and colored  
patterns to the tape backing if desired. Inkjet printing allows for the ability to change these colors, or  
colored patterns, on the backing without shutting the line down. Printing an LAB will allow a tape backing  
to have multi designs or patterns in one roll of tape if desired. A printable ink with LAB properties  
35 combines the printing and LAB coating steps. This has the process simplification advantage of combining  
two steps into one step, but also enables printing during the converting process without disrupting current  
high volume manufacturing.

Thus, in one aspect, the present disclosure provides an article. The article includes a polymeric film having a first major surface and a second major surface; and a plurality of discrete domains of an inkjet printing ink comprising a low adhesion backsize coating composition deposited on the first major surface of the polymeric film; wherein the low adhesion backsize coating composition has a viscosity  
5 between 1 to 30 cp at a printing temperature between 20 to 70 degrees Celsius.

In another aspect, the present disclosure provides a method, comprising: providing a polymeric film having a first major surface and a second major surface; depositing an inkjet printing ink comprising a low adhesion backsize coating composition onto the first major surface of the polymeric film; and curing the inkjet printing ink to form a plurality of discrete domains of an inkjet printing ink.

10 Various aspects and advantages of exemplary embodiments of the present disclosure have been summarized. The above Summary is not intended to describe each illustrated embodiment or every implementation of the present disclosure. Further features and advantages are disclosed in the embodiments that follow. The Drawings and the Detailed Description that follow more particularly exemplify certain embodiments using the principles disclosed herein.

## 15 DEFINITIONS

For the following defined terms, these definitions shall be applied for the entire Specification, including the claims, unless a different definition is provided in the claims or elsewhere in the Specification based upon a specific reference to a modification of a term used in the following definitions:

20 The terms “about” or “approximately” with reference to a numerical value or a shape means +/- five percent of the numerical value or property or characteristic, but also expressly includes any narrow range within the +/- five percent of the numerical value or property or characteristic as well as the exact numerical value. For example, a temperature of “about” 100°C refers to a temperature from 95°C to 105°C, but also expressly includes any narrower range of temperature or even a single temperature within  
25 that range, including, for example, a temperature of exactly 100°C. For example, a viscosity of “about” 1 Pa-sec refers to a viscosity from 0.95 to 1.05 Pa-sec, but also expressly includes a viscosity of exactly 1 Pa-sec. Similarly, a perimeter that is “substantially square” is intended to describe a geometric shape having four lateral edges in which each lateral edge has a length which is from 95% to 105% of the length of any other lateral edge, but which also includes a geometric shape in which each lateral edge has exactly  
30 the same length.

The term “substantially” with reference to a property or characteristic means that the property or characteristic is exhibited to a greater extent than the opposite of that property or characteristic is exhibited. For example, a substrate that is “substantially” transparent refers to a substrate that transmits more radiation (e.g. visible light) than it fails to transmit (e.g. absorbs and reflects). Thus, a substrate that  
35 transmits more than 50% of the visible light incident upon its surface is substantially transparent, but a substrate that transmits 50% or less of the visible light incident upon its surface is not substantially transparent.

The terms “a”, “an”, and “the” include plural referents unless the content clearly dictates otherwise. Thus, for example, reference to a material containing “a compound” includes a mixture of two or more compounds.

5

### BRIEF DESCRIPTION OF THE DRAWINGS

The disclosure may be more completely understood in consideration of the following detailed description of various embodiments of the disclosure in connection with the accompanying figures, in which:

10

FIG. 1 is a side, cross-sectional view of an article according to one exemplary embodiment.

While the above-identified drawings, which may not be drawn to scale, set forth various embodiments of the present disclosure, other embodiments are also contemplated, as noted in the Detailed Description. In all cases, this disclosure describes the presently disclosed invention by way of representation of exemplary embodiments and not by express limitations. It should be understood that numerous other modifications and embodiments can be devised by those skilled in the art, which fall within the scope and spirit of this disclosure.

15

### DETAILED DESCRIPTION

Before any embodiments of the present disclosure are explained in detail, it is understood that the invention is not limited in its application to the details of use, construction, and the arrangement of components set forth in the following description. The invention is capable of other embodiments and of being practiced or of being carried out in various ways that will become apparent to a person of ordinary skill in the art upon reading the present disclosure. Also, it is understood that the phraseology and terminology used herein is for the purpose of description and should not be regarded as limiting. The use of “including,” “comprising,” or “having” and variations thereof herein is meant to encompass the items listed thereafter and equivalents thereof as well as additional items. It is understood that other embodiments may be utilized and structural or logical changes may be made without departing from the scope of the present disclosure.

25

As used in this Specification, the recitation of numerical ranges by endpoints includes all numbers subsumed within that range (e.g. 1 to 5 includes 1, 1.5, 2, 2.75, 3, 3.8, 4, and 5, and the like).

30

Unless otherwise indicated, all numbers expressing quantities or ingredients, measurement of properties and so forth used in the Specification and embodiments are to be understood as being modified in all instances by the term “about.” Accordingly, unless indicated to the contrary, the numerical parameters set forth in the foregoing specification and attached listing of embodiments can vary depending upon the desired properties sought to be obtained by those skilled in the art utilizing the teachings of the present disclosure. At the very least, and not as an attempt to limit the application of the doctrine of equivalents to

35

the scope of the claimed embodiments, each numerical parameter should at least be construed in light of the number of reported significant digits and by applying ordinary rounding techniques.

A article according to one embodiment of the invention is illustrated in FIG. 1 and hereinafter referred to by the numeral 100. The article 100 includes a polymeric film 110 having a first major surface 112 and a second major surface 116. A plurality of discrete domains 120 of an inkjet printing ink comprising a low adhesion backsize coating composition deposited on the first major surface 112 of the polymeric film 110. The average space L1 between each domain of the inkjet printing ink is between 0 and 50 mils, between 0 and 40 mils, between 0 and 30 mils, between 0 and 25 mils, or in some embodiments, less than, equal to, or greater than 0, 5, 10, 15, 20, 25, 30, 35, 40, 45, 50 mils. In some embodiments, the plurality of discrete domains 120 of an inkjet printing ink can have the same low adhesion backsize coating composition. In some embodiments, at least part of the plurality of discrete domains 120 of an inkjet printing ink can have different low adhesion backsize coating composition. In some embodiments, all of the plurality of discrete domains 120 of an inkjet printing ink can have different low adhesion backsize coating composition.

The plurality of discrete domains 120 of an inkjet printing ink can cover 1% to 99%, 5% to 95%, 10% to 90%, 20% to 80%, 30% to 70%, 40% to 60% of the first major surface, or in some embodiments, less than, equal to, or greater than 1%, 2%, 3%, 4%, 5%, 10%, 15%, 20%, 25%, 30%, 35%, 40%, 45%, 50%, 60%, 70%, 80%, 90%, 95%, 96%, 97%, 98% or 99% of the first major surface.

Low adhesion backsize coating composition can include a silicone copolymers, for example, crosslinking polysiloxanes. One class of silicone copolymers that provide good properties for UV-curable inks are acrylate terminated silicones (“silicone macromers”), for example methacrylate-terminated poly(dimethylsiloxane). An example of such materials is Silicone “Plus” HG-10 Siloxane, which is commercially available from 3M Company, St. Paul, MN. Silicone “Plus” HG-10 is a methacrylate terminated poly(dimethylsiloxane) polymer having a number average molecular weight of 10,000.

Another class of silicone copolymers can include poly(dimethylsiloxane), poly(dimethylsiloxane-co-diphenylsiloxane), poly(methylphenylsiloxane-co-diphenylsiloxane), and poly(dimethylsiloxane-co-methylphenylsiloxane). Siloxane polymers useful in the practice of this invention may be prepared by any of a number of methods familiar to those skilled in the art, including, for example, anionic, condensation, or ring-opening polymerization. Siloxane polymers useful for this invention may also be prepared with the introduction of functional end-groups or functional pendant groups. This may be accomplished through the use of functional monomers, functional initiators, or functional chain terminators, for example, divinyl terminated poly(methylphenylsiloxane-co-diphenylsiloxane).

Low adhesion backsize coating composition can include acrylates. Suitable acrylates can include, but are not limited to Mono(meth)acrylates, Di(meth)acrylates, aliphatic (meth)acrylates, 2-Hydroxyethyl acrylate, Dipropylene Glycol Diacrylate, 2-Phenoxyethyl acrylate, and fluorinated (meth)acrylates.

Low adhesion backsize coating composition can include inkjet inks. Preferable inkjet inks are curable by UV irradiation. Suitable inkjet inks can include Type-G DICE Gammajet ink (Prototype and Production Systems Inc. Plymouth, MN), UV Clear ink (Kao Collins Inc., Cincinnati, OH), Liojet® AP-

Series ink (Toyo Ink America, Wood Dale, IL), UV Inkjet Ink 1500 Series ink (3M Co. St. Paul, MN), and UV Ink LH-Clear ink (Mimaki USA, Inc., Suwanee, GA).

Low adhesion backsize coating composition can include fluorinated acrylate monomer used for release liners. Suitable fluorinated acrylate monomer can include LTM Diacrylate (3M Co. St. Paul, MN) and A1330, B2340, B5278, B5785, D4989, H1554 (TCI America, Portland, OR).

Low adhesion backsize coating composition can include UV photoinitiator. Suitable UV photoinitiator can include those described in U.S. Patent NO. 340408, for example Daracur TPO & TPO-L, Irgacure 651, Irgacure 184, Irgacure 819 (Ludwigshafen DE), Esacure KB-1 and IGM.

In order to be suitable for inkjet printing, the the low adhesion backsize coating composition has a viscosity between 1 to 30 cp, between 5 to 25 cp, between 10 to 20 cp, or in some embodiments, less than, equal to, or greater than 1, 2, 5, 10, 15, 20, 25, 30 cp at a printing temperature between 20 to 70 degrees Celsius.

The inkjet printing ink can lower the force required to remove the polymeric film with the ink from the adjacent sheet in order to facilitate dispensing and minimize stock deformation or curl. The release force for the polymeric film with the inkjet printing ink released from the adjacent polymeric film can be from 10 g/in to 1000 g/in, from 15 g/in to 900 g/in, from 20 g/in to 800 g/in, from 30 g/in to 700 g/in, from 40 g/in to 600 g/in, from 50 g/in to 500 g/in, or in some embodiments, less than or equal to, 1000, 900, 800, 700, 600, 500, 400, 300, 200, 100, 50, 40, 30, 20 g/in.

In some embodiments, the polymeric film can be selected from polyolefins, halogenated polyolefins, polyamides, polytetrafluoroethylene, polyacrylates, polystyrenes, nylon, polyesters, polyester copolymers, polyurethanes, polysulfones, styrene-maleic anhydride copolymers, styrene-acrylonitrile copolymers, ionomers based on sodium or zinc salts or ethylene methacrylic acid, polymethyl methacrylates, cellulose, acrylic polymers and copolymers, polycarbonates, polyacrylonitriles ethylene-vinyl acetate copolymers, and fluoropolymers. In some embodiments, suitable substrate 120 can be conveniently an organic polymeric layer that is processed to be heat-shrinkable by any suitable means. Semicrystalline or amorphous polymers can be made heat-shrinkable by orienting them at a temperature above their glass transition temperature, T<sub>g</sub>, and then cooling. Examples of useful semicrystalline polymeric films include polyolefins such as polyethylene (PE), polypropylene (PP), and syndiotactic polystyrene (sPS); polyesters such as polyethylene terephthalate (PET), polyethylene naphthalate (PEN), and polyethylene-2,6-naphthalate; fluoropolymers such as polyvinylidene difluoride, and ethylene:tetrafluoroethylene copolymers (ETFE); polyamides such as Nylon 6 and Nylon 66; polyphenylene oxide, and polyphenylene sulfide. Examples of amorphous polymer films include polymethylmethacrylate (PMMA), polyimides (PI), polycarbonate (PC), polyether sulfone (PES), atactic polystyrene (aPS), polyvinyl chloride (PVC), and norbornene based cyclic olefin polymer (COP) and cyclic olefin copolymer (COC). Some polymer materials are available in both semicrystalline and amorphous forms. Semicrystalline polymers such as those listed above can also be made heat-shrinkable

by heating to the peak crystallization temperature and cooling. In some embodiments, the polymeric film can be a polyethylene terephthalate film.

In some embodiments, the article can include an adhesive 130 on the second major surface 116 of the polymeric film 110. Suitable adhesive for use in the article includes any adhesive that provides acceptable adhesion. Suitable adhesives can be pressure sensitive and in certain embodiments have a relatively high moisture vapor transmission rate to allow for moisture evaporation. Suitable pressure sensitive adhesives include those based on acrylates, urethane, hydrogels, hydrocolloids, block copolymers, silicones, rubber based adhesives (including natural rubber, polyisoprene, polyisobutylene, butyl rubber etc.) as well as combinations of these adhesives. The adhesive component may contain tackifiers, plasticizers, rheology modifiers as well as active components including for example an antimicrobial agent. Suitable adhesive can include those described in U.S. Patent Nos. 3,389,827; 4,112,213; 4,310,509; 4,323,557; 4,595,001; 4,737,410; 6,994,904 and International Publication Nos. WO 2010/056541; WO 2010/056543 and WO 2014/149718, the disclosures of which are hereby incorporated by reference. The adhesive can be processed to form solid, pattern or porous adhesive layer.

A method of making the article of the present application is provided. A polymeric film having a first major surface and a second major surface is provided and an inkjet printing ink comprising a low adhesion backsize coating composition can be deposited onto the first major surface of the polymeric film. Then, the inkjet printing ink is cured to form a plurality of discrete domains of an inkjet printing ink. The inkjet printing ink can be deposited by standard inkjet printing presses. In some embodiments, an adhesive can be applied onto the second major surface of the polymeric film.

A printable ink with LAB properties combines the printing and LAB coating steps. This has the process simplification advantage of combining two steps into one step, but also enables printing during the converting process without disrupting current high volume manufacturing. Printing during converting is advantageous because digital printing is more compatible with converting line speeds and capital investment requirements are much lower. The printable ink with LAB properties of the present application has the ability to precisely change (on-demand with inkjet) the release force by controlling the domain density and surface area printed.

The following embodiments are intended to be illustrative of the present disclosure and not limiting.

## EMBODIMENTS

1. An article, comprising: a polymeric film having a first major surface and a second major surface; and a plurality of discrete domains of an inkjet printing ink comprising a low adhesion backsize coating composition deposited on the first major surface of the polymeric film; wherein the low adhesion backsize coating composition has a viscosity between 1 to 30 cp at a printing temperature between 20 to 70 degrees Celsius.

2. The article of embodiment 1, wherein the low adhesion backsize coating composition comprises Mono(meth)acrylates, Di(meth)acrylates, aliphatic (meth)acrylates, fluorinated (meth)acrylates, Poly(dimethylsiloxane-co-diphenylsiloxane), divinyl terminated and/or Poly(dimethylsiloxane), mono(meth)acrylate terminated.

5

3. The article of any one of embodiments 1-2, wherein the polymeric film comprises polyesters, polyolefins, polytetrafluoroethylene, polyvinyl chloride, polycarbonates, polyacrylates, polyurethanes, and/or cellulosic.

10

4. The article of any one of embodiments 1-3, wherein the polymeric film is a polyethylene terephthalate film.

5. The article of any one of embodiments 1-4, wherein low adhesion backsize coating composition is curable.

15

6. The article of any one of embodiments 1-5, wherein the release force for the polymeric film with the inkjet printing ink is from 10 g/in to 1000 g/in.

20

7. The article of any one of embodiments 1-6, wherein the average space between each domain of the inkjet printing ink is between 0 and 50 mils.

8. The article of any one of embodiments 1-7, further comprising an adhesive on the second major surface of the polymeric film.

25

9. The article of any one of embodiments 1-8, wherein the plurality of discrete domains of an inkjet printing ink cover 1% to 99% of the first major surface.

30

10. A method, comprising providing a polymeric film having a first major surface and a second major surface; depositing an inkjet printing ink comprising a low adhesion backsize coating composition onto the first major surface of the polymeric film; and curing the inkjet printing ink to form a plurality of discrete domains of an inkjet printing ink.

35

11. The method of embodiment 10, wherein the low adhesion backsize coating composition has a viscosity between 1 to 30 cp at a printing temperature between 20 to 70 degrees Celsius.

12. The method of any one of embodiments 10-11, further comprising applying an adhesive onto the second major surface of the polymeric film.



							<b>divinyl terminated wt%</b>	<b>terminated wt%</b>
1	Ink A	13.64	20.09	63.60	2.67			
2	Ink B	13.50	19.89	62.96	2.64	0.01		
3	Ink C	13.50	19.89	62.96	2.64		0.01	
4	Ink D	13.50	19.89	62.96	2.64			0.01

Mending tape (obtained under the tradename SCOTCH 810 MAGIC TAPE from 3M, Saint Paul, MN), masking tape (obtained under the tradename SCOTCH 232 MASKING TAPE from 3M, Saint Paul, MN), and packaging tape (obtained under the tradename 3M 369 PACKAGING TAPE from 3M, Saint Paul, MN) were applied to the cured ink coatings of each of Examples 1-4, using a four inch diameter hand-roller, as well as to uncoated polyester film Comparative Example C1. After 30 minutes' time, release adhesion was tested using a peel tester (obtained under the tradename IMASS SP-2100 Slip/Peel Tester from Instrumentors, Inc., Strongsville, OH). ASTM test D3330-78 was followed to perform a 180° peel at 12 in/min, employing a 2 sec start time and a 10 sec data collection time. Release adhesion results are shown in Table 2. "PET-Ink Fail" denotes that the peel happened between the ink and the PET, rather than between the ink and the tape. "30+" mean that the machine's measurement limit of 30oz/in width was exceeded.

Table 2: Tape release adhesion results from ink

<b>Tape</b>	<b>Ex. 1 Ink A oz/in width (N/cm)</b>	<b>Ex. 2 Ink B oz/in width (N/cm)</b>	<b>Ex. 3 Ink C oz/in width (N/cm)</b>	<b>Ex. 4 Ink D oz/in width (N/cm)</b>	<b>Ex. 5 PET (no coating) oz/in width (N/cm)</b>
Magic	12.4 (1.36)	1.1 (0.12)	0.8 (0.09)	1.3 (0.14)	13 (1.42)
Masking	25.6 (2.80)	9.1 (1.00)	0.6 (0.07)	0.7 (0.08)	21.4 (2.34)
Packaging	PET-Ink Fail	9.6 (1.05)	1.6 (0.18)	1 (0.11)	30+ (3.28+)

**Example 5-13 and Comparative Examples C2 and C3: Release adhesion from printed LAB ink**

Ink formulations E and F, shown in Table 3, were printed using an inkjet printer (obtained under the tradename DIMATIX MATERIALS PRINTER DMP-2831 from Fujifilm Dimatix, Inc., Santa Clara, CA) with a cartridge (obtained under the tradename DIMATIX MATERIALS CARTRIDGE DMC-11610 from Fujifilm Dimatix, Inc., Santa Clara, CA) onto corona treated biaxially oriented PET polyester film. Air corona treatment was performed at 0.25 J/cm<sup>2</sup> using a corona treater (obtained from Pillar Technologies, Hartland, WI) on a laboratory scale. The same ink formulations were also inkjet printed onto the backside (adhesive strip side) of repositionable note paper (obtained under the tradename POST-IT from 3M, Saint Paul, MN), taking care to avoid printing on the adhesive strip. In all cases, the inkjet-printed ink was then cured using an ultraviolet LED source (obtained under the tradename OMNICURE AC475-395 from Excelitas Technologies, Waltham, MA) at 1400 mJ/cm<sup>2</sup> in a nitrogen purged atmosphere. The dot sizes were measured on the corona treated PET and were found to be 84 +/-2 microns in diameter, and the dot sizes on POST-IT paper were 39 +/-5 microns. The dot size is a function of the drop volume and contact angle. The spacing of the printed ink dots was varied from 50 microns to 250 microns in the various Examples.

Table 3: Ink formulations used for printing in Examples 5-13

<b>Ink</b>	<b>DICE Type G Ink (obtained from Prototype and Production Systems, Inc., Plymouth, MN) wt%</b>	<b>ODA wt%</b>	<b>LTM Diacrylate wt%</b>	<b>Poly(dimethylsiloxane-co-diphenylsiloxane), divinyl terminated wt%</b>
Ink E	99.90			0.10
Ink F	99.00	1.00		
Ink G	99.90		0.10	

Mending tape (obtained under the tradename SCOTCH 810 MAGIC TAPE from 3M, Saint Paul, MN), was applied to the printed and cured ink with a four inch diameter hand-roller as well as to unprinted corona treated polyester film and to the unprinted POST-IT paper (backside). After 30 minutes' time, release adhesion was tested using a peel tester (obtained under the tradename IMASS SP-2100 Slip/Peel Tester from Instrumentors, Inc., Strongsville, OH). ASTM test D3330-78 was followed to perform a 180° peel at 12 in/min, employing a 2 sec start time and a 10 sec data collection time. Release adhesion results are shown in Table 4 and Table 5.

Table 4: Release adhesion from printed ink on corona treated polyester film at varied dot spacings

Example	Ink	Dot Spacing $\mu\text{m} \times \mu\text{m}$	Adhesion oz/in width (N/cm)
C2	No Ink	(PET Control)	16.9 (1.85)
5	Ink E	50 x 50	8.5 (0.93)
6	Ink E	100 x 100	8.4 (0.92)
7	Ink E	150 x 150	13.0 (1.42)
8	Ink E	200 x 200	14.5 (1.59)
9	Ink E	250 x 250	15.7 (1.72)

Table 5: Release adhesion from printed ink on POST-IT Note paper at varied dot spacings

Example	Ink	Dot Spacing $\mu\text{m} \times \mu\text{m}$	Adhesion oz/in width (N/cm)
C3	No Ink	(POST-IT paper Control)	17.0 (1.86)
10	Ink E	100 x 100	7.1 (0.78)
11	Ink E	200 x 200	13.2 (1.44)
12	Ink F	100 x 100	7.7 (0.84)
13	Ink F	200 x 200	12.4 (1.36)

#### 5 Example 14-18: Release adhesion from two printed LAB inks

Two ink formulations, from Table 3, were inkjet printed and then cured onto corona treated polyester film as described in Example 5-13. The spacing of the printed ink dots was varied from 50 microns to 150

microns. Release adhesion was tested as in the previous Examples. Release adhesion results are shown in Table 6, with Comp. Ex. C2 listed again for comparison.

Table 6: Release adhesion from two printed inks on corona treated polyester at varied dot spacings

Ex.	Ink 1	Dot Spacing µm x µm	Ink 2	Dot Spacing µm x µm	Adhesion oz/in width (N/cm)
C2	No Ink		No Ink	(PET Control)	16.9 (1.85)
14	Ink E	50 x 50	Ink F	50 x 50	12.3 (1.35)
15	Ink E	100 x 100	Ink F	50 x 50	11.9 (1.30)
16	Ink E	150 x 150	Ink F	50 x 50	12.9 (1.41)
17	Ink E	150 x 150	Ink F	150 x 150	8.7 (0.95)
18	Ink E	50 x 50	Ink G	50 x 50	10.7 (1.17)

5

**Examples 19 and 20: Patterned LAB inks**

To demonstrate that it is possible to spatially pattern where the release adhesion (or other property of the cured inks) is higher or lower (for instance, in order to provide less release adhesion only at an edge of a tape roll), two ink formulations, from Table 3, were inkjet printed onto corona treated polyester film as described in previous Examples in a pattern of alternating 3 mm wide lines, and then cured. For Example 19, lines of Ink E with added cyan pigment were printed at 200 µm x 200 µm spacing and lines of Ink F with added cyan pigment were printed at 75 µm x 75 µm spacing. For Example 20, lines of Ink E with added yellow pigment were printed at 75 µm x 75 µm spacing and lines of Ink E with added cyan pigment were printed at 75 µm x 75 µm spacing.

10

15

The film of Example 19, so printed, exhibited clearly defined stripes of lighter (less saturated) and darker (more saturated) color. The film of Example 20, so printed, exhibited clearly defined stripes of yellow and cyan color.

All references and publications cited herein are expressly incorporated herein by reference in their entirety into this disclosure. Illustrative embodiments of this invention are discussed and reference has been made to possible variations within the scope of this invention. For example, features depicted in connection with one illustrative embodiment may be used in connection with other embodiments of the

20

invention. These and other variations and modifications in the invention will be apparent to those skilled in the art without departing from the scope of the invention, and it should be understood that this invention is not limited to the illustrative embodiments set forth herein. Accordingly, the invention is to be limited only by the claims provided below and equivalents thereof.

What is claimed is:

1. An article, comprising:  
a polymeric film having a first major surface and a second major surface; and  
5 a plurality of discrete domains of an inkjet printing ink comprising a low adhesion backsize coating composition deposited on the first major surface of the polymeric film;  
wherein the low adhesion backsize coating composition has a viscosity between 1 to 30 cp at a printing temperature between 20 to 70 degrees Celsius.
- 10 2. The article of embodiment 1, wherein the low adhesion backsize coating composition comprises Mono(meth)acrylates, Di(meth)acrylates, aliphatic (meth)acrylates, fluorinated (meth)acrylates, Poly(dimethylsiloxane-co-diphenylsiloxane), divinyl terminated and/or Poly(dimethylsiloxane), mono(meth)acrylate terminated.
- 15 3. The article of any one of claims 1-2, wherein the polymeric film comprises polyesters, polyolefins, polytetrafluoroethylene, polyvinyl chloride, polycarbonates, polyacrylates, polyurethanes, and/or cellulosic.
- 20 4. The article of any one of claims 1-3, wherein the polymeric film is a polyethylene terephthalate film.
5. The article of any one of claims 1-4, wherein low adhesion backsize coating composition is curable.
- 25 6. The article of any one of claims 1-5, wherein the release force for the polymeric film with the inkjet printing ink is from 10 g/in to 1000 g/in.
7. The article of any one of claims 1-6, wherein the average space between each domain of the inkjet printing ink is between 0 and 50 mils.
- 30 8. The article of any one of claims 1-7, further comprising an adhesive on the second major surface of the polymeric film.
9. The article of any one of claims 1-8, wherein the plurality of discrete domains of an inkjet  
35 printing ink cover 1% to 99% of the first major surface.
10. A method, comprising:

providing a polymeric film having a first major surface and a second major surface;  
depositing an inkjet printing ink comprising a low adhesion backsize coating composition onto the  
first major surface of the polymeric film; and  
curing the inkjet printing ink to form a plurality of discrete domains of an inkjet printing ink.

5

11. The method of embodiment 10, wherein the low adhesion backsize coating composition has a  
viscosity between 1 to 30 cp at a printing temperature between 20 to 70 degrees Celsius.

12. The method of any one of claims 10-11, further comprising applying an adhesive onto the second  
major surface of the polymeric film.

10




FIG. 1

# INTERNATIONAL SEARCH REPORT

International application No PCT/IB2019/060447
---------------------------------------------------

<b>A. CLASSIFICATION OF SUBJECT MATTER</b> INV. C09J7/20      C09J7/40      C09D11/30 ADD.				
According to International Patent Classification (IPC) or to both national classification and IPC				
<b>B. FIELDS SEARCHED</b>				
Minimum documentation searched (classification system followed by classification symbols) C09J C09D				
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched				
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used) EPO-Internal, WPI Data				
<b>C. DOCUMENTS CONSIDERED TO BE RELEVANT</b>				
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.		
X	US 5 061 535 A (KRECKEL KARL-WERNER [US] ET AL) 29 October 1991 (1991-10-29) abstract column 3, line 64 - column 5, line 13; claims 1,2,6-8; figures -----	1,3-9		
X	US 2016/032149 A1 (TIGHE LAURENCE E [US]) 4 February 2016 (2016-02-04) abstract paragraph [0013]; claim 1; figure 2 -----	1-4,6-9		
Y		12		
X	US 6 258 427 B1 (KERINS JOHN E [US] ET AL) 10 July 2001 (2001-07-10) abstract column 5, line 6 - line 49; claims 1,2,4,8,9 -----	1,2,6,7, 9-11		
----- -/--				
<input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C. <input checked="" type="checkbox"/> See patent family annex.				
* Special categories of cited documents : <table style="width: 100%; border: none;"> <tr> <td style="width: 50%; border: none; vertical-align: top;">                     "A" document defining the general state of the art which is not considered to be of particular relevance                      "E" earlier application or patent but published on or after the international filing date                      "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)                      "O" document referring to an oral disclosure, use, exhibition or other means                      "P" document published prior to the international filing date but later than the priority date claimed                 </td> <td style="width: 50%; border: none; vertical-align: top;">                     "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention                      "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone                      "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art                      "&amp;" document member of the same patent family                 </td> </tr> </table>			"A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier application or patent but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family
"A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier application or patent but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family			
Date of the actual completion of the international search	Date of mailing of the international search report			
27 February 2020	06/03/2020			
Name and mailing address of the ISA/ European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Fax: (+31-70) 340-3016	Authorized officer  Meier, Stefan			

# INTERNATIONAL SEARCH REPORT

International application No PCT/IB2019/060447
---------------------------------------------------

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X  Y	US 2018/154575 A1 (HORTELANO EDWIN RAY [US] ET AL) 7 June 2018 (2018-06-07) abstract paragraphs [0003], [0044], [0048]; claims 1-3,5,13,28; examples 1,2 -----	1,6,7, 9-11 12

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No  
PCT/IB2019/060447

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5061535	A	29-10-1991	NONE
-----			
US 2016032149	A1	04-02-2016	NONE
-----			
US 6258427	B1	10-07-2001	NONE
-----			
US 2018154575	A1	07-06-2018	US 2018154575 A1 07-06-2018
		WO 2018106830 A1	14-06-2018
-----			