



(22) Date de dépôt/Filing Date: 2009/03/02

(41) Mise à la disp. pub./Open to Public Insp.: 2010/02/11

(45) Date de délivrance/Issue Date: 2021/05/04

(62) Demande originale/Original Application: 2 944 734

(30) Priorités/Priorities: 2008/08/04 (US61/085,956);
2008/08/11 (US61/087,934); 2008/09/11 (US61/096,278);
2009/02/26 (US12/393,884); 2009/02/26 (US12/393,768)

(51) Cl.Int./Int.Cl. *A61L 27/54* (2006.01),
A61K 31/167 (2006.01), *A61K 8/04* (2006.01),
A61K 8/73 (2006.01), *A61L 27/20* (2006.01),
A61L 27/52 (2006.01), *A61P 23/00* (2006.01),
A61Q 19/08 (2006.01)

(72) Inventeur/Inventor:
LEBRETON, PIERRE F., FR

(73) Propriétaire/Owner:
ALLERGAN INDUSTRIE, SAS, FR

(74) Agent: GOWLING WLG (CANADA) LLP

(54) Titre : GELS A BASE D'ACIDE HYALURONIQUE COMPRENANT DES AGENTS ANESTHESIQUES

(54) Title: HYALURONIC ACID-BASED GELS INCLUDING LIDOCAINE

(57) Abrégé/Abstract:

Disclosed herein are cohesive soft tissue fillers, for example, dermal and subdermal fillers, based on hyaluronic acids and pharmaceutically acceptable salts thereof. In one aspect, hyaluronic acid-based compositions described herein include a therapeutically effective amount of at least one anesthetic agent, for example, lidocaine. The present hyaluronic acid-based compositions including lidocaine have an enhanced stability and cohesivity, relative to conventional compositions including lidocaine, for example when subjected to sterilization techniques or when stored for long periods of time. Methods and processes of preparing such hyaluronic acid-based compositions are also provided.

Abstract

Disclosed herein are cohesive soft tissue fillers, for example, dermal and subdermal fillers, based on hyaluronic acids and pharmaceutically acceptable salts thereof. In one aspect, hyaluronic acid-based compositions described herein include a therapeutically effective amount of at least one anesthetic agent, for example, lidocaine. The present hyaluronic acid-based compositions including lidocaine have an enhanced stability and cohesivity, relative to conventional compositions including lidocaine, for example when subjected to sterilization techniques or when stored for long periods of time. Methods and processes of preparing such hyaluronic acid-based compositions are also provided.

HYALURONIC ACID-BASED GELS INCLUDING LIDOCAINE**FIELD OF THE INVENTION**

15 [0002] The present invention generally relates to injectable soft tissue fillers and more specifically relates to hyaluronic acid-based dermal and subdermal fillers including an anesthetic agent.

BACKGROUND

20 [0003] It is generally accepted that as a person ages, the face begins to show effects of gravity, sun-exposure, and years of facial muscle movement, such as smiling, frowning, chewing and squinting. The underlying tissues that keep the skin appearing youthful begin to break down, often resulting in laugh lines, smile lines, "crow's feet" and facial creases often referred to as the "effects of aging."

25 [0004] In an effort to treat or correct the effects of aging, soft tissue fillers have been developed to help fill in facial lines and depressions and for restoring fat loss-related tissue volume loss. The soft tissue fillers thereby temporarily restore a smoother, more youthful appearance.

30 [0005] Ideally, soft tissue fillers are long-lasting, soft, smooth and natural appearing when implanted in the skin or beneath the skin. Further, soft tissue fillers are easy to implant into a patient using a fine gauge needle and require low extrusion force for injection. Ideal fillers would also cause no adverse

side effects, and would be injectable with minimal or no discomfort to the patient.

5 [0006] Collagen based soft tissue fillers were developed over 20 years ago, and for some time, bovine collagen-based fillers were the only U.S. Food and Drug Administration (FDA)-approved dermal fillers. Because these dermal fillers are bovine based, one of the main disadvantages has been the potential for allergic reaction in patients. It is believed that approximately 3-5% of human subjects show serious allergic reactions to bovine collagen, thus requiring careful testing before using these fillers in any particular person. In addition to allergic reactions, collagen based fillers degrade rapidly upon
10 injection and require frequent treatments to sustain a smoother, more youthful appearance.

[0007] In February 2003, human-derived collagen filler compositions received FDA approval. These collagens provide the advantage of a
15 significantly reduced risk of allergic reactions. However, despite the reduced incidence of allergic reactions, the human derived collagen fillers still suffered from the rapid degradation of the injected product.

[0008] The search for fillers that do not provoke allergic reactions and sustain a smoother, more youthful appearance has brought about the
20 development of hyaluronic acid (HA)-based products. In December 2003, the first HA-based filler was approved by the FDA. This was rapidly followed by the development of other HA-based fillers.

[0009] HA, also known as hyaluronan, is a naturally occurring, water soluble polysaccharide, specifically a glycosaminoglycan, which is a major
25 component of the extra-cellular matrix and is widely distributed in animal tissues. HA has excellent biocompatibility and does not cause allergic reactions when implanted into a patient. In addition, HA has the ability to bind to large amounts of water, making it an excellent volumizer of soft tissues.

[0010] The development of HA-based fillers which exhibit ideal *in vivo*
30 properties as well as ideal surgical usability has proven difficult. For example,

HA-based fillers that exhibit desirable stability properties *in vivo*, can be so highly viscous that injection through fine gauge needles is difficult. Conversely, HA-based fillers that are relatively easily injected through fine gauge needles often have relatively inferior stability properties *in vivo*.

- 5 [0011] One method to overcome this problem is to use crosslinked HA-based fillers. Crosslinked HA is formed by reacting free HA with a crosslinking agent under suitable reaction conditions. Methods of preparing HA based soft tissue fillers including both crosslinked and free HA are well known.
- 10 [0012] It has been proposed to incorporate certain therapeutic agents, for example, anesthetic agents such as lidocaine, into injectable HA-based compositions. Unfortunately, HA-based injectable compositions which incorporate lidocaine during the manufacturing process are prone to partial or almost complete degradation prior to injection, particularly during high
- 15 temperature sterilization steps and/or when placed in storage for any significant length of time.

- [0013] It is an objective of the HA-based soft filler compositions and methods of making and using them as described herein to provide soft tissue fillers that do not cause allergic reactions in patients, are biocompatible and
- 20 are stable and usable *in vivo* and include one or more local anesthetic agents.

SUMMARY

- [0014] The present description relates to soft tissue fillers, for example, dermal and subdermal fillers, based on hyaluronic acid (HA) and
- 25 pharmaceutically acceptable salts of HA, for example, sodium hyaluronate (NaHA). HA-based compositions described herein include a therapeutically effective amount of at least one anesthetic agent. In one embodiment, for example, the anesthetic agent is lidocaine. The present HA-based compositions including at least one anesthetic agent have an enhanced
- 30 stability, relative to conventional HA-based compositions including, for

example, lidocaine, when subjected to sterilization techniques such as autoclaving, and/or when stored for long periods at ambient temperature. Methods for preparing such HA-based compositions are also provided as well as products made by such methods.

5 **[0015]** Described herein are soft tissue filler compositions, the compositions generally comprising: a hyaluronic acid component crosslinked with a crosslinking agent selected from the group consisting of 1,4-butanediol diglycidyl ether (BDDE), 1,4-bis(2,3-epoxypropoxy)butane, 1,4-bisglycidylloxybutane, 1,2-bis(2,3-epoxypropoxy)ethylene and 1-(2,3-
10 epoxypropyl)-2,3-epoxycyclohexane, and 1,4-butanediol diglycidyl ether; and at least one anesthetic agent combined with the crosslinked HA component.

[0016] In yet another embodiment, the at least one anesthetic agent is lidocaine. In a further embodiment, the amount of the anesthetic agent is present at a concentration between about 0.1% and about 5.0% by weight of
15 the composition. In still another embodiment, the anesthetic agent is present at a concentration between about 0.2% and about 1.0% by weight of the composition. In one embodiment, the anesthetic agent is lidocaine and is present at a concentration of about 0.3% by weight of the composition.

[0017] In still another embodiment, the soft tissue filler composition has an
20 extrusion force of between about 10 N and about 13 N, for example, at a rate of about 12.5 mm/minute. In yet another embodiment, the composition has a viscosity of between about 5 Pa*s and about 450 Pa*s, for example, when measured at about 5 Hz.

[0018] In one embodiment, the HA component is a gel, for example, a
25 cohesive, hydrated gel. In one embodiment, the HA component is a crosslinked HA gel having no greater than about 1% to about 10% free HA. For purposes of this disclosure, free HA includes truly free HA as well as lightly crosslinked HA chains and fragments, all in soluble form in water.

[0019] In yet other embodiments, the HA component comprises greater than about 10%, for example, greater than about 15%, for example, up to or greater than about 20% free HA.

5 [0020] In yet another embodiment, the HA component is a gel comprising particles of crosslinked HA in a relatively fluidic medium of free HA. In some embodiments, the HA component has an average particle size of greater than about 200 μm , for example, greater than about 250 μm .

[0021] Further described herein is a soft tissue filler composition comprising: a HA component crosslinked with 1,4-butanediol diglycidyl ether
10 (BDDE), said HA component having a degree of crosslinking of less than about 5%, for example, about 2%, and an anesthetic component having a concentration between about 0.1% and about 5.0% by weight of the soft tissue filler composition, wherein the anesthetic is lidocaine.

[0022] Further described herein are methods of preparing soft tissue filler
15 compositions, the methods comprising the steps of: providing a HA component crosslinked with at least one crosslinking agent selected from the group consisting of 1,4-butanediol diglycidyl ether (BDDE), 1,4-bis(2,3-epoxypropoxy)butane, 1,4-bisglycidyl ether, 1,2-bis(2,3-epoxypropoxy)ethylene and 1-(2,3-epoxypropyl)-2,3-epoxycyclohexane, and
20 1,4-butanediol diglycidyl ether or combinations thereof; adjusting the pH of said HA component to an adjusted pH above about 7.2; and adding a solution containing at least one anesthetic agent to the HA component having the adjusted pH to obtain a HA-based filler composition.

[0023] In another embodiment, the composition is sterilized, for example,
25 by autoclaving, to form a sterilized composition and wherein the sterilized composition is stable at ambient temperature for at least about months, for example, at least 9 months, at least about 12 months, for example, at least about 36 months, or more.

[0024] In still another embodiment, the adjusted pH is above about 7.5. In
30 another embodiment, the method further comprises the step of homogenizing

the HA component during or after the step of adding the solution containing the at least one anesthetic agent. In a further embodiment, the step of homogenizing comprises subjecting the composition to mixing with a controlled shear.

5 **[0025]** In another embodiment, the step of providing a HA component comprises providing dry free NaHA material and hydrating the dry free NaHA material in an alkaline solution to obtain an alkaline, free NaHA gel. In yet another embodiment, the alkaline, free NaHA gel has a pH greater than about 8.0. In still another embodiment the pH is greater than about 10.

10 **[0026]** In a further embodiment, the HA component comprises greater than about 20% free HA and the crosslinked portion of the HA component has a degree of crosslinking of less than about 6% or less than about 5%.

15 **[0027]** In still a further embodiment, the soft tissue filler composition has a particulate nature in that it comprises particles of crosslinked HA dispersed in a fluid soluble HA medium. In some embodiments, the average size of such particles is at least about 200 μm , and in other embodiments the average size of such particles is at least about 250 μm .

20 **[0028]** Further described herein is a soft tissue filler composition comprising: a hyaluronic acid (HA) component crosslinked with 1,4-butanediol diglycidyl ether (BDDE), said HA component having a degree of crosslinking of less than about 5%, and an anesthetic component having a concentration between about 0.1% and about 5.0% by weight of the soft tissue filler composition, wherein the anesthetic is lidocaine.

25 **[0029]** In a specific embodiment of the invention, a method of preparing a soft tissue filler composition is further described, the method comprising the steps of: providing dry free NaHA material and hydrating the dry free NaHA material in an alkaline solution to obtain an alkaline, free NaHA gel; crosslinking the free NaHA gel with BDDE to form a crosslinked alkaline HA composition with a degree of crosslinking less than about 5% and a pH above
30 about 7.2; adding a solution containing lidocaine HCl to the HA component

having the adjusted pH to obtain said HA-based filler composition; homogenizing the HA-based filler composition thereby forming a homogenized HA-based filler composition; and sterilizing the homogenized HA-based filler composition thereby forming a sterilized HA-based filler composition, wherein the soft tissue filler composition has a particle size of greater than about 200 μm , for example, a particle size of greater than about 250 μm .

BRIEF DESCRIPTION OF THE DRAWINGS

10 **[0030]** Figure 1 graphically illustrates the viscosity of Sample 1 prepared without lidocaine, with lidocaine and pH adjustment during formation and with lidocaine but without pH adjustment during formation versus the shear frequency.

15 **[0031]** Figure 2 graphically illustrates the viscosity of Sample 2 prepared without lidocaine, with lidocaine and pH adjustment during formation and with lidocaine but without pH adjustment during formation versus the shear frequency.

20 **[0032]** Figure 3 graphically illustrates the viscosity of Sample 3 prepared without lidocaine, with lidocaine and pH adjustment during formation and with lidocaine but without pH adjustment during formation versus the shear frequency.

25 **[0033]** Figure 4 graphically illustrates the viscosity of Sample 4 prepared without lidocaine, with lidocaine and pH adjustment during formation and with lidocaine but without pH adjustment during formation versus the shear frequency.

[0034] Figure 5 graphically illustrates the viscosity of Sample 5 prepared without lidocaine, with lidocaine and pH adjustment during formation and with lidocaine but without pH adjustment during formation versus the shear frequency.

[0035] Figure 6 graphically illustrates the relative viscosity/elasticity characteristics of Sample 5 prepared without lidocaine, with lidocaine and pH adjustment during formation and with lidocaine but without pH adjustment during formation versus the shear frequency.

5 **[0036]** Figure 7 graphically illustrates the viscosity of Sample 6 prepared without lidocaine, with lidocaine and pH adjustment during formation and with lidocaine but without pH adjustment during formation versus the shear frequency.

10 **[0037]** Figure 8 graphically illustrates the relative viscosity/elasticity characteristics of Sample 6 prepared without lidocaine, with lidocaine and pH adjustment during formation and with lidocaine but without pH adjustment during formation versus the shear frequency.

[0038] Figure 9 graphically illustrates the lidocaine concentration in the gel from Sample 5 in Example 4 made by the procedure of Test 2 versus time.

15

DEFINITIONS

[0039] Certain terms as used in the specification are intended to refer to the following definitions, as detailed below. Where the definition of terms departs from the commonly used meaning of the term, applicant intends to utilize the definitions provided below, unless specifically indicated.

20 **[0040]** Autoclave stable or stable to autoclaving as used herein describes a product or composition that is resistant to degradation such that the product or composition maintains at least one, and preferably all, of the following aspects after effective autoclave sterilization: transparent appearance, pH, extrusion force and/or rheological characteristics, hyaluronic acid (HA)
25 concentration, sterility, osmolarity, and lidocaine concentration.

[0041] Centrifugation as used herein refers to the process of using centrifugal forces to evenly distribute substances of greater and lesser density. Centrifugation is commonly used to separate a liquid phase from a solid or gel phase. Substantial phase separations resulting from
30 centrifugation would be at least those visible by the naked eye, for example, a

liquid phase and a solid phase distinctly separated when viewed with the naked eye.

[0042] High molecular weight HA as used herein describes a HA material having a molecular weight of at least about 1.0 million Daltons ($mw \geq 10^6$ Da or 1 MDa) to about 4.0 MDa. For example, the high molecular weight HA in the present compositions may have a molecular weight of about 2.0 MDa. In another example, the high molecular weight HA may have a molecular weight of about 2.8 MDa.

[0043] Low molecular weight HA as used herein describes a HA material having a molecular weight of less than about 1.0 MDa. Low molecular weight HA can have a molecular weight of between about 200,000 Da (0.2 MDa) to less than about 1.0 MDa, for example, between about 300,000 Da (0.3 MDa) to about 750,000 Da. (0.75 MDa).

[0044] Degree of Crosslinking as used herein refers to the intermolecular junctions joining the individual HA polymer molecules, or monomer chains, into a permanent structure, or as disclosed herein the soft tissue filler composition. Moreover, degree of crosslinking for purposes of the present disclosure is further defined as the percent weight ratio of the crosslinking agent to HA-monomeric units within the crosslinked portion of the HA based composition. It is measured by the weight ratio of HA monomers to crosslinker (HA monomers:crosslinker).

[0045] Free HA as used herein refers to individual HA polymer molecules that are not crosslinked to, or very lightly crosslinked to (very low degree of crosslinking) the highly crosslinked (higher degree of crosslinking) macromolecular structure making up the soft tissue filler composition. Free HA generally remains water soluble. Free HA can alternatively be defined as the "uncrosslinked," or lightly crosslinked component of the macromolecular structure making up the soft tissue filler composition disclosed herein.

[0046] Cohesive as used herein is the ability of a HA-based composition to retain its shape and resist deformation. Cohesiveness is affected by,

among other factors, the molecular weight ratio of the initial free HA, the degree of crosslinking, the amount of residual free HA following crosslinking, and HA-based composition pH. Moreover, a cohesive HA-based composition resists phase separation when tested according to the method disclosed at Example 1 herein.

DETAILED DESCRIPTION

[0047] The present disclosure generally relates to soft tissue fillers, for example, dermal and subdermal fillers, based on hyaluronic acids (HA) and pharmaceutically acceptable salts of HA, for example, sodium hyaluronate (NaHA). In one aspect, HA-based compositions described herein include a therapeutically effective amount of at least one anesthetic agent, for example, lidocaine. The present HA-based compositions including at least one anesthetic agent have an enhanced stability, relative to conventional HA-based compositions including, for example, lidocaine, when subjected to high temperatures and pressures, for example, those experienced during heat and/or pressure sterilization techniques, for example, autoclaving, and/or for example, when stored at ambient temperature for an extended period of time.

[0048] The stable compositions maintain at least one of, or all of, the following aspects after effective autoclave sterilization and/or prolonged storage: transparent appearance, pH for use in a patient, extrusion force and/or rheological characteristics, HA concentration, sterility, osmolarity, and lidocaine concentration. Methods or processes of preparing such HA-based compositions are also provided as well as products made by such methods or processes.

[0049] As used herein, hyaluronic acid (HA) can refer to any of its hyaluronate salts, and includes, but is not limited to, sodium hyaluronate (NaHA), potassium hyaluronate, magnesium hyaluronate, calcium hyaluronate, and combinations thereof.

[0050] Generally, the concentration of HA in the compositions described herein is preferably at least 10 mg/mL and up to about 40 mg/mL. For example, the concentration of HA in some of the compositions is in a range between about 20 mg/mL and about 30 mg/mL. Further, for example, in
 5 some embodiments, the compositions have a HA concentration of about 22 mg/mL, about 24 mg/mL, about 26 mg/mL, or about 28 mg/mL.

[0051] In addition, the concentration of one or more anesthetics is in an amount effective to mitigate pain experienced upon injection of the composition. The at least one local anesthetic can be selected from the group
 10 of ambucaine, amolanone, amylocaine, benoxinate, benzocaine, betoxycaine, biphenamine, bupivacaine, butacaine, butamben, butanilicaine, butethamine, butoxycaine, carticaine, chloroprocaine, cocaethylene, cocaine, cyclomethycaine, dibucaine, dimethysquin, dimethocaine, diperodon, dycyclonine, ecgonidine, ecgonine, ethyl chloride, etidocaine, beta-eucaine,
 15 euprocine, fenalcomine, formocaine, hexylcaine, hydroxytetracaine, isobutyl p-aminobenzoate, leucinocaine mesylate, levoxadrol, lidocaine, mepivacaine, meprylcaine, metabutoxycaine, methyl chloride, myrtecaine, naepaine, octacaine, orthocaine, oxethazaine, parethoxycaine, phenacaine, phenol, piperocaine, piridocaine, polidocanol, pramoxine, prilocaine, procaine,
 20 propanocaine, proparacaine, propipocaine, propoxycaine, psuedococaine, pyrrocaine, ropivacaine, salicyl alcohol, tetracaine, tolycaine, trimecaine, zolamine, and salts thereof. In one embodiment, the at least one anesthetic agent is lidocaine, such as in the form of lidocaine HCl. The compositions described herein may have a lidocaine concentration of between about 0.1%
 25 and about 5% by weight of the composition, for example, about 0.2% to about 1.0% by weight of the composition. In one embodiment, the composition has a lidocaine concentration of about 0.3% of the composition. The concentration of lidocaine in the compositions described herein can be therapeutically effective meaning the concentration is adequate to provide a
 30 therapeutic benefit without inflicting harm to the patient.

[0052] In one aspect of the invention, a method is provided for preparing a HA-based composition including an effective amount of lidocaine wherein the method comprises providing a precursor composition comprising a cohesive crosslinked HA-based gel, adding a solution containing lidocaine, for example
5 in the form of lidocaine HCl, thereto and homogenizing the mixture to obtain a cohesive, at least partially crosslinked, HA-based composition including lidocaine that is stable to autoclaving. The cohesive, crosslinked HA-based gel includes no greater than about 1% to about 10% of free HA material by volume, for example, no greater than about 5% free HA material.

10 **[0053]** In some embodiments of the present invention, the HA component of the present compositions, hereinafter sometimes, "precursor composition" is a hydrated, cohesive gel. A cohesive gel, relative to a non-cohesive gel, is better able retain its shape and resist deformation, for example, after being subjected to shear or other stresses. It has been discovered by the present
15 inventor that such cohesive gels are less likely to substantially degrade or become unstable over time or when subjected to external stimuli such as sterilization, relative to non-cohesive gels.

[0054] Without intending to be bound by any particular theory of operability, it is believed that the cohesivity of the precursor composition in
20 some embodiments of the invention acts to substantially or entirely prevent or impede any breakdown or degradation of the crosslinked HA in the composition with the addition of lidocaine.

[0055] It is believed that such degradation may primarily occur because many, perhaps most crosslinked HA based gels are conventionally
25 manufactured in a manner that produces gels which are not sufficiently cohesive to prevent such degradation when lidocaine is added. It has now been discovered that the addition of lidocaine to sufficiently cohesive crosslinked HA-based compositions does not cause substantial or significant degradation of the compositions, and the compositions maintain their integrity
30 in terms of rheology, viscosity, appearance and other characteristics even when stored for a lengthy period of time, for example, for a period of time of at

least about 6 months, about 9 months, about 12 months, or about 36 months or greater, for example, at ambient temperatures, and even after being subjected to sterilization procedures, for example, autoclaving.

5 [0056] It is a surprising discovery that formulations of crosslinked HA-based compositions including lidocaine can be manufactured in a manner to produce sterilization-stable, injectable HA/lidocaine compositions.

10 [0057] Further described herein is a method for preparing stable HA-based compositions containing an effective amount of lidocaine by preparing a precursor composition, for example, a cohesive, crosslinked HA-based gel, adding lidocaine chlorhydrate to the gel to form a HA/lidocaine gel mixture, and homogenizing the mixture, to obtain a crosslinked HA-based composition that is stable to autoclaving.

15 [0058] In certain embodiments, the precursor composition is a cohesive, hydrated HA-based gel. Such a "cohesive" gel will generally include no greater than between about 1% to about 10% soluble-liquid form or free HA by volume. Such cohesive gels are considered by some in the industry to be monophasic, or substantially single-phase compositions, in that less than about 1% to about 10% of the composition comprises free HA.

20 [0059] In yet other embodiments, the precursor composition is a relatively non-cohesive, hydrated HA-based gel. Such a "non-cohesive" gel generally includes greater than 10%, for example, greater than about 15%, for example, greater than 20% or more of free HA.

25 [0060] In some embodiments, the precursor composition may comprise a first component made up of relatively highly crosslinked HA in a substantially solid phase, and a second component comprising free or relatively less crosslinked HA in a substantially fluidic phase in which the relatively highly crosslinked HA is dispersed.

30 [0061] In some embodiments, the present compositions have a somewhat particulate nature and comprise particles of relatively highly crosslinked HA dispersed in a medium of free HA. In some embodiments, the average size of

such particles of crosslinked HA is at least about 200 μm or at least about 250 μm . Such particulate compositions are generally less cohesive than otherwise similar compositions which have no discernable particles, or have particles having an average size of less than 200 μm .

- 5 **[0062]** For example, in some embodiments, the precursor composition may be manufactured by pressing a mass of relatively highly crosslinked HA-based gel through a sieve or a mesh to create relatively highly crosslinked HA particles of generally uniform size and shape. These particles are then mixed with a carrier material, for example, an amount of free HA to produce a gel.
- 10 **[0063]** In other embodiments, a method of preparing a HA-based composition including an effective amount of lidocaine is provided wherein the method comprises providing a precursor composition including a substantially pH neutral, at least partially crosslinked HA-based gel and adjusting the pH of the gel to a pH of greater than about 7.2, for example, about 7.5 to about 8.0.
- 15 The method further comprises the step of combining a solution containing lidocaine, for example in the form of lidocaine HCl, with the slightly alkaline gel after the pH has been so adjusted and obtaining a HA-based composition including lidocaine that is stable to autoclaving.
- 20 **[0064]** Another method of preparing a stable HA-based composition containing an effective amount of lidocaine, as described elsewhere herein, generally comprises the steps of: providing purified NaHA material, for example, in the form of fibers; hydrating the material; and crosslinking the hydrated material with a suitable crosslinking agent to form a crosslinked HA-based gel. The method further comprises the steps of neutralizing and
- 25 swelling the gel, and adding to the gel a solution containing lidocaine, preferably an acidic salt of lidocaine chlorhydrate, to form a HA/lidocaine gel. Further still, the method further comprises homogenizing the HA/lidocaine gel and packaging the homogenized HA/lidocaine gel, for example, in syringes for dispensing. The syringes are then sterilized by autoclaving at an effective
- 30 temperature and pressure. In accordance with the present description, the packaged and sterilized cohesive NaHA/lidocaine gels exhibit enhanced

stability relative to HA-based compositions including lidocaine which are made using conventional methods.

5 [0065] The present products and compositions are considered to be sterile when exposed to temperatures of at least about 120°C to about 130°C and/or pressures of at least about 12 pounds per square inch (PSI) to about 20 PSI during autoclaving for a period of at least about 1 minute to about 15 minutes.

10 [0066] The present products and compositions also remain stable when stored for long periods of time at room temperature. Preferably, the present compositions remain stable for a period of at least about two months, or at least about six months, or at least about 9 months, or at least about 12 months, or at least about 36 months, at temperatures of at least about 25°C. In a specific embodiment, the compositions are stable at a temperature up to about 45°C for a period of at least two months.

15 [0067] The manufacturing process includes, in one embodiment, the initial step of providing raw HA material in the form of dry HA fibers or powder. The raw HA material may be HA, its salts and/or mixtures thereof. In a preferred embodiment, the HA material comprises fibers or powder of NaHA, and even more preferably, bacterial-sourced NaHA. In some aspects of the present description, the HA material may be animal derived. The HA material may be a combination of raw materials including HA and at least one other polysaccharide, for example, glycosaminoglycan (GAG).

20 [0068] In some embodiments, the HA material in the compositions nearly entirely comprises or consists of high molecular weight HA. That is, nearly 100% of the HA material in the present compositions may be high molecular weight HA as defined above. In other embodiments, the HA material in the compositions comprises a combination of relatively high molecular weight HA and relatively low molecular weight HA, as defined above.

30 [0069] The HA material of the compositions may comprise between about 5% to about 95% high molecular weight HA with the balance of the HA

material including low molecular weight HA. In one embodiment of the invention, the ratio of high molecular weight to low molecular weight HA is at least about, and preferably greater than 2 ($w/w \geq 2$) with the high molecular weight HA having a molecular weight of above 1.0 MDa.

5 [0070] It will be appreciated by those of ordinary skill in the art that the selection of high and low molecular weight HA material and their relative percentages or ratios is dependent upon the desired characteristics, for example, extrusion force, elastic modulus, viscous modulus and phase angle expressed as the ratio of viscous modulus to elastic modulus, cohesivity, etc.
10 of the final HA-based product. For additional information that may be helpful in understanding this and other aspects of the present disclosure, see Lebreton, U.S. Patent Application Publication No. 2006/0194758.

[0071] The HA-based gels can be prepared according to the present
15 description by first cleaning and purifying dry or raw HA material having a desired high/low molecular weight ratio. These steps generally involve hydrating the dry HA fibers or powder in the desired high/low molecular weight ratio, for example, using pure water, and filtering the material to remove large foreign matters and/or other impurities. The filtered, hydrated material is then
20 dried and purified. The high and low molecular weight HA may be cleaned and purified separately, or may be mixed together, for example, in the desired ratio, just prior to crosslinking.

[0072] In one aspect of the present disclosure, pure, dry NaHA fibers are hydrated in an alkaline solution to produce a free NaHA alkaline gel. Any
25 suitable alkaline solution may be used to hydrate the NaHA in this step, for example, but not limited to aqueous solutions containing sodium hydroxide (NaOH), potassium hydroxide (KOH), sodium bicarbonate (NaHCO_3), lithium hydroxide (LiOH), and the like. In another embodiment, the suitable alkaline solution is aqueous solutions containing NaOH. The resulting alkaline gel will
30 have a pH above 7.5. The pH of the resulting alkaline gel can have a pH

greater than 9, or a pH greater than 10, or a pH greater than 12, or a pH greater than 13.

5 [0073] The next step in the manufacturing process involves the step of crosslinking the hydrated, alkaline NaHA gel with a suitable crosslinking agent. The crosslinking agent may be any agent known to be suitable for crosslinking polysaccharides and their derivatives via their hydroxyl groups. Suitable crosslinking agents include, but are not limited to, 1,4-butanediol diglycidyl ether (or 1,4-bis(2,3-epoxypropoxy)butane or 1,4-bisglycidyloxybutane, all of which are commonly known as BDDE), 1,2-
10 bis(2,3-epoxypropoxy)ethylene and 1-(2,3-epoxypropyl)-2,3-epoxycyclohexane. The use of more than one crosslinking agent or a different crosslinking agent is not excluded from the scope of the present disclosure. In one aspect of the present disclosure, the HA gels described herein are crosslinked using BDDE.

15 [0074] The step of crosslinking may be carried out using any means known to those of ordinary skill in the art. Those skilled in the art appreciate how to optimize conditions of crosslinking according to the nature of the HA, and how to carry out crosslinking to an optimized degree.

[0075] Degree of crosslinking for purposes of the present disclosure is
20 defined as the percent weight ratio of the crosslinking agent to HA-monomeric units within the crosslinked portion of the HA based composition. It is measured by the weight ratio of HA monomers to crosslinker (HA monomers:crosslinker).

[0076] The degree of crosslinking in the HA component of the present
25 compositions is at least about 2% and is up to about 20%.

[0077] In other embodiments, the degree of crosslinking is greater than 5%, for example, is about 6% to about 8%.

[0078] In some embodiments, the degree of crosslinking is between about 4% to about 12%. In some embodiments, the degree of crosslinking is less
30 than about 6%, for example, is less than about 5%.

[0079] In some embodiments, the HA component is capable of absorbing at least about one time its weight in water. When neutralized and swollen, the crosslinked HA component and water absorbed by the crosslinked HA component is in a weight ratio of about 1:1. The resulting hydrated HA-based
5 gels have a characteristic of being highly cohesive.

[0080] The HA-based gels in accordance with some embodiments of the invention may have sufficient cohesivity such that the gels will not undergo substantial phase separation after centrifugation of the gel at 2000 rd/min for 5 minutes. In another embodiment, the gels have the characteristic of being
10 capable of absorbing at least one time their weight of water and have sufficient cohesivity such that when swollen with water at a gel/water weight ratio of about 1:1, the gels maintain their integrity, for example, when subjected to centrifugation.

[0081] The hydrated crosslinked, HA gels may be swollen to obtain the
15 desired cohesivity. This step can be accomplished by neutralizing the crosslinked, hydrated HA gel, for example by adding an aqueous solution containing of an acid, such as HCl. The gels are then swelled in a phosphate buffered saline (PBS) solution for a sufficient time and at a low temperature.

[0082] In one embodiment, the resulting swollen gels are highly cohesive
20 with no visible distinct particles, for example, no visibly distinct particles when viewed with the naked eye. In one embodiment, the gels have no visibly distinct particles under a magnification of less than 35X.

[0083] The cohesive, substantially single-phase gels are now purified by conventional means such as, dialysis or alcohol precipitation, to recover the
25 crosslinked material, to stabilize the pH of the material and to remove any un-reacted crosslinking agent. Additional water or a slightly alkaline aqueous solution can be added to bring the concentration of the NaHA to a desired concentration.

[0084] The pH of the purified, substantially pH neutral, crosslinked HA
30 gels are preferably adjusted to cause the gels to become slightly alkaline such

that the gels have a pH of greater than about 7.2, for example, about 7.5 to about 8.0. This step may be accomplished by any suitable means, for example, by adding a suitable amount of dilute NaOH, KOH, NaHCO₃ or LiOH, to the gels or any other alkaline molecule, solution and/or buffering composition know by one skilled in the art.

[0085] An effective amount of lidocaine, such as lidocaine HCl, is then added to the purified cohesive NaHA gels. For example, in some embodiments, the lidocaine HCl is provided in a powder form which is solubilized using water for injection (WFI). The gels are kept neutral with a buffer or by adjustment with diluted NaOH in order that the final HA/lidocaine composition will have a desired, substantially neutral pH. The final HA-based filler compositions including lidocaine have a lidocaine concentration of between at least about 0.1% and about 5%, for example, about 2% w/w of the composition, or in another example about 0.3%.

[0086] After the addition of the lidocaine HCl, or alternatively, during the addition of the lidocaine HCl, the HA/lidocaine gels, or compositions, are homogenized to create highly homogenous cohesive HA/lidocaine gels having a desired consistency and stability. The homogenization step may comprise mixing, stirring, or beating the gels with a controlled shearing force to obtain a substantially homogenous mixture.

[0087] The HA/lidocaine compositions described herein display a viscosity which is dependent on the composition's properties and the presence of at least one anesthetic agent. The viscosity of the HA/lidocaine compositions can be from about 50 Pa*s to about 450 Pa*s. In other embodiments, the viscosity can be from about 50 Pa*s to about 300 Pa*s, from about 100 Pa*s to about 400 Pa*s, or about 250 Pa*s to about 400 Pa*s, or about 50 Pa*s to about 250 Pa*s.

[0088] After homogenization, the HA/lidocaine compositions are introduced into syringes and sterilized. Syringes useful according to the present description include any syringe known in the art capable of delivering

viscous dermafiller compositions. The syringes generally have an internal volume of about 0.4 mL to about 3 mL, more preferably between about 0.5 mL and about 1.5 mL or between about 0.8 mL and about 2.5 mL. This internal volume is associated with an internal diameter of the syringe which plays a

5 key role in the extrusion force needed to inject high viscosity dermafiller compositions. The internal diameters are generally about 4 mm to about 9 mm, more preferably from about 4.5 mm to about 6.5 mm or from about 4.5 mm to about 8.8 mm. Further, the extrusion force needed to deliver the HA/lidocaine compositions from the syringe is dependent on the needle

10 gauge. The gauges of needles used generally include gauges between about 18G and about 40G, more preferably about 25G to about 33G or from about 16G to about 25G. A person of ordinary skill in the art can determine the correct syringe dimensions and needle gauge required to arrive at a particular extrusion force requirement.

15 [0089] The extrusion forces displayed by the HA/lidocaine compositions described herein using the needle dimensions described above are at an injection speeds that are comfortable to a patient. Comfortable to a patient is used to define a rate of injection that does not injure or cause excess pain to a patient upon injection to the soft tissue. One skilled in the art will appreciate

20 that comfortable as used herein includes not only patient comfort, but also comfort and ability of the physician or medical technician injecting the HA/lidocaine compositions. Although certain extrusion forces may be achievable with the HA/lidocaine compositions of the present description, one skilled in the art understands that high extrusion forces can lead to lack of

25 control during injection and that such lack of control may result in additional pain to the patient. Extrusion forces of the present HA/lidocaine compositions can be from about 8 N to about 15 N, or more preferably from about 10 N to about 13 N, or about 11 N to about 12 N, for example, at an extrusion rate of about 12.5 mm/min.

[0090] Sterilization, as used herein comprises any method known in the art to effectively kill or eliminate transmissible agents, preferably without substantially altering or degrading the HA/lidocaine compositions.

[0091] One preferable method of sterilization of the filled syringes is by autoclave. Autoclaving can be accomplished by applying a mixture of heat, pressure and moisture to a sample in need of sterilization. Many different sterilization temperatures, pressures and cycle times can be used for this step. For example, the filled syringes may be sterilized at a temperature of at least about 120°C to about 130°C or greater. Moisture may or may not be utilized. The pressure applied is in some embodiments depending on the temperature used in the sterilization process. The sterilization cycle may be at least about 1 minute to about 20 minutes or more.

[0092] Another method of sterilization incorporates the use of a gaseous species which is known to kill or eliminate transmissible agents. Preferably, ethylene oxide is used as the sterilization gas and is known in the art to be useful in sterilizing medical devices and products.

[0093] A further method of sterilization incorporates the use of an irradiation source which is known in the art to kill or eliminate transmissible agents. A beam of irradiation is targeted at the syringe containing the HA/lidocaine solution, and the wavelength of energy kills or eliminates the unwanted transmissible agents. Preferable energy useful include, but is not limited to ultraviolet (UV) light, gamma irradiation, visible light, microwaves, or any other wavelength or band of wavelengths which kills or eliminates the unwanted transmissible agents, preferably without substantially altering or degrading the HA/lidocaine composition.

[0094] Further described are, in another embodiment, methods of manufacturing cohesive HA-based compositions generally comprising the steps of providing a crosslinked HA-based gel without an anesthetic, (hereinafter, sometimes, a precursor gel) adjusting the pH of the precursor gel to obtain a gel having a pH of between about 7.2 and 8.0, and adding a

suitable amount of lidocaine, or other anesthetic agent, to the pH-adjusted gels to obtain cohesive HA-based compositions that include an anesthetic agent. In one embodiment, the precursor gel is a highly cohesive, substantially single phase gel comprising no greater than about 1% to about 5 10% free HA by volume, for example, no greater than about 10% free HA by volume. In another embodiment, the precursor gel is a relatively less cohesive gel comprising at least 10% to about 20% or more free HA by volume.

Example 1

Method for testing for cohesivity of gel

10 [0095] For purposes of example only and not to be considered as limiting the present invention in any way, the following tests may be performed in order to evidence or quantify cohesivity of a HA-based gel composition.

[0096] First, 0.2 g or 0.4 g of a gel composition to be tested is placed in a 15 glass syringe. Next, 0.2 g or more of phosphate buffer is added to the syringe and the mixture is thoroughly mixed for about 1 hour to obtain a homogenous mixture. Then, the homogenized mixture is centrifuged for 5 min at 2000 tr/min to remove the air bubbles and to allow the decantation of any particles. The syringe is then held in a vertical position and one drop of eosin colorant is 20 deposited at the surface of the gel by means of a syringe and an 18G needle. After 10 min, the dye has slowly diffused through the gel.

[0097] After dilution of the gel, homogenization and decantation, a 25 relatively low cohesivity gel shows a phase separation (an upper diluted less viscous phase without particles and a lower one composed of decanted particles that are visible with the naked eye or under microscope). Under the same conditions, a highly cohesive gel shows substantially no phase separation, and the dye is prevented from diffusing into the cohesive formulation. A relatively less cohesive gel, on the other hand, shows a clear phase separation.

30

Example 2**Synthesis of a Soft Tissue Filler with Lidocaine**

5 [0098] NaHA fibers or powder are hydrated in an alkaline solution, for example, an aqueous solution containing NaOH. The mixture is mixed at ambient temperature, about 23°C, to form a substantially homogenous, alkaline HA gel.

[0099] A crosslinking agent, BDDE, is diluted in an aqueous solution and added to the alkaline HA gel. The mixture is homogenized for several minutes.

10 [00100] Alternatively, BDDE can be added directly to the HA fibers (dry state) at the beginning of the process, prior to the hydration. The crosslinking reaction will then start relatively slowly at ambient temperature, ensuring even better homogeneity and efficacy of the crosslinking. Methods of crosslinking polymers in the dry state using a polyfunctional crosslinking agent such as
15 BDDE are described in, for example, Piron et al., U.S. Patent No. 6,921,819.

[00101] The resulting crosslinked HA gel mixture is then heated at about 50°C for about 2.5 hours. The material is now a highly crosslinked HA/BDDE
20 gel (aspect = solid gel). This crosslinked gel is then neutralized with a suitable acidic solution. The neutralized HA gel is then swollen in a phosphate buffer at a cold temperature, for example a temperature of about 5°C, to obtain a highly cohesive HA gel. In this specific example, the phosphate buffered saline solution contains water-for-injection (WFI),
25 disodium hydrogen phosphate, and sodium dihydrogen phosphate. When neutralized and swollen, the crosslinked HA component and water absorbed by the crosslinked HA component is in a weight ratio of about 1:1.

[00102] The cohesive swollen HA gel is then mechanically stirred and filled into dialysis membranes and dialyzed against a phosphate buffer. The HA gel
30 is then filled into dialysis membranes and dialyzed against a phosphate buffer

for up to several days with regular changes of the bath, in order to remove the un-reacted crosslinker, to stabilize the pH close to neutrality (pH=7.2) and to ensure proper osmolarity of the HA gel. The osmolarity of the resulting cohesive HA gel is between about 200 mOsmol and about 400 mOsmol, most preferably about 300 mOsmol.

[00103] After dialysis, the resulting cohesive HA gel has a substantially neutral pH, preferably about 7.2, and no visibly distinct particles in a fluidic media when viewed at a magnification of less than about 35X.

[00104] Lidocaine chlorhydrate (lidocaine HCl) in powder form is first solubilized in WFI and filtered through a 0.2 µm filter. Dilute NaOH solution is added to the cohesive HA gel in order to reach a slightly basic pH (for example, a pH of between about 7.5 and about 8). The lidocaine HCl solution is then added to the slightly basic gel to reach a final desired concentration, for example, a concentration of about 0.3% (w/w). The resulting pH of the HA/lidocaine mixture is then about 7 and the HA concentration is about 24 mg/mL. Mechanical mixing is performed in order to obtain a proper homogeneity in a standard reactor equipped with an appropriate blender mechanism. The resulting composition is cohesive.

[00105] If desired, a suitable amount of free HA gel may be added to the HA/lidocaine gel mixture with the advantage of increasing the kinetics of lidocaine delivery. For example, free HA fibers are swollen in a phosphate buffer solution, in order to obtain a homogeneous viscoelastic gel. This free HA gel is then added to the crosslinked HA/lidocaine gel (for example, at about 5%, w/w). The resulting gel is then filled into sterile syringes and autoclaved at sufficient temperatures and pressures for sterilization for at least about 1 minute.

[00106] After autoclaving, the final HA/lidocaine product is packaged and distributed to physicians. The product manufactured in accordance with this method exhibits one or more characteristics of stability as defined elsewhere herein. For example, the autoclaved HA/lidocaine product has a viscosity,

cohesivity, and extrusion force that are acceptable. No degradation of the HA/lidocaine gel product is found during testing of the product after the product has spent several months in storage.

Example 3

5

Properties of Soft Tissue Fillers

[00107] Properties of HA/lidocaine compositions manufactured in accordance with methods described herein are shown in the Table 1 below. Extrusion force for example was measured using an INSTRON® Advanced Materials Testing System Model 5564 (Instron, Norwood, MA) running BLUEHILL® software version 2.11 (Instron, Norwood, MA). Other rheological data was collected using a Versa test Column with a MECMESIN® dynamometer AGF 100 N (Mecmesin Limited, West Sussex, United Kingdom) running Emperor software and a TERMO FISHER SCIENTIFIC® Rheometer RS600 (Thermo Fisher Scientific, Inc. Corp., Waltham, MA).

15

Table 1

	HA/lidocaine Composition
Appearance	Homogeneous transparent gel
pH	7.2
Extrusion force (N)	10.8N
NaHA Content	23.7 mg/g
Sterility	Sterile ($SAL \leq 10^{-6}$)
Osmolarity	321 mOsm/kg
Lidocaine Content (%)	0.29%
2,6-dimethylaniline content	Conforms

[00108] In order to ensure that product specifications were maintained throughout the shelf life of the composition, multiple studies were performed. In addition, 2,6 dimethylaniline content was measured in order to confirm the absence of lidocaine degradation.

20

[00109] Table 2 provides a summary of stability testing results on the composition manufactured as described herein.

Table 2

Test	HA/lidocaine Composition		
	3 month results	6 month results	9 month results
Aspect Transparent and homogeneous	Conforms	Conforms	Conforms
pH	7.2	7.2	7.2
Extrusion Force (N)	11.9	11.1	11.9
NaHA Concentration (mg/g)	23.8	23.1	24.2
Sterility	Conforms	Conforms	Conforms
Osmolarity (mOsm/kg)	349	329	342
Lidocaine Content (%)	0.29	0.29	0.29
2,6-dimethylaniline content	Conforms	Conforms	Conforms

[00110] It was discovered that at 9 months time (from manufacture date), the composition continues to meet the product specifications.

5

Example 4

Stability of Soft Tissue Fillers

[00111] The following sterilized HA formulations (Samples 1-6) were obtained for testing.

10 [00112] Sample 1 is a free HA mixture 13.5mg/g, with hydroxyl propyl methyl cellulose (HPMC) 5.5 mg/g.

[00113] Sample 2 is contains 5.5-6.5 mg/mL of high molecular weight HA (about 4-6 MDa) and a degree of elasticity (G') of about 200.

[00114] Sample 3 is a non-commercial gel made of distinct gel particles mixed with free HA (80/20, w/w). The HA particles (80%) is obtained by disintegration of a "solid" heavily crosslinked HA gel. The particles have different shapes and dimensions (several microns to several mm).

- 5 **[00115]** Sample 4 is a cohesive crosslinked HA formulation. Sample 4 has a HA concentration of about 18 mg/mL, less than 6% crosslinking, a G' of about 60 and a high molecular weight to low molecular weight HA ratio from about 95% to about 5%, to about 100% high molecular weight HA.

- 10 **[00116]** Sample 5 is a cohesive crosslinked HA formulation. Sample 5 has a HA concentration of about 24 mg/mL, about 6% crosslinking, a G' of about 170 and a high molecular weight to low molecular weight HA ratio from about 95% to 5% to about 100% high molecular weight HA.

- 15 **[00117]** Sample 6 is a cohesive crosslinked HA formulation. Sample 6 has a HA concentration of about 20 mg/mL, about 5% crosslinking, a G' of about 450 and a high molecular weight to low molecular weight HA ratio from about 10% to 90%.

[00118] Each of Samples 1-6 was prepared as follows:

- 20 **[00119]** Test 1: About 20 g of each of Samples 1-6 was individually mixed with a solution of lidocaine chlorhydrate and homogenized. In this test, during the addition of the lidocaine chlorhydrate, the pH of the sample gel is substantially neutral and is not adjusted, for example, with the addition of sodium hydroxide solution. Each of the Samples was then filled into syringes and autoclaved.

- 25 **[00120]** Test 2: About 20 g of each of Samples 1-6 was individually mixed with a solution of lidocaine chlorhydrate, and the pH was adjusted to 7.2 using NaOH solution as described in Example 2 above. Each of the Samples was then filled into syringes and autoclaved.

- 30 **[00121]** Test 3: About 20 g of each of Samples 1-6 was mixed with an equivalent amount of WFI to take into account dilution effect. No lidocaine

was added. Each of the Samples was then filled into syringes and autoclaved.

5 **[00122] Results:** For each of the Samples in Tests 1-3, rheological measurements were performed using the rheological measurement equipment described in Example 3. The results are generally shown graphically in accompanying Figures 1-8. Definitions of symbols and units in Table 3 generally apply to Figures 1-8.

Table 3

Symbol	Name	Units	Description
G'	Elastic Modulus	Pa	Quantifies the solid-like behavior or resistance to permanent deformation.
G''	Viscous Modulus	Pa	Quantifies the liquid-like behavior or resistance to flow.
(G''/G')	Tan Delta		(G''/G') the ratio of the viscous modulus to the elastic modulus and useful for quantifying the extent of elasticity. A value is below 1 means that the fluid is more elastic conversely a value above 1 means the fluid is more viscous.

10

[00123] As a general guideline, a stable Sample including lidocaine prepared according to Test 1 or 2 would exhibit similar viscosity, when subjected to shear across a range of frequencies, as the Samples prepared according to Test 3 which contain no lidocaine.

15 **[00124]** It was discovered that neither of Samples 1 and 2 with lidocaine was stable to autoclaving and as a result, degrade and become substantially less viscous in both Test 1 and Test 2. Figures 1 and 2 in particular illustrate that Samples 1 and 2 have a lowered viscosity, and hence were less stable to shear when the product was prepared with lidocaine as compared to the
 20 product without lidocaine, even when the Sample was prepared according to Test 2 wherein a pH adjustment was performed.

[00125] With regard to viscosity, Sample 3 and Sample 4 were found to be stable to autoclaving in Test 2 but were not stable in Test 1. Sample 6 was found to be stable to autoclaving in both Test 1 and Test 2. Figures 3 and 4 illustrate that Samples 3 and 4 were stable when prepared with lidocaine and with pH adjustment, but were not stable when lidocaine was added and the pH not adjusted. Figure 6 illustrates that Sample 5 prepared with lidocaine and pH control had similar viscous and elastic properties (G''/G') to Sample 5 prepared without lidocaine. When Sample 5 was prepared with lidocaine and no pH adjustment, the viscous and elastic properties changed an insubstantial amount (Fig. 6). Figs. 7 and 8 illustrate that Sample 6 was stable and had similar viscous and elastic properties (G''/G') when prepared with lidocaine, both with and without pH control.

[00126] Sample 6 was found to be stable to autoclaving in both of Test 1 and Test 2. Figure 7 illustrates that Sample 6, no matter how it is produced, had similar viscosity and hence little shear comparison between preparation protocols. Figure 8 further illustrates that Sample 6 retained similar viscous and elastic properties no matter how it was produced.

15

Example 5

Kinetic Release

[00127] The following example illustrates the kinetic of release of lidocaine from cohesive HA gels according to the present description. The aim of the Example is to show that the lidocaine contained in cohesive HA gels according to the present description is freely released from the gels when placed in the skin.

[00128] Dialysis was performed for different periods of time (about 10g of gel were placed in a small dialysis bag and then put in 30g of water). After each dialysis was stopped at a given time, the gel was homogenized with a spatula and the amount of lidocaine was determined by UV method. The final concentration of the dialysis bath met the theoretical concentration of lidocaine which indicates the free release of lidocaine from the gel.

[00129] Table 3 illustrates lidocaine concentration in % (w/w), correction of the value and determination of the % of released lidocaine. Additionally, Figure 9 graphically illustrates the results tabulated in Table 3 below. Within

Figure 9 is indicated the theoretical equilibrium concentration of lidocaine that would exist if the lidocaine were retained in the gel or if it were to be freely released. As is graphically illustrated therein, the data suggest that the lidocaine is freely released from the gel.

5 **Table 3**

	MMA3056	MMA4031- EC6	MMA4031- EC2	MMA4031- EC3	MMA4031- EC4	MMA4031- EC5	MMA4029- EC7
Dialysis time (h)	0 hr	1 hr 30 min	5 hr	7 hr	23 hr	48 hr	72 hr
[lidocaine] (%)	0.29	0.20	0.16	0.15	0.08	0.07	0.07

[00130] The concentration profile of lidocaine in Sample 5 from Example 4 (Figure 9) shows that over time it reaches an equilibrium that corresponds to free release of lidocaine. This *in vitro* study shows that lidocaine is freely released from the gel and not retained in the gel once implanted.

[00131] Although the invention has been described and illustrated with a certain degree of particularity, it is understood that the present disclosure has been made only by way of example, and that numerous changes in the combination and arrangement of parts can be resorted to by those skilled in the art without departing from the scope of the invention, as hereinafter claimed.

[00132] Unless otherwise indicated, all numbers expressing quantities of ingredients, properties such as molecular weight, reaction conditions, and so forth used in the specification and claims are to be understood as being modified in all instances by the term "about." Accordingly, unless indicated to the contrary, the numerical parameters set forth in the specification and attached claims are approximations that may vary depending upon the desired properties sought to be obtained by the present invention. At the very least,

each numerical parameter should at least be construed in light of the number of reported significant digits and by applying ordinary rounding techniques. Notwithstanding that the numerical ranges and parameters setting forth the broad scope of the invention are approximations, the numerical values set forth in the specific examples are reported as precisely as possible. Any numerical value, however, inherently contains certain errors necessarily resulting from the standard deviation found in their respective testing measurements.

[00133] The terms "a," "an," "the" and similar referents used in the context of describing the invention (especially in the context of the following claims) are to be construed to cover both the singular and the plural, unless otherwise indicated herein or clearly contradicted by context. Recitation of ranges of values herein is merely intended to serve as a shorthand method of referring individually to each separate value falling within the range. Unless otherwise indicated herein, each individual value is incorporated into the specification as if it were individually recited herein. All methods described herein can be performed in any suitable order unless otherwise indicated herein or otherwise clearly contradicted by context. The use of any and all examples, or exemplary language (e.g., "such as") provided herein is intended merely to better illuminate the invention and does not pose a limitation on the scope of the invention otherwise claimed. No language in the specification should be construed as indicating any non-claimed element essential to the practice of the invention.

[00134] Groupings of alternative elements or embodiments of the invention disclosed herein are not to be construed as limitations. Each group member may be referred to and claimed individually or in any combination with other members of the group or other elements found herein. It is anticipated that one or more members of a group may be included in, or deleted from, a group for reasons of convenience and/or patentability. When any such inclusion or deletion occurs, the specification is deemed to contain the group as modified

thus fulfilling the written description of all Markush groups used in the appended claims.

[00135] Certain embodiments of this invention are described herein, including the best mode known to the inventors for carrying out the invention.

5 Of course, variations on these described embodiments will become apparent to those of ordinary skill in the art upon reading the foregoing description. The inventor expects skilled artisans to employ such variations as appropriate, and the inventors intend for the invention to be practiced otherwise than specifically described herein. Accordingly, this invention includes all
10 modifications and equivalents of the subject matter recited in the claims appended hereto as permitted by applicable law. Moreover, any combination of the above-described elements in all possible variations thereof is encompassed by the invention unless otherwise indicated herein or otherwise clearly contradicted by context.

[00137] Specific embodiments disclosed herein may be further limited in
20 the claims using consisting of or and consisting essentially of language. When used in the claims, whether as filed or added per amendment, the transition term "consisting of" excludes any element, step, or ingredient not specified in the claims. The transition term "consisting essentially of" limits the scope of a claim to the specified materials or steps and those that do not
25 materially affect the basic and novel characteristic(s). Embodiments of the invention so claimed are inherently or expressly described and enabled herein.

[00138] In closing, it is to be understood that the embodiments of the invention disclosed herein are illustrative of the principles of the present
30 invention. Other modifications that may be employed are within the scope of

the invention. Thus, by way of example, but not of limitation, alternative configurations of the present invention may be utilized in accordance with the teachings herein. Accordingly, the present invention is not limited to that precisely as shown and described.

WHAT IS CLAIMED IS:

1. A method of preparing a sterile soft tissue filler composition that is stable to autoclaving, the method comprising:

providing a precursor composition comprising a cross-linked hyaluronic acid (HA)-based gel cross-linked with a cross-linking agent wherein the cross-linking agent is a mixture of 1,4 butanediol diglycidyl ether, 1,2-bis(2,3-epoxypropoxy)ethylene, and 1-(2,3-epoxypropyl)-2,3-epoxycyclohexane, wherein the precursor composition comprises hyaluronic acid at a concentration between 18 and 24 mg/ml and an elastic modulus between about 60 and 450 Pa;

adding a solution comprising an anesthetic agent to form a mixture wherein the anesthetic agent is lidocaine;

homogenizing the mixture to obtain a partially crosslinked, HA-based soft tissue filler composition that is stable to autoclaving, and;

sterilizing the composition by autoclaving to prepare the sterile soft tissue filler composition;

wherein;

prior to adding the solution comprising an anesthetic agent, the pH of the composition is adjusted to above pH 7.2.

2. The method of claim 1, wherein said precursor composition comprises a degree of cross-linking from about 2% to about 20%.

3. The method of claim 1, wherein said precursor composition comprises a degree of cross-linking of from about 6% to about 8%.

4. The method of claim 1, wherein said precursor composition comprises a degree of cross-linking from about 4% to about 12%.

5. The method of claim 1, wherein said precursor composition comprises a degree of

cross-linking of about 6% or less.

6. The method of claim 1, wherein said precursor composition comprises a degree of cross-linking of about 5% or less.

7. The method of claim 1, wherein said precursor composition exhibits about 6% cross-linking.

8. The method of claim 1, wherein said precursor composition exhibits about 5% cross-linking.

9. The method of claim 1, wherein said precursor composition comprises hyaluronic acid at a concentration of about 18 mg/ml.

10. The method of claim 1, wherein said precursor composition comprises hyaluronic acid at a concentration of about 20 mg/ml.

11. The method of claim 1, wherein said precursor composition comprises hyaluronic acid at a concentration of about 24 mg/ml.

12. The method of claim 1, wherein said precursor composition comprises an elastic modulus of about 450 Pa.

13. The method of claim 1, wherein said precursor composition comprises an elastic modulus of about 170 Pa.

14. The method of claim 1, wherein said precursor composition comprises an elastic modulus of about 60 Pa.

15. The method of claim 1, wherein the soft tissue filler composition comprises about 1% to about 10% of free HA material by volume.

16. The method of claim 1, wherein the soft tissue filler composition comprises less than about 5% free HA material.

17. The method of claim 1, wherein the precursor composition is a hydrated gel.

18. The method of claim 1, wherein the lidocaine is lidocaine HCl.
19. The method of claim 1, wherein the precursor composition comprises a first component comprising cross-linked HA in a solid phase and a second component comprising free or cross-linked HA in a fluidic phase.
20. The method of claim 1, wherein the precursor composition comprises particles of cross-linked HA having an average size less than about 200 μm .
21. The method of claim 1, wherein the method further comprises the steps of preparing the precursor composition by pressing a mass of cross-linked HA-based gel through a sieve or a mesh to create cross-linked HA particles of uniform size and shape and then mixing the particles with an amount of free HA to produce a gel.
22. The method of claim 1, wherein the precursor composition provided is pH neutral.
23. The method of claim 1, wherein the precursor composition is adjusted to be between about pH 7.5 and about 8.0.
24. The method of claim 1, wherein said precursor composition is alkaline.
25. The method of claim 1, wherein said step of providing a precursor composition comprises providing purified sodium hyaluronic acid (NaHa) material, hydrating the material to form hydrated material and crosslinking the hydrated material with the cross-linking agent defined in claim 1 to form the cross-linked HA-based gel, neutralizing and swelling the gel prior to adding the solution comprising lidocaine to form a HA/lidocaine gel, homogenizing the mixture to form a homogenized HA/lidocaine gel, and:
 - a) sterilizing the homogenized HA/Lidocaine gel by autoclaving, or;
 - b) packaging the homogenized HA/lidocaine gel in a syringe for dispensing, followed by sterilizing the homogenized HA/Lidocaine gel in the syringe by autoclaving.
26. The method of claim 25, wherein the NaHA material comprises fibers or powder.
27. The method of claim 25, wherein the syringe containing gel is sterilized.

28. The method of claim 27, wherein the syringe containing gel is sterilized by autoclaving for at least one minute.

29. The method of claim 1, wherein the precursor composition comprising HA is bacterial sourced.

30. The method of claim 1, wherein the HA-based gel comprises high molecular weight HA of at least 1.0 million Daltons.

31. The method of claim 1, wherein the HA-based gel consists of high molecular weight HA of at least 1.0 million Daltons.

32. The method of claim 30, wherein the HA-based gel further comprises a second lower molecular weight HA of less than 1.0 million Daltons.

33. The method of claim 1, wherein the HA-based gel comprises about 5% to about 95% high molecular weight HA of at least 1.0 million Daltons.

34. The method of claim 32, wherein a ratio of the high molecular weight HA to the lower molecular weight HA is greater than about 2.

35. The method of claim 1,

wherein said providing a precursor composition comprises hydrating dry NaHA fibers or powder in an alkaline solution to produce a hydrated NaHA alkaline gel;

cross-linking the hydrated NaHa alkaline gel with the cross-linking agent to form a cross-linked HA gel wherein the cross-linking agent is 1,2-bis(2,3-epoxypropoxy)ethylene, 1-(2,3-epoxypropyl)-2,3-epoxycyclohexane or a mixture thereof;

optionally swelling the cross-linked HA gel, and;

purifying the cross-linked HA gel prior to

adding the solution comprising lidocaine to form a lidocaine-containing cross-

linked HA gel;

homogenizing the gel to create a highly homogeneous soft tissue filler composition, and

sterilizing the composition by autoclaving the composition.

36. The method of claim 35, wherein the hydrated NaHA alkaline gel has a pH greater than 9.

37. The method of claim 36, wherein the pH is greater than 10.

38. The method of claim 37, wherein the pH is greater than 13.

39. The method of claim 1, wherein the gel is swelled in a buffer to produce swollen gel.

40. The method of claim 39, wherein the buffer is phosphate buffered saline.

41. The method of claim 39, wherein the swollen gel exhibits no visibly distinct particles when viewed with the naked eye.

42. The method of claim 39, wherein the swollen gel has no visibly distinct particles under a magnification of less than 35X.

43. The method of claim 1, wherein the soft tissue filler composition is purified by dialysis or alcohol precipitation.

44. The method of claim 1, wherein the anesthetic is lidocaine and is present in an amount of from about 0.1% to about 5% w/w.

45. The method of claim 44, wherein the lidocaine is present in an amount of about 0.3% w/w.

46. The method of claim 1 wherein the homogenizing comprises mixing, stirring, beating or a combination thereof to obtain a substantially homogeneous mixture.

47. The method of claim 1 wherein the soft tissue filler composition exhibits a viscosity

from about 50 Pa*s to about 450 Pa*s.

48. The method of claim 1 wherein the soft tissue filler composition exhibits a viscosity from about 60 Pa*s to about 300 Pa*s.

49. The method of claim 1 wherein the soft tissue filler composition exhibits a viscosity from about 100 Pa*s to about 400 Pa*s.

50. The method of claim 1 wherein the soft tissue filler composition exhibits a viscosity from about 250 Pa*s to about 400 Pa*s.

51. The method of claim 1 wherein the soft tissue filler composition exhibits a viscosity from about 60 Pa*s to about 250 Pa*s.

52. The method of claim 1, wherein the method further comprises the step of preparing the cross-linked HA-based gel by combining dry NaHa fibers or powder and the cross linking agent and crosslinking at least some of the NaHa in the dry state.

53. The method of claim 1, wherein the precursor composition comprises hyaluronic acid at a concentration of about 20 mg/ml, about 5% cross-linking, and an elastic modulus of about 450 Pa.

54. The method of claim 1, wherein the precursor composition comprises hyaluronic acid at a concentration of about 18 mg/ml, cross-linking at 6% or less, and an elastic modulus of about 60 Pa.

55. The method of claim 1, wherein the precursor composition comprises hyaluronic acid at a concentration of about 24 mg/ml, cross-linking at about 6%, and an elastic modulus of about 170 Pa.




FIG. 1








FIG. 2

**FIG. 3****FIG. 4**

**FIG. 5****FIG. 6**




FIG. 7




FIG. 8




FIG. 9