

(19)



(11)

EP 3 748 077 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention of the grant of the patent:
12.03.2025 Bulletin 2025/11

(51) International Patent Classification (IPC):
D21H 27/00 ^(2006.01) **D21C 3/20** ^(2006.01)
D21C 5/00 ^(2006.01) **D21H 11/12** ^(2006.01)
D21C 3/02 ^(2006.01)

(21) Application number: **19020674.8**

(52) Cooperative Patent Classification (CPC):
D21C 5/00; D21C 3/02; D21C 3/20; D21H 11/12;
D21H 27/002

(22) Date of filing: **05.12.2019**

(54) **EUCALYPTUS GLOBULUS BARK PULP FOR TISSUE PRODUCTS**

PULPE AUS EUCALYPTUS-GLOBULUS-RINDE FÜR TISSUEPRODUKTE

PULPE D'ÉCORCE D'EUCALYPTUS GLOBULUS POUR PRODUITS TEXTILES

(84) Designated Contracting States:
AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR

(30) Priority: **03.06.2019 PT 2019115562**

(43) Date of publication of application:
09.12.2020 Bulletin 2020/50

(73) Proprietor: **RAIZ - Instituto De Investigação Da Floresta E Papel**
3800-783 Eixo, Aveiro (PT)

(72) Inventors:
• **DE OLIVEIRA RODRIGUES PINTO, Paula Cristina**
3800-783 Eixo, Aveiro (PT)

- **MARTINS SALGUEIRO CARTA, Ana Margarida**
3800-783 Eixo, Aveiro (PT)
- **FERREIRA BASTOS, Margarida**
3800-783 Eixo, Aveiro (PT)
- **SENA DA COSTA BRANCO, Pedro Miguel**
3800-783 Eixo, Aveiro (PT)
- **DE OLIVEIRA, Ricardo Jorge**
3800-783 Eixo, Aveiro (PT)

(56) References cited:
WO-A1-00/19005 CN-A- 102 011 334
CN-A- 109 082 929 JP-A- 2010 136 646
JP-A- 2011 047 083 JP-A- 2011 193 981
US-A1- 2010 305 241 US-A1- 2013 029 106
US-B1- 6 296 736

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 3 748 077 B1

Description

FIELD OF THE INVENTION

- 5 **[0001]** The present invention relates to tissue paper sheets incorporating 20%-30% (w/w) of an *Eucalyptus globulus* bark pulp as defined in the present claim 1, and their use for the production of household and sanitary products.

BACKGROUND OF THE INVENTION

- 10 **[0002]** The industrial process of pulp production can generally be described as involving the processes of preparation of the raw material and cooking, the later which can be chemical or mechanical. Wood is the main source of raw material for cellulose pulp production.
- 15 **[0003]** One of the steps in the preparation of the raw material is the stripping of the wood logs to remove the bark. Industrial pulp and paper producers remove bark from the raw material because it is low in fiber, has a high extractable content, is dark and usually incorporates large amounts of debris such as sand.
- 20 **[0004]** The resulting bark is used for energy production at biomass boilers usually present at pulp and paper mills. The pulp produced through wood cooking is then converted into different products such as printing and writing papers, packaging boards and tissue papers.
- 25 **[0005]** The document CN102011334B describes a cooking method using *Eucalyptus* bark. In the described method, the *Eucalyptus* bark is subjected to grinding, to an alkaline treatment and milling of the resulting pulp. The pulp is also described as being used for the preparation of corrugated paper. The method described is intended to be an alternative for reducing the environmental impact of the pulp and paper production process. No paper properties of the corrugated paper produced are detailed.
- 30 **[0006]** The document CN109082929A discloses a method of using *Eucalyptus* bark for the preparation of pulp for paper production, characterized by a crushing step of the bark, followed by immersing it in an alkaline liquid for 30-48 hours, and mixing the resulting pulp with water and carrying out a final grinding. The method is described as simple, inexpensive and environmentally friendly. Additionally it is described in said document that the pulp produced is suitable for the production of corrugated paper. No paper properties of the corrugated paper produced are detailed.
- 35 **[0007]** JP2011047083A describes a method for the production of liberian fibers from the bark of a tree plant, which involves a saccharification treatment with a saccharifying enzyme followed by a solid - liquid separation.
- 40 **[0008]** JP2010136646A relates to a method for the production of saccharides, more energy efficient, by controlling the water content and the drying temperature, through bark saccharification.
- 45 **[0009]** CN102011334A discloses a method for producing corrugated paper by using eucalyptus bark, particularly from *Eucalyptus Urophylla*'s.
- 50 **[0010]** CN109082929A describes a method of using eucalyptus barks for paper production, particularly corrugated paper, advanced corrugated paper and blank sheet of paper.
- 55 **[0011]** US6296736B1 relates to refers to a method of producing sanitary products from recycled newspapers, by washing the newspapers pulp to reduce the proportion of fines and by treating the it with a surfactant system as it is introduced into the papermachine.
- 60 **[0012]** JP2011193981A discloses a sanitary paper with excellent touch and that generates little paper dust, consisting of long fibers of size 24 mesh.
- 65 **[0013]** Tissue papers are those used for hygienic and sanitary purposes, both at home and in public places. A tissue paper product, such as toilet paper, napkins, kitchen rolls or tissues, is characterized by key properties such as strength, absorption, softness and even visual appearance.
- 70 **[0014]** This type of products, in order to be preferentially chosen by the consumer, needs to have a positive balance of these different properties in order to achieve a product of overall higher quality. It is currently found that when actions are taken to increase the quality of a product property, other product characteristics are often negatively affected.
- 75 **[0015]** Different approaches for enhancing these properties of tissue papers can be found in the literature. EP0478045A1 describes a soft tissue paper having a suitable tensile strength, obtained by incorporating into its constitution cellulose pulps obtained by different chemical and mechanical methods, and which have different types of wood as their raw material. Adopting this solution to improve the mentioned paper characteristics will lead to changes on an existing industrial production process of paper products. Additional costs are easily associated with these significant changes to an industrial process.
- 80 **[0016]** Another possibility commonly adopted for tissue paper products to improve their characteristics would be the use of chemical additives, as explained in EP0347154A2, which describes a product incorporating starch and polysiloxane to achieve an acceptable balance between softness and tensile strength of tissue paper products.
- 85 **[0017]** Similarly, EP0981668A1 describes a tissue paper product wherein at least one inner surface of the paper contains a resistance enhancing polymeric agent.

[0018] US5316623A provides a method for obtaining a tissue paper product having good absorption capacity and strength, which consists on the use of a combination of alkaline or neutral resins, water soluble anionic polymers and tertiary amines.

[0019] Adopting these approaches, in addition to not guaranteeing an overall improved tissue paper characteristics, will always have an associated environmental cost with regard to possible negative effects on the environment.

[0020] There is thus a need for tissue paper products with a wide range of improved paper properties, which are valued by the consumers, such as strength, absorption and even visual appearance, which can be associated with the ideas of sustainability and environmental concern, produced through alternative raw materials, which do not involve complex sources and mixtures of materials, which can be used in existing industrial processes and without significant changes, allowing reducing the waste streams of industrial processes, fulfilling possible deficiencies in the amount of raw material available for pulp and paper production, and which make possible to reduce, in number and quantity, the use of chemical additives for enhancing the characteristics of tissue papers. Such a problem is solved by the invention described herein.

SUMMARY OF THE INVENTION

[0021] The present invention is defined in the current claim 1. This invention describes tissue products with a globally improved consumer-friendly pulp properties, such as strength, absorption and even visual appearance associated with sustainability ideas and environmental concerns comprising 20% - 30% (w/w) of a *Eucalyptus globulus* bark fibers pulp. Additionally, they are advantageously produced through alternative raw materials, not involving complex sources and mixtures of raw materials, in existing industrial processes and without significant modifications, with a reduction of the waste streams associated with industrial processes, filling possible deficiencies in the amount of raw material available for pulp and paper production, and making it possible to reduce, in number and quantity, the use of chemical additives for enhancing the characteristics of tissue papers.

[0022] This disclosure describes a cellulose pulp for the production of tissue products comprising *Eucalyptus globulus* bark fibers.

[0023] The *Eucalyptus globulus* bark pulp is comprised of fibers having a length of not less than 0.8 mm, a width of not less than 20 μm and a coarseness value of not less than 8 mg/100m. The *Eucalyptus globulus* bark pulp presents a viscosity of not less than 1100 mL/g and a carboxyl content of not less than 9%.

[0024] The *Eucalyptus globulus* bark pulp is produced by a method involving the steps of bark chip selection, bark pre-extraction with an ethanol:water mixture, and cooking of the chips with NaOH and Na_2S for a time of not less than 200 minutes and at a temperature from 17 to 170 $^{\circ}\text{C}$.

[0025] The disclosed invention therefore includes sheets of tissue paper incorporating the *Eucalyptus globulus* bark pulp, and short and long cellulose fiber pulps. The sheets have improved paper properties compared to tissue sheets that incorporate only *Eucalyptus globulus* wood pulp in their composition.

[0026] In the production process of tissue products, the described *Eucalyptus globulus* bark pulp can be used in different forms, such as in the form of dried pulp bales and in the form of a slush, the later feed to the industrial process through pipeline systems.

[0027] The tissue paper sheets have bulk values from 2 to 7 cm^3/g and a tensile index from 10 to 30 kN.m/kg . An absorption capacity greater than 8 $\text{gH}_2\text{O/g}_{\text{paper}}$ and softness values of not less than 70 HF were found.

[0028] The tissue paper sheets disclosed in this document have a tear index greater than 3 $\text{mN.m}^2/\text{g}$, preferably greater than 8 $\text{mN.m}^2/\text{g}$, a burst index of not less than 1 $\text{kPa.m}^2/\text{g}$, a capillarity greater than 60 mm/10min, preferably greater than 70 mm/10min and an opacity greater than 75%, preferably greater than 90%.

[0029] The invention disclosed herein thus includes the use of tissue papers sheets, incorporating the *Eucalyptus globulus* bark pulp as defined in claim 1, for the production of household and sanitary products, such as toilet paper, napkins, kitchen paper rolls and tissues.

DETAILED DESCRIPTION OF THE INVENTION

1. *Eucalyptus globulus* bark cooking

[0030] *Eucalyptus globulus* bark cooking was performed in a time and temperature controlled rotary digester.

[0031] To carry out the cooking, a batch of bark chips with the most uniform size as possible was selected. Prior to each run, the bark was pre-extracted with an ethanol:water mixture (52:48).

[0032] The composition of the cooking liquor, prepared by dissolving previously calculated amounts of NaOH and Na_2S , was confirmed according to the standard SCAN-N 2-88, also known as the ABC Test.

[0033] This test is performed by three successive titrations with a hydrochloric acid solution to obtain real concentrations of the cooking liquor. The cooking conditions are shown in Table 1. The cooking results are shown in Table 2.

Table 1. Operational conditions used for cooking *Eucalyptus globulus* bark.

Ratio liquid/wood	8
Sulfide Index (%)	28
T _{initial} (°C)	17.3
T _{final} (°C)	170
Total time (min)	213
Time at T _{max} (min)	153
Active alkali, %Na ₂ S	22

Table 2. *Eucalyptus globulus* bark cooking results.

Bark humidity (%)	73.87
Dry pulp produced (g)	293.25
Uncooked (g)	6.97
Uncooked (%)	1.2
Pulp yield (%)	48.9
Kappa index	13.92

2. Biometric Characterization

[0034] The biometric analysis of the fibers was performed in a Fiber Tester equipment (Lorentzen & Wettre), which is an instrument for advanced fiber analysis. The equipment measures, by 2D image analysis, a wide variety of properties such as length, width, fines content, coarseness, among others. Coarseness is defined as the weight per unit length of fiber expressed in milligrams per 100 meters. For that, 1 g (dry basis) of pulp was dispersed in 1 L of distilled water. Subsequently, all the suspensions were positioned for analysis by the equipment using available software. For each pulp three measurements were made, the final value of each parameter resulting from the arithmetic mean of the values obtained at the three measurements.

3. Chemical characterization

a. Extractable compounds content

[0035] Extractable compounds are hydrophobic (lipophilic) components present in wood and extracted by organic solvents.

[0036] The extractable compounds content was determined using ethanol/toluene in quantities enough for samples analysis preparation, as it requires a pulp pre-extraction. The extraction was carried out during approximately 4 hours (24 extraction cycles) of 2 g (dry basis) of pulp in a 100 mL capacity Soxhlet extraction apparatus, using 250 mL of a 1:2 (v/v) ethanol/toluene solution. The insoluble residue was filtered and washed with hot absolute ethanol, for removing any remaining toluene, and dried at room temperature, contrary to what is indicated at the standard TAPPI T 204 om-88, since washing with water, as described, could lead to the loss of pentosans and other polysaccharides of low molecular weight. The obtained extract was dried at a rotary evaporator equipment and the extractable content was determined gravimetrically.

b. Pentosans content

[0037] Pentosans content was determined according to the Tappi Test Method T 223 cm-10. This method is based on the action of hydrochloric acid on the pulp hemicelluloses, hydrolyzing them and, consequently, converting the xylose and other pentoses to furfural, which is collected with the distillate and, reacting with orcinol, forms a colored complex making therefore possible the content quantification by spectrophotometry.

[0038] About 0.5-1.0 g (dry basis) of unbleached pulp pre-extracted in ethanol/toluene (1:2), together with 20 g of NaCl and 100 mL of HCL 3.85 N, was inserted into a distillation flask. In a hopper, 250 mL of 3.85 N HCl was added and the acid distillation was started into a volumetric flask placed in an ice bath.

[0039] Finally, 5 mL of the distillate was pipetted, 25 mL of the orcinol ferric chloride reagent was added, and the mixture was kept in a thermostatic bath for 1 hour. Absolute ethanol was added and the volumetric flask was placed again in the thermostatic bath for another hour. The solution absorbance at 630 nm was then read, and measurements comparisons were carried out using a 5 mL blank of 3.85 N HCl.

[0040] The pentosans content was obtained with the aid of the calibration curve and equations as described below:

$$m_{xy\text{lan}} (mg) = 0,88 \times m_{xy\text{lose}} (mg)$$

$$\text{Pentosans content (\%)} = \frac{m_{\text{pentosans in each sample}}}{10 \times w}$$

where w is the dry weight (g) of the sample.

c. Carboxyl content

[0041] The content of carboxyl groups was determined according to the TAPPI T 237 om-93 standard method. About 2.5 ± 0.1 g of disintegrated pulp was first weighed and 250 mL of a diluted hydrochloric acid solution (approximately 0.1 M) was added during 12 hours, ensuring that all existing carboxylic groups are in their protonated form. Subsequently, the pulp was filtered and washed with distilled water until the pH of the filtrate equaled the pH of the distilled water.

[0042] To the pulp it was added 50 mL of an aqueous sodium bicarbonate-sodium chloride solution, the resulting mixture stirred for about 5 hours, filtered, and the filtrate twice titrated (25 mL in each titration) with a standard solution of hydrochloric acid (0.01 M) using methyl red as indicator. At the first color change the solution was boiled for 1 minute to release CO_2 . Titration is resumed ending only when the solution changes to pink. The blank was prepared by titrating 25 mL of sodium bicarbonate-sodium chloride solution with 0.01 M HCl. The content of carboxyl groups was determined with the following equation:

$$\text{Content COOH} \left(\frac{\text{mmol}}{100 \text{ g}} \right) = \left(b - a - \frac{C_w \times a}{50} \right) \times \left(\frac{50}{25 \times w} \right)$$

where a is the volume, in mL, of hydrochloric acid (0,01 M) spent during titration, b is the volume, in mL, of hydrochloric acid (0,01 M) consumed during the blank titration, C_w is the mass, in g, of the water in the pulp after filtration, and w is the weight, in g, of the dry pulp.

d. Pulp viscosity

[0043] The viscosity was determined according to the SCAN-test standards SCAN-CM 15:88, which consists on the determination of the viscosity of cellulose pulps by solubilization in a dilute copper-ethylenediamine (CED) solution.

[0044] The pulp sample was reduced to small fragments in the amount indicated at the table provided by the method (Table 7, Annex C.1.) - 150 mg of pulp were weighed. Each sample was placed into a glass vial along with 25 mL of distilled water and some copper wires. The vials were then placed on a shaker for as long as necessary to ensure that the pulp was completely disintegrated. The procedure continued with adding 25 mL of 1 M CED solution, expelling all existing air and stirring until the sample is completely dissolved. Finally, the temperature of the viscometer bath and the sample's were adjusted to 25.0 ± 0.1 °C and, with the aid of a syringe, a portion of the solution was aspirated and allowed to flow unobstructed. The time it takes to travel the distance between the two viscometer marks was measured to within ± 0.2 s. At least 5 readings were taken for each sample.

[0045] With the flow time of each sample, t_n , it is possible to calculate its relative viscosity, η_{rel} , through the relationship shown in the equation:

$$\eta_{rel} = h \times t_n$$

where h represents the viscometer constant, obtained from the equipment calibration. From the table provided by the aforementioned standard, it is possible to read the value resulting from multiplying the viscosity value with the pulp concentration, $[\eta]C$.

[0046] Biometric and chemical measurements and comparisons were carried out for a pulp produced with *Eucalyptus globulus* wood (**SF**), characterized by containing short fibers, and for a pulp containing long cellulose fibers (**LF**), in addition

to for the pulp produced with *Eucalyptus globulus* bark (**BP**) by the process described above.

4. Preparation of paper sheets

[0047] Tissue paper sheets with a weight of 20 g/m², and not subjected to any pressing procedure, were prepared following an adaptation of the standard method ISO 5269-1:2005. Additionally, 60 g/m² tissue paper sheets were prepared according to the same ISO.

[0048] The pulps described above, **SF**, **LF** and **BP** were used. The prepared formulations are described in Table 3. Reference formulations (**REF 1** and **REF 2**) consist on formulations used for the production of tissue paper sheets. The other formulations were based on the replacement of short fibers content by bark pulp (**BP1** and **BP2**).

[0049] The prepared sheets were stored according to the standard ISO 187:1990 for further analysis.

Table 3. Formulations used in sheet preparation.

Formulations	Percentages (%) (w/w)			
	References		Formulations BP	
	RE F 1	RE F 2	BP 1	BP 2
SF	70	100	50	40
LF	30	-	30	30
BP	-	-	20	30

5. Paper properties of 20 g/m² tissue sheets

[0050] The 20 g/m² sheets were analyzed as indicated in Table 4.

Table 4. Paper properties analyzed for sheets of 20 g/m² and respective measure standards.

Property	Standard
Weight	ISO 12625-6:2005
Bulk	ISO 12625-3:2014
Dry tensile index	ISO 12625-4:2005
Klemm capillarity	ISO 8787-1986
Absorption capacity	Adaptation 12625-8:2010

[0051] The softness was analyzed on an Emtec TSA - Tissue Softness Analyzer. This device combines data from the three parameters that have the greatest influence on the human feel to the touch: fibers softness, smoothness, and sheet stiffness. The calculation method used by the device is an algorithm that calculates the hand feel (HF).

[0052] The water absorption of the tissue papers was determined according to the standard ISO 12625-8:2010, by the immersion absorption method. Approximately 2 g of paper was placed in a basket of certain dimensions, contrary to what is mentioned at the standard, which indicates the use of 5 g of paper.

6. Paper properties of 60 g/m² tissue sheets

[0053] The 60 g/m² sheets were analyzed as indicated in Table 5.

Table 5. Paper properties analyzed for sheets of 60 g/m² and respective measure standards.

Property	Standard
Weight	ISO 536:2012
Bulk	ISO 534:2011
Traction index	ISO 1924-2
Burst index	ISO 2758:2014

(continued)

Property	Standard
Extension	ISO 1924-2:2008
Tear Index	ISO 1974:2012
Opacity	ISO 2471
Gurley air resistance	ISO 5636-5:2013
Capillarity	NP686:1990

[0054] Additionally, a Scott Test was carried out and the Gurley's air resistance was measured.

[0055] Mechanical strength properties of pulp furnishes ultimately contribute to the strength characteristics of the outcoming material, as paper sheets are subjected to considerable stresses during processing and use. The Scott Test is related to the internal fibers bonding strength of the paper when subjected to delamination. It allows the determination of the energy (or force) required to delaminate a sheet of paper in the z-direction. In this method (TAPPI T 569 standard) the paper sheet is delaminated under the action of a pendulum of controlled mass and velocity. The internal strength of the fibers is affected by the paper sheets formation (bonding between layers) and also by the process of pulp refining.

[0056] The Gurley's air resistance is a structural property that quantifies the time required for a certain volume of air (100 mL) to pass through a given area of paper under constant pressure, ISO 5636-5:2013 standard. It is an indirect measure of the porosity of the fibrous matrix.

[0057] Both tests were performed under the same atmospheric conditions used for sample conditioning and sample preparation ($T = 23\text{ }^{\circ}\text{C} \pm 1\text{ }^{\circ}\text{C}$ and Relative Humidity (RH) = $50\% \pm 2\%$, according to the ISO 187:1990 standard.

Examples

a. Biometric and Chemical Properties

[0058] The biometric properties of the 3 pulps, **SF**, **LF**, **BP**, were analyzed and the results are shown in Table 6.

Table 6. Biometric properties of SF, LF and BP pulps.

	SF	LF	BP
Fiber length, mm	0.79 ± 0.00	2.15 ± 0.01	0.8 ± 0.00
Fiber width, μm	18.6 ± 0.1	32.4 ± 0.1	20.80 ± 0.08
N.° fibers/g, $\times 10^{-6}$	18.7 ± 0.1	4.30 ± 0.07	15.6 ± 0.6
Coarseness, mg/100m	6.3 ± 1.20	15.1 ± 0.4	8.4 ± 0.3
Fines (0,0-0,200 mm),	4.2 ± 0.1	5.7 ± 0.1	3.8 ± 0.1
Shape, %	90.7 ± 0.1	88.2 ± 0.07	92.73 ± 0.05
Curl, %	9.2 ± 0.1	13.4 ± 0.1	7.8 ± 0.1
Mean kink index	1.3 ± 0.0	0.90 ± 0.00	0.84 ± 0.00

[0059] Considering the obtained results, it is verified that the fiber length values are within the expected. Concerning the width results, it was found that the **BP** fibers have higher values than the other short fibers. When it comes to coarseness, **LF** fibers have the highest value. Regarding the other fibers, **BP** showed the highest value, followed by **SF**.

[0060] The chemical characterization of the pulps under study was also performed (Table 7).

Table 7. Chemical properties of SF, LF and BP pulps.

	SF	LF	BP
Viscosity, mL/g	716 ± 3	699 ± 14	1171.9 ± 0.0
Carboxylic, %	7.03 ± 0.05	8.92 ± 0.23	9.89 ± 0.12
Pentosans, %	19.6 ± 0.25	8.1 ± 0.02	14.04 ± 0.18

(continued)

	SF	LF	BP
Extractable, %	0.21 ± 0.00 *	0.40 ± 0.22 *	0.47 ± 0.04"

* Extractable in acetone

** Extractable in ethanol:toluene(1:2)

[0061] Considering the viscosity results, **BP** revealed a considerably higher value than the **SF**'s (homologous), meaning the degree of cellulose polymerization was preserved.

[0062] Regarding the carboxyl content, this is higher in **BP** compared to other pulps'.

[0063] The pentosans content (measured by the xylan content, the majority of hemicelluloses in short fiber pulps) is within the typical range and considered as favorable.

b. Paper properties - 20 g/m² tissue paper sheets

[0064] The paper sheets produced for the reference formulation **REF 1** (70:30:0) and **REF 2** (100:0:0) and the paper sheets with incorporation of bark pulp **BP 1** (50:30:20) and **BP 2** (40:30:30) were analyzed and the main results are shown in Table 8.

Table 8. Results obtained for the properties of sheets of 20 g/m², reference and with *Eucalyptus globulus* bark pulp (formulation = %SF : %LF : %BP).

	REF 1 (70:30:0)	REF 2 (100:0:0)	BP 1 (50:30:20)	BP 2 (40:30:30)
Weight, g/m ²	21.1 ± 0.3	21.1 ± 0.4	21.0 ± 0.4	20.7 ± 0.3
Thickness, μm	135.4 ± 7.0	127.3 ± 5.6	134.7 ± 4.5	137 ± 2.1
Bulk, cm ³ /g	6.4 ± 0.4	6.0 ± 0.3	6.4 ± 0.2	6.6 ± 0.1
Tensile index, Nm/g	4.4 ± 0.3	4.42 ± 0.3	10.8 ± 0.3	9.5 ± 0.9
Absorption capacity, g _{H₂O} /g _{paper}	8.05 ± 0.04	7.54 ± 0.3	8.25 ± 0.60	8.49 ± 0.17
Air permeability, L/m ² /s	840 ± 84	741 ± 86	690 ± 25	818 ± 54
Softness, HF	80.5 ± 1.9	80.5 ± 2.5	70.2 ± 1.4	74.5 ± 0.9
Softness, TS7	13 ± 1	13.4 ± 1.4	18.68 ± 0.73	16.33 ± 0.48
Softness, TS750	13.3 ± 1.3	11.6 ± 0.4	17.9 ± 1.2	16.3 ± 1.1
Klemm Capillarity, mm				
10 s	27.5 ± 3.5	25.0 ± 2.8	24.5 ± 1.5	28.0 ± 1.4
20 s	38.5 ± 2.7	33.8 ± 1.1	33.5 ± 1.5	38.0 ± 1.6
30 s	45.8 ± 1.3	40.8 ± 2.5	41.0 ± 1.0	43.7 ± 0.9
60 s	59.5 ± 1.5	54.8 ± 3.4	56.3 ± 2.1	59.3 ± 1.3
180 s	91.3 ± 1.1	87.0 ± 4.1	91.0 ± 3.0	93.7 ± 2.5
300 s	112.0 ± 0.7	105.3 ± 5.4	111.3 ± 2.9	112.5 ± 1.5

[0065] The paper sheets with higher **BP** incorporation, especially the **BP 2** formulation, revealed a higher thickness, for the same grammage and, consequently, a higher bulk, comparing to **REF 1** and **REF 2**.

[0066] The results for the air permeability (L/m²/s), sheet permeable air flow per unit of time, indirect measure of porosity, show a slight decrease in porosity. However, it is noted that the measured variations are within the deviation values ranges.

[0067] The tensile index increased with the incorporation of bark pulp.

[0068] In terms of water absorption properties, capillarity and absorption capacity were evaluated, and the results indicated that incorporation of **BP** fibers led to an increase of the absorption capacity (when compared to **REF 1** and **REF 2**) and little significant variations were found in terms of capillarity.

[0069] Concerning softness, the increase in **BP** led to a decrease in softness compared to reference **REF 1** and **REF 2**. However, these correspond to a minimum loss of 6 HF points.

c. Paper properties - 60 g/m² tissue paper sheets

[0070] 60 g/m² paper sheets were also produced from the **BP** incorporation formulations. These were analyzed and the results are shown in Table 9.

Table 9. Results obtained for the properties of sheets of 60 g/m² with *Eucalyptus globulus* bark pulp (formulation = % SF : %LF : %BP).

	REF 1 (70:30:0)	REF 2 (100:0:0)	BP 1 (50:30:20)	BP 2 (40:30:30)
Weight, g/m ²	64.5 ± 0.02	64.7 ± 0.01	62.9 ± 0.02	64.5 ± 0.02
Thickness, μm	97.8 ± 7.9	113.9 ± 13.4	113.3 ± 4.9	116.9 ± 12.5
Bulk, cm ³ /g	1.25 ± 0.02	1.76 ±	1.80 ± 0.03	1.81 ± 0.02
Tensile index, Nm/g	19.0 ± 0.2	21.0 ± 1.6	26.0 ± 1.6	28.0 ± 1.6
Tear index, mN. m ² /g	6.4 ± 0.7	3.10 ± 0.7	8.9 ± 1.2	8.6 ± 1.1
Burst index, kPa.m ² /g	1.30 ± 0.1	0.95 ± 0.1	1.31 ± 0.1	1.31 ± 0.1
Extension, %	1.2 ± 0.1	1.1 ± 0.2	1.5 ± 0.1	1.5 ± 0.1
Opacity, %	76.9 ± 0.5	78.6 ± 0.4	91.8 ± 2.5	93.9 ± 0.7
Gurley air resistance, s	3.6 ± 0.3	0.90 ± 0.1	1.10 ± 0.1	1.10 ± 0.1
Scott Test, J/m ²	326 ± 40	103 ± 8	114 ± 11	129 ± 14
Capillarity, mm/10min	61.0 ± 2.4	92.0 ± 3.0	86.0 ± 1.2	79.0 ± 1.6

[0071] Analyzing the depicted results it is observed that, similarly to the results with the 20 g/m² paper sheets, the incorporation of **BP** leads to a bulk increase. Additionally, the incorporation of **BP** led to an increase in the tensile and tear indexes, comparing to the references. As for the burst index, it did not change significantly.

[0072] With regard to capillarity, the incorporation of **BP** fibers resulted in increased capillarity, especially when compared to **REF 1**. The opacity of the fibrous structures also increases with the incorporation of **BP**.

Claims

1. Tissue paper sheets comprising 20%-30% (w/w) of an *Eucalyptus globulus* bark fibers pulp and having a bulk from 2 to 7 cm³/g and a tensile index from 10 to 30 kN.m/kg
2. The tissue paper sheets according to claim 1, having a tear index greater than 3 mN.m²/g, a burst index of not less than 1 kPa.m²/g, a capillarity greater than 60 mm/10min and an opacity greater than 75%.
3. The tissue paper sheets according to any of the claims 1 to 2, having a tear index greater than 8 mN.m²/g, a capillarity greater than 70 mm/10 min and an opacity greater than 90%.
4. Use of the tissue paper sheets described in any of the claims 1 to 3 for the production of household and sanitary products.

Patentansprüche

1. Tissuepapierbögen, umfassend 20 % bis 30 % (w/w) einer Eucalyptus globulus-Rindenfaserzellstoffmasse und mit einem Volumen von 2 bis 7 cm³/g und einem Zugfestigkeitsindex von 10 bis 30 kN.m/kg.
2. Die Tissuepapierbögen nach Anspruch 1, mit einem Weiterreißindex von mehr als 3 mN.m²/g, einem Berstindex von mindestens 1 kPa.m²/g, einer Kapillarität von mehr als 60 mm/10 min und einer Opazität von mehr als 75 %.
3. Die Tissuepapierbögen nach einem der Ansprüche 1 bis 2, mit einem Weiterreißindex von mehr als 8 mN.m²/g, einer Kapillarität von mehr als 70 mm/10 min und einer Opazität von mehr als 90 %.

4. Verwendung der in einem der Ansprüche 1 bis 3 beschriebenen Tissuepapierbögen zur Herstellung von Haushalts- und Hygieneprodukten.

5 **Revendications**

1. Feuilles de papier tissu comprenant 20 % à 30 % (p/p) de pâte de fibres d'écorce d'Eucalyptus globulus, ayant un volume spécifique compris entre 2 et 7 cm³/g et un indice de traction compris entre 10 et 30 kN.m/kg.
- 10 2. Les feuilles de papier tissu selon la revendication 1, ayant un indice de déchirure supérieur à 3 mN.m²/g, un indice d'éclatement d'au moins 1 kPa.m²/g, une capillarité supérieure à 60 mm/10 min et une opacité supérieure à 75 %.
3. Les feuilles de papier tissu selon l'une quelconque des revendications 1 à 2, ayant un indice de déchirure supérieur à 8 mN.m²/g, une capillarité supérieure à 70 mm/10 min et une opacité supérieure à 90 %.
- 15 4. Utilisation des feuilles de papier tissu décrites dans l'une quelconque des revendications 1 à 3 pour la production de produits ménagers et sanitaires.

20

25

30

35

40

45

50

55

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- CN 102011334 B [0005]
- CN 109082929 A [0006] [0010]
- JP 2011047083 A [0007]
- JP 2010136646 A [0008]
- CN 102011334 A [0009]
- US 6296736 B1 [0011]
- JP 2011193981 A [0012]
- EP 0478045 A1 [0015]
- EP 0347154 A2 [0016]
- EP 0981668 A1 [0017]
- US 5316623 A [0018]