

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
18 August 2005 (18.08.2005)

PCT

(10) International Publication Number  
**WO 2005/075296 A1**

- (51) International Patent Classification<sup>7</sup>: **B65B 53/02**, B29C 55/06, B65D 75/00, B32B 27/32
- (21) International Application Number:  
PCT/IL2005/000157
- (22) International Filing Date: 9 February 2005 (09.02.2005)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
160283 9 February 2004 (09.02.2004) IL
- (71) Applicant (for all designated States except US): **POLY-SACK PLASTIC INDUSTRIES LTD.** [IL/IL]; D.N. Negev, 85455 Kibbutz Nir Yitzhak (IL).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **GUTHMAN, Yoav** [IL/IL]; D.N. Negev, 85455 Kibbutz Nir Yitzhak (IL). **SEGAL, Maor** [IL/IL]; D.N. Negev, 85455 Kibbutz Nir Yitzhak (IL).
- (74) Agent: **REINHOLD COHN AND PARTNERS**; P.O.B. 4060, 61040 Tel Aviv (IL).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**  
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: A METHOD FOR WRAPPING AN ARTICLE WITH A POLYMERIC FILM

(57) Abstract: The present invention provides a polymeric sheet prepared by short-gap stretching technique and being shrunk along its main axis. Such sheets may be utilized for wrap-around applications, obtaining shrinkage of polymeric sheets to particularly small dimensions along the machine direction, and wrapping articles in the wrap-around method even when these articles include locations of circumferences of considerably different dimensions.

WO 2005/075296 A1

- 1 -

## A METHOD FOR WRAPPING AN ARTICLE WITH A POLYMERIC FILM

### FIELD OF THE INVENTION

This invention relates to novel uses of polymeric films produced by stretching in the longitudinal direction, and in particular by short-gap stretching.

### BACKGROUND OF THE INVENTION

In the context of the present invention, a *short-gap-stretching process* is any process involving transferring a heated polymeric film from a first heated roll having a first radius and revolving in a first radial velocity to a second heated roll having a second radius and revolving in a second radial velocity, that is larger than said first radial velocity, through a gap which is as small as possible. Two publications that describe such processes are: US 5,184,379 and US 6,375,781.

In the article entitled "Industrial Applications Of SML Short Gap Monoaxially Film Stretching Process" (<http://olymp.wu-wien.ac.at:8080/usr/h98a/h9851644/news/news8.htm>), the author describes the short-gap-stretching method he uses, some of the properties of films obtained thereby, and a variety of possible uses thereof.

The present invention suggests novel uses for such films, and even more generally, for films produced by unidirectional stretching in the longitudinal direction.

- 2 -

## SUMMARY OF THE INVENTION

According to one of its aspects, the present invention provides a method for wrapping an article with a heat shrinkable polymeric film comprising:

- (a) providing a polymeric film produced by a process including stretching said film mainly in its longitudinal direction, said stretching being by means comprising at least one pair of rollers rotating in mutually different linear velocities, the gap between said rollers being at least 10 times smaller than the width of said film to obtain a heat shrinkable polymeric film;
- (b) surrounding at least a portion of the outer surface of said article with a portion of said heat shrinkable polymeric film; and
- (c) heating said heat shrinkable polymeric film so as to shrink it around said article.

According to another aspect of the present invention, there is provided an article wrapped by a method according to the invention.

Typical articles to be wrapped according to the present invention are containers, particularly cylindrical containers, most particularly cylindrical containers with non-uniform diameter such as drink-containing bottles, drinking cans, containers for liquid soap, shampoo containers, batteries, medications, bottles with tamper evidence seals, etc. However, the invention is not limited to the wrapping of such articles, and may be used for wrapping articles of any shape or form, such as forks, cups, boards, etc.

The term *wrapping an article* should be construed, in the context of the present invention, as to surrounding the article in close proximity to the outer surface thereof. In many cases, wrapping includes the attachment of the wrapping film to the entire surface of the wrapped portion of the article. However, this is not necessarily the case, and the invention is not limited to such cases.

A *heat shrinkable film* is a film that shrinks upon heating. It may shrink in two dimensions (biaxially shrinkable film) or only in one dimension (monoaxially

- 3 -

shrinkable film). The shrinkable films according to the present invention shrink along one direction, while along the other direction they retain their original dimensions, or change by no more than 5%.

The stretching of the film is mainly along its longitudinal direction, while contraction in other directions is practically impaired by the use of rollers having between them a distance which is at least ten times smaller than the width of the film (or of the rollers). The distance between the rollers may be in accordance with the present invention smaller than the width of the film in a factor of between 10 and 5000, preferably between about 50 and about 2500.

According to one embodiment of the invention, the shrinkable film is used when its shrinkable dimension is in the direction of the film flow, and the wrapping is carried out in the *wrap around* method.

According to another embodiment, the film wrapped around the article in the sleeve method, namely, it is first cut, closed to form a sleeve having its main axis in the direction of the film flow, the article is inserted into the sleeve, which is then heated to shrink around the article.

The degree of shrinking obtained in the method according to the invention may be between about 10% and about 90%. While 20% shrinkage may also be obtained with other production technologies, for applications where shrinkage of 60% or more is required, the present invention, which uses polymeric film produced by the short-gap-stretching process, is the only technical solution known to the inventors to date. Accordingly, the present invention also provides a polymeric sheet that is unidirectionally shrunk along its main axis (namely in the machine direction) to 50% or less of its original dimension, preferably to 40% or less. In case the polymeric sheet is made of polyolefin, such as polyethylene or polypropylene, the state of the art allows unidirectional shrinking to no less than 75% of the original dimension in the machine direction, and the present invention provides sheets made by such polymers that are shrunk to 70% or less, preferably to 60% or less of their original dimension. The possibility to shrink polymeric sheets to a large degree allows wrapping an article in the wrap-around method, even

- 4 -

if its circumference in one location is considerably different from the circumference in another location. In this connection, considerably different means difference of 50% or more, and in the wrapping polymer is polyolefin, difference of 30% or more.

A polymeric film, for use in accordance with the invention may be composed of any polymeric material known in the art *per se*, and some examples for these are: polystyrene, polyolefins, such as polyethylene, polypropylene, polyvinylchloride, polyamides, Polyester, nylon, copolymers thereof, mixtures thereof, cyclic olefinic copolymers, etc. In particular, a shrinkable polymeric film that is a multilayer is also suitable for use in accordance with the invention. Non-limiting examples for suitable heat shrinkable polymers are such multilayers wherein all the multilayer is stretched as in (a) above, and a multilayer that is produced by attaching a layer that is stretched as in (a) above to another layer, for example, to a bidirectionally oriented layer. Such attaching may be carried out in any of the methods known in the art, such as lamination, coextrusion, and the like.

In accordance with the polymer and additives used, the wrapping may have characteristics such as being a barrier to gases such as oxygen, nitrogen, air, and CO<sub>2</sub>, and/or to water vapor, UV rays, or combinations thereof. In this way, wrappings that lengthen the shelf life of articles that are sensitive to water, oxygen, and/or UV may be obtained.

The temperature to which a film must be heated to shrink it is as known in the art regarding similar films that were obtained by other techniques (i.e. between about 80 and about 120°C, depending on the kind of polymer applied), although some adjustments may be required.

#### **DETAILED DESCRIPTION OF A POSSIBLE EMBODIMENT**

In order to understand the invention and to see how it may be carried out in practice, a possible embodiment will now be described, by way of non-limiting example only.

– 5 –

A polymeric film was produced from a blend of two polyethylene resins, one of which was produced in Spain by Dow Plastics and sold under the trade-name of Dowlex™, and the other produced by Basell Polyolefins (Germany) and sold under the trade-name of Hostalen™. The polymer was processed in a short-gap-stretching machine produced by Lenzing Aktiengesellschaft, described in US 5,184,379, at a heating temperature of 100°C – 120°C and a stretch ratio of 1:6 to produce a monoaxially heat shrinkable film. The film produced in this way underwent shrinkage by up to 70% upon subsequent heating to 100°C - 110°C.

The obtained monoaxially shrinkable film was used for wrapping a plastic bottle in the shape of a woman, having a maximal outer diameter of 6.84 cm and minimal outer diameter of 6.05 cm. The wrapping was carried out on a KRONES roll-fed shrink labeling systems type Krones Contiroll 720-12, at 18,000 bottles per hour and at a tunnel temperature of 250°C.

The film was wrapped around a drum, cut to form a label, and glue was applied to the label's edges. Then the label was wrapped around the bottle such that the glued edges attached the label to the bottle, and the labeled bottle was heated to let the label shrink. This is in contrast to the sleeve method, which is not in accordance with the present invention, wherein the article to be wrapped is introduced into a sleeve made of the wrapping polymer, and then the sleeve is shrunk.

**CLAIMS:**

1. A method for wrapping an article with a heat shrinkable polymeric film comprising:
  - (a) providing a polymeric film produced by a process including stretching said film mainly in its longitudinal direction, said stretching being by means comprising at least one pair of rollers rotating in mutually different linear velocities, the gap between said rollers being at least 10 times smaller than the width of said film to obtain a heat shrinkable polymeric film;
  - (b) surrounding at least a portion of the outer surface of said article with a portion of said heat shrinkable polymeric film; and
  - (c) heating said heat shrinkable polymeric film so as to shrink it around said article.
2. A method according to claim 1, wherein said gap is smaller than the width of said film by a factor of between 10 and 5000.
3. A method according to claim 2, wherein said factor is between 50 and 2500.
4. A method according to any one of claims 1 to 3, wherein said wrapping around is carried out in the *wrap around* method.
5. A method according to any one of claims 1 to 3, wherein said wrapping is made in the sleeve method.
6. A method according to any one of claims 1 to 5 wherein said article is a container.
7. A method according to claim 6 wherein said container is cylindrical.
8. A method according to claim 7 wherein said cylindrical container is of non-uniform diameter.
9. A method according to the preceding claim, wherein the shrinkable film is used with its shrinkable dimension in the direction of the film flow.

– 7 –

10. A method according to any one of the preceding claims, wherein said film shrinks to between about 90% and about 10% of its original dimension.
11. A method according to claim 10 wherein said film shrinks to about 40% or less of its original dimensions.
12. A method according to any one of the preceding claims, wherein said polymeric film comprises a polymer selected from the group consisting of: polystyrene, polyolefins, polyvinylchloride, polyamides, Polyester, nylon, copolymers thereof, and mixtures thereof.
13. A method according to claim 12 wherein said polyolefin is selected from the group consisting of polyethylene and polypropylene.
14. A method according to any one of the preceding claims, wherein said polymer film is capable of acting as a barrier against gas diffusion and/or UV radiation.
15. A method according to claim 14 wherein said gas is oxygen, nitrogen, air, CO<sub>2</sub> and/or water vapor.
16. An article wrapped according to any one of the preceding claims.
17. An article according to claim 16, having a form of a cylinder with non-uniform diameter.
18. An article according to claim 16, wherein the film wrapped around it is printed to form a label.
19. A method for protecting an article from damaging radiation, comprising wrapping said article in accordance with a method according to any one of claims 1-15.
20. A method for lengthening the shelf life of a product that is sensitive to humidity, oxygen, nitrogen, air, and/or CO<sub>2</sub>, comprising wrapping said article in accordance with a method according to any of claims 1-15.
21. A method according to claim 1 comprising:
  - (a) providing a polymeric film produced by a process including stretching said film mainly in its longitudinal direction, said stretching being by means comprising at least one pair of



– 8 –

- rollers rotating in mutually different linear velocities, the gap between said rollers being at least 10 times smaller than the width of said film to obtain a heat-shrinkable polymeric film;
- (b) attaching said heat shrinkable polymeric film to at least one polymeric film to obtain a heat shrinkable multilayer
  - (c) surrounding at least a portion of the outer surface of said article with a portion of said heat shrinkable multilayer; and
  - (d) heating said heat shrinkable multilayer so as to shrink it around said article.
22. A method according to the preceding claim, wherein the attaching mentioned in (b) is carried out by lamination.
23. A method according to claim 21, wherein the attaching mentioned in (b) is carried out by coextrusion.
24. A method according to claim 1, wherein said polymeric film is composed of a plurality of layers attached to each other to produce a multilayer.
25. A polymeric sheet that is unidirectionally shrunked in the machine direction to 50% or less of its original dimension.
26. A polymeric sheet according to claim 25, shrunked in the machine direction to 40% or less of its original dimension.
27. A polymeric sheet made of polyolefin, unidirectionally shrunked in the machine direction to 70% or less of its original dimension.
28. A polymeric sheet according to claim 27, wherein said shrink is to 60% or less of the original dimension.
29. An article wrapped with a polymeric sheet in a wrap-around method along a first and a second location, the circumference in said first location being smaller in 50% or more than a circumference in the second location.
30. An article wrapped with a polymeric sheet in a wrap-around method along a first and a second location, the circumference in said first location being smaller in 30% or more than a circumference in the second location, characterized in that said polymeric sheet is olefinic.

31. An article according to claim 30, wherein said polymeric sheet is made of polyethylene and/or polypropylene.

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/IL2005/000157

**A. CLASSIFICATION OF SUBJECT MATTER**

IPC 7 B65B53/02 B29C55/06 B65D75/00 B32B27/32

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B65B B29C B65D B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 5 234 731 A (FERGUSON ET AL) 10 August 1993 (1993-08-10) column 5, lines 35-64	1-24
Y	EP 1 095 758 A (ILLINOIS TOOL WORKS INC) 2 May 2001 (2001-05-02) cited in the application the whole document	1-24
X	US 4 059 400 A (HECKMAN ET AL) 22 November 1977 (1977-11-22) column 3, lines 34-64	25-28
A	EP 1 120 347 A (G.+L. HEIKAUS KUNSTSTOFFVERARBEITUNG UND VERPACKUNGEN GMBH) 1 August 2001 (2001-08-01) figure 3	29-31
	-/--	

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

° Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

18 May 2005

Date of mailing of the international search report

27/05/2005

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Philippon, D

## INTERNATIONAL SEARCH REPORT

International Application No  
PCT/IL2005/000157

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 38 21 164 A1 (NEWTEC INTERNATIONAL, AIX-LES-BAINS, FR) 5 January 1989 (1989-01-05) claim 1 -----	29-31
A	US 3 796 785 A (REST W,DT ET AL) 12 March 1974 (1974-03-12) column 1, line 64 - column 217; figures -----	1
A	US 5 175 049 A (HUFF ET AL) 29 December 1992 (1992-12-29) column 5, lines 18-50 -----	21
A	FR 1 552 515 A (SHELL INTERNATIONALE RESEARCH MAATSCHAPPIJ N.V) 3 January 1969 (1969-01-03) the whole document -----	1-31

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IL2005/000157

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 5234731	A	10-08-1993	AU 648074 B2	14-04-1994
			AU 7639591 A	28-11-1991
			CA 2022977 A1	26-11-1991
			NZ 237977 A	22-12-1994
EP 1095758	A	02-05-2001	US 6375781 B1	23-04-2002
			BR 0004846 A	31-07-2001
			CA 2319305 A1	28-04-2001
			EP 1095758 A2	02-05-2001
			NO 20005439 A	30-04-2001
US 4059400	A	22-11-1977	AU 506430 B2	03-01-1980
			AU 2337077 A	21-09-1978
			DE 2713465 A1	13-10-1977
			FR 2346299 A1	28-10-1977
			GB 1524336 A	13-09-1978
			JP 1271246 C	25-06-1985
			JP 52119681 A	07-10-1977
			JP 59046769 B	14-11-1984
			ZA 7700846 A	27-09-1978
EP 1120347	A	01-08-2001	DE 10003016 A1	09-08-2001
			EP 1120347 A2	01-08-2001
DE 3821164	A1	05-01-1989	FR 2617124 A1	30-12-1988
			FR 2622532 A2	05-05-1989
US 3796785	A	12-03-1974	NONE	
US 5175049	A	29-12-1992	NONE	
FR 1552515	A	03-01-1969	GB 1103080 A	14-02-1968
			BE 710014 A	29-07-1968
			DE 1611977 A1	04-02-1971
			NL 6801271 A	31-07-1968