



(11) **EP 2 831 292 B1**

(12) **EUROPEAN PATENT SPECIFICATION**

(45) Date of publication and mention
of the grant of the patent:
19.06.2019 Bulletin 2019/25

(51) Int Cl.:
C21D 8/00 (2006.01) C22C 38/18 (2006.01)

(21) Application number: **13713452.4**

(86) International application number:
PCT/EP2013/056940

(22) Date of filing: **02.04.2013**

(87) International publication number:
WO 2013/144373 (03.10.2013 Gazette 2013/40)

(54) **HIGH STRENGTH COLD ROLLED STEEL SHEET AND METHOD OF PRODUCING SUCH STEEL SHEET**

HOCHFESTES KALTGEWALZTES STAHLBLECH UND VERFAHREN ZUR HERSTELLUNG EINES SOLCHEN STAHLBLECHS

TÔLE D'ACIER LAMINÉE À FROID À HAUTE RÉSISTANCE ACIER ET SON PROCÉDÉ DE PRODUCTION

(84) Designated Contracting States:
**AL AT BE BG CH CY CZ DE DK EE ES FI FR GB
GR HR HU IE IS IT LI LT LU LV MC MK MT NL NO
PL PT RO RS SE SI SK SM TR**

- **KRIZAN, Daniel**
A-4020 Linz (AT)
- **PAUL, Stefan**
A-8784 Trieben (AT)
- **PICHLER, Andreas**
A-4840 Vöcklabruck (AT)

(30) Priority: **30.03.2012 PCT/EP2012/055913**

(43) Date of publication of application:
04.02.2015 Bulletin 2015/06

(74) Representative: **Johansson, Lars E.**
Hynell Patenttjänst AB
P.O. Box 138
683 23 Hagfors (SE)

(73) Proprietor: **voestalpine Stahl GmbH**
4020 Linz (AT)

(72) Inventors:
• **HEBESBERGER, Thomas**
A-4061 Pasching (AT)

(56) References cited:
EP-A1- 1 870 482 GB-A- 2 438 618
JP-A- 2004 332 099 JP-A- 2006 283 131
JP-A- 2008 280 577

Note: Within nine months of the publication of the mention of the grant of the European patent in the European Patent Bulletin, any person may give notice to the European Patent Office of opposition to that patent, in accordance with the Implementing Regulations. Notice of opposition shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 2 831 292 B1

Description

TECHNICAL FIELD

[0001] The present invention relates to high strength cold rolled steel sheet suitable for applications in automobiles, construction materials and the like, specifically a high strength steel sheet excellent in formability. In particular, the invention relates to a cold rolled steel sheet having a tensile strength of at least 780 MPa.

[0002] Such a cold rolled high-strength steel sheet is known e.g. from JP 2004 332099 A.

BACKGROUND ART

[0003] For a great variety of applications increased strength levels are pre-requisite for light weight constructions in particular in the automotive industry, since car body mass reduction results in reduced fuel consumption.

[0004] Automotive body parts are often stamped out of sheet steels, forming complex structural members of thin sheet. However, such part cannot be produced from conventional high strength steels because of a too low formability for complex structural parts. For this reason multiphase Transformation Induced Plasticity aided steels (TRIP steels) have gained considerable interest in the last years.

[0005] TRIP steels possess a multi-phase microstructure, which includes a meta-stable retained austenite phase, which is capable of producing the TRIP effect. When the steel is deformed, the austenite transforms into martensite, which results in remarkable work hardening. This hardening effect, acts to resist necking in the material and postpone failure in sheet forming operations. The microstructure of a TRIP steel can greatly alter its mechanical properties. The most important aspects of the TRIP steel microstructure are the volume percentage, size and morphology of the retained austenite phase, as these properties directly affect the austenite to martensite transformation when the steel is deformed. There are several ways in which to chemically stabilize austenite at room temperature. In low alloy TRIP steels the austenite is stabilized through its carbon content and the small size of the austenite grains. The carbon content necessary to stabilize austenite is approximately 1 wt. %. However, high carbon content in steel cannot be used in many applications because of impaired weldability.

[0006] Specific processing routs are therefore required to concentrate the carbon into the austenite in order to stabilize it at room temperature. A common TRIP steel chemistry also contains small additions of other elements to help in stabilizing the austenite as well as to aid in the creation of microstructures which partition carbon into the austenite. The most common additions are 1.5 wt. % of both Si and Mn. In order to inhibit the austenite to decompose during the bainite transformation it is generally considered necessary that the silicon content should be at least 1 wt. %. The silicon content of the steel is important as silicon is insoluble in cementite. US 2009/0238713 discloses such a TRIP steel. However, a high silicon content can be responsible for a poor surface quality of hot rolled steel and a poor coatability of cold rolled steel. Accordingly, partial or complete replacement of silicon by other elements has been investigated and promising results have been reported for Al-based alloy design. However, a disadvantage with the use of aluminium is the segregation behaviour during casting, which results in a depletion of Al in the centre position of the slabs resulting in an increased risk of the formation of martensite bands in the final microstructure.

[0007] Depending on the matrix phase the following main types of TRIP steels are cited:

TPF TRIP steel with matrix of polygonal ferrite

TPF steels, as already mentioned before-hand, contain the matrix from relatively soft polygonal ferrite with inclusions from bainite and retained austenite. Retained austenite transforms to martensite upon deformation, resulting in a desirable TRIP effect, which allows the steel to achieve an excellent combination of strength and drawability. Their stretch flangability is however lower compared to TBF, TMF and TAM steels with more homogeneous microstructure and stronger matrix.

TBF TRIP steel with matrix of bainitic ferrite

TBF steels have been known for long and attracted a lot of interest because the bainitic ferrite matrix allows an excellent stretch flangability. Moreover, similarly to TPF steels, the TRIP effect, ensured by the strain-induced transformation of metastable retained austenite islands into martensite, remarkably improves their drawability.

TMF TRIP steel with matrix of martensitic ferrite

TMF steels also contain small islands of metastable retained austenite embedded into strong martensitic matrix, which enables these steels to achieve even better stretch flangability compared to TBF steels. Although these steels also exhibit the TRIP effect, their drawability is lower compared to TBF steels.

TAM TRIP steel with matrix of annealed martensite

TAM steels contain the matrix from needle-like ferrite obtained by re-annealing of fresh martensite. A pronounced TRIP effect is again enabled by the transformation of metastable retained austenite inclusions into martensite upon straining. Despite their promising combination of strength, drawability and stretch flangability, these steels have not gained a remarkable industrial interest due to their complicated and expensive double-heat cycle.

DISCLOSURE OF THE INVENTION

[0008] The present invention is directed to a high strength cold rolled steel sheet having a tensile strength of at least 780 MPa and having an excellent formability and a method of producing the same on an industrial scale. In particular, the invention relates to a cold rolled TPF steel sheet having properties adapted for the production in a conventional industrial annealing line. Accordingly, the steel shall not only possess good formability properties but at the same time be optimized with respect to A_{c3} -temperature, M_s -temperature, austempering time and temperature and other factors such as sticky scale influencing the surface quality of the hot rolled steel sheet and the processability of the steel sheet in the industrial annealing line.

DETAILED DESCRIPTION

[0009] The invention is described in the claims.

[0010] In the following specification the following abbreviations are:

PF= polygonal ferrite,
 B = bainite,
 BF= bainitic ferrite,
 TM = tempered martensite.
 RA = retained austenite
 R_m = tensile strength (MPa)
 A_g = uniform elongation, UEI (%)
 A_{80} = total elongation (%)
 $R_{p0.2}$ = yield strength (MPa)
 HR = hot rolling reduction (%)
 T_{an} = annealing temperature ($^{\circ}$ C)
 t_{an} = annealing time (s)
 CR1= cooling rate ($^{\circ}$ C/s)
 T_Q = quenching temperature ($^{\circ}$ C)
 CR2 = cooling rate ($^{\circ}$ C/s)
 T_{RJ} = stop temperature of rapid cooling ($^{\circ}$ C)
 T_{OA} = overageing/austempering temperature ($^{\circ}$ C)
 t_{OA} = overageing/austempering time (s)
 CR3 = cooling rate ($^{\circ}$ C/s)

[0011] The cold rolled high strength TPF steel sheet has a composition consisting of the following elements (in wt. %):

C	0.1 - 0.3
Mn	1.4 - 2.7
Si	0.4 - 1.0
Cr	0.1 - 0.9
Si + Cr	≥ 0.9
Al	≤ 0.8
Nb	< 0.1
Mo	< 0.3
Ti	< 0.2
V	< 0.2
Cu	< 0.5
Ni	< 0.5
B	< 0.005

(continued)

Ca	< 0.005
Mg	< 0.005
REM	< 0.005

balance Fe apart from impurities.

[0012] The reasons for the limitation of the elements are explained below.

[0013] The elements C, Mn, Si and Cr are essential to the invention for the reasons set out below:

C: 0.1 - 0.3 %

[0014] C is an element which stabilizes austenite and is important for obtaining sufficient carbon within the retained austenite phase. C is also important for obtaining the desired strength level. Generally, an increase of the tensile strength in the order of 100 MPa per 0.1 %C can be expected. When C is lower than 0.1 % then it is difficult to attain a tensile strength of 780 MPa. If C exceeds 0.3 % then weldability is impaired. For this reasons, preferred ranges are 0.1 - 0.25 %, 0.13 - 0.17 %, 0.15 - 0.19 % or 0.19-0.23 % depending on the desired strength level.

Mn: 1.4 - 2.7 %

[0015] Manganese is a solid solution strengthening element, which stabilises the austenite by lowering the M_s temperature and prevents pearlite to be formed during cooling. In addition, Mn lower the A_{c3} temperature. At a content of less than 1.4 % it might be difficult to obtain a tensile strength of at least 780 MPa. It may be difficult to obtain a tensile strength of at least 780 MPa already at a content of less than 1.7 %. However, if the amount of Mn is higher than 2.7 % problems with segregation may occur and the workability may be deteriorated. The upper limit is also determined by the influence of Mn on the microstructure during cooling on the run out table and in the coil since a high Mn contents may result in the formation of a martensite fraction which is unfavourable for cold rolling. Preferred ranges are therefore 1.5 - 2.5, 1.5 - 1.7 %, 1.5 - 2.3, 1.7 - 2.3 %, 1.8 - 2.2 %, 1.9 - 2.3 % and 2.3 - 2.5 %.

Si: 0.4 - 1.0 %

[0016] Si acts as a solid solution strengthening element and is important for securing the strength of the thin steel sheet. Si is insoluble in cementite and will therefore act to greatly delay the formation of carbides during the bainite transformation as time must be given to Si to diffuse from the precipitating cementite. Si improves the mechanical properties of the steel sheet. However, high Si forms Si oxides on the surface which may result in pickles on the rolls resulting in surface defects. Further, galvanizing is very difficult for high Si contents, i.e. the risk for surface defects increases. Therefore, Si is limited to 1.0 %. Preferred ranges are therefore 0.4 - 0.9 %, 0.4 - 0.8 %, 0.5 - 0.9 %, 0.5 - 0.7 % and 0.75 - 0.90 %.

Cr: 0.1 - 0.9 %

[0017] Cr is effective in increasing the strength of the steel sheet. Cr is an element that forms ferrite and retards the formation of pearlite and bainite. The A_{c3} temperature and the M_s temperature are only slightly lowered with increasing Cr content. In this type of steel the amount of retained austenite increases with the chromium content. However, due to the retardation of the bainite transformation longer holding times are required such that the processing on a conventional industrial annealing line is made difficult or impossible, when using normal line speeds. For this reason the amount of Cr is preferably limited to 0.8 %. Preferred ranges are therefore 0.15 - 0.6 %, 0.15 - 0.35 %, 0.3 - 0.7 %, 0.5 - 0.7 %, 0.4 - 0.8 %, and 0.25 - 0.35 %.

Si + Cr: ≥ 0.9

[0018] Si and Cr are also efficient in reducing the risk for martensite banding in that they counteract the effect of the manganese segregation during casting. In addition, and completely unforeseen, the combined provision of Si and Cr has been found to result in an increased amount of residual austenite, which, in turn, results in an improved ductility. For these reasons the amount of Si + Cr must be ≥ 0.9 . However, too large amounts of Si + Cr could result in a strong delay of the bainite formation and therefore Si + Cr is preferably limited to 1.4 %. Preferred ranges are therefore 1.0 - 1.4 %, 1.05 - 1.30 % and 1.1 - 1.2 %.

Si/Cr = 1 - 5

[0019] Si shall be present in the steel in at least the same amount as Cr in order to get a balance between a strong retardation of cementite precipitation and a small delay of the bainite formation kinetics as Si and Cr retards cementite formation and Cr has a strong delaying effect on the bainite formation kinetics. Preferably Si is present in a greater amount than Cr. Preferred ranges for Si/Cr are therefore 1 - 5, 1.5 - 3, 1.7 - 3, 1.7 - 2.8, 2 - 3 and 2.1 - 2.8.

[0020] In addition to C, Mn, Si and Cr the steel may optionally contain one or more of the following elements in order to adjust the microstructure, influence on transformation kinetics and/or to fine tune one or more of the mechanical properties.

Al: ≤ 0.8

[0021] Al promotes ferrite formation and is also commonly used as a deoxidizer. Al, like Si, is not soluble in the cementite and therefore considerably delays the cementite formation during bainite formation. Additions of Al result in a remarkable increase in the carbon content in the retained austenite. However, the M_s temperature is increased with increasing Al content. A further drawback of Al is that it results in a drastic increase in the A_{c3} temperature. However, since the inventive TPF alloys can be annealed in the two-phase region substantial amounts of Al may be used. Al is used with success for the substitution of Si in TRIP steel grades. However, a main disadvantage of Al is its segregation behavior during casting. During casting Mn is enriched in the middle of the slabs and the Al-content is decreased. Therefore in the middle a significant austenite stabilized region or band is formed. This results at the end of the processing in martensite banding and at low strain internal cracks are formed in the martensite band. On the other hand, Si and Cr are also enriched during casting. Hence, the propensity for martensite banding may be reduced by alloying with Si and Cr since the austenite stabilization due to the Mn enrichment is counteracted by these elements. For these reasons the Al content is preferably limited to 0.6 %, preferably 0.1 %, most preferably to less than 0.06 %.

Nb: < 0.1

[0022] Nb is commonly used in low alloyed steels for improving strength and toughness because of its remarkable influence on the grain size development. Nb increases the strength elongation balance by refining the matrix microstructure and the retained austenite phase due to precipitation of NbC. Hence, additions of Nb may be used to obtain a high strength steel sheet having good deep drawability. At contents above 0.1 % the effect is saturated.

[0023] Preferred ranges are therefore 0.01-0.08 %, 0.01 - 0.04 % and 0.01 - 0.03 %. Even more preferred ranges are 0.02-0.08 %, 0.02-0.04 % and 0.02-0.03 %.

Mo: < 0.3

[0024] Mo can be added in order to improve the strength. Addition of Mo together with Nb results in precipitation of fine NbMoC carbides which results in a further improvement in the combination of strength and ductility.

Ti: < 0.2 ; V: < 0.2

[0025] These elements are effective for precipitation hardening. Ti may be added in preferred amounts of 0.01 - 0.1 %, 0.02 - 0.08 % or 0.02 - 0.05 %. V may be added in preferred amounts of 0.01 - 0.1 % or 0.02 - 0.08 %.

Cu: < 0.5 ; Ni: < 0.5

[0026] These elements are solid solution strengthening elements and may have a positive effect on the corrosion resistance. They may be added in amounts of 0.05 - 0.5 % or 0.1 - 0.3 % if needed.

B: < 0.005

[0027] B suppresses the formation of ferrite and improves the weldability of the steel sheet. For having a noticeable effect at least 0.0002 % should be added. However, excessive amounts of B deteriorate the workability.

[0028] Preferred ranges are < 0.004 %, 0.0005- 0.003 % and 0.0008 -0.0017 %.

Ca: < 0.005 ; Mg: < 0.005 ; REM: < 0.005

[0029] These elements may be added in order to control the morphology of the inclusions in the steel and thereby

improve the hole expandability and the stretch flangability of the steel sheet.

[0030] Preferred ranges are 0.0005 -0.005 % and 0.001- 0.003 %.

Si > Al

[0031] The high strength cold rolled steel sheet according to the invention has a silicon based design, i.e. the amount of Si is larger than the amount of Al, preferably Si > 1.3 Al, more preferably Si > 2Al, most preferably Si > 3Al.

Mn + 3Cr

[0032] To avoid a too strong retardation of the bainite formation in the steel sheet of the present invention it is preferred to control the ratio of $Mn + 3Cr \leq 3.8$, preferably ≤ 3.6 and more preferred ≤ 3.4 .

$(Rp_{0.2})/(R_m)$

[0033] In the steel sheet of the present invention it is preferred to control the yield ratio of $(Rp_{0.2})/(R_m) \leq 0.7$, preferably $(Rp_{0.2})/(R_m) \leq 0.75$, in order to get the desired formability.

[0034] The high strength cold rolled TPF steel sheet has a multiphase microstructure comprising (in vol. %)

retained austenite	5 - 22
bainite + bainitic ferrite + tempered martensite	≤ 80
polygonal ferrite	≥ 10

[0035] The amount of retained austenite (RA) is 5-22 %, preferably 6 - 22 %, and more preferred 6 - 16 %. Because of the TRIP effect retained austenite is a prerequisite when high elongation is necessary. High amount of residual austenite decreases the stretch flangability. In these steel sheets the matrix mainly consists of the soft polygonal ferrite (PF) with an amount generally exceeding 50 %. Only a minor amount of bainitic ferrite (BF) is usually present in the final microstructure. As a consequence of insufficient local austenite stability the structure may also contain some minor amounts of fresh martensite forming during cooling to room temperature.

[0036] The high strength cold rolled TPF steel sheet has the following mechanical properties

tensile strength (R_m)	≥ 780	MPa
total elongation (A_{80})	≥ 12	%, preferably ≥ 13 %, more preferred ≥ 14 %

[0037] The R_m and A_{80} values were derived according to the European norm EN 10002 Part 1, wherein the samples were taken in the longitudinal direction of the strip.

[0038] The formability of the steel sheet was assessed by the strength-elongation balance ($R_m \times A_{80}$).

[0039] The steel sheet of the present invention fulfils the following condition:

$$R_m \times A_{80} \geq 13\,000 \text{ MPa}\%$$

[0040] The mechanical properties of the steel sheet of the present invention can be largely adjusted by the alloying composition and the microstructure.

[0041] In one preferred embodiment the high strength cold rolled steel sheet has a tensile strength of at least 780MPa wherein the steel comprises:

C	0.17 - 0.23
Mn	1.5 - 1.8, preferably 1.5 - 1.7
Si	0.4 - 0.8, preferably 0.4 - 1.7
Cr	0.3 - 0.7, preferably 0.4 - 0.7

optionally

Nb	0.01- 0.03, preferably 0.02 - 0.03
----	------------------------------------

EP 2 831 292 B1

or

C	0.13 - 0.17
Mn	1.7 - 2.3
Si	0.5 - 0.9
Cr	0.3 - 0.7

optionally

Nb 0.01 - 0.03, preferably 0.02 - 0.03

and wherein the steel sheet fulfil at least one of the following requirements:

(R _m)	780 - 1200	MPa
(A ₈₀)	≥ 15	%

and

$R_m \times A_{80} \geq 14\,000$ MPa%, preferably $\geq 16\,000$ MPa%

[0042] Typical compositions for the high strength cold rolled steel sheet having a tensile strength of at least 780 MPa could be:

C ~ 0.2 %, Mn ~ 1.6 %, Si ~ 0.6 %, Cr ~ 0.6 %, Nb ~ 0 or 0.025 %, or
C ~ 0.15 %, Mn ~ 1.8 %, Si ~ 0.7 %, Cr ~ 0.4 %, Nb ~ 0 or 0.025%, rest iron apart from impurities.

[0043] In another preferred embodiment the high strength cold rolled steel sheet has a tensile strength of at least 980 MPa wherein the steel comprises:

C	0.18 - 0.22
Mn	1.7 - 2.3
Si	0.5 - 0.9
Cr	0.3 - 0.8

optionally

Si + Cr	≥ 1.0
Nb	0.01 - 0.03

or

C	0.14 - 0.20
Mn	1.9 - 2.5
Si	0.5 - 0.9
Cr	0.3 - 0.8

optionally

Si + Cr	≥ 1.0
Nb	0.01 - 0.03

and wherein the steel sheet fulfil at least one of the following requirements

EP 2 831 292 B1

$$\begin{array}{lll} (R_m) & 980 - 1200 & \text{MPa} \\ (A_{80}) & \geq 13 & \% \end{array}$$

and

$$R_m \times A_{80} \geq 13\,000 \quad \text{MPa}\%$$

[0044] Typical compositions for the high strength cold rolled steel sheet having a tensile strength of at least 980 MPa could C ~ 0.18 %, Mn ~ 2.2 %, Si ~ 0.8 %, Cr ~ 0.5 %, Nb ~ 0 or 0.025 %, rest iron apart from impurities.

[0045] In yet another preferred embodiment the high strength cold rolled steel sheet has a tensile strength (R_m) of at least 1180 MPa. In this embodiment the steel comprises

$$\begin{array}{ll} \text{C} & 0.18 - 0.22 \\ \text{Mn} & 1.7 - 2.5, \text{ preferably } 1.7 - 2.3 \\ \text{Si} & 0.5 - 0.9 \\ \text{Cr} & 0.4 - 0.8 \end{array}$$

optionally

$$\begin{array}{ll} \text{Si} + \text{Cr} & \geq 1.1 \\ \text{Nb} & 0.01 - 0.03, \text{ preferably } 0.02 - 0.03 \end{array}$$

and fulfil at least one of the following requirements

$$\begin{array}{ll} (R_m) & 1000 - 1400 \text{ MPa, preferably } 1180 - 1400 \text{ MPa} \\ (A_{80}) & \geq 10 \%, \text{ preferably } \geq 14 \% \end{array}$$

and

$$R_m \times A_{80} \geq 12\,000 \quad \text{MPa}\%, \text{ preferably } \geq 15\,000 \text{ MPa}\%$$

[0046] A typical composition for the high strength cold rolled steel sheet having a tensile strength of at least 1180 MPa could be:

$$\begin{array}{l} \text{C} \sim 0.2 \%, \text{ Mn} \sim 2.2 \%, \text{ Si} \sim 0.8 \%, \text{ Cr} \sim 0.6 \%, \text{ Nb} \sim 0 \text{ or } 0.025 \%, \text{ rest iron apart from impurities, or} \\ \text{C} \sim 0.2 \%, \text{ Mn} \sim 2 \%, \text{ Si} \sim 0.6 \%, \text{ Cr} \sim 0.6 \%, \text{ Nb} \sim 0 \text{ or } 0.025 \%, \text{ rest iron apart from impurities.} \end{array}$$

[0047] The high strength cold rolled steel sheet of the present invention can be produced using a conventional industrial annealing line. The processing comprises the steps of:

- a) providing a cold rolled strip having a composition as set out above,
- b) annealing the cold rolled strip at an annealing temperature, T_{an} , that is between 760 °C and $A_{c3} + 20$ °C, followed by
- c) cooling the cold rolled strip from the annealing temperature, T_{an} , to a cooling stop temperature, T_{RJ} , that is between 300 and 475 °C, preferably 350 and 475 °C at a cooling rate that is sufficient to avoid pearlite formation, followed by
- d) austempering the cold rolled strip at an overageing/austempering temperature, T_{OA} , that is between 320 and 480 °C, and
- e) cooling the cold rolled strip to ambient temperature.

[0048] The process shall preferably further comprise the steps of:

in step b) the annealing being performed at an annealing temperature, T_{an} , that is between 760 and 820 °C, during an annealing holding time, t_{an} , of up to 100 s, preferably 60 s,

in step c) the cooling can be performed according to a cooling pattern having two separate cooling rates; a first cooling rate, CR1, of about 3 - 20 °C/s, from the annealing temperature, T_{an} , to a quenching temperature, T_Q , that is between 600 and 750 °C, and a second cooling rate, CR2, of about 20 - 100 °C/s, from the quenching temperature, T_Q , to the stop temperature of rapid cooling, T_{RJ} , and

in step d) the austempering of the steel sheet being performed at an overageing/austempering temperature, T_{OA} , that is between 350 and 475 °C and an overageing/austempering time, t_{OA} , that is between 50 and 600 s.

[0049] Preferably, no external heating is applied to the steel sheet between step c) and d).

[0050] In one conceivable method of producing the high strength cold rolled steel sheet of the invention the austempering in step d) is performed at an overageing/austempering temperature, T_{OA} , which is between 375 and 475 °C for an overageing/austempering time, t_{OA} , of ≤ 200 s.

[0051] In another conceivable method of producing the high strength cold rolled steel sheet of the invention the austempering in step d) is performed at an overageing/austempering temperature, T_{OA} , which is between 350 and 450 °C for an overageing/austempering time, t_{OA} , of ≥ 200 s.

[0052] The reasons for regulating the heat treatment conditions are set out below:

Annealing temperature, T_{an} , = 760 °C to A_{c3} temperature + 20 °C:

[0053] The annealing temperature controls the recrystallization, the dissolution of cementite and the amount of ferrite and austenite during annealing. Low annealing temperature, T_{an} , results in an unrecrystallized microstructure and an insufficient dissolution of cementite. High annealing temperatures results in a fully austenitization and grain growth. This may result in an insufficient ferrite formation during cooling.

Austempering temperature, T_{OA} , being between 320 and 480 °C:

[0054] By controlling the austempering temperature, T_{OA} , to the mentioned range, the amount of bainite, the undesirable precipitation of cementite and therefore the amount and stability of retained austenite, RA, can be controlled. Lower austempering temperature, T_{OA} , will lower the bainite formation kinetics and a too small amount of bainite can result in an unsatisfying stabilized retained austenite. A higher austempering temperature, T_{OA} , increases the bainite formation kinetic but generally the amount of bainite is reduced and this may result in an unsatisfyingly stabilized retained austenite. A further increase of the austempering temperature could result in undesirable precipitation of cementite.

Cooling stop temperature of rapid cooling, T_{RJ} , being between 300 and 475 °C

[0055] By controlling the cooling stop temperature of rapid cooling, T_{RJ} , a further controlling of the transformation prior austempering is possible and this can be applied for a fine tuning of the obtained amounts of different constituents.

First and second cooling rates, CR1, CR2:

[0056] A cooling pattern for cooling the annealed strip from the annealing temperature, T_{an} , to the stop temperature of rapid cooling, T_{RJ} , may have two separate cooling steps. By controlling the first cooling rate, CR1 to about 3 - 20 °C/s from the annealing temperature, T_{an} , to a quenching temperature, T_Q , that is between 600 and 750 °C and a second cooling rate, CR2, of about 20 - 100 °C/s from the quenching temperature, T_Q , to the stop temperature of rapid cooling, T_{RJ} , the amount of polygonal ferrite and, by extension, the amount of austenite may be controlled. Furthermore, by this cooling pattern the formation of pearlite is avoided, as pearlite deteriorates formability properties of the steel sheet. However, a small amount of pearlite may be present in the quenched strip. Up to 1 % of pearlite may be present although it is preferred that the quenched strip is void of pearlite.

Third cooling rate CR3:

[0057] The cooling schedule from the austempering temperature, T_{OA} , to room temperature typical applied in annealing lines has a neglectable impact on the microstructure and mechanical properties of the steel sheet.

Examples

[0058] A number of test alloys A-Q were manufactured having chemical compositions according to table I. Steel sheets were manufactured and subjected to heat treatment using a conventional industrial annealing line according to the parameters specified in Table II. The microstructures of the steel sheets were examined along with a number of other mechanical properties and the result is presented in Table III. In Table I and Table III examples according to the invention or outside the invention are marked by Y or N respectively.

5

10

15

20

25

30

35

40

45

50

55

Table I

Steel	C	Si	Mn	P	S	Al	Cr	Ni	Mo	Cu	V	Nb	Ti	B	N	Ac3	Ms	Invention
A	0,200	0,65	1,55	0,0048	0,0041	0,069	0,015	0,009	<0,001	0,014	< 0,001	< 0,001	<0,001	0,0004	0,0035	802	400	N
B	0,198	0,64	1,56	0,0047	0,0034	0,063	0,300	0,009	0,001	0,013	< 0,001	< 0,001	<0,001	0,0003	0,0038	801	397	Y
C	0,197	0,65	1,51	0,0039	0,0021	0,060	0,550	0,014	<0,001	0,014	< 0,001	< 0,001	0,001	0,0003	0,0037	803	396	Y
D	0,197	0,62	1,98	0,0056	0,0065	0,055	0,014	0,010	0,003	0,015	0,002	< 0,002	0,003	0,0003	0,0046	788	388	N
E	0,199	0,85	2,25	0,0076	0,0068	0,046	0,120	0,011	0,003	0,017	0,002	0,027	0,003	0,0003	0,0040	790	375	Y
F	0,220	0,87	2,30	0,0070	0,0054	0,045	0,320	0,009	0,002	0,017	0,002	0,027	0,003	0,0004	0,0037	785	362	Y
G	0,200	0,84	2,26	0,0081	0,0049	0,046	0,580	0,011	0,003	0,016	0,002	0,027	0,003	0,0003	0,0047	789	369	Y
H	0,210	0,84	2,00	0,0077	0,0050	0,050	0,310	0,010	0,003	0,017	0,002	0,026	0,003	0,0003	0,0046	794	376	Y
I	0,210	0,84	2,24	0,0079	0,0051	0,048	0,320	0,011	0,003	0,017	0,002	< 0,002	0,002	0,0004	0,0051	787	369	Y
J	0,220	0,84	2,23	0,0082	0,0040	0,054	0,320	0,011	0,003	0,017	0,002	0,049	0,003	0,0003	0,0051	785	365	Y
K	0,198	0,55	1,51	0,0066	0,0042	0,044	0,017	0,010	0,004	0,015	0,002	< 0,002	0,003	0,0003	0,0046	799	403	N
L	0,196	0,72	1,49	0,0065	0,0043	0,045	0,017	0,010	0,004	0,015	0,002	< 0,002	0,003	0,0003	0,0047	807	402	N
M	0,200	1,09	1,52	0,0062	0,0039	0,043	0,018	0,010	0,004	0,015	0,002	< 0,002	0,002	0,0003	0,0045	822	396	N
N	0,200	1,52	1,50	0,0068	0,0041	0,042	0,017	0,010	0,004	0,015	0,002	< 0,002	0,003	0,0002	0,0048	842	392	N
O	0,131	0,84	2,31	0,0076	0,0037	0,038	0,290	0,012	0,003	0,018	0,002	< 0,001	0,002	0,0003	0,0038	805	400	Y
P	0,250	0,82	2,34	0,0078	0,0039	0,041	0,300	0,012	0,003	0,018	0,002	< 0,001	0,002	0,0003	0,0042	775	349	Y
Q	0,145	0,65	1,9	0,009	0,0022	0,045	0,35	0,015	0,004	0,016	0,002	0,025	0,003	0,0002	0,0046	808	415	Y

EP 2 831 292 B1

Table II

Heat cycle No.	HR	T _{an}	t _{an}	CR1	T _Q	CR2	T _{RJ}	T _{OA}	t _{OA}	CR3
1	20	800	60	5	720	50	325	325	600	30
2	20	800	60	5	720	50	350	350	600	30
3	20	800	60	5	720	50	375	375	600	30
4	20	800	60	5	720	50	400	400	600	30
5	20	800	60	5	720	50	425	425	600	30
6	20	800	60	5	720	50	450	450	600	30
7	20	800	60	5	720	50	400	400	120	30
8	20	800	60	5	720	50	425	425	120	30
9	20	800	60	5	720	50	450	450	120	30
10	20	800	60	5	720	50	475	475	120	30
11	20	800	60	5	720	50	425	425	60	30
12	20	780	60	5	720	50	400	400	600	30
13	20	820	60	5	720	50	400	400	600	30
14	20	880	60	5	720	50	400	400	600	30

Table III

Example	Chemical composition	Heat cycle No.	PF	B + BF + TM	RA	Rp0.2	Rm	Ag	A80	Rm x A80	Invention	Rp0.2/Rm
1	A	4	72	24,0	4,0	562	713	13,5	17,5	12478	N	0,79
2	B	4	63	29,0	8,0	598	821	16,5	21,0	17241	Y	0,73
3	C	4	57	30,0	13,0	604	825	17,5	23,5	19388	Y	0,73
4	D	4	38	54,5	7,5	634	911	9,3	13,3	12116	N	0,70
5	E	4	34	53	13,0	613	941	14,8	18,5	17409	Y	0,65
6	F	4	29	59,5	11,5	603	1049	14,6	17,8	18672	Y	0,57
7	G	4	25	65,1	9,9	594	1116	11,3	14,3	15959	Y	0,53
8	H	4	36	53,0	11,0	561	919	17,3	21,1	19391	Y	0,61
9	I	4	27	60,9	12,1	580	1021	12,9	16,4	16744	Y	0,57
10	J	4	30	59,1	10,9	606	990	13,8	17,2	17028	Y	0,61
11	K	4	73	20,8	6,2	523	650	11,3	15,4	10010	N	0,80
12	L	4	67	25,2	7,8	483	702	14,1	17,8	12496	N	0,69
13	M	4	63	25,1	11,9	472	735	17,4	21,5	15803	N	0,64
14	N	4	65	20,5	14,5	504	754	18,9	26,5	19981	N	0,67
15	O	4	43	48,1	8,9	603	945	10,4	14,9	14081	Y	0,64
16	P	4	26	59,7	14,3	667	1129	10,1	12,5	14113	Y	0,59
17	C	1	61	31,6	7,4	663	964	8,6	11,4	10990	N	0,69
18	C	2	59	33,0	8,0	648	903	11,9	16,1	14538	Y	0,72
19	C	3	58	32,5	9,5	624	843	15,1	18,9	15933	Y	0,74
20	C	4	60	29,2	10,8	598	829	15,9	20,5	16995	Y	0,72
21	C	5	62	25,5	12,5	482	823	17,5	21,8	17941	Y	0,59
22	C	6	65	28,5	6,5	513	894	12,8	17,3	15466	Y	0,57
23	C	7	58	28,5	13,5	476	877	15,9	20,2	17715	Y	0,54
24	C	8	62	23,4	14,6	478	842	18,3	24,3	20461	Y	0,57
25	C	9	61	23,8	15,2	422	861	16,2	21,2	18253	Y	0,49

(continued)

Example	Chemical composition	Heat cycle No.	PF	B + BF + TM	RA	Rp0.2	Rm	Ag	A80	Rm x A80	Invention	Rp0.2/Rm
26	C	10	65	25,9	9,1	427	891	15,2	18,8	16751	Y	0,48
27	Q	8	38	50,1	11,9	512	821	17,8	22,6	18555	Y	0,62
28	Q	11	36	52,5	11,5	498	835	16,4	20,6	17201	Y	0,60
29	H	12	39	50,6	10,4	516,6	889,2	17,1	20,7	18406	Y	0,58
30	H	13	31	58,8	10,2	681,2	968,1	12,5	16,8	16264	Y	0,70
31	H	14	<5	> 86	9,0	784,2	973,6	8,7	12	11683	N	0,81

INDUSTRIAL APPLICABILITY

[0059] The present invention can be widely applied to high strength steel sheets having excellent formability for vehicles such as automobiles.

Claims

1. A high strength cold rolled steel sheet comprising:

a) a composition consisting of the following elements (in wt. %):

C	0.1 - 0.3
Mn	1.4 - 2.7
Si	0.4 - 1.0
Cr	0.1 - 0.9
Si + Cr	≥ 0.9
Al	≤ 0.8
Nb	< 0.1
Mo	< 0.3
Ti	< 0.2
V	< 0.2
Cu	< 0.5
Ni	< 0.5
S	≤ 0.01
P	≤ 0.02
N	≤ 0.02
B	< 0.005
Ca	< 0.005
Mg	< 0.005
REM	< 0.005

balance Fe apart from impurities,

b) a multiphase microstructure consisting of (in vol. %)

retained austenite	5 - 22
bainite + ferritic bainite + tempered martensite	≤ 80
polygonal ferrite	≥ 10

c) the following mechanical properties

a tensile strength (R_m)	≥ 780	MPa
an elongation (A_{80})	≥ 12	%, preferably ≥ 13 %,

and optionally fulfilling the following condition

$$R_m \times A_{80} \geq 13\,000 \quad \text{MPa}\%$$

2. A high strength cold rolled steel sheet according to claim 1 fulfilling at least one of:

C 0.13 - 0.25

EP 2 831 292 B1

(continued)

Mn	1.5 - 2.5, preferably 1.5 - 2.3, even more preferred 1.7 - 2.3
Si	0.4 - 0.9
Cr	0.2 - 0.6

3. A high strength cold rolled steel sheet according to any of the preceding claims fulfilling at least one of:

Al	≤ 0.1 , preferably ≤ 0.06
Nb	0.02 - 0.08
Mo	0.05 - 0.3
Ti	0.02 - 0.08
V	0.02 - 0.1
Cu	0.05 - 0.4
Ni	0.05 - 0.4
B	0.0002 - 0.003
Ca	0.0005 - 0.005
Mg	0.0005 - 0.005
REM	0.0005 - 0.005

4. A high strength cold rolled steel sheet according to any of the preceding claims fulfilling at least one of:

S	≤ 0.01	preferably ≤ 0.003
P	≤ 0.02	preferably ≤ 0.01
N	≤ 0.02	preferably ≤ 0.005
Ti	$> 3.4N$	

5. A high strength cold rolled steel sheet according to according to any of the preceding claims wherein the maximum size of the retained austenite (RA) is $\leq 6 \mu\text{m}$, preferably $\leq 3 \mu\text{m}$.

6. A high strength cold rolled steel sheet according to any of the preceding claims wherein the multiphase microstructure comprising (in vol. %)

retained austenite	6-16
bainite + ferritic bainite + tempered martensite	≤ 80
polygonal ferrite	≥ 10

7. A high strength cold rolled steel sheet according to any of the preceding claims wherein the steel comprises:

C	0.17 - 0.23
Mn	1.5 - 1.8, preferably 1.5 - 1.7
Si	0.4 - 0.8, preferably 0.4 - 0.7
Cr	0.3 - 0.7, preferably 0.4 - 0.7

optionally

Nb	0.01-0.03, preferably 0.02 - 0.03
----	-----------------------------------

and wherein the steel sheet fulfils at least one of the following requirements:

EP 2 831 292 B1

(R_m) 780 - 1200 MPa
(A₈₀) ≥ 15 %

and

$R_m \times A_{80} \geq 16\,000 \text{ MPa\%}$

8. A high strength cold rolled steel sheet according to any of claims 1-6 wherein the steel comprises:

C 0.13 - 0.17
Mn 1.7 - 2.3
Si 0.5 - 0.9
Cr 0.3 - 0.7

optionally

Nb 0.01 - 0.03, preferably 0.02 - 0.03

and wherein the steel sheet fulfils at least one of the following requirements:

(R_m) 780 - 1200 MPa
(A₈₀) ≥ 15 %

and

$R_m \times A_{80} \geq 14\,000 \text{ MPa\%, preferably } \geq 16\,000 \text{ MPa\%}$

9. A high strength cold rolled steel sheet according to any of claims 1-6 wherein the steel comprises:

C 0.18 - 0.22
Mn 1.7 - 2.3
Si 0.5 - 0.9
Cr 0.3 - 0.8

optionally

Si + Cr ≥ 1.0
Nb 0.01 - 0.03

and wherein the steel sheet fulfils at least one of the following requirements

(R_m) 980 - 1200 MPa
(A₈₀) ≥ 13 %

and

$R_m \times A_{80} \geq 13\,000 \text{ MPa\%}$

EP 2 831 292 B1

10. A high strength cold rolled steel sheet according to any of claims 1-6 wherein the steel comprises

C	0.14 - 0.20
Mn	1.9 - 2.5
Si	0.5 - 0.9
Cr	0.3 - 0.8

optionally

Si + Cr	≥ 1.0
Nb	0.01 - 0.03

and wherein the steel sheet fulfils at least one of the following requirements

(R_m)	980 - 1200	MPa
(A_{80})	≥ 13	%

and

$$R_m \times A_{80} \geq 13\,000 \text{ MPa\%}.$$

11. A high strength cold rolled steel sheet according to any of claims 1-6 wherein the steel comprises:

C	0.18 - 0.22
Mn	1.7 - 2.5, preferably 1.7 - 2.3
Si	0.5 - 0.9
Cr	0.4 - 0.8

optionally

Si + Cr	≥ 1.1
Nb	0.01 - 0.03, preferably 0.02 - 0.03

and wherein the steel sheet fulfils at least one of the following requirements:

(R_m)	1000 - 1400	MPa, preferably 1180 - 1400 MPa
(A_{80})	≥ 10	%, preferably ≥ 14 %

and

$$R_m \times A_{80} \geq 12\,000 \text{ MPa\%}, \text{ preferably } \geq 15\,000 \text{ MPa\%}$$

12. A high strength cold rolled steel sheet according to any of the preceding claims wherein the ratio $Mn + 3 \times Cr \leq 3.8$, preferably ≤ 3.6 , most preferred ≤ 3.4 .

13. A high strength cold rolled steel sheet according to any of the preceding claims wherein the amount of Si > Al, preferably Si > 1.3 Al, more preferably Si > 5Al, most preferably Si > 10Al.

14. A high strength cold rolled steel sheet according to any of the preceding claims wherein the ratio of Si/Cr = 1 - 5, preferably 1.5 - 3, more preferably 1.7 - 3, most preferably 1.7-2.8.

15. A high strength cold rolled steel sheet according to any of the preceding claims which is not provided with a hot dip galvanizing layer.

16. A method of producing a high strength cold rolled steel sheet according to any of the preceding claims comprising the steps of:

- a) providing a cold rolled steel strip having a composition as set out in any of the preceding claims,
- b) annealing the cold rolled steel strip at an annealing temperature, T_{an} , that is between 760 °C and $A_{c3} + 20$ °C, followed by
- c) cooling the cold rolled steel strip from the annealing temperature, T_{an} , to a cooling stop temperature of rapid cooling, T_{RJ} , that is between 300 and 475 °C, preferably 350 and 475 °C at a cooling rate that is sufficient to avoid pearlite formation, followed by
- d) austempering the cold rolled steel strip at an overageing/austempering temperature, T_{OA} , that is between 320 and 480 °C, followed by
- e) cooling the cold rolled steel strip sheet to ambient temperature.

17. A method of producing a high strength cold rolled steel sheet according to claim 16 wherein the austempering in step d) is performed at an overageing/austempering temperature, T_{OA} , that is between 375 and 475°C for a time of ≤ 200 s.

18. A method of producing a high strength cold rolled steel sheet according to claim 16 wherein the austempering in step d) is performed at an overageing/austempering temperature, T_{OA} , that is between 350 and 450 °C for a time of ≥ 200 s.

Patentansprüche

1. Hochfestes kaltgewalztes Stahlblech, umfassend:

a) eine Zusammensetzung, die aus den folgenden Elementen besteht (in Gew.-%):

C	0, 1 - 0,3
Mn	1,4 - 2,7
Si	0,4 - 1, 0
Cr	0, 1 - 0,9
Si + Cr	$\geq 0, 9$
Al	$\leq 0,8$
Nb	$< 0, 1$
Mo	$< 0,3$
Ti	$< 0,2$
V	$< 0,2$
Cu	$< 0,5$
Ni	$< 0,5$
S	$\leq 0,01$
P	$\leq 0,02$
N	$\leq 0, 02$
B	$< 0,005$
Ca	$< 0,005$
Mg	$< 0,005$
REM	$< 0,005$

Rest Fe außer Verunreinigungen,

b) eine mehrphasige Feinstruktur, bestehend aus (in Vol.-%)

Restaustenit

5 - 22

EP 2 831 292 B1

(fortgesetzt)

Bainit + ferritisches Bainit + vergütetes Martensit ≤ 80
polygonales Ferrit ≥ 10

5

c) die folgenden mechanischen Eigenschaften

Zugfestigkeit (R_m) ≥ 780 MPa
Dehnung (A_{80}) $\geq 12\%$, bevorzugt $\geq 13\%$

10

und wahlweise die folgende Bedingung erfüllend

15

$R_m \times A_{80} \geq 13\,000$ MPa%

2. Hochfestes kaltgewalztes Stahlblech nach Anspruch 1, erfüllend mindestens eines der folgenden:

20

C 0,13 - 0,25
Mn 1,5 - 2,5, bevorzugt 1,5 - 2,3, bevorzugter 1,7 - 2,3
Si 0,4 - 0,9
Cr 0,2 - 0,6

25

3. Hochfestes kaltgewalztes Stahlblech nach einem der vorhergehenden Ansprüche, erfüllend mindestens eines der folgenden:

30

Al $\leq 0,1$, bevorzugt $\geq 0,06$
Nb 0,02 - 0,08
Mo 0,05 - 0,3
Ti 0,02 - 0,08
V 0,02 - 0,1
Cu 0,05 - 0,4
Ni 0,05 - 0,4
B 0,0002 - 0,003
Ca 0,0005 - 0,005
Mg 0,0005 - 0,005
REM 0,0005 - 0,005

35

40

4. Hochfestes kaltgewalztes Stahlblech nach einem der vorhergehenden Ansprüche, erfüllend mindestens eines der folgenden:

45

S $\leq 0,01$ bevorzugt $\leq 0,003$
P $\leq 0,02$ bevorzugt $\leq 0,01$
N $\leq 0,02$ bevorzugt $\leq 0,005$
Ti $> 3,4N$

50

5. Hochfestes kaltgewalztes Stahlblech nach einem der vorhergehenden Ansprüche, wobei die maximale Größe des Restaustentins (RA) $\leq 6\ \mu\text{m}$, bevorzugt $\leq 3\ \mu\text{m}$ ist.

55

6. Hochfestes kaltgewalztes Stahlblech nach einem der vorhergehenden Ansprüche, wobei die mehrphasige Feinstruktur umfasst (in Vol.-%)

EP 2 831 292 B1

	Restaustenit	6-16
5	Bainit + ferritisches Bainit + vergütetes Martensit	≤ 80
	polygonales Ferrit	≥ 10

7. Hochfestes kaltgewalztes Stahlblech nach einem der vorhergehenden Ansprüche, wobei der Stahl umfasst:

10	C	0,17 - 0,23
	Mn	1,5 - 1,8, bevorzugt 1,5 - 1,7
	Si	0,4 - 0,8, bevorzugt 0,4 - 0,7
	Cr	0,3 - 0,7, bevorzugt 0,4 - 0,7

15 wahlweise

Nb	0,01 - 0,03, bevorzugt 0,02 - 0,03
----	------------------------------------

20 und wobei das Stahlblech mindestens eine der folgenden Anforderungen erfüllt:

(R _m)	780 - 1200	MPa
(A ₈₀)	≥ 15	%

25 und

$$R_m \times A_{80} \geq 16\,000 \text{ MPa}\%$$

30 8. Hochfestes kaltgewalztes Stahlblech nach einem der Ansprüche 1-6, wobei der Stahl umfasst:

	C	0,13 - 0,17
	Mn	1,7 - 2,3
35	Si	0,5 - 0,9
	Cr	0,3 - 0,7

wahlweise

40	Nb	0,01 - 0,03, bevorzugt 0,02 - 0,03
----	----	------------------------------------

und wobei das Stahlblech mindestens eine der folgenden Anforderungen erfüllt:

45	(R _m)	780 - 1200	MPa
	(A ₈₀)	≥ 15	%

und

$$R_m \times A_{80} \geq 14\,000 \text{ MPa}\%, \text{ bevorzugt } 16\,000 \text{ MPa}\%$$

55 9. Hochfestes kaltgewalztes Stahlblech nach einem der Ansprüche 1-6, wobei der Stahl umfasst:

	C	0,18 - 0,22
	Mn	1,7 - 2,3

EP 2 831 292 B1

(fortgesetzt)

Si	0,5 - 0,9
Cr	0,3 - 0,8

5

wahlweise

Si + Cr	$\geq 1,0$
Nb	0,01 - 0,03

10

und wobei das Stahlblech mindestens eine der folgenden Anforderungen erfüllt

(R _m)	980 - 1200	MPa
(A ₈₀)	≥ 13	%

15

und

20

$R_m \times A_{80} \geq 13\,000 \text{ MPa\%}$

10. Hochfestes kaltgewalztes Stahlblech nach einem der Ansprüche 1-6, wobei der Stahl umfasst

25

C	0,14 - 0,20
Mn	1,9 - 2,5
Si	0,5 - 0,9
Cr	0,3 - 0,8

30

wahlweise

Si + Cr	$\geq 1,0$
Nb	0,01 - 0,03

35

und wobei das Stahlblech mindestens eine der folgenden Anforderungen erfüllt

(R _m)	980 - 1200	MPa
(A ₈₀)	≥ 13	%

40

und

45

$R_m \times A_{80} \geq 13\,000 \text{ MPa\%}$

11. Hochfestes kaltgewalztes Stahlblech nach einem der Ansprüche 1-6, wobei der Stahl umfasst:

50

C	0,18 - 0,22
Mn	1,7 - 2,5, bevorzugt 1,7 - 2,3
Si	0,5 - 0,9
Cr	0,4 - 0,8

55

wahlweise

Si + Cr	$\geq 1,1$
Nb	0,01 - 0,03, bevorzugt 0,02 - 0,03

EP 2 831 292 B1

und wobei das Stahlblech mindestens eine der folgenden Anforderungen erfüllt:

$$\begin{array}{lll} (R_m) & 1000 - 1400 & \text{MPa, bevorzugt } 1180 - 1400 \text{ MPa} \\ (A_{80}) & \geq 10 & \%, \text{ bevorzugt } \geq 14 \% \end{array}$$

und

$$R_m \times A_{80} \geq 12\,000 \quad \text{MPa}\%, \text{ bevorzugt } \geq 15\,000 \text{ MPa}\%$$

12. Hochfestes kaltgewalztes Stahlblech nach einem der vorhergehenden Ansprüche, wobei das Verhältnis $Mn + 3 \times Cr \leq 3,8$, bevorzugt $\leq 3,6$, ganz besonders bevorzugt $\leq 3,4$ ist.

13. Hochfestes kaltgewalztes Stahlblech nach einem der vorhergehenden Ansprüche, wobei die Menge von Si $> Al$, bevorzugt Si $> 1,3 Al$, besonders bevorzugt Si $> 5 Al$, ganz besonders bevorzugt Si $> 10 Al$.

14. Hochfestes kaltgewalztes Stahlblech nach einem der vorhergehenden Ansprüche, wobei das Verhältnis von Si/Cr = 1 - 5, bevorzugt 1,5 - 3, besonders bevorzugt 1,7 - 3, ganz besonders bevorzugt 1,7 - 2,8.

15. Hochfestes kaltgewalztes Stahlblech nach einem der vorhergehenden Ansprüche, das nicht mit einer feuerverzinkten Schicht versehen ist.

16. Verfahren zum Herstellen eines hochfesten kaltgewalzten Stahlblechs nach einem der vorhergehenden Ansprüche, das die folgenden Schritte umfasst:

a) Bereitstellen eines kaltgewalzten Stahlstreifens, der eine Zusammensetzung nach einem der vorhergehenden Ansprüche aufweist,

b) Glühen des kaltgewalzten Stahlstreifens bei einer Glühtemperatur T_{an} zwischen 760 °C und $A_{c3} + 20$ °C, gefolgt von

c) Kühlen des kaltgewalzten Stahlstreifens von der Glühtemperatur T_{an} auf eine Kühlstopptemperatur vom schnellen Kühlen T_{RJ} zwischen 300 °C und 475 °C, bevorzugt 350 und 475 °C mit einer Abkühlrate, die ausreicht, um Peralitbildung zu vermeiden, gefolgt von

d) Zwischenstufenvergüten des kaltgewalzten Stahlstreifens bei einer Überalterungs-/Zwischenstufenvergütungstemperatur T_{OA} zwischen 320 °C und 480 °C, gefolgt von

e) Abkühlen des kaltgewalzten Stahlstreifens auf Umgebungstemperatur.

17. Verfahren zum Herstellen eines hochfesten kaltgewalzten Stahlblechs nach Anspruch 16, wobei die Zwischenstufenvergütung in Schritt d) bei einer Überalterungs-/Zwischenstufenvergütungstemperatur T_{OA} zwischen 375 und 475 °C über einen Zeitraum von ≤ 200 sec durchgeführt wird.

18. Verfahren zum Herstellen eines hochfesten kaltgewalzten Stahlblechs nach Anspruch 16, wobei die Zwischenstufenvergütung in Schritt d) bei einer Überalterungs-/Zwischenstufenvergütungstemperatur T_{OA} zwischen 350 und 450 °C über einen Zeitraum von ≥ 200 sec durchgeführt wird.

Revendications

1. Une tôle d'acier laminée à froid à haute résistance comprenant :

a) une composition constituée des éléments suivants (en % en poids) :

C	0,1 - 0,3
Mn	1,4 - 2,7
Si	0,4 - 1,0
Cr	0,1 - 0,9
Si+ Cr	$\geq 0,9$

EP 2 831 292 B1

(suite)

5	Al	$\leq 0,8$
	Nb	$< 0,1$
	Mo	$< 0,3$
	Ti	$< 0,2$
	V	$< 0,2$
	Cu	$< 0,5$
10	Ni	$< 0,5$
	S	$\leq 0,01$
	P	$\leq 0,02$
	N	$\leq 0,02$
	B	$< 0,005$
15	Ca	$< 0,005$
	Mg	$< 0,005$
	REM	$< 0,005$

le reste étant du Fe, à l'exception des impuretés,
b) une microstructure multiphase composée de (% en volume)

	austénite retenue	5 - 22
	bainite + bainite ferritique + martensite trempée	≤ 80
25	ferrite polygonale	≥ 10

c) les propriétés mécaniques suivantes :

30	résistance à la traction (R_m)	≥ 780 MPa
	un allongement (A_{80})	≥ 12 %, de préférence ≥ 13 %,

et remplissant facultativement la condition suivante

35	$R_m \times A_{80}$	≥ 13000 MPa%
----	---------------------	-------------------

2. Une tôle d'acier laminée à froid à haute résistance selon la revendication 1, remplissant au moins une des conditions suivantes :

40	C	0,13 - 0,25
	Mn	1,5 - 2,5, de préférence 1,5 - 2,3, de façon encore préférée 1,7 à 2,3
	Si	0,4 - 0,9
45	Cr	0,2 - 0,6

3. Une tôle d'acier laminée à froid à haute résistance selon l'une des revendications précédentes remplissant au moins une des conditions suivantes :

50	Al	$\leq 0,1$, de préférence $\leq 0,06$
	Nb	0,02 - 0,08
	Mo	0,05 - 0,3
55	Ti	0,02 - 0,08
	V	0,02 - 0,1
	Cu	0,05 - 0,4

EP 2 831 292 B1

(suite)

Ni	0,05 - 0,4
B	0,0002 - 0,003
Ca	0,0005 - 0,005
Mg	0,0005 - 0,005
REM	0,0005 - 0,005

4. Une tôle d'acier laminée à froid à haute résistance selon l'une quelconque des revendications précédentes remplissant au moins l'une des conditions suivantes :

S	≤ 0,01	de préférence ≤ 0,003
P	≤ 0,02	de préférence ≤ 0,01
N	≤ 0,02	de préférence ≤ 0,005
Ti	> 3,4N	

5. Une tôle d'acier laminée à froid à haute résistance selon l'une quelconque des revendications précédentes, dans laquelle la taille maximale de l'austénite retenue (RA) est ≤ 6 μm, de préférence ≤ 3 μm.

6. Une tôle d'acier laminée à froid à haute résistance selon l'une quelconque des revendications précédentes, dans laquelle la microstructure multiphase comprend (en % en volume)

austénite retenue	6 - 16
bainite + bainite ferritique + martensite revenue	≤ 80
ferrite polygonale	≥ 10

7. Une tôle d'acier laminée à froid à haute résistance selon l'une quelconque des revendications précédentes, dans laquelle l'acier comprend :

C	0,17 - 0,23
Mn	1,5 - 1,8, de préférence 1,5 - 1,7
Si	0,4 - 0,8, de préférence 0,4 - 0,7
Cr	0,3 - 0,7, de préférence 0,4 - 0,7

facultativement

Nb	0,01 - 0,03, de préférence 0,02 - 0,03
----	--

et la tôle d'acier remplissant au moins une des exigences suivantes :

(R _m)	780 - 1200	MPa
(A ₈₀)	≥ 15	%

et

$$R_m \times A_{80} \geq 16000 \text{ MPa}\%$$

8. Une tôle d'acier laminée à froid à haute résistance selon l'une quelconque des revendications 1 à 6, dans laquelle l'acier comprend :

EP 2 831 292 B1

5	C	0,13 - 0,17
	Mn	1,7 - 2,3
	Si	0,5 - 0,9
	Cr	0,3 - 0,7

facultativement

10	Nb	0,01 - 0,03, de préférence 0,02 - 0,03
----	----	--

et la tôle d'acier remplissant au moins une des exigences suivantes :

15	(R _m)	780 - 1200	MPa
	(A ₈₀)	≥ 15	%

et

20	R _m x A ₈₀	≥ 14000	MPa%, de préférence ≥ 16000 MPa%
----	----------------------------------	---------	----------------------------------

9. Une tôle d'acier laminée à froid à haute résistance selon l'une quelconque des revendications 1 à 6, dans laquelle l'acier comprend :

25	C	0,18 - 0,22
	Mn	1,7 - 2,3
	Si	0,5 - 0,9
30	Cr	0,3 - 0,8

facultativement

35	Si+ Cr	≥ 1,0
	Nb	0,01 - 0,03

et la tôle d'acier remplissant au moins une des exigences suivantes

40	(R _m)	980 - 1200	MPa
	(A ₈₀)	≥ 13	%

et

45	R _m x A ₈₀ ~	≥ 13000	MPa%
----	------------------------------------	---------	------

10. Une tôle d'acier laminée à froid à haute résistance selon l'une quelconque des revendications 1 à 6, dans laquelle l'acier comprend

50	C	0,14 - 0,20
	Mn	1,9 - 2,5
	Si	0,5 - 0,9
55	Cr	0,3 - 0,8

facultativement

EP 2 831 292 B1

Si+ Cr $\geq 1,0$
Nb 0,01 - 0,03

et la tôle d'acier remplissant au moins une des exigences suivantes

(R_m) 980 - 1200 MPa
(A₈₀) ≥ 13 %

et

R_m x A₈₀ ≥ 13000 MPa%.

11. Une tôle d'acier laminée à froid à haute résistance selon l'une quelconque des revendications 1 à 6, dans laquelle l'acier comprend :

C 0,18 - 0,22
Mn 1,7 - 2,5 de préférence 1,7 - 2,3
Si 0,5 - 0,9
Cr 0,4 - 0,8

facultativement

Si+ Cr $\geq 1,1$
Nb 0,01 - 0,03, de préférence 0,02 - 0,03

et la tôle d'acier remplissant au moins une des exigences suivantes

(R_m) 1000 - 1400 Mpa de préférence 1180 - 1400 Mpa
(A₈₀) ≥ 10 % de préférence ≥ 14 %

et

R_m x A₈₀ ≥ 12000 MPa% de préférence ≥ 15000 MPa%

12. Une tôle d'acier laminée à froid à haute résistance selon l'une quelconque des revendications précédentes dans laquelle le rapport Mn + 3 x Cr $\leq 3,8$, de préférence $\leq 3,6$, de façon la plus préférée $\leq 3,4$.

13. Une tôle d'acier laminée à froid à haute résistance selon l'une quelconque des revendications précédentes, dans laquelle la quantité de Si > Al, de préférence Si > 1,3Al, de façon encore préférée Si > 5Al, de façon la plus préférée Si > 10Al.

14. Une tôle d'acier laminée à froid à haute résistance selon l'une quelconque des revendications précédentes, dans laquelle le rapport Si/Cr = 1 - 5, de préférence 1,5 - 3, de façon encore préférée 1,7 - 3, de façon la plus préférée 1,7 - 2,8.

15. Une tôle d'acier laminée à froid à haute résistance selon l'une des revendications précédentes, qui n'est pas munie d'une couche de galvanisation par immersion à chaud.

16. Un procédé de fabrication d'une tôle d'acier laminée à froid à haute résistance selon l'une quelconque des revendications précédentes comprenant les étapes consistant à :

a) prévoir un feuillard laminé à froid ayant une composition telle que définie dans l'une des revendications précédentes,

b) opérer un recuit du feuillard laminé à froid à une température de recuit, T_{an} , comprise entre 760°C et $A_{c3} + 20^\circ\text{C}$, suivi par

c) refroidir le feuillard laminé à froid depuis la température de recuit, T_{an} , à une température d'arrêt de refroidissement du refroidissement rapide, T_{RJ} , c'est-à-dire comprise entre 300 et 475°C, de préférence entre 350 et 475°C, à une vitesse de refroidissement qui est suffisante pour éviter la formation de perlite, suivi par

d) austempériser le feuillard laminé à froid à une température de sur-vieillissement/transformation bainitique, T_{0A} , qui est comprise entre 320 et 480°C, suivi par

e) refroidir le feuillard laminé à froid à température ambiante.

17. Un procédé de fabrication d'une tôle d'acier laminée à froid à haute résistance selon la revendication 16, dans lequel l'austempérisation à l'étape d) est effectuée à une température de sur-vieillissement/transformation bainitique, T_{0A} , qui est comprise entre 375 et 475°C pendant une durée ≤ 200 s.

18. Un procédé de fabrication d'une tôle d'acier laminée à froid à haute résistance selon la revendication 16, dans lequel l'austempérisation à l'étape d) est effectuée à une température de sur-vieillissement / transformation bainitique, T_{0A} , qui est comprise entre 350 et 450°C pendant une durée ≥ 200 s.

REFERENCES CITED IN THE DESCRIPTION

This list of references cited by the applicant is for the reader's convenience only. It does not form part of the European patent document. Even though great care has been taken in compiling the references, errors or omissions cannot be excluded and the EPO disclaims all liability in this regard.

Patent documents cited in the description

- JP 2004332099 A [0002]
- US 20090238713 A [0006]