

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
2 February 2006 (02.02.2006)

PCT

(10) International Publication Number
WO 2006/012000 A1

- (51) International Patent Classification⁷: **A61L 12/08**, C11D 3/00
- (21) International Application Number:
PCT/US2005/021077
- (22) International Filing Date: 15 June 2005 (15.06.2005)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
10/882,072 30 June 2004 (30.06.2004) US
- (71) Applicant (for all designated States except US): **JOHNSON & JOHNSON VISION CARE, INC.** [US/US]; 7500 Centurion Parkway, Suite 100, Jacksonville, Florida 32256 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): **ALVAREZ-CARRIGAN, Nayiby** [US/US]; 1628 Restone Court, St. Augustine, Florida 32092 (US). **BROWN-SKROBOT, Susan** [US/US]; 8707 Rolling Brook Lane, Jacksonville, Florida 32256 (US). **MEYERS, Ann-Marie Wong** [US/US]; 3134 Misty Creek Lane, Jacksonville, Florida 32216 (US). **NEELY, Frank** [US/US]; 804 Lapoma Way, Jacksonville, Florida 32259 (US). **PALL, Brian** [US/US]; 4908 Joseph Creek Drive, Jacksonville, Florida 32258 (US). **RATHORE, Osman** [PK/US]; 7743 Watermark Lane, Jacksonville, FL 32256 (US).
- (74) Agents: **JOHNSON, Philip S.** et al.; Johnson & Johnson, One Johnson & Johnson Plaza, New Brunswick, New Jersey 08933-7003 (US).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SM, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 2006/012000 A1

(54) Title: PACKAGING SOLUTION FOR OPHTHALMIC DEVICE

(57) Abstract: This invention relates to solutions for packaging ophthalmic devices comprising at least one antimicrobial metal salt having a K_{sp} of less than 10^{-10} which prevent the loss of said antimicrobial metal salt during autoclaving and storage.

PACKAGING SOLUTION FOR OPHTHALMIC DEVICE

5

FIELD OF THE INVENTION

This invention relates to packaging solutions that minimize the loss of inorganic additives present in a contact lens.

BACKGROUND OF THE INVENTION

Contact lenses have been used commercially to improve vision since the
10 1950s. The first contact lenses were made of hard materials. They were used
by a patient during waking hours and removed for cleaning. Current
developments in the field gave rise to soft contact lenses, which may be worn
continuously, for several days or more without removal for cleaning. Although
many patients favor these lenses due to their increased comfort, these lenses
15 can cause some adverse reactions to the user. The extended use of the lenses
can encourage the buildup of bacteria or other microbes, particularly,
Pseudomonas aeruginosa, on the surfaces of soft contact lenses. The build-up
of bacteria and other microbes can cause adverse side effects such as contact
lens acute red eye and the like. Contact lenses comprising antimicrobial metal
20 salts have been disclosed for preventing or retarding bacterial and microbial
buildup. However, for these lenses to be effective commercially, it is necessary
for the amount of antimicrobial metal salt in the lens to be consistent from lot to
lot.

25

DETAILED DESCRIPTION OF THE INVENTION

The present invention relates to a packaging solution for packaging an
ophthalmic device comprising at least one antimicrobial metal salt having a K_{sp} of
less than about 10^{-10} wherein said solution is substantially free from packaging

solution salts which have anions, which when combined with said antimicrobial metal, form a salt having a KSP of less than about 10^{-6} . When packaged in solutions of the present invention, the contact lenses comprising antimicrobial metal salts maintain a consistent level of antimicrobial metal salt.

5 As used herein, the term "ophthalmic device" refers to a device that resides in or on the eye. These devices can provide optical correction, wound care, drug delivery, diagnostic functionality, cosmetic enhancement or effect or a combination of these properties. The term lens includes but is not limited to soft contact lenses, hard contact lenses, intraocular lenses, overlay lenses, ocular
10 inserts, and optical inserts and the like.

As used herein, the term, "antimicrobial metal salt" means a salt that when incorporated into an ophthalmic device imparts to the ophthalmic device one or more of the following properties, the inhibition of the adhesion of bacteria or other microbes to the device, the inhibition of the growth of bacteria or other
15 microbes on the device, and the killing of bacteria or other microbes on the surface of the device or in an area surrounding the device. For purposes of this invention, adhesion of bacteria or other microbes to the device, the growth of bacteria or other microbes on the device and the presence of bacteria or other
20 microbes on the surface of the device are collectively referred to as "microbial colonization." Preferably, the lenses exhibit a reduction of viable bacteria or other microbe of at least about 0.25 log, more preferably at least about 0.5 log, most preferably at least about 1.0 log ($\geq 90\%$ inhibition). Such bacteria or other microbes include but are not limited to those organisms found in the eye, particularly *Pseudomonas aeruginosa*, *Acanthamoeba species*, *Staphylococcus aureus*, *E. coli*, *Staphylococcus epidermidis*, and *Serratia marcescens*.
25

As use herein, the term "metal salt" means any molecule having the general formula $[M]_a [X]_b$ wherein X contains any negatively charged ion, a is ≥ 1 , b is ≥ 1 and M is any positively charged metal selected from, but not limited to, the following Al^{+3} , Co^{+2} , Co^{+3} , Ca^{+2} , Mg^{+2} , Ni^{+2} , Ti^{+2} , Ti^{+3} , Ti^{+4} , V^{+2} , V^{+3} , V^{+5} , Sr^{+2} ,
30 Fe^{+2} , Fe^{+3} , Ag^{+2} , Ag^{+} , Au^{+2} , Au^{+3} , Au^{+1} , Pd^{+2} , Pd^{+4} , Pt^{+2} , Pt^{+4} , Cu^{+1} , Cu^{+2} , Mn^{+2} , Mn^{+3} , Mn^{+4} , Zn^{+2} , and the like. Examples of X include but are not limited to CO_3^{-2} , NO_3^{-1} , PO_4^{-3} , Cl^{-1} , I^{-1} , Br^{-1} , S^{-2} , O^{-2} , $C_{1-5}alkylCO_2^{-1}$ and the like. As used herein the term metal salts does not include zeolites, disclosed in WO03/011351,

which is hereby incorporated by reference in its entirety. The preferred a is 1, 2, or 3. The preferred b is 1, 2, or 3. The preferred metals ions are Mg^{+2} , Zn^{+2} , Cu^{+1} , Cu^{+2} , Au^{+2} , Au^{+3} , Au^{+1} , Pd^{+2} , Pd^{+4} , Pt^{+2} , Pt^{+4} , Ag^{+2} , and Ag^{+1} . The particularly preferred metal ion is Ag^{+1} . Examples of suitable metal salts include
5 but are not limited to manganese sulfide, zinc oxide, zinc sulfide, copper sulfide, and copper phosphate. Examples of silver salts include but are not limited to silver nitrate, silver sulfate, silver iodate, silver carbonate, silver phosphate, silver sulfide, silver chloride, silver bromide, silver iodide, and silver oxide. The preferred silver salts are silver iodide, silver chloride, and silver bromide. It is
10 preferred that the diameter of the metal salt particles is less than about ten microns (10 μm), more preferably less than about 5 μm , most preferably equal to or less than about 200 nm.

The K_{sp} ; or solubility product constant is the product of the equilibrium constant K, and the concentration of solid salt in solution. K_{sp} values for a
15 number of salts are published in CRC Handbook of Chemistry and Physics, 78th Edition, CRC Press, Boca Raton Florida, 1997-99, pages 8-106 through 8-109). For example, if the metal salt is silver carbonate (Ag_2CO_3), the K_{sp} is expressed by the following equation



20 The K_{sp} is calculated as follows

$$K_{sp} = [Ag^+]^2 [CO_3^{2-}]$$

It has been discovered that if a contact lens comprising at least one antimicrobial metal salt having a K_{sp} of less than about 10^{-10} is packaged in a solution which is substantially free from salts having anions which when
25 combined with said antimicrobial metal form a salt having a K_{sp} of more than about 10^{-6} , little of the antimicrobial metal salt is lost during autoclaving and storing the lens. Preferably the lenses lose less than about 30% by weight of the antimicrobial salt and preferably less than about 20% by weight during autoclaving and storing. More preferably, upon repeated autoclaving, at least
30 two autoclaving cycles, and up to five autoclaving cycles, the loss of the antimicrobial salt is less than about 15%.

Preferably the K_{sp} of the salt formed from said antimicrobial metal and packaging solution salt anion is more than about 10^{-6} and the K_{sp} of the

antimicrobial metal salt is less than about 10^{-12} . In another embodiment, the difference between the K_{sp} of the antimicrobial metal salt and the salt formed from said antimicrobial metal and the packaging solution salt anion (or ΔK_{sp}) is at least about six orders of magnitude, preferably at least about seven orders
5 of magnitude and more preferably at least about eight orders of magnitude. Combinations of antimicrobial metal and packing solutions salts wherein the ΔK_{sp} is less than about 6 orders of magnitude may be used so long as the quantity of the salt in the packing solution is low enough that loss upon repeated autoclaving is less than about 15%.

10 In one embodiment, the solution may be any water-based solution that is used for the packaging, storage and/or cleaning of contact lenses, so long as the K_{sp} of the salt formed from the antimicrobial metal and the packaging solution salt anion meets the requirements specified herein. Typical solutions include, without limitation, saline solutions, buffered solutions, buffered saline
15 solutions and deionized water. The preferred aqueous solution is borate buffered solution containing salts including, without limitation, sodium sulfate, sodium lactate, sodium citrate, sodium chloride, mixtures thereof and the like.

In one embodiment of the present invention the packaging solution also has an osmolality of about 220 mOsm/kg or greater and preferably of about
20 230 mOsm/kg or greater.

Osmolality is a measure of the number of particles present in solution and is independent of the size or weight of the particles. It can be measured only by use of a property of the solution that is dependent only on the particle concentration. These properties are collectively referred to as Colligative
25 Properties (vapor pressure depression, freezing point depression, boiling point elevation, osmotic pressure). Osmolality of a solution is the number of osmoles of solute per kilogram of solvent. This is the amount of a substance that yields, in ideal solution, that number of particles (Avogadro's number) that would depress the freezing point of the solvent by 1.86K. The osmolality
30 values reported in the Examples were measured via freezing point depression using a Micro-Osmometer Model 3 MOplus. Solutions having the osmolality specified herein may be readily prepared by incorporating appropriate amounts of ionic salts, such as those listed herein. A suitable concentration range for

the salt(s) are between about 0.01 to about 5 weight% and preferably between about 0.1 to about 3.0 weight % as part of a buffer system (such as borate or phosphate).

In another embodiment the packaging solution also has a conductivity of at least about 4 mS/cm or greater, and preferably at least about 5 mS/cm or greater. Conductivity is the ability of a material to conduct electric current. Conductivity may be measured using commercial conductivity probes. Solutions having the desired conductivities may be made by incorporating the salts listed herein. Salts which are more conductive, such as, for example sodium chloride, may be used in lesser quantities than salts with relatively low conductivities such as sodium borate.

In a further embodiment solutions of the present invention comprise an osmolality of at least about 220 mOsm/kg and a conductivity of at least about 4 mS/cm., preferably an osmolality of at least about 220 mOsm/kg and a conductivity of at least about 5 mS/cm., more preferably an osmolality of at least about 230 mOsm/kg and a conductivity of at least about 4 mS/cm., and most preferably an osmolality of at least about 230 mOsm/kg and a conductivity of at least about 5 mS/cm.

The solutions of the present invention may also comprise any known active and carrier components useful for lens packaging solution. Suitable active ingredients for lens packaging solutions include, without limitation, antibacterial agents, anti-dryness agents, such as polyvinyl alcohol, polyvinylpyrrolidone, dextran, polyethylene oxides, hydroxy propylmethyl cellulose (HPMC), tonicity agents, pharmaceuticals, nutraceuticals, additives which prevent the lens from sticking to the package and the like, and combinations thereof.

To form the solution, the ingredients are combined with the water-based solution, stirred, and dissolved. The pH of the solution preferably is adjusted to about 6.2 to about 7.7. The lens to be stored in the packaging solution of the invention is immersed in the solution and the solution and lens placed in the package in which the lens is to be stored. Alternatively, the solution may be placed into the package and the lens then placed into the solution. Typically,

the package is then sealed by any convenient method, such as by heat sealing, and undergoes a suitable sterilization procedure.

Soft contact lenses may be made from any hydrophilic hydrogel or silicone elastomer or hydrogel materials, which include but are not limited to silicone hydrogels, and fluorohydrogels. Examples of soft contact lenses formulations include but are not limited to the formulations of etafilcon A, genfilcon A, lenefilcon A, polymacon, aquafilcon A, balafilcon A, galyfilcon A, senofilcon A and lotrafilcon A, and the like. The preferable contact lens formulations are etafilcon A, balafilcon A, aquafilcon A, lotrafilcon A, galyfilcon A, senofilcon A and silicone hydrogels, as prepared in U.S. 5,998,498, US Ser. No. 09/532,943, a continuation-in-part of US Pat App. No. 09/532,943, filed on August 30, 2000, WO03/22321, U.S. 6,087,415, US 2002/0016383, JP 2001-188181, JP 2001-201723, JP 2001-183502, JP 2002-327063, U.S. 5,760,100, U.S. 5,776, 999, U.S. 5,789,461, U.S. 5,849,811, and U.S. 5,965,631. These patents as well as all other patent disclosed herein are hereby incorporated by reference in their entirety.

Hard contact lenses are made from polymers that include but are not limited to polymers of poly(methyl)methacrylate, silicon acrylates, silicone acrylates, fluoroacrylates, fluoroethers, polyacetylenes, and polyimides, where the preparation of representative examples may be found in US 4,330,383. Intraocular lenses of the invention can be formed using known materials. For example, the lenses may be made from a rigid material including, without limitation, polymethyl methacrylate, polystyrene, polycarbonate, or the like, and combinations thereof. Additionally, flexible materials may be used including, without limitation, hydrogels, silicone materials, acrylic materials, fluorocarbon materials and the like, or combinations thereof. Typical intraocular lenses are described in WO 0026698, WO 0022460, WO 9929750, WO 9927978, WO 0022459, U.S. 4,301,012; 4,872,876; 4,863,464; 4,725,277 and 4,731,079.

Additionally, suitable contact lenses may be formed from reaction mixtures comprising at least one silicone containing component. A silicone-containing component is one that contains at least one $[-Si-O-Si-]$ group, in a monomer, macromer or prepolymer. Preferably, the Si and attached O are present in the silicone-containing component in an amount greater than 20

weight percent, and more preferably greater than 30 weight percent of the total molecular weight of the silicone-containing component. Useful silicone-containing components preferably comprise polymerizable functional groups such as acrylate, methacrylate, acrylamide, methacrylamide, N-vinyl lactam, N-
5 vinylamide, and styryl functional groups. Examples of silicone components which may be included in the silicone hydrogel formulations include, but are not limited to silicone macromers, prepolymers and monomers. Examples of silicone macromers include, without limitation, polydimethylsiloxane methacrylated with pendant hydrophilic groups as described in United States
10 Patents Nos. 4,259,467; 4,260,725 and 4,261,875; polydimethylsiloxane macromers with polymerizable functional group(s) described in U.S. Patents Nos. 4,136,250; 4,153,641; 4,189,546; 4,182,822; 4,343,927; 4,254,248; 4,355,147; 4,276,402; 4,327,203; 4,341,889; 4,486,577; 4,605,712; 4,543,398; 4,661,575; 4,703,097; 4,837,289; 4,954,586; 4,954,587; 5,346,946; 5,358,995;
15 5,387,632 ; 5,451,617; 5,486,579; 5,962,548; 5,981,615; 5,981,675; and 6,039,913; polysiloxane macromers incorporating hydrophilic monomers such as those described in U.S. Patents Nos. 5,010,141; 5,057,578; 5,314,960; 5,371,147 and 5,336,797; macromers comprising polydimethylsiloxane blocks and polyether blocks such as those described in U.S. Patents Nos. 4,871,785
20 and 5,034,461, combinations thereof and the like.

The silicone and/or fluorine containing macromers described in U.S. Patents Nos. 5,760,100; 5,776,999; 5,789,461; 5,807,944; 5,965,631 and 5,958,440 may also be used. Suitable silicone monomers include tris(trimethylsiloxy)silylpropyl methacrylate, hydroxyl functional silicone
25 containing monomers, such as 3-methacryloxy-2-hydroxypropyloxy)propylbis(trimethylsiloxy)methylsilane and those disclosed in WO03/22321, and mPDMS containing or the siloxane monomers described in U.S. Patents Nos. 4,120,570, 4,139,692, 4,463,149, 4,450,264, 4,525,563; 5,998,498; 3,808,178; 4,139,513; 5,070,215; 5,710,302; 5,714,557 and
30 5,908,906.

Additional suitable siloxane containing monomers include, amide analogs of TRIS described in U.S. 4,711,943, vinylcarbamate or carbonate analogs described in U.S. 5,070,215, and monomers contained in U.S.

6,020,445, monomethacryloxypropyl terminated polydimethylsiloxanes, polydimethylsiloxanes, 3-methacryloxypropylbis(trimethylsiloxy)methylsilane, methacryloxypropylpentamethyl disiloxane and combinations thereof.


Suitable hydrophilic components are well known in the art and are disclosed in WO 2003/022321. Preferred hydrophilic monomers which may be incorporated into the polymer of the present invention include hydrophilic monomers such as N,N-dimethyl acrylamide (DMA), 2-hydroxyethyl acrylate, glycerol methacrylate, 2-hydroxyethyl methacrylamide, N-vinylpyrrolidone (NVP), HEMA, and polyethyleneglycol monomethacrylate. Most preferred hydrophilic monomers include DMA, NVP, HEMA and mixtures thereof.

Polymeric wetting agents and compatibilizing components may also be included. As used herein, "polymeric wetting agent" refers to substances having a weight average molecular weight of at least about 2,500 Daltons. The preferred weight average molecular weight of these polymeric wetting agents is greater than about 100,000; more preferably between about 150,000 to about 2,000,000 Daltons, more preferably still between about 300,000 to about 1,800,000 Daltons.


Alternatively, the molecular weight of polymeric wetting agents can be also expressed by the K-value, based on kinematic viscosity measurements, as described in Encyclopedia of Polymer Science and Engineering, N-Vinyl Amide Polymers, Second edition, Vol 17, pgs. 198-257, John Wiley & Sons Inc. When expressed in this manner, hydrophilic monomers having K-values of greater than about 12 and preferably between about 30 and about 150.

The way in which the polymeric wetting agent is added to the lens is not critical. The polymeric wetting agent may be added to the reaction mixture as a polymer, may be formed from at least one hydrophilic monomer which is added to the reaction mixture and forms a hydrophilic polymer upon curing of the reaction mixture or may be added after the lens is formed in the packaging solution. Examples of polymeric wetting agents include but are not limited to polymers and copolymers comprising polyamides, polylactones, polyimides, polyactams and functionalized polyamides, polylactones, polyimides, polyactams, such as DMA functionalized by copolymerizing DMA with a lesser molar amount of a hydroxyl-functional monomer such as HEMA, and then

reacting the hydroxyl groups of the resulting copolymer with materials containing radical polymerizable groups, such as isocyanatoethylmethacrylate or methacryloyl chloride. Hydrophilic prepolymers made from DMA or n-vinyl pyrrolidone with glycidyl methacrylate may also be used. The glycidyl methacrylate ring can be opened to give a diol which may be used in conjunction with other hydrophilic prepolymer in a mixed system to increase the compatibility of the high molecular weight hydrophilic polymer, hydroxyl-functionalized silicone containing monomer and any other groups which impart compatibility. Polymeric wetting agents include but are not limited to those disclosed in US 6,367,929, WO 2003/022321 and acyclic polyamides comprising repeating units of Formula



Wherein X is a direct bond,



wherein R³ is a C1 to C3 alkyl group;

R¹ is selected from H, straight or branched, substituted or unsubstituted C1 to C4 alkyl groups,

R² is selected from H, straight or branched, substituted or unsubstituted C1 to C4 alkyl groups, amino groups having up to two carbons, amide groups having up to four carbon atoms and alkoxy groups having up to two carbons and wherein the number of carbon atoms in R1 and R2 taken together is 8 or less, and preferably 6 or less. Homopolymers and copolymers comprising N-vinylpyrrolidone, N-vinyl-N-methylacetamide, (meth)acrylic acid, N, N-dimethylacrylamide, combinations thereof and the like are particularly preferred.

In certain embodiments a hydroxyl containing component may also be included. The hydroxyl containing component that may be used to make the polymers of this invention have at least one polymerizable double bond and at least one hydroxyl group. Examples of polymerizable double bonds include acrylic, methacrylic, acrylamido, methacrylamido, fumaric, maleic, styryl, isopropenylphenyl, O-vinylcarbonate, O-vinylcarbamate, allylic, O-vinylacetyl and N-vinylactam and N-vinylamido double bonds. The hydroxyl containing component may also act as a crosslinking agent. The hydroxyl group may be a primary, secondary or tertiary alcohol group, and may be located on an alkyl or aryl group. Examples of hydroxyl containing monomers that may be used include but are not limited to 2-hydroxyethyl methacrylate ("HEMA"), 2-hydroxyethyl acrylate, 2-hydroxyethyl methacrylamide, 2-hydroxyethyl acrylamide, N-2-hydroxyethyl vinyl carbamate, 2-hydroxyethyl vinyl carbonate, 2-hydroxypropyl methacrylate, hydroxyhexyl methacrylate, hydroxyoctyl methacrylate and other hydroxyl functional monomers as disclosed in U.S. Patents 5,006,622; 5,070,215; 5,256,751 and 5,311,223. Preferred hydroxyl containing components include 2-hydroxyethyl methacrylate.

In addition, the lens may also include cross-linkers, photoinitiators, UV absorbers, medicinal agents, antimicrobial compounds, reactive tints, pigments, copolymerizable and nonpolymerizable dyes, release agents, combinations thereof and the like. These additional components may be incorporated into the lens in any way, such as, but not limited to polymerized into the lens matrix, admixed into the monomer mix used to make the lens or absorbed into the lens.

The contact lenses may be coated to increase their compatibility with living tissue with a number of agents that are used to coat lens. For example, the coating procedures, compositions, and methods of WO03/11551, U.S. 6,087,415, 5,779,943, 5,275,838, 4,973,493, 5,135,297, 6,193,369, 6,213,604, 6,200,626, and 5,760,100 may be used and these applications and patents are hereby incorporated by reference for those procedures, compositions, and methods.

The amount of antimicrobial metal in the lenses is measured based upon the total weight of the lenses. When the antimicrobial metal is silver, the preferred amount of silver is about 0.00001 weight percent (0.1 ppm) to about 10.0 weight percent, preferably about 0.0001 weight percent (1 ppm) to about 1.0 weight percent, most preferably about 0.001 weight percent (10 ppm) to about 0.1 weight percent, based on the dry weight of the lens. With respect to adding metal salts, the molecular weight of the metal salts determines the conversion of weight percent of metal ion to metal salt. The preferred amount of silver salt is about 0.00003 weight percent (0.3 ppm) to about 30.0 weight percent, preferably about 0.0003 weight percent (3 ppm) to about 3.0 weight percent, most preferably about 0.003 weight percent (30 ppm) to about 0.3 weight percent, based on the dry weight of the lens.

The preferred antimicrobial metal salts of this invention are silver iodide, silver chloride and silver bromide, where silver iodide is particularly preferred.

The term "forming" refers to any of a number of methods used to form lenses that include but are not limited to curing with light or heat. The lens formulations of the present invention can be formed by any of the methods known to those skilled in the art, such as shaking or stirring, and used to form polymeric articles or devices by known methods.

Metal salts of the invention may be added (prior to curing) to the soft contact lens formulations described in US 5,710,302, WO 9421698, EP 406161, JP 2000016905, U.S. 5,998,498, US Pat. App. No. 09/532,943, U.S. 6,087,415, U.S. 5,760,100, U.S. 5,776,999, U.S. 5,789,461, U.S. 5,849,811, and U.S. 5,965,631. In addition, metal salts of the invention may be added to the formulations of commercial soft contact lenses.

In order to illustrate the invention the following examples are included. These examples do not limit the invention. They are meant only to suggest a method of practicing the invention. Those knowledgeable in contact lenses as well as other specialties may find other methods of practicing the invention. However, those methods are deemed to be within the scope of this invention.

The osmolality of a solution may be measured using a Micro-Osmometer Model 3 MOplus and the following procedure. The instrument was internally calibrated with NIST traceable 50 mOsm and 850 mOsm standards. The

solutions to be tested were kept sealed in a vial until evaluation. The sampling system (a pipette fitted with a plunger) was rinsed by pipetting sample solution into the barrel of the sampling system and discarding. Solution was pipetted into the sample system, the sample system was placed in the osmometer and the osmolality was measured. The measurement was repeated three times and the average is reported.

The conductivity may be measured using a FISHER® ACCUMET® 150 and the following procedure. The instrument is calibrated using NIST traceable conductivity standards. The solutions to be tested were kept sealed in a vial until evaluation. About 30 ml of solution was placed in a hinged cap sample vial. The conductivity probe is dipped into the solution at least three times prior to sample evaluation to wet the probe and remove any bubbles. The conductivity probe and automatic temperature compensation probe are immersed in the sample solution and the conductivity is recorded when the reading on the instrument stabilizes.

Silver content of the lenses after lens autoclaving was determined by Instrumental Neutron Activation Analysis "INAA". INAA is a qualitative and quantitative elemental analysis method based on the artificial induction of specific radionuclides by irradiation with neutrons in a nuclear reactor. Irradiation of the sample is followed by the quantitative measurement of the characteristic gamma rays emitted by the decaying radionuclides. The gamma rays detected at a particular energy are indicative of a particular radionuclide's presence, allowing for a high degree of specificity. Becker, D. A.; Greenberg, R.R.; Stone, S. F. J. Radioanal. Nucl. Chem. 1992, 160(1), 41-53; Becker, D. A.; Anderson, D. L.; Lindstrom, R. M.; Greenberg, R. R.; Garrity, K. M.; Mackey, E. A. J. Radioanal. Nucl. Chem. 1994, 179(1), 149-54. The INAA procedure used to quantify silver content in contact lens material uses the following two nuclear reactions:

1. In the activation reaction, ^{110}Ag is produced from stable ^{109}Ag (isotopic abundance = 48.16 %) after capture of a radioactive neutron produced in a nuclear reactor.
2. In the decay reaction, ^{110}Ag ($\tau^{1/2} = 24.6$ seconds) decays primarily by negatron emission proportional to initial concentration with an energy

characteristic to this radio- nuclide (657.8 keV).

The gamma-ray emission specific to the decay of ^{110}Ag from irradiated standards and samples are measured by gamma-ray spectroscopy, a well-established pulse-height analysis technique, yielding a measure of the
5 concentration of the analyte.

EXAMPLES

The following abbreviations were used in the examples

- Blue HEMA = the reaction product of reactive blue number 4 and HEMA, as
10 described in Example 4 or U.S. Pat. no. 5,944,853
- CGI 1850 = 1:1 (w/w) blend of 1-hydroxycyclohexyl phenyl ketone and bis (2,6-dimethoxybenzoyl)-2,4,4-trimethylpentyl phosphine oxide
- DI water = deionized water
- D3O = 3,7-dimethyl-3-octanol
- 15 DMA = N,N-dimethylacrylamide
- HEMA = hydroxyethyl methacrylate
- IPA = Isopropyl alcohol
- Macromer = a macromer made according to Example 14, herein
- MC = methyl ether cellulose
- 20 mPDMS = *mono*-methacryloxypropyl terminated polydimethylsiloxane (MW 800-1000)
- Norbloc = 2-(2'-hydroxy-5-methacryloxyethylphenyl)-2H-benzotriazole
- ppm = parts per million micrograms of sample per gram of dry lens
- PVP= polyvinylpyrrolidinone (K 90)
- 25 Simma 2 = 3-methacryloxy-2-hydroxypropyloxy)propylbis (trimethylsiloxy)methylsilane
- BBPS = borate buffered packaging solution
- SSPS = borate buffered sodium sulfate packaging solution
- TEGDMA = tetraethyleneglycol dimethacrylate
- 30 w/w = weight/total weight
- w/v = weight/total volume

v/v =volume/total volume

The following solutions were prepared for use

5 **Borate buffered packaging solution (BBPS)**

A solution was made by adding 0.185 weight % of sodium borate, 0.926 weight % boric acid and 98.89 weight % water into a volumetric flask and was mixed at ambient temperature until all solids were dissolved. Properties for the BBPS are listed in Table 1, below.

10

Borate buffered saline solution (BBSS)

A solution was made by adding 0.185 g of sodium borate, 0.926 g boric acid, 0.847 g sodium chloride and 100 mL water into a flask and was mixed at ambient temperature until all solids were dissolved. Properties for the BBSS

15 are listed in Table 1, below

Borate buffered Sodium Sulfate packaging solution (SSPS)

A solution was made by adding 0.185 weight % of sodium borate, 0.926 weight % boric acid, 1.4 weight % of sodium sulfate and 97.49 weight % water into a volumetric flask and was mixed at ambient temperature until all solids were dissolved. Properties for the SSPS are listed in Table 1, below.

20

Borate buffered packaging solution with 400uL of Packing Soln. (spiked)

A solution was made by adding 0.15 weight % of sodium borate, 0.92 weight % boric acid, 0.35% sodium chloride, 0.004% EDTA and 98.58 weight % water into a volumetric flask and was mixed at ambient temperature until all solids were dissolved. Properties for the special packing solution are listed in Table 1. below.

25

Table 1. Solution Properties

30

Properties	BBPS	BBSS	SSPS	Spiked
PH	7.59(0)	7.52	7.52(0)	7.50(0)
Osmolality (mOsm/kg)(std)	163(0)	417	382(0.5)	273(0)

Conductivity(m S/cm)	0.7(0)	14.6	15.3(0.2)	6.8(0)
Ksp (Ag/solution anion)	(Ag ₂ B ₄ O ₇)	1.77x10 ⁻¹⁰ (AgCl)	1.2x10 ⁻⁵ (AgSO ₄)	1.77x10 ⁻¹⁰ (AgCl)

Example 1

A monomer mix is made by mixing 77 weight % of the monomers listed in
 5 Table 2 with and 23% D3O.

Table 2

Component	Wt%
SiMAA2	28
MPDMS	31
DMA	24
HEMA	6
PVP	7
Norbloc	2
Blue HEMA	0.02
CGI 1850	0.48
TEGDMA	1.5

Contact lenses were made by placing the monomer mix into thermoplastic
 contact lens molds, and irradiating using Philips TL20W/03T fluorescent bulbs
 10 (intensity of about 1 mW/cm² for 8 minutes and about 4 mW/cm² for 4 minutes)
 at 45°C. The molds were opened and lenses were extracted into IPA solvent
 to insure removal of residual diluent and monomers. The lenses were then
 rinsed in a 50 ppm methyl cellulose in DI mixture to insure removal of solvent.
 The lenses were then equilibrated in deionized water.

15

Examples 2-13

Lenses made as in Example 1 were placed in a 300ppm sodium iodide
 solution overnight at room temperature. The lenses were immersed in a 150
 ppm silver nitrate solution for 2-minutes at room temperature and then rinsed
 20 2-times with DI water in 30-minute intervals to remove any excess silver. Three
 lenses were equilibrated in each of the solutions listed in Table 3, below. Each
 set of three contact lenses was packaged into three polypropylene blister
 packs containing the solutions shown in Table 3. The blister packs were heat
 sealed (225°C, 90 psi and 1.5 seconds). The blister packs containing the
 25 lenses were autoclaved at 121°C for 30 minutes, and allowed to cool to room

temperature. The number of autoclave cycles each set of blister packs was exposed to is listed in Table 3. Each lens was analyzed for residual silver content after the noted number of autoclave cycles. The results are shown in Table 3, below.

5

Table 3

Ex. #	Solution	# cycles	[Ag] (μg)*
2	BBPS	1	4.37(0.11)
3	BBPS	3	4.52(0.06)
4	BBPS	5	4.57(0.22)
5	BBPS	8	4.57(0.07)
6	SSPS	1	3.3(0.2)
7	SSPS	3	3.4(0.3)
8	SSPS	5	3.4(0.1)
9	SSPS	8	3.4(0.2)
10	Spiked	1	3.3(0.1)
11	Spiked	3	2.4(0.1)
12	Spiked	5	1.9(0.9)
13	Spiked	8	1.7(0.1)

* standard deviations shown in parenthesis

Example 14

- 10 The following ingredients were combined using the steps below to generate Macromer.

Table 4

Chemical	Weight (g) or volume (ml)
Bis(dimethylamino)-methylsilane	5.72 g
1.0 M Solution of tetrabutylammonium 3-chlorobenzoate (TBACB) in THF	2.6 ml
p-xylene	15.83 g
MMA	29.44 g
Bloc-HEMA	361.16 g
THF	840 g

Methyltrimethylsilyl dimethylketene acetal	38.53 g
0.4 M solution of tetrabutylammonium 3-chlorobenzoate (TBACB) in THF	6 ml
Step 2	
Bloc-HEMA	89.23 g
MPDMS	693.00 g
TRIS	701.46 g
Bis(dimethylamino)-methylsilane	3.81 g
Step 3	
Solution of Bloc-HEMA	361.16 g
MMA	29.44 g
Bis(dimethylamino)-methylsilane	1.92 g
THF	270 g
Step 4	
Water	93.9 g
Methanol	141.2 g
Dichloroacetic acid	1.68 g
Step 5	
3-Isopropenyl- α,α -dimethylbenzyl isocyanate	169.07 g
TEA	1.18 g

Bloc-HEMA, MMA, mPDMS (about 800 to about 1000MW), TRIS, p-xylene and tetrahydrofuran (THF) were dried over preactivated 4A molecular sieve, and THF, mPDMS, and TRIS were passed through aluminum oxide column before
 5 use.

To a dry container in a dry box under nitrogen was added bis(dimethylamino)-methylsilane, a 1M solution of tetrabutylammonium 3-chlorobenzoate (TBACB) in THF, p-xylene, MMA (1.4 eqv. relative to initiator), Bloc-HEMA (8.5 eqv. relative to photoinitiator) and THF. The above mixture was charged to a dry
 10 flask equipped with a thermocouple and a condenser connected to a nitrogen source.

To the reaction mixture was injected methyltrimethylsilyl dimethylketene acetal while stirring and purging with nitrogen. The reaction was allowed to exotherm to about 65°C and then after the temperature of the solution dropped, a
 15 solution of TBACB in dry THF (0.4 M) was fed in slowly throughout the rest of the reaction. Then in step 2, a mixture of Bloc-HEMA (2.1 eqv. to initiator), mPDMS (3.3 eqv. to initiator), TRIS (7.9 eqv. to initiator) and

bis(dimethylamino)-methylsilane, prepared in dry box, was added under nitrogen.

The reaction mixture was again allowed to exotherm to approximately 42°C and then allowed to cool to 32°C. The solution was stirred at 32°C by using a temperature controller and heating equipment for about five hours. In step 3, a mixture of Bloc-HEMA (8.5 eqv. to initiator), MMA (1.4 eqv. relative to initiator) and bis(dimethylamino)-methylsilane was added and the whole mixture allowed to exotherm to 46 – 49°C. After the mixture reacted about two hours, 270 g of THF was added to reduce the viscosity and the solution was stirred for additional 30 minutes.

In step 4, a mixture of water, methanol and dichloroacetic acid was added and the mixture was refluxed for five hours to de-block the protecting groups. The solvents were then removed by distillation and toluene was added to aid in removal of residual water until a vapor temperature reached 110°C.

A solution of TMI and 1.2 mole % TEA relative to TMI was added to the above solution in toluene. The whole mixture was stirred at 110°C for three hours and the disappearance of the isocyanate peak was monitored by IR. The toluene was removed under reduced pressure at around 45°C to give a raw macromer.

Purification procedures were employed to remove high molecular weight species. The raw macromer was re-dissolved in acetone (2:1 w / w acetone to macromer) and the acetone solution was set overnight to allow high molecular weight species to separate. The top clear phase was filtered through a PTFE membrane by pressure filtration. The filtrate was slowly charged into water (4:1 v / v water to filtrate) and the macromer was precipitated out. The macromer was collected and dried using a vacuum oven at 45 - 65°C under reduced pressure until there was no weight change.

Further purification to remove low molecular weight species was also done by re-precipitation of the Macromer from the mixture of acetone and acetonitrile (1:5 v / v).

Example 15

Sodium Iodide (3.2 mg Aldrich) was added to 15.0 g of a hydrogel blend made from the following (all amounts were calculated as weight percent of the total weight of the combination): 17.98% Macromer 5, 28.0% mPDMS, 14.0%
5 TRIS, 26.0% DMA, 5.0% HEMA, 1.0% TEGDMA, 5.0% PVP, 2.0% Norbloc, 1.0% CGI 1850 and 0.02% Blue HEMA, 80 weight percent of the preceding component mixture was further diluted with diluent, 20 weight percent of D3O ("D3O Monomer Blend"). The mixture was sonicated for 1.5 hours at
10 30°C, and then stored in a heated oven @ 55°C overnight. The monomer mix was degassed under vacuum for 30 minutes, and used to make lenses, utilizing Topas frames at 50-55°C under Philips TL03 lamps with 30 minutes of irradiation.

Eight frames were manually demolded, and the lenses (obtained sticking
15 to the back curve or front curve) were enclosed individually in hydration vehicles (Fisher brand, HistoPrep disposable plastic tissue capsules) and immersed in 2L of DI water containing 447 mg AgNO₃. An orbital shaker was used to keep the solution agitated. After 2 hours, the lenses were removed from the hydration vehicles, and released from the molds in a jar containing 150 mL of silver nitrate
20 solution (0.15 mg/mL in DI water) and 225 mL isopropyl alcohol. After 2 hours, the solution was replaced with 200 mL isopropanol, and the lenses were then stepped down using DI water/IPA mixtures by (4 x 40 mL) exchanges of the hydration solution with DI water, allowing the lenses to equilibrate 20-30 minutes between exchanges. The lenses were then transferred into DI water for a total of
25 4 x 75 mL washes of 20-30 minutes each. Lenses from the last DI water wash were stored in a 10 mL of fresh DI water. The lenses were autoclaved (each in 3.0 mL of Special Packing Solution). The final silver content in the lenses was determined by INAA to be 286 ± 15 ppm (theoretical = 189 ppm).

Example 16

Tetrabutylammonium Chloride (8.9 mg, Fluka) was added to 15.1 g of D3O Monomer Blend. The mixture was sonicated for 1 hour, rolled on a jar roller for a further 30 minutes, and then stored in a heated oven @ 55°C

overnight. The monomer mix was degassed under vacuum for 30 minutes, and used to make lenses, utilizing Topas frames at 50°C under Philips TL03 lamps with 30 minutes of irradiation.

Ten frames of lenses were manually demolded, and the rings due to excess monomer were discarded. The lenses, obtained sticking to either the back curve or front curve, were loaded onto hydration trays, which were then immersed in 2.75 L of silver nitrate solution ('silverizing bath', 0.155 mg/mL in DI water). The silver nitrate solution was kept agitated by utilizing an orbital shaker. After 2 hours, the lenses were removed from the hydration trays, and placed in a jar containing 120 mL solution from the 'silverizing bath' and 180 mL isopropanol to release the lenses from the molds.

The released lenses were then further hydrated analogously to the procedure described in Example 15. The final silver content in the lenses was determined to be 331 ± 7 ppm (theoretical = 286 ppm). The average haze value for these lenses was $21.8 \pm 1.8\%$ relative to CSI commercial standards.

Examples 17-20

Lenses made in Examples 14 and 15 were packaged in 3.0 mL glass vials half of the lenses of each lens type were packaged in BBPS and the other half were packaged in BBSS and sealed. The lenses were autoclaved one to three times at 121°C for 30 minutes. The lenses were evaluated for silver content and the data is presented in Table 5, below.

Table 5

	17	18	19	20
Antimicrobial salt	AgCl	AgCl	AgI	AgI
Ksp Antimicrobial salt	1.77×10^{-10}	1.77×10^{-10}	8.52×10^{-17}	8.52×10^{-17}
Solution	BBPS	BBSS	BBPS	BBSS
[Ag] _{initial}	342 (6)	342 (6)	286 (15)	286 (15)
[Ag] _{1 cycle}	180 (8)	42 (5)	233 (3)	131 (4)
[Ag] _{2 cycle}	164 (9)	36 (3)	236 (6)	94 (6)
[Ag] _{3 cycle}	179 (11)	33 (6)	239 (7)	62 (4)

25

Values in parentheses are standard deviations

What is claimed is

1. A packaging solution for packaging an ophthalmic device comprising at least one antimicrobial metal salt having a K_{sp} of less than about 10^{-10}
5 wherein said solution is substantially free from packaging solution salts which have anions which when combined with said antimicrobial metal form a salt having a K_{sp} of more than about 10^{-6} .
2. The packaging solution of claim 1 wherein the K_{sp} of the salt formed
10 from said antimicrobial metal and packaging solution salt anion is more than about 10^{-6} .
3. The packaging solution of claim 1 wherein said packaging solution has an osmolality of about 220 mOsm/kg or greater.
15
4. The packaging solution of claim 1 wherein said packaging solution salts has an osmolality of about 230 mOsm/kg or greater.
5. The packaging solution of claim 1 wherein said packaging solution
20 has a conductivity of at least about 4 mS/cm or greater.
6. The packaging solution of claim 1 wherein said packaging solution has a conductivity of at least about 5 mS/cm or greater
- 25 7. The packaging solution of claim 1 wherein said ophthalmic device is a contact lens.
8. The packaging solution of claim 1 wherein said antimicrobial metal salt comprises at least one cation selected from the group consisting of Al^{+3} , Co^{+2} ,
30 Co^{+3} , Ca^{+2} , Mg^{+2} , Ni^{+2} , Ti^{+2} , Ti^{+3} , Ti^{+4} , V^{+2} , V^{+3} , V^{+5} , Sr^{+2} , Fe^{+2} , Fe^{+3} , Ag^{+2} , Ag^{+} , Au^{+2} , Au^{+3} , Au^{+1} , Pd^{+2} , Pd^{+4} , Pt^{+2} , Pt^{+4} , Cu^{+1} , Cu^{+2} , Mn^{+2} , Mn^{+3} , Mn^{+4} , Zn^{+2} and combinations thereof.

9. The packaging solution of claim 1 wherein said antimicrobial metal salt

comprises at least one cation selected from the group consisting of Mg^{+2} , Zn^{+2} , Cu^{+1} , Cu^{+2} , Au^{+2} , Au^{+3} , Au^{+1} , Pd^{+2} , Pd^{+4} , Pt^{+2} , Pt^{+4} , Ag^{+2} , Ag^{+1} and combinations thereof.

5

10. The packaging solution of claim 1 wherein said antimicrobial metal is a silver salt.

11. The packaging solution of claim 1 wherein said antimicrobial metal salt is selected from the group consisting of manganese sulfide, zinc oxide, zinc sulfide, copper sulfide, copper phosphate, silver nitrate, silver sulfate, silver iodate, silver carbonate, silver phosphate, silver sulfide, silver chloride, silver bromide, silver iodide, silver oxide and mixtures thereof.

12. The packaging solution of claim 1 wherein said antimicrobial metal salt is selected from the group consisting of silver iodide, silver chloride, silver bromide and mixtures thereof.

13. The packaging solution of claim 1 wherein said ophthalmic device loses less than about 30% by weight of the antimicrobial salt during autoclaving and storing.

14. The packaging solution of claim 1 wherein said ophthalmic device loses less than about 20% by weight of the antimicrobial salt during autoclaving and storing.

15. The packaging solution of claim 1 wherein said ophthalmic device loses less than about 15% by weight of the antimicrobial salt after at least two autoclaving cycles.

30

16. The packaging solution of claim 1 wherein said solution is a borate buffered solution comprising at least one salt selected from the group

consisting of sodium sulfate, sodium lactate, sodium citrate, sodium chloride and mixtures thereof.

5 17. A packaging solution for packaging an ophthalmic device comprising at least one antimicrobial metal salt having a K_{sp} wherein said solution is substantially free from packaging solution salts which have anions which when combined with said antimicrobial metal form a salt having a K_{sp} which is at least about six orders of magnitude different that said K_{sp} of said antimicrobial metal salt.

10

18. A packaging solution for packaging an ophthalmic device comprising at least one antimicrobial metal salt having a K_{sp} wherein said solution is substantially free from packaging solution salts which have anions which when combined with said antimicrobial metal form a salt having a K_{sp} which is more than about six orders of magnitude different that said K_{sp} of said antimicrobial metal salt and said antimicrobial metal salt is present in a concentration sufficient to provide loss upon autoclaving of less than about 15%.

20 19. A method for reducing loss of an antimicrobial metal from an ophthalmic lens packaged in a packaging solution comprising the step of packaging said ophthalmic lens in a packaging solution which is substantially free from packaging solution salts which have anions which when combined with said antimicrobial metal form a salt having a K_{sp} of less than about 10^{-6} .

25

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US2005/021077

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 A61L12/08 C11D3/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 A61L C11D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 2004/047879 A (JOHNSON & JOHNSON VISION CARE, INC) 10 June 2004 (2004-06-10) page 8, line 1 - page 14, line 8; examples -----	1-19
X	US 2004/115242 A1 (MEYERS ANN-MARIE W ET AL) 17 June 2004 (2004-06-17) paragraphs '0289!, '0290! -----	1-19
X	US 2003/095230 A1 (NEELY FRANK L ET AL) 22 May 2003 (2003-05-22) claims 1,19,25 -----	1-19

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

° Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

25 August 2005

Date of mailing of the international search report

15/09/2005

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Jochheim, J

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US2005/021077

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 2004047879 A	10-06-2004	US 2004150788 A1	05-08-2004
		AU 2003294450 A1	18-06-2004
		AU 2003295818 A1	18-06-2004
		WO 2004047878 A1	10-06-2004
		WO 2004047879 A2	10-06-2004
		US 2005117112 A1	02-06-2005
US 2004115242 A1	17-06-2004	US 2003044447 A1	06-03-2003
		US 2004213827 A1	28-10-2004
		TW 592732 B	21-06-2004
		US 2004151755 A1	05-08-2004
US 2003095230 A1	22-05-2003	US 2003043341 A1	06-03-2003
		BR 0117090 A	03-08-2004
		CA 2456129 A1	13-02-2003
		CN 1558779 A	29-12-2004
		EP 1414502 A2	06-05-2004
		JP 2004536669 T	09-12-2004
		WO 03011351 A2	13-02-2003