



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : C08F 4/655, 10/02, C08L 23/04, C08J 5/18</p>	<p>A1</p>	<p>(11) International Publication Number: WO 99/51646</p> <p>(43) International Publication Date: 14 October 1999 (14.10.99)</p>
<p>(21) International Application Number: PCT/FI99/00286</p> <p>(22) International Filing Date: 6 April 1999 (06.04.99)</p> <p>(30) Priority Data: 980788 6 April 1998 (06.04.98) FI</p> <p>(71) Applicant (for all designated States except US): BOREALIS POLYMERS OY [FI/FI]; P.O. Box 330, FIN-06101 Porvoo (FI).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only): LINDROOS, Jarmo [FI/FI]; Kissansalmentie 16a, FIN-06750 Tolkkinen (FI). JOHANSSON, Solveig [SE/SE]; Haglingevägen 1, S-444 47 Stenungsund (SE). WALDVOGEL, Päivi [FI/FI]; Päiväläispolku 12 c, FIN-06450 Porvoo (FI).</p> <p>(74) Agent: BERGGREN OY AB; P.O. Box 16, FIN-00101 Helsinki (FI).</p>		<p>(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i> <i>With amended claims.</i></p>
<p>(54) Title: OLEFIN POLYMERIZATION CATALYST COMPONENT, ITS PREPARATION AND USE</p>		
<p>(57) Abstract</p> <p>A catalyst having high activity independent of the hydrogen concentration and low gel productivity in the polymerization of ethylene has been prepared. The preparation comprises the steps of reacting: a support comprising a magnesium halide compound having the formula (1): $RO_{2-n}MgX_n$ wherein R is a C₁-C₂₀ alkyl, a C₇-C₂₆ aralkyl, a C₁-C₂₀ alkoxy or a C₇-C₂₆ aralkoxy, each same or different X is a halogen, and n is an integer 1 or 2, an alkyl metal halide compound having the formula (2): $R^1_n M^1 X^1_{(3m^1-n^1)}$ wherein M is B or Al, each same or different R¹ is a C₁-C₁₀ alkyl, each same or different X¹ is a halogen, m¹ is 1 or 2, n¹ is 1 or 2 when m¹ is 1 and n¹ is an integer from 1 to 5 when m¹ is 2; a magnesium composition containing magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide, said magnesium composition having the empirical formula (3): $R^2_n (R^3O)_{2-n} Mg$ wherein each same or different R² is a C₁-C₂₀ alkyl, each same or different R³ is a C₁-C₂₀ alkyl, n² is between 0.01 and 1.99, and a titanium halide compound having the formula (4): $(R^4O)_n TiX^2_{4-n^3}$ wherein each same or different R⁴ is a C₁-C₂₀ alkyl, each same or different X² is a halogen, n³ is 0 or an integer 1-3, and Ti is quadrivalent titanium.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Olefin polymerization catalyst component, its preparation and use

The invention relates to a process for the preparation of a high activity catalyst component for the production of olefin polymers. The invention also relates to a
5 procatalyst prepared by said process and the use of such a procatalyst in the polymerization of olefins.

Background of the invention

Olefinic unsaturated monomers such as ethylene can often be polymerized in the presence of a catalyst composition, which has essentially two components: a
10 compound of a transition metal belonging to one of groups 4 to 6 of the Periodic Table of Elements (Hubbard, IUPAC 1990) which is often called a procatalyst, and a compound of a metal belonging to any of groups 1 to 3 of said Table which is often called a cocatalyst. This kind of Ziegler-Natta catalyst composition has been
15 further developed by depositing the procatalyst on a more or less inert and particulate support and by adding to the catalyst composition in the stages of its preparation several additives, among others electron donating compounds. These compounds have improved the polymerization activity of the catalyst, the operating life and other properties of the catalyst composition and first of all properties of the polymers which are obtained by means of the catalyst composition.

20 When ethylene polymers are produced, the polymer molecules formed are not similar by molecular weight, but a mixture having a narrow or broad molecular weight distribution is developed. The broadness of the molecular weight distribution may be described by utilization of the ratio of two different averages, namely the weight average molecular M_w and the number average molecular weight M_n , where
25 a high value of M_w/M_n indicates a broad molecular distribution. For controlling the molecular weight a so called chain transfer agent can be added to the polymerization reaction mixture. In order to obtain polymer products having different molecular weights, different amounts of the chain transfer agent for controlling the molecular weight must be fed into the polymerization reaction mixture. The most usual and
30 preferable chain transfer agent is hydrogen, because when using it no foreign atoms or atom groups are left in the growing molecule, that would cause inconveniencies for the polymerization process or disadvantageous properties of the polymer produced.

How well the molecular weight of the produced polymer varies as function of the hydrogen amount, i.e. how much the so called hydrogen sensibility changes, greatly depends on the catalyst composition. Generally the problem is, that in polyethylene production the polymerization activity decreases to quite an extent the more hydrogen is present.

This absence of catalyst activity balance is a common drawback for all prior art catalysts today. The imbalance shows up when, using prior art catalysts, a drastic drop in the productivity of the catalysts occurs when going from polymerization conditions giving high molecular weight polymers (low melt flow rate) to polymerization conditions giving low molecular weight polymers (high melt flow rate). Even if such a commercial catalyst can have a quite good productivity at a polymer melt flow rate (MFR, defined according to standard ISO 1133) of 1, there is often only 10% left of the productivity when producing a MFR of 500. Thus it is desirable to provide a catalyst system having a high activity which is independent of the molar mass of the polymer under formation.

The activity balance discussed above is important in production of bimodal polyethylene. There, a low molecular weight component is produced in one stage at a high hydrogen concentration and a high molecular weight component is produced in another stage at a low hydrogen concentration. Since no fresh catalyst is added between these polymerization stages, the catalyst employed in production of bimodal polyethylene must be able to produce the different molecular weights with a high productivity.

EP-A-32307 discloses a procatalyst that has been prepared by treating an inorganic support like silica with a chlorination agent like ethyl aluminium dichloride which support is then contacted with a magnesium alkyl compound like butyl ethyl magnesium, and with titanium tetrachloride (see claim 1, example 1, table 1).

WO-A-96/05236 discloses a catalyst component comprising (i) a particulate support where the majority of particles is in the form of an agglomerate of subparticles and (ii) a magnesium halide. The publication discusses the preparation of the support material. It also describes catalyst preparation and polymerization examples. The catalyst is prepared by adding titanium tetrachloride and DEAC on the agglomerated carrier containing magnesium chloride. The polymerization examples show that a higher bulk density and a higher MFR (better hydrogen response) as well as a lower FRR (narrower molecular weight distribution) is obtained by the catalyst prepared

according to the disclosure. The publication does not refer to the homogeneity of the material.

EP-A-688 794 discloses a process for the preparation of a high activity procatalyst, wherein an inorganic support is reacted with an alkyl metal chloride, the first
 5 reaction product is reacted with a compound containing hydrocarbyl and hydrocarbyl oxide linked to magnesium, and the obtained second reaction product is contacted with a titanium chloride compound. The obtained procatalyst has good activity both at high and low MFR polymerization conditions, but it has the drawback of giving an inhomogeneous ethylene polymer product, resulting in gels and
 10 white spots in the polymer material. These inhomogeneities have detrimental effect on the appearance and mechanical properties of polyethylene film.

Description of the invention

The drawbacks encountered by EP-A-688 794 and other prior art catalysts have now been eliminated by a modified process, characterized by the steps of reacting a
 15 support, at least the surface of which comprises a magnesium halide compound having the formula (1):



wherein R is a C₁-C₂₀ alkyl or a C₇-C₂₆ aralkyl, each same or different X is a halogen, and n is an integer 1 or 2,

20 an alkyl metal halide compound having the formula (2):



wherein M is B or Al, each same or different R¹ is a C₁-C₁₀ alkyl, each same or different X¹ is a halogen, n¹ is 1 or 2 when m¹ is 1 and n¹ is an integer from 1 to 5 when m¹ is 2,

25 a magnesium composition containing magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide, said magnesium composition having the empirical formula (3):



wherein each same or different R^2 is a C_1 - C_{20} alkyl, each same or different R^3 is a C_1 - C_{20} alkyl or a C_1 - C_{20} alkyl containing a hetero element, and n^2 is between 0.01 and 1.99, and

a titanium halide compound having the formula (4):



wherein each same or different R^4 is a C_1 - C_{20} alkyl, each same or different X^2 is a halogen, n^3 is 0 or an integer 1-3, and Ti is quadrivalent titanium.

By the formula (1) is meant that the inorganic support may be coated by $MgCl_2$ or $RoMgCl$. Thus n is 1 or 2.

10 By "magnesium composition" above is meant a mixture or a compound. Note that formula (3) is an empirical formula and expresses the molar amounts of alkyl R^2 and alkoxy OR^3 relative to the amount of magnesium Mg, which has been defined as 1, and differs from formulas (1), (2) and (4), which disclose the molecular composition of distinct compounds only.

15 A procatalyst has now been discovered by which ethylene homopolymers or copolymers having low or high molecular weights can be produced with an even and high activity as well as a homogeneous consistence. Independently of the amount of hydrogen introduced into the polymerization reactor, the activity of the catalyst remains more or less unchanges and a homogeneous ethylene polymer
20 product is obtained.

The unique feature of the catalyst according to the invention now lies over its good balance in activity and a homogeneous product in a very wide range of molar mass regulating hydrogen partial pressures used in the polymerization. It is thus possible to carry out an ethylene polymerization by the use of this catalyst at high and low
25 melt flow and still have very similar high productivity as well as a homogeneous, gel free product. This MFR/activity balance renders the catalyst universally applicable for most types of PE resins in all polymerization processes using heterogeneous catalyst systems.

Preferably, the claimed process comprises the subsequent steps of:

30 a) providing said support comprising a magnesium halide compound having the formula (1),

- b) contacting said support comprising a magnesium halide compound having the formula (1) with said alkyl metal halide compound having the formula (2), to give a first product,
- 5 c) contacting said first product with said magnesium composition containing magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide and having the empirical formula (3), to give a second product, and
- d) contacting said second product with said titanium halide compound having the formula (4).

10 The support used in the process is preferably in the form of particles, the size of which is from about 1 μm to about 1000 μm , preferably about 10 μm to about 100 μm . The support material must have a suitable particle size distribution, a high porosity and a large specific surface area. A good result is achieved if the support material has a specific surface area between 100 and 500 m^2/g support and a pore volume of 1-3 ml/g support.

15 The above catalyst components (2) to (4) are reacted with a suitable catalyst support. If the catalyst components (2) to (4) are in the form of a solution of low viscosity, a good catalyst morphology and therewith a good polymer morphology can be achieved.

20 It is advantageous if in the magnesium halide compound having the formula (1), R is a $\text{C}_1\text{-C}_{20}$ alkoxy or a $\text{C}_7\text{-C}_{26}$ aralkoxy. However, it is preferable, if said compound (1) is a magnesium dihalide, most preferably MgCl_2 . For example, the support may comprise solid MgCl_2 , either alone as a powder, or as a powder mixture with other inorganic powders.

25 According to another embodiment of the invention, the support comprising a magnesium halide compound having the formula (1) also comprises an inorganic oxide. Several oxides are suitable, but silicon, aluminium, titanium, chromium and zirconium oxide or mixtures thereof are preferred. The most preferred inorganic oxides are silica, alumina, silica-alumina, magnesia and mixtures thereof, uttermost preferably silica. The inorganic oxide can also be chemically pretreated, e.g. by
30 silylation or by treatment with aluminium alkyls.

It is recommendable to dry the inorganic oxide before impregnating it by other catalyst components. A good result is achieved if the oxide is heat-treated at 100 $^\circ\text{C}$

to 900 °C for a sufficient time, and thereby the surface hydroxyl groups, in the case of silica, are reduced to below 2 mmol/g SiO₂.

According to this aspect of the invention, the support comprises particles having a core comprising said inorganic oxide and a shell comprising said magnesium halide compound having the formula (1). Then, the support comprising a magnesium halide compound having the formula (1) and an inorganic oxide can conveniently be prepared by treating particles of the inorganic oxide with a solution of the magnesium halide and removing the solvent by evaporation.

When using a support containing both said magnesium halide compound (1) and another component, the amount of magnesium halide compound (1) is such that the support contains from 1 to 20 % by weight, preferably from 2 to 6 % by weight, of magnesium.

The invention further comprises a step of reacting an alkyl metal halide compound of the formula (2):



wherein M is B or Al, each same or different R¹ is a C₁-C₁₀ alkyl, each same or different X¹ is a halogen, m¹ is 1 or 2, n¹ is 1 or 2 when m¹ is 1 and n¹ is an integer from 1 to 5 when m¹ is 2. In formula (2), Me is preferably Al. Each same or different R¹ is preferably a C₁-C₆ alkyl, and, independently, the preferred same or different halogen X¹ is chlorine. n¹ is preferably 1 and m¹ is preferably the integer 1 or 2. Most preferably, the alkyl metal halide compound having the formula (2) is an alkyl aluminium dichloride, e.g. ethyl aluminium dichloride (EADC).

The alkyl metal halide compound is preferably deposited on the support material. An even deposition is preferably achieved if the viscosity of the halide or its solution is below 10 mPa*s at the temperature applied. To achieve this low viscosity the alkyl metal halide can be diluted by a non-polar hydrocarbon. The best deposition is however achieved if the total volume of the absorbed alkyl metal halide solution is not exceeding the pore volume of the support. A good choice is to use a 5-25% hydrocarbon solution of ethyl aluminium dichloride. The number of additions of the halide is preferably adjusted so that the technique are of not exceeding the pore volume at any additions is not violated, thereby giving an even distribution of the chemical in the surface of the support material.

In the above mentioned preferred order of reaction steps a) to d), step b) can advantageously be performed so that undiluted alkyl metal halide (2) is used to treat the support comprising a magnesium halide compound having the formula (1). Alternatively, the support is contacted with a solution of the alkyl metal halide compound having the formula (2) in an essentially non-polar solvent, preferably a non-polar hydrocarbon solvent, most preferably a C₄-C₁₀ hydrocarbon. The concentration of the alkyl metal halide compound having the formula (2) in said non-polar solvent is usually 1-80% by weight, preferably 5-40% by weight, most preferably 10-30% by weight. Advantageously, the support is contacted with a solution of said alkyl metal halide compound (2) in a ratio mol of the alkyl metal halide compound (2) to grams of the support of between about 0.01 mmol/g and about 100 mmol/g, preferably between about 0.5 mmol/g and about 2.0 mmol/g. The amount of reactants can also be expressed as molar ratio, whereby it is advantageous, if the molar ratio of said alkyl metal halide compound (2) to said magnesium halide compound (1) of the support is between about 0.01 mol/mol to about 100, preferably about 0.1 mol/mol to about 10, most preferably from about 0.2 to about 3.0.

In step b), the temperature at said contacting is e.g. 5-80 °C, preferably 10-50 °C, most preferably 20-40°C. The duration of said contacting is 0.1-3 h, preferably 0.5-1.5 h.

In the claimed process, the magnesium composition containing magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide and having the empirical formula (3), each same or different R² is preferably a C₂-C₁₀ alkyl, most preferably a C₂-C₈ alkyl. Each same or different R³ is preferably a C₃-C₂₀ alkyl, more preferably a branched C₄-C₁₀ alkyl, most preferably a 2-ethyl-1-hexyl or a 2-propyl-1-pentyl.

The magnesium composition containing magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide having the empirical formula (3) can also be defined by its preparation. According to one embodiment of the invention, it is a contact product of a dialkyl magnesium having the formula (5):



wherein each same or different R² is defined as above, and an alcohol. Preferably, the dialkyl magnesium having the formula (5) is dibutyl magnesium, butyl ethyl magnesium or butyl octyl magnesium.

hydrocarbon used. When depositing the magnesium composition on the support material its hydrocarbon solution should have a viscosity that is lower than 10 mPa*s at the temperature applied. The viscosity of the magnesium complex solution can be adjusted for example by the choice of the group R⁴ in the formula (3), by the choice of the concentration of the hydrocarbon solution, by the choice of the ratio between the magnesium alkyl and the alcohol or by using some viscosity lowering agent. The titanium compound can be added to the support material with or without a previous drying of the catalyst to remove the volatile hydrocarbons. Remaining hydrocarbons can if desired be removed by using slight underpressure, elevated temperature or nitrogen flash.

In the claimed process, the transition metal compound is a titanium halide compound having the formula (4). R⁴ is preferably a C₂-C₈ alkyl, most preferably a C₂-C₆ alkyl. X² is preferably chlorine and, independently, n³ is preferably 0. Said titanium halide compound having the formula (4) is advantageously titanium tetrachloride.

According to one embodiment of the invention, in addition to said titanium compound having the formula (4), a titanium compound having the formula (7):



wherein each same or different R⁵ is a C₁-C₂₀ alkyl, preferably a C₂-C₈ alkyl, most preferably a C₂-C₆ alkyl, each same or different X³ is a halogen, preferably chlorine, n⁴ is an integer 1-4, and Ti is quadrivalent titanium, is reacted. The titanium compound (7) always has at least one alkoxy group, which helps dissolving the titanium compound (4) which does not necessarily contain alkoxide, into an organic solvent before the contacting. Naturally, the more alkoxide groups compound (4) has, the less is the need for compound (7). If compound (7) is used, the preferable combination is that of titanium tetrachloride and a titanium tetra C₁-C₆-alkoxide.

In step d) of the preferred step sequence a) → d), said second product is advantageously contacted with the titanium compound having the formula (4) in a ratio moles of said titanium compound/g of the support of 0.01-10 mmol/g, preferably 0.1-2 mmol/g. Preferably, said second reaction product is contacted with said titanium compound (4) in a ratio moles of said titanium compound (4)/moles of the magnesium compound (3) of 0.05-2 mol/mol, preferably 0.1-1.2 mol/mol, most preferably 0.2-0.7 mol/mol. The temperature is usually 10-80 °C, preferably 30-

60 °C, most preferably from about 40 °C to about 50 °C, and the contacting time is usually 0.5-10 h, preferably 2-8 h, most preferably from about 3.5 h to about 6.5 h.

Above, the process for the preparation of a high activity catalyst component for the production of olefin polymers of different molecular weight and homogeneous
 5 consistence, has been described in detail. The invention also relates to such a high activity catalyst component. The suitability for both low and high molecular weight polymerization means, that the claimed catalyst component has high activity both when producing low melt flow rate ethylene polymer and high melt flow rate
 10 polymer. High molecular weight polymer has high melt viscosity, i.e. low melt flow rate, and low molecular weight polymer has low melt viscosity, i.e. high melt flow rate.

Simultaneously or separately, it preferably produces ethylene homopolymer and copolymer with low gel content. Most preferably it produces ethylene homopolymer having a Gel number, measured under specified test conditions, of approximately
 15 0/0 1/m². This means, that by the standards used, the claimed catalyst components can be used to produce totally homogenous (gelless) low and high molecular weight ethylene polymer.

The invention also relates to the use of a catalyst component according to the invention in the polymerization of olefins, preferably in the homo- or
 20 copolymerization of ethylene. The advantage of the use is based on the fact that the claimed catalyst is suitable for both low molecular weight and high molecular weight ethylene polymerization and that the ethylene polymer produced is of high quality.

In the polymerization, said alkyl metal halide compound of the formula (2) can, if
 25 used, also act completely or partially as a cocatalyst. However, it is preferable to add a cocatalyst having the formula (9):



wherein R⁶ is a C₁-C₂₀ alkyl, preferably a C₁-C₁₀ alkyl, most preferably a C₂-C₆ alkyl such as ethyl, X is a halogen, preferably chlorine, n is 1 to 3, more preferably
 30 2 or 3, most preferably 3, to the polymerization mixture. The cocatalyst having the formula (9) is optional depending on whether said alkyl metal halide compound (2) is acting as cocatalyst or not.

Experimental Part

Some Factors Influencing the Gel Level

Those familiar with the art know that the gel level is influenced by two properties of the polymer, the average molecular weight (for which the melt flow rate, or MFR, is an often used measure) and the broadness of the molecular weight distribution (for which the shear thinning index, or SHI, and the flow rate ratio, or FRR, are often used measures). A high molecular weight (or, a low MFR) usually results in a higher gel level than a low molecular weight (or, a high MFR). Also, a broad molecular weight distribution (or, a high SHI or FRR) usually results in a higher gel level than a narrow molecular weight distribution (or, a low SHI).

Film Blowing

Pelletized material samples were blown to a film on a pilot film line. The film blowing conditions were:

- Die diameter 30 mm
- 15 Die gap 0.75 mm
- Blow-up ratio 3.0

Determination of the Gel Level

A sample of the size 210 mm x 297 mm was cut from a film blown on the Collin line. The film sample was put into a gel scanner, which classifies the gels according to their size. The scanner gives the number of gels in three size classes, < 0.3 mm, 0.3...0.7 mm and > 0.7 mm. Generally the number of gels in the smallest class can be affected by different random factors, so often only the numbers of the intermediate (0.3...0.7 mm) and large (> 0.7 mm) gels are given.

25 Determination of the Dispersion of the Black Pellets

The dispersion indicates the homogeneity of the black samples in a similar fashion as the gel level indicates the homogeneity of the film samples. It is measured from the black pellets according to the ISO/DIS 11420 method as follows:

30 Six pellets are cut using a microtome to 20 μm cuts. Using an optical microscope, the white spots seen in the sample are then measured and classified according to their size. The average number of white spots in each size class is calculated. An

ISO value indicating the dispersion is attributed to the material. A high ISO rating denotes a poor homogeneity (large inhomogeneities).

Examples

Preparation of Complex 1

- 5 7.9 g (60.8 mmol) of 2-ethyl-1-hexanol was added slowly to 27.8 (33.2 mmol) of 19.9% butyl-octyl-magnesium. The reaction temperature was kept under 35 °C. This complex was used in the following catalyst preparations. 2-ethyl-1-hexanol/butyl-octyl-magnesium ratio is 1.83:2.

Preparation of Complex 2

- 10 8.6 g (66.4 mmol) of 2-ethyl-1-hexanol was added slowly to 27.8 (33.2 mmol) of 19.9% butyl-octyl-magnesium. The reaction temperature was kept under 35 °C. This complex was used in the following catalyst preparations. 2-ethyl-1-hexanol/butyl-octyl-magnesium ratio is 2:1.

Comparative Example 1:

15 Production of the Film Material

The polymer samples were produced in a continuously operating pilot plant as follows:

The catalyst used in this example was one known in the art, prepared according to patent application EP-A-688794 on a 40 µm silica carrier.

- 20 The catalyst was fed into a 50 dm³ loop prepolymerization reactor, where a small amount of polymer was formed on the catalyst particles. The slurry containing the prepolymer was taken out of the reactor and passed into a 500 dm³ loop reactor. There the reactor conditions were set so that ethylene homopolymer with MFR₂ = 500 was formed at a rate of about 25 kg/h. The polymer slurry was taken out of the
25 loop reactor into a flash unit, where the hydrocarbons were separated from the polymer.

- The polymer was then passed into a gas phase reactor where the polymerization was continued at a rate of about 35 kg/h. The reactor conditions were set so that MFR₂₁ of the polymer collected from the reactor was about 9 and the density about
30 946 kg/m³.

The powder was then collected and blended with additives after which it was pelletized. A film was then blown from a pellet sample and the gel level was determined as described above. Table 1 shows some data of the material.

Comparative Example 2 (Catalyst APS 12 μm)

- 5 6.0 g (1.6 mmol/g carrier) of 20% EADC was added to 5.9 g of Sylopol 2212 silica carrier. The mixture was stirred for one hour at 30 °C. 8.9 g (1.4 mmol/g carrier) of complex prepared according to Complex Preparation 1 was added after which the mixture was stirred for 4 hours at 35-45 °C. 0.76 g (0.7 mmol/g carrier) of TiCl_4 was added and the mixture was stirred for 5 hours at 45 °C. The catalyst was dried
10 at 45-80 °C for 3 hours.

Composition of the catalyst was: Al 2.4%, Mg 2.0%, Ti 2.0%, Cl 12.5%.

The polymer was prepared as in Comparative example 1.

Comparative Example 3

Production of the Pipe Material:

- 15 The material was produced according to Comparative Example 1, except that a catalyst was prepared on a 20 μm silica carrier. Also, the material targets were changed to some extent. In the first stage, material having $\text{MFR}_2 = 300$ was produced at a rate of 32 kg/h. The gas phase reactor was operated so that the production was 39 kg/h, MFR_{21} of the final material was 9 and density was 948.
20 The polymer was then blended with additives including an additive containing carbon black to give the material a black colour. The material was then pelletized. The dispersion was then determined from the black pellets according to the procedure described earlier. Table 1 shows some data of the material.

Example 1 (Catalyst APS 11 μm)

- 25 3.7 g (1.0 mmol/g carrier) of 20% EADC was added to 5.9 g of Sylopol 5510 silica/ MgCl_2 carrier and the mixture was stirred for one hour at 30 °C. 5.7 g (0.9 mmol/g carrier) of complex prepared according to Complex Preparation 1 was added and the mixture was stirred for 4 hours at 35-45 °C. 0.6 g (0.55 mmol/g carrier) of TiCl_4 was added and the mixture was stirred for 5 hours at 45 °C. The
30 catalyst was dried at 45-80 °C for 3 hours.

Composition of the catalyst was: Al 1.8%, Mg 3.9%, Ti 2.1%, Cl 18.5%.

The polymerization was performed as in Comparative example 1.

Example 2

Production of the Film Material

5 The catalyst was prepared according to Example 1, with the exception that a carrier having 29 μm average particle size was used. The bimodal polyethylene material was produced according to Comparative Example 1. Table 1 shows process and evaluation data.

Example 3

Production of the Pipe Material

10 The catalyst was prepared according to Example 1, with the exception that a carrier having 20 μm average particle size was used. The bimodal polyethylene material was produced according to Comparative Example 3. Table 1 shows process and evaluation data.

Polymerization Results

15 The catalysts have been tested in bimodal Loop-Gas-phase process under fixed split and loop melt index.

Table 1. Polymerization and Analysis Results Obtained with Different Catalysts

	CE1	CE2	CE3	Ex 1	Ex 2	Ex 3
Productivity in loop	1.8	5.0		5.0	3.8	
Loop MFR ₂	520	514	300	650	430	323
Final MFR ₂₁	9.7	6.6	9.5	6.3	6.1	9.2
Final density	945.5	946.5	949 ¹	945.5	946.2	949 ¹
SHI _{5/300}	87.5	61.0	40.4 ²	90.2	111	56.6 ²
Gels (0.3...0.7/>0.7)	50/0	300/0		0/0	0/0	
Dispersion <30/30...60/60...80/ >80 μm			14/2/0.3/0. 8			17/2/0/0. 2
ISO rating			5.5			3.0

¹ Base resin density, not including carbon black

² SHI_{2.7/210}

Flow rate ratio (FRR) has been calculated as the ratio of two MFR values measured using different loads, $FRR_{21/5} = MFR_{21}/MFR_5$.

The number of gels was calculated from film blown to film with pilot line. Comparative results to pilot film line were also obtained from the film analysis with
5 large scale film lines.

The representative polymer lots were characterized by rheology, where $SHI_{5/300}$ comparison is made to polymer with same molecular weight.

Measurements were made on Rheometrics RDA II at 190 °C. Complex viscosity (η^*) together with storage modulus (G') and loss modulus (G'') as a function of
10 frequency (ω) or complex modulus (G^*) were obtained.

Complex viscosity (η^*) as a function of complex modulus (G^*) corresponds to viscosity as a function of shear stress and its shape is independent of MW. SHI calculated from this function can be used as a measure of MWD.

$$SHI_{5/300} = \eta_{5\text{kPa}} / \eta_{300\text{kPa}}$$

15 where $\eta_{5\text{kPa}}$ and $\eta_{300\text{kPa}}$ are η^* at a constant G^* of 5 kPa and 300 kPa, respectively.

Claims

1. A process for the preparation of a high activity catalyst component for the production of olefin polymers, **characterized** in that it comprises the steps of reacting:

- 5 a support comprising a magnesium halide compound having the formula (1):



wherein R is a C₁-C₂₀ alkyl, a C₇-C₂₆ aralkyl, a C₁-C₂₀ alkoxy or a C₇-C₂₆ aralkoxy, each same or different X is a halogen, and n is an integer 1 or 2,

an alkyl metal halide compound having the formula (2):



wherein M is B or Al, each same or different R¹ is a C₁-C₁₀ alkyl, each same or different X¹ is a halogen, m¹ is 1 or 2, n¹ is 1 or 2 when m¹ is 1 and n¹ is an integer from 1 to 5 when m¹ is 2,

- 15 a magnesium composition containing magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide, said magnesium composition having the empirical formula (3):



wherein each same or different R² is a C₁-C₂₀ alkyl, each same or different R³ is a C₁-C₂₀ alkyl, n² is between 0.01 and 1.99, and

- 20 a titanium halide compound having the formula (4):



wherein each same or different R⁴ is a C₁-C₂₀ alkyl, each same or different X² is a halogen, n³ is 0 or an integer 1-3, and Ti is quadrivalent titanium.

- 25 2. A process according to claim 1, **characterized** in that it comprises the subsequent steps of:

a) providing said support comprising a magnesium halide compound having the formula (1),

- b) contacting said support comprising a magnesium halide compound having the formula (1) with said alkyl metal halide compound having the formula (2), to give a first product,
- c) contacting said first product with said magnesium composition containing magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide and having the empirical formula (3), to give a second product, and
- d) contacting said second product with said titanium halide compound having the formula (4).
3. A process according to claim 1 or 2, **characterized** in that said support is in the form of particles, the size of which is from about 1 μm to about 1000 μm , preferably from about 10 μm to about 100 μm .
4. A process according to claim 1, 2 or 3, **characterized** in that said magnesium halide compound having the formula (1) is a magnesium dihalide, preferably MgCl_2 .
5. A process according to any of claim 1-4, **characterized** in that said support comprising a magnesium halide compound having the formula (1) also comprises an inorganic oxide.
6. A process according to any of claims 1-5, **characterized** in that said inorganic oxide is an inorganic oxide having surface hydroxyls, such as silica, alumina, silica-alumina, magnesia and mixtures thereof, preferably silica.
7. A process according to any preceding claim, **characterized** in that said support comprises particles having a core comprising said inorganic oxide and a shell comprising said magnesium halide compound.
8. A process according to claim 5, 6 or 7, **characterized** in that in said support, the amount of said magnesium halide compound having the formula (1), expressed as per cent magnesium Mg calculated on the weight of the support, is 1-20%, preferably 2-6%.
9. A process according to any preceding claim, **characterized** in that in said alkyl metal halide having the formula (2), independently, Me is Al, each same or different R^1 is a C_1 - C_6 alkyl, each X^1 is a chlorine, n^1 is 1, and m^1 is an integer 1 or 2.

10. A process according to claim 9, **characterized** in that said alkyl metal halide compound having the formula (2) is an alkyl aluminium dichloride, e.g. ethyl-aluminium dichloride.
11. A process according to any of claims 2 to 10, **characterized** in that in step b),
5 said support comprising a magnesium halide compound having the formula (1) is contacted with a solution of said alkyl metal halide compound having the formula (2) in an essentially non-polar solvent, preferably a non-polar hydrocarbon solvent, most preferably a C₄-C₁₀ hydrocarbon.
12. A process according to claim 11, **characterized** in that the concentration of
10 said alkyl metal halide compound having the formula (2) in said non-polar solvent is 1-80% by weight, preferably 5-40% by weight, most preferably 10-30% by weight.
13. A process according to claim 11 or 12, **characterized** in that the total volume of the alkyl metal halide compound (2) solution is not exceeding the pore volume of the support.
14. A process according to any of claims 2 to 12, **characterized** in that in step b),
15 said support comprising a magnesium halide compound having the formula (1) is contacted with a solution of said alkyl metal halide compound having the formula (2) in a ratio moles of said alkyl metal halide to grams of said support of between about 0.01 mmol/g and about 100 mmol/g, preferably about 0.5 mmol/g and about
20 2.0 mmol/g.
15. A process according to any of claims 2 to 14, **characterized** in that in step b), said support comprising a magnesium halide compound having the formula (1) is contacted with a solution of said alkyl metal halide compound having the formula
25 (2) in a molar ratio of said alkyl metal halide compound (2) to said magnesium halide compound (1) of between about 0.01 and about 100 mol/mol, preferably about 0.1 mol/mol and about 10 mol/mol, most preferably about 0.2 and about 3.0 mol/mol.
16. A process according to any preceding claim, **characterized** in that in said magnesium composition containing magnesium bonded to a hydrocarbyl and
30 magnesium bonded to a hydrocarbyl oxide having the empirical formula (3), each same or different R² is a C₂-C₁₀ alkyl.
17. A process according to any preceding claim, **characterized** in that in said magnesium composition containing magnesium bonded to a hydrocarbyl and

magnesium bonded to a hydrocarbyl oxide having the empirical formula (3), each same or different R^3 is a C_3 - C_{20} alkyl, preferably a branched C_4 - C_{10} alkyl, most preferably a 2-ethyl-1-hexyl or a 2-propyl-1-pentyl.

18. A process according to any preceding claim, **characterized** in that said
5 magnesium composition containing magnesium bonded to a hydrocarbyl and
magnesium bonded to a hydrocarbyl oxide having the empirical formula (3) is a
contact product of a dialkyl magnesium having the formula (5):



wherein each same or different R^2 is defined as above, and an alcohol.

- 10 19. A process according to claim 18, **characterized** in that said dialkyl magnesium
having the formula (5) is dibutyl magnesium, butyl ethyl magnesium or butyl octyl
magnesium.

- 15 20. A process according to any preceding claim, **characterized** in that said
magnesium composition containing magnesium bonded to a hydrocarbyl and
magnesium bonded to a hydrocarbyl oxide having the empirical formula (3) is a
contact product of a dialkyl magnesium and an alcohol having the formula (6):



wherein each same or different R^3 is the same as above.

- 20 21. A process according to claim 20, **characterized** in that said alcohol having the
formula (6) is a 2-alkyl alkanol, preferably 2-ethyl hexanol or 2-propyl pentanol.

22. A process according to any of claims 18-21, **characterized** in that said
magnesium composition containing magnesium bonded to a hydrocarbyl and
magnesium bonded to a hydrocarbyl oxide having the empirical formula (3) is a
contact product of a dialkyl magnesium and an alcohol in a molar ratio alcohol to
25 dialkyl magnesium of 0.01-100 mol/mol, preferably 1.0-5.0 mol/mol, more
preferably 1.7-2.0 mol/mol, most preferably 1.8-1.98 mol/mol.

23. A process according to any of claims 2-22, **characterized** in that in step c),
said first product is contacted with said magnesium composition containing
magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide
30 and having the empirical formula (3).

24. A process according to any of claims 2-23, **characterized** in that in step c), said support or, optionally, said first reaction product, is contacted with said magnesium composition containing magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide and having the empirical formula (3) in a ratio moles of magnesium/g of the support of between 0.001-1000 mmol/g of the support, preferably 0.01-100 mmol/g of the support, most preferably 0.1-10 mmol/g of the support. (g of the support means, in the case of said first reaction product, the support which was used as starting material for the first reaction product.)
25. A process according to any of claims 2-24, **characterized** in that in step c), said support or said first product is contacted with a solution of said magnesium composition (3) in a hydrocarbon.
26. A process according to claim 25, **characterized** in that the concentration of said solution is 5-60% by weight.
27. A process according to claims 25 or 26, **characterized** in that the volume of said solution is about two times the pore volume of the support or said first product.
28. A process according to any preceding claim, **characterized** in that in said titanium halide compound having the formula (4), R⁴ is a C₂-C₈ alkyl, preferably a C₂-C₆ alkyl.
29. A process according to any preceding claim, **characterized** in that in said titanium halide compound having the formula (4), X² is chlorine.
30. A process according to any preceding claim, **characterized** in that in said titanium halide compound having the formula (4), n³ is 0.
31. A process according to any preceding claim, **characterized** in that said titanium halide compound having the formula (4) is titanium tetrachloride.
32. A process according to any preceding claim, **characterized** in that in addition to said titanium compound having the formula (4), a titanium compound having the formula (7):



- wherein each same or different R⁵ is a C₁-C₂₀ alkyl, preferably a C₂-C₈ alkyl, most preferably a C₂-C₆ alkyl, each same or different X³ is a halogen, preferably chlorine, n⁴ is an integer 1-4, and Ti is quadrivalent titanium, is reacted.

33. A process according to claim 32, **characterized** in that titanium tetrachloride and titanium tetra C₁-C₆-alkoxide are reacted.
34. A process according to any of claims 2-33, **characterized** in that said second reaction product is contacted with said titanium compound having the formula (4) in a ratio moles of said titanium compound/g of the support of 0.01-10 mmol/ g of the support, preferably 0.1-2 mmol/g of the support.
35. A process according to any of claims 2-34, **characterized** in that said second reaction product is contacted with said titanium compound having the formula (4) in a ratio moles of said titanium compound/total moles of the magnesium of 0.05-2 mol/mol, preferably 0.1-1.2 mol/mol, most preferably 0.2-0.7 mol/mol.
36. A high activity catalyst component for the production of olefin polymers, **characterized** in that it has been prepared by a process according to one of claims 1-35.
37. A high activity catalyst component according to claim 36, **characterized** in that it has high activity both when producing low melt flow rate ethylene polymer and high melt flow rate polymer.
38. A polyethylene composition produced in at least two polymerization stages using a catalyst according to claim 36 or 37 and having an SHI_{5/300} higher than 60, **characterized** in that it has a low gel level.
39. A film produced from a composition according to claim 38, **characterized** in that the number of gels in size class 0.3-0.7 mm and >0.7 mm are < 20 and 0 respectively.
40. A polyethylene composition produced in at least two polymerization stages using a catalyst component according to claim 36 or 37 and having an MFR₂₁ between 5 and 15 and an SHI_{2.7/210} higher than 40, **characterized** in that when compounded with a carbon black additive, the resulting compound has a low dispersion value.
41. A polyethylene composition according to claim 40, **characterized** in that it has a dispersion (ISO-rating) lower than 5.
42. Use of a high activity catalyst component according to any of claims 36 or 37 in the polymerization of olefins, preferably in the homo- or copolymerization of ethylene.

43. Use according to claim 42, together with a cocatalyst having the formula (9):



wherein each R^6 is independently a C_1 - C_{20} alkyl, preferably a C_1 - C_{10} alkyl, most preferably a C_2 - C_6 alkyl such as ethyl, X is a halogen, preferably chlorine, n is 1 to 5 3, more preferably 2 or 3, most preferably 3.

AMENDED CLAIMS

[received by the International Bureau on 27 September 1999 (27.09.99);
original claims 1-43 replaced by new claims 1-39; (6 pages)]

1. A two-stage process for the polymerization of ethylene, **characterized** in that a polyethylene composition, which has a molecular weight distribution expressed as $SHI_{5/300}$ of higher than 60 and a low gel level, is produced by means of a high activity catalyst component, prepared by the steps of reacting:

a support comprising a magnesium halide compound having the formula (1):



wherein R is a C₁-C₂₀ alkyl, a C₇-C₂₆ aralkyl, a C₁-C₂₀ alkoxy or a C₇-C₂₆ aralkoxy, each same or different X is a halogen, and n is an integer 1 or 2,

- 10 an alkyl metal halide compound having the formula (2):



wherein M is B or Al, each same or different R¹ is a C₁-C₁₀ alkyl, each same or different X¹ is a halogen, m¹ is 1 or 2, n¹ is 1 or 2 when m¹ is 1, or n¹ is an integer from 1 to 5 when m¹ is 2,

- 15 a magnesium composition containing magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide, said magnesium composition having the empirical formula (3)



- 20 wherein each same or different R² is a C₁-C₂₀ alkyl, each same or different R³ is a C₁-C₂₀ alkyl, n² is between 0.01 and 1.99, and

a titanium halide compound having the formula (4):



wherein each same or different R⁴ is a C₁-C₂₀ alkyl, each same or different X² is a halogen, n³ is 0 or an integer 1-3, and Ti is quadrivalent titanium.

- 25 2. A process according to claim 1, **characterized** in that the polyethylene composition gives a film, the number of gels in size class 0.3-0.7 and size class >0.7 are <20 and 0, respectively.

3. A process according to claim 1 or 2, **characterized** in that the catalyst component preparation comprises the subsequent steps of:
- a) providing said support comprising a magnesium halide compound having the formula (1),
 - 5 b) contacting said support comprising a magnesium halide compound having the formula (1) with said alkyl metal halide compound having the formula (2), to give a first product,
 - c) contacting said first product with said magnesium composition containing magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide and having the empirical formula (3), to give a second product, and
10
 - d) contacting said second product with said titanium halide compound having the formula (4).
4. A process according to claim 1, 2 or 3, **characterized** in that said support is in the form of particles, the size of which is from about 1 μm to about 1000 μm , preferably from about 10 μm to about 100 μm .
15
5. A process according to any of claims 1-4, **characterized** in that said magnesium halide compound having the formula (1) is a magnesium dihalide, preferably MgCl_2 .
6. A process according to any of claims 1-5, **characterized** in that said support comprising a magnesium halide compound having the formula (1) also comprises an inorganic oxide.
20
7. A process according to any of claims 1-6, **characterized** in that said inorganic oxide is an inorganic oxide having surface hydroxyls, such as silica, alumina, silica-alumina, magnesia and mixtures thereof, preferably silica.
- 25 8. A process according to any preceding claim, **characterized** in that said support comprises particles having a core comprising said inorganic oxide and a shell comprising said magnesium halide compound.
9. A process according to claim 6, 7 or 8, **characterized** in that in said support, the amount of said magnesium halide compound having the formula (1), expressed as per cent magnesium Mg calculated on the weight of the support, is 1-20%, preferably 2-6%.
30

10. A process according to any preceding claim, **characterized** in that in said alkyl metal halide having the formula (2), independently, M is Al, each same or different R¹ is a C₁-C₆ alkyl, each X¹ is a chlorine, n¹ is 1, and m¹ is an integer 1 or 2.
- 5 11. A process according to claim 10, **characterized** in that said alkyl metal halide compound having the formula (2) is an alkyl aluminium dichloride, e.g. ethyl-aluminium dichloride.
12. A process according to any of claims 3 to 11, **characterized** in that in step b) of the catalyst component preparation, said support comprising a magnesium halide
10 compound having the formula (1) is contacted with a solution of said alkyl metal halide compound having the formula (2) in an essentially non-polar solvent, preferably a non-polar hydrocarbon solvent, most preferably a C₄-C₁₀ hydrocarbon.
13. A process according to claim 11, **characterized** in that the concentration of said alkyl metal halide compound having the formula (2) in said non-polar solvent is
15 1-80% by weight, preferably 5-40% by weight, most preferably 10-30% by weight.
14. A process according to claim 12 or 13, **characterized** in that the total volume of the alkyl metal halide compound (2) solution is not exceeding the pore volume of the support.
15. A process according to any of claims 3 to 13, **characterized** in that in said step
20 b), said support comprising a magnesium halide compound having the formula (1) is contacted with a solution of said alkyl metal halide compound having the formula (2) in a ratio moles of said alkyl metal halide to grams of said support of between about 0.01 mmol/g and about 100 mmol/g, preferably about 0.5 mmol/g and about 2.0 mmol/g.
- 25 16. A process according to any of claims 3 to 15, **characterized** in that in said step b), said support comprising a magnesium halide compound having the formula (1) is contacted with a solution of said alkyl metal halide compound having the formula (2) in a molar ratio of said alkyl metal halide compound (2) to said magnesium
30 halide compound (1) of between about 0.01 and about 100 mol/mol, preferably about 0.1 mol/mol and about 10 mol/mol, most preferably about 0.2 and about 3.0 mol/mol.
17. A process according to any preceding claim, **characterized** in that in said magnesium composition containing magnesium bonded to a hydrocarbyl and

magnesium bonded to a hydrocarbyl oxide having the empirical formula (3), each same or different R^2 is a C_2 - C_{10} alkyl.

18. A process according to any preceding claim, **characterized** in that in said magnesium composition containing magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide having the empirical formula (3), each same or different R^3 is a C_3 - C_{20} alkyl, preferably a branched C_4 - C_{10} alkyl, most preferably a 2-ethyl-1-hexyl or a 2-propyl-1-pentyl.

19. A process according to any preceding claim, **characterized** in that said magnesium composition containing magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide having the empirical formula (3) is a contact product of a dialkyl magnesium having the formula (5):



wherein each same or different R^2 is defined as above, and an alcohol.

20. A process according to claim 19, **characterized** in that said dialkyl magnesium having the formula (5) is dibutyl magnesium, butyl ethyl magnesium or butyl octyl magnesium.

21. A process according to any preceding claim, **characterized** in that said magnesium composition containing magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide having the empirical formula (3) is a contact product of a dialkyl magnesium and an alcohol having the formula (6):




wherein each same or different R^3 is the same as above.

22. A process according to claim 21, **characterized** in that said alcohol having the formula (6) is a 2-alkyl alkanol, preferably 2-ethyl hexanol or 2-propyl pentanol.

23. A process according to any of claims 19-22, **characterized** in that said magnesium composition containing magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide having the empirical formula (3) is a contact product of a dialkyl magnesium and an alcohol in a molar ratio alcohol to dialkyl magnesium of 0.01-100 mol/mol, preferably 1.0-5.0 mol/mol, more preferably 1.7-2.0 mol/mol, most preferably 1.8-1.98 mol/mol.

24. A process according to any of claims 3-23, **characterized** in that in step c), said first product is contacted with said magnesium composition containing magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide and having the empirical formula (3).
- 5 25. A process according to any of claims 3-24, **characterized** in that in step c), said support or, optionally, said first reaction product, is contacted with said magnesium composition containing magnesium bonded to a hydrocarbyl and magnesium bonded to a hydrocarbyl oxide and having the empirical formula (3) in a ratio moles of magnesium/g of the support of between 0.001-1000 mmol/g of the support, preferably 0.01-100 mmol/g of the support, most preferably 0.1-10 mmol/g of the support. (g of the support means, in the case of said first reaction product, the support which was used as starting material for the first reaction product.)
- 10 26. A process according to any of claims 3-25, **characterized** in that in step c), said support or said first product is contacted with a solution of said magnesium composition (3) in a hydrocarbon.
- 15 27. A process according to claim 26, **characterized** in that the concentration of said solution is 5-60% by weight.
28. A process according to claims 26 or 27, **characterized** in that the volume of said solution is about two times the pore volume of the support or said first product.
- 20 29. A process according to any preceding claim, **characterized** in that in said titanium halide compound having the formula (4), R^4 is a C_2 - C_8 alkyl, preferably a C_2 - C_6 alkyl.
30. A process according to any preceding claim, **characterized** in that in said titanium halide compound having the formula (4), X^2 is chlorine.
- 25 31. A process according to any preceding claim, **characterized** in that in said titanium halide compound having the formula (4), n^3 is 0.
32. A process according to any preceding claim, **characterized** in that said titanium halide compound having the formula (4) is titanium tetrachloride.
33. A process according to any preceding claim, **characterized** in that in addition to said titanium compound having the formula (4), a titanium compound having the formula (7):
- 30



wherein each same or different R^5 is a C_1 - C_{20} alkyl, preferably a C_2 - C_8 alkyl, most preferably a C_2 - C_6 alkyl, each same or different X^3 is a halogen, preferably chlorine, n^4 is an integer 1-4, and Ti is quadrivalent titanium, is reacted.

5 34. A process according to claim 33, **characterized** in that titanium tetrachloride and titanium tetra C_1 - C_6 -alkoxide are reacted.

35. A process according to any of claims 3-34, **characterized** in that said second reaction product is contacted with said titanium compound having the formula (4) in a ratio moles of said titanium compound/g of the support of 0.01-10 mmol/ g of the support, preferably 0.1-2 mmol/g of the support.

36. A process according to any of claims 3-35, **characterized** in that said second reaction product is contacted with said titanium compound having the formula (4) in a ratio moles of said titanium compound/total moles of the magnesium of 0.05-2 mol/mol, preferably 0.1-1.2 mol/mol, most preferably 0.2-0.7 mol/mol.

15 37. A polyethylene composition produced in at least two polymerization stages according to any preceding claim, **characterized** in that it has an MFR₂₁ between 5 and 15 and an SHI_{2.7/210} higher than 40, that when compounded with a carbon black additive, the resulting compound has a low dispersion value.

38. A polyethylene composition according to claim 37, **characterized** in that it has a dispersion (ISO rating) lower than 5.

39. A process according to any of claims 1 to 36, together with a cocatalyst having the formula (9):



25 wherein each R^6 is independently a C_1 - C_{20} alkyl, preferably a C_1 - C_{10} alkyl, most preferably a C_2 - C_6 alkyl such as ethyl, X is a halogen, preferably chlorine, n is 1 to 3, more preferably 2 or 3, most preferably 3.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/FI 99/00286

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C08F4/655 C08F10/02 C08L23/04 C08J5/18

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08F C08L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 97 22633 A (BOREALIS AS ;PALMQVIST ULF (SE); JOHANSSON SOLVEIG (SE); THORN LAR) 26 June 1997 (1997-06-26)	1-6, 8-12, 14-31, 36, 42, 43
	example 3	
Y	page 24, line 26 - line 32	32-35
X	page 11, line 36 - page 12, line 2	3
X	page 12, line 32 - line 37	6
	page 13, line 17 - page 14, line 10	
X	page 15, line 9 - line 14	13
X	page 27, line 16 - line 28	37

Y	EP 0 688 794 A (BOREALIS POLYMERS OY) 27 December 1995 (1995-12-27) cited in the application page 7, line 21 - line 27 example 4 page 3, line 38 - line 41	32-35

	-/--	

Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

^o Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

9 July 1999

Date of mailing of the international search report

27/07/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Fischer, B

INTERNATIONAL SEARCH REPORT

International Application No

PCT/FI 99/00286

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 97 47682 A (SAHILA AIMO ;AEAERILAE JARI (FI); BOREALIS POLYMERS OY (FI); HAGST) 18 December 1997 (1997-12-18) page 20; examples 2-5; table 5 -----	40

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/FI 99/00286

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9722633 A	26-06-1997	AU 705479 B	20-05-1999
		AU 1216697 A	14-07-1997
		CA 2240170 A	26-06-1997
		CZ 9801914 A	14-10-1998
		EP 0869978 A	14-10-1998

EP 0688794 A	27-12-1995	US 5770540 A	23-06-1998
		AT 169934 T	15-09-1998
		AU 702291 B	18-02-1999
		AU 2740495 A	15-01-1996
		AU 7614698 A	03-09-1998
		BR 9508079 A	02-09-1997
		CA 2193483 A	28-12-1995
		CN 1158136 A	27-08-1997
		CZ 9603754 A	14-05-1997
		DE 69504143 D	24-09-1998
		DE 69504143 T	06-05-1999
		EP 0835887 A	15-04-1998
		ES 2123210 T	01-01-1999
		WO 9535323 A	28-12-1995
		HU 75296 A	28-05-1997
JP 10502951 T	17-03-1998		

WO 9747682 A	18-12-1997	FI 962366 A	08-12-1997
		AU 3034997 A	07-01-1998
		AU 6308096 A	10-02-1997
		CA 2226549 A	30-01-1997
		CN 1195363 A	07-10-1998
		EP 0837915 A	29-04-1998
		EP 0902809 A	24-03-1999
		WO 9703139 A	30-01-1997
		PL 325016 A	06-07-1998
