



(43) International Publication Date
7 November 2013 (07.11.2013)

(10) International Publication Number
WO 2013/166408 A1

(51) International Patent Classification:

A61K 9/10 (2006.01) *A61K 9/51* (2006.01)
A61K 47/32 (2006.01)

(21) International Application Number:

PCT/US2013/039499

(22) International Filing Date:

3 May 2013 (03.05.2013)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/642,261 3 May 2012 (03.05.2012) US

(71) Applicant: **KALA PHARMACEUTICALS, INC.**
[US/US]; 135 Beaver Street, Suite 309, Waltham, MA
02452 (US).

(72) Inventor: **POPOV, Alexey**; 60 Hope Avenue, Waltham,
MA 02453 (US).

(74) Agent: **LEE, Jessamine, N.**; Wolf, Greenfield & Sacks,
P.C., 600 Atlantic Avenue, Boston, MA 02210-2206 (US).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,

BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,
HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP,
KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD,
ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI,
NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU,
RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ,
TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA,
ZM, ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ,
UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,
TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,
EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV,
MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
ML, MR, NE, SN, TD, TG).

Published:

- with international search report (Art. 21(3))
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments (Rule 48.2(h))

(54) Title: PHARMACEUTICAL NANOPARTICLES SHOWING IMPROVED MUCOSAL TRANSPORT

(57) Abstract: Compositions with improved particle transport in mucus are provided. The compositions include modifying the surface coatings of particles including pharmaceutical agents that have a low aqueous solubility. In some embodiments, a surface coating includes a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer, such as poly(vinyl alcohol) (PVA). Such compositions and methods can be used to achieve efficient transport of particles of pharmaceutical agents through mucus barriers in the body for a wide spectrum of applications, including drug delivery, imaging, and diagnostic applications.



WO 2013/166408 A1

PHARMACEUTICAL NANOPARTICLES SHOWING IMPROVED MUCOSAL TRANSPORTField of the Invention

[0001] The present invention generally relates to particles, compositions, and methods that aid particle transport in mucus.

Background of the Invention

[0002] A mucus layer present at various points of entry into the body, including the eyes, nose, lungs, gastrointestinal tract, and female reproductive tract, is naturally adhesive and serves to protect the body against pathogens, allergens, and debris by effectively trapping and quickly removing them via mucus turnover. For effective delivery of therapeutic, diagnostic, or imaging particles via mucus membranes, the particles must be able to readily penetrate the mucus layer to avoid mucus adhesion and rapid mucus clearance. Several lines of evidence suggest that conventional nanoparticles are not capable of crossing mucosal barriers. However, it has been recently demonstrated that polymeric nanoparticles (degradable or not) modified with a special surface coating (covalently or non-covalently) can diffuse in physiologically thick mucus samples nearly as rapidly as they would in water. Such polymer-based mucus-penetrating particles (MPP) can encapsulate various therapeutic, imaging, or diagnostic agents to enable drug delivery, diagnostic, or imaging applications.

[0003] Despite these improvements, only a handful of surface coatings have been shown to facilitate mucus penetration of particles. Accordingly, improvements in compositions and methods involving mucus-penetrating particles for delivery of pharmaceutical agents would be beneficial.

Summary of the Invention

[0004] The present description generally relates to particles, compositions, and methods that aid particle transport in mucus. In some embodiments, the compositions and methods include a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer (*e.g.*, poly(vinyl alcohol), PVA), which facilitates mucus penetration. The subject matter of this application involves, in some cases, interrelated products, alternative solutions to a particular problem, and/or a plurality of different uses of structures and compositions.

[0005] In one set of embodiments, a method of forming coated particles is provided. The method comprises coating a plurality of core particles with a surface-altering agent to form coated particles, wherein the surface-altering agent comprises a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer, the polymer having a molecular weight of at least about 1 kDa and less than or equal to about 1000 kDa, and wherein the polymer is at least about 30% hydrolyzed and less than about 95% hydrolyzed. Each of the core particles comprises a pharmaceutical agent or a salt thereof. The coated particles have a relative velocity of greater than 0.5 in mucus.

[0006] In another set of embodiments, a composition comprising a plurality of coated particles is provided. Each of the coated particles comprises a core particle comprising a pharmaceutical agent or a salt thereof and a coating comprising a surface-altering agent surrounding the core particle. The surface-altering agent comprises a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer, the polymer having a molecular weight of at least about 1 kDa and less than or equal to about 1000 kDa, wherein the polymer is at least about 30% hydrolyzed and less than about 95% hydrolyzed. The coated particles have a relative velocity of greater than 0.5 in mucus.

[0007] In another set of embodiments, a method is provided. The method comprises delivering to mucus or a mucus membrane a composition comprising a plurality of coated particles. The coated particle comprises a core particle comprising a pharmaceutical agent or a salt thereof, and a coating comprising a surface-altering agent surrounding the core particle. The surface-altering agent comprises a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer, the polymer having a molecular weight of at least about 1 kDa and less than or equal to about 1000 kDa, wherein the polymer is at least about 30% hydrolyzed and less than about 95% hydrolyzed. The coated particles have a relative velocity of greater than 0.5 in mucus.

[0008] Other advantages and novel features of the present invention will become apparent from the following detailed description of various non-limiting embodiments of the invention when considered in conjunction with the accompanying figures. In cases where the present specification and a document incorporated by reference include conflicting and/or inconsistent disclosure, the present specification shall control. If two or more documents

incorporated by reference include conflicting and/or inconsistent disclosure with respect to each other, then the document having the later effective date shall control.

Brief Description of the Drawings

[0009] Non-limiting embodiments of the present invention will be described by way of example with reference to the accompanying figures, which are schematic and are not intended to be drawn to scale. In the figures, each identical or nearly identical component illustrated is typically represented by a single numeral. For purposes of clarity, not every component is labeled in every figure, nor is every component of each embodiment of the invention shown where illustration is not necessary to allow those of ordinary skill in the art to understand the invention. In the figures:

[00010] FIG. 1 is a schematic drawing of a mucus-penetrating particle having a coating and a core of a solid pharmaceutical agent according to one set of embodiments;

[00011] FIG. 2A is a plot showing the ensemble averaged velocity $\langle V_{\text{mean}} \rangle$ in human cervicovaginal mucus (CVM) for PSCOO particles coated with various poly(vinyl alcohols) (PVAs) according to one set of embodiments;

[00012] FIG. 2B is a plot showing the relative velocity $\langle V_{\text{mean}} \rangle_{\text{rel}}$ in CVM for PSCOO particles coated with various PVAs according to one set of embodiments;

[00013] FIG. 3 is a plot showing relative velocity $\langle V_{\text{mean}} \rangle_{\text{rel}}$ in CVM for PSCOO particles incubated with various PVAs mapped according to the PVA's molecular weight and degree of hydrolysis, according to one set of embodiments. Each data point represents $\langle V_{\text{mean}} \rangle_{\text{rel}}$ for the particles stabilized with a specific PVA.

[00014] FIGs. 4A-4B are plots showing bulk transport in CVM *in vitro* of PSCOO nanoparticles coated with various PVAs, according to one set of embodiments. Negative controls are uncoated 200nm PSCOO particles; Positive controls are 200nm PSCOO particles coated with Pluronic® F127. FIGs. 4A-4B represent data obtained with two different CVM samples;

[00015] FIGs. 5A-5B are plots showing ensemble-average velocity $\langle V_{\text{mean}} \rangle$ (FIG. 5A) and relative sample velocity $\langle V_{\text{mean}} \rangle_{\text{rel}}$ (FIG. 5B) for poly(lactic acid) (PLA) nanoparticles (sample) prepared by emulsification with various PVAs as measured by multiple-particle tracking in CVM, according to one set of embodiments;

[00016] FIG. 6 is a plot showing relative velocity $\langle V_{\text{mean}} \rangle_{\text{rel}}$ in CVM for PLA nanoparticles prepared by emulsification with various PVAs mapped according to the PVA's molecular weight and degree of hydrolysis, according to one set of embodiments. Each data point represents $\langle V_{\text{mean}} \rangle_{\text{rel}}$ of the particles stabilized with a specific PVA. The "+" signs represent measurements in multiple CVM samples;

[00017] FIGs. 7A-7B are plots showing ensemble-average velocity $\langle V_{\text{mean}} \rangle$ (FIG. 7A) and relative sample velocity $\langle V_{\text{mean}} \rangle_{\text{rel}}$ (FIG. 7B) for pyrene nanoparticles (sample) and controls as measured by multiple-particle tracking in CVM, according to one set of embodiments;

[00018] FIGs. 8A-8F are representative CVM velocity (V_{mean}) distribution histograms for pyrene/nanocrystals obtained with various surface-altering agents (SAMPLE=Pyrene nanoparticles, POSITIVE=200nm PS-PEG5K, NEGATIVE=200nm PS-COO); according to one set of embodiments; and

[00019] FIG. 9 is a plot of relative velocity $\langle V_{\text{mean}} \rangle_{\text{rel}}$ for pyrene nanocrystals coated with PVA in CVM mapped according to the PVA's molecular weight and degree of hydrolysis according to one set of embodiments.

[00020] FIG. 10 is a plot showing the pharmacokinetics of Loteprednol Etabonate (LE) in the cornea of New Zealand white rabbits *in vivo*. Rabbits were given one 50 μL dose of each one of the three LE-MPPs (*i.e.*, LE-F127, LE-Tween 80, and LE-PVA) or Lotemax[®] in each eye. The PVA had a molecular weight of about 2 kDa and was about 75% hydrolyzed. The dose of LE was 0.5% in all instances. Error bars show standard errors of the mean ($n = 6$).

[00021] FIG. 11 is a plot showing the mucus mobility of loteprednol etabonate (LE) particles coated with various PVAs as a function of the molecular weight (MW (kDa)) and hydrolysis degree (% hydrolysis) of the PVAs. Samples that do not form particles within the target range are indicated as "Does not formulate."

Detailed Description

[00022] Particles, compositions, and methods that aid particle transport in mucus are provided. The compositions and methods may include, in some embodiments, modifying the surface coatings of particles including pharmaceutical agents that have a low aqueous solubility. In some embodiments, a surface coating includes a synthetic polymer having

pendant hydroxyl groups on the backbone of the polymer, such as poly(vinyl alcohol) (PVA). Such compositions and methods can be used to achieve efficient transport of particles of pharmaceutical agents through mucus barriers in the body for a wide spectrum of applications, including drug delivery, imaging, and diagnostic applications. In certain embodiments, a pharmaceutical composition including such particles is well-suited for administration routes involving the particles passing through a mucosal barrier.

[00023] In some embodiments, the compositions and methods involve the use of PVAs that aids particle transport in mucus. The compositions and methods may involve making mucus-penetrating particles (MPP) by, for example, an emulsification process in the presence of specific PVAs. In certain embodiments, the compositions and methods involve making MPP from pre-fabricated particles by non-covalent coating with specific PVAs. In other embodiments, the compositions and methods involve making MPP in the presence of specific PVAs without any polymeric carriers, or with minimal use of polymeric carriers. It should be appreciated, however, that in other embodiments, polymeric carriers can be used.

[00024] PVA is a water-soluble non-ionic synthetic polymer. Due to its surface active properties, PVA is widely used in the food and drug industries as a stabilizing agent for emulsions and, in particular, to enable encapsulation of a wide variety of compounds by emulsification techniques. PVA has the “generally recognized as safe” or “GRAS” status with the Food and Drug Administration (FDA), and has been used in auricular, intramuscular, intraocular, intravitreal, iontophoretic, ophthalmic, oral, topical, and transdermal drug products and/or drug delivery systems.

[00025] In certain previous studies, many have described PVA as a mucoadhesive polymer, suggesting or reporting that incorporating PVA in the particle formulation process leads to particles that are strongly mucoadhesive. Surprisingly, and contrary to the established opinion that PVA is a mucoadhesive polymer, the inventors have discovered within the context of the invention that compositions and methods utilizing specific PVA grades aid particle transport in mucus and are not mucoadhesive in certain applications described herein. Specifically, mucus-penetrating particles can be prepared by tailoring the degree of hydrolysis and/or molecular weight of the PVA, which was previously unknown. This discovery significantly broadens the arsenal of techniques and ingredients applicable for manufacturing MPP and advantageously addresses certain limitations of certain existing

materials that have been shown to facilitate mucus penetration, such as poly(ethylene glycol) (PEG) and (poly(ethylene oxide)-poly(propylene oxide)-poly(ethylene oxide) block copolymers (Pluronics®).

[00026] In particular, in light of drug delivery applications, there may be certain limitations involving PEGylated or Pluronic®-coated MPP: A) PEGylation of prefabricated particles or the use of PEG-containing block copolymers to produce PEGylated MPP may generate new inactive ingredients as defined by the FDA. These new ingredients may require expensive and time-consuming preclinical and clinical safety studies and represents significant regulatory hurdles with the FDA, which may limit the practical potential of PEGylated MPP. B) It is difficult to prepare Pluronic®-coated MPP directly via emulsification techniques, the industry's most popular and most universal approach to nano- and microencapsulation,. This limitation significantly reduces the scope of compounds that can be efficiently encapsulated into Pluronic®-coated MPP. In particular, it may preclude efficient encapsulation of water soluble to slightly water soluble ingredients (*e.g.*, drugs, proteins, oligonucleotides, *etc.* with an aqueous solubility of greater than about 1 mg/mL) that are most commonly encapsulated by double emulsion techniques. Accordingly, improvements in compositions and methods that would allow direct preparation of MPP by emulsification techniques would be beneficial. C) Pluronics® are currently not approved by the FDA for dosage via auricular, intramuscular, intraocular, intravitreal routes, which are approved dosage routes for PVA. Additionally, the maximum Pluronic® concentration currently approved by the FDA for ophthalmic dosage is 0.2%, while for PVA it is 1.4%. Accordingly, improvements in compositions and methods that would allow preparation of MPP by utilizing PVA (*e.g.*, instead of Pluronics®) are likely to greatly facilitate clinical development of the mucus-penetrating particle technology overall and, in particular, for the aforementioned dosage routes.

[00027] In some embodiments described herein, the compositions and methods of making particles, including certain compositions and methods for making particles that have increased transport through mucosal barriers, address one or more, or all, of the concerns described above. Specifically, in some embodiments, the compositions and methods involve making mucus-penetrating particles by an emulsification process in the presence of specific PVAs. Advantageously, by utilizing PVA for MPP preparation, certain limitations of

PEGylated or Pluronic®-coated MPP with respect to drug loading, scope of encapsulatable materials, and/or complexity of clinical development, may be addressed.

[00028] It should be appreciated that while in some embodiments it may be advantageous to form mucus-penetrating particles without the use of PEG or Pluronic®, in other embodiments PEG and/or Pluronic® may be included in the compositions and methods described herein.

[00029] In some embodiments, the particles described herein have a core-shell type arrangement. The core may comprise any suitable material such as a solid pharmaceutical agent or a salt thereof having a relatively low aqueous solubility a polymeric carrier, a lipid, and/or a protein. The core may also comprise a gel or a liquid in some embodiments. The core may be coated with a coating or shell comprising a surface-altering agent that facilitates mobility of the particle in mucus. As described in more detail below, in some embodiments the surface-altering agent may comprise a polymer (e.g., a synthetic polymer or a natural polymer) having pendant hydroxyl groups on the backbone of the polymer. The molecular weight and/or degree of hydrolysis of the polymer may be chosen to impart certain transport characteristics to the particles, such as increased transport through mucus.

[00030] Non-limiting examples of particles are now provided. As shown in the illustrative embodiment of FIG.1, a particle 10 includes a core 16 (which may be in the form of a particle, referred to herein as a core particle) and a coating 20 surrounding the core. In one set of embodiments, a substantial portion of the core is formed of one or more solid pharmaceutical agents (e.g., a drug, therapeutic agent, diagnostic agent, imaging agent) that can lead to certain beneficial and/or therapeutic effects. The core may be, for example, a nanocrystal (i.e., a nanocrystal particle) of a pharmaceutical agent. In other embodiments, the core may include a polymeric carrier, optionally with one or more pharmaceutical agents encapsulated or otherwise associated with the core. In yet other cases, the core may include a lipid, a protein, a gel, a liquid, and/or another suitable material to be delivered to a subject. The core includes a surface 24 to which one or more surface-altering agents can be attached. For instance, in some cases, core 16 is surrounded by coating 20, which includes an inner surface 28 and an outer surface 32. The coating may be formed, at least in part, of one or more surface-altering agents 34, such as a polymer (e.g., a synthetic polymer or a polymer having pendant hydroxyl groups), which may associate with surface 24 of the core. Surface-

altering agent 34 may be associated with the core particle by, for example, being covalently attached to the core particle, non-covalently attached to the core particle, adsorbed to the core, or attached to the core through ionic interactions, hydrophobic and/or hydrophilic interactions, electrostatic interactions, van der Waals interactions, or combinations thereof. In one set of embodiments, the surface-altering agents, or portions thereof, are chosen to facilitate transport of the particle through a mucosal barrier (*e.g.*, mucus or a mucosal membrane).

[00031] Particle 10 may optionally include one or more components 40 such as targeting moieties, proteins, nucleic acids, and bioactive agents which may optionally impart specificity to the particle. For example, a targeting agent or molecule (*e.g.*, a protein, nucleic acid, nucleic acid analog, carbohydrate, or small molecule), if present, may aid in directing the particle to a specific location in the subject's body. The location may be, for example, a tissue, a particular cell type, or a subcellular compartment. One or more components 40, if present, may be associated with the core, the coating, or both; *e.g.*, they may be associated with surface 24 of the core, inner surface 28 of the coating, outer surface 32 of the coating, and/or embedded in the coating. The one or more components 40 may be associated through covalent bonds, absorption, or attached through ionic interactions, hydrophobic and/or hydrophilic interactions, electrostatic interactions, van der Waals interactions, or combinations thereof. In some embodiments, a component may be attached (*e.g.*, covalently) to one or more of the surface-altering agents of the coated particle using methods known to those of ordinary skill in the art.

[00032] It should be understood that components and configurations other than those shown in FIG. 1 or described herein may be suitable for certain particles and compositions, and that not all of the components shown in FIG. 1 are necessarily present in some embodiments.

[00033] In one set of embodiments, particle 10, when introduced into a subject, may interact with one or more components in the subject such as mucus, cells, tissues, organs, particles, fluids (*e.g.*, blood), portions thereof, and combinations thereof. In some such embodiments, the coating of particle 10 can be designed to include surface-altering agents or other components with properties that allow favorable interactions (*e.g.*, transport, binding, adsorption) with one or more materials from the subject. For example, the coating may

include surface-altering agents or other components having a certain hydrophilicity, hydrophobicity, surface charge, functional group, specificity for binding, and/or density to facilitate or reduce particular interactions in the subject. One specific example includes choosing a certain hydrophilicity, hydrophobicity, surface charge, functional group, specificity for binding, and/or density of one or more surface-altering agents to reduce the physical and/or chemical interactions between the particle and mucus of the subject, so as to enhance the mobility of the particle through mucus. Other examples are described in more detail below.

[00034] In some embodiments, once a particle is successfully transported across a mucosal barrier (*e.g.*, mucus or a mucosal membrane) in a subject, further interactions between the particle in the subject may take place. Interactions may take place, in some instances, through the coating and/or the core, and may involve, for example, the exchange of materials (*e.g.*, pharmaceutical agents, therapeutic agents, proteins, peptides, polypeptides, nucleic acids, nutrients, *e.g.*) from the one or more components of the subject to particle 10, and/or from particle 10 to the one or more components of the subject. For example, in some embodiments in which the core is formed of or comprises a pharmaceutical agent, the breakdown, release and/or transport of the pharmaceutical agent from the particle can lead to certain beneficial and/or therapeutic effects in the subject. As such, the particles described herein can be used for the diagnosis, prevention, treatment or management of certain diseases or bodily conditions.

[00035] Specific examples for the use of the particles described herein are provided below in the context of being suitable for administration to a mucosal barrier (*e.g.*, mucus or a mucosal membrane) in a subject. It should be appreciated that while many of the embodiments herein are described in this context, and in the context of providing a benefit for diseases and conditions that involve transport of materials across a mucosal barrier, the invention is not limited as such and the particles, compositions, kits, and methods described herein may be used to prevent, treat, or manage other diseases or bodily conditions.

[00036] Mucus is a sticky viscoelastic gel that protects against pathogens, toxins, and debris at various points of entry into the body, including the eyes, nose, lungs, gastrointestinal tract, and female reproductive tract. Many synthetic nanoparticles are strongly mucoadhesive and become effectively trapped in the rapidly-cleared peripheral mucus layer, vastly limiting

their distribution throughout the mucosal membrane as well as penetration toward the underlying tissue. The residence time of these trapped particles is limited by the turnover rate of the peripheral mucus layer, which, depending on the organ, ranges from seconds to several hours. To ensure effective delivery of particles including pharmaceutical agents (*e.g.*, therapeutic, diagnostic, and/or imaging agents) via mucus membranes, such particles must be able to readily diffuse through the mucus barrier, avoiding mucus adhesion.

[00037] It has been recently demonstrated that modifying surfaces of polymeric nanoparticles with a mucus-penetrating coating can minimize adhesion to mucus and thus allow rapid particle penetration across mucus barriers. Specifically, it has been shown that polymeric nanoparticles as large as 500 nm, when coated covalently with dense coatings of low molecular weight PEG (2 kDa -5 kDa) or non-covalently with specific Pluronic[®] molecules (*e.g.*, P103, P105, F127) can penetrate human mucus nearly as fast as they move in pure water, and at rates almost 100-fold faster than similarly-sized uncoated polymeric particles. Despite these improvements, only a handful of surface coatings have been shown to facilitate mucus penetration of particles. Accordingly, improvements in compositions and methods involving mucus-penetrating particles for delivery of pharmaceutical agents would be beneficial.

Core Particles

[00038] As described above in reference to FIG. 1, particle 10 may include a core 16. The core may be formed of any suitable material, such as an organic material, an inorganic material, a polymer, a lipid, a protein or combinations thereof. In one set of embodiments, the core comprises a solid. The solid may be, for example, a crystalline or an amorphous solid, such as a crystalline or amorphous solid pharmaceutical agent (*e.g.*, a therapeutic agent, diagnostic agent, and/or imaging agent), or a salt thereof. In other embodiments, the core may comprise a gel or a liquid (*e.g.*, an oil-in-water or water-in-oil emulsion). In some embodiments, more than one pharmaceutical agents may be present in the core. Specific examples of pharmaceutical agents are provided in more detail below.

[00039] The pharmaceutical agent may be present in the core in any suitable amount, *e.g.*, at least about 0.01 wt%, at least about 0.1 wt%, at least about 1 wt%, at least about 5 wt%, at least about 10 wt%, at least about 20 wt%, at least about 30 wt%, at least about 40 wt%, at

least about 50 wt%, at least about 60 wt%, at least about 70 wt%, at least about 80 wt%, at least about 85 wt%, at least about 90 wt%, at least about 95 wt%, or at least about 99 wt% of the core. In one embodiment, the core is formed of 100 wt% of the pharmaceutical agent. In some cases, the pharmaceutical agent may be present in the core at less than or equal to about 100 wt%, less than or equal to about 90 wt%, less than or equal to about 80 wt%, less than or equal to about 70 wt%, less than or equal to about 60 wt%, less than or equal to about 50 wt%, less than or equal to about 40 wt%, less than or equal to about 30 wt%, less than or equal to about 20 wt%, less than or equal to about 10 wt%, less than or equal to about 5 wt%, less than or equal to about 2 wt%, or less than or equal to about 1 wt%. Combinations of the above-referenced ranges are also possible (*e.g.*, present in an amount of at least about 80 wt% and less than or equal to about 100 wt%). Other ranges are also possible.

[00040] In embodiments in which the core particles comprise relatively high amounts of a pharmaceutical agent (*e.g.*, at least about 50 wt% of the core particle), the core particles generally have an increased loading of the pharmaceutical agent compared to particles that are formed by encapsulating agents into polymeric carriers. This is an advantage for drug delivery applications, since higher drug loadings mean that fewer numbers of particles may be needed to achieve a desired effect compared to the use of particles containing polymeric carriers.

[00041] As described herein, in other embodiments in which a relatively high amounts of a polymer or other material forms the core, less amounts of pharmaceutical agent may be present in the core.

[00042] The core may be formed of solid materials having various aqueous solubilities (*i.e.*, a solubility in water, optionally with one or more buffers), and/or various solubilities in the solution in which the solid material is being coated with a surface-altering agent. For example, the solid material may have an aqueous solubility (or a solubility in a coating solution) of less than or equal to about 5 mg/mL, less than or equal to about 2 mg/mL, less than or equal to about 1 mg/mL, less than or equal to about 0.5 mg/mL, less than or equal to about 0.1 mg/mL, less than or equal to about 0.05 mg/mL, less than or equal to about 0.01 mg/mL, less than or equal to about 1 µg/mL, less than or equal to about 0.1 µg/mL, less than or equal to about 0.01 µg/mL, less than or equal to about 1 ng/mL, less than or equal to about 0.1 ng/mL, or less than or equal to about 0.01 ng/mL at 25 °C. In some embodiments,

the solid material may have an aqueous solubility (or a solubility in a coating solution) of at least about 1 pg/mL, at least about 10 pg/mL, at least about 0.1 ng/mL, at least about 1 ng/mL, at least about 10 ng/mL, at least about 0.1 µg/mL, at least about 1 µg/mL, at least about 5 µg/mL, at least about 0.01 mg/mL, at least about 0.05 mg/mL, at least about 0.1 mg/mL, at least about 0.5 mg/mL, at least about 1.0 mg/mL, at least about 2 mg/mL.

Combinations of the above-noted ranges are possible (*e.g.*, an aqueous solubility or a solubility in a coating solution of at least about 10 pg/mL and less than or equal to about 1 mg/mL). Other ranges are also possible. The solid material may have these or other ranges of aqueous solubilities at any point throughout the pH range (*e.g.*, from pH 1 to pH 14).

[00043] In some embodiments, the core may be formed of a material within one of the ranges of solubilities classified by the U.S. Pharmacopeia Convention: *e.g.*, very soluble: >1,000 mg/mL; freely soluble: 100-1,000 mg/mL; soluble: 33-100 mg/mL; sparingly soluble: 10-33 mg/mL; slightly soluble: 1-10 mg/mL; very slightly soluble: 0.1-1 mg/mL; and practically insoluble: <0.1 mg/mL.

[00044] Although a core may be hydrophobic or hydrophilic, in many embodiments described herein, the core is substantially hydrophobic. “Hydrophobic” and “hydrophilic” are given their ordinary meaning in the art and, as will be understood by those skilled in the art, in many instances herein, are relative terms. Relative hydrophobicities and hydrophilicities of materials can be determined by measuring the contact angle of a water droplet on a planar surface of the substance to be measured, *e.g.*, using an instrument such as a contact angle goniometer and a packed powder of the core material.

[00045] In some embodiments, a material (*e.g.*, a material forming a particle core) has a contact angle of at least about 20 degrees, at least about 30 degrees, at least about 40 degrees, at least about 50 degrees, at least about 60 degrees, at least about 70 degrees, at least about 80 degrees, at least about 90 degrees, at least about 100 degrees, at least about 110 degrees, at least about 120 degrees, or at least about 130 degrees. In some embodiments, a material has a contact angle of less than or equal to about 160 degrees, less than or equal to about 150 degrees, less than or equal to about 140 degrees, less than or equal to about 130 degrees, less than or equal to about 120 degrees, less than or equal to about 110 degrees, less than or equal to about 100 degrees, less than or equal to about 90 degrees, less than or equal to about 80 degrees, or less than or equal to about 70 degrees. Combinations of the above-referenced

ranges are also possible (*e.g.*, a contact angle of at least about 30 degrees and less than or equal to about 120 degrees). Other ranges are also possible.

[00046] Contact angle measurements can be made using a variety of techniques; here a static contact angle measurement between a pellet of the starting material which will be used to form the core and a bead of water is referenced. The material used to form the core was received as a fine powder or otherwise was ground into a fine powder using a mortar and pestle. In order to form a surface on which to make measurements, the powder was packed using a 7 mm pellet die set from International Crystal Labs. The material was added to the die and pressure was applied by hand to pack the powder into a pellet, no pellet press or high pressure was used. The pellet was then suspended for testing so that the top and bottom of the pellet (defined as the surface water is added to and the opposite parallel surface respectively) were not in contact with any surface. This was done by not fully removing the pellet from the collar of the die set. The pellet therefore touches the collar on the sides and makes no contact on the top or bottom. For contact angle measurements, water was added to the surface of the pellet until a bead of water with a steady contact angle over 30 seconds was obtained. The water was added into the bead of water by submerging or contacting the tip of the pipette or syringe used for addition to the bead of water. Once a stable bead of water was obtained, an image was taken and the contact angle was measured using standard practices.

[00047] In embodiments in which the core comprises an inorganic material (*e.g.*, for use as imaging agents), the inorganic material may include, for example, a metal (*e.g.*, Ag, Au, Pt, Fe, Cr, Co, Ni, Cu, Zn, and other transition metals), a semiconductor (*e.g.*, silicon, silicon compounds and alloys, cadmium selenide, cadmium sulfide, indium arsenide, and indium phosphide), or an insulator (*e.g.*, ceramics such as silicon oxide). The inorganic material may be present in the core in any suitable amount, *e.g.*, at least about 1 wt%, at least about 5 wt%, at least about 10 wt%, at least about 20 wt%, at least about 30 wt%, at least about 40 wt%, at least about 50 wt%, at least about 75 wt%, at least about 90 wt%, or at least about 99 wt%. In one embodiment, the core is formed of 100 wt% inorganic material. In some cases, the inorganic material may be present in the core at less than or equal to about 100 wt%, less than or equal to about 90 wt%, less than or equal to about 80 wt%, less than or equal to about 70 wt%, less than or equal to about 60 wt%, less than or equal to about 50 wt%, less than or equal to about 40 wt%, less than or equal to about 30 wt%, less than or equal to about 20

wt%, less than or equal to about 10 wt%, less than or equal to about 5 wt%, less than or equal to about 2 wt%, or less than or equal to about 1 wt%. Combinations of the above-referenced ranges are also possible (*e.g.*, present in an amount of at least about 1 wt% and less than or equal to about 20wt%). Other ranges are also possible.

[00048] The core may, in some cases, be in the form of a quantum dot, a carbon nanotube, a carbon nanowire, or a carbon nanorod. In some cases, the core comprises, or is formed of, a material that is not of biological origin.

[00049] In some embodiments, the core includes one or more organic materials such as a synthetic polymer and/or a natural polymer. Examples of synthetic polymers include non-degradable polymers such as polymethacrylate and degradable polymers such as polylactic acid, polyglycolic acid and copolymers thereof. Examples of natural polymers include hyaluronic acid, chitosan, and collagen. Other examples of polymers that may be suitable for portions of the core include those herein suitable for forming coatings on particles, as described below. In some cases, the one or more polymers present in the core may be used to encapsulate or adsorb one or more pharmaceutical agents.

[00050] In certain embodiments, a core may include a pharmaceutical agent comprising a lipid and/or a protein. Other materials are also possible.

[00051] If a polymer is present in the core, the polymer may be present in the core in any suitable amount, *e.g.*, less than or equal to about 100 wt%, less than or equal to about 90 wt%, less than or equal to about 80 wt%, less than or equal to about 70 wt%, less than or equal to about 60 wt%, less than or equal to about 50 wt%, less than or equal to about 40 wt%, less than or equal to about 30 wt%, less than or equal to about 20 wt%, less than or equal to about 10 wt%, less than or equal to about 5 wt%, less than or equal to about 2 wt%, or less than or equal to about 1 wt%. In some cases, the polymer may be present in an amount of at least about 1 wt%, at least about 5 wt%, at least about 10 wt%, at least about 20 wt%, at least about 30 wt%, at least about 40 wt%, at least about 50 wt%, at least about 75 wt%, at least about 90 wt%, or at least about 99 wt% in the core. Combinations of the above-referenced ranges are also possible (*e.g.*, present in an amount of at least about 1 wt% and less than or equal to about 20wt%). Other ranges are also possible. In one set of embodiments, the core is formed is substantially free of a polymeric component.

[00052] The core may have any suitable shape and/or size. For instance, the core may be substantially spherical, non-spherical, oval, rod-shaped, pyramidal, cube-like, disk-shaped, wire-like, or irregularly shaped. The core may have a largest or smallest cross-sectional dimension of, for example, less than or equal to about 10 μm , less than or equal to about 5 μm , less than or equal to about 1 μm , less than or equal to about 800 nm, less than or equal to about 700 nm, less than or equal to about 500 nm, less than or equal to 400 nm, less than or equal to 300 nm, less than or equal to about 200 nm, less than or equal to about 100 nm, less than or equal to about 75 nm, less than or equal to about 50 nm, less than or equal to about 40 nm, less than or equal to about 35 nm, less than or equal to about 30 nm, less than or equal to about 25 nm, less than or equal to about 20 nm, less than or equal to about 15 nm, or less than or equal to about 5 nm. In some cases, the core may have a largest or smallest cross-sectional dimension of, for example, at least about 5 nm, at least about 20 nm, at least about 50 nm, at least about 100 nm, at least about 200 nm, at least about 300 nm, at least about 400 nm, at least about 500 nm, at least about 1 μm , or at least about 5 μm . Combinations of the above-referenced ranges are also possible (*e.g.*, a largest or smallest cross-sectional dimension of at least about 50 nm and less than about 500 nm). Other ranges are also possible. In some embodiments, the sizes of the cores formed by a process described herein have a Gaussian-type distribution. Unless indicated otherwise, the measurements of particle/core sizes herein refer to the smallest cross-sectional dimension.

[00053] Those of ordinary skill in the art are familiar with techniques to determine sizes (*e.g.*, smallest or largest cross-sectional dimensions) of particles. Examples of suitable techniques include (DLS), transmission electron microscopy, scanning electron microscopy, electroresistance counting and laser diffraction. Other suitable techniques are known to those of ordinary skill in the art. Although many methods for determining sizes of particles are known, the sizes described herein (*e.g.*, average particle sizes, thicknesses) refer to ones measured by dynamic light scattering.

Methods of Forming Core Particles and Coated Particles

[00054] The core particles described herein may be formed by any suitable method. Suitable methods may include, for example, so called top-down techniques, *i.e.* techniques based on size reduction of relatively large particles into smaller particles (*e.g.*, milling or

homogenization) or so called bottom-up techniques, *i.e.* techniques based on the growth of particles from smaller particles or individual molecules (*e.g.*, precipitation or spray-freezing into liquid).

[00055] In some embodiments, core particles may be coated with a coating. For example, core particles may be provided or formed in a first step, and then the particles may be coated in a second step to form coated particles. In other embodiments, core particles may be formed and coated substantially simultaneously (*e.g.*, in a single step). Examples of these and other methods are provided below.

[00056] In some embodiments, the coated particles described herein are formed by a method that involves using a formulation process, a milling process, and/or a dilution process. In certain embodiments, a method of forming the particles includes a milling process, optionally with a formulation process and/or a dilution process. A formulation process may be used to form a suspension or solution comprising a core material, one or more surface-altering agents, and other components, such as solvents, tonicity agents, chelating agents, salts, anti-microbial agents and/or buffers (*e.g.*, a sodium citrate and citric acid buffer), each of which is as described herein. The formulation process may be performed using a formulation vessel. The core material and other components may be added into the formulation vessel at the same time or different times. A mixture of the core material and/or one or more other components may be stirred and/or shaken, or otherwise agitated in the vessel to facilitate suspending and/or dissolving the components. The temperature and/or pressure of the fluids containing the core material, the other components, and/or the mixture may also be individually increased or decreased to facilitate the suspending and/or dissolving processes. In some embodiments, the core material and other components are processed as described herein in the formulation vessel under an inert atmosphere (*e.g.*, nitrogen or argon) and/or protected from light. The suspension or solution obtained from the formulation vessel may be subsequently subject to a milling process which may be followed by a dilution process.

[00057] In some embodiments involving a core comprising a solid material, a milling process may be used to reduce the size of the solid material to form particles in the micrometer to nanometer size range. The milling process may be performed using a mill or other suitable apparatus. Dry and wet milling processes such as jet milling, cryo-milling, ball

milling, sonication, media milling, and homogenization are known and can be used in methods described herein. Generally, in a wet milling process, a suspension of the material to be used as the core is agitated with or without excipients to reduce particle size. Dry milling is a process wherein the material to be used as the core is mixed with milling media with or without excipients to reduce particle size. In a cryo-milling process, a suspension of the material to be used as the core is mixed with milling media with or without excipients under cooled temperatures.

[00058] After milling or other suitable process for reducing the size of a core material, a dilution process may be used to form and/or modify coated particles from a suspension. The coated particles may comprise a core material, one or more surface-altering agents, and other components, such as solvents, tonicity agents, chelating agents, salts anti-microbial agents, and buffers (*e.g.*, a sodium citrate and citric acid buffer). A dilution process may be used to achieve a target dosing concentration by diluting a solution or suspension of particles that were coated during a milling step, with or without the additional of surface-altering agents and/or other components. In certain embodiments, a dilution process may be used to exchange a first surface-altering agent with a second surface-altering agent from a surface of a particle as described herein.

[00059] The dilution process may be performed using a product vessel or any other suitable apparatus. In certain embodiments, the suspension is diluted, *i.e.*, mixed or otherwise processed with a diluent, in the product vessel. The diluent may contain solvents, surface-altering agents, tonicity agents, chelating agents, salts, or anti-microbial agents, or a combination thereof, as described herein. The suspension and the diluent may be added into the product vessel at the same time or different times. In certain embodiments when the suspension is obtained from a milling process involving milling media, the milling media may be separated from the suspension before the suspension is added into the product vessel. The suspension, the diluent, or the mixture of the suspension and the diluent may be stirred and/or shaken, or otherwise agitated, to form the coated particles described herein. The temperature and/or pressure of the suspension, the diluent, or the mixture may also be individually increased or decreased to form the coated particles. In some embodiments, the suspension and the diluent are processed in the product vessel under an inert atmosphere (*e.g.*, nitrogen or argon) and/or protected from light.

[00060] In some embodiments, the core particles described herein may be produced by milling of a solid material (*e.g.*, a pharmaceutical agent) in the presence of one or more stabilizers/surface-altering agents. Small particles of a solid material may require the presence of one or more stabilizers/surface-altering agents, particularly on the surface of the particles, in order to stabilize a suspension of particles without agglomeration or aggregation in a liquid solution. In some such embodiments, the stabilizer may act as a surface-altering agent, forming a coating on the particle.

[00061] As described herein, in some embodiments, a method of forming a core particle involves choosing a stabilizer/surface-altering agent that is suitable for both milling and for forming a coating on the particle and rendering the particle mucus penetrating. For example, as described in more detail below, it has been demonstrated that 200-500 nm nanoparticles of a model compound pyrene produced by milling of pyrene in the presence of certain PVA polymers resulted in particles that can penetrate physiological mucus samples at the same rate as well-established polymer-based MPP. Interestingly, it was observed that only a subset of PVA polymers tested fit the criteria of being suitable for both milling and for forming a coating on the particle that renders the particle mucus penetrating, as described in more detail below.

[00062] In a wet milling process, milling can be performed in a dispersion (*e.g.*, an aqueous dispersion) containing one or more stabilizers (*e.g.*, a surface-altering agent), a grinding medium, a solid to be milled (*e.g.*, a solid pharmaceutical agent), and a solvent. Any suitable amount of a stabilizer/surface-altering agent can be included in the solvent. In some embodiments, a stabilizer/surface-altering agent may be present in the solvent in an amount of at least about 0.001 % (wt% or % weight to volume (w:v)), at least about 0.01 %, at least about 0.1 %, at least about 0.5 %, at least about 1 %, at least about 2 %, at least about 3 %, at least about 4 %, at least about 5 %, at least about 6 %, at least about 7 %, at least about 8 %, at least about 10 %, at least about 12 %, at least about 15 %, at least about 20 %, at least about 40 %, at least about 60 %, or at least about 80 % of the solvent. In some cases, the stabilizer/surface-altering agent may be present in the solvent in an amount of about 100 % (*e.g.*, in an instance where the stabilizer/surface-altering agent is the solvent). In other embodiments, the stabilizer/surface-altering agent may be present in the solvent in an amount of less than or equal to about 100 %, less than or equal to about 80 %, less than or equal to

about 60 %, less than or equal to about 40 %, less than or equal to about 20 %, less than or equal to about 15 %, less than or equal to about 12 %, less than or equal to about 10 %, less than or equal to about 8 %, less than or equal to about 7 %, less than or equal to about 6 %, less than or equal to about 5 %, less than or equal to about 4 %, less than or equal to about 3 %, less than or equal to about 2 %, or less than or equal to about 1 % of the solvent.

Combinations of the above-referenced ranges are also possible (*e.g.*, an amount of less than or equal to about 5 % and at least about 1 % of the solvent). Other ranges are also possible. The particular range chosen may influence factors that may affect the ability of the particles to penetrate mucus such as the stability of the coating of the stabilizer/surface-altering agent on the particle surface, the average thickness of the coating of the stabilizer/surface-altering agent on the particles, the orientation of the stabilizer/surface-altering agent on the particles, the density of the stabilizer/surface altering agent on the particles, stabilizer:drug ratio, drug concentration, the size and polydispersity of the particles formed, and the morphology of the particles formed.

[00063] The pharmaceutical agent (or salt thereof) may be present in the solvent in any suitable amount. In some embodiments, the pharmaceutical agent (or salt thereof) is present in an amount of at least about 0.001 % (wt% or % weight to volume (w:v)), at least about 0.01 %, at least about 0.1 %, at least about 0.5 %, at least about 1 %, at least about 2 %, at least about 3 %, at least about 4 %, at least about 5 %, at least about 6 %, at least about 7 %, at least about 8 %, at least about 10 %, at least about 12 %, at least about 15 %, at least about 20 %, at least about 40 %, at least about 60 %, or at least about 80 % of the solvent. In some cases, the pharmaceutical agent (or salt thereof) may be present in the solvent in an amount of less than or equal to about 100%, less than or equal to about 90%, less than or equal to about 80 %, less than or equal to about 60 %, less than or equal to about 40 %, less than or equal to about 20 %, less than or equal to about 15 %, less than or equal to about 12 %, less than or equal to about 10 %, less than or equal to about 8 %, less than or equal to about 7 %, less than or equal to about 6 %, less than or equal to about 5 %, less than or equal to about 4 %, less than or equal to about 3 %, less than or equal to about 2 %, or less than or equal to about 1 % of the solvent. Combinations of the above-referenced ranges are also possible (*e.g.*, an amount of less than or equal to about 20 % and at least about 1 % of the solvent). In some embodiments, the pharmaceutical agent is present in the above ranges but in w:v

[00064] The ratio of stabilizer/surface-altering agent to pharmaceutical agent (or salt thereof) in a solvent may also vary. In some embodiments, the ratio of stabilizer/surface-altering agent to pharmaceutical agent (or salt thereof) may be at least 0.001:1 (weight ratio, molar ratio, or w:v ratio), at least 0.01:1, at least 0.01:1, at least 1:1, at least 2:1, at least 3:1, at least 5:1, at least 10:1, at least 25:1, at least 50:1, at least 100:1, or at least 500:1. In some cases, the ratio of stabilizer/surface-altering agent to pharmaceutical agent (or salt thereof) may be less than or equal to 1000:1 (weight ratio or molar ratio), less than or equal to 500:1, less than or equal to 100:1, less than or equal to 75:1, less than or equal to 50:1, less than or equal to 25:1, less than or equal to 10:1, less than or equal to 5:1, less than or equal to 3:1, less than or equal to 2:1, less than or equal to 1:1, or less than or equal to 0.1:1.

Combinations of the above-referenced ranges are possible (*e.g.*, a ratio of at least 5:1 and less than or equal to 50:1). Other ranges are also possible.

[00065] Stabilizers/surface-altering agents may be, for example, polymers or surfactants. Examples of polymers are those suitable for use in coatings, as described in more detail below. Non-limiting examples of surfactants that are suitable for use in coatings as surface-altering agents include L- α -phosphatidylcholine (PC), 1,2-dipalmitoylphosphatidylcholine (DPPC), oleic acid, sorbitan trioleate, sorbitan mono-oleate, sorbitan monolaurate, polyoxyethylene sorbitan monolaurate, polyoxyethylene sorbitan monooleate, natural lecithin, oleyl polyoxyethylene ether, stearyl polyoxyethylene ether, lauryl polyoxyethylene ether, block copolymers of oxyethylene and oxypropylene, synthetic lecithin, diethylene glycol dioleate, tetrahydrofurfuryl oleate, ethyl oleate, isopropyl myristate, glyceryl monooleate, glyceryl monostearate, glyceryl monoricinoleate, cetyl alcohol, stearyl alcohol, polyethylene glycol 400, cetyl pyridinium chloride, benzalkonium chloride, olive oil, glyceryl monolaurate, corn oil, cotton seed oil, and sunflower seed oil. Derivatives of the above-noted compounds are also possible. Combinations of the above-noted compounds and others described herein may also be used as surface-altering agents in the inventive particles. As described herein, in some embodiments a surface-altering agent may act as a stabilizer, a surfactant, and/or an emulsifier. In some embodiments, the surface altering agent may aid particle transport in mucus.

[00066] It should be appreciated that while in some embodiments the stabilizer/surface-altering agent used for milling forms a coating on a particle surface, which coating renders

particle mucus penetrating, in other embodiments, the stabilizer/surface-altering agent may be exchanged with one or more other stabilizers/surface-altering agents after the particle has been formed. For example, in one set of methods, a first stabilizer/surface-altering agent may be used during a milling process and may coat a surface of a core particle, and then all or portions of the first stabilizer/surface-altering agent may be exchanged with a second stabilizer/surface-altering agent to coat all or portions of the core particle surface. In some cases, the second stabilizer/surface-altering agent may render the particle mucus penetrating more than the first stabilizer/surface-altering agent. In some embodiments, a core particle having a coating including multiple surface-altering agents may be formed.

[00067] Any suitable grinding medium can be used for milling. In some embodiments, a ceramic and/or polymeric material and/or a metal can be used. Examples of suitable materials may include zirconium oxide, silicon carbide, silicon oxide, silicon nitride, zirconium silicate, yttrium oxide, glass, alumina, alpha-alumina, aluminum oxide, polystyrene, poly(methyl methacrylate), titanium, steel. A grinding medium may have any suitable size. For example, the grinding medium may have an average diameter of at least about 0.1 mm, at least about 0.2 mm, at least about 0.5 mm, at least about 0.8 mm, at least about 1 mm, at least about 2 mm, or at least about 5 mm. In some cases, the grinding medium may have an average diameter of less than or equal to about 5 mm, less than or equal to about 2 mm, less than or equal to about 1 mm, less than or equal to about 0.8, less than or equal to about 0.5 mm, or less than or equal to about 0.2 mm. Combinations of the above-referenced ranges are also possible (*e.g.*, an average diameter of at least about 0.5 millimeters and less than or equal to about 1 mm). Other ranges are also possible.

[00068] Any suitable solvent may be used for milling. The choice of solvent may depend on factors such as the solid material (*e.g.*, pharmaceutical agent) being milled, the particular type of stabilizer/surface-altering agent being used (*e.g.*, one that may render the particle mucus penetrating), the grinding material be used, among other factors. Suitable solvents may be ones that do not substantially dissolve the solid material or the grinding material, but dissolve the stabilizer/surface-altering agent to a suitable degree. Non-limiting examples of solvents may include water, buffered solutions, other aqueous solutions, alcohols (*e.g.*, ethanol, methanol, butanol), and mixtures thereof that may optionally include other components such as pharmaceutical excipients, polymers, pharmaceutical agents, salts,

preservative agents, viscosity modifiers, tonicity modifier, taste masking agents, antioxidants, pH modifier, and other pharmaceutical excipients. In other embodiments, an organic solvent can be used. A pharmaceutical agent may have any suitable solubility in these or other solvents, such as a solubility in one or more of the ranges described above for aqueous solubility or for solubility in a coating solution.

[00069] In other embodiments, core particles may be formed by an emulsification technique (emulsification). Generally, emulsification techniques may involve dissolving or dispersing a material to be used as the core in a solvent; this solution or dispersion is then emulsified in a second immiscible solvent, thereby forming a plurality of particles comprising the material. Suitable emulsification techniques may include formation of oil-in-water emulsions, water-in-oil emulsions, water-oil-water emulsions, oil-water-oil emulsions, solid-in-oil-in-water emulsions, and solid-in-water-in-oil emulsions, *etc.*, with or without subsequent solvent removal, for example, by evaporation or extraction. Emulsification techniques are versatile and may be useful for preparing core particles comprising pharmaceutical agents having a relatively low aqueous solubility as well as pharmaceutical agents having a relatively high aqueous solubility.

[00070] In some embodiments, the core particles described herein may be produced by emulsification in the presence of one or more stabilizers. In some such embodiments, the stabilizer may act as a surface-altering agent, forming a coating on the particle (*i.e.*, the emulsification and coating steps may be performed substantially simultaneously).

[00071] In some embodiments, a method of forming a core particle by emulsification involves choosing a stabilizer that is suitable for both emulsification and for forming a coating on the particle and rendering the particle mucus penetrating. For example, as described in more detail below, it has been demonstrated that 200-500 nm nanoparticles of a model polymer PLA produced by emulsification in the presence of certain PVA polymers resulted in particles that can penetrate physiological mucus samples at the same rate as well-established polymer-based MPP. Interestingly, it was observed that only a subset of PVA polymers tested fit the criteria of being suitable for both emulsification and for forming a coating on the particle that renders the particle mucus penetrating, as described in more detail below.

[00072] In other embodiments, the particles are first formed using an emulsification technique, following by coating of the particles with a surface-altering agent.

[00073] Any suitable solvent and solvent combinations can be used for emulsification. Some examples of solvents which can serve as oil phase are organic solvents such as chloroform, dichloromethane, ethyl acetate, ethyl ether, petroleum ether (hexane, heptane), and oils such as peanut oil, cottonseed oil; safflower oil; sesame oil; olive oil; corn oil; soybean oil, and silicone oil. Some examples of solvents which can serve as water phase are water and aqueous buffers. Other solvents are also possible.

[00074] In other embodiments, core particles may be formed by a precipitation technique. Precipitation techniques (*e.g.*, microprecipitation techniques, nanoprecipitation techniques, crystallization techniques, controlled crystallization techniques) may involve forming a first solution comprising the material to be used as the core (*e.g.*, a pharmaceutical agent) and a solvent, wherein the material is substantially soluble in the solvent. The solution may be added to a second solution comprising another solvent in which the material is substantially insoluble (*i.e.*, an anti-solvent), thereby forming a plurality of particles comprising the material. In some cases, one or more surface-altering agents, surfactants, materials, and/or bioactive agents may be present in the first and/or second solutions. A coating may be formed during the process of precipitating the core (*e.g.*, the precipitating and coating steps may be performed substantially simultaneously). In other embodiments, the particles are first formed using a precipitation technique, following by coating of the particles with a surface-altering agent.

[00075] In some embodiments, a precipitation technique may be used to form polymeric core particles with or without a pharmaceutical agent. Generally, a precipitation technique involves dissolving the polymer to be used as the core in a solvent (with or without a pharmaceutical agent present), and the solution is then added to a miscible anti-solvent (with or without excipients present) to form the core particle. In some embodiments, this technique may be useful for preparing, for example, polymeric core particles comprising pharmaceutical agents that are slightly soluble (1-10mg/L), very slightly soluble (0.1-1 mg/mL) or practically insoluble (<0.1 mg/mL) in aqueous solutions (*e.g.*, agents having a relatively low aqueous solubility).

[00076] Any suitable solvent can be used for precipitation. In some embodiments, a suitable solvent for precipitation may include, for example, acetone, acetonitrile, dimethylformamide, dimethylsulfoxide, N-methyl-2-pyrrolidone, 2-pyrrolidone, tetrahydrofuran. Other organic solvents and non-organic solvents can also be used.

[00077] Any suitable anti-solvent can be used for precipitation, including the solvents described herein that may be used for milling. In one set of embodiments, an aqueous solution is used (*e.g.*, water, buffered solutions, other aqueous solutions, and alcohols such as ethanol, methanol, butanol), and mixtures thereof that may optionally include other components such as pharmaceutical excipients, polymers, and pharmaceutical agents.

[00078] Stabilizers/surface-altering agents for emulsification and precipitation may be polymers or surfactants, including the stabilizers/surface-altering agents described herein that may be used for milling.

[00079] Non-limiting examples of suitable polymers suitable for forming all or portions of a core by emulsification or precipitation may include polyamines, polyethers, polyamides, polyesters, polycarbamates, polyureas, polycarbonates, polystyrenes, polyimides, polysulfones, polyurethanes, polyacetylenes, polyethylenes, polyethyleneimines, polyisocyanates, polyacrylates, polymethacrylates, polyacrylonitriles, polyarylates, polypeptides, polynucleotides, and polysaccharides. Non-limiting examples of specific polymers include poly(caprolactone) (PCL), ethylene vinyl acetate polymer (EVA), poly(lactic acid) (PLA), poly(L-lactic acid) (PLLA), poly(glycolic acid) (PGA), poly(lactic acid-co-glycolic acid) (PLGA), poly(L-lactic acid-co-glycolic acid) (PLLGA), poly(D,L-lactide) (PDLA), poly(L-lactide) (PLLA), poly(D,L-lactide-co-caprolactone), poly(D,L-lactide-co-caprolactone-co-glycolide), poly(D,L-lactide-co-PEO-co-D,L-lactide), poly(D,L-lactide-co-PPO-co-D,L-lactide), polyalkyl cyanoacrylate, polyurethane, poly-L-lysine (PLL), hydroxypropyl methacrylate (HPMA), poly(ethylene glycol), poly-L-glutamic acid, poly(hydroxy acids), polyanhydrides, polyorthoesters, poly(ester amides), polyamides, poly(ester ethers), polycarbonates, polyalkylenes such as polyethylene and polypropylene, polyalkylene glycols such as poly(ethylene glycol) (PEG), polyalkylene oxides (PEO), polyalkylene terephthalates such as poly(ethylene terephthalate), polyvinyl alcohols (PVA), polyvinyl ethers, polyvinyl esters such as poly(vinyl acetate), polyvinyl halides such as poly(vinyl chloride) (PVC), polyvinylpyrrolidone, polysiloxanes, polystyrene (PS),

polyurethanes, derivatized celluloses such as alkyl celluloses, hydroxyalkyl celluloses, cellulose ethers, cellulose esters, nitro celluloses, hydroxypropylcellulose, carboxymethylcellulose, polymers of acrylic acids, such as poly(methyl(meth)acrylate) (PMMA), poly(ethyl(meth)acrylate), poly(butyl(meth)acrylate), poly(isobutyl(meth)acrylate), poly(hexyl(meth)acrylate), poly(isodecyl(meth)acrylate), poly(lauryl(meth)acrylate), poly(phenyl(meth)acrylate), poly(methyl acrylate), poly(isopropyl acrylate), poly(isobutyl acrylate), poly(octadecyl acrylate) (jointly referred to herein as “polyacrylic acids”), and copolymers and mixtures thereof, polydioxanone and its copolymers, polyhydroxyalkanoates, polypropylene fumarate), polyoxymethylene, poloxamers, poly(ortho)esters, poly(butyric acid), poly(valeric acid), poly(lactide-co-caprolactone), and trimethylene carbonate, polyvinylpyrrolidone, bovine serum albumin, human serum albumin, collagen, DNA, RNA, carboxymethyl cellulose, chitosan, dextran.

[00080] In some embodiments, a precipitation technique may be used to form particles comprised predominantly of a pharmaceutical agent (*e.g.*, nanocrystals). Generally, such a precipitation technique involves dissolving the pharmaceutical agent to be used as the core in a solvent, which is then added to a miscible anti-solvent with or without excipients to form the core particle. In some embodiments, this technique may be useful for preparing, for example, particles of pharmaceutical agents that are slightly soluble (1-10mg/L), very slightly soluble (0.1-1 mg/mL) or practically insoluble (<0.1 mg/mL) in aqueous solutions (*e.g.*, agents having a relatively low aqueous solubility).

[00081] In some embodiments, precipitation by salt (or complex) formation may be used to form particles (*e.g.*, nanocrystals) of a salt of a pharmaceutical agent. Generally, precipitation by salt formation involves dissolving the material to be used as the core in a solvent with or without excipients followed by addition of a counter-ion or a complexing agent, which forms an insoluble salt or a complex with the pharmaceutical agent to form the core particle. This technique may be useful for preparing particles of pharmaceutical agents that are soluble in aqueous solutions (*e.g.*, agents having a relatively high aqueous solubility). In some embodiments, pharmaceutical agents having one or more charged or ionizable groups can interact with a counter-ion (*e.g.*, a cation or an anion) to form a salt complex.

[00082] A variety of counter-ions can be used to form salt complexes, including metals (*e.g.*, alkali metals, alkali earth metals and transition metals). Non-limiting examples of

cationic counter-ions include zinc, calcium, aluminum, zinc, barium, and magnesium. Non-limiting examples of anionic counter-ions include phosphate, carbonate, and fatty acids. Counter-ions may be, for example, monovalent, divalent, or trivalent. Other counter-ions are known in the art and can be used in the embodiments described herein. Other ionic and non-ionic complexing agents are also possible.

[00083] A variety of different acids may be used in a precipitation process. In some embodiments, a suitable acid may include deconoic acid, hexanoic acid, mucic acid, octanoic acid. In other embodiments, a suitable acid may include acetic acid, adipic acid, L-ascorbic acid, L-aspartic acid, capric acid (decanoic acid), carbonic acid, citric acid, fumaric acid, galactaric acid, D-glucoheptonic acid, D-gluconic acid, D-glucuronic acid, glutamic acid, glutaric acid, glycerophosphoric acid, glycolic acid, hippuric acid, hydrochloric acid, DL-lactic acid, lauric acid, maleic acid, (-)-L-malic acid, palmitic acid, phosphoric acid, sebacic acid, stearic acid, succinic acid, sulfuric acid, (+)-L-tartaric acid, or thiocyanic acid. In other embodiments, a suitable acid may include alginic acid, benzenesulfonic acid, benzoic acid, (+)-camphoric acid, caprylic acid (octanoic acid), cyclamic acid, dodecylsulfuric acid, ethane-1,2-disulfonic acid, ethanesulfonic acid, ethanesulfonic acid, 2-hydroxy-, gentisic acid, glutaric acid, 2-oxo-, isobutyric acid, lactobionic acid, malonic acid, methanesulfonic acid, naphthalene-1,5-disulfonic acid, naphthalene-2-sulfonic acid, 2-naphthoic acid, 1-hydroxy-, nicotinic acid, oleic acid, orotic acid, oxalic acid, pamoic acid, (embonic acid), propionic acid, (-)-L-pyroglutamic acid, or *p*-toluenesulfonic acid. In yet other embodiments, a suitable acid may include acetic acid, 2,2-dichloro-, benzoic acid, 4-acetamido-, (+)-camphor-10-sulfonic acid, caproic acid (hexanoic acid), cinnamic acid, formic acid, hydrobromic acid, DL-mandelic acid, nitric acid, salicylic acid, salicylic acid, 4-amino-, or undecylenic acid (undec-10-enoic acid). Mixtures of one or more such acids can also be used.

[00084] A variety of different bases may be used in a precipitation process. In some embodiments, a suitable base includes ammonia, L-arginine, calcium hydroxide, choline, glucamine, *N*-methyl-, lysine, magnesium hydroxide, potassium hydroxide, or sodium hydroxide. In other embodiments, a suitable base may include benethamine, benzathine, betaine, deanol, diethylamine, ethanol, 2-(diethylamino)-, hydrabamine, morpholine, 4-(2-hydroxyethyl)- morpholine, pyrrolidine, 1-(2-hydroxyethyl)-, or tromethamine. In other

embodiments, a suitable base may include diethanolamine (2,2'-iminobis(ethanol)), ethanolamine (2-aminoethanol), ethylenediamine, 1*H*-imidazole, piperazine, triethanolamine (2,2',2''-nitrilotris(ethanol)), or zinc hydroxide. Mixtures of one or more such bases can also be used.

[00085] Any suitable solvent can be used for precipitation by salt formation, including the solvents described herein that may be used for milling. In one set of embodiments, an aqueous solution is used (*e.g.*, water, buffered solutions, other aqueous solutions, alcohols (*e.g.*, ethanol, methanol, butanol), and mixtures thereof that may optionally include other components such as pharmaceutical excipients, polymers, and pharmaceutical agents.

[00086] In the precipitation process, the salt may have a lower aqueous solubility (or solubility in the solvent containing the salt) than the pharmaceutical agent in the non-salt form. The aqueous solubility (or solubility in the solvent) of the salt may be, for example, less than or equal to about 5 mg/mL, less than or equal to about 2 mg/mL, less than or equal to about 1 mg/mL, less than or equal to about 0.5 mg/mL, less than or equal to about 0.1 mg/mL, less than or equal to about 0.05 mg/mL, or less than or equal to about 0.01 mg/mL, less than or equal to about 1 µg/mL, less than or equal to about 0.1 µg/mL, less than or equal to about 0.01 µg/mL, less than or equal to about 1 ng/mL, less than or equal to about 0.1 ng/mL, or less than or equal to about 0.01 ng/mL at 25 °C. In some embodiments, the salt may have an aqueous solubility (or solubility in the solvent) of at least about 1 pg/mL, at least about 10 pg/mL, at least about 0.1 ng/mL, at least about 1 ng/mL, at least about 10 ng/mL, at least about 0.1 µg/mL, at least about 1 µg/mL, at least about 5 µg/mL, at least about 0.01 mg/mL, at least about 0.05 mg/mL, at least about 0.1 mg/mL, at least about 0.5 mg/mL, at least about 1.0 mg/mL, at least about 2 mg/mL. Combinations of the above-noted ranges are possible (*e.g.*, an aqueous solubility (or solubility in the solvent) of at least about 0.001 mg/mL and less than or equal to about 1 mg/mL). Other ranges are also possible. The salt may have these or other ranges of aqueous solubilities at any point throughout the pH range (*e.g.*, from pH 1 to pH 14).

[00087] In some embodiments, the solvent used for precipitation includes one or more surface-altering agents as described herein, and a coating of the one or more surface-altering agents may be formed around the particle as it precipitates out of solution. The surface-altering agent may be present in the solvent at any suitable concentration, such as a

concentration of at least about 0.001% (w/v), at least about 0.005% (w/v), at least about 0.01% (w/v), at least about 0.05% (w/v), at least about 0.1% (w/v), at least about 0.5% (w/v), at least about 1% (w/v), or at least about 5% (w/v) in the aqueous solution. In some instances, the surface-altering agent is present in the solvent at a concentration of less than or equal to about 5% (w/v), less than or equal to about 1% (w/v), less than or equal to about 0.5% (w/v), less than or equal to about 0.1% (w/v), less than or equal to about 0.05% (w/v), less than or equal to about 0.01% (w/v), or less than or equal to about 0.005% (w/v). Combinations of the above-referenced ranges are also possible (*e.g.*, a concentration of at least about 0.01 (w/v) and less than or equal to about 1% (w/v). Other ranges are also possible.

[00088] Another exemplary method of forming a core particle includes a freeze-drying technique. In this technique, a pharmaceutical agent or salt thereof may be dissolved in an aqueous solution, optionally containing a surface-altering agent. A counter-ion may be added to the solution, and the solution may be immediately flash frozen and freeze dried. Dry powder can be reconstituted in a suitable solvent (*e.g.*, an aqueous solution such as water) at a desired concentration.

[00089] A counter-ion may be added to a solvent for freeze-drying in any suitable range. In some cases, the ratio of counter-ion to pharmaceutical agent (*e.g.*, salt) may be at least 0.1:1 (weight ratio or molar ratio), at least 1:1, at least 2:1, at least 3:1, at least 5:1, at least 10:1, at least 25:1, at least 50:1, or at least 100:1. In some cases, the ratio of counter-ion to pharmaceutical agent (*e.g.*, salt) may be less than or equal to 100:1 (weight ratio or molar ratio), less than or equal to 75:1, less than or equal to 50:1, less than or equal to 25:1, less than or equal to 10:1, less than or equal to 5:1, less than or equal to 3:1, less than or equal to 2:1, less than or equal to 1:1, or less than or equal to 0.1:1. Combinations of the above-referenced ranges are possible (*e.g.*, a ratio of at least 5:1 and less than or equal to 50:1). Other ranges are also possible.

[00090] If the surface-altering agent is present in the solvent prior to freeze drying, it may be present at any suitable concentration, such as a concentration of at least about 0.001% (w/v), at least about 0.005% (w/v), at least about 0.01% (w/v), at least about 0.05% (w/v), at least about 0.1% (w/v), at least about 0.5% (w/v), at least about 1% (w/v), or at least about 5% (w/v) in the aqueous solution. In some instances, the surface-altering agent is present in

the solvent at a concentration of less than or equal to about 5% (w/v), less than or equal to about 1% (w/v), less than or equal to about 0.5% (w/v), less than or equal to about 0.1% (w/v), less than or equal to about 0.05% (w/v), less than or equal to about 0.01% (w/v), or less than or equal to about 0.005% (w/v). Combinations of the above-referenced ranges are also possible (*e.g.*, a concentration of at least about 0.01% (w/v) and less than or equal to about 1% (w/v). Other ranges are also possible.

[00091] The concentration of surface-altering agent present in the solvent may be above or below the critical micelle concentration (CMC) of the surface-altering agent, depending on the particular surface-altering agent used. In other embodiments, stable particles can be formed by adding excess counter-ion to a solution containing a pharmaceutical agent. The precipitate can then be washed by various methods such as centrifugation. The resultant slurry may be sonicated. One or more surface-altering agents may be added to stabilize the resultant particles.

[00092] Other methods of forming core particles are also possible. Techniques for forming core particles may include, for example, coacervation-phase separation; melt dispersion; interfacial deposition; in situ polymerization; self-assembly of macromolecules (*e.g.*, formation of polyelectrolyte complexes or polyelectrolyte-surfactant complexes); spray-drying and spray-congealing; electro-spray; air suspension coating; pan and spray coating; freeze-drying, air drying, vacuum drying, fluidized-bed drying; precipitation (*e.g.*, nanoprecipitation, microprecipitation); critical fluid extraction; and lithographic approaches (*e.g.*, soft lithography, step and flash imprint lithography, interference lithography, photolithography).

[00093] Combinations of the methods described herein and other methods are also possible. For example, in some embodiments, a core of a pharmaceutical agent is first formed by precipitation, and then the size of the core is further reduced by a milling process.

[00094] Following formation of particles of a pharmaceutical agent, the particles may be optionally exposed to a solution comprising a (second) surface-altering agent that may associate with and/or coat the particles. In embodiments in which the pharmaceutical agent already includes a coating of a first surface-altering agent, all or portions of a second surface-altering agent may be exchanged with a second stabilizer/surface-altering agent to coat all or portions of the particle surface. In some cases, the second surface-altering agent may render

the particle mucus penetrating more than the first surface-altering agent. In other embodiments, a particle having a coating including multiple surface-altering agents may be formed (*e.g.*, in a single layer or in multiple layers). In other embodiments, a particle having multiple coatings (*e.g.*, each coating optionally comprising different surface-altering agents) may be formed. In some cases, the coating is in the form of a monolayer of a surface-altering agent. Other configurations are also possible.

[00095] In any of the methods described herein, a particle may be coated with a surface-altering agent by incubating the particle in a solution with the surface-altering agent for a period of at least about 1 minutes, at least about 2 minutes, at least about 5 min., at least about 10 min., at least about 15 min., at least about 20 min., at least about 30 min., at least about 60 min., or more. In some cases, incubation may take place for a period of less than or equal to about 10 hours, less than or equal to about 5 hours, or less than or equal to about 60 min. Combinations of the above referenced ranges are also possible (*e.g.*, an incubation period of less than or equal to 60 min. and at least about 2 min.).

Particle Coatings

[00096] As shown in the embodiment illustrated in FIG. 1, core 16 may be surrounded by coating 20 comprising one or more surface-altering agents. In some embodiments, the coating is formed of one or more surface-altering agents or other molecules disposed on the surface of the core. The particular chemical makeup and/or components of the coating and surface-altering agent(s) can be chosen so as to impart certain functionality to the particles, such as enhanced transport through mucosal barriers.

[00097] It should be understood that a coating which surrounds a core need not completely surround the core, although such embodiments may be possible. For example, the coating may surround at least about 10%, at least about 30%, at least about 50%, at least about 60%, at least about 70%, at least about 80%, at least about 90%, or at least about 99% of the surface area of a core. In some cases, the coating substantially surrounds a core. In other cases, the coating completely surrounds a core. In other embodiments, a coating surrounds less than or equal to about 100%, less than or equal to about 90%, less than or equal to about 80%, less than or equal to about 70%, less than or equal to about 60%, or less than or equal to about 50% of the surface area of a core. Combinations of the above-referenced ranges are

also possible (*e.g.*, surrounding greater than 80% and less than 100% of the surface area of a core).

[00098] The components of the coating may be distributed evenly across a surface of the core in some cases, and unevenly in other cases. For example, the coating may include portions (*e.g.*, holes) that do not include any material in some cases. If desired, the coating may be designed to allow penetration and/or transport of certain molecules and components into or out of the coating, but may prevent penetration and/or transport of other molecules and components into or out of the coating. The ability of certain molecules to penetrate and/or be transported into and/or across a coating may depend on, for example, the packing density of the surface-altering agents forming the coating and the chemical and physical properties of the components forming the coating. As described herein, the coating may include one layer of material (*e.g.*, a monolayer), or multilayers of materials in some embodiments. A single type of surface-altering agent may be present, or multiple types of surface-altering agent.

[00099] A coating of a particle can have any suitable thickness. For example, a coating may have an average thickness of at least about 1 nm, at least about 5 nm, at least about 10 nm, at least about 30 nm, at least about 50 nm, at least about 100 nm, at least about 200 nm, at least about 500 nm, at least about 1 μm , or at least about 5 μm . In some cases, the average thickness of a coating is less than or equal to about 5 μm , less than or equal to about 1 μm , less than or equal to about 500 nm, less than or equal to about 200 nm, less than or equal to about 100 nm, less than or equal to about 50 nm, less than or equal to about 30 nm, less than or equal to about 10 nm, or less than or equal to about 5 nm. Combinations of the above-referenced ranges are also possible (*e.g.*, an average thickness of at least about 1 nm and less than or equal to about 100 nm). Other ranges are also possible. For particles having multiple coatings, each coating layer may have one of the thicknesses described above.

[000100] In some embodiments, the compositions and methods described herein may allow for the coating of a core particle with hydrophilic surface-altering agents without requiring covalent linking of the surface-altering moieties to the core surface. In some such embodiments, a core having a hydrophobic surface may be coated with a polymer described herein, thereby causing a plurality of surface-altering moieties to be on the core surface without substantially altering the characteristics of the core itself. For example, the surface

altering agent may be adsorbed to the outer surface of the core particle. In other embodiments, however, a surface-altering agent is covalently linked to a core particle. In certain embodiments in which the surface-altering agent is adsorbed onto a surface of a core, the surface-altering agent may be in equilibrium with other molecules of the surface-altering agent in solution, optionally with other components (e.g., in a composition/formulation). In some cases, the adsorbed surface-altering agent may be present on the surface of the core at a density described herein. The density may be an average density as the surface altering agent is in equilibrium with other components in solution.

[000101] The coating and/or surface-altering agent of a particle described herein may comprise any suitable material, such as a hydrophobic material, a hydrophilic material, and/or an amphiphilic material. In some embodiments, the coating includes a polymer. In certain embodiments, the polymer is a synthetic polymer (*i.e.*, a polymer not produced in nature). In other embodiments, the polymer is a natural polymer (*e.g.*, a protein, polysaccharide, rubber). In certain embodiments, the polymer is a surface active polymer. In certain embodiments, the polymer is a non-ionic polymer. In certain embodiments, the polymer is a linear, synthetic non-ionic polymer. In certain embodiments, the polymer is a non-ionic block copolymer. In some embodiments, the polymer may be a copolymer, *e.g.*, where one repeat unit is relatively hydrophobic and another repeat unit is relatively hydrophilic. The copolymer may be, for example, a diblock, triblock, alternating, or random copolymer. The polymer may be charged or uncharged.

[000102] In some embodiments, a coating comprises a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer. For example, in certain embodiments, the polymer may include poly(vinyl alcohol), a partially hydrolyzed poly(vinyl acetate) or a copolymer of vinyl alcohol and vinyl acetate. In certain embodiments, a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer may include poly(ethylene glycol)-poly(vinyl acetate)-poly(vinyl alcohol) copolymers, poly(ethylene glycol)-poly(vinyl alcohol) copolymers, poly(propylene oxide)-poly(vinyl alcohol) copolymers, and poly(vinyl alcohol)-poly(acryl amide) copolymers. Without wishing to be bound by theory, a particle including a coating comprising a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer may have reduced mucoadhesion as compared to a control particle due to, at least in part, the display of a plurality of hydroxyl groups on the particle surface.

One possible mechanism for the reduced mucoadhesion is that the hydroxyl groups alter the microenvironment of the particle, for example, by ordering water and other molecules in the particle/mucus environment. An additional or alternative possible mechanism is that the hydroxyl groups shield the adhesive domains of the mucin fibers, thereby reducing particle adhesion and speeding up particle transport.

[000103] Moreover, the ability of a particle coated with a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer to be mucus penetrating may also depend, at least in part, on the degree of hydrolysis of the polymer. In some embodiments, the hydrophobic portions of the polymer (*e.g.*, portions of the polymer that are not hydrolyzed) may allow the polymer to be adhered to the core surface (*e.g.*, in the case of the core surface being hydrophobic), thus allowing for a strong association between the core and the polymer. Surprisingly, it has been found that in some embodiments involving the surface-altering agent PVA, too high of a degree of hydrolysis does not allow for sufficient adhesion between the PVA and the core (*e.g.*, in the case of the core being hydrophobic), and thus, the particles coated with such a polymer generally do not exhibit sufficient reduced mucoadhesion. In some embodiments, too low of a degree of hydrolysis does not enhance particle transport in mucus, perhaps due to the lower amounts of hydroxyl groups available for altering the microenvironment of the particle and/or shielding the adhesive domains of the mucin fibers.

[000104] A synthetic polymer having pendant hydroxyl groups on the backbone of the polymer may have any suitable degree of hydrolysis (and, therefore, varying amounts of hydroxyl groups). The appropriate level of hydrolysis may depend on additional factors such as the molecular weight of the polymer, the composition of the core, the hydrophobicity of the core, *etc.* In some embodiments, a synthetic polymer (*e.g.*, PVA or partially hydrolyzed poly(vinyl acetate) or a copolymer of vinyl alcohol and vinyl acetate) may be at least about 30% hydrolyzed, at least about 35% hydrolyzed, at least about 40% hydrolyzed, at least about 45% hydrolyzed, at least about 50% hydrolyzed, at least about 55% hydrolyzed, at least about 60% hydrolyzed, at least about 65% hydrolyzed, at least about 70% hydrolyzed, at least about 75% hydrolyzed, at least about 80% hydrolyzed, at least about 85% hydrolyzed, at least about 87% hydrolyzed, at least about 90% hydrolyzed, at least about 95% hydrolyzed, or at least about 98% hydrolyzed. In some embodiments, the synthetic polymer may be less than or equal to about 100% hydrolyzed, less than or equal to about 98% hydrolyzed, less than or

equal to about 97% hydrolyzed, less than or equal to about 96% hydrolyzed, less than or equal to about 95% hydrolyzed, less than or equal to about 94% hydrolyzed, less than or equal to about 93% hydrolyzed, less than or equal to about 92% hydrolyzed, less than or equal to about 91% hydrolyzed, less than or equal to about 90% hydrolyzed, less than or equal to about 87% hydrolyzed, less than or equal to about 85% hydrolyzed, less than or equal to about 80% hydrolyzed, less than or equal to about 75% hydrolyzed, less than or equal to about 70% hydrolyzed, or less than or equal to about 60% hydrolyzed.

Combinations of the above-mentioned ranges are also possible (*e.g.*, a polymer that is at least about 80% hydrolyzed and less than or equal to about 95% hydrolyzed). Other ranges are also possible.

[000105] The molecular weight of a synthetic polymer described herein (*e.g.*, one having pendant hydroxyl groups on the backbone of the polymer) may be selected so as to reduce the mucoadhesion of a core and to ensure sufficient association of the polymer with the core. In certain embodiments, the molecular weight of the synthetic polymer is at least about 1 kDa, at least about 2 kDa, at least about 5 kDa, at least about 8 kDa, at least about 9 kDa, at least about 10 kDa, at least about 12 kDa, at least about 15 kDa at least about 20 kDa, at least about 25 kDa, at least about 30 kDa, at least about 40 kDa, at least about 50 kDa, at least about 60 kDa, at least about 70 kDa, at least about 80 kDa, at least about 90 kDa, at least about 100 kDa at least about 110 kDa, at least about 120 kDa, at least about 130 kDa, at least about 140 kDa, at least about 150 kDa, at least about 200 kDa, at least about 500 kDa, or at least about 1000 kDa. In some embodiments, the molecular weight of the synthetic polymer is less than or equal to about 1000 kDa, less than or equal to about 500 kDa, less than or equal to about 200 kDa, less than or equal to about 180 kDa, less than or equal to about 150 kDa, less than or equal to about 130 kDa, less than or equal to about 120 kDa, less than or equal to about 100 kDa, less than or equal to about 85 kDa, less than or equal to about 70 kDa, less than or equal to about 65 kDa, less than or equal to about 60 kDa, less than or equal to about 50 kDa, or less than or equal to about 40 kDa, less than or equal to about 30 kDa, less than or equal to about 20 kDa, less than or equal to about 15 kDa, or less than or equal to about 10 kDa. Combinations of the above-mentioned ranges are also possible (*e.g.*, a molecular weight of at least about 10 kDa and less than or equal to about 30 kDa). The

above-mentioned molecular weight ranges can also be combined with the above-mentioned hydrolysis ranges to form suitable polymers.

[000106] In some embodiments, a synthetic polymer described herein is or comprises PVA. PVA is a non-ionic polymer with surface active properties. It is a synthetic polymer typically produced through hydrolysis of poly(vinyl acetate). Partially hydrolyzed PVA is comprised of two types of repeating units: vinyl alcohol units and residual vinyl acetate units. The vinyl alcohol units are relatively hydrophilic; the vinyl acetate units are relatively hydrophobic. In some instances, the sequence distribution of vinyl alcohol units and vinyl acetate units is blocky. For example, a series of vinyl alcohol units may be followed by a series of vinyl acetate units, and followed by more vinyl alcohol units to form a polymer having a mixed block-copolymer type arrangement, with units distributed in a blocky manner. In certain embodiments, the repeat units form a copolymer, *e.g.*, a diblock, triblock, alternating, or random copolymer. Polymers other than PVA may also have these configurations of hydrophilic units and hydrophobic units.

[000107] In certain embodiments, the surface-altering agent is a PVA that is less than or equal to about 98% hydrolyzed and has a molecular weight of less than or equal to about 75 kDa, or a PVA that is less than about 95% hydrolyzed. In some embodiments, the surface-altering agent is a PVA that does not have both properties of a hydrolysis degree of greater than 95% and a molecular weight of greater than 31 kDa. In certain embodiments, such surface-altering agents may be used to coat certain pharmaceutical agents such as corticosteroids (*e.g.*, LE) and/or other compounds described herein.

[000108] In some embodiments, the hydrophilic units of a synthetic polymer described herein may be substantially present at the outer surface of the particle. For example, the hydrophilic units may form a majority of the outer surface of the coating and may help stabilize the particle in an aqueous solution containing the particle. The hydrophobic units may be substantially present in the interior of the coating and/or at the surface of the core particle, *e.g.*, to facilitate attachment of the coating to the core.

[000109] The molar fraction of the relatively hydrophilic units and the relatively hydrophobic units of a synthetic polymer may be selected so as to reduce the mucoadhesion of a core and to ensure sufficient association of the polymer with the core, respectively. As described herein, the molar fraction of the hydrophobic units of the polymer may be chosen

such that adequate association of the polymer with the core occurs, thereby increasing the likelihood that the polymer remains adhered to the core. The molar fraction of the relatively hydrophilic units to the relatively hydrophobic units of a synthetic polymer may be, for example, at least 0.5:1, at least 1:1, at least 2:1, at least 3:1, at least 5:1, at least 7:1, at least 10:1, at least 15:1, at least 20:1, at least 25:1, at least 30:1, at least 40:1, at least 50:1, at least 75:1, or at least 100:1. In some embodiments, the molar fraction of the relatively hydrophilic units to the relatively hydrophobic units of a synthetic polymer may be, for example, less than or equal to 100:1, less than or equal to 75:1, less than or equal to 50:1, less than or equal to 40:1, less than or equal to 30:1, less than or equal to 25:1, less than or equal to 20:1, less than or equal to 15:1, less than or equal to 10:1, less than or equal to 7:1, less than or equal to 5:1, less than or equal to 3:1, less than or equal to 2:1, or less than or equal to 1:1.

Combinations of the above-referenced ranges are also possible (*e.g.*, a ratio of at least 1:1 and less than or equal to 50:1). Other ranges are also possible.


[000110] The molecular weight of the PVA polymer may also be tailored to increase the effectiveness of the polymer to render particles mucus penetrating. Examples of PVA polymers having various molecular weights and degree of hydrolysis are shown in Table 1.

[000111] Table 1. Grades of PVA. The molecular weight (MW) and hydrolysis degree values were provided by the manufacturers.

PVA acronym*	MW, kDa	Hydrolysis degree, %
2K75	2	75 - 79
9K80	9 - 10	80
13K87	13 - 23	87 - 89
13K98	13 - 23	98
31K87	31 - 50	87 - 89
31K98	31 - 50	98 - 99
57K86	57 - 60	86 - 89
85K87	85 - 124	87 - 89
85K99	85 - 124	99+
95K95	95	95
105K80	104	80
130K87	130	87 - 89

*PVA acronym explanation: XXKYY, where XX stands for the PVA's lower-end molecular weight in kDa and YY stands for the PVA's lower-end hydrolysis in %.

[000112] In certain embodiments, the synthetic polymer is represented by the formula:



wherein n is an integer between 0 and 22730, inclusive; and m is an integer between 0 and 11630, inclusive. In certain embodiments, n is an integer between 25 and 20600, inclusive. In some embodiments, m is an integer between 5 and 1100, inclusive. In certain embodiments, m is an integer between 0 and 400 inclusive or between 1 and 400 inclusive. It is noted that n and m represent the total content of the vinyl alcohol and vinyl acetate repeat units in the polymer, respectively, rather than the block lengths.

[000113] The value of n may vary. In certain embodiments, n is at least 5, at least 10, at least 20, at least 30, at least 50, at least 100, at least 200, at least 300, at least 500, at least 800, at least 1000, at least 1200, at least 1500, at least 1800, at least 2000, at least 2200, at least 2400, at least 2600, at least 3000, at least 5000, at least 10000, at least 15000, at least 20000, or at least 25000. In some cases, n is less than or equal to 30000, less than or equal to 25000, less than or equal to 20000, less than or equal to 25000, less than or equal to 20000, less than or equal to 15000, less than or equal to 10000, less than or equal to 5000, less than or equal to 3000, less than or equal to 2800, less than or equal to 2400, less than or equal to 2000, less than or equal to 1800, less than or equal to 1500, less than or equal to 1200, less than or equal to 1000, less than or equal to 800, less than or equal to 500, less than or equal to 300, less than or equal to 200, less than or equal to 100, or less than or equal to 50. Combinations of the above-referenced ranges are also possible (*e.g.*, n being at least 50 and less than or equal to 2000). Other ranges are also possible.

[000114] Similarly, the value of m may vary. For instance, in certain embodiments, m is at least 5, at least 10, at least 20, at least 30, at least 50, at least 70, at least 100, at least 150, at least 200, at least 250, at least 300, at least 350, at least 400, at least 500, at least 800, at least 1000, at least 1200, at least 1500, at least 1800, at least 2000, at least 2200, at least 2400, at least 2600, at least 3000, at least 5000, at least 10000, or at least 15000. In some cases, m is less than or equal to 15000, less than or equal to 10000, less than or equal to 5000, less than or equal to 3000, less than or equal to 2800, less than or equal to 2400, less than or equal to 2000, less than or equal to 1800, less than or equal to 1500, less than or equal to 1200, less than or equal to 1000, less than or equal to 800, less than or equal to 500, less than or equal to

400, less than or equal to 350, less than or equal to 300, less than or equal to 250, less than or equal to 200, less than or equal to 150, less than or equal to 100, less than or equal to 70, less than or equal to 50, less than or equal to 30, less than or equal to 20, or less than or equal to 10. Combinations of the above-referenced ranges are also possible (*e.g.*, *m* being at least 5 and less than or equal to 200). Other ranges are also possible.

[000115] In some embodiments, the particles described herein include a coating comprising a block copolymer having a relatively hydrophilic block and a relatively hydrophobic block. In some cases, the hydrophilic blocks may be substantially present at the outer surface of the particle. For example, the hydrophilic blocks may form a majority of the outer surface of the coating and may help stabilize the particle in an aqueous solution containing the particle. The hydrophobic block may be substantially present in the interior of the coating and/or at the surface of the core particle, *e.g.*, to facilitate attachment of the coating to the core. In some instances, the coating comprises a surface-altering agent including a triblock copolymer, wherein the triblock copolymer comprises a hydrophilic block – hydrophobic block – hydrophilic block configuration. Diblock copolymers having a hydrophilic block – hydrophobic block configuration are also possible. Combinations of block copolymers with other polymers suitable for use as coatings are also possible. Non-linear block configurations are also possible such as in comb, brush, or star copolymers. In some embodiments, the relatively hydrophilic block includes a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer (*e.g.*, PVA).

[000116] The molecular weight of the hydrophilic blocks and the hydrophobic blocks of the block copolymers may be selected so as to reduce the mucoadhesion of a core and to ensure sufficient association of the block copolymer with the core, respectively. The molecular weight of the hydrophobic block of the block copolymer may be chosen such that adequate association of the block copolymer with the core occurs, thereby increasing the likelihood that the block copolymer remains adhered to the core.

[000117] In certain embodiments, the combined molecular weight of the (one or more) relatively hydrophobic blocks or repeat units of a block copolymer is at least about 0.5 kDa, at least about 1 kDa, at least about 2 kDa, at least about 3 kDa, at least about 4 kDa, at least about 5 kDa, at least about 6 kDa, at least about 10 kDa, at least about 12 kDa, at least about 15 kDa, at least about 20 kDa, or at least about 50 kDa, at least about 60 kDa, at least about

70 kDa, at least about 80 kDa, at least about 90 kDa, at least about 100 kDa at least about 110 kDa, at least about 120 kDa, at least about 130 kDa, at least about 140 kDa, at least about 150 kDa, at least about 200 kDa, at least about 500 kDa, or at least about 1000 kDa. In some embodiments, the combined molecular weight of the (one or more) relatively hydrophobic blocks or repeat units is less than or equal to about 1000 kDa, less than or equal to about 500 kDa, less than or equal to about 200 kDa, less than or equal to about 150 kDa, less than or equal to about 140 kDa, less than or equal to about 130 kDa, less than or equal to about 120 kDa, less than or equal to about 110 kDa, less than or equal to about 100 kDa, less than or equal to about 90 kDa, less than or equal to about 80 kDa, less than or equal to about 50 kDa, less than or equal to about 20 kDa, less than or equal to about 15 kDa, less than or equal to about 13 kDa, less than or equal to about 12 kDa, less than or equal to about 10 kDa, less than or equal to about 8 kDa, or less than or equal to about 6 kDa. Combinations of the above-mentioned ranges are also possible (*e.g.*, at least about 3 kDa and less than or equal to about 15 kDa). Other ranges are also possible.

[000118] In some embodiments, the combined (one or more) relatively hydrophilic blocks or repeat units of a block copolymer constitute at least about 15 wt%, at least about 20 wt%, at least about 25 wt%, at least about 30 wt%, at least about 35 wt%, at least about 40 wt%, at least about 45 wt%, at least about 50 wt%, at least about 55 wt%, at least about 60 wt%, at least about 65 wt%, or at least about 70 wt% of the block copolymer. In some embodiments, the combined (one or more) relatively hydrophilic blocks or repeat units of a block copolymer constitute less than or equal to about 90 wt%, less than or equal to about 80 wt%, less than or equal to about 60 wt%, less than or equal to about 50 wt%, or less than or equal to about 40 wt% of the block copolymer. Combinations of the above-referenced ranges are also possible (*e.g.*, at least about 30 wt% and less than or equal to about 80 wt%). Other ranges are also possible.

[000119] In some embodiments, the combined molecular weight of the (one or more) relatively hydrophilic blocks or repeat units of the block copolymer may be at least about 0.5 kDa, at least about 1 kDa, at least about 2 kDa, at least about 3 kDa, at least about 4 kDa, at least about 5 kDa, at least about 6 kDa, at least about 10 kDa, at least about 12 kDa, at least about 15 kDa, at least about 20 kDa, or at least about 50 kDa, at least about 60 kDa, at least about 70 kDa, at least about 80 kDa, at least about 90 kDa, at least about 100 kDa at least


about 110 kDa, at least about 120 kDa, at least about 130 kDa, at least about 140 kDa, at least about 150 kDa, at least about 200 kDa, at least about 500 kDa, or at least about 1000 kDa. In certain embodiments, the combined molecular weight of the (one or more) relatively hydrophilic blocks or repeat units is less than or equal to about 1000 kDa, less than or equal to about 500 kDa, less than or equal to about 200 kDa, less than or equal to about 150 kDa, less than or equal to about 140 kDa, less than or equal to about 130 kDa, less than or equal to about 120 kDa, less than or equal to about 110 kDa, less than or equal to about 100 kDa, less than or equal to about 90 kDa, less than or equal to about 80 kDa, less than or equal to about 50 kDa, less than or equal to about 20 kDa, less than or equal to about 15 kDa, less than or equal to about 13 kDa, less than or equal to about 12 kDa, less than or equal to about 10 kDa, less than or equal to about 8 kDa, less than or equal to about 6 kDa, less than or equal to about 5 kDa, less than or equal to about 3 kDa, less than or equal to about 2 kDa, or less than or equal to about 1 kDa. Combinations of the above-mentioned ranges are also possible (*e.g.*, at least about 0.5 kDa and less than or equal to about 3 kDa). Other ranges are also possible. In embodiments in which two hydrophilic blocks flank a hydrophobic block, the molecular weights of the two hydrophilic blocks may be substantially the same or different.

[000120] In certain embodiments, the polymer of a surface-altering agent includes a polyether portion. In certain embodiments, the polymer includes a polyalkylether portion. In certain embodiments, the polymer includes polyethylene glycol tails. In certain embodiments, the polymer includes a polypropylene glycol central portion. In certain embodiments, the polymer includes polybutylene glycol as the central portion. In certain embodiments, the polymer includes polypentylene glycol as the central portion. In certain embodiments, the polymer includes polyhexylene glycol as the central portion. In certain embodiments, the diblock copolymer of one of the polymers described herein. In certain embodiments, the polymer is a triblock copolymer of one of the polymers described herein. As disclosed herein, any recitation of PEG may be replaced with polyethylene oxide (PEO), and any recitation of PEO may be replaced with PEG. In some embodiments, a diblock or triblock copolymer comprises a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer (*e.g.*, PVA) as one or more of the blocks (with varying degrees of hydrolysis and varying molecular weights as described herein). The

synthetic polymer blocks may form the central portion or the end portions of the block copolymer.

[000121] In certain embodiments, the polymer is a triblock copolymer of a polyalkyl ether (*e.g.*, polyethylene glycol, polypropylene glycol) and another polymer (*e.g.*, a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer (*e.g.*, PVA). In certain embodiments, the polymer is a triblock copolymer of a polyalkyl ether and another polyalkyl ether. In certain embodiments, the polymer is a triblock copolymer of polyethylene glycol and another polyalkyl ether. In certain embodiments, the polymer is a triblock copolymer of polypropylene glycol and another polyalkyl ether. In certain embodiments, the polymer is a triblock copolymer with at least one unit of polyalkyl ether. In certain embodiments, the polymer is a triblock copolymer of two different polyalkyl ethers. In certain embodiments, the polymer is a triblock copolymer including a polyethylene glycol unit. In certain embodiments, the polymer is a triblock copolymer including a polypropylene glycol unit. In certain embodiments, the polymer is a triblock copolymer of a more hydrophobic unit flanked by two more hydrophilic units. In certain embodiments, the hydrophilic units are the same type of polymer. In some embodiments, the hydrophilic units include a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer (*e.g.*, PVA). In certain embodiments, the polymer includes a polypropylene glycol unit flanked by two more hydrophilic units. In certain embodiments, the polymer includes two polyethylene glycol units flanking a more hydrophobic unit. In certain embodiments, the polymer is a triblock copolymer with a polypropylene glycol unit flanked by two polyethylene glycol units. The molecular weights of the two blocks flanking the central block may be substantially the same or different.

[000122] In certain embodiments, the polymer is of the formula:



wherein *n* is an integer between 2 and 1140, inclusive; and *m* is an integer between 2 and 1730, inclusive. In certain embodiments, *n* is an integer between 10 and 170, inclusive. In

certain embodiments, m is an integer between 5 and 70 inclusive. In certain embodiments, n is at least 2 times m , 3 times m , or 4 times m .

[000123] In certain embodiments, the coating includes a surface-altering agent comprising a (poly(ethylene glycol))-(poly(propylene oxide))-(poly(ethylene glycol)) triblock copolymer (hereinafter “PEG-PPO-PEG triblock copolymer”), present in the coating alone or in combination with another polymer such as a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer (*e.g.*, PVA). As described herein, the PEG blocks may be interchanged with PEO blocks in some embodiments. The molecular weights of the PEG (or PEO) and PPO segments of the PEG-PPO-PEG triblock copolymer may be selected so as to reduce the mucoadhesion of the particle, as described herein. Without wishing to be bound by theory, a particle having a coating comprising a PEG-PPO-PEG triblock copolymer may have reduced mucoadhesion as compared to a control particle due to, at least in part, the display of a plurality of PEG (or PEO) segments on the particle surface. The PPO segment may be adhered to the core surface (*e.g.*, in the case of the core surface being hydrophobic), thus allowing for a strong association between the core and the triblock copolymer. In some cases, the PEG-PPO-PEG triblock copolymer is associated with the core through non-covalent interactions. For purposes of comparison, the control particle may be, for example, a carboxylate-modified polystyrene particle of similar size as the coated particle in question.

[000124] In certain embodiments, a surface-altering agent includes a polymer comprising a poloxamer, having the trade name Pluronic®. Pluronic® polymers that may be useful in the embodiments described herein include, but are not limited to, F127, F38, F108, F68, F77, F87, F88, F98, L101, L121, L31, L35, L43, L44, L61, L62, L64, L81, L92, N3, P103, P104, P105, P123, P65, P84, and P85.

[000125] Examples of molecular weights of certain Pluronic® molecules are shown in Table 2.

[000126] Table 2: Molecular Weights of Pluronic® molecules

Pluronic®	Average MW	MW PPO	PEO wt %	MW PEO
L31	1000	900	10	100
L44	2000	1200	40	800
L81	2667	2400	10	267

L101	3333	3000	10	333
P65	3600	1800	50	1800
L121	4000	3600	10	400
P103	4286	3000	30	1286
F38	4500	900	80	3600
P123	5143	3600	30	1543
P105	6000	3000	50	3000
F87	8000	2400	70	5600
F68	9000	1800	80	7200
F127	12000	3600	70	8400
P123	5750	4030	30	1730

[000127] Although other ranges may be possible and useful in certain embodiments described herein, in some embodiments, the hydrophobic block of the PEG-PPO-PEG triblock copolymer has one of the molecular weights described above (*e.g.*, at least about 3 kDa and less than or equal to about 15 kDa), and the combined hydrophilic blocks have a weight percentage with respect to the polymer in one of the ranges described above (*e.g.*, at least about 15 wt%, at least about 20 wt%, at least about 25 wt%, or at least about 30 wt%, and less than or equal to about 80 wt%). Certain Pluronic[®] polymers that fall within these criteria include, for example, F127, F108, P105 and P103.

[000128] It should be appreciated that the ability of a surface-altering agent to render a particle or core mucus penetrating may depend at least in part on the particular core/surface-altering agent combination, including the ability of the surface-altering agent to attach to the core and/or the density of the surface-altering agent on the core/particle surface. As such, in some embodiments a particular surface-altering agent may enhance the mobility of one type of particle or core but may not enhance the mobility of particle or core of another type.

[000129] Although many of the embodiments described herein involve a single coating, in other embodiments, a particle may include more than one coating (*e.g.*, at least two, three, four, five, or more coatings), and each coating need not be formed of or comprise a mucus penetrating material. In some cases, an intermediate coating (*i.e.*, a coating between the core surface and an outer coating) may include a polymer that facilitates attachment of an outer coating to the core surface. In many embodiments, an outer coating of a particle includes a polymer comprising a material that facilitates the transport of the particle through mucus.

[000130] As such, a coating (*e.g.*, an inner coating, an intermediate coating, and/or an outer coating) may include any suitable polymer. In some cases, the polymer may be biocompatible and/or biodegradable. In some cases, the polymeric material may comprise more than one type of polymer (*e.g.*, at least two, three, four, five, or more, polymers). In some cases, a polymer may be a random copolymer or a block copolymer (*e.g.*, a diblock copolymer, a triblock copolymer) as described herein.

[000131] Non-limiting examples of suitable polymers may include polyamines, polyethers, polyamides, polyesters, polycarbamates, polyureas, polycarbonates, polystyrenes, polyimides, polysulfones, polyurethanes, polyacetylenes, polyethylenes, polyethyleneimines, polyisocyanates, polyacrylates, polymethacrylates, polyacrylonitriles, and polyarylates. Non-limiting examples of specific polymers include poly(caprolactone) (PCL), ethylene vinyl acetate polymer (EVA), poly(lactic acid) (PLA), poly(L-lactic acid) (PLLA), poly(glycolic acid) (PGA), poly(lactic acid-co-glycolic acid) (PLGA), poly(L-lactic acid-co-glycolic acid) (PLLGA), poly(D,L-lactide) (PDLA), poly(L-lactide) (PLLA), poly(D,L-lactide-co-caprolactone), poly(D,L-lactide-co-caprolactone-co-glycolide), poly(D,L-lactide-co-PEO-co-D,L-lactide), poly(D,L-lactide-co-PPO-co-D,L-lactide), polyalkyl cyanoacrylate, polyurethane, poly-L-lysine (PLL), hydroxypropyl methacrylate (HPMA), poly(ethylene glycol), poly-L-glutamic acid, poly(hydroxy acids), polyanhydrides, polyorthoesters, poly(ester amides), polyamides, poly(ester ethers), polycarbonates, polyalkylenes such as polyethylene and polypropylene, polyalkylene glycols such as poly(ethylene glycol) (PEG), polyalkylene oxides (PEO), polyalkylene terephthalates such as poly(ethylene terephthalate), polyvinyl alcohols (PVA), polyvinyl ethers, polyvinyl esters such as poly(vinyl acetate), polyvinyl halides such as poly(vinyl chloride) (PVC), polyvinylpyrrolidone, polysiloxanes, polystyrene (PS), polyurethanes, derivatized celluloses such as alkyl celluloses, hydroxyalkyl celluloses, cellulose ethers, cellulose esters, nitro celluloses, hydroxypropylcellulose, carboxymethylcellulose, polymers of acrylic acids, such as poly(methyl(meth)acrylate) (PMMA), poly(ethyl(meth)acrylate), poly(butyl(meth)acrylate), poly(isobutyl(meth)acrylate), poly(hexyl(meth)acrylate), poly(isodecyl(meth)acrylate), poly(lauryl(meth)acrylate), poly(phenyl(meth)acrylate), poly(methyl acrylate), poly(isopropyl acrylate), poly(isobutyl acrylate), poly(octadecyl acrylate) (jointly referred to herein as “polyacrylic acids”), and copolymers and mixtures thereof, polydioxanone and its copolymers, polyhydroxyalkanoates,

polypropylene fumarate), polyoxymethylene, poloxamers, poly(ortho)esters, poly(butyric acid), poly(valeric acid), poly(lactide-co-caprolactone), and trimethylene carbonate, polyvinylpyrrolidone.

[000132] The molecular weight of a polymer may vary. In some embodiments, the molecular weight may be at least about 0.5 kDa, at least about 1 kDa, at least about 2 kDa, at least about 3 kDa, at least about 4 kDa, at least about 5 kDa, at least about 6 kDa, at least about 8 kDa, at least about 10 kDa, at least about 12 kDa, at least about 15 kDa, at least about 20 kDa, at least about 30 kDa, at least about 40 kDa, or at least about 50 kDa. In some embodiments, the molecular weight may be less than or equal to about 50 kDa, less than or equal to about 40 kDa, less than or equal to about 30 kDa, less than or equal to about 20 kDa, less than or equal to about 12 kDa, less than or equal to about 10 kDa, less than or equal to about 8 kDa, less than or equal to about 6 kDa, less than or equal to about 5 kDa, or less than or equal to about 4 kDa. Combinations of the above-referenced ranges are possible (*e.g.*, a molecular weight of at least about 2 kDa and less than or equal to about 15 kDa). Other ranges are also possible. The molecular weight may be determined using any known technique such as light-scattering and gel permeation chromatography. Other methods are known in the art.

[000133] In certain embodiments, the polymer is biocompatible, *i.e.*, the polymer does not typically induce an adverse response when inserted or injected into a living subject; for example, it does not include significant inflammation and/or acute rejection of the polymer by the immune system, for instance, via a T-cell-mediated response. It will be recognized, of course, that “biocompatibility” is a relative term, and some degree of immune response is to be expected even for polymers that are highly compatible with living tissue. However, as used herein, “biocompatibility” refers to the acute rejection of material by at least a portion of the immune system, *i.e.*, a non-biocompatible material implanted into a subject provokes an immune response in the subject that is severe enough such that the rejection of the material by the immune system cannot be adequately controlled, and often is of a degree such that the material must be removed from the subject. One simple test to determine biocompatibility is to expose a polymer to cells *in vitro*; biocompatible polymers are polymers that typically does not result in significant cell death at moderate concentrations, *e.g.*, at concentrations of about 50 micrograms/10⁶ cells. For instance, a biocompatible polymer may cause less than about

20% cell death when exposed to cells such as fibroblasts or epithelial cells, even if phagocytosed or otherwise uptaken by such cells. In some embodiments, a substance is “biocompatible” if its addition to cells *in vitro* results in less than or equal to 20% cell death, and their administration *in vivo* does not induce unwanted inflammation or other such adverse effects.

[000134] In certain embodiments, a biocompatible polymer may be biodegradable, *i.e.*, the polymer is able to degrade, chemically and/or biologically (*e.g.*, by the cellular machinery or by hydrolysis), within a physiological environment, such as within the body or when introduced to cells. For instance, the polymer may be one that hydrolyzes spontaneously upon exposure to water (*e.g.*, within a subject), and/or the polymer may degrade upon exposure to heat (*e.g.*, at temperatures of about 37 °C). Degradation of a polymer may occur at varying rates, depending on the polymer or copolymer used. For example, the half-life of the polymer (the time at which 50% of the polymer is degraded into monomers and/or other non-polymeric moieties) may be on the order of days, weeks, months, or years, depending on the polymer. The polymer may be biologically degraded, *e.g.*, by enzymatic activity or cellular machinery, in some cases, for example, through exposure to a lysozyme (*e.g.*, having relatively low pH). In some cases, the polymer may be broken down into monomers and/or other non-polymeric moieties that cells can either reuse or dispose of without significant toxic effect on the cells (*i.e.*, fewer than about 20 % of the cells are killed when the components are added to cells *in vitro*). For example, polylactide may be hydrolyzed to form lactic acid, polyglycolide may be hydrolyzed to form glycolic acid, *etc.*).

[000135] Examples of biodegradable polymers include, but are not limited to, poly(ethylene glycol)-poly(propylene oxide)-poly(ethylene glycol) triblock copolymers, poly(lactide) (or poly(lactic acid)), poly(glycolide) (or poly(glycolic acid)), poly(orthoesters), poly(caprolactones), polylysine, poly(ethylene imine), poly(acrylic acid), poly(urethanes), poly(anhydrides), poly(esters), poly(trimethylene carbonate), poly(ethyleneimine), poly(acrylic acid), poly(urethane), poly(beta amino esters) or the like, and copolymers or derivatives of these and/or other polymers, for example, poly(lactide-co-glycolide) (PLGA).

[000136] In certain embodiments, a polymer may biodegrade within a period that is acceptable in the desired application. In certain embodiments, such as *in vivo* therapy, such degradation occurs in a period usually less than about five years, one year, six months, three

months, one month, fifteen days, five days, three days, or even one day or less (*e.g.*, 1-4 hours, 4-8 hours, 4-24 hours, 1-24 hours) on exposure to a physiological solution with a pH between 6 and 8 having a temperature of between 25 and 37 °C. In other embodiments, the polymer degrades in a period of between about one hour and several weeks, depending on the desired application.

[000137] Although coatings and particles described herein may include polymers, in some embodiments, the particles described herein comprise a hydrophobic material that is not a polymer (*e.g.*, a non-polymer) and is not a pharmaceutical agent. For example, all or portions of a particle may be coated with a passivating layer in some embodiments. Non-limiting examples of non-polymeric materials may include certain metals, waxes, and organic materials (*e.g.*, organic silanes, perfluorinated or fluorinated organic materials).

Particles with reduced mucoadhesion

[000138] As described herein, in some embodiments, a method involves identifying a material such as a particle to which it is desired that its mucoadhesiveness be reduced. Materials in need of increased diffusivity through mucus may be, for example, hydrophobic, have many hydrogen bond donors or acceptors, and/or may be highly charged. In some cases, the material may include a crystalline or amorphous solid material. The material, which may serve as a core, may be coated with a suitable polymer described herein, thereby forming a particle with a plurality of surface-altering moieties on the surface, resulting in reduced mucoadhesion. Particles herein described as having reduced mucoadhesion may alternatively be characterized as having increased transport through mucus, being mobile in mucus, or mucus-penetrating (*i.e.*, mucus-penetrating particles), meaning that the particles are transported through mucus faster than a (negative) control particle. The (negative) control particle may be a particle that is known to be mucoadhesive, *e.g.*, an unmodified particle or core that is not coated with a coating described herein, such as a 200 nm carboxylated polystyrene particle.

[000139] In certain embodiments, methods herein include preparing a pharmaceutical composition or formulation of the modified substance, *e.g.*, in a formulation adapted for delivery (*e.g.*, topical delivery) to mucus or a mucosal surface of a subject. The pharmaceutical composition with surface-altering moieties may be delivered to the mucosal

surface of a subject, may pass through the mucosal barrier in the subject, and/or prolonged retention and/or increased uniform distribution of the particles at mucosal surfaces, *e.g.*, due to reduced mucoadhesion. As will be known by those of ordinary skill in the art, mucus is a viscoelastic and adhesive substance that traps most foreign particles. Trapped particles are not able to reach the underlying epithelium and/or are quickly eliminated by mucus clearance mechanisms. For a particle to reach the underlying epithelium and/or for a particle to have prolonged retention in the mucosal tissue, the particle must quickly penetrate mucus secretions and/or avoid the mucus clearance mechanisms. If a particle does not adhere substantially to the mucus, the particle may be able to diffuse in the interstitial fluids between mucin fibers and reach the underlying epithelium and/or not be eliminated by the mucus clearance mechanisms. Accordingly, modifying mucoadhesive materials, (*e.g.*, pharmaceutical agents that are hydrophobic) with a material to reduce the mucoadhesion of the particle may allow for efficient delivery of the particles to the underlying epithelium and/or prolonged retention at mucosal surfaces.

[000140] Furthermore, in some embodiments, the particles described herein having reduced mucoadhesion facilitate better distribution of the particles at a tissue surface, and/or have a prolonged presence at the tissue surface, compared to particles that are more mucoadhesive. For example, in some cases a luminal space such as the gastrointestinal tract is surrounded by a mucus-coated surface. Mucoadhesive particles delivered to such a space are typically removed from the luminal space and from the mucus-coated surface by the body's natural clearance mechanisms. The particles described herein with reduced mucoadhesion may remain in the luminal space for relatively longer periods compared to the mucoadhesive particles. This prolonged presence may prevent or reduce clearance of the particles, and/or may allow for better distribution of the particles on the tissue surface. The prolonged presence may also affect the particle transport through the luminal space, *e.g.*, the particles may distribute into the mucus layer and may reach the underlying epithelium.

[000141] In certain embodiments, a material (*e.g.*, a core) coated with a polymer described herein may pass through mucus or a mucosal barrier in a subject, and/or exhibit prolonged retention and/or increase uniform distribution of the particles at mucosal surfaces, *e.g.*, such substances are cleared more slowly (*e.g.*, at least 2 times, 5 times, 10 times, or even at least 20 times more slowly) from a subject's body as compared to a (negative) control particle.

The (negative) control particle may be a particle that is known to be mucoadhesive, *e.g.*, an unmodified particle or core that is not coated with a coating described herein, such as a 200 nm carboxylated polystyrene particle.

[000142] In certain embodiments, a particle described herein has certain a relative velocity, $\langle V_{\text{mean}} \rangle_{\text{rel}}$, which is defined as follows:

$$\langle V_{\text{mean}} \rangle_{\text{rel}} = \frac{\langle V_{\text{mean}} \rangle_{\text{Sample}} - \langle V_{\text{mean}} \rangle_{\text{Negative control}}}{\langle V_{\text{mean}} \rangle_{\text{Positive control}} - \langle V_{\text{mean}} \rangle_{\text{Negative control}}} \quad (\text{Equation 1})$$

1)
where $\langle V_{\text{mean}} \rangle$ is the ensemble average trajectory-mean velocity, V_{mean} is the velocity of an individual particle averaged over its trajectory, the sample is the particle of interest, the negative control is a 200 nm carboxylated polystyrene particle, and the positive control is a 200 nm polystyrene particle densely PEGylated with 2 kDa - 5 kDa PEG.

[000143] The relative velocity can be measured by a multiple particle tracking technique. For instance, a fluorescent microscope equipped with a CCD camera can be used to capture 15 s movies at a temporal resolution of 66.7 ms (15 frames/s) under 100x magnification from several areas within each sample for each type of particles: sample, negative control, and positive control. The sample, negative and positive controls may be fluorescent particles to observe tracking. Alternatively non-fluorescent particles may be coated with a fluorescent molecule, a fluorescently tagged surface agent or a fluorescently tagged polymer. An advanced image processing software (*e.g.*, Image Pro or MetaMorph) can be used to measure individual trajectories of multiple particles over a time-scale of at least 3.335 s (50 frames).

[000144] In some embodiments, a particle described herein has a relative velocity of greater than or equal to about 0.3, greater than or equal to about 0.4, greater than or equal to about 0.5, greater than or equal to about 0.6, greater than or equal to about 0.7, greater than or equal to about 0.8, greater than or equal to about 0.9, greater than or equal to about 1.0, greater than or equal to about 1.1, greater than or equal to about 1.2, greater than or equal to about 1.3, greater than or equal to about 1.4, greater than or equal to about 1.5, greater than or equal to about 1.6, greater than or equal to about 1.7, greater than or equal to about 1.8, greater than or equal to about 1.9 or greater than or equal to about 2.0 in mucus. In some embodiments, a particle described herein has a relative velocity of less than or equal to about 10.0, less than or equal to about 8.0, less than or equal to about 6.0, less than or equal to about 4.0, less than

or equal to about 3.0, less than or equal to about 2.0, less than or equal to about 1.9, less than or equal to about 1.8, less than or equal to about 1.7, less than or equal to about 1.6, less than or equal to about 1.5, less than or equal to about 1.4, less than or equal to about 1.3, less than or equal to about 1.2, less than or equal to about 1.1, less than or equal to about 1.0, less than or equal to about 0.9, less than or equal to about 0.8, or less than or equal to about 1.7 in mucus. Combinations of the above-noted ranges are possible (*e.g.*, a relative velocity of greater than or equal to about 0.5 and less than or equal to about 6.0). Other ranges are also possible. The mucus may be, for example, human cervicovaginal mucus.

[000145] In certain embodiments, a particle described herein can diffuse through mucus or a mucosal barrier at a greater rate or diffusivity than a control particle or a corresponding particle (*e.g.*, a corresponding particle that is unmodified and/or is not coated with a coating described herein). In some cases, a particle described herein may pass through mucus or a mucosal barrier at a rate of diffusivity that is at least about 10 times, 20 times, 30 times, 50 times, 100 times, 200 times, 500 times, 1000 times, 2000 times, 5000 times, 10000 times, or more, higher than a control particle or a corresponding particle. In some cases, a particle described herein may pass through mucus or a mucosal barrier at a rate of diffusivity that is less than or equal to about 10000 times higher, less than or equal to about 5000 times higher, less than or equal to about 2000 times higher, less than or equal to about 1000 times higher, less than or equal to about 500 times higher, less than or equal to about 200 times higher, less than or equal to about 100 times higher, less than or equal to about 50 times higher, less than or equal to about 30 times higher, less than or equal to about 20 times higher, or less than or equal to about 10 times higher than a control particle or a corresponding particle.

Combinations of the above-referenced ranges are also possible (*e.g.*, at least about 10 times and less than or equal to about 1000 times higher than a control particle or a corresponding particle). Other ranges are also possible.

[000146] For the purposes of the comparisons described herein, the corresponding particle may be approximately the same size, shape, and/or density as the test particle but lacking the coating that makes the test particle mobile in mucus. In some cases, the measurement is based on a time scale of about 1 second, or about 0.5 second, or about 2 seconds, or about 5 seconds, or about 10 seconds. Those of ordinary skill in the art will be aware of methods for determining the geometric mean square displacement and rate of diffusivity.

[000147] In addition, a particle described herein may pass through mucus or a mucosal barrier with a geometric mean squared displacement that is at least about 10 times, 20 times, 30 times, 50 times, 100 times, 200 times, 500 times, 1000 times, 2000 times, 5000 times, 10000 times, or more, higher than a corresponding particle or control particle. In some cases, a particle described herein may pass through mucus or a mucosal barrier with a geometric mean squared displacement that is less than or equal to about 10000 times higher, less than or equal to about 5000 times higher, less than or equal to about 2000 times higher, less than or equal to about 1000 times higher, less than or equal to about 500 times higher, less than or equal to about 200 times higher, less than or equal to about 100 times higher, less than or equal to about 50 times higher, less than or equal to about 30 times higher, less than or equal to about 20 times higher, or less than or equal to about 10 times higher than a control particle or a corresponding particle. Combinations of the above-referenced ranges are also possible (*e.g.*, at least about 10 times and less than or equal to about 1000 times higher than a control particle or a corresponding particle). Other ranges are also possible.

[000148] In some embodiments, a particle described herein diffuses through a mucosal barrier at a rate approaching the rate or diffusivity at which said particles can diffuse through water. In some cases, a particle described herein may pass through a mucosal barrier at a rate or diffusivity that is less than or equal to about 1/100, less than or equal to about 1/200, less than or equal to about 1/300, less than or equal to about 1/400, less than or equal to about 1/500, less than or equal to about 1/600, less than or equal to about 1/700, less than or equal to about 1/800, less than or equal to about 1/900, less than or equal to about 1/1000, less than or equal to about 1/2000, less than or equal to about 1/5000, less than or equal to about 1/10,000 the diffusivity that the particle diffuse through water under identical conditions. In some cases, a particle described herein may pass through a mucosal barrier at a rate or diffusivity that is greater than or equal to about 1/10,000, greater than or equal to about 1/5000, greater than or equal to about 1/2000, greater than or equal to about 1/1000, greater than or equal to about 1/900, greater than or equal to about 1/800, greater than or equal to about 1/700, greater than or equal to about 1/600, greater than or equal to about 1/500, greater than or equal to about 1/400, greater than or equal to about 1/300, greater than or equal to about 1/200, greater than or equal to about 1/100 the diffusivity that the particle diffuse through water under identical conditions. Combinations of the above-referenced ranges are

also possible (*e.g.*, greater than or equal to about 1/5000 and less than 1/500 the diffusivity that the particle diffuse through water under identical conditions). Other ranges are also possible. The measurement may be based on a time scale of about 1 second, or about 0.5 second, or about 2 seconds, or about 5 seconds, or about 10 seconds.

[000149] In a particular embodiment, a particle described herein may diffuse through human cervicovaginal mucus at a diffusivity that is less than about 1/500 the diffusivity that the particle diffuses through water. In some cases, the measurement is based on a time scale of about 1 second, or about 0.5 second, or about 2 seconds, or about 5 seconds, or about 10 seconds.

[000150] In certain embodiments, the present invention provides particles that travel through mucus, such as human cervicovaginal mucus, at certain absolute diffusivities. For example, the particles of described herein may travel at diffusivities of at least about 1×10^{-4} $\mu\text{m/s}$, 2×10^{-4} $\mu\text{m/s}$, 5×10^{-4} $\mu\text{m/s}$, 1×10^{-3} $\mu\text{m/s}$, 2×10^{-3} $\mu\text{m/s}$, 5×10^{-3} $\mu\text{m/s}$, 1×10^{-2} $\mu\text{m/s}$, 2×10^{-2} $\mu\text{m/s}$, 4×10^{-2} $\mu\text{m/s}$, 5×10^{-2} $\mu\text{m/s}$, 6×10^{-2} $\mu\text{m/s}$, 8×10^{-2} $\mu\text{m/s}$, 1×10^{-1} $\mu\text{m/s}$, 2×10^{-1} $\mu\text{m/s}$, 5×10^{-1} $\mu\text{m/s}$, $1 \mu\text{m/s}$, or $2 \mu\text{m/s}$. In some cases, the particles may travel at diffusivities of less than or equal to about $2 \mu\text{m/s}$, less than or equal to about $1 \mu\text{m/s}$, less than or equal to about 5×10^{-1} $\mu\text{m/s}$, less than or equal to about 2×10^{-1} $\mu\text{m/s}$, less than or equal to about 1×10^{-1} $\mu\text{m/s}$, less than or equal to about 8×10^{-2} $\mu\text{m/s}$, less than or equal to about 6×10^{-2} $\mu\text{m/s}$, less than or equal to about 5×10^{-2} $\mu\text{m/s}$, less than or equal to about 4×10^{-2} $\mu\text{m/s}$, less than or equal to about 2×10^{-2} $\mu\text{m/s}$, less than or equal to about 1×10^{-2} $\mu\text{m/s}$, less than or equal to about 5×10^{-3} $\mu\text{m/s}$, less than or equal to about 2×10^{-3} $\mu\text{m/s}$, less than or equal to about 1×10^{-3} $\mu\text{m/s}$, less than or equal to about 5×10^{-4} $\mu\text{m/s}$, less than or equal to about 2×10^{-4} $\mu\text{m/s}$, or less than or equal to about 1×10^{-4} $\mu\text{m/s}$. Combinations of the above-referenced ranges are also possible (*e.g.*, greater than or equal to about 2×10^{-4} $\mu\text{m/s}$ and less than or equal to about 1×10^{-1} $\mu\text{m/s}$). Other ranges are also possible. In some cases, the measurement is based on a time scale of about 1 second, or about 0.5 second, or about 2 seconds, or about 5 seconds, or about 10 seconds.

[000151] It should be appreciated that while many of the mobilities (*e.g.*, relative velocities, diffusivities) described here may be measured in human cervicovaginal mucus, they may be measured in other types of mucus as well.

[000152] In certain embodiments, a particle described herein comprises surface-altering moieties at a given density. The surface-altering moieties may be the portions of a surface-altering agent that are, for example, exposed to the solvent containing the particle. As an example, the hydrolyzed units/blocks of PVA may be surface-altering moieties of the surface-altering agent PVA. In some cases, the surface-altering moieties and/or surface-altering agents are present at a density of at least about 0.001 units or molecules per nm², at least about 0.002, at least about 0.005, at least about 0.01, at least about 0.02, at least about 0.05, at least about 0.1, at least about 0.2, at least about 0.5, at least about 1, at least about 2, at least about 5, at least about 10, at least about 20, at least about 50, at least about 100 units or molecules per nm², or more units or molecules per nm². In some cases, the surface-altering moieties and/or surface-altering agents are present at a density of less than or equal to about 100 units or molecules per nm², less than or equal to about 50, less than or equal to about 20, less than or equal to about 10, less than or equal to about 5, less than or equal to about 2, less than or equal to about 1, less than or equal to about 0.5, less than or equal to about 0.2, less than or equal to about 0.1, less than or equal to about 0.05, less than or equal to about 0.02, or less than or equal to about 0.01 units or molecules per nm². Combinations of the above-referenced ranges are possible (*e.g.*, a density of at least about 0.01 and less than or equal to about 1 units or molecules per nm²). Other ranges are also possible. In some embodiments, the density values described above may be an average density as the surface altering agent is in equilibrium with other components in solution.

[000153] Those of ordinary skill in the art will be aware of methods to estimate the average density of surface-altering moieties (see, for example, S.J. Budijono et al., *Colloids and Surfaces A: Physicochem. Eng. Aspects* 360 (2010) 105–110 and Joshi, *et al.*, *Anal. Chim. Acta* 104 (1979) 153–160, each of which is incorporated herein by reference). For example, as described herein, the average density of surface-altering moieties can be determined using HPLC quantitation and DLS analysis. A suspension of particles for which surface density determination is of interest is first sized using DLS: a small volume is diluted to an appropriate concentration (~100 µg/mL, for example), and the z-average diameter is taken as a representative measurement of particle size. The remaining suspension is then divided into two aliquots. Using HPLC, the first aliquot is assayed for the total concentration of core material and for the total concentration of surface-altering moiety. Again using HPLC the

second aliquot is assayed for the concentration of free or unbound surface-altering moiety. In order to get only the free or unbound surface-altering moiety from the second aliquot, the particles, and therefore any bound surface-altering moiety, are removed by ultracentrifugation. By subtracting the concentration of the unbound surface-altering moiety from the total concentration of surface-altering moiety, the concentration of bound surface-altering moiety can be determined. Since the total concentration of core material was also determined from the first aliquot, the mass ratio between the core material and the surface-altering moiety can be determined. Using the molecular weight of the surface-altering moiety the number of surface-altering moiety to mass of core material can be calculated. To turn this number into a surface density measurement, the surface area per mass of core material needs to be calculated. The volume of the particle is approximated as that of a sphere with the diameter obtained from DLS allowing for the calculation of the surface area per mass of core material. In this way the number of surface-altering moieties per surface area can be determined. Unless otherwise indicated, the density values herein were determined using this method.

[000154] In certain embodiments, the particles described herein comprise surface-altering moieties and/or agents that affect the zeta-potential of the particle. The zeta potential of the coated particle may be, for example, at least about -100 mV, at least about -75 mV, at least about -50 mV, at least about -40 mV, at least about -30 mV, at least about -20 mV, at least about -10 mV, at least about -5 mV, at least about 5 mV, at least about 10 mV, at least about 20 mV, at least about 30 mV, at least about 40 mV, at least about 50 mV, at least about 75 mV, or at least about 100 mV. Combinations of the above-referenced ranges are possible (*e.g.*, a zeta-potential of at least about -50 mV and less than or equal to about 50 mV). Other ranges are also possible.

[000155] The coated particles described herein may have any suitable shape and/or size. In some embodiments, a coated particle has a shape substantially similar to the shape of the core. In some cases, a coated particle described herein may be a nanoparticle, *i.e.*, the particle has a characteristic dimension of less than about 1 micrometer, where the characteristic dimension of the particle is the diameter of a perfect sphere having the same volume as the particle. In other embodiments, larger sizes are possible (*e.g.*, about 1 – 10 microns). A plurality of particles, in some embodiments, may also be characterized by an

average size (*e.g.*, an average largest cross-sectional dimension, or an average smallest cross-sectional dimension for the plurality of particles). A plurality of particles may have an average size of, for example, less than or equal to about 10 μm , less than or equal to about 5 μm , less than or equal to about 1 μm , less than or equal to about 800 nm, less than or equal to about 700 nm, less than or equal to about 500 nm, less than or equal to 400 nm, less than or equal to 300 nm, less than or equal to about 200 nm, less than or equal to about 100 nm, less than or equal to about 75 nm, less than or equal to about 50 nm, less than or equal to about 40 nm, less than or equal to about 35 nm, less than or equal to about 30 nm, less than or equal to about 25 nm, less than or equal to about 20 nm, less than or equal to about 15 nm, or less than or equal to about 5 nm. In some cases, a plurality of particles may have an average size of, for example, at least about 5 nm, at least about 20 nm, at least about 50 nm, at least about 100 nm, at least about 200 nm, at least about 300 nm, at least about 400 nm, at least about 500 nm, at least about 1 μm , at least or at least about 5 μm . Combinations of the above-referenced ranges are also possible (*e.g.*, an average size of at least about 50 nm and less than or equal to about 500 nm). Other ranges are also possible. In some embodiments, the sizes of the cores formed by a process described herein have a Gaussian-type distribution.

Pharmaceutical Agents

[000156] In some embodiments, a coated particle comprises at least one pharmaceutical agent. The pharmaceutical agent may be present in the core of the particle and/or present in a coating of the particle (*e.g.*, dispersed throughout the core and/or coating). In some cases, a pharmaceutical agent may be disposed on the surface of the particle (*e.g.*, on an outer surface of a coating, the inner surface of a coating, on a surface of the core). The pharmaceutical agent may be contained within a particle and/or disposed in a portion of the particle using commonly known techniques (*e.g.*, by coating, adsorption, covalent linkage, encapsulation, or other process). In some cases, the pharmaceutical agent may be present in the core of the particle prior to or during coating of the particle. In some cases, the pharmaceutical agent is present during the formation of the core of the particle, as described herein.

[000157] Non-limiting examples of pharmaceutical agents include imaging agents, diagnostic agents, therapeutic agents, agents with a detectable label, nucleic acids, nucleic

acid analogs, small molecules, peptidomimetics, proteins, peptides, lipids, vaccines, viral vectors, virus, and surfactants.

[000158] In some embodiments, a pharmaceutical agent contained in a particle described herein has a therapeutic, diagnostic, or imaging effect in a mucosal tissue to be targeted. Non-limiting examples of mucosal tissues include oral (*e.g.*, including the buccal and esophageal membranes and tonsil surface), ophthalmic, gastrointestinal (*e.g.*, including stomach, small intestine, large intestine, colon, rectum), nasal, respiratory (*e.g.*, including nasal, pharyngeal, tracheal and bronchial membranes), and genital (*e.g.*, including vaginal, cervical and urethral membranes) tissues.

[000159] Any suitable number of pharmaceutical agents may be present in a particle described herein. For example, at least 1, at least 2, at least 3, at least 4, at least 5, or more, but generally less than 10, pharmaceutical agents may be present in a particle described herein.

[000160] A number of drugs that are mucoadhesive are known in the art and may be used as pharmaceutical agents in the particles described herein (see, for example, Khanvilkar K, Donovan MD, Flanagan DR, Drug transfer through mucus, *Advanced Drug Delivery Reviews* 48 (2001) 173-193; Bhat PG, Flanagan DR, Donovan MD. Drug diffusion through cystic fibrotic mucus: steady-state permeation, rheologic properties, and glycoprotein morphology, *J Pharm Sci*, 1996 Jun;85(6):624-30). Additional non-limiting examples of pharmaceutical agents include imaging and diagnostic agents (such as radioopaque agents, labeled antibodies, labeled nucleic acid probes, dyes, such as colored or fluorescent dyes, *etc.*) and adjuvants (radiosensitizers, transfection-enhancing agents, chemotactic agents and chemoattractants, peptides that modulate cell adhesion and/or cell mobility, cell permeabilizing agents, vaccine potentiators, inhibitors of multidrug resistance and/or efflux pumps, *etc.*).

[000161] Additional non-limiting examples of pharmaceutical agents include aloxiprin, auranofin, azapropazone, benorylate, diflunisal, etodolac, fenbufen, fenoprofen calcium, flurbiprofen, furosemide, ibuprofen, indomethacin, ketoprofen, loteprednol etabonate, meclofenamic acid, mefenamic acid, nabumetone, naproxen, oxyphenbutazone, phenylbutazone, piroxicam, sulindac, albendazole, buphenium hydroxynaphthoate, cambendazole, dichlorophen, ivermectin, mebendazole, oxamniquine, oxfendazole, oxantel

embonate, praziquantel, pyrantel embonate, thiabendazole, amiodarone HCl, disopyramide, flecainide acetate, quinidine sulphate. Anti-bacterial agents: benethamine penicillin, cinoxacin, ciprofloxacin HCl, clarithromycin, clofazimine, cloxacillin, demeclocycline, doxycycline, erythromycin, ethionamide, imipenem, nalidixic acid, nitrofurantoin, rifampicin, spiramycin, sulphabenzamide, sulphadoxine, sulphamerazine, sulphacetamide, sulphadiazine, sulphafurazole, sulphamethoxazole, sulphapyridine, tetracycline, trimethoprim, dicoumarol, dipyridamole, nicoumalone, phenindione, amoxapine, maprotiline HCl, mianserin HCL, nortriptyline HCl, trazodone HCL, trimipramine maleate, acetoexamide, chlorpropamide, glibenclamide, glipizide, glipizide, tolazamide, tolbutamide, beclamide, carbamazepine, clonazepam, ethotoin, methoin, methsuximide, methylphenobarbitone, oxcarbazepine, paramethadione, phenacetamide, phenobarbitone, phenytoin, phensuximide, primidone, sulthiame, valproic acid, amphotericin, butoconazole nitrate, clotrimazole, econazole nitrate, fluconazole, flucytosine, griseofulvin, itraconazole, ketoconazole, miconazole, natamycin, nystatin, sulconazole nitrate, terbinafine HCl, terconazole, tioconazole, undecenoic acid, allopurinol, probenecid, sulphin-pyrazone, amlodipine, benidipine, darodipine, dilitazem HCl, diazoxide, felodipine, guanabenz acetate, isradipine, minoxidil, nicardipine HCl, nifedipine, nimodipine, phenoxybenzamine HCl, prazosin HCL, reserpine, terazosin HCL, amodiaquine, chloroquine, chlorproguanil HCl, halofantrine HCl, mefloquine HCl, roguanil HCl, pyrimethamine, quinine sulphate, dihydroergotamine mesylate, ergotamine tartrate, methysergide maleate, pizotifen maleate, sumatriptan succinate, atropine, benzhexol HCl, biperiden, ethopropazine HCl, hyoscyamine, mepenzolate bromide, oxyphencyclimine HCl, tropicamide, aminogluthetimide, amsacrine, azathioprine, busulphan, chlorambucil, cyclosporin, dacarbazine, estramustine, etoposide, lomustine, melphalan, mercaptopurine, methotrexate, mitomycin, mitotane, mitozantrone, procarbazine HCl, tamoxifen citrate, testolactone, benznidazole, clioquinol, decoquinol, diiodohydroxyquinoline, diloxanide furoate, dinitolmide, furzolidone, metronidazole, nimorazole, nitrofurazone, ornidazole, tinidazole, carbimazole, propylthiouracil, alprazolam, amylobarbitone, barbitone, bentazepam, bromazepam, bromperidol, brotizolam, butobarbitone, carbromal, chlordiazepoxide, chlormethiazole, chlorpromazine, clobazam, clotiazepam, clozapine, diazepam, droperidol, ethinamate, flunarisone, flunitrazepam, fluopromazine, flupenthixol decanoate, fluphenazine decanoate, flurazepam, haloperidol, lorazepam, lormetazepam,

medazepam, meprobamate, methaqualone, midazolam, nitrazepam, oxazepam, pentobarbitone, perphenazine pimozone, prochlorperazine, sulpiride, temazepam, thioridazine, triazolam, zopiclone, acebutolol, alprenolol, atenolol, labetalol, metoprolol, nadolol, oxprenolol, pindolol, propranolol, amrinone, digitoxin, digoxin, enoximone, lanatoside C, medigoxin, beclomethasone, betamethasone, budesonide, cortisone acetate, desoxymethasone, dexamethasone, fludrocortisone acetate, flunisolide, flucortolone, fluticasone propionate, hydrocortisone, methylprednisolone, prednisolone, prednisone, triamcinolone, acetazolamide, amiloride, bendrofluazide, bumetanide, chlorothiazide, chlorthalidone, ethacrynic acid, frusemide, metolazone, spironolactone, triamterene, bromocriptine mesylate, lysuride maleate, bisacodyl, cimetidine, cisapride, diphenoxylate HCl, domperidone, famotidine, loperamide, mesalazine, nizatidine, omeprazole, ondansetron HCl, ranitidine HCl, sulphasalazine, acrivastine, astemizole, cinnarizine, cyclizine, cyproheptadine HCl, dimenhydrinate, flunarizine HCl, loratadine, meclozine HCl, oxatamide, terfenadine, bezafibrate, clofibrate, fenofibrate, gemfibrozil, probucol, amyl nitrate, glyceryl trinitrate, isosorbide dinitrate, isosorbide mononitrate, pentaerythritol tetranitrate, betacarotene, vitamin A, vitamin B 2 , vitamin D, vitamin E, vitamin K, codeine, dextropropoxyphene, diamorphine, dihydrocodeine, meptazinol, methadone, morphine, nalbuphine, pentazocine, clomiphene citrate, danazol, ethinyl estradiol, medroxyprogesterone acetate, mestranol, methyltestosterone, norethisterone, norgestrel, estradiol, conjugated oestrogens, progesterone, stanozolol, stibestrol, testosterone, tibolone, amphetamine, dexamphetamine, dexfenfluramine, fenfluramine, and mazindol.

Uses and Pharmaceutical Compositions

[000162] The particles described herein may be employed in any suitable application. In some cases, the particles are part of pharmaceutical compositions (*e.g.*, as described herein), for example, those used to deliver a pharmaceutical agent (*e.g.*, a drug, therapeutic agent, diagnostic agent, imaging agent) through or to mucus or a mucosal surface. A pharmaceutical composition may comprise at least one particle described herein and one or more pharmaceutically acceptable excipients or carriers. The composition may be used in treating, preventing, and/or diagnosing a condition in a subject, wherein the method comprises administering to a subject the pharmaceutical composition. A subject or patient to

be treated by the articles and methods described herein may mean either a human or non-human animal, such as primates, mammals, and vertebrates.

[000163] Methods involving treating a subject may include preventing a disease, disorder or condition from occurring in the subject which may be predisposed to the disease, disorder and/or condition but has not yet been diagnosed as having it; inhibiting the disease, disorder or condition, *e.g.*, impeding its progress; and relieving the disease, disorder, or condition, *e.g.*, causing regression of the disease, disorder and/or condition. Treating the disease or condition includes ameliorating at least one symptom of the particular disease or condition, even if the underlying pathophysiology is not affected (*e.g.*, such treating the pain of a subject by administration of an analgesic agent even though such agent does not treat the cause of the pain).

[000164] In some embodiments, a pharmaceutical composition described herein is delivered to a mucosal surface in a subject and may pass through a mucosal barrier in the subject (*e.g.*, mucus), and/or may exhibit prolonged retention and/or increased uniform distribution of the particles at mucosal surfaces, *e.g.*, due to reduced mucoadhesion. Non-limiting examples of mucosal tissues include oral (*e.g.*, including the buccal and esophageal membranes and tonsil surface), ophthalmic, gastrointestinal (*e.g.*, including stomach, small intestine, large intestine, colon, rectum), nasal, respiratory (*e.g.*, including nasal, pharyngeal, tracheal and bronchial membranes), genital (*e.g.*, including vaginal, cervical and urethral membranes).

[000165] Pharmaceutical compositions described herein and for use in accordance with the articles and methods described herein may include a pharmaceutically acceptable excipient or carrier. A pharmaceutically acceptable excipient or pharmaceutically acceptable carrier may include a non-toxic, inert solid, semi-solid or liquid filler, diluent, encapsulating material or formulation auxiliary of any suitable type. Some examples of materials which can serve as pharmaceutically acceptable carriers are sugars such as lactose, glucose, and sucrose; starches such as corn starch and potato starch; cellulose and its derivatives such as sodium carboxymethyl cellulose, ethyl cellulose, and cellulose acetate; powdered tragacanth; malt; gelatin; talc; excipients such as cocoa butter and suppository waxes; oils such as peanut oil, cottonseed oil; safflower oil; sesame oil; olive oil; corn oil and soybean oil; glycols such as propylene glycol; esters such as ethyl oleate and ethyl laurate; agar; detergents such as Tween 80; buffering agents such as magnesium hydroxide and aluminum hydroxide; alginic acid;

pyrogen-free water; isotonic saline; Ringer's solution; ethyl alcohol; and phosphate buffer solutions, as well as other non-toxic compatible lubricants such as sodium lauryl sulfate and magnesium stearate, as well as coloring agents, releasing agents, coating agents, sweetening, flavoring and perfuming agents, preservatives and antioxidants can also be present in the composition, according to the judgment of the formulator. As would be appreciated by one of skill in this art, the excipients may be chosen based on the route of administration as described below, the pharmaceutical agent being delivered, time course of delivery of the agent, *etc.*

[000166] Pharmaceutical compositions containing the particles described herein may be administered to a subject via any route known in the art. These include, but are not limited to, oral, sublingual, nasal, intradermal, subcutaneous, intramuscular, rectal, vaginal, intravenous, intraarterial, intracisternally, intraperitoneal, intravitreal, periocular, topical (as by powders, creams, ointments, or drops), buccal and inhalational administration. In some embodiments, compositions described herein may be administered parenterally as injections (intravenous, intramuscular, or subcutaneous), drop infusion preparations, or suppositories. As would be appreciated by one of skill in this art, the route of administration and the effective dosage to achieve the desired biological effect may be determined by the agent being administered, the target organ, the preparation being administered, time course of administration, disease being treated, intended use, *etc.*

[000167] As an example, the particles may be included in a pharmaceutical composition to be formulated as a nasal spray, such that the pharmaceutical composition is delivered across a nasal mucus layer. As another example, the particles may be included in a pharmaceutical composition to be formulated as an inhaler, such that the pharmaceutical compositions is delivered across a pulmonary mucus layer. As another example, if compositions are to be administered orally, it may be formulated as tablets, capsules, granules, powders, or syrups. Similarly, the particles may be included in a pharmaceutical composition that is to be delivered via ophthalmic, gastrointestinal, nasal, respiratory, rectal, urethral and/or vaginal tissues.

[000168] For application by the ophthalmic mucous membrane route, subject compositions may be formulated as eye drops or eye ointments. These formulations may be prepared by conventional means, and, if desired, the subject compositions may be mixed with any

conventional additive, such as a buffering or pH-adjusting agents, tonicity adjusting agents, viscosity modifiers, suspension stabilizers, preservatives, and other pharmaceutical excipients. In addition, in certain embodiments, subject compositions described herein may be lyophilized or subjected to another appropriate drying technique such as spray drying.

[000169] In some embodiments, particles described herein that may be administered in inhalant or aerosol formulations comprise one or more pharmaceutical agents, such as adjuvants, diagnostic agents, imaging agents, or therapeutic agents useful in inhalation therapy. The particle size of the particulate medicament should be such as to permit inhalation of substantially all of the medicament into the lungs upon administration of the aerosol formulation and may be, for example, less than about 20 microns, *e.g.*, in the range of about 1 to about 10 microns, *e.g.*, about 1 to about 5 microns, although other ranges are also possible. The particle size of the medicament may be reduced by conventional means, for example by milling or micronisation. Alternatively, the particulate medicament can be administered to the lungs via nebulization of a suspension. The final aerosol formulation may contain, for example, between 0.005-90% w/w, between 0.005-50%, between 0.005-10%, between about 0.005-5% w/w, or between 0.01-1.0% w/w, of medicament relative to the total weight of the formulation. Other ranges are also possible.

[000170] It is desirable, but by no means required, that the formulations described herein contain no components which may provoke the degradation of stratospheric ozone. In particular, in some embodiments, propellants are selected that do not contain or do not consist essentially of chlorofluorocarbons such as CCl_3F , CCl_2F_2 , and CF_3CCl_3 .

[000171] The aerosol may comprise propellant. The propellant may optionally contain an adjuvant having a higher polarity and/or a higher boiling point than the propellant. Polar adjuvants which may be used include (*e.g.*, C_{2-6}) aliphatic alcohols and polyols such as ethanol, isopropanol, and propylene glycol, preferably ethanol. In general, only small quantities of polar adjuvants (*e.g.*, 0.05-3.0% w/w) may be required to improve the stability of the dispersion-the use of quantities in excess of 5% w/w may tend to dissolve the medicament. Formulations in accordance with the embodiments described herein may contain less than 1% w/w, *e.g.*, about 0.1% w/w, of polar adjuvant. However, the formulations described herein may be substantially free of polar adjuvants, especially ethanol. Suitable volatile adjuvants include saturated hydrocarbons such as propane, n-

butane, isobutane, pentane and isopentane and alkyl ethers such as dimethyl ether. In general, up to 50% w/w of the propellant may comprise a volatile adjuvant, for example, up to 30% w/w of a volatile saturated C₁-C₆ hydrocarbon. Optionally, the aerosol formulations according to the invention may further comprise one or more surfactants. The surfactants can be physiologically acceptable upon administration by inhalation. Within this category are included surfactants such as L- α -phosphatidylcholine (PC), 1,2-dipalmitoylphosphatidylcholine (DPPC), oleic acid, sorbitan trioleate, sorbitan mono-oleate, sorbitan monolaurate, polyoxyethylene sorbitan monolaurate, polyoxyethylene sorbitan monooleate, natural lecithin, oleyl polyoxyethylene ether, stearyl polyoxyethylene ether, lauryl polyoxyethylene ether, block copolymers of oxyethylene and oxypropylene, synthetic lecithin, diethylene glycol dioleate, tetrahydrofurfuryl oleate, ethyl oleate, isopropyl myristate, glyceryl monooleate, glyceryl monostearate, glyceryl monoricinoleate, cetyl alcohol, stearyl alcohol, polyethylene glycol 400, cetyl pyridinium chloride, benzalkonium chloride, olive oil, glyceryl monolaurate, corn oil, cotton seed oil, and sunflower seed oil.

[000172] The formulations described herein may be prepared by dispersal of the particles in the selected propellant and/or co-propellant in an appropriate container, *e.g.*, with the aid of sonication. The particles may be suspended in co-propellant and filled into a suitable container. The valve of the container is then sealed into place and the propellant introduced by pressure filling through the valve in the conventional manner. The particles may be thus suspended or dissolved in a liquified propellant, sealed in a container with a metering valve and fitted into an actuator. Such metered dose inhalers are well known in the art. The metering valve may meter 10 to 500 μ L and preferably 25 to 150 μ L. In certain embodiments, dispersal may be achieved using dry powder inhalers (*e.g.*, spinhaler) for the particles (which remain as dry powders). In other embodiments, nanospheres, may be suspended in an aqueous fluid and nebulized into fine droplets to be aerosolized into the lungs.

[000173] Sonic nebulizers may be used because they minimize exposing the agent to shear, which may result in degradation of the particles. Ordinarily, an aqueous aerosol is made by formulating an aqueous solution or suspension of the particles together with conventional pharmaceutically acceptable carriers and stabilizers. The carriers and stabilizers vary with the requirements of the particular composition, but typically include non-ionic surfactants

(Tweens, Pluronic[®], or polyethylene glycol), innocuous proteins like serum albumin, sorbitan esters, oleic acid, lecithin, amino acids such as glycine, buffers, salts, sugars, or sugar alcohols. Aerosols generally are prepared from isotonic solutions.

[000174] Liquid dosage forms for oral administration include pharmaceutically acceptable emulsions, microemulsions, solutions, suspensions, syrups, and elixirs. In addition to the active ingredients (*i.e.*, microparticles, nanoparticles, liposomes, micelles, polynucleotide/lipid complexes), the liquid dosage forms may contain inert diluents commonly used in the art such as, for example, water or other solvents, solubilizing agents and emulsifiers such as ethyl alcohol, isopropyl alcohol, ethyl carbonate, ethyl acetate, benzyl alcohol, benzyl benzoate, propylene glycol, 1,3-butylene glycol, dimethylformamide, oils (in particular, cottonseed, groundnut, corn, germ, olive, castor, and sesame oils), glycerol, tetrahydrofurfuryl alcohol, polyethylene glycols and fatty acid esters of sorbitan, and mixtures thereof. Besides inert diluents, the oral compositions can also include adjuvants such as wetting agents, emulsifying and suspending agents, sweetening, flavoring, and perfuming agents.

[000175] Injectable preparations, for example, sterile injectable aqueous or oleaginous suspensions may be formulated according to the known art using suitable dispersing or wetting agents and suspending agents. The sterile injectable preparation may also be a sterile injectable solution, suspension, or emulsion in a nontoxic parenterally acceptable diluent or solvent, for example, as a solution in 1,3-butanediol. Among the acceptable vehicles and solvents that may be employed are water, Ringer's solution, U.S.P. and isotonic sodium chloride solution. In addition, sterile, fixed oils are conventionally employed as a solvent or suspending medium. For this purpose any bland fixed oil can be employed including synthetic mono- or diglycerides. In addition, fatty acids such as oleic acid are used in the preparation of injectables. In certain embodiments, the particles are suspended in a carrier fluid comprising 1% (w/v) sodium carboxymethyl cellulose and 0.1% (v/v) Tween 80.

[000176] The injectable formulations can be sterilized, for example, by filtration through a bacteria-retaining filter, or by incorporating sterilizing agents in the form of sterile solid compositions which can be dissolved or dispersed in sterile water or other sterile injectable medium prior to use.

[000177] Compositions for rectal or vaginal administration can be suppositories which can be prepared by mixing the particles with suitable non-irritating excipients or carriers such as cocoa butter, polyethylene glycol, or a suppository wax which are solid at ambient temperature but liquid at body temperature and therefore melt in the rectum or vaginal cavity and release the particles.

[000178] Solid dosage forms for oral administration include capsules, tablets, pills, powders, and granules. In such solid dosage forms, the particles are mixed with at least one inert, pharmaceutically acceptable excipient or carrier such as sodium citrate or dicalcium phosphate and/or a) fillers or extenders such as starches, lactose, sucrose, glucose, mannitol, and silicic acid, b) binders such as, for example, carboxymethylcellulose, alginates, gelatin, polyvinylpyrrolidinone, sucrose, and acacia, c) humectants such as glycerol, d) disintegrating agents such as agar-agar, calcium carbonate, potato or tapioca starch, alginic acid, certain silicates, and sodium carbonate, e) solution retarding agents such as paraffin, f) absorption accelerators such as quaternary ammonium compounds, g) wetting agents such as, for example, cetyl alcohol and glycerol monostearate, h) absorbents such as kaolin and bentonite clay, and i) lubricants such as talc, calcium stearate, magnesium stearate, solid polyethylene glycols, sodium lauryl sulfate, and mixtures thereof. In the case of capsules, tablets, and pills, the dosage form may also comprise buffering agents.

[000179] Solid compositions of a similar type may also be employed as fillers in soft and hard-filled gelatin capsules using such excipients as lactose or milk sugar as well as high molecular weight polyethylene glycols and the like.

[000180] The solid dosage forms of tablets, dragees, capsules, pills, and granules can be prepared with coatings and shells such as enteric coatings and other coatings well known in the pharmaceutical formulating art. They may optionally contain opacifying agents and can also be of a composition that they release the active ingredient(s) only, or preferentially, in a certain part of the intestinal tract, optionally, in a delayed manner. Examples of embedding compositions which can be used include polymeric substances and waxes.

[000181] Solid compositions of a similar type may also be employed as fillers in soft and hard-filled gelatin capsules using such excipients as lactose or milk sugar as well as high molecular weight polyethylene glycols and the like.

[000182] Dosage forms for topical or transdermal administration of an inventive pharmaceutical composition include ointments, pastes, creams, lotions, gels, powders, solutions, sprays, inhalants, or patches. The particles are admixed under sterile conditions with a pharmaceutically acceptable carrier and any needed preservatives or buffers as may be required. Ophthalmic formulation, ear drops, and eye drops are also contemplated as being within the scope of this invention.

[000183] The ointments, pastes, creams, and gels may contain, in addition to the particles described herein, excipients such as animal and vegetable fats, oils, waxes, paraffins, starch, tragacanth, cellulose derivatives, polyethylene glycols, silicones, bentonites, silicic acid, talc, and zinc oxide, or mixtures thereof.

[000184] Powders and sprays can contain, in addition to the particles described herein, excipients such as lactose, talc, silicic acid, aluminum hydroxide, calcium silicates, and polyamide powder, or mixtures of these substances. Sprays can additionally contain customary propellants such as chlorofluorohydrocarbons.

[000185] Transdermal patches have the added advantage of providing controlled delivery of a compound to the body. Such dosage forms can be made by dissolving or dispensing the microparticles or nanoparticles in a proper medium. Absorption enhancers can also be used to increase the flux of the compound across the skin. The rate can be controlled by either providing a rate controlling membrane or by dispersing the particles in a polymer matrix or gel.

[000186] The particles described herein comprising a pharmaceutical agent may be administered to a subject to be delivered in an amount sufficient to deliver to a subject a therapeutically effective amount of an incorporated pharmaceutical agent as part of a diagnostic, prophylactic, or therapeutic treatment. In general, an effective amount of a pharmaceutical agent or component refers to the amount necessary to elicit the desired biological response. The desired concentration of pharmaceutical agent in the particle will depend on numerous factors, including, but not limited to, absorption, inactivation, and excretion rates of the drug as well as the delivery rate of the compound from the subject compositions, the desired biological endpoint, the agent to be delivered, the target tissue, *etc.* It is to be noted that dosage values may also vary with the severity of the condition to be alleviated. It is to be further understood that for any particular subject, specific dosage

regimens should be adjusted over time according to the individual need and the professional judgment of the person administering or supervising the administration of the compositions. Typically, dosing will be determined using techniques known to one skilled in the art.

[000187] The pharmaceutical agent may be present in the composition and/or formulation in any suitable amount, *e.g.*, at least about 0.01 wt%, at least about 0.1 wt%, at least about 1 wt%, at least about 5 wt%, at least about 10 wt%, at least about 20 wt% of the composition and/or formulation. In some cases, the pharmaceutical agent may be present in the composition and/or formulation at less than or equal to about 30 wt%, less than or equal to about 20 wt%, less than or equal to about 10 wt%, less than or equal to about 5 wt%, less than or equal to about 2 wt%, or less than or equal to about 1 wt%. Combinations of the above-referenced ranges are also possible (*e.g.*, present in an amount of at least about 0.1 wt% and less than or equal to about 10 wt%). Other ranges are also possible. In certain embodiments, the pharmaceutical agent is about 0.1-2 wt% of the composition and/or formulation. In certain embodiments, the pharmaceutical agent is about 2-20 wt% of the composition and/or formulation. In certain embodiments, the pharmaceutical agent is about 0.2 wt% of the composition and/or formulation. In certain embodiments, the pharmaceutical agent is about 0.4 wt% of the composition and/or formulation. In certain embodiments, the pharmaceutical agent is about 1 wt% of the composition and/or formulation. In certain embodiments, the pharmaceutical agent is about 2 wt% of the composition and/or formulation. In certain embodiments, the pharmaceutical agent is about 5 wt% of the composition and/or formulation. In certain embodiments, the pharmaceutical agent is about 10 wt% of the composition and/or formulation.

[000188] The concentration and/or amount of any pharmaceutical agent to be administered to a subject may be readily determined by one of ordinary skill in the art. Known methods are also available to assay local tissue concentrations, diffusion rates from particles and local blood flow before and after administration of the therapeutic formulation.

[000189] The compositions and/or formulations described herein may have any suitable osmolarity. In some embodiments, a composition and/or formulation described herein may have an osmolarity of at least about 0 mOsm/L, at least about 5 mOsm/L, at least about 25 mOsm/L, at least about 50 mOsm/L, at least about 75 mOsm/L, at least about 100 mOsm/L, at least about 150 mOsm/L, at least about 200 mOsm/L, at least about 250 mOsm/L, or at

least about 310 mOsm/L. In certain embodiments, a composition and/or formulation described herein may have an osmolarity of less than or equal to about 310 mOsm/L, less than or equal to about 250 mOsm/L, less than or equal to about 200 mOsm/L, less than or equal to about 150 mOsm/L, less than or equal to about 100 mOsm/L, less than or equal to about 75 mOsm/L, less than or equal to about 50 mOsm/L, less than or equal to about 25 mOsm/L, or less than or equal to about 5 mOsm/L. Combinations of the above-referenced ranges are also possible (*e.g.*, an osmolarity of at least about 0 mOsm/L and less than or equal to about 50 mOsm/L). Other ranges are also possible. The osmolarity of the composition and/or formulation can be varied by changing, for example, the concentration of salts present in the solvent of the composition and/or formulation.

[000190] In one set of embodiments, a composition and/or formulation includes one or more chelating agents. A chelating agent used herein refers to a chemical compound that has the ability to react with a metal ion to form a complex through one or more bonds. The one or more bonds are typically ionic or coordination bonds. The chelating agent can be an inorganic or an organic compound. A metal ion capable of catalyzing certain chemical reactions (*e.g.*, oxidation reactions) may lose its catalytic activity when the metal ion is bound to a chelating agent to form a complex. Therefore, a chelating agent may show preservative properties when it binds to a metal ion. Any suitable chelating agent that has preservative properties can be used, such as phosphonic acids, aminocarboxylic acids, hydroxycarboxylic acids, polyamines, aminoalcohols, and polymeric chelating agents. Specific examples of chelating agents include, but are not limited to, ethylenediaminetetraacetic acid (EDTA), nitrilotriacetic acid (NTA), diethylenetriaminepentacetic acid (DTPA), *N*-hydroxyethylethylene diaminetriacetic acid (HEDTA), tetraborates, triethylamine diamine, and salts and derivatives thereof. In certain embodiments, the chelating agent is EDTA. In certain embodiments, the chelating agent is a salt of EDTA. In certain embodiments, the chelating agent is disodium EDTA.

[000191] A chelating agent may be present at a suitable concentration in a composition and/or formulation including the coated particles described herein. In certain embodiments, the concentration of the chelating agent is greater than or equal to about 0.0003 wt%, greater than or equal to about 0.001wt%, greater than or equal to about 0.003wt%, greater than or equal to about 0.01wt%, greater than or equal to about 0.03wt%, greater than or equal to

about 0.05 wt%, greater than or equal to about 0.1wt%, greater than or equal to about 0.3wt%, greater than or equal to about 1wt%, or greater than or equal to about 3wt%. In certain embodiments, the concentration of the chelating agent is less than or equal to about 3wt%, less than or equal to about 1wt%, less than or equal to about 0.3wt%, less than or equal to about 0.1wt%, less than or equal to about 0.05 wt%, less than or equal to about 0.03wt%, less than or equal to about 0.01wt%, less than or equal to about 0.003wt%, less than or equal to about 0.001 wt%, or less than or equal to about 0.0003wt%. Combinations of the above-noted ranges are possible (*e.g.*, a concentration of greater than or equal to about 0.01 wt% and less than or equal to about 0.3wt%). Other ranges are also possible. In certain embodiments, the concentration of the chelating agent is about 0.001-0.1 wt%. In certain embodiments, the concentration of the chelating agent is about 0.005 wt%. In certain embodiments, the concentration of the chelating agent is about 0.01 wt%. In certain embodiments, the concentration of the chelating agent is about 0.05wt%. In certain embodiments, the concentration of the chelating agent is about 0.1 wt%.

[000192] In some embodiments, a chelating agent may be present in a composition and/or formulation in one or more of the above-noted ranges during a formation process and/or a dilution process described herein. In certain embodiments, a chelating agent may be present in a composition and/or formulation in one or more of the above-noted ranges in a final product.

[000193] In some embodiments, an antimicrobial agent may be included in a composition and/or formulation including the coated particles described herein. An antimicrobial agent used herein refers to a bioactive agent effective in the inhibition of, prevention of, or protection against microorganisms such as bacteria, microbes, fungi, viruses, spores, yeasts, molds, and others generally associated with infections. Examples of antimicrobial agents include cephalosporins, clindamycin, chloramphenicol, carbapenems, minocyclines, rifampin, penicillins, monobactams, quinolones, tetracycline, macrolides, sulfa antibiotics, trimethoprim, fusidic acid, aminoglycosides, amphotericin B, azoles, flucytosine, cilofungin, bactericidal nitrofurans, nanoparticles of metallic silver or an alloy of silver containing about 2.5 wt % copper, silver citrate, silver acetate, silver benzoate, bismuth pyrithione, zinc pyrithione, zinc percarbonates, zinc perborates, bismuth salts, parabens (*e.g.*,

methyl-, ethyl-, propyl-, butyl-, and octyl-benzoic acid esters), citric acid, benzalkonium chloride (BAC), rifamycin, and sodium percarbonate.

[000194] An antimicrobial agent may be present at a suitable concentration in a composition and/or formulation including the coated particles described herein. In certain embodiments, the concentration of the antimicrobial agent may be greater than or equal to about 0.0003wt%, greater than or equal to about 0.001wt%, greater than or equal to about 0.003wt%, greater than or equal to about 0.01wt%, greater than or equal to about 0.03wt%, greater than or equal to about 0.1wt%, greater than or equal to about 0.3wt%, greater than or equal to about 1wt%, or greater than or equal to about 3wt%. In certain embodiments, the concentration of the antimicrobial agent may be less than or equal to about 3wt%, less than or equal to about 1wt%, less than or equal to about 0.3wt%, less than or equal to about 0.1wt%, less than or equal to about 0.03wt%, less than or equal to about 0.01wt%, less than or equal to about 0.003wt%, less than or equal to about 0.001wt%, or less than or equal to about 0.0003wt%. Combinations of the above-noted ranges are possible (*e.g.*, a concentration of greater than or equal to about 0.001 wt% and less than or equal to about 0.1wt%). Other ranges are also possible. In certain embodiments, the concentration of the antimicrobial agent is about 0.001-0.05 wt%. In certain embodiments, the concentration of the antimicrobial agent is about 0.002 wt%. In certain embodiments, the concentration of the antimicrobial agent is about 0.005 wt%. In certain embodiments, the concentration of the antimicrobial agent is about 0.01wt%. In certain embodiments, the concentration of the antimicrobial agent is about 0.02 wt%. In certain embodiments, the concentration of the antimicrobial agent is about 0.05 wt%.

[000195] In some embodiments, an antimicrobial agent may be present in a composition and/or formulation in one or more of the above-noted ranges during a formation process and/or a dilution process described herein. In certain embodiments, an antimicrobial agent may be present in a composition and/or formulation in one or more of the above-noted ranges in a final product.

[000196] In some embodiments, a tonicity agent may be included in a composition and/or formulation including the coated particles described herein. A tonicity agent used herein refers to a compound or substance that can be used to adjust the composition of a formulation to the desired osmolarity range. In certain embodiments, the desired osmolarity range is an

isotonic range compatible with blood. In certain embodiments, the desired osmolarity range is hypotonic. In certain embodiments, the desired osmolarity range is hypertonic. Examples of tonicity agents include glycerin, lactose, mannitol, dextrose, sodium chloride, sodium sulfate, sorbitol, saline-sodium citrate (SSC), and the like. In certain embodiments, a combination of one or more tonicity agents may be used. In certain embodiments, the tonicity agent is glycerin. In certain embodiments, the tonicity agent is sodium chloride.

[000197] A tonicity agent (such as one described herein) may be present at a suitable concentration in a composition and/or formulation including the coated particles described herein. In certain embodiments, the concentration of the tonicity agent is greater than or equal to about 0.003wt%, greater than or equal to about 0.01wt%, greater than or equal to about 0.03wt%, greater than or equal to about 0.1wt%, greater than or equal to about 0.3wt%, greater than or equal to about 1wt%, greater than or equal to about 3wt%, greater than or equal to about 10wt%, greater than or equal to about 20 wt%, or greater than or equal to about 30wt%. In certain embodiments, the concentration of the tonicity agent is less than or equal to about 30 wt%, less than or equal to about 10 wt%, less than or equal to about 3 wt%, less than or equal to about 1 wt%, less than or equal to about 0.3wt%, less than or equal to about 0.1wt%, less than or equal to about 0.03wt%, less than or equal to about 0.01 wt%, or less than or equal to about 0.003 wt%. Combinations of the above-noted ranges are possible (*e.g.*, a concentration of greater than or equal to about 0.1wt% and less than or equal to about 10wt%). Other ranges are also possible. In certain embodiments, the concentration of the tonicity agent is about 0.1-1%. In certain embodiments, the concentration of the tonicity agent is about 0.5-3%. In certain embodiments, the concentration of the tonicity agent is about 0.25 wt%. In certain embodiments, the concentration of the tonicity agent is about 0.45wt%. In certain embodiments, the concentration of the tonicity agent is about 0.9wt%. In certain embodiments, the concentration of the tonicity agent is about 1.2wt%. In certain embodiments, the concentration of the tonicity agent is about 2.4wt%. In certain embodiments, the concentration of the tonicity agent is about 5 wt%.

[000198] In some embodiments, a tonicity agent may be present in a composition and/or formulation in one or more of the above-noted ranges during a formation process and/or a dilution process described herein. In certain embodiments, a tonicity agent may be present in a composition and/or formulation in one or more of the above-noted ranges in a final product.

[000199] It is appreciated in the art that the ionic strength of a formulation comprising particles may affect the polydispersity of the particles. Polydispersity is a measure of the heterogeneity of sizes of particles in a formulation. Heterogeneity of particle sizes may be due to differences in individual particle sizes and/or to the presence of aggregation in the formulation. A formulation comprising particles is considered substantially homogeneous or “monodisperse” if the particles have essentially the same size, shape, and/or mass. A formulation comprising particles of various sizes, shapes, and/or masses is deemed heterogeneous or “polydisperse”.

[000200] The ionic strength of a formulation comprising particles may also affect the colloidal stability of the particles. For example, a relatively high ionic strength of a formulation may cause the particles of the formulation to coagulate and therefore may destabilize the formulation. In some embodiments, a formulation comprising particles is stabilized by repulsive inter-particle forces. For example, the particles may be electrically or electrostatically charged. Two charged particles may repel each other, preventing collision and aggregation. When the repulsive inter-particle forces weaken or become attractive, particles may start to aggregate. For instance, when the ionic strength of the formulation is increased to a certain level, the charges (*e.g.*, negative charges) of the particles may be neutralized by the oppositely charged ions present in the formulation (*e.g.*, Na^+ ions in solution). As a result, the particles may collide and bond to each other to form aggregates (*e.g.*, clusters or flocs) of larger sizes. The formed aggregates of particles may also differ in size, and thus the polydispersity of the formulation may also increase. For example, a formulation comprising similarly-sized particles may become a formulation comprising particles having various sizes (*e.g.*, due to aggregation) when the ionic strength of the formulation is increased beyond a certain level. In the course of aggregation, the aggregates may grow in size and eventually settle to the bottom of the container, and the formulation is considered colloidally unstable. Once the particles in a formulation form aggregates, it is usually difficult to disrupt the aggregates into individual particles.

[000201] Certain formulations described herein show unexpected properties in that, among other things, the presence of one or more ionic tonicity agents (*e.g.*, a salt such as NaCl) in the formulations at certain concentrations actually decreases or maintains the degree of aggregation of the particles present in the formulations, and/or does not significantly increase

aggregation. In certain embodiments, the polydispersity of a formulation decreases, is relatively constant, or does not change by an appreciable amount upon addition of one or more ionic tonicity agents into the formulation.

[000202] For example, in some embodiments, the polydispersity of a composition and/or formulation is relatively constant in the presence of added ionic strength and/or when the added ionic strength of the composition and/or formulation is kept relatively constant or increased (*e.g.*, during a formation and/or dilution process). In certain embodiments, when the ionic strength increases by at least 50%, the polydispersity increases by less than or equal to about 200%, less than or equal to about 150%, less than or equal to about 100%, less than or equal to about 75%, less than or equal to about 50%, less than or equal to about 30%, less than or equal to about 20%, less than or equal to about 10%, less than or equal to about 3%, or less than or equal to about 1%. In certain embodiments, when the ionic strength is increased by at least 50%, the polydispersity increases by greater than or equal to about 1%, greater than or equal to about 3%, greater than or equal to about 10%, greater than or equal to about 30%, or greater than or equal to about 100%. Combinations of the above-noted ranges are possible (*e.g.*, an increase in polydispersity of less than or equal to 50% and greater than or equal to 1%). Other ranges are also possible.

[000203] The ionic strength of a formulation described herein may be controlled (*e.g.*, increased) through a variety of means, such as the addition of one or more ionic tonicity agents (*e.g.*, a salt such as NaCl) to the formulation. In certain embodiments, the ionic strength of a formulation described herein is greater than or equal to about 0.0005 M, greater than or equal to about 0.001 M, greater than or equal to about 0.003 M, greater than or equal to about 0.01 M, greater than or equal to about 0.03 M, greater than or equal to about 0.1 M, greater than or equal to about 0.3 M, greater than or equal to about 1 M, greater than or equal to about 3 M, or greater than or equal to about 10 M. In certain embodiments, the ionic strength of a formulation described herein is less than or equal to about 10 M, less than or equal to about 3 M, less than or equal to about 1 M, less than or equal to about 0.3 M, less than or equal to about 0.1 M, less than or equal to about 0.03 M, less than or equal to about 0.01 M, less than or equal to about 0.003 M, less than or equal to about 0.001 M, or less than or equal to about 0.0005 M. Combinations of the above-noted ranges are possible (*e.g.*, an ionic strength of greater than or equal to about 0.01 M and less than or equal to about 1 M).

Other ranges are also possible. In certain embodiments, the ionic strength of a formulation described herein is about 0.1 M. In certain embodiments, the ionic strength of a formulation described herein is about 0.15 M. In certain embodiments, the ionic strength of a formulation described herein is about 0.3 M.

[000204] In certain embodiments, the polydispersity of a formulation does not change upon addition of one or more ionic tonicity agents into the formulation. In certain embodiments, the polydispersity does not significantly increase upon addition of one or more ionic tonicity agents into the formulation. In certain embodiments, the polydispersity increases to a level described herein upon addition of one or more ionic tonicity agents into the formulation.

[000205] The polydispersity of a formulation described herein may be measured by the polydispersity index (PDI). The PDI is used to describe the width of the particle size distribution and is often calculated from a cumulants analysis of the dynamic light scattering (DLS) measured intensity autocorrelation function. The calculations for these parameters are defined in the standards ISO 13321:1996 E and ISO 22412:2008. The PDI is dimensionless and, when measured by DLS, scaled such that values smaller than 0.05 indicate a highly monodisperse sample while values greater than 0.7 indicate a very broad size distribution. In certain embodiments, the PDI of a formulation and/or composition described herein is less than or equal to about 1, less than or equal to about 0.9, less than or equal to about 0.8, less than or equal to about 0.7, less than or equal to about 0.6, less than or equal to about 0.5, less than or equal to about 0.4, less than or equal to about 0.3, less than or equal to about 0.2, less than or equal to about 0.15, less than or equal to about 0.1, less than or equal to about 0.05, less than or equal to about 0.01, or less than or equal to about 0.005. In certain embodiments, the PDI of a formulation and/or composition described herein is greater than or equal to about 0.005, greater than or equal to about 0.01, greater than or equal to about 0.05, greater than or equal to about 0.1, greater than or equal to about 0.15, greater than or equal to about 0.2, greater than or equal to about 0.3, greater than or equal to about 0.4, greater than or equal to about 0.5, greater than or equal to about 0.6, greater than or equal to about 0.7, greater than or equal to about 0.8, greater than or equal to about 0.9, or greater than or equal to about 1. Combinations of the above-noted ranges are possible (*e.g.*, a PDI of greater than or equal to about 0.1 and less than or equal to about 0.5). Other ranges are also possible. In certain

embodiments, the PDI of a formulation is about 0.1. In certain embodiments, the PDI of a formulation is about 0.15. In certain embodiments, the PDI of a formulation is about 0.2.

[000206] In certain embodiments, the compositions and/or formulations described herein may be highly dispersible and do not tend to form aggregates. Even when the particles do form aggregates, the aggregates may be easily broken up into individual particles without rigorously agitating the compositions and/or formulations.

[000207] Generally, it is desired that a formulation is sterile before or upon administration to a subject. A sterile formulation is essentially free of pathogenic microorganisms, such as bacteria, microbes, fungi, viruses, spores, yeasts, molds, and others generally associated with infections. In some embodiments, compositions and/or formulations including the coated particles described herein may be subject to an aseptic process and/or other sterilization process. An aseptic process typically involves sterilizing the components of a formulation, final formulation, and/or container closure of a drug product through a process such as heat, gamma irradiation, ethylene oxide, or filtration and then combining in a sterile environment. In some cases, an aseptic process is preferred. In other embodiments, terminal sterilization is preferred.

[000208] Examples of other sterilization methods include radiation sterilization (*e.g.*, gamma, electron, or x-ray radiation), heat sterilization, sterile filtration, and ethylene oxide sterilization. The terms “radiation” and “irradiation” are used herein interchangeably. Unlike other sterilization methods, radiation sterilization has the advantage of high penetrating ability and instantaneous effects, without the need to control temperature, pressure, vacuum, or humidity in some instances. In certain embodiments, the radiation used to sterilize the coated particles described herein is gamma radiation. Gamma radiation may be applied in an amount sufficient to kill most or substantially all of the microbes in or on the coated particles. The temperature of the coated particles described herein and the rate of radiation may be relatively constant during the entire gamma radiation period. Gamma irradiation may be performed at any suitable temperature (*e.g.*, ambient temperature, about 40 °C, between about 30 to about 50 °C). Unless otherwise indicated, measurements of gamma irradiation described herein refer to ones performed at about 40 °C.

[000209] In embodiments in which a sterilization process is used, it may be desired that the process does not: (1) significantly change the particle size of the coated particles described

herein; (2) significantly change the integrity of the active ingredient (such as a drug) of the coated particles described herein; and (3) generate unacceptable concentrations of impurities during or following the process. In certain embodiments, the impurities generated during or following the process are degradants of the active ingredient of the coated particles described herein.

[000210] The compositions and/or formulations described herein may have any suitable pH values. The term “pH,” unless otherwise provided, refers to pH measured at ambient temperature (*e.g.*, about 20 °C, about 23 °C, or about 25 °C). The compositions and/or formulations have, for example, an acidic pH, a neutral pH, or a basic pH and may depend on, for example, where the compositions and/or formulations are to be delivered in the body. In certain embodiments, the compositions and/or formulations have a physiological pH. In certain embodiments, the pH value of the compositions and/or formulations is at least about 1, at least about 2, at least about 3, at least about 4, at least about 5, at least about 6, at least about 6.2, at least about 6.4, at least about 6.6, at least about 6.8, at least about 7, at least about 7.2, at least about 7.4, at least about 7.6, at least about 7.8, at least about 8, at least about 8.2, at least about 8.4, at least about 8.6, at least about 8.8, at least about 9, at least about 10, at least about 11, or at least about 12. In certain embodiments, the pH value of the compositions and/or formulations is less than or equal to about 12, less than or equal to about 11, less than or equal to about 10, less than or equal to about 9, less than or equal to about 8.8, less than or equal to about 8.6, less than or equal to about 8.4, less than or equal to about 8.2, less than or equal to about 8, less than or equal to about 7.8, less than or equal to about 7.6, less than or equal to about 7.4, less than or equal to about 7.2, less than or equal to about 7, less than or equal to about 6.8, less than or equal to about 6.6, less than or equal to about 6.4, less than or equal to about 6.2, less than or equal to about 6, less than or equal to about 5, less than or equal to about 4, less than or equal to about 3, less than or equal to about 2, or less than or equal to about 1. Combinations of the above-noted ranges are possible (*e.g.*, a pH value of at least about 5 and less than or equal to about 8.2). Other ranges are also possible. In certain embodiments, the pH value of the compositions and/or formulations described herein is at least about 5 and less than or equal to about 8.

[000211] In one set of embodiments, a composition comprising a plurality of coated particles is provided. The coated particles include a core particle comprising a

pharmaceutical agent or a salt thereof and a coating comprising a surface-altering agent surrounding the core particle. The core particle including the pharmaceutical agent or a salt thereof may be, for example, a solid and may have an aqueous solubility of less than or equal to about 1 mg/mL at 25 °C (e.g., less than or equal to about 0.1 mg/mL at 25 °C) at any point throughout the pH range. However, other cores (e.g., polymer cores) may be used, as described herein. The surface-altering agent is or comprises a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer. The polymer has a molecular weight of at least about 1 kDa and less than or equal to about 1000 kDa (e.g., less than or equal to about 200 kDa), and may be least about 30% hydrolyzed (e.g., at least about 70% hydrolyzed) and less than or equal to about 98% hydrolyzed (e.g., less than about 95% hydrolyzed). The synthetic polymer may be, for example, poly(vinyl alcohol), a partially hydrolyzed poly(vinyl acetate) or a copolymer of vinyl alcohol and vinyl acetate. (In certain embodiments, the polymer is a PVA that is less than or equal to about 98% hydrolyzed and has a molecular weight of less than or equal to about 75 kDa, or a PVA that is less than about 95% hydrolyzed.) The surface-altering agent may be adsorbed to the surface of the core particle. In certain cases, the surface-altering agent is present on the surface of the core particle at a density of at least about 0.001 molecules per nanometer squared (e.g., at least about 0.01 molecules per nanometer squared). The coated particles have a relative velocity of greater than 0.5 in mucus. The coated particles may have an average size of at least about 20 nm and less than or equal to about 1 μ m (e.g., less than or equal to about 500 nm). The thickness of the coating may be, for example, less than or equal to about 100 nm (e.g., less than or equal to about 50 nm, less than or equal to about 30 nm, less than or equal to about 10 nm). The composition may be a pharmaceutical composition including one or more pharmaceutically acceptable carriers, additives, and/or diluents. The total amount of surface-altering agent present in the composition may be, for example, between about 0.001% to about 5% by weight (e.g., between about 0.01% to about 5% by weight, or between about 0.1% to about 5% by weight). In some embodiments, the PDI of the composition is greater than or equal to about 0.1 and less than or equal to about 0.5 (e.g., less than or equal to about 0.3, or less than or equal to about 0.2). Optionally, in some embodiments, the plurality of coated particles are in solution (e.g., an aqueous solution) with one or more free surface-altering agents in the composition. The free surface-altering agent(s) in solution and surface-

altering agent on the surface of the particle may be the same (or different) surface-altering agent(s) and may be in equilibrium with each other in the composition. Methods of use and/or delivery of such compositions to a patient or subject (e.g., to mucus or a mucus membrane) are also provided.

[000212] In one set of embodiments, a composition comprising a plurality of coated particles is provided. The coated particles include a core particle comprising a pharmaceutical agent or a salt thereof and a coating comprising a surface-altering agent surrounding the core particle. The core particle including the pharmaceutical agent or a salt thereof may be, for example, a solid and may have an aqueous solubility of less than or equal to about 1 mg/mL at 25 °C (e.g., less than or equal to about 0.1 mg/mL at 25 °C) at any point throughout the pH range. However, other cores (e.g., polymer cores) may be used, as described herein. The surface-altering agent is or comprises a poly(vinyl alcohol), wherein the poly(vinyl alcohol) is selected from PVA 13K87, PVA 31K98, PVA 31K87, PVA 9K80, PVA 2K75, PVA 57K87, PVA 85K87, PVA105K80, PVA130K87 (where the numbers before and after “K” indicate PVA’s molecular weight in kDa and hydrolysis degree in %, respectively), and combinations thereof. The surface-altering agent may be adsorbed to the surface of the core particle. In certain cases, the surface-altering agent is present on the surface of the core particle at a density of at least about 0.001 molecules per nanometer squared (e.g., at least about 0.01 molecules per nanometer squared). The coated particles have a relative velocity of greater than 0.5 in mucus. The coated particles may have an average size of at least about 20 nm and less than or equal to about 1 μ m (e.g., less than or equal to about 500 nm). The thickness of the coating may be, for example, less than or equal to about 100 nm (e.g., less than or equal to about 50 nm, less than or equal to about 30 nm, less than or equal to about 10 nm). The composition may be a pharmaceutical composition including one or more pharmaceutically acceptable carriers, additives, and/or diluents. The total amount of surface-altering agent present in the composition may be, for example, between about 0.001% to about 5% by weight (e.g., between about 0.01% to about 5% by weight, or between about 0.1% to about 5% by weight). In some embodiments, the PDI of the composition is greater than or equal to about 0.1 and less than or equal to about 0.5 (e.g., less than or equal to about 0.3, or less than or equal to about 0.2). Optionally, in some embodiments, the plurality of coated particles are in solution (e.g., an aqueous solution) with

one or more free surface-altering agents in the composition. The free surface-altering agent(s) in solution and surface-altering agent on the surface of the particle may be the same (or different) surface-altering agent(s) and may be in equilibrium with each other in the composition. Methods of use and/or delivery of such compositions to a patient or subject (e.g., to mucus or a mucus membrane) are also provided.

[000213] These and other aspects of the present invention will be further appreciated upon consideration of the following Examples, which are intended to illustrate certain particular embodiments of the invention but are not intended to limit its scope, as defined by the claims.

Examples

Example 1

[000214] The following describes a non-limiting example of a method of forming mucus-penetrating particles from pre-fabricated polymeric particles by physical adsorption of certain poly(vinyl alcohol) polymers (PVA). Carboxylated polystyrene nanoparticles (PSCOO) were used as the prefabricated particle / core particle with a well-established strongly mucoadhesive behavior. The PVAs acted as surface-altering agents forming coatings around the core particles. PVA of various molecular weights (MW) and hydrolysis degrees were evaluated to determine effectiveness of the coated particles in penetrating mucus.

[000215] PSCOO particles were incubated in aqueous solution in the presence of various PVA polymers to determine whether certain PVAs can physically (non-covalently) coat the core particle with a mucoinert coating that would minimize particle interactions with mucus constituents and lead to rapid particle penetration in mucus. In these experiments, the PVA acted as a coating around the core particles, and the resulting particles were tested for their mobility in mucus, although in other embodiments, PVA may be exchanged with other surface-altering agents that can increase mobility of the particles in mucus. The PVAs tested ranged in the average molecular weight from 2 kDa to 130 kDa and in the average hydrolysis degree from 75% to 99+%. The PVAs that were tested are listed in Table 1, shown above.

[000216] The particle modification process was as follows: 200nm carboxylated-modified red fluorescent polystyrene nanoparticles (PSCOO) were purchased from Invitrogen. The

PSCOO particles (0.4 - 0.5 %wt) were incubated in an aqueous PVA solution (0.4 – 0.5 %wt) for at least 1 hour at room temperature.

[000217] The mobility and distribution of the modified nanoparticles in human cervicovaginal mucus (CVM) were characterized using fluorescence microscopy and multiple particle tracking software. In a typical experiment, $\leq 0.5 \mu\text{L}$ of an incubated nanosuspension (diluted $\sim 10\times$ with 0.5 %wt aqueous solution of a corresponding PVA) was added to 20 μl of fresh CVM along with controls. Conventional nanoparticles (200 nm blue fluorescent carboxylate-modified polystyrene microspheres from Invitrogen) were used as a negative control to confirm the barrier properties of the CVM samples. Yellow-green fluorescent polystyrene nanoparticles covalently coated with PEG 2 kDa were used as a positive control with well-established MPP behavior. Using a fluorescent microscope equipped with a CCD camera, 15 s movies were captured at a temporal resolution of 66.7 ms (15 frames/s) under 100x magnification from several areas within each sample for each type of particles: sample (observed through a Texas Red filter set), negative control (observed through a DAPI filter set), and positive control (observed through a FITC filter set). Next, using an advanced image processing software, individual trajectories of multiple particles were measured over a time-scale of at least 3.335 s (50 frames). Resulting transport data are presented here in the form of trajectory-mean velocity V_{mean} , *i.e.*, velocity of an individual particle averaged over its trajectory, and ensemble-average velocity $\langle V_{\text{mean}} \rangle$, *i.e.*, V_{mean} averaged over an ensemble of particles. To enable easy comparison between different samples and normalize velocity data with respect to natural variability in penetrability of CVM samples, ensemble-average (absolute) velocity is then converted to relative sample velocity $\langle V_{\text{mean}} \rangle_{\text{rel}}$ according to the formula shown in Equation 1. Multiple particle tracking confirmed that in all tested CVM samples the negative controls were constrained, while the positive controls were mobile as demonstrated by the differences in $\langle V_{\text{mean}} \rangle$ for the positive and negative controls (Table 3).

[000218] Table 3. Transport of nanoparticles incubated with various PVA (sample) and controls in CVM: Ensemble-average velocity $\langle V_{\text{mean}} \rangle$ ($\mu\text{m/s}$) and relative sample velocity $\langle V_{\text{mean}} \rangle_{\text{rel}}$.

Stabilizer/Surface-	Negative Control	Positive Control	Sample	Sample (relative)
---------------------	------------------	------------------	--------	-------------------

altering agent	$\langle V_{\text{mean}} \rangle$	SD	$\langle V_{\text{mean}} \rangle$	SD	$\langle V_{\text{mean}} \rangle$	SD	$\langle V_{\text{mean}} \rangle_{\text{rel}}$	SD
PVA2K75	1.39	0.33	3.3	0.68	3.44	0.7	1.07	0.59
PVA9K80	0.4	0.08	5.13	1.16	4.88	1.74	0.95	0.44
PVA13K87	0.56	0.61	5.23	1.24	4.92	1.77	0.93	0.49
PVA31K87	0.53	0.63	4.48	1.38	3.69	1.94	0.80	0.60
PVA57K86	0.5	0.25	5.74	1.11	4.76	0.91	0.81	0.25
PVA85K87	0.29	0.28	4.25	0.97	4.01	0.71	0.94	0.31
PVA105K80	0.98	0.52	5.44	0.86	4.93	0.66	0.89	0.27
PVA130K87	1.41	0.56	3.75	0.82	3.57	0.6	0.92	0.53
PVA95K95	0.51	0.36	3.19	0.68	0.45	0.19	-0.02	-0.15
PVA13K98	0.43	0.17	3.42	1.65	0.5	0.76	0.02	0.26
PVA31K98	0.41	0.23	6.03	1.19	0.26	0.14	-0.03	-0.05
PVA85K99	0.28	0.1	4.7	0.82	0.53	0.77	0.06	0.18

[000219] It was discovered that nanoparticles incubated in the presence of certain (but, interestingly, not all) PVA transported through CVM at the same rate or nearly the same velocity as the positive control. Specifically, the particles stabilized with PVA2K75, PVA9K80, PVA13K87, PVA31K87, PVA57K86, PVA85K87, PVA105K80, and PVA130K87 exhibited $\langle V_{\text{mean}} \rangle$ that significantly exceeded those of the negative controls and were indistinguishable, within experimental error, from those of the positive controls. The results are shown in Table 3 and FIG. 2A. For these samples, $\langle V_{\text{mean}} \rangle_{\text{rel}}$ values exceeded 0.5, as shown in FIG. 2B.

[000220] On the other hand, nanoparticles incubated with PVA95K95, PVA13K98, PVA31K98, and PVA85K99 were predominantly or completely immobilized as demonstrated by respective $\langle V_{\text{mean}} \rangle_{\text{rel}}$ values of no greater than 0.1 (Table 3 and FIG. 2B).

[000221] To identify the characteristics of the PVA that render particles mucus penetrating, $\langle V_{\text{mean}} \rangle_{\text{rel}}$ of the nanoparticles prepared by incubation with the various PVAs was mapped with respect to MW and hydrolysis degree of the PVAs used (FIG. 3). It was concluded that at least those PVAs that have the hydrolysis degree of less than 95% rendered the nanocrystals mucus-penetrating. Without wishing to be bound by any theory, it is believed that the unhydrolyzed (vinyl acetate) units of PVA can provide effective hydrophobic association with the surface of the core particles if the content of these segments in the PVA is sufficient (*e.g.*, greater than 5% in some embodiments); while the hydrophilic (vinyl alcohol) units of PVA present at the surface of the coated particles render them hydrophilic and can shield the coated particles from adhesive interactions with mucus.

[000222] To further confirm the ability of the specific PVA grades to convert mucoadhesive particles into mucus-penetrating particles by physical adsorption, PSCOO nanoparticles incubated with the various PVAs were tested using the bulk transport assay. In this method, 20 μ L of CVM was collected in a capillary tube and one end is sealed with clay. The open end of the capillary tube is then submerged in 20 μ L of an aqueous suspension of particles which is 0.5% w/v drug. After the desired time, typically 18 hours, the capillary tube is removed from the suspension and the outside is wiped clean. The capillary containing the mucus sample is placed in an ultracentrifuge tube. Extraction media is added to the tube and incubated for 1 hour while mixing which removes the mucus from the capillary tube and extracts the drug from the mucus. The sample is then spun to remove mucins and other non-soluble components. The amount of drug in the extracted sample can then be quantified using HPLC. The results of these experiments are in good agreement with those of the microscopy method, showing clear differentiation in transport between positive (mucus-penetrating particles) and negative controls (conventional particles). The bulk transport results for PSCOO nanoparticles incubated with the various PVAs are shown in FIG. 4. These results corroborate microscopy / particle tracking findings with PSCOO nanoparticles incubated with the various PVAs and demonstrate the incubating nanoparticles with partially hydrolyzed PVAs enhances mucus penetration.

Example 2

[000223] The following describes a non-limiting example of a method of forming mucus-penetrating particles by an emulsification process in the presence of certain poly(vinyl alcohol) polymers (PVA). Polylactide (PLA), a biodegradable pharmaceutically relevant polymer was used as a material to form the core particle via an oil-in-water emulsification process. The PVAs acted as emulsion stabilizers and surface-altering agents forming coatings around the produced core particles. PVA of various molecular weights (MW) and hydrolysis degrees were evaluated to determine effectiveness of the formed particles in penetrating mucus.

[000224] PLA solution in dichloromethane was emulsified in aqueous solution in the presence of various PVA to determine whether certain PVAs can physically (non-covalently) coat the surface of generated nanoparticles with a coating that would lead to rapid particle

penetration in mucus. In these experiments, the PVA acted as a surfactant that forms a stabilizing coating around droplets of emulsified organic phase that, upon solidification, form the core particles. The resulting particles were tested for their mobility in mucus, although in other embodiments, PVA may be exchanged with other surface-altering agents that can increase mobility of the particles in mucus. The PVAs tested ranged in the average molecular weight from 2 kDa to 130 kDa and in the average hydrolysis degree from 75% to 99+%. The PVAs that were tested are listed in Table 1, shown above.

[000225] The emulsification-solvent evaporation process was as follows: Approximately 0.5 mL of 20-40 mg/ml solution of PLA (Polylactide grade 100DL7A, purchased from Surmodics) in dichloromethane was emulsified in approximately 4mL of an aqueous PVA solution (0.5 – 2 %wt) by sonication to obtain a stable emulsion with the target number-average particle size of <500 nm. Obtained emulsions were immediately subjected to exhaustive rotary evaporation under reduced pressure at room temperature to remove the organic solvent. Obtained suspensions were filtered through 1 micron glass fiber filters to remove any agglomerates. Table 4 lists the particle size characteristics of the nanosuspensions obtained by this emulsification procedure with the various PVA. In all cases, a fluorescent organic dye Nile Red was added to the emulsified organic phase to fluorescently label the resulting particles.

[000226] **Table 4.** Particle size measured by DLS in nanosuspensions obtained by the emulsification process with various PVA.

PVA Grade	Z-Ave D (nm)	N-Ave D (nm)
PVA2K75	186	156
PVA10K80	208	173
PVA13K98	245	205
PVA31K87	266	214
PVA31K98	245	228
PVA85K87	356	301
PVA85K99	446	277
PVA95K95	354	301

PVA105K80	361	300
PVA130K87	293	243

[000227] The mobility and distribution of the produced nanoparticles in human cervicovaginal mucus (CVM) were characterized using fluorescence microscopy and multiple particle tracking software. In a typical experiment, $\leq 0.5 \mu\text{L}$ of a nanosuspension (diluted if necessary to the PVA concentration of $\sim 0.5\%$) was added to $20 \mu\text{L}$ of fresh CVM along with controls. Conventional nanoparticles (200 nm blue fluorescent carboxylate-modified polystyrene microspheres from Invitrogen) were used as a negative control to confirm the barrier properties of the CVM samples. Yellow-green fluorescent polystyrene nanoparticles covalently coated with PEG 2 kDa were used as a positive control with well-established MPP behavior. Using a fluorescent microscope equipped with a CCD camera, 15 s movies were captured at a temporal resolution of 66.7 ms (15 frames/s) under 100x magnification from several areas within each sample for each type of particles: sample (observed through a Texas Red filter set due to the encapsulated Nile Red), negative control (observed through a DAPI filter set), and positive control (observed through a FITC filter set). Next, using an advanced image processing software, individual trajectories of multiple particles were measured over a time-scale of at least 3.335 s (50 frames). Resulting transport data are presented here in the form of trajectory-mean velocity V_{mean} , *i.e.*, velocity of an individual particle averaged over its trajectory, and ensemble-average velocity $\langle V_{\text{mean}} \rangle$, *i.e.*, V_{mean} averaged over an ensemble of particles. To enable easy comparison between different samples and normalize velocity data with respect to natural variability in penetrability of CVM samples, ensemble-average (absolute) velocity is then converted to relative sample velocity $\langle V_{\text{mean}} \rangle_{\text{rel}}$ according to the formula shown in Equation 1. Multiple particle tracking confirmed that in all tested CVM samples the negative controls were constrained, while the positive controls were mobile as demonstrated by the differences in $\langle V_{\text{mean}} \rangle$ for the positive and negative controls (Table 5).

[000228] Table 5. Transport of PLA nanoparticles obtained by the emulsification process with various PVAs (sample) and controls in CVM: Ensemble-average velocity $\langle V_{\text{mean}} \rangle$ ($\mu\text{m/s}$) and relative sample velocity $\langle V_{\text{mean}} \rangle_{\text{rel}}$.

Stabilizer/Surface-	Negative Control	Positive Control	Sample	Sample
---------------------	------------------	------------------	--------	--------

altering agent							(relative)	
	$\langle V_{\text{mean}} \rangle$	SD	$\langle V_{\text{mean}} \rangle$	SD	$\langle V_{\text{mean}} \rangle$	SD	$\langle V_{\text{mean}} \rangle_{\text{rel}}$	SD
PVA2K75	0.95	0.64	5.5	0.92	5.51	1.2	1.00	0.39
PVA9K80	0.72	0.47	5.61	0.79	4.6	1.5	0.79	0.35
PVA31K87	0.63	0.60	4.94	1.50	3.36	1.84	0.63	0.51
PVA85K87	0.57	0.4	4.49	1.21	2.9	1.56	0.59	0.45
PVA105K80	0.69	0.56	4.85	1.54	3.55	1.26	0.69	0.43
PVA130K87	0.95	0.54	4.98	1.25	3.46	1.23	0.62	0.39
PVA95K95	1.39	1.28	5.72	1.57	1.63	1.5	0.06	0.46
PVA13K98	1.02	0.49	5.09	0.99	2.61	1.54	0.39	0.41
PVA31K98	1.09	0.6	5.09	0.9	2.6	1.13	0.38	0.34
PVA85K99	0.47	0.33	5.04	2.2	0.81	0.77	0.07	0.19

[000229] It was discovered that nanoparticles prepared in the presence of certain (but, interestingly, not all) PVA transported through CVM at the same rate or nearly the same velocity as the positive control. Specifically, the particles stabilized with PVA2K75, PVA9K80, PVA13K87, PVA31K87, PVA85K87, PVA105K80, and PVA130K87 exhibited $\langle V_{\text{mean}} \rangle$ that significantly exceeded those of the negative controls and were indistinguishable, within experimental error, from those of the positive controls, as shown in Table 5 and FIG. 5A. For these samples, $\langle V_{\text{mean}} \rangle_{\text{rel}}$ values exceeded 0.5, as shown in FIG. 5B.

[000230] On the other hand, pyrene nanoparticles obtained with PVA95K95, PVA13K98, PVA31K98, and PVA85K99 were predominantly or completely immobilized as demonstrated by respective $\langle V_{\text{mean}} \rangle_{\text{rel}}$ values of no greater than 0.4 (Table 5 and FIG. 5B). To identify the characteristics of the PVA that render particles mucus penetrating, $\langle V_{\text{mean}} \rangle_{\text{rel}}$ of the nanoparticles prepared with the various PVAs was mapped with respect to MW and hydrolysis degree of the PVAs used (FIG. 6). It was concluded that at least those PVAs that have the hydrolysis degree of less than 95% rendered the nanocrystals mucus-penetrating. Without wishing to be bound by any theory, it is believed that the unhydrolyzed (vinyl acetate) units of PVA can provide effective hydrophobic association with the surface of the core particles if the content of these segments in the PVA is sufficient (*e.g.*, greater than 5% in some embodiments); while the hydrophilic (vinyl alcohol) units of PVA present at the surface of the coated particles render them hydrophilic and can shield the coated particles from adhesive interactions with mucus.

Example 3

[000231] The following describes a non-limiting example of a method of forming mucus-penetrating non-polymeric solid particles by nanomilling in the presence of certain poly(vinyl alcohol) polymers (PVA). Pyrene, a model hydrophobic compound, was used as the core particle processed by a nanomilling. The PVA acted as nanomilling aids facilitating particle size reduction of the core particles and surface-altering agents forming coatings around the core particles. PVA of various molecular weights (MW) and hydrolysis degrees were evaluated to determine effectiveness of the nanomilled particles in penetrating mucus.

[000232] Pyrene was nanomilled in aqueous dispersions in the presence of various PVA to determine whether PVAs of certain MW and hydrolysis degree can: 1) aid particle size reduction to several hundreds of nanometers and 2) physically (non-covalently) coat the surface of generated nanoparticles with a mucoinert coating that would minimize particle interactions with mucus constituents and prevent mucus adhesion. In these experiments, the PVA acted as a coating around the core particles, and the resulting particles were tested for their mobility in mucus. The PVAs tested ranged in the average molecular weight from 2 kDa to 130 kDa and in the average hydrolysis degree from 75% to 99+%. The PVAs that were tested are listed in Table 1, shown above. A variety of other polymers, oligomers, and small molecules listed in Table 6, including pharmaceutically relevant excipients such as polyvinylpyrrolidones (Kollidon), hydroxypropyl methylcellulose (Methocel), Tween, Span, *etc.*, were tested in a similar manner.

[000233] **Table 6.** Other stabilizers/surface-altering agents tested with pyrene as a model compound.

Chemical Family	Grades
Polyvinylpyrrolidone (PVP)	Kollidon 17 Kollidon 25 Kollidon 30
PVA-poly(ethylene glycol) graft-copolymer	Kollicoat IR
Hydroxypropyl methylcellulose (HPMC)	Methocel E50 Methocel K100

Non-ionic polyoxyethylene surfactants	Solutol HS 15 Span 20 Span 80 Triton X100 Tween 20 Tween 80 Tyloxapol
Non-ionic small molecule surfactants	Octyl glucoside
Ionic small molecule surfactants	Cetytrimethylammonium bromide (CTAB) Sodium dodecyl sulfate (SDS)

[000234] An aqueous dispersion containing pyrene and one of the stabilizers/surface-altering agents listed above was stirred with milling media until particle size was reduced below 500 nm (as measured by dynamic light scattering). Table 7 lists particle size characteristics of pyrene particles obtained by nanomilling in the presence of the various stabilizers/surface-altering agents. When Span 20, Span 80, or Octyl glucoside were used as stabilizers/surface-altering agents, stable nanosuspensions could not be obtained. Therefore, these stabilizers/surface-altering agents were excluded from further investigation due to their inability to effectively aid particle size reduction.

[000235] **Table 7.** Particle size measured by DLS in nanosuspensions obtained by nanomilling of pyrene with various stabilizers/surface-altering agents.

Stabilizer/surface-altering agent	Z-Ave D (nm)	N-Ave D (nm)
PVA2K75	340	301
PVA9K80	380	337
PVA13K87	375	326
PVA13K98	396	314
PVA31K87	430	373
PVA31K98	344	220
PVA85K87	543	434
PVA85K99	381	236
PVA95K95	534	392
PVA130K87	496	450
Kollidon 17	237	163
Kollidon 25	307	210
Kollidon 30	255	185
Kollicoat IR	364	192
Methocel E50	244	160

Methocel K100	375	216
Tween 20	567	381
Tween 80	553	322
Solutol HS	576	378
Triton X100	410	305
Tyloxapol	334	234
Cremophor RH40	404	373
Span 20	not measurable*	
Span 80	not measurable*	
Octyl glucoside	not measurable*	
SDS	603	377
CTAB	432	354

* milling with Span 20, Span 80, Octyl glucoside failed to effectively reduce pyrene particle size and produce stable nanosuspensions.

[000236] The mobility and distribution of the produced pyrene nanoparticles in human cervicovaginal mucus (CVM) were characterized using fluorescence microscopy and multiple particle tracking software. In a typical experiment, $\leq 0.5 \mu\text{L}$ of a nanosuspension (diluted if necessary to the surfactant concentration of $\sim 1\%$) was added to $20 \mu\text{L}$ of fresh CVM along with controls. Conventional nanoparticles (200 nm yellow-green fluorescent carboxylate-modified polystyrene microspheres from Invitrogen) were used as a negative control to confirm the barrier properties of the CVM samples. Red fluorescent polystyrene nanoparticles covalently coated with PEG 5 kDa were used as a positive control with well-established MPP behavior. Using a fluorescent microscope equipped with a CCD camera, 15 s movies were captured at a temporal resolution of 66.7 ms (15 frames/s) under 100x magnification from several areas within each sample for each type of particles: sample (pyrene), negative control, and positive control (natural blue fluorescence of pyrene allowed observing of pyrene nanoparticles separately from the controls). Next, using an advanced image processing software, individual trajectories of multiple particles were measured over a time-scale of at least 3.335 s (50 frames). Resulting transport data are presented here in the form of trajectory-mean velocity V_{mean} , *i.e.*, velocity of an individual particle averaged over its trajectory, and ensemble-average velocity $\langle V_{\text{mean}} \rangle$, *i.e.*, V_{mean} averaged over an ensemble of particles. To enable easy comparison between different samples and normalize velocity data with respect to natural variability in penetrability of CVM samples, ensemble-average

(absolute) velocity is then converted to relative sample velocity $\langle V_{\text{mean}} \rangle_{\text{rel}}$ according to the formula shown in Equation 1.

[000237] Prior to quantifying mobility of pyrene particles, their spatial distribution in the mucus sample was assessed visually. It was found that pyrene/Methocel nanosuspensions did not achieve uniform distribution in CVM and strongly aggregated into domains much larger than the mucus mesh size (data not shown). Such aggregation is indicative of mucoadhesive behavior and effectively prevents mucus penetration. Therefore, further quantitative analysis of particle mobility was deemed unnecessary. Similarly to the positive control, all other tested pyrene/surface-altering agent systems achieved a fairly uniform distribution in CVM. Multiple particle tracking confirmed that in all tested CVM samples the negative controls were constrained, while the positive controls were mobile as demonstrated by the differences in $\langle V_{\text{mean}} \rangle$ for the positive and negative controls (Table 8).

[000238] **Table 8.** Transport of pyrene nanoparticles (sample) obtained with various stabilizers/surface-altering agents and controls in CVM: Ensemble-average velocity $\langle V_{\text{mean}} \rangle$ (um/s) and relative sample velocity $\langle V_{\text{mean}} \rangle_{\text{rel}}$.

Stabilizer/Surface-altering agent	Negative Control		Positive Control		Sample		Sample (relative)	
	$\langle V_{\text{mean}} \rangle$	SD	$\langle V_{\text{mean}} \rangle$	SD	$\langle V_{\text{mean}} \rangle$	SD	$\langle V_{\text{mean}} \rangle_{\text{rel}}$	SD
PVA2K75	0.4	0.24	5.73	0.73	4.73	1.08	0.81	0.24
PVA9K80	0.36	0.20	6.00	0.70	6.19	1.13	1.03	0.24
PVA13K87	1.01	1.21	5.09	0.98	4.54	1.03	0.87	0.51
PVA31K87	1.28	1.14	4.88	0.6	4.57	1.123	0.91	0.55
PVA85K87	1.05	0.9	4.1	0.57	3.3	0.98	0.74	0.51
PVA130K87	0.51	0.82	5.29	0.73	4.12	1.49	0.76	0.40
PVA95K95	0.4	0.27	4.53	1.03	0.67	0.6	0.07	0.16
PVA13K98	0.61	0.42	2.13	0.99	1.29	0.57	0.45	0.56
PVA31K98	0.68	0.87	5.77	1.24	2.69	2.02	0.39	0.45
PVA85K99	0.43	0.23	5.42	0.97	2.23	1.60	0.36	0.33
Kollicoat IR	0.62	0.62	5.39	0.55	0.92	0.81	0.06	0.22
Kollidon 17	1.69	1.8	5.43	0.98	0.82	0.59	-0.23	-0.52
Kollidon 25	0.41	0.34	5.04	0.64	1.29	1.09	0.19	0.25
Kollidon 30	0.4	0.2	4.28	0.57	0.35	0.11	-0.01	0.06
Methocel E50*								
Methocel K100*								
Tween 20	0.77	0.93	5.35	1.76	1.58	2.02	0.18	0.49
Tween 80	0.46	0.34	3.35	1.89	0.94	0.5	0.17	0.24
Solutol HS	0.42	0.13	3.49	0.5	0.8	0.6	0.12	0.20

Triton X100	0.26	0.13	4.06	1.11	0.61	0.19	0.09	0.07
Tyloxapol	0.5	0.5	3.94	0.58	0.42	0.23	-0.02	-0.16
Cremophor RH40	0.48	0.21	3.2	0.97	0.49	0.24	0.00	0.12
SDS	0.3	0.12	5.99	0.84	0.34	0.15	0.01	0.03
CTAB	0.39	0.09	4.75	1.79	0.32	0.31	-0.02	-0.07

* Aggregated in CVM, hence not mucus-penetrating (velocity in CVM not measured)

[000239] It was discovered that nanoparticles obtained in the presence of certain (but, interestingly, not all) PVA transported through CVM at the same rate or nearly the same velocity as the positive control. Specifically, pyrene nanoparticles stabilized with PVA2K75, PVA9K80, PVA13K87, PVA31K87, PVA85K87, and PVA130K87 exhibited $\langle V_{\text{mean}} \rangle$ that significantly exceeded those of the negative controls and were indistinguishable, within experimental error, from those of the positive controls, as shown in Table 8 and FIG. 7A. For these samples, $\langle V_{\text{mean}} \rangle_{\text{rel}}$ values exceeded 0.5, as shown in FIG. 7B.

[000240] On the other hand, pyrene nanoparticles obtained with the other stabilizers/surface-altering agents, including PVA95K95, PVA13K98, PVA31K98, and PVA85K99, were predominantly or completely immobilized as demonstrated by respective $\langle V_{\text{mean}} \rangle_{\text{rel}}$ values of no greater than 0.5 and, with most stabilizers/surface-altering agents, no greater than 0.4 (Table 8 and FIG. 7B). Additionally, FIGs. 8A-8F are histograms showing distribution of V_{mean} within an ensemble of particles. These histograms illustrate muco-diffusive behavior of samples stabilized with PVA2K75 and PVA9K80 (similar histograms were obtained for samples stabilized with PVA13K87, PVA31K87, PVA85K87, and PVA130K87, but are not shown here) as opposed to muco-adhesive behavior of samples stabilized with PVA31K98, PVA85K99, Kollidon 25, and Kollicoat IR (chosen as representative muco-adhesive samples).

[000241] To identify the characteristics of the PVA that render pyrene nanocrystals mucus penetrating, $\langle V_{\text{mean}} \rangle_{\text{rel}}$ of the pyrene nanocrystals stabilized with various PVAs was mapped with respect to MW and hydrolysis degree of the PVAs used (FIG. 9). It was concluded that at least those PVAs that have the hydrolysis degree of less than 95% rendered the nanocrystals mucus-penetrating. Without wishing to be bound by any theory, it is believed that the unhydrolyzed (vinyl acetate) segments of PVA can provide effective hydrophobic association with the surface of the core particles if the content of these segments in the PVA is sufficient (*e.g.*, greater than 5% in some embodiments); while the hydrophilic (vinyl

alcohol) segments of PVA present at the surface of the coated particles render them hydrophilic and can shield the coated particles from adhesive interactions with mucus.

Example 4

[000242] This non-limiting example demonstrates that LE MPPs containing Pluronic[®] F127, Tween 80[®], or PVA as the surface-altering agent showed improved exposure of LE in rabbits compared to Lotemax[®].

[000243] In order to demonstrate that the LE MPPs' ability to enhance the exposure of LE is not limited to the inclusion of F127 as the surface-altering agent in the LE MPPs, two additional surface-altering agents were studied: Tween 80[®] and polyvinyl alcohol (PVA). Tween 80[®] is an FDA approved surface-altering agent which consists of PEGylated sorbitan forming a head group and an alkyl tail. Tween 80[®] is different from a range of other surface-altering agents (*e.g.*, F127 and PVA) in that, among other things, it is oligomeric and thus significantly lower in molecular weight. PVA is an FDA approved polymer produced by, *e.g.*, partially hydrolyzing polyvinyl acetate, creating a random copolymer of polyvinyl acetate and polyvinyl alcohol. PVA is different from a range of other surface-altering agents (*e.g.*, F127 and Tween 80[®]) in that, among other things, it contains no PEG. Earlier it was shown that some PVAs enable mucus penetration while other PVAs do not. This differentiated mucus penetration behavior may be controlled by the molecular weight and degree of hydrolysis of PVA. Based on the results from these experiments, a PVA that has a molecular weight of about 2 kDa and is about 75% hydrolyzed was selected for the study of mucus penetration properties of LE MPPs.

[000244] To form the LE MPPs, a milling procedure was employed as described herein. In one set of experiments, an aqueous dispersion containing LE and one surface-altering agent selected from F127, Tween 80[®], and PVA (2 kDa, 75% hydrolyzed) was milled with a grinding medium until the particle size was reduced to below about 300 nm as measured by dynamic light scattering. Mucus mobility was characterized in human cervicovaginal mucus based on the previously described characterization methods. All three LE MPPs (*i.e.*, LE-F127, LE-Tween80, and LE-PVA) showed mucus penetrating properties (FIG. 10).

[000245] *In vivo*, a single topical instillation of each one of the three LE MPPs to New Zealand white rabbits produced LE levels in the cornea of the rabbit which were significantly higher than the LE levels from a similarly administered dose of Lotemax[®] (FIG. 10). These

results demonstrate that the MPPs, compositions, and/or formulations containing a drug enhance exposure of the drug based on the mucus penetrating properties of the particles.

Example 5

[000246] The following non-limiting example describes the assessment of different surface-altering agents (*e.g.*, poly(vinyl alcohols) (PVAs)) in producing mucus-penetrating particles comprising loteprednol etabonate (LE) as the core material.

[000247] In this example, LE, a relatively hydrophobic pharmaceutical agent, was milled as aqueous suspensions with milling media in the presence of various types of PVAs as the surface-altering agents. The characteristics of the PVAs tested, including the molecular weight (MW) and degree of hydrolysis, are listed in Table 9. The milling process was carried out until LE particles were uniformly small, *i.e.*, Z-average diameter (D) ≤ 500 nm and polydispersity index (PDI) < 0.20 as measured by dynamic light scattering (DLS). The resulting particle size and polydispersity index for LE nanoparticles as measured by DLS are also listed in Table 9.

[000248] **Table 9.** Characteristics of poly(vinyl alcohols) (PVAs) tested (molecular weight (MW) and degree of hydrolysis), and particle size (D and PDI) measured by DLS of nanosuspensions obtained by milling of loteprednol etabonate (LE) with the PVAs as the surface-altering agents.

PVA	MW (kDa)	% Hydrolysis	D (nm)	PDI
PVA 2K75	2	75 - 79	172	0.105
PVA 13K87	13 - 23	87 - 89	333	0.112
PVA 31K87	31 - 50	87 - 89	253	0.085
PVA 31K98	31 - 50	98 - 99	281	0.105
PVA 85K87	85 - 124	87 - 89	323	0.136
PVA 85K99	85 - 124	≥ 99	> 500	> 0.2
PVA 95K95	95	95	366	0.136
PVA 130K87	130	87 - 89	388	0.131

[000249] The mucus-penetrating ability of LE nanoparticles from the produced nanosuspensions was characterized in reconstituted cervicovaginal mucus (CVM) (as described in Example 2) by high resolution dark-field microscopy. In a typical sample preparation, 20 μ L of rehydrated CVM and 0.5 μ L of a nanosuspension at a nanoparticle

concentration of 5% w/v LE were deposited onto a microscope slide. In the case of LE milled in DPPC or DPPC+2PEG-PE, 1 μ L of nanosuspensions at a concentration of 1% w/v LE was used. Videos at 15s length and temporal resolution of 66.7 ms (15 frames/s) were acquired of randomized regions within the mucus sample under dark-field microscopy at high magnification (100x). Mobility of LE nanoparticles in the videos was determined visually by comparing the degree particles' motion (i.e., overall particles' velocity and the amount of particles that appear mobile) in recorded videos against a well-established positive control (LE nanoparticles milled in Pluronic® F127, "mobile" or "mucus-penetrating") and negative control (LE nanoparticles milled in SDS, "not mobile" or "not mucus-penetrating"), and classified as "mobile" and "not mobile," respectively.

[000250] To identify the characteristics of the PVAs that render LE nanocrystals mucus penetrating, the mobility for LE nanoparticles obtained by milling with various PVAs was mapped with respect to MW and hydrolysis degree of the PVAs used (FIG. 11). It was observed that those PVAs that have both properties of hydrolysis degree > 95% and molecular weight > 31 kDa failed to produce stable nanocrystals or those that were mucus-penetrating. Without wishing to be bound by any theory, it is believed that the unhydrolyzed segments (vinyl acetate) of PVA can provide effective hydrophobic association with the surface of the core particles if the content of these segments in the PVA is sufficient (e.g., equal or greater than 2% in some embodiments); while the hydrophilic segments (vinyl alcohol) of PVA present at the surface of the coated particles render the coated particles hydrophilic and can shield the coated particles from adhesive interactions with mucus. The results suggest that the following surface-altering agents render LE nanoparticles mucus-penetrating: PVA 2K75, PVA 13K87, PVA 31K87, PVA 31K98, PVA 85K87, and PVA 130K87.

Other Embodiments

[000251] While several embodiments of the present invention have been described and illustrated herein, those of ordinary skill in the art will readily envision a variety of other means and/or structures for performing the functions and/or obtaining the results and/or one or more of the advantages described herein, and each of such variations and/or modifications is deemed to be within the scope of the present invention. More generally, those skilled in

the art will readily appreciate that all parameters, dimensions, materials, and configurations described herein are meant to be exemplary and that the actual parameters, dimensions, materials, and/or configurations will depend upon the specific application or applications for which the teachings of the present invention is/are used. Those skilled in the art will recognize, or be able to ascertain using no more than routine experimentation, many equivalents to the specific embodiments of the invention described herein. It is, therefore, to be understood that the foregoing embodiments are presented by way of example only and that, within the scope of the appended claims and equivalents thereto, the invention may be practiced otherwise than as specifically described and claimed. The present invention is directed to each individual feature, system, article, material, kit, and/or method described herein. In addition, any combination of two or more such features, systems, articles, materials, kits, and/or methods, if such features, systems, articles, materials, kits, and/or methods are not mutually inconsistent, is included within the scope of the present invention.

[000252] The indefinite articles “a” and “an,” as used herein in the specification and in the claims, unless clearly indicated to the contrary, should be understood to mean “at least one.”

[000253] The phrase “and/or,” as used herein in the specification and in the claims, should be understood to mean “either or both” of the elements so conjoined, *i.e.*, elements that are conjunctively present in some cases and disjunctively present in other cases. Other elements may optionally be present other than the elements specifically identified by the “and/or” clause, whether related or unrelated to those elements specifically identified unless clearly indicated to the contrary. Thus, as a non-limiting example, a reference to “A and/or B,” when used in conjunction with open-ended language such as “comprising” can refer, in one embodiment, to A without B (optionally including elements other than B); in another embodiment, to B without A (optionally including elements other than A); in yet another embodiment, to both A and B (optionally including other elements); *etc.*

[000254] As used herein in the specification and in the claims, “or” should be understood to have the same meaning as “and/or” as defined above. For example, when separating items in a list, “or” or “and/or” shall be interpreted as being inclusive, *i.e.*, the inclusion of at least one, but also including more than one, of a number or list of elements, and, optionally, additional unlisted items. Only terms clearly indicated to the contrary, such as “only one of” or “exactly one of,” or, when used in the claims, “consisting of,” will refer to the inclusion of

exactly one element of a number or list of elements. In general, the term “or” as used herein shall only be interpreted as indicating exclusive alternatives (*i.e.* “one or the other but not both”) when preceded by terms of exclusivity, such as “either,” “one of,” “only one of,” or “exactly one of.” “Consisting essentially of,” when used in the claims, shall have its ordinary meaning as used in the field of patent law.

[000255] As used herein in the specification and in the claims, the phrase “at least one,” in reference to a list of one or more elements, should be understood to mean at least one element selected from any one or more of the elements in the list of elements, but not necessarily including at least one of each and every element specifically listed within the list of elements and not excluding any combinations of elements in the list of elements. This definition also allows that elements may optionally be present other than the elements specifically identified within the list of elements to which the phrase “at least one” refers, whether related or unrelated to those elements specifically identified. Thus, as a non-limiting example, “at least one of A and B” (or, equivalently, “at least one of A or B,” or, equivalently “at least one of A and/or B”) can refer, in one embodiment, to at least one, optionally including more than one, A, with no B present (and optionally including elements other than B); in another embodiment, to at least one, optionally including more than one, B, with no A present (and optionally including elements other than A); in yet another embodiment, to at least one, optionally including more than one, A, and at least one, optionally including more than one, B (and optionally including other elements); *etc.*

[000256] In the claims, as well as in the specification above, all transitional phrases such as “comprising,” “including,” “carrying,” “having,” “containing,” “involving,” “holding,” and the like are to be understood to be open-ended, *i.e.*, to mean including but not limited to. Only the transitional phrases “consisting of” and “consisting essentially of” shall be closed or semi-closed transitional phrases, respectively, as set forth in the United States Patent Office Manual of Patent Examining Procedures, Section 2111.03.

Claims

1. A composition comprising a plurality of coated particles, wherein each of the coated particles comprises:
 - a core particle comprising a pharmaceutical agent or a salt thereof; and
 - a coating comprising a surface-altering agent surrounding the core particle,wherein the surface-altering agent comprises a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer, the polymer having a molecular weight of at least about 1 kDa and less than or equal to about 1000 kDa, wherein the polymer is at least about 30% hydrolyzed and less than about 95% hydrolyzed, and
wherein the coated particles have a relative velocity of greater than 0.5 in mucus.
2. A method, comprising:
 - delivering to mucus or a mucus membrane a composition comprising a plurality of coated particles, wherein the coated particle comprises:
 - a core particle comprising a pharmaceutical agent or a salt thereof; and
 - a coating comprising a surface-altering agent surrounding the core particle,
 - wherein the surface-altering agent comprises a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer, the polymer having a molecular weight of at least about 1 kDa and less than or equal to about 1000 kDa, wherein the polymer is at least about 30% hydrolyzed and less than about 95% hydrolyzed, and
 - wherein the coated particles have a relative velocity of greater than 0.5 in mucus.
3. A method of forming coated particles, comprising:
 - coating a plurality of core particles with a surface-altering agent to form coated particles,
 - wherein the surface-altering agent comprises a synthetic polymer having pendant hydroxyl groups on the backbone of the polymer, the polymer having a molecular weight of at least about 1 kDa and less than or equal to about 1000 kDa, wherein the polymer is at least about 30% hydrolyzed and less than about 95% hydrolyzed,

wherein each of the core particles comprises a pharmaceutical agent or a salt thereof,
and

wherein the coated particles have a relative velocity of greater than 0.5 in mucus.

4. The method or composition of any preceding claim, wherein the surface-altering agent is covalently attached to the core particles.
5. The method or composition of any preceding claim, wherein the surface-altering agent is non-covalently adsorbed to the core particles.
6. The method or composition of any preceding claim, wherein the synthetic polymer is polyvinyl alcohol.
7. The method or composition of any preceding claim, wherein the surface-altering agent comprises a linear polymer having pendant hydroxyl groups on the backbone of the polymer.
8. The method or composition of any preceding claim, wherein the polymer has a molecular weight of at least about 2 kDa, at least about 5 kDa, at least about 10 kDa, at least about 20 kDa, at least about 50 kDa, at least about 80 kDa, at least about 100 kDa, or at least about 120 kDa.
9. The method or composition of any preceding claim, wherein the polymer has a molecular weight of less than or equal to about 200 kDa, less than or equal to about 180 kDa, less than or equal to about 150 kDa, less than or equal to about 130 kDa, less than or equal to about 100 kDa, less than or equal to about 80 kDa, less than or equal to about 50 kDa, or less than or equal to about 30 kDa.
10. The method or composition of any preceding claim, wherein the polymer is at least about 40% hydrolyzed, at least about 50% hydrolyzed, at least about 60% hydrolyzed, at least about 70% hydrolyzed, at least about 80% hydrolyzed, or at least about 90% hydrolyzed.

11. The method or composition of any preceding claim, wherein the polymer is less than about 94%, less than about 90%, less than about 85%, or less than about 80% hydrolyzed.
12. The method or composition of any preceding claim, wherein the surface-altering agent is present in a solution during the coating step, and the pharmaceutical agent or salt has a solubility of less than about 1 mg/mL in the solution at 25 °C.
13. The method or composition of any preceding claim, wherein each of the core particles comprises a solid crystalline pharmaceutical agent or a salt thereof.
14. The method or composition of any preceding claim, wherein each of the core particles comprises a solid amorphous pharmaceutical agent or a salt thereof.
15. The method or composition of any preceding claim, wherein each of the core particles comprises a salt of the solid pharmaceutical agent.
16. The method or composition of any preceding claim, wherein each of the core particles comprises a pharmaceutical agent or a salt thereof that is encapsulated in a polymer, a lipid, a protein, or a combination thereof.
17. The method or composition of any preceding claim, wherein the pharmaceutical agent is at least one of a therapeutic agent or a diagnostic agent.
18. The method or composition of any preceding claim, wherein the pharmaceutical agent is at least one of a small molecule, a peptide, a peptidomimetic, a protein, a nucleic acid, or a lipid.
19. The method or composition of any preceding claim, wherein the pharmaceutical agent or a salt thereof has an aqueous solubility of less than or equal to about 5 mg/mL, less than or equal to about 1 mg/mL, or less than or equal to about 0.1 mg/mL at 25 °C.

20. The method or composition of any preceding claim, wherein the pharmaceutical agent constitutes at least about 50 wt% of the core particle, at least about 80 wt% of the core particle, at least about 85 wt% of the core particle, at least about 90 wt% of the core particle, at least about 95 wt% of the core particle, or at least about 99 wt% of the core particle.
21. The method or composition of any preceding claim, wherein the core particle has an average size of at least about 50 nm, or at least about 100 nm, and less than or equal to about 1 μm .
22. The method or composition of any preceding claim, wherein the coated particles have an average size of at least about 50 nm or at least about 100 nm, and less than or equal to about 1 μm .
23. The method or composition of any preceding claim, wherein the coated particles have a relative velocity of greater than 0.6, 0.7, 0.8, 0.9, or 1.0 in mucus.
24. The method or composition of any preceding claim, wherein the mucus is human cervicovaginal mucus.
25. A pharmaceutical composition comprising the composition of any preceding claim and one or more pharmaceutically acceptable carriers.
26. A pharmaceutical preparation suitable for inhalation, injection, or topical administration to a mucus membrane comprising the composition of any preceding claim.
27. The method of claim 1 comprising forming and coating the core particles substantially simultaneously.
28. The method of any one of the preceding claims comprising forming the core particles by milling in a solution comprising the surface-altering agent.

29. The method of any one of the preceding claims further comprising the step of combining a milling agent with the core particles and a solution comprising the surface-altering agent.

30. The method of any one of the preceding claims further comprising the step of reducing the size of the core particles using the milling agent.

31. The method or composition of any preceding claim, wherein the surface-altering agent is present in a solution at a concentration of at least about 0.01% (w/v), at least about 0.05% (w/v), at least about 0.1 % (w/v) at least about 0.3% (w/v), at least about 0.5% (w/v), or at least about 1.0% (w/v) during the coating step or in the composition.

32. The method or composition of any preceding claim, wherein the composition has a PDI of less than or equal to about 0.5, less than or equal to about 0.3, or less than or equal to about 0.2.

33. The method or composition of any preceding claim, wherein the composition has a PDI of greater than or equal to about 0.1 and less than or equal to about 0.5, greater than or equal to about 0.1 and less than or equal to about 0.3, or greater than or equal to about 0.1 and less than or equal to about 0.2.




FIG. 1




FIG. 2A




FIG. 2B




FIG. 3




FIG. 4A




FIG. 4B




FIG. 5A




FIG. 5B




FIG. 6




FIG. 7A






FIG. 7B

FIG. 8A


PVA2K75

**FIG. 8B**


PVA9K80

**FIG. 8C**


PVA31K98

**FIG. 8D**


PVA85K99

**FIG. 8E**

Kollidon 25

**FIG. 8F**

Kollicoat IR








FIG. 9

**FIG. 10**

**FIG. 11**

INTERNATIONAL SEARCH REPORT

International application No
PCT/US2013/039499

A. CLASSIFICATION OF SUBJECT MATTER
INV. A61K9/10 A61K47/32 A61K9/51
ADD.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EP0-Internal, BIOSIS, EMBASE, MEDLINE, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 2 335 686 A1 (LEK PHARMACEUTICALS [SI]) 22 June 2011 (2011-06-22) examples 1-11 claims 1-8	1-33
X	US 2005/191359 A1 (GOLDSSTEIN RINA [IL] ET AL) 1 September 2005 (2005-09-01) example 10 claims 1-6	1-33

☐

Further documents are listed in the continuation of Box C.

☒

See patent family annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

14 August 2013

Date of mailing of the international search report

26/08/2013

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040,
Fax: (+31-70) 340-3016

Authorized officer

Sindel, Ulrike

INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/US2013/039499

Patent document cited in search report	Publication date	Patent family member(s)	Publication date	
EP 2335686	A1	22-06-2011	EP 2335686 A1	22-06-2011
			WO 2011080148 A2	07-07-2011

US 2005191359	A1	01-09-2005	NONE	
