



(22) Date de dépôt/Filing Date: 2000/05/18

(41) Mise à la disp. pub./Open to Public Insp.: 2000/12/23

(45) Date de délivrance/Issue Date: 2010/02/09

(30) Priorité/Priority: 1999/06/23 (US09/338,615)

(51) Cl.Int./Int.Cl. *C09D 5/46* (2006.01),
C23C 4/02 (2006.01), *C23C 4/10* (2006.01),
C23C 4/18 (2006.01)

(72) Inventeurs/Inventors:
WEI, XIAOHAN, US;
DORFMAN, MITCHELL R., US;
CORREA, LUIS F., US;
JANSEN, FRANZ, CH;
PETERS, JOHN, CH

(73) Propriétaire/Owner:
SULZER METCO (US) INC., US

(74) Agent: OSLER, HOSKIN & HARCOURT LLP

(54) Titre : POUDRE DE SILICATE DICALCIQUE OBTENUE PAR PULVERISATION THERMIQUE, REVETEMENT
COMPOSE DE CETTE POUDRE ET FABRICATION DE CETTE POUDRE

(54) Title: THERMAL SPRAY POWDER OF DICALCIUM SILICATE AND COATING THEREOF AND MANUFACTURE
THEREOF

(57) **Abrégé/Abstract:**

A powder of dicalcium silicate is made by spray drying calcia and silica with incorporation of sodium and phosphorus or stabilized zirconia. The spray dried powder is sintered to form a thermal spray powder. Sprayed coatings have a web of interconnected, randomly oriented microcracks substantially perpendicular to the coating surface. The coatings are stable in thermal cycling and a hot corrosive environment.

ABSTRACT OF THE DISCLOSURE

A powder of dicalcium silicate is made by spray drying calcia and silica with incorporation of sodium and phosphorus or stabilized zirconia. The spray dried powder is sintered to form a thermal
5 spray powder. Sprayed coatings have a web of interconnected, randomly oriented microcracks substantially perpendicular to the coating surface. The coatings are stable in thermal cycling and a hot corrosive environment.

THERMAL SPRAY POWDER OF DICALCIUM SILICATE
AND COATING THEREOF AND MANUFACTURE THEREOF

5 This invention relates to thermal spray powders of dicalcium
silicate, thermal spray coatings thereof, and a process for
manufacturing such powders.

BACKGROUND

10 Thermal spraying involves the melting or at least heat softening
of a heat fusible material such as a metal or ceramic, and
propelling the softened material in particulate form against a
surface which is to be coated. The heated particles strike the
surface where they are quenched and bonded thereto. In a plasma
type of thermal spray gun, a high temperature stream of plasma
gas heated by an arc is used to melt and propel powder particles.
15 Other types of thermal spray guns include a combustion spray gun
in which powder is entrained and heated in a combustion flame,
such as a high velocity, oxygen-fuel (HVOF) gun. Thermal spray
coatings of oxide ceramics are well distinguished from other
forms such as sintered or melt casted by a characteristic
20 microstructure of flattened spray particles visible in
metallographically prepared cross sections of coatings.

25 In one group of thermal spray materials, powders are formed of
oxides for spraying coatings that are used for thermal insulation
at high temperature such as on burner can surfaces in gas turbine
engines. Coatings are also needed for erosion and wear
protection at high temperatures, and require resistance against
thermal cycle fatigue and hot corrosion in a combustion
environment. Zirconium dioxide (zirconia) typically is used in
such applications. Because of phase transitions, the zirconia is
30 partially or fully stabilized with about 5% (by weight) 15%
calcium oxide (calcia) or 6% to 20% yttrium oxide (yttria).

ME-5021

However, these coatings have limitations particularly in resistance to hot corrosion as they allow attack of the substrate or a bond coating

5 Dicalcium silicate (Ca_2SiO_4) is a ceramic conventionally used for cement and refractory applications. Excellent hot corrosion and heat resistance of dicalcium silicate based coatings also has been demonstrated in a high temperature combustion environment. However, it is polymorphic with at least five phases including three high temperature α modifications, an intermediate
10 temperature monoclinic β phase (larnite) and an ambient temperature γ phase. The transformation from the β phase to the γ phase exhibits a volume increase of 12% leading to degradation in both the thermal spray process and the coatings in thermal cycling. The β phase may be retained by quenching or the use of
15 a stabilizer such as sodium or phosphorous. Other suggested stabilizers include oxides (or ions) of sulphur, boron, chromium, arsenic, vanadium, manganese, aluminum, iron, strontium, barium and potassium. At least some of these have also been reported as unsuccessful, and therefore still questionable in stabilizing,
20 including chromium, aluminum, iron, strontium and barium.

U.S. patent No. 4,255,495 (Levine et al.) discloses plasma sprayed coatings of thermal barrier oxides containing at least one alkaline earth silicate such as calcium silicate. U.S. patent No. 5,082,741 (Tiara et al.) and an article "Advanced
25 Thermal Barrier Coatings Involving Efficient Vertical Micro-Cracks" by N.Nakahira, Y.Harada, N.Mifune, T.Yogoro and H.Yamane, Proceedings of International Thermal Spray Conference, Orlando FL, 28 May - 5 June 1992, disclose thermal spray coatings of dicalcium silicate combined with calcium zirconate (CaZrO_3) in a
30 range of proportions.

A commercial powder of β phase dicalcium silicate for thermal spraying is sold by Montreal Carbide Co. Ltd., Boucherville CQ, Canada, indicated in their "Technical Bulletin MC-C₂S" (undated).

ME-5021

In a chemical analysis the present inventors measured less than 1% by weight of potential stabilizers such as phosphorous in Montreal Carbide powder.

5 A commercial powder of dicalcium silicate for thermal spraying also is sold by Cerac Inc., Milwaukee, Wisconsin. In a Certificate of Analysis for calcium silicate (October 20, 1997), Cerac reports major β phase and low levels of aluminum (0.12%), iron (0.1%) and magnesium (0.25%), and 0.02% or less of other elements.

10 An object of the present invention is to provide an improved powder of dicalcium silicate for thermal sprayed coatings for thermal barriers having resistance to hot corrosion and sulfidation in a combustion environment. A further object is to provide a novel process of manufacturing such a powder. Another
15 object is to provide an improved thermal sprayed coating of dicalcium silicate for thermal barriers having resistance to hot corrosion and sulfidation in a combustion environment.

SUMMARY

20 The foregoing and other objects are achieved by a thermal spray powder comprising a substantially uniform powder composition consisting of dicalcium silicate, sodium, a further ingredient selected from the group consisting of phosphorous and zirconium, and incidental ingredients, such that the dicalcium silicate is stabilized in a larnite phase that is majority by volume. In one
25 embodiment the further ingredient comprises phosphorous, in which case, preferably, the sodium recited as disodium monoxide is present in an amount of about 0.2% to 0.8%, and the phosphorous recited as phosphorous pentoxide is present in an amount of about 2.5% to 4%. In another embodiment the further ingredient
30 comprises zirconium, in which case, preferably, the sodium recited as disodium monoxide is present in an amount of about 0.2% to 0.8%, and the zirconium recited as zirconium dioxide is

ME-5021

present in an amount of about 10% to 50%. These percentages are by weight of oxide based on the total composition. The zirconium, if present, should be at least partially in the form of zirconium dioxide containing calcium oxide as stabilizer of the zirconium dioxide, or yttrium oxide its stabilizer.

Objectives also are achieved by a process of manufacturing a thermal spray powder of dicalcium silicate having a stabilized crystal structure. An aqueous mixture is formed of calcium carbonate powder, silicon dioxide powder, and an organic binder containing as an integral constituent a stabilizing element in an amount sufficient to stabilize the dicalcium silicate in a larnite phase that is majority by volume. The aqueous mixture is spray dried to form a powder. The spray dried powder is heated, such as by sintering or plasma melting, such that the dicalcium silicate is formed with larnite phase that is majority by volume.

Preferably the stabilizing element is sodium, advantageously contained in an organic binder sodium carboxymethylcellulose. Further advantageously, the aqueous mixture further comprises a compound of phosphorous, preferably as hydrous aluminum phosphate in aqueous solution. Alternatively or in addition to phosphorous, the aqueous mixture further comprises stabilized zirconium dioxide powder with calcia or yttria stabilizer.

Objectives are further achieved by a thermal spray coating of a composition as described above for the powder. The coating has a web of interconnected, randomly oriented microcracks substantially perpendicular to the coating surface. The coating may include a bonding layer of a thermal sprayed nickel or cobalt alloy on a metallic substrate, and an intermediate layer of a thermal sprayed partially or fully stabilized zirconium oxide. The layer of dicalcium silicate composition is thermal sprayed onto the intermediate layer. The intermediate layer blocks reaction between the bonding layer and the layer of dicalcium silicate composition.

DETAILED DESCRIPTION

Dicalcium silicate compositions can be manufactured by agglomeration procedures such as spray drying as taught in U.S. patent No. 3,617,358 (Dittrich),

5 followed by sintering (calcination) or melting. Sodium is added as a stabilizing ingredient. A second added ingredient is phosphorous as a stabilizer. Alternatively to the phosphorous, the second additive is stabilized zirconia or, as another alternative, both phosphorous and zirconia may be
 10 added. In spray drying a water soluble organic or inorganic binder is used in an aqueous mixture or slurry containing the other ingredients. In a preferred embodiment, the sodium is added by way of containment in the binder formulation, advantageously sodium carboxymethylcellulose (sodium CMC)
 15 containing about 2% by weight sodium. Other ingredients and calculated formulae are listed in Table 1 for seven formulations.

Table 1
 Spray Dry Menu
 (Quantities in units of weight)

Run #	CaCO ₃	SiO ₂	AP	CZ	YZ
1	154	46			
2	150	50	25		
3	150	50	10		
4	154	46	25		
5	154	46	10		
6	154	46			33
7	154	46		33	

AP - Al(H₂PO₄)₃, 50% solution.

CZ - ZrO₂-5CaO-0.5Al₂O₃-0.4SiO₂, in weight percents.

YZ - ZrO₂-7Y₂O₃, in weight percent.

Raw materials were precipitated calcium carbonate (CaCO₃, purity 98%, size 1-10 μm), ground silica (SiO₂, purity 99%, 2-15 μm), hydrous aluminum phosphate (AP), calcia stabilized zirconia (CZ, 98% purity, 0.4-20 μm) and yttria stabilized zirconia (YZ, 99%
 35 purity, 0.4-15 μm). The amounts of each ingredient are in units of weight, each formulation being in 60 liters of distilled water

per unit of weight of the raw materials. The binder is present in an amount of 4% by weight of the raw materials. The Na₂O content was nearly constant around 0.45% as the binder remained constant. A surfactant such as sodium polyacrylate is added in an amount of 2% by weight. The mixture is atomized conventionally with compressed air upwardly through a nozzle into a heated oven region, as described in the aforementioned Dittrich patent, and the resulting agglomerated powder is collected.

Table 2 lists powders by lot numbers formulated (some in two sizes) from these compositions. All were subsequently sintered at 1200°C for 3 hours, except Lot 709 which was treated by feeding through a plasma gun as described in U.S. patent Nos. 4,450,184 (Longo et al.).

Table 3 gives chemical compositions (from chemical analyses) and phases (from x-ray diffraction) for eight of the lots.

Table 2
Powders

	<u>Lot #</u>	<u>Run #</u>	<u>Size</u>	<u>Additives</u>	<u>Heat Treat</u>
20	307	1	Std	Na	Sinter
	309	1	Fine	Na	Sinter
	403	2	Std	Na, P	Sinter
	414	3	Std	Na, P	Sinter
	429	4	Std	Na, P	Sinter
25	506	5	Std	Na, P	Sinter
	513	6	Std	Na, CZ	Sinter
	515	6	Fine	Na, CZ	Sinter
	520	7	Std	Na, YZ	Sinter
	709	1	Std	Na	Plasma
30	821	Blend of Run 1 & CZ 75/25 Wt%			

Std = Standard - predominantly 30 to 125 μm
 Fine - predominantly 22 to 88 μm.
 Na - sodium; P - phosphorous

Table 3
Powder Compositions
(Volume Percents)

	<u>Lot#</u>	<u>CaO</u>	<u>SiO₂</u>	<u>MgO</u>	<u>Al₂O₃</u>	<u>P₂O₅</u>	<u>Na₂O</u>	<u>Y₂O₃</u>	<u>ZrO₂</u>	<u>Phases</u>
5	307	62.23	36.28	0.42	0.29	0.03	0.49			100% β
	309	64.48	43.03	0.40	0.29	0.09	0.41			100% β
	403	56.92	33.62	0.35	1.80	6.67	0.39			75% β, CA
	414	58.83	36.66	0.37	0.89	2.73	0.42			75% β, CA
	429	57.67	33.30	0.38	1.72	6.17	0.45			75% β, CA
10	506	61.96	32.58	0.40	0.95	3.09	0.49			75% β, CA
	513	49.19	29.09	0.33	0.47	0.01	0.40	0.04	19.71	75% β, CZ
	515	51.04	27.63	0.33	0.47	0.01	0.41	0.03	19.25	75% β, CZ
	520	47.37	28.84	0.28	0.42	0.02	0.40	1.53	20.62	75% β, YZ

CA is calcium aluminate, Ca₃Al₂O₆.

β - larnite

The powders were thermal sprayed with a Sulzer Metco model F4 plasma gun with a model Twin 10 (TM) powder feeder, using an 8 mm nozzle, argon primary gas at 30 standard liters/minute (slpm) flow, hydrogen secondary gas at 12 slpm, argon powder carrier gas at 3 slpm, 550 amperes, 63 volts, 12 cm spray distance and 3 kg/hr powder feed rate. Several types of substrates included cold rolled steel, Fe-13Cr-44Mo alloy and a Ni alloy of 1.5Co-18Fe-22Cr-9Mo-0.6W-0.1C-max1Mn-max1Si. The substrates were prepared conventionally by grit blasting. Coatings having a thickness of 650 to 730 μm were effected. The finer powders were sprayed with the same gun and parameters except at a spray rate 1.2 kg/hr. Table 4 shows detected phases in the coatings.

Table 4
Plasma Sprayed Coating Phases

	<u>Lot/Coating #</u>	<u>Detected Phases</u>
30	307	β
	309	β
	403	α ortho
	414	β (+), α ortho
35	429	α ortho
	506	β (+)
	513	α ortho, cubic zirconia
	515	α hex, cubic zirconia
	520	α hex, cubic zirconia
40	709	β
	821	β, cubic zirconia

(+) after β designates disordered lattice.

A more important feature of the preferred coatings is a web of interconnected, randomly oriented microcracks substantially perpendicular to the coating surface. Such cracks relieve stresses in thermal cycling. These microcracks were
5 observed particularly in a coating from lot 506 which is stabilized at 75% β phase (larnite) with disodium monoxide and phosphorous pentoxide, and contains aluminum oxide bound with the calcia as $\text{Ca}_3\text{Al}_2\text{O}_6$. However, the x-ray diffraction pattern indicated a disordered lattice. Similar microcracking was
10 observed in a coating from lot 515 containing sodium and calcia stabilized zirconia (CZ). Compositional inhomogeneity was visible in coatings with high amounts of silica or phosphorous (lots 403, 429), and inhomogeneity for lot 414. Lot 429, low in phosphorous, was most uniform. The microcracking is considered
15 to be important for stress relief in thermal cycling. In the coatings, there should be between about 1 and 5 microcracks per cm^2 of coating surface.

After a heat treatment at 1200°C for 48 hours, only three coatings appeared stable against dusting, 506 (low phosphorous)
20 and 515 (CZ), and 414 which completely detached. The only coating to retain the β phase was 506. Coating 515 exhibited a mechanical stable appearance. It is concluded that the coatings that dusted would not be stable in hot environments. Coating 414 was "superstabilized" in a high temperature α phase formed in the
25 heat treatment. A significant amount of calcium zirconate (CaZrO_3) was formed in the heat treated coating 515. After a second heat treatment of coatings 506 and 515 at 1300°C for 48 hours, only the β phase was detected in the coatings. These coatings remained stable.

30 Further long term cyclic corrosion testing was performed with coatings 414, 506 (both low phosphorous) and 515 up to 900°C , with V_2O_5 (85 wt%) / Na_2SO_4 (15 wt%) ash as a corrosive agent. These coatings efficiently protected the underlying bond coat and substrate from attack from the agent which did not penetrate the

ME-5021

coatings. Reference yttria stabilized zirconia coatings were damaged and partly spalled, and the corrosive agent penetrated the coating.

5 More broadly, the disodium monoxide should be present in an amount of about 0.2% to 0.8%. If phosphorous pentoxide is the second stabilizer, it should be present in an amount of about 2.5% to 4%. Alternatively, if zirconium dioxide (zirconia) is the second additive, it should be present in an amount of about 10% to 50% by weight. The powder should have a size distribution
10 generally within a range between about 10 and 100 μm . Alternatives to the aluminum phosphate as a raw material are sodium phosphate and zirconium phosphate.

As indicated above for a preferred aspect of the invention, the organic binder for the spray dry process contains the stabilizing
15 element sodium as an integral constituent of the binder compound. More broadly, other stabilizing elements such as potassium or any of the other stabilizing elements set forth above for dicalcium silicate may be used. The stabilizing element is in an amount sufficient to stabilize the dicalcium silicate in a larnite phase
20 that is at least majority or, preferably, substantially fully stabilized larnite.

The powder size distribution generally should be in a range of 10 μm to 200 μm , for example predominantly 30 to 125 μm for thicker coatings or 22 to 88 μm for thinner coatings. The zirconia, when
25 used, should be partially or fully stabilized with about 5% to 15% by weight of calcia or 6% to 20% by weight of yttria. At least some stabilization of the zirconia is desired because some zirconia phase is in the powder particles. Stabilized zirconia is distinguished from calcium zirconate which contains
30 substantially more calcia. Other known or desired stabilizers for the zirconia such as magnesium oxide may be used. In an alternative embodiment, phosphorous is used along with the sodium in powder and coatings containing the stabilized zirconia.

ME-5021

Proportions should be the same as for the individual cases.

Plasma gun melting of spray dried powder in place of sintering, is an alternative. Also, lot 821 tested a blend of lot 307 dicalcium silicate with a partially stabilized zirconia powder.

5 Although lot 307 was stabilized only with sodium which was less effective, the testing suggested that powders of the present invention may be blended with other compatible high temperature powders for tailored results. Advantageously, the zirconium oxide is blended in an amount of about 10% to 50% by weight of
10 the total powder, preferably 15% to 25%, for example 20%.

Preferably the dicalcium silicate is applied over a conventional bonding layer of alloy, such as Ni-22Cr-10Al-1.0Y (by weight), or Ni-20Cr or Ni-50Cr, thermal sprayed on an alloy substrate.

15 However, at high temperature the dicalcium silicate may react with the bonding alloy. Zirconia is less prone to such a reaction. Therefore, an advantageous coating is formed of a bonding layer of a thermal sprayed nickel or cobalt alloy on a metallic substrate, and an intermediate layer of a thermal
20 sprayed partially or fully stabilized zirconium oxide. The layer of dicalcium silicate composition is thermal sprayed onto the intermediate layer, the bonding layer being between about 100 μm and 200 μm thick, and the intermediate layer preferably being
25 between about 50 and 200 μm thick. The intermediate layer thereby blocks reaction between the bonding layer and the layer of dicalcium silicate composition.

Applications for the coatings include burner cans, heat shields, blades, vanes and seals in gas turbine engines, rocket nozzles, piston crowns and valve faces in diesel engines, and contact rolls and tundish outlets in steel mills.

30 While the invention has been described above in detail with reference to specific embodiments, various changes and modifications which fall within the spirit of the invention and

ME-5021

scope of the appended claims will become apparent to those skilled in this art. Therefore, the invention is intended only to be limited by the appended claims or their equivalents.

The embodiments of the present application for which an exclusive property or privilege is claimed are defined as follows:

1. A substantially uniform thermal spray powder consisting essentially of: dicalcium silicate, a sodium compound and a further ingredient selected from the group consisting of a phosphorous compound and a zirconium compound, wherein the dicalcium silicate in the powder is stabilized in a larnite phase that comprises a majority of the powder by volume, wherein the sodium compound is disodium monoxide present in an amount of about 0.2% to 0.8%, and wherein the phosphorous compound is phosphorous pentoxide present in an amount of about 2.5% to 4% if present, and wherein the zirconium compound is zirconium dioxide present in an amount of about 10% to 50% if present, the percentages being by weight of oxide based on the total composition.
2. The powder of claim 1 further consisting essentially of an inevitable impurity wherein the inevitable impurity is aluminum oxide present in an amount of up to about 2% by weight based on the total composition.
3. The powder of claim 1 further consisting essentially of an inevitable impurity wherein the inevitable impurity is magnesium oxide present in an amount of up to about 0.5% by weight based on the total composition.
4. The powder of claim 1 wherein at least part of the zirconium is in the form of zirconium dioxide containing calcium oxide as stabilizer of the zirconium dioxide.
5. The powder of claim 1 wherein at least part of the zirconium is in the form of zirconium dioxide containing yttrium oxide as stabilizer of the zirconium dioxide.

6. The powder of claim 1 wherein the particle size distribution of the powder is within a range between about 10 and 100 μm .

7. The powder of claim 1 further comprising a powder of stabilized zirconium oxide in an amount of about 10% to 50% blended with the powder composition of dicalcium silicate, based on the total weight of the powder.

8. A process of manufacturing a thermal spray powder of dicalcium silicate having a stabilized crystal structure, comprising the steps of:

forming an aqueous mixture of calcium carbonate powder, silicon dioxide powder, and an organic binder comprising sodium and one of phosphorous or zirconium as a stabilizing element in an amount sufficient to stabilize the dicalcium silicate in a larnite phase that is majority by volume;

spray drying the aqueous mixture to form a spray dried powder; and

heating the spray dried powder such that the dicalcium silicate is formed with the larnite phase that is majority by volume.

9. The process of claim 8 wherein the stabilizing element is in an amount sufficient to substantially fully stabilize the dicalcium silicate in the larnite phase.

10. The process of claim 8 wherein the organic binder is sodium carboxymethylcellulose.

11. The process of claim 8 wherein the compound of phosphorous is hydrous aluminum phosphate in aqueous solution.

12. The process of claim 8 wherein the aqueous mixture further comprises stabilized zirconium dioxide.

13. The process of claim 12 wherein the zirconium dioxide contains calcium oxide as stabilizer.
14. The process of claim 12 wherein the zirconium dioxide contains yttrium oxide as stabilizer.
15. The process of claim 8 wherein each powder in the aqueous mixture has a size less than 20 μm .
16. The process of claim 8 wherein the step of heating comprises sintering the powder.
17. The process of claim 8 wherein the step of heating comprises feeding the powder through a plasma gun.
18. A thermal spray coating comprising a layer of a substantially uniform coating composition consisting of dicalcium silicate, sodium, a further ingredient selected from the group consisting of phosphorous and zirconium, and inevitable impurities, the coating having a coating surface and a web of interconnected, randomly oriented microcracks substantially perpendicular to the coating surface.
19. The coating of claim 18 wherein the further ingredient comprises phosphorous, and the dicalcium silicate is stabilized in a larnite phase that is majority by volume.
20. The coating of claim 19 wherein the sodium compound is disodium monoxide present in an amount of about 0.2% to 0.8%, and the phosphorous compound is phosphorous pentoxide present in an amount of about 2.5% to 4%, the percentages being by weight of oxide based on the total composition.
21. The coating of claim 19 wherein the inevitable impurity is aluminum oxide present in an amount of up to about 2% by weight based on the total composition.

22. The coating of claim 18 wherein the inevitable impurity is magnesium oxide present in an amount of up to about 0.5% by weight based on the total composition.

23. The coating of claim 18 wherein the further ingredient is the zirconium compound.

24. The coating of claim 23 wherein the sodium compound is disodium monoxide present in an amount of about 0.2% to 0.8%, and the zirconium compound is zirconium dioxide present in an amount of about 10% to 50%, the percentages being by weight of oxide based on the total composition.

25. The coating of claim 23 wherein at least part of the zirconium is in the form of zirconium dioxide containing calcium oxide as stabilizer of the zirconium dioxide.

26. The coating of claim 23 wherein at least part of the zirconium is in the form of zirconium dioxide containing yttrium oxide as stabilizer of the zirconium dioxide.

27. The coating of claim 18 wherein the coating contains between about one and five microcracks per cm of coating surface.

28. The coating of claim 18 wherein the layer of dicalcium silicate composition is between about 50 μm and 200 μm thick.

29. The coating of claim 18 further comprising a bonding layer of a thermal sprayed nickel or cobalt alloy on a metallic substrate, and an intermediate layer of a thermal sprayed partially or fully stabilized zirconium oxide, the layer of dicalcium silicate composition being thermal sprayed onto the intermediate layer, the bonding layer being between about 100 μm and 200 μm thick, and the intermediate layer being between about 50 μm and 200 μm thick, whereby the

intermediate layer blocks reaction between the bonding layer and the layer of dicalcium silicate composition.