



(86) Date de dépôt PCT/PCT Filing Date: 2014/10/20 (87) Date publication PCT/PCT Publication Date: 2015/04/23 (45) Date de délivrance/Issue Date: 2018/06/19 (85) Entrée phase nationale/National Entry: 2016/03/30 (86) N° demande PCT/PCT Application No.: CA 2014/000756 (87) N° publication PCT/PCT Publication No.: 2015/054779 (30) Priorité/Priority: 2013/10/18 (US61/892,559)	(51) Cl.Int./Int.Cl. <i>C08L 9/02</i> (2006.01), <i>C08J 3/18</i> (2006.01), <i>C08J 3/20</i> (2006.01), <i>C08J 3/24</i> (2006.01), <i>C08J 5/04</i> (2006.01), <i>C08K 3/04</i> (2006.01), <i>C08K 3/36</i> (2006.01), <i>C08K 7/02</i> (2006.01) (72) Inventeurs/Inventors: BEDARD, FRANCOIS, CA; COUE, JEAN-DAMIEN, CA; DUBE, DENIS, CA; MACDONALD, LYLE, CA (73) Propriétaire/Owner: SOUCY TECHNO INC., CA (74) Agent: BERESKIN & PARR LLP/S.E.N.C.R.L.,S.R.L.
--	---

(54) Titre : COMPOSITIONS DE CAOUTCHOUC ET LEURS UTILISATIONS
(54) Title: RUBBER COMPOSITIONS AND USES THEREOF

(57) **Abrégé/Abstract:**

There are provided rubber compositions comprising an elastomer comprising a rubber chosen from acrylonitrile-butadiene, hydrogenated acrylonitrile-butadiene, carboxylated acrylonitrile-butadiene and mixtures thereof; reinforcing fibers chosen from aramid fibers, carbon fibers, polyester fibers, glass fibers, nylon fibers and mixtures thereof, and/or nanometric filamentary structures chosen from nanowires, nanorods, nanofibers, nanoribbons, nanotubes and mixtures thereof, the nanometric filamentary structures being functionalized or unfunctionalized; and a filler chosen from carbon black and silica. These compositions can be cured or uncured and they can be used for preparing various articles. Methods for preparing such compositions are also disclosed.

- (51) International Patent Classification:

<i>C08L 9/02</i> (2006.01)	<i>C08J 5/04</i> (2006.01)
<i>C08J 3/18</i> (2006.01)	<i>C08K 3/04</i> (2006.01)
<i>C08J 3/20</i> (2006.01)	<i>C08K 3/36</i> (2006.01)
<i>C08J 3/24</i> (2006.01)	<i>C08K 7/02</i> (2006.01)
- (21) International Application Number:
PCT/CA2014/000756
- (22) International Filing Date:
20 October 2014 (20.10.2014)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
61/892,559 18 October 2013 (18.10.2013) US
- (71) Applicant: **SOUCY TECHNO INC.** [CA/CA]; 2550 St-Roch Sud, Sherbrooke, Québec J1N 2R6 (CA).
- (72) Inventors: **BÉDARD, François**; 1595 Matisse, Sherbrooke, Québec J1N 4J5 (CA). **DUBÉ, Denis**; 1061 Beausoleil, Sherbrooke, Québec J1N 4G6 (CA). **MAC-DONALD, Lyle**; 3130 Ch. St-Roch, Sherbrooke, Québec J1R 0H3 (CA). **COUÉ, Jean-Damien**; 128 rue Clark, Sherbrooke, Québec J1J 2N5 (CA).
- (74) Agent: **BERESKIN & PARR LLP/S.E.N.C.R.L., S.R.L.**; 40th Floor, 40 King Street West, Toronto, Ontario M5H 3Y2 (CA).
- (81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.
- (84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).
- Published:**
— *with international search report (Art. 21(3))*

WO 2015/054779 A1

(54) Title: RUBBER COMPOSITIONS AND USES THEREOF

(57) **Abstract:** There are provided rubber compositions comprising an elastomer comprising a rubber chosen from acrylonitrile-butadiene, hydrogenated acrylonitrile-butadiene, carboxylated acrylonitrile-butadiene and mixtures thereof; reinforcing fibers chosen from aramid fibers, carbon fibers, polyester fibers, glass fibers, nylon fibers and mixtures thereof, and/or nanometric filamentary structures chosen from nanowires, nanorods, nanofibers, nanoribbons, nanotubes and mixtures thereof, the nanometric filamentary structures being functionalized or unfunctionalized; and a filler chosen from carbon black and silica. These compositions can be cured or uncured and they can be used for preparing various articles. Methods for preparing such compositions are also disclosed.

RUBBER COMPOSITIONS AND USES THEREOF

[0002] The present disclosure relates to improvements in the field of chemistry applied to rubber compositions. For example, such rubber compositions can be useful for preparing various articles for example used in the field of oil and gas industry as well as in the field of mining industry.

[0003] So far, rubber compositions have been developed for uses made under difficult or harsh conditions. This is the case, for example, for articles used in oil and gas industries and mining industries.

[0004] Some technologies require rubber articles that show outstanding resistance properties to oil, heat, pressure and abrasion. For examples, the rubber articles can be in contact with oil and abrasives such as and at depths as far as 3000 meters down in earth.

[0005] Unfortunately, the solutions proposed so far are most of the time either too expensive or not reliable.

[0006] There would thus be a need to develop new rubber composition effective for preparing rubber articles that would exhibit better durability in presence oil and abrasives. There would also be a need to develop compositions effective for preparing rubber articles showing the same (or better) level of durability than the standard compositions but that can be made at lower costs.

[0007] There is however still a need for providing an alternative to the existing solutions for preparing rubber compositions.

[0008] According to one aspect, there is provided a rubber composition comprising :

an elastomer;

reinforcing fibers and/or nanometric filamentary structures; and

a filler.

[0009] According to another aspect, there is provided a rubber composition comprising :

an elastomer;

reinforcing fibers and/or nanometric filamentary structures; and

a filler,

wherein the composition is an uncured rubber composition.

[0010] According to another aspect, there is provided a rubber composition comprising :

an elastomer;

reinforcing fibers and/or nanometric filamentary structures; and

a filler,

wherein the composition is a cured rubber composition.

[0011] According to another aspect, there is provided a rubber composition comprising :

about 45 to about 70 wt. % of an elastomer;

about 0.1 to about 10 wt. % of reinforcing fibers and/or nanometric filamentary structures; and

about 15 to about 40 wt. % of a filler.

[0012] According to another aspect, there is provided a rubber composition comprising :

about 45 to about 70 wt. % of an elastomer;

about 0.1 to about 10 wt. % of reinforcing fibers and/or nanometric filamentary structures; and

about 15 to about 40 wt. % of a filler.

wherein the composition is an uncured rubber composition.

[0013] According to another aspect, there is provided a rubber composition comprising :

about 45 to about 70 wt. % of an elastomer;

about 0.1 to about 10 wt. % of reinforcing fibers and/or nanometric filamentary structures; and

about 15 to about 40 wt. % of a filler.

wherein the composition is a cured rubber composition.

[0014] According to another aspect, there is provided a rubber composition comprising :

about 30 to about 85 wt. % of an elastomer;

about 0.1 to about 10 wt. % of reinforcing fibers and/or nanometric filamentary structures; and

about 15 to about 40 wt. % of a filler.

[0015] According to another aspect, there is provided a rubber composition comprising :

about 30 to about 85 wt. % of an elastomer;

about 0.1 to about 10 wt. % of reinforcing fibers and/or nanometric filamentary structures; and

about 15 to about 40 wt. % of a filler.

wherein the composition is an uncured rubber composition.

[0016] According to another aspect, there is provided a rubber composition comprising :

about 30 to about 85 wt. % of an elastomer;

about 0.1 to about 10 wt. % of reinforcing fibers and/or nanometric filamentary structures; and

about 15 to about 40 wt. % of a filler.

wherein the composition is a cured rubber composition.

[0017] According to another aspect, there is provided a rubber composition comprising :

an elastomer comprising a rubber chosen from acrylonitrile-butadiene polymer, hydrogenated acrylonitrile-butadiene polymer, carboxylated acrylonitrile-butadiene polymer and mixtures thereof;

reinforcing fibers and/or nanometric filamentary structures; and

a filler.

[0018] According to another aspect, there is provided a rubber composition comprising :

an elastomer comprising a rubber chosen from hydrogenated acrylonitrile-butadiene polymer, carboxylated acrylonitrile-butadiene polymer and mixtures thereof;

reinforcing fibers and/or nanometric filamentary structures; and

a filler.

[0019] According to another aspect, there is provided a rubber composition comprising :

an elastomer comprising a rubber chosen from acrylonitrile-butadiene polymer, hydrogenated acrylonitrile-butadiene polymer, carboxylated acrylonitrile-butadiene polymer and mixtures thereof;

reinforcing fibers chosen from aramid fibers, carbon fibers, polyester fibers, glass fibers, nylon fibers and mixtures thereof, and/or nanometric filamentary structures chosen from nanowires, nanorods, nanofibers, nanoribbons, nanotubes and mixtures thereof, the nanometric filamentary structures being functionalized or unfunctionalized; and

a filler chosen from carbon black and silica.

[0020] According to another aspect, there is provided a rubber composition comprising :

an elastomer comprising a rubber chosen from hydrogenated acrylonitrile-butadiene polymer, carboxylated acrylonitrile-butadiene polymer and mixtures thereof;

reinforcing fibers chosen from aramid fibers, carbon fibers, polyester fibers, glass fibers, nylon fibers and mixtures thereof, and/or nanometric filamentary structures chosen from nanowires, nanorods, nanofibers, nanoribbons, nanotubes and mixtures thereof, the nanometric filamentary structures being functionalized or unfunctionalized; and

a filler chosen from carbon black and silica.

[0021] It was found that such compositions were effective for preparing various articles at low costs. In fact, these compositions allowed for preparing articles having the desired properties for various uses, while allowing for simple preparation processes at low costs. Moreover, these compositions were found to effective for preparing rubber articles showing improved and superior characteristics over articles made by prior art compositions.

[0022] In the following drawings, which represent by way of examples only, various embodiments of the disclosure.

[0023] Further features and advantages will become more readily apparent from the following description of various embodiments as illustrated by way of examples.

[0024] The expression "nanometric filamentary structures" as used herein refers to structures having a high dipole moment when they are charged since such nanometric structures have a high aspect ratio (length / diameter), which can be, for example, above 10. For example, they have a diameter that is inferior to about 100 nm, which allows a significant increase in the local electric field at the tip or the surface of the structures, so that they can readily emit electrons by the field or Schottky emission effect.

[0025] In understanding the scope of the present disclosure, the term "comprising" and its derivatives, as used herein, are intended to be open ended terms that specify the presence of the stated features, elements, components, groups, integers, and/or steps, but do not exclude the presence of other unstated features, elements, components, groups, integers and/or steps. The foregoing also applies to words having similar meanings such as the terms, "including", "having" and their derivatives. The term "consisting" and its derivatives, as used herein, are intended to be closed terms that specify the presence of the stated features, elements, components, groups, integers, and/or steps, but exclude the presence of other unstated features, elements, components, groups, integers and/or steps. The term "consisting essentially of", as used herein, is intended to specify the presence of the stated features, elements, components, groups, integers, and/or steps as well as those that do not materially affect the basic and novel characteristic(s) of features, elements, components, groups, integers, and/or steps.

[0026] Terms of degree such as "about" and "approximately" as used herein mean a reasonable amount of deviation of the modified term such that the end result is not significantly changed. These terms of degree should be construed as including a deviation of at least $\pm 5\%$ or at least $\pm 10\%$ of the modified term if this deviation would not negate the meaning of the word it modifies.

[0027] The term "wt %" as used herein when describing an ingredient present in a composition, refers to the weight % of this ingredient based on the total weight of the composition.

[0028] For example, in the composition, the elastomer, reinforcing fibers and/or nanometric filamentary structures and filler can be substantially uniformly distributed.

[0029] For example, the elastomer can comprise a rubber chosen from acrylonitrile-butadiene polymer (NBR), hydrogenated acrylonitrile-butadiene polymer (HNBR), carboxylated acrylonitrile-butadiene polymer (XNBR) and mixtures thereof.

[0030] For example, the elastomer can comprise a rubber that is acrylonitrile-butadiene polymer (NBR).

[0031] For example, the elastomer can comprise a rubber that is hydrogenated acrylonitrile-butadiene polymer (HNBR).

[0032] For example, the elastomer can comprise a rubber that is carboxylated acrylonitrile-butadiene polymer (XNBR).

[0033] For example, the elastomer can comprise about 25 to about 60 wt. %, about 30 to about 55 wt. %, about 40 to about 60 wt. %, about 45 to about 55 wt. %, about 40 to about 50 wt. % or about 46 to about 52 wt. % of acrylonitrile.

[0034] For example, the reinforcing fibers can be chosen from aramid fibers, carbon fibers, polyester fibers, glass fibers, nylon fibers and mixtures thereof, and/or nanometric filamentary structures chosen from nanowires, nanorods, nanofibers, nanoribbons, nanotubes and mixtures thereof.

[0035] For example, the nanometric filamentary structures can be functionalized or unfunctionalized.

[0036] For example, the filler can be chosen from carbon black and silica, and a mixture thereof.

[0037] For example, the filler can be chosen from carbon black and silica, bis (triethoxysilylpropyl) polysulfide, and mixtures thereof.

[0038] For example, the composition can comprise about 30 to about 85 wt. % of the elastomer, about 35 to about 80 wt. %, about 45 to about 70 wt. % of the elastomer, about 50 to about 65 wt. % of the elastomer, about 55 to about 60 wt. % of the elastomer, about 52 to about 61 wt. % of the elastomer, about 50 to about 55 wt. % of the elastomer, about 52 to about 54 wt. % of the elastomer, about 40 to about 60 wt. % of the elastomer, about 57 to about 59 wt. % of the elastomer, about 40 to about 55 wt. % of the elastomer, or about 42 to about 48 wt. % of the elastomer.

[0039] For example, the composition can comprise about 0.1 to about 10 wt. %, about 0.1 to about 3 wt. %, about 0.25 to about 1.75 wt, about 0.5 to about 1.5 wt. %, or about 0.75 to about 1.25 wt. % of the reinforcing fibers.

[0040] For example, the composition can comprise about 0.1 to about 10 wt. %, about 0.1 to about 3 wt. %, about 0.25 to about 1.75 wt. %, about 0.5 to about 1.5 wt. % or about 0.75 to about 1.25 wt. % of the nanometric filamentary structures.

[0041] For example, the composition can comprise about 0.1 to about 10 wt. % of the reinforcing fibers and/or nanometric filamentary structures.

[0042] For example, the composition can comprise about 0.5 to about 10 wt. % of the reinforcing fibers and/or nanometric filamentary structures.

[0043] For example, the composition can comprise about 1 to about 5 wt. % of the reinforcing fibers and/or nanometric filamentary structures.

[0044] For example, the composition can comprise about 1 to about 3 wt. % of the reinforcing fibers and/or nanometric filamentary structures.

[0045] For example, the nanometric filamentary structures can comprise nanowires, nanorods, nanofibers, nanoribbons, nanotubes or bundles thereof, or mixtures thereof.

[0046] For example, the nanometric filamentary structures can comprise functionalized nanowires, functionalized nanorods, functionalized nanofibers,

functionalized nanoribbons, functionalized nanotubes or bundles thereof, or mixtures thereof.

[0047] For example, the nanometric filamentary structures can be chosen from single-wall carbon nanotubes (SWCNT), functionalized single-wall carbon nanotubes, multi-wall carbon nanotubes (MWCNT), functionalized multi-wall carbon nanotubes, carbon nanometric fibres, functionalized carbon nanometric fibres and mixtures thereof.

[0048] For example, the nanometric filamentary structures can comprise a member chosen from of C, BN, B, Si, Ge, Bi, Sn, Te, Se, Hg, Si_3N_4 , V_2O_3 , MX_2 wherein M is Ti, Zr, Hf, Nb, Ta, Mo, W or Re and X is S, Se or Te, InP, InAs, GaN, GaP, GaAs, Ga_2O_3 , ZnO, In_2O_3 , $\text{Na}_2\text{V}_3\text{O}_7$, Al_2O_3 , B_2O_3 , MgO, CdO, SiO_2 , SnO_2 , CuO, $(\text{SN})_x$, Cu_2S , $\text{B}_x\text{C}_y\text{N}_z$, NiCl_2 , InS, ZnS, ZnSe, CdS, CdSe, Ag_2Se , SiC, B_4C , M_2MoX_6 wherein M is Li or Na and X is Se or Te, coated structures thereof and mixtures thereof.

[0049] For example, the aramid fibers can be short or long. For example, the aramid fibers can be in pulp or milled form.

[0050] For example the aramid fibers can be TwaronTM or KevlarTM.

[0051] For example, the rubber compositions of the disclosure can be used in the manufacture of various rubber articles including tracks, pneumatics, strips, sheets, bands, belts, hoses, linings, gaskets, guides, drive lugs, guide lugs, transmission belts, conveyor belts, a part of a pumping system, a powersection stator, etc.

[0052] For example, the composition can comprise about 15 to about 40 wt. %, about 20 to about 35 wt. %, about 25 to about 32 wt %, about 20 to about 25 wt % or about 26 to about 30 wt. % of the filler.

[0053] For example, the elastomer can comprise acrylonitrile-butadiene rubber.

[0054] For example, the elastomer can comprise hydrogenated acrylonitrile-butadiene rubber.

[0055] For example, the elastomer can comprise carboxylated acrylonitrile-butadiene rubber.

[0056] For example, the elastomer can comprise carboxylated acrylonitrile-butadiene rubber and acrylonitrile-butadiene rubber.

[0057] For example, the acrylonitrile-butadiene rubber can comprise about 15 to about 65 wt. % of acrylonitrile, about 25 to about 50 wt. % of acrylonitrile or about 30 to about 45 wt. % of acrylonitrile.

[0058] For example, the hydrogenated acrylonitrile-butadiene rubber can comprise about 15 to about 65 wt. % of acrylonitrile, about 25 to about 50 wt. % of acrylonitrile or about 30 to about 45 wt. % of acrylonitrile.

[0059] For example, the carboxylated acrylonitrile-butadiene rubber can comprise about 15 to about 65 wt. % of acrylonitrile, about 25 to about 50 wt. % of acrylonitrile or about 30 to about 45 wt. % of acrylonitrile.

[0060] For example, the composition can comprise reinforcing fibers that are aramide fibers.

[0061] For example, the composition can comprises nanometric filamentary structures that are carbon nanotubes. The carbon nanotubes can be functionalized or not.

[0062] For example, the carbon nanotubes can be multi-wall carbon nanotubes.

[0063] For example, the carbon nanotubes can be single-wall carbon nanotubes.

[0064] For example, the composition can further comprise a cross-linking agent. For example, the cross-linking agent can comprise sulphur.

[0065] For example, the composition can further comprise a cross-linking agent chosen from sulphur, metal oxides and peroxides.

[0066] For example, the composition can comprise about 0.5 to about 3.0 % or about 0.5 to about 2.0 % of the cross-linking agent.

[0067] For example, the composition can further comprise a plastifier.

[0068] For example, the plastifier can comprise high aromatic oil, naphthenic oil, paraffinic oil, adipates, phthalates, sebacates and mixtures thereof.

[0069] For example, the composition can comprise about 1 to about 3 % or about 1.5 to about 2.5 % of the plastifier.

[0070] For example, the composition can comprise about 1 to about 20 % or about 2 to about 15 % of the plastifier.

[0071] For example, the composition can further comprise an anti-aging agent.

[0072] For example, the anti-aging agent can comprise 1,2-dihydro-2,2,4-trimethylquinoline, n-cyclohexyl-n'-phenyl-p-phenylenediamine, zincmethylmercaptobenzimidazole, n-isopropyl-n'-phenyl-p-phenylenediamine (ippd), wingstay 100, n. n'-bis-(1-ethyl-3-methyl phenyl)-p-phenylenediamine, n-(1, 3-dimethylbutyl)-n'-phenyl-p-phenylenediamine, octylated diphenylamine, n, n'-diphenyl-p-phenylenediamine, 4,4'-Bis-(a,a'-dimethylbenzyl) diphenylamine, BLETM 75, or mixtures thereof.

[0073] For example, the composition can comprise about 1.0 to about 3.0 %, or about 1.5 to about 2.5 % of the anti-aging agent.

[0074] For example, the composition can further comprise a fluidizing agent.

[0075] For example, the fluidizing agent can comprise a hydrocarbon resin a phenolic resin, zinc soap salts, or mixtures thereof.

[0076] For example, the composition can comprise about 0.5 to about 3.0 % or about 1.0 to about 2.5 % of the fluidizing agent.

[0077] For example, the composition can further comprise a rubber vulcanization accelerator agent.

[0078] For example, the rubber vulcanization accelerator agent can be chosen from diphenylguanidine, (TBBS) N-tertiary butyl-2-benzothiazolesulfenamide, (TBSI) N-t-butyl-2-benzothiazolesulfenimide,

benzothiazyl-2-dicyclohexyl sulfenamide, DelacTM MOR, (MBS: 2-(Morpholiniothio) benzothiazole sulfenamide), DelacTM S (CBS N-Cyclohexyl-2-benzothiazolesulfenamide) DCBS (N,N-dicyclohexyl-2-benzothiazolesulfenamide) MBT (2-mercaptobenzothiazole), MBTS (Dibenzothiazoledisulfide), DPG (Diphenylguanidine), ethylene thiourea, DTDM (4,4 dithiodimorpholine, TMTM (Tetramethylthiuram monosulfide), TMTD (Tetramethylthiuram disulfide), etc. and mixtures thereof.

[0079] For example, the composition can comprise about 0.5 to about 1.5 % or about 0.75 to about 1.25 % of the vulcanization accelerator agent.

[0080] For example, the composition can further comprise a retarding agent.

[0081] For example, the retarding agent can be chosen from (PVI) N-(cyclohexylthio)phthalimide, retarder SAX (salicylic acid), retarder ESEN, (2-benzozoic acid, and mixtures thereof.

[0082] For example, the composition can comprise about 0.1 to about 1.0 % or about 0.2 to about 0.8 % of the retarding agent.

[0083] For example, the composition can further comprise a hardening agent.

[0084] For example, the hardening be an agent chosen from phenolic resin, hexamethylnetetramine, resimene (hexamethoxymethyl/n-butyl-melamine formaldehyde resin), etc. and mixtures thereof.

[0085] For example, the composition can comprise about 0.5 to about 2.5 % or about 1.0 to about 2.0 % of the hardening agent.

[0086] For example, the composition can further comprise a reticulation agent.

[0087] For example, the reticulation agent can be chosen from stearic acid, zinc oxide and a mixture thereof.

[0088] For example, the composition can be an uncured rubber composition.

[0089] For example, the composition can be an uncured rubber composition having a Mooney viscosity ML 145°C of about 10 to about 120, measured according to D-1646 standard.

[0090] For example, the composition can be an uncured rubber composition having a Mooney viscosity ML 145°C of about 40 to about 100, measured according to D-1646 standard.

[0091] For example, the composition can be an uncured rubber composition having a Mooney viscosity ML 145°C of about 50 to about 100, measured according to D-1646 standard.

[0092] For example, the composition can be an uncured rubber composition having a Mooney viscosity ML 145°C of about 50 to about 80, measured according to D-1646 standard.

[0093] For example, the composition can be an uncured rubber composition having a Mooney viscosity ML₁₊₄ 145°C of about 60 to about 80, measured according to D-1646 standard.

[0094] For example, the composition can be an uncured rubber composition having a Mooney Scorch time t₅ 145°C of about 3 to about 10 minutes, measured according to ASTM D-1646 standard.

[0095] For example, the composition can be an uncured rubber composition having a Mooney Scorch time t₅ 145°C of about 4 to about 8 minutes, measured according to ASTM D-1646 standard.

[0096] For example, the composition can be an uncured rubber composition having a Mooney Scorch time t₅ 145°C of about 4 to about 6 minutes, measured according to ASTM D-1646 standard.

[0097] For example, the composition can be an uncured rubber composition having a Mooney Scorch time t₅ 145°C of about 4 to about 5 minutes, measured according to ASTM D-1646 standard.

[0098] For example, the composition can be an uncured rubber composition having a specific gravity of about 1.0 to about 1.5 g/mL, measured according to ASTM D-297 standard.

[0099] For example, the composition can be an uncured rubber composition having a specific gravity of about 1.1 to about 1.2 g/mL, measured according to ASTM D-297 standard.

[00100] For example, the composition can be an uncured rubber composition having a specific gravity of about 1.10 to about 1.15 g/mL, measured according to ASTM D-297 standard.

[00101] For example, the composition can be a cured rubber composition.

[00102] For example, the composition can be a cured rubber composition having an elongation % of about 400 to about 650, measured according to ASTM D-412 standard.

[00103] For example, the composition can be a cured rubber composition having an elongation % of about 450 to about 600, measured according to ASTM D-412 standard.

[00104] For example, the composition can be a cured rubber composition having an elongation % of about 500 to about 575, measured according to ASTM D-412 standard.

[00105] For example, the composition can be a cured rubber composition having an elongation % of about 510 to about 560, measured according to ASTM D-412 standard.

[00106] For example, the composition can be a cured rubber composition having an elongation % of about 520 to about 550, measured according to ASTM D-412 standard.

[00107] For example, the composition can be a cured rubber composition having a 25 % modulus of about 100 to about 500, measured according to ASTM D-412 standard.

[00108] For example, the composition can be a cured rubber composition having a 25 % modulus of about 150 to about 450, measured according to ASTM D-412 standard.

[00109] For example, the composition can be a cured rubber composition having a 25 % modulus of about 150 to about 300, measured according to ASTM D-412 standard.

[00110] For example, the composition can be a cured rubber composition having a 25 % modulus of about 200 to about 300, measured according to ASTM D-412 standard.

[00111] For example, the composition can be a cured rubber composition having a 25 % modulus of about 225 to about 275, measured according to ASTM D-412 standard.

[00112] For example, the composition can be a cured rubber composition having a cured rubber composition having a 100 % modulus of about 300 to about 1500, measured according to ASTM D-412 standard.

[00113] For example, the composition can be a cured rubber composition having a cured rubber composition having a 100 % modulus of about 300 to about 1000, measured according to ASTM D-412 standard.

[00114] For example, the composition can be a cured rubber composition having a cured rubber composition having a 100 % modulus of about 400 to about 900, measured according to ASTM D-412 standard.

[00115] For example, the composition can be a cured rubber composition having a cured rubber composition having a 100 % modulus of about 500 to about 900, measured according to ASTM D-412 standard.

[00116] For example, the composition can be a cured rubber composition having a cured rubber composition having a 100 % modulus of about 700 to about 900, measured according to ASTM D-412 standard.

[00117] For example, the composition can be a cured rubber composition having a cured rubber composition having a 100 % modulus of about 700 to about 850, measured according to ASTM D-412 standard.

[00118] For example, the composition can be a cured rubber composition having a cured rubber composition having a 300 % modulus of about 1500 to about 3000, measured according to ASTM D-412 standard.

[00119] For example, the composition can be a cured rubber composition having a cured rubber composition having a 300 % modulus of about 2000 to about 2800, measured according to ASTM D-412 standard.

[00120] For example, the composition can be a cured rubber composition having a cured rubber composition having a 300 % modulus of about 2100 to about 2700, measured according to ASTM D-412 standard.

[00121] For example, the composition can be a cured rubber composition having a 300 % modulus of about 2200 to about 2650, measured according to ASTM D-412 standard.

[00122] For example, the composition can be a cured rubber composition having a 300 % modulus of about 2200 to about 2400, measured according to ASTM D-412 standard.

[00123] For example, the rubber composition can be a cured rubber composition and wherein the composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, substantially maintains its elongation properties measured according to ASTM D-412 standard.

[00124] For example, the rubber composition can be a cured rubber composition and wherein the composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, can have an elongation % of about -25 % to about 25 %, about -10 % to about 10 % or about -5 % to about 5 % measured according to ASTM D-412 standard, as compared to the a sample measured before fluid immersion.

[00125] For example, the rubber composition can be a cured rubber composition and wherein the composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, substantially maintains its weight.

[00126] For example, the rubber composition can be a cured rubber composition and wherein the composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, can have a weight

variation % of about -10 % to about 10 % or about -5 % to about 5 % as compared to a sample measured before fluid immersion.

[00127] For example, the rubber composition can be a cured rubber composition and wherein the composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, has a positive weight variation % of less than about 10 % or of less than about 5 %, as compared to a sample measured before fluid immersion.

[00128] For example, the rubber composition can be a cured rubber composition and wherein the composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, can substantially maintain its hardness properties measured according to ASTM D-2240 standard.

[00129] For example, the rubber composition can be a cured rubber composition and wherein the composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, can have a hardness variation % of about -15 % to about 15 %, about -15 % to about 5 %, about -15 % to about 5 % or about -5 % to about 0 % as compared to a sample measured before fluid immersion.

[00130] For example, the rubber composition can be a cured rubber composition and wherein the composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, can substantially maintain its tensile strength properties measured according to ASTM D-412 standard.

[00131] For example, the rubber composition can be a cured rubber composition and wherein the composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, has a tensile strength variation % of about -25 % to about 0 %, about -15 % to about 0 %, about -10 % to about 0 % or about -5 % to about 0 %, as compared to a sample measured before fluid immersion.

[00132] For example, the rubber composition can be a cured rubber composition and wherein the composition can have a hardness (shore A) of

about 50 to about 100, about 55 to about 95, about 60 to about 85, about 65 to about 85, about 60 to about 75, about 65 to about 70, about 66 to about 72 or about 75 to about 80, measured according to ASTM D-2240 standard.

[00133] For example, the elastomer can comprise about 25 to about 60 wt.%, about 30 to about 55 wt.%, about 45 to about 55 wt.%, about 40 to about 60 wt.%, about 45 to about 55 wt.%, about 40 to about 50 wt.% or about 46 to about 52 wt.% of acrylonitrile.

[00134] For example, the composition can further comprise talc.

[00135] For example, the composition can further comprise microcrystalline talc.

[00136] For example, talc or microcrystalline talc can be present at a concentration of about 1 to about 20 wt. %, about 2 to about 15 wt. %, about 5 to about 15 wt. % or about 6 to about 12 wt. %.

[00137] For example, the composition can further comprise a clay.

[00138] For example, the composition can further comprise a nanoclay.

[00139] For example, the clay or nanoclay can be present at a concentration of about 1 to about 20 wt. %, about 2 to about 15 wt. %, about 5 to about 15 wt. %, or about 6 to about 12 wt. %.

[00140] According to another aspect, there is provided a method of manufacturing a composition as defined in the present disclosure. The method comprises:

mixing together the elastomer and the reinforcing fibers and/or nanometric filamentary structures to obtain a first mixture;

mixing together the first mixture with the filler so as to obtain a second mixture; and

mixing together the second mixture with a crosslinking agent.

[00141] According to another aspect, there is provided a method of manufacturing a composition as defined in the present disclosure. The method comprises:

mixing together the elastomer and the reinforcing fibers and/or nanometric filamentary structures to obtain a first mixture;

mixing together the first mixture with the filler and optionally an anti-aging agent so as to obtain a second mixture; and

mixing together the second mixture with a crosslinking agent, optionally an hardening agent, and optionally a vulcanization accelerator agent.

[00142] According to another aspect, there is provided an article comprising a rubber composition as defined in the present disclosure.

[00143] According to another aspect, there is provided a method for manufacturing an article comprising rubber, the method comprising using a rubber composition as defined in the present disclosure when moulding, extruding and/or calendering the article.

[00144] For example, the method can comprise calendering and/or extruding the rubber composition so as to obtain a rubber band, a rubber strip, a rubber log or a rubber sheet; and moulding and vulcanizing the a rubber band, a rubber strip, a rubber lug or a rubber sheet so as to obtain the article.

[00145] For example, the method can comprise calendering and/or extruding the rubber composition so as to obtain is a rubber band, a rubber strip, a rubber log or a rubber sheet; and moulding and vulcanizing a plurality of rubber bands, rubber strips, rubber lugs or rubber sheets so as to obtain the article.

[00146] For example, the moulding can be carried out by compression moulding.

[00147] For example, the article can be a rubber band, a rubber strip or a rubber sheet.

- [00148] For example, the article can be a track for use on a vehicle.
- [00149] For example, the article can be a snowmobile track.
- [00150] For example, the article can be a tractor track.
- [00151] For example, the article can be a tank track.
- [00152] For example, the track can be an endless track.
- [00153] For example, the article can be a tire.
- [00154] For example, the article can be a gasket.
- [00155] For example, the article can be a hose.
- [00156] For example, the article can be a transmission belt.
- [00157] For example, the article can be a tank lining.
- [00158] For example, the article can be a part of a pumping system.
- [00159] For example, the article can be a rubber band, a rubber strip, a rubber lug, a rubber belt or a rubber sheet .
- [00160] For example, the article can be chosen from strips, sheets, bands, belts, hoses, linings, gaskets, guides, drive lugs, guide lugs, and transmission belts.
- [00161] According to another aspect, there is provided a method for manufacturing an article comprising rubber, the method comprising using a rubber composition as defined in the present disclosure when moulding, extruding and/or calendering the article.
- [00162] For example, the method can comprise calendering and/or extruding the rubber composition so as to obtain a rubber band, a rubber strip, a rubber log or a rubber sheet; and moulding and vulcanizing the a rubber band, a rubber strip, a rubber lug or a rubber sheet so as to obtain the article.
- [00163] For example, the method can comprise calendering and/or extruding the rubber composition so as to obtain is a rubber band, a rubber strip, a rubber log or a rubber sheet; and moulding and vulcanizing a plurality

of rubber bands, rubber strips, rubber lugs or rubber sheets so as to obtain the article.

[00164] For example, the moulding can be carried out by compression moulding.

[00165] The below presented examples are non-limitative and are used to better exemplify the processes of the present disclosure.

Example 1 – Preparation of Rubber Composition 1

[00166] The ingredients use for the Composition 1 with their amount in phr - mass (g) per hundred grams of elastomer are represented in Table 1. The equivalents in % by weight is also presented. The Acrylonitrile-Butadiene-Polymer (NBR) was produced by Khumo. The Merge 1F770TM is a 23.5% w/w dispersion of short pulp aramid Kevlar fibers in a NBR matrix processed in liquid phase by DupontTM inc. It is a dispersion of aramid fiber. The NC 7000TM used is a high aspect ratio Multi Wall Carbon nanotube from NanocylTM sa with average wall diameter of 9.5 nm and with an average length of 1.5 microns. The carbon blacks grades used were produced from ContinentalTM inc. and corresponds to a N550 grade with an Iodine adsorption value of 50 mg/g and a DBP absorption value of 120 mL/100g and a N774 grade with an Iodine adsorption value of 35 mg/g and a DBP absorption value of 75 mL/100g.

[00167] Stearic acid and zinc oxide are used to promote reticulation of rubber during curing as well as process aids. 1,3-dimethylbutyl)-N'-phenyl-P-Phenylenediamine are used as anti-aging and anti-fatigue agents to capture free radicals. Parafin wax is used as a UV blocking agent. They were supplied by Ferguson Chemicals Inc.

[00168] N-tertiary butyl-2- benzothiazole sulfenimide was used as rubber vulcanization accelerator agent. Sulfur was used as e crosslinking agent. It was supplied by FergusonTM Chemicals Inc.

Table 1 Formulation of Rubber Composition 1

Material ----- phr -----(wt. %)

First Stage Mix
TM
 Kosyn KNB-35LM Acrylonitrile-Butadiene-Polymer (NBR) --- 96.65 ---52.36

MERGE 1F770 KEVLAR Engineered Elastomer (in NBR) ---4.35---2.36

PRO 7000 (NC 7000 MWCNT)----- 2.00-----1.08

Carbon Black N-774----10----5.42

Second Stage Mix

Masterbatch from first stage

Carbon Black N-550----35----18.96

DBEEA (Dibutoxyethoxyethyl adipate plastisizer)---- 21----11.38

Stearic Acid----1-----0.54

Zinc Oxide----5-----2.71

 6PPD / FLEXONE-7F N-(1,3-dimethylbutyl)-N'-phenyl-P-Phenylenediamine)--
 --- 2.5-----1.35

TM
 NOCHEK 4709A (Parafin Wax)----- 3-----1.63
Third Stage Mix

Masterbatch from second stage

TBBS (N-tertiary butyl-2- benzothiazole sulfenamide)----- 2-----1.08

SOUFRE H-10 (Sulfur)----- 2.1-----1.14

Mixing and processing method

[00169] All the mixing phases and stages were carried in a Farrell 1.5 L Banbury mixer with Tangential rotors blending the ingredients by friction with the chamber sidewall and an hydraulic ram to put pressure to the mix. It is equipped with an automated control box permitting variable mixing speeds and an accurate control over time, pressure, energy and temperature during all the mixing process. The batch produced is then processed in a Laboratory Two Roll Mill put into sheet form and then cooled down after each mix stage. If the mix is not final, it goes back to the mixer as a masterbatch for the next mixing step 24 hours later.

[00170] The first stage mix (preparation of MasterBatch 1) was carried out as follow:

- 1) Add PRO 7000;
- 2) Add carbon black, polymer and Merge 1F770;
- 3) Mix Ram float at low speed (70 rpm) for 20 seconds;
- 4) Mix until temperature rise to 120 Celcius at 50 rpm;
- 5) Ram up;
- 6) Mix until temperature rise to 140 Celcius at low speed;
- 7) Ram Up; and
- 8) Drop

3 minutes mixing time total, thereby obtaining MasterBatch 1

[00171] The aim of this first pass mix was to break down the viscosity of the nitrile rubber as well as to force the preliminary dispersion of MWCNT, carbon black and Kevlar which is a challenge to achieve completely. It is done at high sheer with a medium drop temperature.

[00172] The second stage mix (preparation of MasterBatch 2) was done as follows:

1) Add MasterBatch 1 and chemicals (EMERY-400/VSTEARIN (Stearic Acid); ZINC OXYDE CR-4/ZOCO (Zinc Oxide); 6PPD / FLEXONE-7FN-(1,3-dimethylbutyl)-N'-phenyl-P-Phenylenediamine) and NOCHEK 4709A (Parafin Wax);

2) Add half carbon black; DBEEA (Dibutoxyethoxyethyl adipate plastisizer) and the rest of carbon black;

3) Mix to 105 Celcius at low speed;

4) Ram up;

5) Mix to 140 Celcius at low speed;

6) Drop;

4 minutes mixing time total, MasterBatch 2.

[00173] The aim of this second pass is to force by high sheer the incorporation of the reinforcing carbon black and Plasticizer and to complete the dispersion of Kevlar, MWCNT and the other chemicals.

[00174] The third stage, the finalization of mixing, was perform accordingly to the following:

1) Add MasterBatch 2 and curative chemicals (TBBS (N-tertiary butyl-2- benzothiazole sulfenamide); SOUFRE H-10 (Sulfur);

2) Mix ram down 55 sec at low speed;

3) Ram up;

5) Mix to 110 Celcius at low speed;

6) Drop;

2 minutes mixing time total, thereby obtaining composition 1 (uncured).

[00175] The mixing of the finalization is done at low sheer and low temperature. It is meant to be done to finalize the dispersion of the curative agents without beginning the cure and to avoid scorching of the product.

Example 2 – Use of Rubber Composition 1 for preparing articles

[00176] The resulting uncured rubber Composition 1 can then be transformed in sheet form, profiles or lugs using a - two, three or four roll - calendar or an extruder equipped with a perform die, a roller head or without. The preformed material – for example a calendered uncured rubber sheet rolled of 15" x 0.120" - may then be used downstream in the production process to be assembled uncured with other layers of itself, layers of other rubber compounds with different properties (hardness) and along with other reinforcing non rubber material, using the natural tack of the rubber or with the use of adhesives or tack cement. It is then cured in a final product by compression moulding, injection, transfer or autoclave. This operation consists of heating the rubber under a certain temperature (about 140 °C to about 180 °C) to make the sulphur creates crosslinks between polymer chains – the curing process that gives to the rubber its final stable elastic properties - at high pressure to remove gas in a product form directed by the moulds form. For example, these products can be used to in the manufacture of hoses, tank liners, power section stators designed for oil and gas prospection applications, but it may also be used to manufacture rubber pieces for other applications, like the mining industry, tank lining, tires (of all kind and sizes), hoses, gaskets and all other rubber goods.

[00177] These compositions can thus be used, for example, in oil sands pipes. The interior is covered with a rubber liner that must be resistant to the immersion in oil as well as being resistant to excessive wear and abrasion. In addition, for powers stator applications, the resistance to excessive heat and pressure due to deep ground forencing. The technology claimed improves drastically all of them and moreover the final field performance. It is likely to do the same for all highly demanding applications were thermal, oil,

chuncking and wear resistance like OTR tires, mining ball mills and conveyors, specialty hoses, etc.

Example 3 – Preparation of Various Rubber Compositions

[00178] Similarly to Composition 1, previously discussed, other compositions (Compositions 2 and 3) have been prepared by using the same method. Their ingredients are listed in Table 2 below.

Example 4 – Comparative Tests for Various Rubber Compositions

[00179] Compositions 1 to 3 have been tested. The physical properties of Compositions 1 to 3 are listed in Table 3.

[00180] Specific Gravity has been measured according to ASTM D-297 standard. Hardness has been measured according to ASTM D-2240 standard with a Bareiss Durometer. Tensile strength, elongation at break and modulus has been measured according to ASTM D-412 standard with a TensiData tensiometer. Tear propagation strength was measured according to ASTM standard D-624 die C with a TensiData tensiometer.

[00181] MDR and viscosimetry have been tested using standards ASTM D-2084 and D-1646 respectively. The aim of these tests are to understand the processing behaviour of the uncured rubber paste to optimise calendering and extrusion as well as to understand and control the curing kinetics (slow curing or fast curing) during mould vulcanization.

[00182] DIN abrasion test has been evaluated with a Bareiss DIN abrader instrument according to ASTM D-5963 method and was meant to measure the resistance of the material to wear with the presence of sands and mud. Heat aging have been tested using standard ASTM D-573 to measure the deterioration of the rubber into a hot air oven at 100°C for a period of time of 70 hours. The aim of this test was to evaluate the thermal resistance and aging properties of the composition. Such a property is quite important to powersection stators application.

Table 2. Ingredients of Various Rubber Compositions

Trade Name	Chemical Formula	Composition 1 (NBR 100, CNT, kevlar)		Composition 2 (HNBR 100, CNT, kevlar)		Composition 3 (XNBR 100, CNT, kevlar)	
		phr	% w/w	phr	% w/w	phr	% w/w
Kosyn KNB-35LM	Acrylonitrile-Butadiene-Polymer (NBR)	96.65	52.36%				
Therban 4364 VP	Hydrogenated Acrylonitrile-Butadiene-Polymer (HNBR)			97.970	53.68%		
Nipol NX-775	Carboxylated Acrylonitrile-Butadiene-Polymer (XNBR)					96.650	53.83%
MERGE 1F770	KEVLAR Engineered Elastomer (in NBR)	4.35	2.36%				
MERGE 1F1598	KEVLAR Engineered Elastomer (in HNBR)			3.030	1.66%	4.350	2.42%
PRO 7000	NC 7000 MWCNT	2	1.08%	2.000	1.10%	2.000	1.11%
Carbon Black N-330	Carbon Black					35.000	19.49%
Carbon Black N-550	Carbon Black	35	18.96%				
Carbon Black N-774	Carbon Black	10	5.42%	35.000	19.18%		
Barythes 22	Barium Sulfate			10.000	5.48%		
DBEEA	Dibutoxyethoxyethyl adipate plastisizer	21	11.38%			15.000	8.35%
DOP	Diocetyl Phthalate			17.000	9.32%		
Degussa Si-69	Bis (triethoxysilylpropyl) polysulfide			2.000	1.10%		
Nipol 1312 LV	Acrylonitrile-Butadiene-Polymer (NBR) Low Molecular weight					7.000	3.90%
Stearic Acid	Stearic acid	1	0.54%	1.000	0.55%	1.000	0.56%
Zinc Oxide	Zinc Oxide	5	2.71%	5.000	2.74%	5.000	2.78%
Pluriol E4000	Polyethylene Glycol			1.000	0.55%		
TMQ	1,2-Dihydro-2,2,4-trimethylquinoline					1.000	0.56%
6PPD	N-cyclohexyl-N'-phenyl-p-phenylenediamine	2.5	1.35%				
Naugard 445	4,4'-Bis-(a,a'-dimethylbenzyl) diphenylamine			1.500	0.82%		
Vanox ZMT1	Zincmethylmercaptopbenzimidazole			1.000	0.55%		
NOCHEK 4709A, Blended Waxe	Paraffin Wax	3	1.63%				
Cumar P-25 DLD (KD-109)	Coumarone Indene Resin					10.000	5.57%
TMTD	Tetramethyl thiuram disulfide			4.000	2.19%	0.300	0.17%
TBBS	N-tertiary butyl-2- benzothiazole sulfenamide	2	1.08%				
MBTS	Benzothiazyl disulfide					1.500	0.84%
Sulphur	Sulphur	2.1	1.14%	2.000	1.10%	0.750	0.42%
Total		184.60	100.00%	182.50	100.00%	179.55	100.00%

Table 3. Physical Properties of Various Rubber Compositions

Tested Compositions			
	Composition 1 (NBR 100, CNT, kevlar)	Composition 2 (HNBR 100, CNT, kevlar)	Composition 3 (XNBR 100, CNT, kevlar)
Tests			
Specific Gravity (g/mL)	1.164	1.170	1.147
Hardness (dureté shore A)	66	72	71
Tensile (psi)	1863	3018	1959
Elongation (%)	302	436	428
Modulus 50%	496	592	465
Modulus 100%	823	846	706
Modulus 300%	1849	1731	1303
Tear (lbs, die C)	200	239	204
MDR 191C ML	0.65	0.36	0.93
MDR 191C t10	0.71	0.8	0.55
MDR 191C t95	1.86	3.33	3.12
MDR 191C MH	14.72	13.77	5.78
Viscosity ML 145C	18	12	24
Scorch T-5 145C	6.75	5.18	5.61
DIN Abrasion (mm3)	114	163	130

[00183] Oil immersion have been evaluated in regards to ASTM D-412 and D-471 standards with a TensiData tensiometer. Immersions were performed using ASTM D-471 standard method with oil IRM903 (former oil ASTM 3) to evaluate the oil resistance properties. Variations in tensile-strain properties were then measured on dumbbells that has been immersed. In oil and gas applications, resistance properties of the rubber compound to fluids is primordial.

Aging (heat and oil) test results

[00184] Further tests have been made on compositions 1 to 3 and are shown in Table 5. More particularly, comparatives tests have been made with Compositions 1 to 3 by comparing them with Compositions A, B and C. Compositions A, B and C are similar to compositions 1, 2 and 3, respectively, with the exception that they do not comprises the reinforcing fibers and the nanometric filamentary structures of the compositions 1, 2 and 3. The Compositions A, B and C are described in Table 4. In Table 5, the Compositions 1 to 3 and A to C have been compared. In order to do so, sheets have been made with these compositions. Sheet 1 has been made with Composition A, sheet 2 has been made with Composition 1, sheet 3 has been made with Composition B, sheet 4 has been made with Composition 2, sheet 5 has been made with Composition C and sheet 6 has been made with Composition 3.

Table 4. Ingredients of Various Comparative Compositions

Trade Name	Chemical Formula	Composition-A (NBR 100, Reference, Oil and Gas Product)			Composition-1 (NBR 100, CNT, kevlar, Oil and Gas Product)			Composition-B (HNBR 100, Reference, Oil and Gas Product)			Composition-2 (HNBR 100, CNT, kevlar, Oil and Gas Product)			Composition-C (XNBR 100, Reference, Oil and Gas Product)			Composition-3 (XNBR 100, CNT, kevlar, Oil and Gas Product)		
		phr	% w/w		phr	% w/w		phr	% w/w		phr	% w/w		phr	% w/w		phr	% w/w	
Kosyn KNB-35LM	Acrylonitrile-Butadiene-Polymer (NBR)	100	53.59%		96.65	52.36%													
Therban 4364 VP	Hydrogenated Acrylonitrile-Butadiene-Polymer (HNBR)							100.000	55.71%		97.970	53.68%							
Nipol NX-775	Carboxylated Acrylonitrile-Butadiene-Polymer (XNBR)													100.000	55.08%	96.650	53.83%		
MERGE 1F770	KEVLAR Engineered Elastomer (in NBR)				4.35	2.36%													
MERGE 1F1598	KEVLAR Engineered Elastomer (in HNBR)										3.030	1.66%			0.00%	4.350	2.42%		
PRO 7000	NC 7000 MWCNT				2	1.08%					2.000	1.10%			0.00%	2.000	1.11%		
Carbon Black N-330	Carbon Black													40.000	22.03%	35.000	19.49%		
Carbon Black N-550	Carbon Black	40	21.44%		35	18.96%													
Carbon Black N-774	Carbon Black	10	5.36%		10	5.42%		35.000	19.50%		35.000	19.18%							
Barythes 22	Barium Sulfate							10.000	5.57%		10.000	5.48%							
DBEEA	Dibutoxyethoxyethyl adipate plastisizer	21	11.25%		21	11.38%								15.000	8.26%	15.000	8.35%		
DOP	Diocyl Phthalate							17.000	9.47%		17.000	9.32%							
Degussa Si-69	Bis (triethoxysilylpropyl) polysulfide							2.000	1.11%		2.000	1.10%							
Nipol 1312 LV	Acrylonitrile-Butadiene-Polymer (NBR) Low Molecular weight													7.000	3.86%	7.000	3.90%		
Stearic Acid	Stearic acid	1	0.54%		1	0.54%		1.000	0.56%		1.000	0.55%		1.000	0.55%	1.000	0.56%		
Zinc Oxide	Zinc Oxide	5	2.68%		5	2.71%		5.000	2.79%		5.000	2.74%		5.000	2.75%	5.000	2.78%		
Pluriol E4000	Polyethylene Glycol							1.000	0.56%		1.000	0.55%							
TMQ	1,2-Dihydro-2,2,4-trimethylquinoline													1.000	0.55%	1.000	0.56%		
6PPD	N-cyclohexyl-N'-phenyl-p-phenylenediamine	2.5	1.34%		2.5	1.35%													
Naugard 445	4,4'-Bis-(a,a'-dimethylbenzyl) diphenylamine							1.500	0.84%		1.500	0.82%							
Varox ZMTI	Zincmethylmercaptobenzimidazole							1.000	0.56%		1.000	0.55%							
NOCHEK 4709A, Blended Waxes	Paraffin Wax	3	1.61%		3	1.63%													
Cumar P-25 DLD (KD-109)	Coumarone Indene Resin													10.000	5.51%	10.000	5.57%		
TMTD	Tetramethyl thiuram disulfide							4.000	2.23%		4.000	2.19%		0.300	0.17%	0.300	0.17%		
TBBS	N-tertiary butyl-2- benzothiazole sulfenamide	2	1.07%		2	1.08%													
MBTS	Benzothiazyl disulfide													1.500	0.83%	1.500	0.84%		
Sulphur	Sulphur	2.1	1.13%		2.1	1.14%		2.000	1.11%		2.000	1.10%		0.750	0.41%	0.750	0.42%		
Total		186.60	100.00%		184.60	100.00%		179.50	100.00%		182.50	100.00%		181.55	100.00%	179.55	100.00%		

Table 5. Tests made on Composition 1

Compounds		Sheet 1-Composition-A (NBR 100, Reference)	Sheet 2-Composition-1 (NBR 100, CNT, kevlar)	Sheet 3-Composition-B (HNBR 100, Reference)	Sheet 4-Composition-2 (HNBR 100, CNT, kevlar)	Sheet 5-Composition-C (XNBR 100, Reference)	Sheet 6-Composition-3 (XNBR 100, CNT, kevlar)
Tests							
Specific Gravity	(g/mL)	1.165	1.164	1.177	1.170	1.155	1.147
Hardness	(shore A)	61	66	62	72	68	71
Tensile	(psi)	1749	1863	3599	3018	1781	1959
Elongation	(%)	321	302	452	436	423	428
Modulus 50%	(psi)	108	496	209	592	244	465
Modulus 100%	(psi)	398	823	333	846	377	706
Modulus 300%	(psi)	1696	1849	1420	1731	1173	1303
Tear	(lbs, die C)	185	200	188	239	177	204
MDR 191 C	ML	0.32	0.65	0.1	0.36	0.69	0.93
	t10	0.72	0.71	0.86	0.8	0.57	0.55
	t95	1.85	1.86	3.31	3.33	3.15	3.12
	MH	12.46	14.72	11.74	13.77	5.04	5.78
Viscosity ML 145 C	Mooney	12	18	7	12	18	24
Scorch T-5 145C	minutes	6.28	6.75	5.87	5.18	5.53	5.61
DIN Abrasion	(mm3)	115	114	162	163	122	130
Heat Aging (70h/100 C)	Hardness difference	6	6	7	5	10	9
	Tensile difference (%)	8.3	-8.1	-26.8	-19.5	48.6	29.7
	Elongation difference (%)	-14.6	-28.5	-37.2	-46.3	-15.1	-19.4
Fluid Immersion (IRM 903, 70h/100C)	Hardness difference	2	0	3	2	4	1
	Tensile difference (%)	-22.6	-37.9	-55.3	-43	2.5	-2.3
	Elongation difference (%)	-43	-58.6	-45.1	-52.5	-32.4	-32.5
	Volume difference (%)	1.4	3.8	-1.1	-0.7	6.4	6.6
	Weight difference (%)	-0.1	2.1	-2.2	-1.8	4.1	4.4

[00185] The comparison of Compositions A to C with the Compositions 1 to 3, their counterparts with the same ingredients plus PRO 7000 and Kevlar Fiber, show interesting behaviour of the materials. The fact of adding MWCNT and aramid fibers exhibit a significant increase in the hardness and modulus when performing the stress-strain test without losing much elongation and tensile strength. The integration of these results thus show that the material with these additives are stronger and tougher. Moreover, the other physical and dynamic properties are not negatively affected by the additives. The DIN abrasion resistances are unchanged as well as heat resistance and immersion-swell resistance properties. This was unexpected since, usually, increasing hardness and modulus with conventional means – polymers, fillers and curative chemicals – is known to be detrimental to these properties, especially abrasion resistance. Briefly, applicants have obtained and tested tougher and more rigid materials, but that surprisingly keep the advantages of softer materials with comparable matrix elastomer. This is usually required for the use in demanding oil and gas applications where resistance to wear, heat and pressure are needed, like the powersection stators.

Example 5 – Fuel Immersion Test for Various Rubber Compositions

[00186] Some tests have been made in order to verify the resistance properties of the compositions when submitted to liquids such as fuel. For example, such compositions can be used for making products that are in contacts with fuel. For example, such products can be fuel tank lining. These tests have been made in accordance with Fuel B immersion test according to ASTM D-471.

[00187] Compositions 4, 5 and 6 have been prepared have been prepared by using the same method as previously described for Composition 1. Their ingredients are listed in Table 6 below and the results of such tests are shown in Table 7.

The results of Fuel B immersion test according to ASTM D-471 shown in Table 7 clearly demonstrate that the compositions of the present disclosure can be useful for preparing products that are resistant to fuel. In the present case, the Fuel B was a mixture of isooctane (70 %) and toluene (30

Table 6. Ingredients of Various Comparative Compositions

Trade Name	Chemical Formula	Composition-4 (NBR 100,, CNT, kevlar, military fuel tank lining)		Composition-5 (NBR 100,, CNT, kevlar, military fuel tank lining)		Composition-6 (NBR 100,, CNT, kevlar, military fuel tank lining)	
		phr	% w/w	phr	% w/w	phr	% w/w
Kosyn KNB-35LL	Acrylonitrile-Butadiene-Polymer (NBR)	96.65	41.80%				
Paracril CJLT	Acrylonitrile-Butadiene-Polymer (NBR)			96.63	50.26%		
Krynac 4975	Acrylonitrile-Butadiene-Polymer (NBR)					96.640	43.52%
SBR 1502	Styrene-Butadiene Rubber	19.94	8.62%				
MERGE 1F770	KEVLAR Engineered Elastomer (in NBR)	4.35	1.88%	4.37	2.27%	4.37	1.97%
PRO 7000	NC 7000 MWCNT	2	0.86%	2	1.04%	2.02	0.91%
Carbon Black N-550	Carbon Black	80	34.60%	67	34.85%	67.00	30.17%
Mistron Vapor R Compacted	Microcrystalline talc					20.00	9.01%
TP-90B	Hexaoxatricosane					19.00	8.56%
DOA	Diocetyl Adipate	11	4.76%				
DBS	Dibutyl Sebacate			9.2	4.79%		
Stearic Acid	Stearic acid	1	0.43%	1	0.52%	1.00	0.45%
Zinc Oxide	Zinc Oxide	5	2.16%	4.2	2.18%	4.20	1.89%
6PPD	N-cyclohexyl-N'-phenyl-p-phenylenediamine	2	0.86%	1.7	0.88%	1.70	0.77%
NOCHEK 4709A, Blended Waxe	Paraffin Wax	3	1.30%	2.5	1.30%	2.50	1.13%
Struktol WB-222	Blend of proprietary fatty acids	2	0.86%				
TBBS	N-tertiary butyl-2- benzothiazole sulfenamide	1.9	0.82%	1.6	0.83%	1.60	0.72%
CTP-PVI	Retarding agent	0.4	0.17%	0.35	0.18%	0.35	0.16%
Sulphur	Sulphur	2	0.86%	1.7	0.88%	1.70	0.77%
Total		231.24	100.00%	192.25	100.00%	222.08	100.00%

Table 7. Fuel Immersion Tests made on Compositions 4, 5 and 6

Tests	Sheet 4-Composition 4 (NBR 100, CNT, kevlar)			Sheet 5-Composition-5 (NBR 100, CNT, kevlar)			Sheet 6-Composition-6 (NBR 100, CNT, kevlar)		
Specific Gravity		(g/mL)		1.208	1.221	1.274			
Hardness		(shore A)		78	78	80			
Tensile		(psi)		2088	2701	2268			
Elongation		(%)		379	348	273			
Modulus 100%		(psi)		1173	1328	1395			
Modulus 300%		(psi)		na	2575	na			
Tear		(lbs, die C)		222	266	201			
MDR 191 C		ML		1.54	1.71	2.20			
		t10		0.94	0.77	0.66			
		t95		2.62	2.25	1.62			
		MH		18.06	18.78	16.42			
Viscosity ML 145 C		Mooney		29	43	42			
Scorch T-5 145C		minutes		10.49	6.55	6.87			
Fuel Immersion (Reference Fuel B; 72h/23C)		Hardness difference (%)		-14	-6	0			
		Tensile difference (%)		-37.5	-21.7	-4.9			
		Elongation difference (%)		-39.2	-25.6	4.8			
		Volume difference (%)		33.9	9.0	0.1			
		Weight difference (%)		21.6	5.8	-0.6			

[00188] The results of Fuel B immersion test according to ASTM D-471 shown in Table 7 clearly demonstrate that the compositions of the present disclosure can be useful for preparing products that are resistant to fuel. In the present case, the Fuel B was a mixture of isooctane (70 %) and toluene (30 %). The different acrylonitrile-butadiene polymers used in Compositions 4, 5 and 6 had different concentrations of acrylonitrile. In fact, Kosyn KNB-35LL has an acrylonitrile concentration of about 34 wt %, while Paracril CJLT has an acrylonitrile concentration of about 40 wt %, and Krynac 4975 has an acrylonitrile concentration of about 49 wt %. Without wishing to be bound to such a theory, it seems that, at least within those results, higher quantity of acrylonitrile allowed for better results since the polar nitrile groups are efficient for preventing non-polar solvents from entering into the composition.

[00189] For all these reasons, it was found that the compositions of the present disclosure were very durable in applications related to oil and gas industry and mining industry. Such compositions can thus be useful for manufacturing various rubber products used in such fields as well as in various other fields.

[00190] The Applicant hereby submits that the person skilled in the art would clearly understand that the various embodiments presented in paragraphs [0024] to [00188], when applicable, can be combined in all possible manners and be applied to the compositions recited in paragraphs [0008] to [0020]. The embodiments of paragraphs [0024] to [00188] of the present disclosure are presented in such a manner in the present disclosure so as to demonstrate that every combinations of embodiments, when applicable, can be made. These embodiments have thus been presented in a manner equivalent to making dependent claims for all the embodiments that depend upon any of the preceding claims (covering the previously presented embodiments), thereby demonstrating that they can be combined together.

[00191] While a description was made with particular reference to the specific embodiments, it will be understood that numerous modifications thereto will appear to those skilled in the art. Accordingly, the above description and accompanying drawings should be taken as specific examples and not in a limiting sense.

WHAT IS CLAIMED IS:

1. A rubber composition comprising :

about 40 to about 70 wt. % of an elastomer comprising a rubber selected from the group consisting of hydrogenated acrylonitrile-butadiene, carboxylated acrylonitrile-butadiene and mixtures thereof;

about 0.1 to about 10 wt. % of reinforcing fibers that are aramid fibers;

about 0.1 to about 10 wt. % of nanometric filamentary structures that are carbon nanotubes, said nanometric filamentary structures being functionalized or unfunctionalized; and

about 15 to about 40 wt. % of a filler selected from the group consisting of carbon black, silica and a mixture thereof.
2. The composition of claim 1, wherein in said composition, said elastomer, reinforcing fibers and nanometric filamentary structures and filler are substantially uniformly distributed.
3. The composition of claim 1 or 2, wherein said composition comprises about 45 to about 65 wt. % of said elastomer.
4. The composition of claim 1 or 2, wherein said composition comprises about 50 to about 60 wt. % of said elastomer.
5. The composition of claim 1 or 2, wherein said composition comprises about 50 to about 55 wt. % of said elastomer.
6. The composition of claim 1 or 2, wherein said composition comprises about 52 to about 54 wt. % of said elastomer.
7. The composition of claim 1 or 2, wherein said composition comprises about 45 to about 55 wt. % of said elastomer.

8. The composition of claim 1 or 2, wherein said composition comprises about 55 to about 60 wt. % of said elastomer.
9. The composition of any one of claims 1 to 8, wherein said composition comprises about 0.25 to about 1.75 wt. % of said reinforcing fibers.
10. The composition of any one of claims 1 to 8, wherein said composition comprises about 0.5 to about 1.5 wt. % of said reinforcing fibers.
11. The composition of any one of claims 1 to 9, wherein said composition comprises about 0.75 to about 1.25 wt. % of said reinforcing fibers.
12. The composition of any one of claims 1 to 11, wherein said composition comprises about 0.25 to about 1.75 wt. % of said nanometric filamentary structures.
13. The composition of any one of claims 1 to 11, wherein said composition comprises about 0.5 to about 1.5 wt. % of said nanometric filamentary structures.
14. The composition of any one of claims 1 to 11, wherein said composition comprises about 0.75 to about 1.25 wt. % of said nanometric filamentary structures.
15. The composition of any one of claims 1 to 8, wherein said composition comprises about 0.5 to about 10 wt. % of said reinforcing fibers and nanometric filamentary structures.
16. The composition of any one of claims 1 to 8, wherein said composition comprises about 1 to about 5 wt. % of said reinforcing fibers and nanometric filamentary structures.

17. The composition of any one of claims 1 to 8, wherein said composition comprises about 1 to about 3 wt. % of said reinforcing fibers and nanometric filamentary structures.
18. The composition of any one of claims 1 to 17, wherein said composition comprises about 20 to about 35 wt. % of said filler.
19. The composition of any one of claims 1 to 17, wherein said composition comprises about 25 to about 32 wt. % of said filler.
20. The composition of any one of claims 1 to 17, wherein said composition comprises about 20 to about 25 wt. % of said filler.
21. A rubber composition comprising :
 - an elastomer comprising a rubber selected from the group consisting of hydrogenated acrylonitrile-butadiene, carboxylated acrylonitrile-butadiene and mixtures thereof;
 - reinforcing fibers that are aramid fibers;
 - nanometric filamentary structures that are carbon nanotubes, said nanometric filamentary structures being functionalized or unfunctionalized; and
 - a filler selected from the group consisting of carbon black, silica, and a mixture thereof,wherein said rubber composition is a cured rubber composition having an elongation % of about 302 to about 650, measured according to ASTM D-412 standard; and a 100 % modulus of about 300 to about 1500 psi, measured according to ASTM D-412 standard.

22. A rubber composition comprising :

an elastomer comprising a rubber selected from the group consisting of hydrogenated acrylonitrile-butadiene, carboxylated acrylonitrile-butadiene and mixtures thereof;

reinforcing fibers that are aramid fibers;

nanometric filamentary structures that are carbon nanotubes, said nanometric filamentary structures being functionalized or unfunctionalized; and

a filler selected from carbon black, silica, and a mixture thereof,

wherein said rubber composition is a cured rubber composition having a 100 % modulus of about 300 to about 1500 psi, measured according to ASTM D-412 standard, and a 300 % modulus of about 1303 to about 3000 psi, measured according to ASTM D-412 standard .

23. The composition of any one of claims 1 to 22, wherein said elastomer comprises carboxylated acrylonitrile-butadiene.

24. The composition of any one of claims 1 to 22, wherein said elastomer comprises hydrogenated acrylonitrile-butadiene.

25. The composition of any one of claims 1 to 24, wherein said carbon nanotubes are multi-wall carbon nanotubes.

26. The composition of any one of claims 1 to 24, wherein said carbon nanotubes are single-wall carbon nanotubes.

27. The composition of any one of claims 1 to 26, further comprising a cross-linking agent.

28. The composition of claim 27, wherein said cross-linking agent is sulphur.

29. The composition of any one of claims 1 to 26, further comprising a cross-linking agent selected from the group consisting of sulphur, metal oxides and peroxides.
30. The composition of any one of claims 27 to 29, wherein said composition comprises about 0.5 to about 3.0 % of said cross-linking agent.
31. The composition of any one of claims 27 to 29, wherein said composition comprises about 0.5 to about 2.0 % of said cross-linking agent.
32. The composition of any one of claims 1 to 31, further comprising a plastifier.
33. The composition of claim 32, wherein said plastifier is high aromatic oil, naphtenic oil, parrafinic oil, phtalates, adipates, sebacates or mixtures thereof.
34. The composition of claim 32 or 33, wherein said composition comprises about 1 to about 3 % of said plastifier.
35. The composition of claim 32 or 33, wherein said composition comprises about 1.5 to about 2.5 % of said plastifier.
36. The composition of claim 32 or 33, wherein said composition comprises about 1 to about 20 % of said plastifier.
37. The composition of claim 32 or 33, wherein said composition comprises about 2 to about 15 % of said plastifier.
38. The composition of any one of claims 1 to 37, further comprising a an anti-aging agent.
39. the composition of claim 38, wherein said anti-aging agent is 1,2-dihydro-2,2,4-trimethylquinoline, n-cyclohexyl-n'-phenyl-p-phenylenediamine, zincmethylmercaptobenzimidazole, n-isopropyl-n'-

phenyl-p-phenylenediamine, wingstay 100, n, n'-bis-(1-ethyl-3-methyl phenyl)-p-phenylenediamine, n-(1, 3-dimethylbutyl)-n'-phenyl-p-phenylenediamine, octylated diphenylamine, n, n'-diphenyl-p-phenylenediamine, BLETM 75, 4,4'-Bis-(a,a'-dimethylbenzyl) diphenylamine or mixtures thereof.

40. The composition of claim 38 or 39, wherein said composition comprises about 1.0 to about 3.0 % of said anti-aging agent.
41. The composition of claim 38 or 39, wherein said composition comprises about 1.5 to about 2.5 % of said anti-aging agent.
42. The composition of any one of claims 1 to 41, further comprising a fluidizing agent.
43. The composition of claim 42, wherein said fluidizing agent is a hydrocarbon resin a phenolic resin, zinc soap salts, or mixtures thereof.
44. The composition of claim 42 or 43, wherein said composition comprises about 0.5 to about 3.0 % of said fluidizing agent.
45. The composition of claim 42 or 43, wherein said composition comprises about 1.0 to about 2.5 % of said fluidizing agent.
46. The composition of any one of claims 1 to 45, further comprising a rubber vulcanization accelerator agent.
47. The composition of claim 46, wherein said rubber vulcanization accelerator agent is selected from the group consisting of diphenylguanidine, N-tertiary butyl-2-benzothiazolesulfenamide, N-t-butyl-2-benzothiazolesulfenimide, benzothiazyl-2-dicyclohexyl sulfonamide, 2-(Morpholinothio) benzothiazole sulfenamide, N-Cyclohexyl-2-benzothiazolesulfenamide, N,N-dicyclohexyl-2-benzothiazolesulfenamide, 2-mercaptobenzothiazole, Dibenzothiazole disulfide, Diphenylguanidine, ethylene thiourea, 4,4

dithiodimorpholine, Tetramethylthiuram monosulfide, Tetramethylthiuram disulfide, and mixtures thereof.

48. The composition of claim 46 or 47, wherein said composition comprises about 0.5 to about 1.5 % of said vulcanization accelerator agent.
49. The composition of any one of claims 1 to 48, further comprising a retarding agent.
50. The composition of claim 49, wherein said retarding agent is selected from the group consisting of N-(cyclohexylthio)phthalimide, retarder SAX, retarder ESEN, benzoic acid, and mixtures thereof.
51. The composition of claim 49 or 50, wherein said composition comprises about 0.1 to about 1.0 % of said retarding agent.
52. The composition of any one of claims 1 to 51, further comprising a hardening agent.
53. The composition of claim 52, wherein said hardening agent is selected from the group consisting of phenolic resin, hexamethylnetetramine, hexamethoxymethyl/n-butyl-melamine formaldehyde resin, and mixtures thereof.
54. The composition of claim 52 or 53, wherein said composition comprises about 0.5 to about 2.5 % of said hardening agent.
55. The composition of claim 52 or 53, wherein said composition comprises about 1.0 to about 2.0 % of said hardening agent.
56. The composition of any one of claims 1 to 55, further comprising a reticulation agent.
57. The composition of claim 56, wherein said reticulation agent is selected from the group consisting of stearic acid, zinc oxide and a mixture thereof.

58. The composition of any one of claims 1 to 20, wherein said composition is an uncured rubber composition.
59. The composition of any one of claims 1 to 20, wherein said composition is an uncured rubber composition having a Mooney viscosity ML 145°C of about 40 to about 100, measured according to ASTM D-1646 standard.
60. The composition of any one of claims 1 to 20, wherein said composition is an uncured rubber composition having a Mooney viscosity ML 145°C of about 50 to about 100, measured according to ASTM D-1646 standard.
61. The composition of any one of claims 1 to 20, wherein said composition is an uncured rubber composition having a Mooney viscosity ML 145°C of about 50 to about 80, measured according to ASTM D-1646 standard.
62. The composition of any one of claims 1 to 20, wherein said composition is an uncured rubber composition having a Mooney viscosity ML 145°C of about 60 to about 80, measured according to ASTM D-1646 standard.
63. The composition of any one of claims 1 to 20, wherein said composition is an uncured rubber composition having a Mooney Scorch time t₅ 145°C of about 3 to about 10 minutes, measured according to ASTM D-1646 standard.
64. The composition of any one of claims 1 to 20, wherein said composition is an uncured rubber composition having a Mooney Scorch time t₅ 145°C of about 4 to about 8 minutes, measured according to ASTM D-1646 standard.
65. The composition of any one of claims 1 to 20, wherein said composition is an uncured rubber composition having a Mooney

Scorch time t₅ 145°C of about 4 to about 6 minutes, measured according to ASTM D-1646 standard.

66. The composition of any one of claims 1 to 20, wherein said composition is an uncured rubber composition having a Mooney Scorch time t₅ 145°C of about 4 to about 5 minutes, measured according to ASTM D-1646 standard.
67. The composition of any one of claims 1 to 20, wherein said composition is an uncured rubber composition having a specific gravity of about 1.0 to about 1.5 g/mL, measured according to ASTM D-297 standard.
68. The composition of any one of claims 1 to 20, wherein said composition is an uncured rubber composition having a specific gravity of about 1.1 to about 1.2 g/mL, measured according to ASTM D-297 standard.
69. The composition of any one of claims 1 to 20, wherein said composition is an uncured rubber composition having a specific gravity of about 1.10 to about 1.15 g/mL, measured according to ASTM D-297 standard.
70. The composition of any one of claims 1 to 20, wherein said rubber composition is a cured rubber composition.
71. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having an elongation % of about 400 to about 650, measured according to ASTM D-412 standard.
72. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having an elongation % of about 450 to about 600, measured according to ASTM D-412 standard.

73. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having an elongation % of about 500 to about 575, measured according to ASTM D-412 standard.
74. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having an elongation % of about 510 to about 560, measured according to ASTM D-412 standard.
75. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having an elongation % of about 520 to about 550, measured according to ASTM D-412 standard.
76. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having a 25 % modulus of about 100 to about 500 psi, measured according to ASTM D-412 standard.
77. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having a 25 % modulus of about 150 to about 450 psi, measured according to ASTM D-412 standard.
78. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having a 25 % modulus of about 150 to about 300 psi, measured according to ASTM D-412 standard.
79. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having a 25 % modulus of about 200 to about 300 psi, measured according to ASTM D-412 standard.

80. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having a 25 % modulus of about 225 to about 275 psi, measured according to ASTM D-412 standard.
81. The composition of any one of claims 1 to 20, wherein said rubber composition is a cured rubber composition having a 100 % modulus of about 300 to about 1500 psi, measured according to ASTM D-412 standard.
82. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having a 100 % modulus of about 400 to about 900 psi, measured according to ASTM D-412 standard.
83. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having a 100 % modulus of about 500 to about 900 psi, measured according to ASTM D-412 standard.
84. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having a 100 % modulus of about 700 to about 900 psi, measured according to ASTM D-412 standard.
85. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having a 100 % modulus of about 700 to about 850 psi, measured according to ASTM D-412 standard.
86. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having a 300 % modulus of about 1500 to about 3000 psi, measured according to ASTM D-412 standard.

87. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having a 300 % modulus of about 2000 to about 2800 psi, measured according to ASTM D-412 standard.
88. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having a 300 % modulus of about 2100 to about 2700 psi, measured according to ASTM D-412 standard.
89. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having a 300 % modulus of about 2200 to about 2650 psi, measured according to ASTM D-412 standard.
90. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition having a 300 % modulus of about 2200 to about 2400 psi, measured according to ASTM D-412 standard.
91. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, substantially maintains its elongation properties measured according to ASTM D-412 standard.
92. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, has an elongation % of about -25 % to about 25 %, measured according to ASTM D-412 standard, as compared to the a sample measured before fluid immersion.
93. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said

composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, has an elongation % of about -10 % to about 10 %, measured according to ASTM D-412 standard, as compared to the a sample measured before fluid immersion.

94. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, has an elongation % of about -5 % to about 5 %, measured according to ASTM D-412 standard, as compared to the a sample measured before fluid immersion.
95. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, substantially maintains its weight.
96. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, has a weight variation % of about -10 % to about 10 %, as compared to a sample measured before fluid immersion.
97. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, has a weight variation % of about -5 % to about 5 %, as compared to a sample measured before fluid immersion.
98. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to

ASTM D-471 standard, has a positive weight variation % of less than about 10 %, as compared to a sample measured before fluid immersion.

99. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, has a positive weight variation % of less than about 5 %, as compared to a sample measured before fluid immersion.
100. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, substantially maintains its hardness properties measured according to ASTM D-2240 standard.
101. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, has a hardness variation % of about -15 % to about 15 %, as compared to a sample measured before fluid immersion.
102. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, has a hardness variation % of about -15 % to about 5 %, as compared to a sample measured before fluid immersion.
103. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to

ASTM D-471 standard, has a hardness variation % of about -10 % to about 5 %, as compared to a sample measured before fluid immersion.

104. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, has a hardness variation % of about -5 % to about 0 %, as compared to a sample measured before fluid immersion.
105. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, substantially maintains its tensile strength properties measured according to ASTM D-412 standard.
106. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, has a tensile strength variation % of about -25 % to about 0 %, as compared to a sample measured before fluid immersion.
107. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, has a tensile strength variation % of about -15 % to about 0 %, as compared to a sample measured before fluid immersion.
108. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to

ASTM D-471 standard, has a tensile strength variation % of about -10 % to about 0 %, as compared to a sample measured before fluid immersion.

109. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition, when submitted to a fuel B immersion test according to ASTM D-471 standard, has a tensile strength variation % of about -5 % to about 0 %, as compared to a sample measured before fluid immersion.
110. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition has a hardness (shore A) of about 50 to about 100, measured according to ASTM D-2240 standard.
111. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition has a hardness (shore A) of about 55 to about 95, measured according to ASTM D-2240 standard.
112. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition has a hardness (shore A) of about 60 to about 85, measured according to ASTM D-2240 standard.
113. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition has a hardness (shore A) of about 65 to about 85, measured according to ASTM D-2240 standard.
114. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition has a hardness (shore A) of about 60 to about 75, measured according to ASTM D-2240 standard.

115. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition has a hardness (shore A) of about 65 to about 70, measured according to ASTM D-2240 standard.
116. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition has a hardness (shore A) of about 66 to about 72, measured according to ASTM D-2240 standard.
117. The composition of any one of claims 1 to 57, wherein said rubber composition is a cured rubber composition and wherein said composition has a hardness (shore A) of about 75 to about 80, measured according to ASTM D-2240 standard.
118. The composition of any one of claims 1 to 117, wherein the elastomer comprises about 25 to about 60 wt.% of acrylonitrile.
119. The composition of any one of claims 1 to 117, wherein the elastomer comprises about 30 to about 55 wt.% of acrylonitrile.
120. The composition of any one of claims 1 to 117, wherein the elastomer comprises about 45 to about 55 wt.% of acrylonitrile.
121. The composition of any one of claims 1 to 117, wherein the elastomer comprises about 40 to about 60 wt.% of acrylonitrile.
122. The composition of any one of claims 1 to 117, wherein the elastomer comprises about 45 to about 55 wt.% of acrylonitrile.
123. The composition of any one of claims 1 to 117, wherein the elastomer comprises about 40 to about 50 wt.% of acrylonitrile.
124. The composition of any one of claims 1 to 117, wherein the elastomer comprises about 46 to about 52 wt.% of acrylonitrile.

125. The composition of any one of claims 1 to 124, wherein the composition further comprises talc.
126. The composition of any one of claims 1 to 124, wherein the composition further comprises microcrystalline talc.
127. The composition of claim 125 or 126, wherein said talc is present at a concentration of about 1 to about 20 wt. %.
128. The composition of claim 125 or 126, wherein said talc is present at a concentration of about 2 to about 15 wt. %.
129. The composition of claim 125 or 126, wherein said talc is present at a concentration of about 5 to about 15 wt. %.
130. The composition of claim 125 or 126, wherein said talc is present at a concentration of about 6 to about 12 wt. %.
131. The composition of any one of claims 1 to 130, wherein the composition further comprises a clay.
132. The composition of any one of claims 1 to 130, wherein the composition further comprises a nanoclay.
133. The composition of claim 131 or 132, wherein said clay is present at a concentration of about 1 to about 20 wt. %.
134. The composition of claim 131 or 132, wherein said clay is present at a concentration of about 2 to about 15 wt. %.
135. The composition of claim 131 or 132, wherein said clay is present at a concentration of about 5 to about 15 wt. %.
136. The composition of claim 131 or 132, wherein said clay is present at a concentration of about 6 to about 12 wt. %.

137. A method of manufacturing a composition as defined in any one of claims 27 to 31 comprising;

mixing together said elastomer, said reinforcing fibers and nanometric filamentary structures to obtain a first mixture;

mixing together said first mixture with said filler so as to obtain a second mixture; and

mixing together said second mixture with said crosslinking agent.

138. A method of manufacturing a composition as defined in any one of claims 1 to 26 comprising;

mixing together said elastomer, said reinforcing fibers and nanometric filamentary structures to obtain a first mixture;

mixing together said first mixture with said filler and optionally an anti-aging agent so as to obtain a second mixture; and

mixing together said second mixture with a crosslinking agent, optionally a hardening agent, and optionally a vulcanization accelerator agent.

139. An article comprising a rubber composition as defined in any one of claims 1 to 136.

140. The article of claim 139, wherein said article is a rubber band, a rubber strip or a rubber sheet.

141. The article of claim 139, wherein said article is a track for use on a vehicle.

142. The article of claim 139, wherein said article is a snowmobile track.

143. The article of claim 139, wherein said article is a tractor track.

- 144. The article of claim 139, wherein said article is a tank track.
- 145. The article of claim 139, wherein said article is a tire.
- 146. A method for manufacturing an article comprising rubber, wherein said method comprises moulding, extruding and/or calendaring a rubber composition as defined in any one of claims 1 to 136.
- 147. The method of claim 146, wherein said article is a rubber band, a rubber strip, a rubber lug, a rubber belt or a rubber sheet.
- 148. The method of claim 146, wherein said article is a track for use on a vehicle.
- 149. The method of claim 146, wherein said article is a tire.
- 150. The method of claim 146, wherein said article is a tank lining.
- 151. The method of claim 146, wherein said article is a hose.
- 152. The method of claim 146, wherein said article is a gasket.
- 153. The method of claim 146, wherein said article is transmission belt.
- 154. The method of claim 146, wherein said article is conveyor belt.
- 155. The method of claim 146, wherein said article a part of a pumping system.
- 156. The method of claim 146, wherein said article is a powersection stator.
- 157. The method of any one of claims 146 to 156, wherein said method comprises calendaring and/or extruding said rubber composition so as to obtain a rubber band, a rubber strip, a rubber log or a rubber sheet; and moulding and vulcanizing said a rubber band, a rubber strip, a rubber lug or a rubber sheet so as to obtain said article.

158. The method of any one of claims 146 to 156, wherein said method comprises calendering and/or extruding said rubber composition so as to obtain is a rubber band, a rubber strip, a rubber log or a rubber sheet; and moulding and vulcanizing a plurality of rubber bands, rubber strips, rubber lugs or rubber sheets so as to obtain said article.
159. The method of claim 157 or 158, wherein said moulding is carried out by compression moulding.